PROCEEDINGS

ESB 2026



35th Annual Conference

of the European Society for Biomaterials

7 - 11 September 2026 • Antwerp, Belgium

ESB 2026

35th Annual Conference of the European Society for Biomaterials

7 - 11 September 2026
Antwerp, Belgium

Posters

D1 - P001
Data-Driven tensile strength prediction of biodegradable zinc alloys

Kansal A., Kumar S., Chaddha H., Sharma A., Kumar A., Angra S.
Dept. of Mechanical Engineering, Punjab Engineering College, Chandigarh, India

Introduction

Biodegradable zinc-based alloys are emerging as promising materials for temporary medical implants, such as bone screws and vascular stents, due to their moderate corrosion rates and biocompatibility[1]. However, achieving high tensile strength while maintaining controlled degradation remains a critical challenge. This study presents a materials informatics framework to optimise zinc alloy compositions, with emphasis on predicting Ultimate Tensile Strength (UTS)[2,3].

Materials and Methods

A curated dataset was compiled from a large number of peer-reviewed studies on biodegradable zinc alloys, including alloy composition, fabrication route, mechanical properties, and corrosion rate. Exploratory data analysis was performed to examine feature distributions and correlations, followed by feature selection. The dataset was split into 80% for training and 20% for testing, with ten-fold cross-validation to ensure robustness. Multiple regression models, including Decision Tree, Random Forest, Gradient Boosting and XGBoost were evaluated for UTS prediction.

Results

Figure 1 presents the correlation heatmap illustrating the relationships between alloy composition, processing parameters, and Ultimate Tensile Strength (UTS), which guided feature selection.Figure 2(a) compares the R^2 values of the evaluated models. Random Forest and Gradient Boosting achieved the highest predictive accuracy ($R^2 \approx 0.92$), followed by XGBoost ($R^2 \approx 0.90$), while Decision Tree showed comparatively lower performance ($R^2 \approx 0.88$).Figure 2(b) shows the MAE comparison. Gradient Boosting yielded the lowest prediction error (MAE ≈ 20.5), outperforming Random Forest (≈ 22.5), Decision Tree (≈ 22–23), and XGBoost (≈ 26).
Overall, Gradient Boosting demonstrated the most balanced and reliable performance for tensile strength prediction.

Conclusion

The integration of machine learning and multi-objective optimization provides an effective framework for designing high-strength biodegradable zinc alloys. Among the evaluated models, Gradient Boosting demonstrated the most reliable predictive performance, achieving high accuracy ($R^2 \approx 0.92$) with the lowest prediction error (MAE ≈ 20.5). This enables efficient screening of alloy compositions prior to experimental validation. The multi-objective optimization approach further identified compositions that balance tensile strength and corrosion performance. Overall, this data-driven strategy reduces experimental effort and accelerates the development of mechanically reliable biodegradable implant materials.




Figure 1. Correlation heatmap of input features




Figure 2. (a) R^2 comparison of ML models; (b) MAE comparison of ML models

References

[1]Rao J., Gao H., Sun J., Yu R., Zhao D., Ding Y. A Critical Review of Biodegradable Zinc Alloys toward Clinical Applications. 2024. https://doi.org/10.1021/acsbiomaterials.4c00210.

[2]Davletshin A., Zhurkevich A., Lara R., Korznikova E.A., Kistanov A.A. Design of optimized composition of biodegradable Zn-based alloys using multi-objective predictions, *J. Alloys Compd* 2025; 1041; 183881. https://doi.org/10.1016/j.jallcom.2025.183881.

[3]Pan C., Lin W., Zhou J., Jian W., Chan K.C., Chan Y.L., Ren L. Novel machine learning driven design strategy for high strength Zn Alloys optimization with multiple constraints. 2025. https://doi.org/10.1038/s41524-025-01666-7.

D1 - P002
SpinCastML an open distribution-aware inverse design application for electrospun biomaterials

Roldan E.
Dept. of Engineering, Manchester Metropolitan University, Manchester, UK

Introduction

Electrospinning is widely used in biomaterials research to fabricate micro- and nanoscale fibrous scaffolds for tissue engineering, drug delivery, wound healing and regenerative medicine. However, rational design of electrospun biomaterials remains challenging due to the strongly coupled effects of polymer chemistry, solvent systems and processing conditions. Small variations can shift electrohydrodynamic regimes and produce distinct, fiber-diameter distributions that directly influence cell response, mechanical performance and mass transport. Because biological function depends not only on mean diameter but on distribution shape and variability, electrospinning must be addressed as a distributional and chemically constrained design problem.

Aim

This work introduces SpinCastML, an open, distribution-aware inverse-design framework tailored to accelerate biomaterial scaffold development.

Materials and Methods

SpinCastML was developed using a curated dataset of 68,480 individual fiber-diameter measurements extracted from 1,778 datasets spanning 16 polymers commonly used in biomedical applications. To address high-dimensional heterogeneity and material imbalance, the framework integrates polymer-balanced Sobol and D-optimal sampling with systematic benchmarking of eleven machine-learning algorithms.
Unlike conventional scalar prediction approaches, SpinCastML models complete fiber-diameter distributions. The selected global predictive model is embedded within a chemistry-aware Inverse Monte Carlo (IMC) engine that enforces polymer–solvent compatibility and solvent miscibility constraints. The IMC module supports both retrospective validation and forward inverse design toward user-defined diameter targets and tolerances relevant to specific biomaterial functions.
Figure 1 illustrates the workflow; Figure 2 shows predicted versus observed performance for the selected model.

Results

A Cubist model trained under polymer-balanced Sobol+D-optimal sampling achieved robust global predictive performance ($R^2 > 0.92$) with stable generalization across chemically diverse polymer systems. The framework accurately reconstructed experimental fiber-diameter distributions ($R^2 > 0.90$ for major polymers). Across seven independent systems, predicted success probabilities differed from experimental success rates by less than 1% absolute error.
Rather than prescribing a single optimal recipe, the IMC engine generated families of chemically feasible polymer–solvent–process configurations with quantified probabilities of meeting target diameter ranges, enabling assessment of scaffold robustness and manufacturability.

Conclusion

SpinCastML advances electrospinning for biomaterials from empirical parameter tuning toward reproducible, data-driven inverse design. By integrating distribution-level modeling, chemical feasibility constraints and probabilistic simulation within an open executable platform, the framework accelerates scaffold optimization, reduces experimental waste and supports application-driven design of electrospun biomaterials. This approach establishes distribution-aware inverse design as a powerful tool for next-generation regenerative and functional biomaterials manufacturing.

D1 - P003

Artificial Intelligence-driven explainable machine learning framework for processing-property prediction of ultra-high molecular weight polyethylene: SHAP-based interpretability and bootstrap uncertainty quantification for intelligent biomaterial design & manufacturing

Sriprakash P.[1,2], Basu B.[1,2*]
[1]Laboratory for Biomaterials Science and Translational Research, Materials Research Centre, Indian Institute of Science, Bangalore, India; [2]Centre of Excellence for Dental and Orthopedic Applications, Material Research Centre, Indian Institute of Science, Bangalore, India

Introduction

Ultra-high molecular weight polyethylene (UHMWPE) is widely regarded as the gold-standard polymer biomaterial for load-bearing orthopaedic applications such as total hip and knee replacements. Its exceptional wear resistance, high toughness, excellent biocompatibility, and long-term mechanical stability make it highly suitable for implants subjected to repetitive mechanical loading. However, the mechanical performance of injection-molded UHMWPE components including ultimate tensile strength (UTS), Young's modulus, and strain at break strongly influenced by processing conditions during manufacturing. Parameters such as melt temperature, mold temperature, injection pressure, holding time, cooling time, and heating time affect polymer chain orientation, crystallinity, and residual stress development within the material.

Due to the extremely high molecular weight of UHMWPE (5×10^6 g/mol), the relationship between processing parameters and resulting mechanical properties becomes highly nonlinear and complex. Traditional empirical models often struggle to capture these interactions accurately. Additionally, performing extensive injection-molding experiments across all parameter combinations is both time-consuming and resource-intensive. Therefore, data-driven modelling approaches are increasingly needed to predict mechanical properties from processing conditions while maintaining physical interpretability.

Aim

This study aims to develop an explainable artificial intelligence (AI)based machine learning framework to predict the mechanical properties of injection-molded UHMWPE. The framework integrates ensemble learning algorithms with SHAP-based interpretability and bootstrap uncertainty analysis to provide accurate and transparent predictions for intelligent biomaterial processing.

Materials and Methods

Medical-grade UHMWPE (GUR 1050, Celanese Ticona, USA; molecular weight 5×10^6 g/mol) was processed using an Xplore micro-injection molding machine. A dataset of 150 samples was generated by varying six processing parameters: melt temperature (180–300 °C), mold temperature (20–80 °C), injection pressure (10–16 bar), holding time (10–20 s), cooling time (60–300 s), and heating time (240–720 s). Tensile specimens were prepared according to ASTM D638 and tested using an Instron 5967 universal testing machine at a crosshead speed of 50 mm/min. Ten supervised regression algorithms including Extra Trees, Random Forest, Gradient Boosting, AdaBoost, and Decision Tree models were evaluated. The dataset was split into training and testing sets (70:30) with five-fold cross-validation. Model interpretability was analysed using SHAP along with permutation and mean decrease impurity importance measures. Bootstrap resampling (80 iterations) was applied to estimate prediction uncertainty.

Results

The Extra Trees model showed the best performance for UTS prediction ($R^2 = 0.983$, rRMSE = 1.83%), while Random Forest achieved the highest accuracy for Young's modulus ($R^2 = 0.923$) and strain at break ($R^2 = 0.948$), satisfying the defined acceptance criteria ($R^2 \geq 0.85$, overfitting ≤ 5%). Bootstrap analysis produced narrow 95% confidence intervals (rRMSE ≈1–2%), confirming strong model stability. SHAP analysis identified melt temperature as the dominant processing parameter (>70% feature importance), followed by mold temperature and injection pressure. Cooling time exhibited a nonlinear effect, improving strength and stiffness at moderate values but reducing ductility at longer durations due to competing crystallization and residual stress effects.

Conclusion

Overall, the proposed explainable machine learning framework accurately predicts mechanical properties while providing clear insights into processing structure property relationships. This approach enables reliable process optimization and supports data-driven manufacturing of UHMWPE for orthopaedic implant applications..

Figure (a.b.c.d) Explain all work flow and the resulr and uncertinity Analysis in ML




Figure (a) Overview of Machine learning and work flow of injection-moldable UHMWPE biomaterials. Process Parameter Optimization figure (b) give the target and feturse important information figure(c,d) give the learning curve analysis how model generalizes the thing

D1 - P004

Snail mucus-based hydrogel system: A sustainable and bioactive approach for neural regeneration

Akyol Z.[1], Izbudak B.[1], Bal Öztürk A.[1,2,3]
[1]Dept. of Stem Cell and Tissue Engineering, Institute of Graduate Education, Istinye University; [2]Stem Cell and Tissue Engineering Research and Application Center (ISUKOK), Istinye University; [3]Dept. of Analytical Chemistry, Faculty of Pharmacy, Istinye University, Istanbul, Türkiye

Introduction

Spinal cord injuries (SCI) cause severe neurological dysfunction with limited therapeutic recovery. Regenerative medicine has focused on biocompatible hydrogels to enhance neural repair[1]. In this study, bioactive snail mucus from *Achatina fulica*, rich in glycoproteins and enzymes, was integrated into gelatin methacryloyl (GelMA) matrix. Snail mucus is increasingly utilized in biomedicine due to its high concentration of bioactive molecules, including allantoin and antimicrobial peptides. These constituents provide synergistic regenerative, antibacterial, and antioxidant properties. Furthermore, reduced graphene oxide (rGO) was incorporated to recapitulate the electro-active neural microenvironment, providing necessary conductivity for intercellular communication. Using the AdBio Pen for *in situ* 3D bioprinting, the formulated hydrogel was printed with strong potential for anatomical integration and SCI regeneration.

Materials and Methods

Graphene oxide (GO) was reduced to rGO using ascorbic acid as a green agent. Snail secretion filtrate (SSF) was harvested from *Achatina fulica*. The structural and biological properties of SSF were evaluated using FTIR analysis, disk diffusion test, and DPPH and MTT assays. In addition, the effects of SSF on the proliferation and migration of neural stem cells were also investigated. A series of SSF-integrated GelMA/rGO formulations were prepared, and their printability characteristics were optimized using printability and injectability tests. Then, SSF-integrated GelMA/rGO scaffolds were prepared via *in situ* 3D-bioprinter (AdBio Pen, AdBioInk Biosystem Technology) and cross-linked under the device-integrated LED light (405 nm). The potential of the obtained scaffolds for use in neural tissue engineering was investigated through the evaluation of their swelling, degradation, mechanical, conductivity, and antioxidant properties, along with biocompatibility, proliferation, and migration analyses performed.

Results

SSF demonstrated significant antioxidant and antibacterial activity together with favorable biocompatibility. Moreover, SSF enhanced the proliferation and migration of neural stem cells, indicating its bioactive potential for neural applications. SSF-integrated GelMA/rGO formulations exhibited suitable printability and injectability for *in situ* bioprinting. The resulting scaffolds showed desirable swelling, degradation, mechanical, and conductive properties, while maintaining good cytocompatibility. Overall, these findings suggest that SSF-integrated GelMA/rGO scaffolds represent a promising and multifunctional platform for neural tissue engineering.

Conclusion

The developed hydrogel combines high swelling capacity, suitable mechanical strength, antibacterial and antioxidant activity, and the electroactive features, indicating its potential for SCI and broader neural tissue engineering applications.

Acknowledgements

Supported by the Health Institutes of Türkiye (TÜSEB) [Project No: 48539].

References

[1]Zhao X., et al. Functional hydrogels for spinal cord injury repair: From bench to bedside. *Mater. Today* 2023; 69; 105-125.

D1 - P005

Personalization and development of clinical solutions for nasal reconstruction: Digital, surgical, biomechanical, and psychological perspectives

Floret L.[1], Al Tabaa K.[1,2], Houaoui A.[1], Langueh C.[1], Farcy-Pauthe R.[1], Boissiere M.[1], Pauthe E.[1]
[1]Lab ERRMECe, Cy Cergy Paris Université, France; [2]Hopital NOVO, Pontoise, France

Introduction

Total nasal reconstruction represents a complex and multidisciplinary challenge, requiring simultaneous consideration of aesthetic, functional, biomechanical, and psychosocial dimensions. Although autologous reconstruction using the paramedian forehead flap remains the clinical gold standard, it is technically demanding, operator dependent, and lacks standardized protocols. These limitations highlight the need for approaches that improve precision, reproducibility, and personalization.

Materials and Methods

This project integrates digital technologies, including 3D facial modeling, virtual surgical planning, and patient-specific 3D-printed materials to optimize the design and fabrication of cartilage grafts and improve the planning of skin flaps. Virtual reconstruction of nasal subunits with standardized thicknesses enables preoperative definition of structural parameters aimed at enhancing postoperative stability. This workflow also paves the way for future automation through artificial intelligence to reduce inter-operator variability and streamline planning.
In parallel, the project explores replacing autologous costal cartilage with biomaterials capable of reproducing the biomechanical gradient of native nasal cartilage. The focus is on achieving dorsal rigidity for structural support and alar flexibility for optimal nares function. Advanced 3D-printed scaffolds incorporating bone-derived substitutes or purified animal extracellular matrices are evaluated for their ability to generate patient-specific, mechanically tuned cartilage substitutes.

Results

The combination of 3D planning, additive manufacturing, and biomaterial-based scaffolds demonstrates the feasibility of producing personalized nasal subunits with tailored mechanical properties. Preliminary evaluations indicate improved reproducibility in graft geometry and potential for enhanced structural stability compared with traditional freehand carving methods.

Conclusion

The convergence of digital planning, additive manufacturing, biomaterials engineering, and future AI-based automation provides a promising pathway toward personalized, accurate, and biomimetic total nasal reconstruction. This integrated approach has the potential to increase morphological precision, reduce inter-operator variability, and improve long-term functional and aesthetic outcomes.

Acknowledgements

INTEGRANOSE “Nasal Reconstruction” Chair. The funding amount granted by I-SITE CY n°ANR-16-IDEX-0008.

D1 - P006

Rapid dataset generation using large language models in additive manufacturing

Carou-Senra P.[1], Rodríguez-Pombo L.[1], Alvarez-Lorenzo C.[1], Goyanes A.[1,2,3,4]
[1]Dept. de Farmacología, Farmacia y Tecnología Farmacéutica, I+D Farma (GI-1645), Facultad de Farmacia, Instituto de Materiales (iMATUS) and Health Research Institute of Santiago de Compostela (IDIS), Universidade de Santiago de Compostela, Santiago de Compostela, Spain; [2]FABRX Ltd., London, UK; [3]FABRX Artificial Intelligence, Santiago de Compostela, Spain; [4]Dept. of Pharmaceutics, UCL School of Pharmacy, University College London, UK

Introduction

Artificial intelligence (AI) has become a transformative force across scientific disciplines, with Large Language Models (LLMs) attracting attention for their ability to generate, interpret, and reason with natural language. This has driven interest in leveraging LLMs to transform unstructured literature into structured, actionable information. A major bottleneck in many fields is the scarcity of high-quality, domain-specific data, which must be manually curated from heterogeneous literature, where inconsistent reporting, variable terminology, and lack of standardization make the process laborious and difficult to reproduce.

Aim

This study aims to develop and validate a multi-prompt LLM-based framework for structured dataset generation from full-text scientific articles, applied to pharmaceutical inkjet printing.

Materials and Methods

Pharmaceutical inkjet printing articles were selected for the extraction and computation of 22 domain-relevant variables. Automated extraction and calculation were performed using GPT-4, progressing from a single foundational prompt to a structured multi-prompt system. Variables were grouped according to process parameters, rheological properties, or dose parameters, with interactions standardized through a decision-tree framework. Extracted data was compared against a human-curated reference dataset created by four domain experts over four months. Both accuracy and time efficiency were systematically evaluated.

Results

Using the structured multi-prompt framework, GPT-4 overall extraction accuracy reached 94.2% across 4,217 analysed values. Across 195 computations derived from 4 calculated variables, accuracy reached 98.3%, including multi-step calculations and unit conversions. Remarkably, individual prompt responses were generally produced in under 40 seconds while the complete analysis of a single article was consistently completed in under four minutes, reducing process time from hours of manual effort to just a few minutes per article.

Conclusion

This study has demonstrated that the automated creation of structured datasets from heterogenous scientific literature from additive manufacturing can be reliably achieved through a full-text, multi-prompt, decision-guided extraction framework powered by LLMs.

Acknowledgements

PCS acknowledges the Predoctoral [ED481A-2023-168] from Xunta de Galicia co-funded by the EU. LRP acknowledges the predoctoral fellowship [FPU20/01245] provided by the Ministerio de Universidades.
Funding: Spain Ministerio de Ciencia, Innovación y Universidades MICIU/AEI/https://doi.org/10.13039/501100011033 [PID2023-149544OB-C22; PID2023-150422OB-I00], ERDF cofunded by the EU, Xunta de Galicia [ED431C 2024/09].

D1 - P007

Label-free osteoclast detection via biologically informed diffusion models with intrinsic uncertainty quantification

Von Witzleben M.[1], Schmidt K.[2], Wirsig K.[1], Gelinsky M.[1], Czarske J.[2,3], Koukourakis N.[2,3]
[1]Centre for Translational Bone, Joint and Soft Tissue Research, Faculty of Medicine & University Hospital, TU Dresden; [2]Chair of Measurement and Sensor System Technique, TU Dresden; [3]BIOLAS Competence Center, TU Dresden, Dresden, Germany

Introduction

Reliable detection of multinucleated cells is a pressing clinical challenge: in bone pathology, inflammatory disease, and tumour biology, quantifying cell fusion carries direct diagnostic consequence. Fluorescence staining — the gold standard for resolving nuclei and cytoskeletal architecture — requires chemical fixation, precluding live-cell observation. A clinical-translatable virtual staining tool must not only predict accurately but also quantify its own uncertainty — a capability intrinsic to denoising diffusion probabilistic models (DDPM) through their stochastic inference, and unavailable in any deterministic architecture. 2D osteoclast cultures are an ideal model system: as the best-characterised multinucleated cell type, they provide reproducible DAPI and Phalloidin ground truth across a wide range of fusion states.

Aim

We develop a biologically informed conditional DDPM that predict DAPI and Phalloidin signals from brightfield images of dense osteoclast cultures — resolving nuclei and fine actin structures — while providing uncertainty estimates of its own predictions.

Materials and Methods

Paired brightfield, DAPI, and Phalloidin images of 2D osteoclast cultures were used as training data. A conditional DDPM with biologically informed weight initialization was trained end-to-end for 100 epochs, with brightfield tiles as input and the corresponding fluorescence channels as ground truth. Prediction quality was assessed via PSNR and SSIM, complemented by nuclei-level detection metrics. Uncertainty calibration was evaluated using Expected Calibration Error (ECE) and Maximum Calibration Error (MCE), derived from repeated stochastic forward passes to decompose aleatoric (data-inherent) and epistemic (model-knowledge) uncertainty. As a first step towards interpretability, gradient-based attribution methods were applied to identify the brightfield features driving individual staining decisions.

Results

The trained DDPM produced detailed reconstructions of DAPI-labelled nuclei and Phalloidin-stained actin rings. The model yielded well-calibrated uncertainty estimates: aleatoric uncertainty was concentrated at structurally ambiguous regions such as overlapping cell boundaries, while epistemic uncertainty was elevated in underrepresented morphological configurations — both confirmed by ECE and MCE. Preliminary gradient-based attribution analyses revealed spatially coherent activation patterns consistent with biologically meaningful features, offering a first window into the model's staining logic.

Conclusion

Biologically informed DDPM enable reliable virtual fluorescence predictions in label-free osteoclast imaging. Crucially, the decomposition of aleatoric and epistemic uncertainty yields spatially resolved confidence measures unavailable in conventional chemical staining — offering a principled basis for quality-controlled diagnostic interpretation. Preliminary gradient-based attribution further indicates that staining decisions are grounded in morphologically coherent brightfield features, supporting model transparency. Collectively, these properties position DDPMs as a rigorous framework for uncertainty-aware virtual staining, with translational relevance extending to the broader class of multinucleated cell pathologies.

Acknowledgements

This work was funded by the German Space Agency at DLR (grant number 50WB2332).

D1 - P008

Enzyme-enabled polymers for open-environment biodegradation

Jones A.M.[1], Miodownik M.[1], Hailes H.C.[1], Jeffries J.W.E.[1]
[1]Dept. Mechanical Engineering, University College London; [2]Dept. Chemistry, University College London, London, UK

Introduction

Regulating the biodegradability of bio-based polymers offers opportunities to design renewable materials with open-environment degradation and composting as viable end-of-life pathways, particularly for applications where recovery is impractical. Products such as tree guards, agricultural films and temporary exterior infrastructure should retain mechanical integrity during use, whilst degrading in a predictable manner. Achieving this balance remains a central challenge in the design of biodegradable polymer and biomaterial systems intended for environmentally responsive applications.

Materials and Methods

In this study we investigate an enzyme enabled materials design strategy in which plastic-degrading enzymes discovered from the natural environment are incorporated into polylactic acid (PLA). Enzymes were stabilised using several immobilisation methods and nano-dispersed within PLA, to create bio-functional polymer composites. Nanocomposites were prepared and subjected to controlled degradation experiments under both laboratory conditions and across field trials in temperate environmental conditions. Assays were performed in combination with a range of analytical techniques including HPLC and LCMS, to assess degradation efficiency. Scanning electron microscopy (SEM) was used to characterise surface degradation behaviour and compare morphological changes during depolymerisation.

Results

Enzyme-embedded PLA materials exhibited distinct degradation profiles depending on the enzyme incorporated within the polymer matrix. Degradation behaviour was compared with benchmark systems based on Proteinase K, demonstrating that degradation kinetics can be modulated through enzyme selection. SEM analysis revealed surface-localised erosion consistent with enzyme-mediated depolymerisation (Figure 1) rather than uncontrolled fragmentation. Degradation behaviour was also found to depend on processing conditions, showing that certain pre-processing parameters influence the activity of embedded enzymes within the composite biomaterial.

Conclusion

These results demonstrate that environmentally derived enzymes can be incorporated within polyester matrices to tune degradation behaviour while maintaining material integrity during use. Importantly, early field trials conducted in temperate environments provide initial validation of enzyme-enabled biodegradable polymers under real world conditions. Using tree guards as a material case study, the work highlights how combining enzyme discovery, polymer processing and green chemistry principles can support the circular design of environmentally responsive biomaterials compatible with temperate eco-systems.

Acknowledgements

EPSRC, Royal Society of Chemistry, The Woodland Trust




Figure 1
SEM analysis reveals surface-localised erosion consistent with enzyme-mediated depolymerisation (right) compared to control samples (left).

D1 - P009

Investigating the role of surface preparation techniques in the corrosion of magnesium WE43 alloy

McCallion A.*, Brown A., Acheson J., Ward J.
School of Engineering, Ulster University, Belfast, Northern Ireland

Introduction

Magnesium (Mg) has gained popularity as biomaterial for temporary, resorbable implant devices, however, due to its low corrosion resistance, Mg must be improved through bulk and surface modification[1]. Extensive *in vitro* testing has been carried out with Mg, the materials and methods used in these experiments vary from study-to-study resulting in different corrosion rates being reported[2]. Therefore, investigations into the effect of different corrosion study variables will be undertaken, to identify a standardised. This study is focusing on the effect of alternative surface preparation methods on the degradation rate of WE43 Mg alloy.

Materials and Methods

Elektron® 43 Mg coupons (12.7 x 12.7 x 4 mm, Luxfer MEL Technologies) were subject to surface preparation techniques and categorised: as-received (AR) with no further processing post-cutting, polished (P) samples prepared with 800,1200, 2000 and 4000 grit SiC paper and sandblasted (SB) prepared using 60, 100, 140 and 168 psi employing 80 grit mineral abrasive. Samples were immersed in a supplemented McCoy's 5A cell culture medium (10% fetal bovine serum + 1% penicillin/streptomycin) for a period of seven days, due to the accelerated degradation of the SB samples.

Results

Initial investigation into the AR, P1200 and SB168 sample sets show SB168 has a higher corrosion rate (4.61 mmpy) compared to P1200 (0.18 mmpy) and AR (0.21 mmpy) (Figure 1). The P1200 samples had the lowest degradation rate, indicating that a lower surface roughness will improve corrosion resistance.

Conclusion

Increasing the surface roughness can enhance the bioactivity of Mg, through improving cell attachment[3]. Furthermore, successful implementation of sandblasting can streamline sample preparation by reducing processing time and producing a more non-uniform surface profile. However, it is important that a trade-off between surface roughness and corrosion resistance be established due to the increased corrosion rate.




Figure 1- Optical microscopic images (a) AR, (b) P1200, (c) SB168, post-immersion in McCoy's medium. Scale bar 2mm.




Figure 2- Average Corrosion Rate of AR, P and SB samples (mmpy).

References

[1]Pogorielov M., Husak E., et al., Magnesium-based biodegradable alloys: Degradation, application, and alloying elements. *Interv. Med. Appl. Sci.* 2017; vol. 9, no. 1; 27–38.
[2]Yang L., Zhang E. Biocorrosion behavior of magnesium alloy in different simulated fluids for biomedical application. *Mater. Sci. Eng. C* 2009; vol. 29, no. 5; 1691–1696.
[3]Chen J., Dai J., et al. On the role of surface roughness in the corrosion of pure magnesium in vitro. *Materials* 2022; vol. 15, no. 11.

D1 - P010

An integrated in *vitro* – *in* silico framework for 3D-printed pcl bioresorbable implants

De Becker O.[1], Vander Sloten J.[1], Geris L.[1,2,3,4]
[1]Biomechanics Section, Dept. of Mechanical Engineering, KU Leuven, Leuven; [2]Prometheus: Division of Skeletal Tissue Engineering, KU Leuven, Leuven; [3]Biomechanics Research Unit, GIGA in silico Medicine, University of Liège, Liège; [4]Skeletal Biology and Engineering Research Center, KU Leuven, Leuven, Belgium

Introduction

Bioresorbable implants provide temporary mechanical support while gradually degrading and being resorbed by the body, thereby promoting tissue regeneration. Among these materials, bioresorbable polymers such as polycaprolactone (PCL) are particularly attractive for non-load-bearing applications due to their favourable biocompatibility and degradation characteristics. PCL degrades primarily through hydrolytic chain scission, followed by the resorption of its degradation products. However, degradation behaviour of these implants is complex and dependent on the implant geometry, making experimental evaluation of multiple design iterations both costly and time-consuming. Computational models incorporating the underlying bioresorption mechanisms offer a complementary approach, enabling the predictions and comparison of implant performance throughout degradation while reducing reliance on extensive experimental testing. This study aims to develop and evaluate an experimentally informed computational framework for the degradation of 3D-printed PCL implants.

Materials and Methods

An experimentally informed computational framework was developed to support the design of bioresorbable PCL implants. The model combines the degradation framework of Pan and Brassart (2023)[1], describing hydrolytic chain scission and diffusion of degradation products, with the recrystallisation model of Han et al. (2009)[2]. To inform and evaluate the model, an *in vitro* degradation study is conducted in which 3D-printed PCL samples are incubated in phosphate-buffered saline (PBS) at 37°C. Degradation is characterised by measuring mass loss, molecular weight (gel permeation chromatography), crystallinity (differential scanning calorimetry), and tensile properties under wet conditions at 37°C. These measurements are performed prior to incubation and after three, six, twelve, and eighteen months. The experimental dataset will be used to calibrate the model parameters and assess the ability of the computational framework to reproduce the observed degradation behaviour of PCL.

Results

Figure 1 shows the evolution of normalised molecular weight and crystallinity over the first six months of degradation. Experimental variability is indicated by the uncertainty ranges. Model calibration using this dataset is currently ongoing.




Figure 1: Evolution of the normalized molecular weight (blue) and normalized crystallinity (orange) over time. Experimental measurements are shown as symbols with their corresponding uncertainty ranges.

Conclusion

The proposed framework shows strong potential as a predictive tool for the degradation of bioresorbable PCL implants. Preliminary simulations based on literature data demonstrate its capability to capture key degradation mechanisms. Following calibration and validation using the complete experimental dataset, the model could support implant design optimisation while reducing reliance on extensive experimental testing.

Acknowledgements

The authors would like to thank the endowed Materialise chair for image based, patient-specific biomechanics (KU Leuven, Belgium) for providing financial support.

References

[1]Pan Z., Brassart L. A reaction-diffusion framework for hydrolytic degradation of amorphous polymers based on a discrete chain scission model. *Acta Biomaterialia*; 167; 361-373.

[2]Han X., Pan J. A model for simultaneous crystallisation and biodegradation of biodegradable polymers. *Biomaterials*; 30; 423-430.

D1 - P011
3D printed porous organic-inorganic scaffolds for bone defect repair

Fu Q., Loganathan S., Dawkins L., Jha A.
School of Chemical and Process Engineering, University of Leeds, Leeds, UK

Introduction

Due to the limited options for surgical grafts which offer optimized structure and bioactive surfaces, the treatment of critical-sized bone defects remains a significant clinical challenge. Natural bone is a porous organic–inorganic composite, therefore, an optimal bone scaffold should feature an interconnected pore structure and a biomimetic composition to achieve mechanical and biological properties. Three-dimensional printing has gained popularity in the medical field due to its versatility and cost-effectiveness. 3D printing allows for precise control over structures and material compositions, facilitation the development of porous organic-inorganic scaffolds. Coating of these 3D printed structures can further enhance the biological properties through the addition of anti-inflammatory, anti-bacterial and osteoinductive/conductive materials.

Materials and Methods

Fused deposition modelling (FDM) has been used as the fabrication technique to produce Gyroid and tri-hexagon Polylactic acid (PLA) structures. A variety of infill densities have been explored using characterisation techniques to investigate the pore morphology and porosity of the FDM PLA scaffolds. Cerium^{3+} doped Hydroxyapatite (HA) was synthesized using wet chemical synthesis followed by freeze-drying. Using collagen (Col) and cellulose (EC) solutions, the doped HA was coated onto the FDM PLA structures to improve the biological properties, using dip-coating. SEM and EDS were used to analyse the coating morphology, and Cell culture techniques were used to investigate the cytotoxicity of the materials.

Results

SEM images (figure 1a) revealed the gyroid pattern achieved a desirable balance between printability and pore structure at infill density of 30–40%, whereas the tri-hexagon obtained this at 40–50%. Porosity tests (figure 1b) showed that the scaffolds with 30-60% infill density had a porosity of 50% to 77%. This range is suitable for bone implant applications. Scaffolds with tri-hexagon pattern had a larger pore size at higher density. SEM and EDS showed the homogenous distribution of HA on the FDM PLA structures. Cytotoxicity studies (figure 2) revealed that the HA coated PLA structures were non-toxic, with EC-HA coating PLA infill density 40% showing improved cell adhesion and viability compared to other samples.


Conclusion

PLA porous scaffolds was successfully printed. Gyroid structures with 30–40% infill density and tri-hexagon structures with 40–50% infill density provided suitable pore morphology for potential biomedical applications. The cerium^{3+} doped HA provided the FDM PLA structures with good biological properties, allowing for cell adhesion and proliferation which is reflected in the cell viability data.

Aknowledgements

The aurthors aknowledge the university of Leeds for supporting this research and providing lab access and equipment. We give thanks to the Bragg Centre, Leeds, for use and access to facilites. The authors are grateful to the Oral Biology Department, School of Dentistry, for support in cell studies.

A



B

No	Infill pattern	Density (%)	Porosity (%)
1	Gyroid	30	64.68
2		40	61.54
3		50	54.06
4		60	27.36
5	Tri-hexagon	30	77.44
6		40	65.38
7		50	57.30
8		60	47.96

Figure 1: (A) SEM images of 3D printed gyroid and trihexagon PLA scaffolds with different infill densities of 30, 40%, 50%, 60%. (B) Porosity of scaffolds has been tested using helium pycnometer.




Figure 2: Cytotoxicty testing for pure PLA, 1:5 Col-HA Ratio PLA, 1:3 EC-HA Ratio PLA, at infill densities of 40% and 50%, with comparison against control G292. Statistical Analysis using ANOVA and independent t-Tests shows no significant difference for Col-HA coated PLA and EC-HA coated PLA at infill densities of 40% and 50% compared with G292 control ($p>0.05$). results indicate coated PLA is non-toxic.

D1 - P012

Development of angiogenic and osteoinductive multivesicular liposomes loaded bioink for bone regeneration

Dagar P., Murab S.
School of Biosciences and Bioengineering, Indian Institute of Technology Mandi, Himachal Pradesh, India

Introduction

Critical-size bone defects resulting from severe trauma, tumor resection, or degenerative diseases present a significant clinical challenge for effective regeneration. Conventional treatments such as autografts and allografts remain the clinical gold standard; however, they are associated with limitations including donor site morbidity, infection risk, limited availability of graft material, and poor geometric conformity to defect sites. Recent advances in tissue engineering have focused on the development of bioactive composite scaffolds capable of promoting stem cell recruitment and osteogenic differentiation. However, many of these scaffolds fail to effectively induce angiogenesis, which is essential for long-term tissue regeneration and nutrient supply. Therefore, the development of scaffolds capable of simultaneously promoting angiogenesis and osteogenesis remains a critical requirement for successful bone repair. In this study, we developed a biomimetic scaffold incorporating multivesicular liposomes (MVLs) loaded with sodium nitroprusside (SNP), a nitric oxide donor known to stimulate angiogenesis via the NO–sGC–cGMP pathway, and hydroxocobalamin, which neutralizes cyanide toxicity associated with SNP and supports osteogenic differentiation. The MVLs were incorporated into an alginate–demineralized bone matrix (DBM) bioink for fabrication of 3D bioprinted scaffolds.

Materials and Methods

MVLs encapsulating SNP and hydroxocobalamin were prepared using a double emulsion method to enable efficient drug encapsulation and sustained release. The physicochemical properties of MVLs were characterized by zeta potential analysis and morphological studies using light microscopy, scanning electron microscopy (SEM). The optimized MVLs were incorporated into alginate–DBM bioink formulations and used for 3D bioprinting through a co-printing strategy. Biocompatibility and cellular responses were evaluated using mesenchymal stem cells and endothelial cells. Osteogenic potential was assessed through Alizarin Red S staining, Live/Dead assay, Alamar Blue assay, phalloidin–DAPI staining, and SEM analysis of cell morphology on printed scaffolds. Angiogenic potential was evaluated using endothelial cell culture through tube formation assay and scratch wound healing assay. Additionally, endothelial cells were bioprinted within the constructs to evaluate cell viability, proliferation, and cytoskeletal organization using Live/Dead staining, Alamar Blue assay, and phalloidin–DAPI staining.

Results




Fig. 1 The prepared MVLs exhibited a multivesicular architecture with an average particle size of approximately 38 µm and a negative zeta potential of −59.4 ± 5.08 mV, indicating good colloidal stability. The encapsulation efficiency of the therapeutic agents was approximately 72%.




Fig 2. In vitro biocompatibility studies demonstrated high cell viability and proliferation in MG63 cells. Osteogenic evaluation showed significant calcium deposition as confirmed by Alizarin Red S staining, along with well-spread cell morphology observed in Phalloidin DAPI cytoskeletal staining.

Conclusion

The developed MVL-loaded alginate–DBM bioink enables fabrication of bioactive 3D bioprinted scaffolds capable of simultaneously promoting angiogenic and osteogenic responses. This multifunctional system provides a promising strategy for enhancing vascularized bone regeneration and may offer an effective approach for the treatment of critical-size bone defects.

Acknowledgement

SM acknowledges the funding support from IIT Mandi (IITM/SG/SUM/88), Anusandhan National Research Foundation (ANRF, India) (SRG/2023/002182), IIT Mandi iHub and HCI Foundation (IIT MANDI iHub/RD/2023/012), and DST-FIST (SR/FST/LS-II/2022/950). PD acknowledge the scholarship support from MoE, Govt. of India

References

[1]Silva Filho P.M., Paz I.A., Nascimento N.R., Santos C.F., Araújo V.R., Aquino C.P., ... and Longhinotti, E. Incorporation of nitroprusside on silica nanoparticles—a strategy for safer use of this NO donor in therapy. *Molecular Pharmaceutics* 2019; 16(7); 2912-2921.
[2]Li N., Shi A., Wang Q., Zhang, G. Multivesicular liposomes for the sustained release of angiotensin I-converting enzyme (ACE) inhibitory peptides from peanuts: design, characterization, and in vitro evaluation. *Molecules* 2019; 24(9), 1746.
[3]Dedova V.D., Cerkasova, T.I. Influence of cyanocobalamin on regeneration of bone after surgical extension of limbs in man. 1961.

D1 - P013

Robocasting of zinc oxide reinforced tricalcium phosphate scaffolds: Rheological, structural, and mechanical insights

Karali B.K.[1,3], Jean F.[3], Lasgorceix M.[3], Leriche A.[3], Basu B.[1,2]
[1]Laboratory of Biomaterials Science and Translational Research, Materials Research Centre, IISc Bangalore, Bengaluru, India; [2]CSIR-Central Glass & Central Research Institute, Kolkata, India; [3]CERAMATHS-Dept. Materials and Processing, Université Polytechnique Hauts-de-France, 59313, Valenciennes, France

Introduction

Bone defect repair requires scaffolds that provide structural support while accommodating tissue ingrowth. While beta-tricalcium phosphate (β-TCP) is osteoconductive, tuning its degradation and mechanical properties remains critical. Incorporating zinc oxide (ZnO) offers a pathway to modulate these properties while introducing therapeutic antibacterial and osteogenic benefits. Direct ink writing (robocasting) enables the precise fabrication of these customizable porous architectures.

Aim

This study formulates extrudable pure TCP and TCP-ZnO pastes to evaluate their rheological behavior, printability, and the subsequent structural and mechanical properties of the sintered 3D scaffolds.

Materials and Methods

Dispersant-flocculant pastes were prepared containing 42 vol% ceramic powder (pure β-TCP or TCP with 10 wt% ZnO). The liquid phase comprised a carboxymethylcellulose (CMC) binder, Darvan C dispersant, and polyethyleneimine (PEI) flocculant. Following rheological assessment, scaffolds were printed and sintered at 1100 °C for 3 hours. Scaffolds were characterized via Rietveld refinement of X-ray diffraction (XRD) data, Archimedes density measurements, and uniaxial compression testing evaluated with Weibull statistics.

Results

Both paste formulations exhibited pronounced shear-thinning profiles optimal for extrusion, with Ostwald power law indices of 0.16 for pure TCP and 0.23 for TCP-ZnO (Figure 1). Upon sintering, pure TCP maintained a highly pure phase (94.9% β-TCP). In contrast, the addition of ZnO induced complex thermal phase transformations, resulting in a composite comprising 55.2% β-TCP, 17.0% Zn-substituted TCP, 16.5% hydroxyapatite, and 11.4% ZnO. The TCP-ZnO scaffolds yielded a higher apparent porosity (52.8%) compared to pure TCP (46.2%). Despite microstructural differences, both scaffolds demonstrated reliable mechanical integrity, presenting Weibull moduli of 6.1 for TCP and 6.4 for TCP-ZnO under compression.




Fig 1: Robocasting paste formulation. The dispersant-flocculant interaction schematic (left) yields a highly extrudable paste, demonstrated by the shear-thinning rheological profiles (right) governed by the Ostwald Power Law.

Conclusion

A dispersant-flocculant gelation approach successfully yields robust, printable TCP and TCP-ZnO pastes. The incorporation of ZnO alters the microstructural evolution during sintering, providing a multi-phase scaffold with tunable porosity and dependable mechanical reliability suitable for targeted bone tissue engineering.

Acknowledgements
Funding support from Indian Institute of Science Bangalore and the BRIDGE mobility internship program from EURAXESS to perform work at CERAMATHS, Universite Polytechnique Hauts de-France, France is acknowledged.

References
[1]Somers N., Jean F., Lasgorceix M., Preux N., Delmotte C., Boilet L., Petit L., Leriche A. Fabrication of doped β-tricalcium phosphate bioceramics by Direct Ink Writing for bone repair applications, *Journal of the European Ceramic Society* 2023; Volume 43, Issue 2; 629-638.

D1 - P014
Metabolite-based anti-inflammatory polymers to modulate the foreign body response

Garantoudi G.A., Van Herck S.
Dept. of Instructive Biomaterial Engineering, MERLN Institute for Technology-Inspired Regenerative Medicine, Faculty of Health, Medicine, & Life Sciences (FHML), Maastricht University, The Netherlands

Introduction
Implantable biomaterials often trigger a foreign body response (FBR), characterized by chronic inflammation and fibrotic encapsulation that can compromise implant performance. Macrophages play a central role in this response, with their polarization state strongly influencing inflammatory and regenerative outcomes. Recent insights in immunometabolism have revealed that macrophage polarization is guided by a distinct difference in metabolic activity profile: pro-inflammatory (M1) macrophages are marked by a high glycolytic metabolism, whereas anti-inflammatory (M2) macrophages prefer beta-oxidation and oxidative phosphorylation.

Pyruvic acid, a central metabolic intermediate, has been shown to possess anti-inflammatory properties and the ability to influence macrophage metabolism. Here, we aim to develop a therapeutic, pyruvate-based polymer as a metabolism modulating biomaterial to guide the immune response towards pro-healing instead of pro-inflammatory.

Materials and Methods
A library of bicyclic pyruvic acid-based monomers is developed to create bio-based polymers in a controlled manner via ring-opening polymerization. Polymerization is performed under varying reaction conditions to investigate polymerization kinetics and to optimize molecular weight control. Structural characterization of the monomers is conducted using nuclear magnetic resonance (NMR) spectroscopy, while the resulting polymers are analyzed by gel permeation chromatography (GPC) to determine molecular weight and dispersity. Degradation assays are carried out in order to evaluate how polymer chain length influences degradation behavior and release of pyruvate-containing degradation products.

The resulting materials were processed into thin films to enable in vitro evaluation of their biological performance. Biocompatibility and immunomodulatory properties were assessed using macrophage cell cultures. Cellular responses were evaluated by examining cell viability, inflammatory markers, and metabolic activity to determine the potential of the materials to influence immune cell polarization.

Results
Preliminary synthesis successfully yielded several pyruvic acid-derived monomers capable of undergoing polymerization. Initial polymerization studies produced polymeric materials with measurable molecular weights and controllable physicochemical properties. The synthesized polymers were successfully processed into thin films suitable for biological evaluation. Cellular responses were analyzed through measurements of cell viability, inflammatory markers, and metabolic activity. Ongoing work focuses on optimizing crosslinking density and degradation profiles to enable controlled release of pyruvate.

Conclusion
This work proposes a metabolically instructive biomaterial platform based on pyruvic acid-containing polymers. By integrating metabolically active degradation products into polymeric scaffolds, these materials aim to modulate macrophage behavior and promote regenerative immune responses. Such immunomodulatory biomaterials may provide new strategies to improve the performance of implantable devices and tissue engineering constructs.

Acknowledgements
This research was financially supported by the Summit Program 'DRIVE-RM', funded by the Dutch Research Council (NWO) (SUMMIT.1.027).

References
[1]Caputa G., Flachsmann L.J., Cameron A.M. *Immunol Cell Biol* 2019; Mar, 97(3); 268-278.
[2]Fan R., Wang L., Botchway B.O.A., Zhang Y., Liu X *Front. Mol. Neurosci* 2022; 15; 1013033.
[3]Lee H.-K., Park J.-Y., Lee H., Kim I.-D., Kim S.-W., Lee J.-K. 2019; Volume 16, Issue 2; 523-537.

[4]Zhou T., Guo Y.-T., Yang C., Meng X.-B., Du, Li Z.-C. *Polym. Chem* 2024; Volume 15, Issue 3; 156-165.

D1 - P015

Development of lignin-based scaffolds for in vitro tissue engineering in microfluidic systems

Vincent B.[1*], Gainvors A.[1], Aguie V.[1], Domenech T.[2]
[1]Université de Reims Champagne-Ardenne, INRAE, FARE, UMR A 614, Reims; [2]Université de Reims Champagne-Ardenne, INRAE, FARE, UMR A 614, FAREMAT, Reims, France

Introduction

During the last ten years, the European demand for soft tissues went up by 80%. Research and development for those kinds of tissues were originally tested on living animals. This is why alternatives like cellular growth supports (or scaffolds) were developed.
According to those facts, the MICROPLAITE project aims to develop news scaffolds, and integrate them in a microfluidic chip with physiological-like conditions. Different scales (from 500µm to nm) are considered for PBS scaffolds, a well-known biodegradable plastic commonly used in scaffolding. These scaffolds will take the form of electrospun membranes, knits, or hydrogels, which will eventually also be combined with each other. In addition to that, we blended lignin, a biopolymer considered as a byproduct of the paper industry who shows good antimicrobial and antioxidant properties. Different types of lignin will be used (soda, kraft, organosolv and lignosulfonate)

Materials and Methods

Blends were made from 1 to 7 % of lignin by using an internal batch mixer and shaped for the characterization assays. Their rheological properties were characterized. The antioxidant properties were tested through the Oxidative Onset Temperature (OOT) or the Oxidative-Induction Time (OIT), using a Differential Scanning Calorimeter (DSC). The antioxidant properties of the blends are also being tested using DPPH (2,2-diphenyl-1-picrylhydrazyl) assay, in a solid state. Additionally, the antibacterial properties were tested using a modified version of the Measurement of antibacterial activity on plastics and other non-porous surfaces (ISO22196) on Staphylococcus Aureus, a Gram plus bacteria commonly used for antibacterial testing. This bacteria is also one of the predominant causative agents, particularly in skin and soft tissue infections.

Results

The results shown are preliminary results for a soda lignin (Protobind 1000). We first tested the evolution of the viscosity according to the percentage of lignin in blends. It is shown in Fig 1 that viscosity is reduced when more lignin is added to the blends. It can be explained by the interactions between lignin and the PBS during the extrusion (i.e. transesterification and chains scission).
For Fig 2, we wanted to highlight the oxidative protection effects of the lignin in plastic blends. Those measurements clearly shows that the lignin is delaying the oxidative temperature of the PBS (237°C without lignin ; 337°C at 5%).

Conclusion

Adding lignin in polymers in order to add new properties to the resulting biocomposites, such as antioxidant or antimicrobial, can also lead to a change in the structure of the polymer. This is why it is important to perform rheology measurements and to keep track of the evolution of the viscosity. Those data will be useful for the processing part, when the blends will be electrospun, knitted or printed. It also helps us determining what is happening on a chemical level during internal batch mixing.

Acknowledgements

This communication is produced as a part of the MICROPLAITE project, co-financed by the European Regional Development Fund (ERDF) under the INTERREG France-Wallonia- Vlaanderen program.




Fig. 1: Frequency sweep of PBS blends from 0 to 5% lignin (140°C, 300 to 0,1 rad.s^{-1})




Fig. 2: DSC OOT (Oxidative Onset Temperature) on PBS blends from 0 to 5% lignin

D1 - P016

Designing a click-chemistry based injectable HA-CS hydrogel as a solution for knee osteoarthritis

Mishra S.[1], Duffy G.[1,2,3,4], Mitra T.[1]
[1]Anatomy Dept., School of Medicine, University of Galway, Galway; [2]CÚRAM: Research Ireland Research Centre for Medical Devices, University of Galway, Galway; [3]AMBER, Research Ireland Research Centre for Advanced Materials and Bioengineering, Royal College of Surgeons in Ireland, Dublin, Ireland; [4]Tissue Engineering Research Group, Dept. of Anatomy and Regenerative Medicine, Royal College of Surgeons in Ireland, Dublin, Ireland

Introduction

Knee osteoarthritis (OA) is a prevalent degenerative joint disorder characterized by cartilage breakdown, synovial inflammation, subchondral bone changes, and pain that impairs mobility. Affecting millions globally, with a prevalence rising to 30% in older adults, OA poses significant socioeconomic burdens due to limited curative options[1]. Traditional treatments, including nonsteroidal anti-inflammatory drugs (NSAIDs), physical therapy, corticosteroids, and eventual joint replacement, often provide only symptomatic relief without addressing underlying pathology[2]. In this context, injectable biomaterial-based approaches have emerged as promising minimally invasive, joint-preserving strategies that aim not only to lubricate and cushion the joint but also to modulate the osteoarthritic microenvironment, deliver therapeutics locally, and support cartilage regeneration[3]. This research introduces a Hyaluronic Acid (HA) and Chondroitin sulphate (CS) based catalyst free, click chemically crosslinked, tri-polymeric, injectable hydrogel system that could provide localized, long-lasting support to degenerated cartilage by providing a cushioning effect to the unpadded bone joint. The gel could also be infused with pain therapeutics for their sustained, gradual and localised delivery inside the knee joint to manage the chronic pain associated with knee OA. The hydrogel is designed to withstand the mechanical forces that typically occur in weight-bearing joints. The hydrogel could restrict the progression of cartilage damage and alleviate chronic pain without invasive surgery.

Materials and Methods

The HA-HA-CS cryogel scaffold is prepared by catalyst free click chemistry technique. Hyaluronic acid (HA) (50-90 KDa) is modified by adding an Azide (N_3^-) group (via Azido-PEG-2-Amine reaction) or DBCO (Dibenzocyclooctyne) group (via DBCO-PEG4-Amine reaction) and Chondroitin sulphate (CS) (10-30 KDa) is modified by adding an Azide (N_3^-) group to the skeleton (via Azido-PEG-2-Amine reaction). The modified chemicals click at room temperature to form a chemically crosslinked HA-HA polymer with intertwined strands of CS.

Results

We modified HA (50-90Kda) into HA-N_3 and HA-DBCO, (Fig. 1.a) and CS into CS-N_3 (Fig. 1.b), confirmed by FT-IR spectroscopy where the appearance of Amide I, II and III peaks and Azide peak show successful modification as compared to starting materials. The modified molecules chemically react to form a viscous hydrogel at room temperature instantly (>30 seconds) (Fig. 3.a, b). The hydrogels were cast into cylindrical discs using 3D printed plastic moulds (diameter: 1mm, height: 4mm) for rheology. Rheological analysis confirms excellent viscoelastic behaviour from Amplitude sweep and Frequency sweep studies (Fig. 2.a, b).

Conclusion

The hydrogel could be used for tissue engineering purposes alongside being used as an injectable therapy for knee osteoarthritis. The hydrogel could be infused with pain therapeutics to be delivered gradually and locally inside the knee joint.

Acknowledgements

The project is funded by Research Ireland (SFI-IRC Pathway Program- Grant Number: 22/PATH-S/10732).

Figure 1. Chemical and Rheological assessment of the HA-HA-CS click hydrogel.
(a,b): Show the zoomed sections of Fourier Transformation Infrared spectroscopy (Performed using Shimadzu IR Tracer-4000) plots with highlighted (by dotted circles) peaks of Amide I (~1600-1700cm^{-1}), II (~1500-1600cm^{-1}), III (~1250-1350cm^{-1}) and Azide (~2100cm^{-1}) for Chondroitin Sulphate (CS) (a) and Hyaluronic Acid (HA) (b).
(c,d): Show Rheological Analysis performed using AntonPaar MV302e Rheometer. The Amplitude sweep curve (c) shows a great viscoelastic region with a crossover observed between G' and G'' very late, almost after 10% Shear strain%. The frequency sweep curve (d) shows stable viscoelasticity maintained till the frequency goes beyond 10ω.
(e,f,g): Show images of the gel. (e,f) show the gel just after preparation. (g) shows the discs prepared for rheological analysis.

References

[1]Li H.-Z., Liang X.-Z., Sun Y.-Q., Jia H.-F., Li J.-C., Li G. Global, regional, and national burdens of osteoarthritis from 1990 to 2021: findings from the 2021 global burden of disease study. *Front. Med* 2024; 11; 1476853.
[2]Courties A., Kouki I., Soliman N., Mathieu S., Sellam J. Osteoarthritis year in review 2024: Epidemiology and therapy. *Osteoarthritis and Cartilage* 2024; Volume 32, Issue 11; 1397–1404.

[3]Kalairaj M. S., Pradhan R., Saleem W., Smith M. M., Gaharwar A. K. Intra-Articular Injectable Biomaterials for Cartilage Repair and Regeneration. *Adv. Healthcare Mater* 2024; 13; 2303794.

D1 – P017

Effect of hydrolytic degradation on the compressive mechanical properties of the TPMS gyroid bone scaffolds

Andrzejewska-Sroka A.[1], Pelikant-Małecka I.[2], Rucka M.[1], Kalinowski L.[1,2]
[1]Dept. of Mechanics of Materials and Structures, Faculty of Civil and Environmental Engineering, Gdańsk University of Technology; [2]Dept. of Medical Laboratory Diagnostics - Fahrenheit Biobank BBMRI.pl, Medical University of Gdansk, Gdańsk, Poland

Introduction

Triple-periodic minimal surface (TPMS), especially gyroid structures, are a promising class of metamaterials with high mechanical performance used in bone tissue engineering based on their continuous curvature, high surface-to-volume ratio, and interconnected porosity [1]. In the field of targeted cancer therapy and regenerative medicine, gyroid scaffolds can provide advantages like controlled porosity and bioavailability, which can support local drug delivery while offering structural reinforcement for bone defect reconstruction after resection [2]. The implementation of additive manufacturing allows TPMS scaffolds to be customized to the patient's anatomy. However, to ensure clinical application, particularly in oncology, where mechanical integrity and predictable resorption are critical, it is necessary to understand how hydrolytic degradation affects their compressive mechanical properties over time.

Aim. The aim was to assess the influence of hydrolytic degradation under physiological conditions on the compressive mechanical properties of the fused filament fabricated (FFF) polylactide (PLA) gyroid scaffolds.

Materials and Methods

Gyroid scaffolds were fabricated from PLA using the FFF process (Fig.1). The layer architecture of the scaffolds was generated with an open-source software MaSMaker [3]. The digital scaffold model exhibited a relative density of 52%. The specimens were sterilised using plasma treatment. The degradation was conducted under standard cell culture conditions (37°C; 5%CO2) in DMEM/F12 containing 10% foetal calf serum, 50 IU/ml streptomycin, 50 IU/ml penicillin. Each scaffold was placed in 12-well plate containing 3 mL of medium per well. The medium was changed once per week. After 0, 7, 14, 21, 28 days of incubation, three scaffolds were compressed using a Zwick/Roell Z10 universal testing machine. An initial load of 50 N was applied prior to loading. The test was carried out at a constant crosshead speed of 1 mm/min until to failure of the scaffold. Then statistical analysis was performed using an ANOVA test.

Results and Discussion




Fig. 1. Gyroid scaffold




Fig. 2. Results of compression test

It was proven that incubation of FFF gyroid scaffolds in a degradation medium resulted in a statistically significant reduction in compressive strength compared with the specimens analysed at the baseline (W0). At the same time, no statistically significant differences in strength values were observed between the tested groups at subsequent degradation time points (W1-W4). See results in Fig. 2.

Conclusion

The obtained results provide a baseline for further *in vitro* studies using osteoblast cultures, with the aim of assessing the biological response and osteoregenerative potential of the analysed structures.

Acknowledgements

Gdańsk University of Technology funded these studies through the grant: „Evaluation of mechanical and biological response of bone scaffolds 3D printed with hybrid polymers” (DEC-37/2021/IDUB/I.3.), which was awarded under the "ARGENTUM TRIGGERING RESEARCH GRANTS - Excellence Initiative - Research University" program.

References

[1]El-asfoury M.S., et al. Orientation driven design and mechanical optimization of gyroid TPMS lattice structures. *Scientific Reports* 2026; 16, 4373; 1-22.

[2]Tenorio-Suárez M.I., et al. MaSMaker: An open-source, portable software to create and integrate maze-like surfaces into arbitrary geometries. *SoftwareX* 2022; 19; 101203.

[3]Yan J., et al. 3D-Printed Triply Periodic Minimal Surface Ceramic Scaffold Loaded With Bone Morphogenetic Protein-2 and Zoledronic for Cranium Defect Repairment. *Journal of Tissue Engineering and Regenerative Medicine* 2025; 9964384; 1-19.

D1 – P018

Enhanced densification and microstructural homogeneity of biodegradable Mg-HA-graphene nanoplatelet composites via two-stage sintering for orthopaedic implants

Adeoye A.O.[1,2], Damanpack A.R.[1,2,] Spitas C.[1,2,] Shoja Razavi R.[1,2,] Ren Y.[1,2], Nie Y.[1,2,3]
[1]Dept. of Mechanical, Materials, and Manufacturing Engineering, University of Nottingham Ningbo China; [2]Advanced Mechanical Engineering, Manufacturing, and Mobility Research Centre, University of Nottingham Ningbo China; [3]Nottingham Ningbo China Beacons of Excellence Research and Innovation Institute, University of Nottingham Ningbo China, China

Introduction

Magnesium alloys are promising candidates for biodegradable orthopaedic implants due to their mechanical compatibility with bone and ability to stimulate osteogenesis. However, rapid corrosion and limited wear resistance hinder clinical use. Reinforcement with hydroxyapatite (HA) and graphene nanoplatelets (GNP) offers improved bioactivity, mechanical strength, and corrosion resistance. This study introduces a two-stage argon-controlled thermal sintering route to produce dense Mg-HA-GNP composites with refined grain size and enhanced microstructural uniformity.

Aim

This study aimed to develop and evaluate biodegradable Mg-HA-graphene nanoplatelet composites using a novel two-stage argon-controlled thermal sintering technique to achieve enhanced densification, refined microstructure, and improved mechanical and biological performance for orthopaedic implant applications.

Materials and Methods

Mg (92 wt%), HA (6 wt%), and GNP (2 wt%) powders were mechanically milled and compacted into pellets. Two sintering strategies were compared: conventional single-stage sintering (CS) and optimised two-stage sintering (TSS). Microstructural evolution was characterized using XRD, BET surface porosity analysis, True density analysis, EBSD and XPS. Mechanical and degradation behaviour were correlated with processing parameters to evaluate structural integrity and biological performance

Results

TSS achieved superior densification and homogeneity compared to conventional sintering. The plot in Fig. 1 below compares the evolution of measured density across 15 pycnometric cycles for Two-Stage Sintering (TSS) and Conventional Sintering (CS). TSS exhibits a narrow, quickly stabilizing band between 3.63 and 3.80 g cm^{-3}, achieving steady-state density by the fourth run, whereas CS fluctuates broadly (4.23-4.63 g cm^{-3}) and stabilizes only after the tenth run. Fig. 2 below is a Cumulative Variance Curve, Cumulative normalized variance as a function of measurement cycle for TSS and CS. The variance in TSS reaches 95 % stabilization by the fourth measurement, while CS requires approximately ten cycles to converge. This rapid stabilization under TSS processing demonstrates more efficient equilibration, improved pore closure, and minimal residual heterogeneity, confirming that the two-stage regime yields a denser and more uniform microstructure with lower internal stresses.

Conclusion

Two-stage sintering effectively suppresses grain coarsening, yielding fine-grained Mg-HA-GNP composites with balanced mechanical and biological properties. The synergy of magnesium's biodegradability, HA's bioactivity, and GNP's reinforcement enables implants that degrade predictably while supporting bone regeneration. These findings highlight the potential of TSS-processed Mg-HA-GNP composites as next-generation biodegradable orthopaedic implants.

Acknowledgements

The authors acknowledge support from the Li Dak-Sum Innovation Fellowship Foundation and the Department of Mechanical, Materials and Manufacturing Engineering, University of Nottingham Ningbo China.




Figure 1. Density versus run number for TSS and CS. TSS stabilizes by the 4th run (3.63-3.80 g cm^{-3}), while CS fluctuates widely (4.23-4.63 g cm^{-3}), indicating superior uniformity in TSS.




Figure 2. Cumulative variance stabilization curves. TSS reaches 95 % stability by the 4th cycle; CS only after the 10th, confirming faster equilibration and uniform pore closure.

D1 – P019

Lignin based bilayer implantable electrospun patches for hernia repair

Orak M.[1], Safakhah S.[1], Yousefimiab E.[1]., Karimzadeh Khoei J.[1], İnce G.[1,2,3]
[1]Materials Science and Nano Engineering, Faculty of Engineering and Natural Sciences, Sabancı University; [2]Nanotechnology Research and Application Center (SUNUM), Sabancı University; [3]Center of Excellence for Functional Surfaces and Interfaces (EFSUN), Sabancı University, Istanbul, Türkiye

Introduction

Electrospun bilayer patches are promising candidates for soft tissue repair due to their ability to combine biological functionality with mechanical support. In this study, a double layer electrospun patch was developed by integrating a biodegradable sulfonated poly (ether ether ketone) (SPEEK)/lignin layer with a non-degradable poly(tetrafluoroethylene) (PTFE)/polycaprolactone (PCL)/lignin reinforcement layer.
Aim. The aim was to obtain a multifunctional scaffold with enhanced structural stability while preserving the degradability and bioactive potential of the front-facing layer.

Materials and Methods

The biodegradable layer was first fabricated using SPEEK/lignin (80/20, 14% w/v) solution by electrospinning. Immediately after deposition, the second layer was directly electrospun onto the first layer without interrupting the process. For the reinforcement layer, PTFE/PCL/lignin (4/4/4, 30% w/v) solution was loaded into a 10 mL syringe and electrospun at a flow rate of 0.4 mL h^{-1} under 24 kV with a tip-to-collector distance of 12 cm.

Results

SEM observations confirmed the successful formation of continuous bilayer fibrous structures for both AL- and OL-based patches (Figure 1). To investigate the mechanical contribution of each layer, tensile testing was performed separately on the biodegradable SPEEK/lignin layer, the non-degradable PTFE/PCL/lignin layer, and the bilayer patch (Table 1).The intermediate mechanical performance of the bilayer patch confirms the reinforcing effect of the PTFE/PCL/lignin backing layer while preserving the compliant character introduced by the degradable SPEEK/lignin surface layer. The biodegradable SPEEK/lignin layer also showed degradation behavior in PBS, supporting its intended role as a temporary bioactive interface within the bilayer design.




Figure 1: SEM images of Double Layer Patch

Table 1. Ultimate tensile strength (UTS) of individual layers and bilayer electrospun patch

Sample	Description	Mean UTS ± SE (MPa)
Biodegradable layer	SPEEK/AL (80/20, 14% w/v)	0.263
Non-degradable layer	PTFE/PCL/AL (4/4, 30% w/v)	5.30 ± 1.53
Bilayer patch	SPEEK/AL + PTFE/PCL/AL	1.48 ± 0.13

Conclusion

The developed bilayer electrospun patch successfully combined the biological advantages of a biodegradable SPEEK/lignin surface with the mechanical reinforcement provided by a PTFE/PCL/lignin backing layer. The resulting structure exhibited improved tensile performance while maintaining a compliant mechanical profile desirable for handling and implantation. These findings suggest that the proposed bilayer design is a promising scaffold architecture for soft tissue repair applications.

D1 – P020

Development of PEDOT:PSS-based composites for fabricating tissue engineering scaffolds

Garrudo F.[1,2,3,4], Silva J.[2,3], Resina L.[5,6], Filippone G.[2,3], Manjua A.[7,8], Marcelino P.[2,3], Barbosa F.[2,3,9], Carvalho M.[2,3], Ferreira L.[2,3,10], Aléman C.[5,6,11], Cabral J.[2,3], Vashishth D.[9], Ferreira F.[2,3], Morgado J.[1]
[1]Dept. of Bioengineering Instituto Superior Técnico, Universidade de Lisboa and Instituto de Telecomunicações, Lisboa, Portugal; [2]Dept. of Bioengineering and iBB – Institute for Bioengineering and Biosciences, Instituto Superior Técnico, Universidade de Lisboa, Lisboa, Portugal; [3]Associate Laboratory i4HB - Institute for Health and Bioeconomy, Portugal; [4]Dept. of Brain and Cognitive Sciences, Picower Institute for Learning and Memory, Massachusetts Institute of Technology, Massachusetts, USA; [5]IMEM-BRT Group, Dept. d'Enginyeria Química, EEBE, Universitat Politècnica de Catalunya, Barcelona, Spain; [6]Barcelona Research Center in Multiscale Science and Engineering, Universitat Politècnica de Catalunya, Barcelona, Spain; [7]Biosensors and Devices Lab, Dept. of Biomedical Engineering, Eindhoven University of Technology, Eindhoven, The Netherlands; [8]Institute for Complex Molecular Systems, Eindhoven University of Technology, Eindhoven, The Netherlands; [9]RPI-Mount Sinai Center for Engineering and Precision Medicine, Dept. of Biomedical Engineering, Rensselaer Polytechnic Institute, Troy, USA; [10]Dept. of Chemical Engineering, Instituto Superior Técnico, Universidade de Lisboa, Lisboa, Portugal; [11]Institute For Bioengineering of Catalonia (IBEC), The Barcelona Institute of Science and Technology, Barcelona, Spain

Introduction

Poly(ethylenedioxythiophene):poly(styrene sulfonate) (PEDOT:PSS) is an electroconductive polymer with several applications in tissue engineering and regenerative medicine. It has numerous advantages, including transparency, chemical stability, and the ability to channel electrical stimulation (ES) to cultured cells. PEDOT:PSS is commercially available as an aqueous suspension, which avoids the use of harmful solvents for its processing. However, this aqueous formulation limits its versatility, in contrast to scaffolds designed for tissue engineering using biocompatible and biodegradable polymers such as poly(capro-ε-lactone) (PCL), poly(acrylonitrile) (PAN), and poly(glycerol sebacate) (PGS). Overcoming this PEDOT:PSS versatility limitation would expand its applications in the design of tridimensional (3D) devices for tissue engineering and drug screening.

Aims

Develop different methodologies for the combined processing of PEDOT:PSS with other water-indispersible polymers to create 3-D electroconductive scaffolds for tissue engineering. We further improved its bioactivity by immobilizing bioactive motifs and studied the effect of ES on cultured cells.

Materials and Methods

To prepare PCL-PEDOT:PSS scaffolds, 3D-extruded PCL scaffolds were dipped into different PEDOT:PSS dispersions containing cross-linkers and electroconductivity enhancement agents. These were then cross-linked at 45 ºC and washed with deionized water. The obtained scaffolds were then characterized structurally (SEM), physico-chemically (DSC, FTIR, Raman, XPS), and tested for their stability under pseudo-physiological conditions, biodegradability and in vitro mineralization potential. To prepare PAN-PEDOT:PSS and PGS-PEDOT:PSS scaffolds, PEDOT:PSS was precipitated and resuspended in DMF:DMSO (9:1) before adding the carrier polymer. For electrospun PAN-PEDOT:PSS scaffolds, cross-linking was performed at 210 ºC, followed by sulfuric acid treatment. For film-cast PGS-PEDOT:PSS scaffolds, cross-linking was performed at high temperature. Both PAN-PEDOT:PSS and PGS-PEDOT:PSS scaffolds were characterized in a similar fashion to PCL-PEDOT:PSS. Biocompatibility was evaluated with neural stem cells (NSCs) (proliferation assay) and mesenchymal/stromal cells (MSCs) (proliferation and osteogenic differentiation assays).

Results

For PCL-PEDOT:PSS scaffolds, immobilization of bioactive motifs did not interfere with scaffold electroconductivity (e.g. 11 S cm^{-1} after functionalization with gelatin). These were stable in PBS for up to 28 days, biodegradable, and extensively mineralized. ES of cultured cells led to Osterix, Collagen I and CACNA1C upregulation. Highly conductive PAN-PEDOT:PSS fibers (3.2×10^{-3} S cm^{-1}) were found to be biocompatible towards NSC and MSC culture. PGS-PEDOT:PSS composites were stable in PBS, but biodegradable even when high amounts of PEDOT:PSS were used; bioactivation further improved MSC cell adhesion.

Conclusion

The developed electrocomposites and scaffolds containing PEDOT:PSS exhibited satisfactory performance and thus hold promise for the development of more advanced models and devices for biomedical applications.

Acknowledgements

The authors acknowledge dedicated funding from Fundação para a Ciência e a Tecnologia (FCT) through project BioMaterARISES (EXPL/CTM-CTM/0995/2021, DOI: 10.54499/EXPL/CTM-CTM/0995/2021). The authors also acknowledge funding provided by FCT through IT (UIDB/50008/2025, doi.org/10.54499/UID/50008/2025), iBB (UID/04565/2025), *Laboratório Associado* I4HB (LA/P/0140/2020). FFFG also acknowledges the support of *Fundación "la Caixa"* through an individual fellowship. LR and CA thank the PID2021-125767OB-I00 project, as well as the Maria de Maeztu Units of Excellence Programme CEX2023-001300-M, both funded by MCIN/AEI /10.13039/501100011033. Support for the research of C.A. was also received through the prize "ICREA Academia" for excellence in research funded by the Generalitat de Catalunya. JCS acknowledges FCT for financial support under the Assistant Researcher FCT Tenure contract (iBB_U5_SCERG_FCT TENURE (121) iBB). This work was also funded by ELECTROBONE project through the seed funding initiative of the European University Alliance Unite! – University Network for Innovation, Technology and Engineering. Views and opinions expressed are however, those of the authors only and do not necessarily reflect those of the Unite! Alliance.

D1 – P021

Combining sustainability and regenerative therapies: Upcycling sea urchin waste into biomimetic collagen-hydroxyapatite scaffolds

Vicinelli G.[1], Campodoni E.[1], Ronconi M.[2], Marzorati S.[2], Panocchia A.[1], Apolloni L.[1,3], Panseri S.[1], Costantini G.[4], Pulze L.[4], Baranzini N.[4], Grimaldi A.[4], Sugni M.[2], Sandri M.[1]

[1]Institute of Science, Technology and Sustainability for Ceramics, National Research Council, ISSMC-CNR, Faenza (RA), Italy; [2]Dept. of Environmental Science and Policy, University of Milan, Milan (MI), Italy; [3]Dept. of Neuroscience, Imaging and Clinical Sciences, University "G. D'Annunzio", Chieti (PE), Italy; [4]Dept. of Biotechnology and Life Science, University of Insubria, Varese, Italy

Introduction

Food waste (FW) is a major global challenge, with around 1.3 billion tons generated annually, much of which is discarded in landfills. Upcycling FW into functional products offers a sustainable solution by recovering biopolymers with potential biomedical applications. Among these, collagen is particularly valuable due to its biocompatibility, biodegradability, and structural role, making it essential for scaffold fabrication. However, conventional collagen from mammalian skin and tendons is limited by high cost, supply constraints, and ethical or religious concerns. Marine FW such as sea urchins provide a promising alternative, yielding collagen that preserves native fibrillar organization and glycosaminoglycan decoration while supporting circular economy principles and reducing production costs. In this study, sea urchin-derived collagen was used to synthesize biomimetic scaffolds through biomineralization, where hydroxyapatite nanocrystals form on collagen fibers, creating hybrid materials that mimic natural bone and support bone tissue regeneration.

Materials and Methods

Native collagen was isolated from sea urchin food (UColl) waste through a decellularization and disaggregation protocol preserving its fibrillar organization and glycosaminoglycan (GAG) decoration. A biomimetic mineralization process was then performed to obtain a UCollMgHA hybrid scaffold with a 70/30 weight ratio (HA/UColl) and a Mg/Ca molar ratio of 5%. Pure UColl scaffold was prepared as control. Both scaffold types were freeze-dried and crosslinked by dehydrothermal treatment (160 °C, vacuum, 48 h) to modulate degradation and were evaluated in vivo using leech models.

Results

The hybrid scaffold exhibited highly interconnected porosity, essential for cell colonization and proliferation. SEM images showed that mineralized fibers self-assembled into three-dimensional structures, exposing hydroxyapatite and forming a low-crystallinity structure with ~30% organic content, as confirmed by FTIR, XRD, and TGA. The scaffolds demonstrated good absorption capacity, adequate stiffness, and stability for up to 21 days, providing sufficient time for regeneration. Biological tests showed in vitro optimal biocompatibility and in leech in vivo models effective cell colonization, proliferation, and integration.

Conclusion

This study demonstrated that sea urchin-derived collagen can be used to develop biomimetic scaffolds that are both sustainable and effective for bone regeneration. Mineralization of hydroxyapatite on collagen fibers produced a scaffold that closely mimics natural bone, with tunable stability, favorable mechanical properties, high biocompatibility, and robust cell colonization. This approach valorizes food waste while providing a biologically relevant alternative to conventional collagen sources.

D1 – P022

Charge-dependent mechanical reinforcement in silk–elastin-like polypeptides hydrogels postprocessing

Gao R., Sarkar S., Lopez Barreiro D.
Dept. of Chemical Engineering, University College London, London, UK

Introduction

Silk–elastin-like polypeptides (SELPs) are recombinant protein-based materials that combine thermoresponsive elastin-like domains with mechanically reinforcing silk-like blocks, enabling programmable hydrogel formation. While higher mechanical strength can be achieved by increasing molecular weight or modifying block arrangements, these strategies require substantial sequence redesign and often lead to reduced protein yields. Postprocessing therefore provide an attractive alternative for enhancing mechanical performance without altering the protein sequence. Ethanol annealing has been widely used to promote β-sheet formation and reinforce silk-based materials, yet the influence of sequence charge on this process remains poorly understood.

Materials and Methods

Three SELP variants with similar molecular weight (~39kDa) but different net charge were investigated: neutral (S2E39-I), negatively charged(S2E39-E), and positively charged(S2E39-K). Freeze-dried proteins were subjected to either formic acid treatment as baseline control or ethanol annealing as a postprocessing treatment. Mechanical and structural responses were characterised using rheology, Fourier transform infrared spectroscopy (FTIR), dynamic light scattering (DLS), zeta potential measurements, atomic force microscopy (AFM), and scanning electron microscopy (SEM). Molecular dynamics (MD) simulations were performed using both all-atom and coarse-grained models.

Results

Rheological measurements revealed that ethanol annealing enhanced the stiffness of the neutral SELP hydrogel, increasing the storage modulus from ~2.2kPa to ~5.6kPa. In contrast, ethanol annealing reduced the mechanical strength of both charged variants, with the storage modulus decrease around 85%. FTIR analysis showed increased β-sheet content for all variants after ethanol treatment, indicating that changes in secondary structure alone could not explain the observed mechanical behaviour. AFM and SEM imaging revealed fibrous network formation in the neutral SELP, whereas charged variants remained largely globular with limited fibre propagation (Figure 1). Zeta potential measurements showed increased absolute surface charge following ethanol annealing, suggesting greater exposure of charged residues. MD simulations further supported this mechanism, showing that ethanol-induced structural rearrangement promotes β-sheet formation within silk domains while exposing charged elastin-like segments at the assembly surface.

Conclusion

These findings demonstrate that ethanol annealing does not universally reinforce SELP hydrogels. Instead, sequence charge governs hierarchical assembly during thermal gelation, where increased electrostatic repulsion in charged SELPs suppresses fibre formation and network development. This work highlights electrostatic regulation as a key design parameter for controlling postprocessing responses in protein-based hydrogels.




Figure 1. AFM images of baseline or ethanol annealed SELP variants.

D1 – P023

Proximity-driven dynamic covalent biomaterials for adaptive extracellular matrix mimics

Kwiatkowski A.A., Schauenburg D., Baker M.B.
MERLN Institute for Technology-Inspired Regenerative Medicine, Maastricht, The Netherlands

Introduction

Living systems rely on dynamic molecular interactions to control structure, function and adaptability. Chemical reactions in biological systems are often regulated by refined spatial locations and proximity rather than by bulk thermodynamics. Dynamic covalent chemistry (DCvC) is an effective method for translating these functions into a synthetic biomaterial by combining the robustness of covalent bonds with the reversibility necessary for adaptive behaviour. Dynamic networks of this nature are of interest for the design of extracellular matrix (ECM)-mimicking biomaterials that are able to respond to environmental stimuli (e.g. pH, redox conditions, temperature …) and support cellular processes. However, current hydrogel systems frequently lack the necessary level of control over network organisation and adaptability. In this work, we develop proximity-driven dynamic covalent biomaterials in which the spatial organisation of reactive motifs guides network formation and material properties.

Materials and Methods

The synthesis of the dynamic covalent building blocks bearing boronic acids (BA) or salicylhydroxamic acid (SHA) will be carried out using established organic chemistry methods. The characterisation of these building blocks will be performed using nuclear magnetic resonance (NMR) and mass spectrometry. The reactive motifs will be incorporated into biomacromolecules, such as human serum albumin (HSA), to generate macromolecular building blocks capable of forming proximity-driven dynamic covalent networks. The formation of the hydrogel network will be driven by reversible BA-SHA interactions that occur in response to proximity, under physiological conditions. The material's formation and mechanical properties will be investigated using rheological measurements. These will include viscoelastic, stress relaxation and self-healing experiments. Hydrogel formations will be evaluated under a range of physiological conditions, including phosphate buffer, phosphate-buffered saline and cell culture media. Furthermore, we will be examining the incorporation of bioactive molecules and their release.

Results

We hypothesise that the spatial organisation of boronate-based dynamic covalent motifs within biomacromolecular scaffolds will promote proximity-driven network formation and enable tunable material properties. The resulting hydrogels are expected to exhibit reversible interactions, adaptive mechanical behaviour, and stimulus-responsive network rearrangement, enabling cells to dynamically interact with and remodel their microenvironment.

Conclusion

The aim of this work is to establish structure–property relationships in boronate-based dynamic covalent biomaterials and demonstrate how proximity-driven chemistry can guide the formation of adaptive ECM-like hydrogels. Initially, boronic acid–salicylhydroxamate interactions will be explored as a dynamic covalent building block that enables reversible and pH-responsive network formation. In the future, this chemistry may be combined with additional dynamic or supramolecular crosslinking motifs to create multi-responsive biomaterials capable of responding to multiple environmental stimuli. Such modular material systems have the potential to provide versatile platforms for regenerative medicine, advanced drug delivery, and tissue engineering applications.

Acknowledgements

This research was financially supported by the Summit Program ‘DRIVE-RM’, funded by the Dutch Research Council (NWO) (SUMMIT.1.027).

D1 – P024

Biomimetic calcium carbonate mineralization using protein and polysaccharide-based templates via a dual membrane double migration approach

Salman M.I.[1], Jangda S.Z.[1], Kruppke B.[2], Lee P.S.[1]
[1]Institute of Materials Science, Chair of Biomaterials, Technical University Dresden; [2]Dept. of Biomaterials, Institute for Bioprocess and Analytical Measurement Technology e.V., Heilbad Heiligenstadt; [2]Institute for Organic and Macromolecular Chemistry, Friedrich Schiller University, Jena, Germany

Introduction

Natural biomineralization creates calcium carbonate ($CaCO_3$) with highly ordered hierarchical structures and excellent mechanical properties, as seen in biological systems such as mollusk shells and marine skeletal structures. These minerals form within organic matrices that regulate nucleation, crystal growth, and structural organization. Inspired by such natural processes, biomimetic mineralization strategies aim to reproduce controlled mineral formation using organic template molecules that mimic biological matrices. In this study, a dual-membrane double-migration system was designed that mimics some aspects of natural mineral formation and to investigate how different template molecules influence $CaCO_3$ formation and structural properties.

Materials and Methods

A migration-based mineralization system was designed in which ionic species move through selective barriers toward a central compartment containing an organic template where mineralization occurs. Calcium chloride ($CaCl_2$) and sodium bicarbonate ($NaHCO_3$) solutions were placed in separate reservoirs, allowing controlled migration of Ca^{2+} and CO_3^{2-} ions. Two types of organic templates were studied: a protein-based template (gelatin) and a polysaccharide-based template (chitin).

Most experiments were performed under ambient conditions, with additional studies at different temperatures to evaluate their effect on mineral growth. The mineralized structures were characterized using electron microscopy and X-ray diffraction to analyze morphology and phase composition. Mechanical properties were evaluated using a ball-on-three-balls test and compared with reference $CaCO_3$ materials.

Results

Template molecules significantly influenced the morphology and microstructure of the resulting $CaCO_3$ minerals. Different morphologies were observed for protein- and polysaccharide-based matrices, highlighting the role of the organic template in guiding crystal growth. However, the overall polymorphic composition of $CaCO_3$ remained similar across the systems. Mechanical testing showed that templated materials exhibited improved properties compared with commercial $CaCO_3$ references. Polysaccharide-based mineralized structures also demonstrated higher mechanical strength than protein-based structures.

Conclusion

The dual-membrane migration strategy provides a biomimetic platform for studying template-directed $CaCO_3$ mineralization using different organic matrices. While both protein- and polysaccharide-based templates influenced mineral organization, polysaccharide-directed mineralization resulted in composites with superior mechanical performance. This approach offers a promising pathway for developing nature-inspired inorganic–organic composites for biomaterials and tissue engineering applications.

D1 – P025

The first step towards a validated reference material for arterial mechanical testing

Loeckx M., Fehervary H., Famaey N.
Dept. Mechanical engineering, KU Leuven, Leuven, Belgium

Introduction

Reported arterial material parameters vary greatly, raising concerns about their suitability for regulatory or predictive models. This spread arises from two sources: methodological variability, driven by differences in test protocols and sample handling, and biological variability, reflecting inherent tissue heterogeneity. A reference material could help distinguish these effects, enabling researchers to focus on reducing methodological variability. However, commercial options lack biofidelic mechanical behavior and recently developed biofidelic substitutes require validation in terms of homogeneity and stability.

Materials and Methods

Fabric reinforced elastomers were produced by embedding a knitted fabric (ribtricot 95% cotton, 5% elastane) in 2 mm Ecoflex 0050 sheets. Three sets of five dogbone samples were prepared in one batch. One set was tested immediately (Set 1), while the remaining sets were stored for 14 days in either saline solution (Set 2) or a closed container (Set 3) before testing.

Mechanical testing followed the C^{4}Bio consensus protocol: 10 preconditioning cycles of 8 mm (~30% strain) followed by failure testing at 1.3 mm/s (~5%/s)[1]. Variability was quantified using the average normalized standard deviation across 100 evenly spaced strain points. These metrics were compared against KU Leuven C^{4}Bio porcine aorta data (circumferential samples).

Results

The mean stress-strain curve (full line) and the SD (shaded area) of the synthetic samples compared to porcine aorta samples are shown in Figure 1. The variability metrics are shown in Table 1.

Conclusion

The fabric reinforced elastomers demonstrated mechanical behaviour with substantially lower variability than biological arterial tissue. Variability across the synthetic sets ranged from 3.7% to 6.9%, representing an approximately 75–85% reduction compared to the 25.4% domain variability observed in porcine aorta samples. Set-dependent differences suggest that short-term storage conditions can influence mechanical consistency, and should be further investigated.

Despite not fully replicating the non-linear arterial response, the materials showed stable behaviour across one batch. Their low variability and ease of production position them as promising candidates for further development into a reference material.

Acknowledgements

Samples were mechanically tested at FIBEr. The equipment used in this study was funded by Research Foundation Flanders (FWO: AKUL/15/25)
This work is supported by KU Leuven (C2M/24/031)




Figure 2: stress-strain curves of the materials

Table 1: Variability measurements

	Variability over entire domain
Biological	25.37%
Set 1	3.67%
Set 2	4.93%
Set 3	6.92%
Set 1 + 2	8.00%
Set 1 + 3	8.30%
Set 2 + 3	6.24%

References

[1]Famaey N. et al. Community challenge towards consensus on characterization of biological tissue: C[4]Bio's first findings. *Journal of biomechanics*; 2026; volume 194.

D1 – P026
Bioinspired polyphenol-based functional biointerfaces

Ruiz-Molina D.
Catalan Institute of Nanoscience and Nanotechnology (ICN2), CSIC and BIST, Campus UAB, Bellaterra, Spain

Introduction

Polyphenol-based interfaces have been subject to intense research, aimed at mimicking natural protein-segregation adhesive properties of mussels and barnacles. To achieve these objectives, our group has been very active on different synthetic approaches, ranging from the polymerization of catechols in the presence of amines (ammonia or bisamines) to the oxidative condensation of readily available pyrocatechol and thiol-capped functional moieties. So far, we have developed functional coatings and thin-films with a broad range of architectures, functionalities and characteristics relevant in biomedicine, among them:

- Nanoparticle-coatings for diagnosis and therapy.
- Fiber-coatings to modulate hydrophilicty, biocompatibility and antimicrobial properties.
- Thin films for the regeneration of human cells/tissues.

In this talk I will give a brief overview of these research topics using representative examples.




Fig. 1: mussel inspired coatings.

References

[1]*Angew. Chem. Int. Ed* 2026; 138 (3); e13698.
[2]*Advance Science* 2026; e10658.
[3]*Journal of Colloid and Interface Science* 2025; 680; 987-996.
[4]*Chemical Engineering Journal* 2024; 481; 148674.
[5]*Biosensors and Bioelectronics* 2024; 260; 116421.
[6]*Materials Today Chemistry* 2024; 35; 101855.
[7]*Chemical Engineering Journal* 2023; 473; 145280.
[8]*Biomimetics* 2023; 8 (1); 3.
[9]*ACS nano* 2021;15 (5); 8592-8609.
[10]*Angew. Chem. Int. Ed.* 52019, 8; 696-714.

D1 – P027

Bioinspired functionalization of PEEK and the resulting cell response especially on osteoblast adhesion and osteogenic gene expression

Gätjen L.[1], Borcherding K.[1], Braun S.[2], Grom S.[2], Wolfram T.[2], He C.[3], Hofzumahaus N.[3]
[1]Dept. Polymer Chemistry and Material Behavior, Fraunhofer IFAM, Bremen; [2]KLS Martin SE&Co.KG, Tuttlingen; [3]Clean-Lasersysteme GmbH, Herzogenrath, Germany

Introduction

Biologization of implant materials aims to transform bioinert substrates into biologically instructive interfaces that actively guide cell behavior and promote tissue integration. Polyetheretherketone (PEEK) exhibits favorable biomechanical properties and radiolucency but lacks intrinsic osteogenic activity. This study presents a multifunctional surface modification strategy combining hierarchical laser structuring, calcium phosphate availability, and collagen-like protein (CLP) coating to mimic structural and compositional characteristics of bone and enhance osteoblast response.

Materials and Methods

PEEK and hydroxyapatite (HA)-filled PEEK substrates were structured using pulsed laser systems to generate hierarchical micro- and nanoscale morphologies with pore sizes ranging from 50 to 500 µm, inspired by trabecular bone architecture. Laser parameter variation enabled precise control of surface topography and promoted calcium phosphate availability. Surface morphology was analyzed by scanning electron microscopy (SEM).

To establish a stable bioactive interface, surfaces were functionalized by plasma polymer coating, enabling subsequent immobilization of CLP. Successful attachment and chemical composition were verified by X-ray photoelectron spectroscopy (XPS).

Osteoblast-like SaOS-2 cells were cultured on modified substrates. Cell adhesion and morphology were assessed after 48 h and 7 days using light microscopy and SEM. Osteogenic differentiation was evaluated by RT-qPCR over 10 days (days 1, 5, and 10), measuring gene expression of ALPL, COL1A1, and BGLAP relative to untreated PEEK controls.

Results

Laser structuring generated spongiosa-like surface morphologies, while preserving substrate integrity. Plasma polymer coating enabled stable CLP immobilization on different surfaces structures.

Cell morphology and surface coverage were influenced by the combined structural and biochemical modifications. Structured and collagen-coated surfaces showed enhanced spreading and formation of interconnected cell layers after prolonged culture. Quantitative adhesion data revealed condition-dependent differences.

RT-qPCR results demonstrated time-dependent modulation of osteogenic marker expression on biologized PEEK surfaces. Distinct temporal patterns suggest that topography and collagen presentation cooperatively influence osteogenic signaling. Ongoing experiments aim to confirm statistical robustness and reproducibility.

Conclusion

The presented bioactivation strategy transforms bioinert PEEK surfaces into a multifunctional, biomimetically engineered interface capable of modulating osteoblast adhesion and gene expression over time. The synergistic integration of hierarchical topography, calcium phosphate availability, and CLP immobilization represents a promising approach to enhance osteointegration of metal-free PEEK implants. Further investigations are required for reliable and safe clinical translation.

Acknowledgements

The OSTEOFUNK project is supported by Evonik Operations GmbH and Coherent GmbH.

Funding
The OSTEOFUNK collaborative project is funded by the Federal Ministry of Research, Technology, and Space (grant number: 13XP5205).





D1 – P028

Biomimetic and resorbable injectable formulation and 3D printing: From skin tissue regeneration to the engineering of in vitro models

Panocchia A.[1], Vicinelli G.[1], Campodoni E.[1], Papasergi S.[2], Sandri M.[1]
[1]CNR-ISSMC, Faenza; [2]CNR-IFT, Naples, Italy

Introduction

Chronic wounds, including diabetic ulcers, pressure sores, and vascular lesions, represent a major clinical and socioeconomic burden due to impaired healing, persistent inflammation, and high infection risk. These lesions are difficult to treat with conventional therapies, which often fail to create a regenerative environment and are prone to reinfection, resulting in prolonged hospitalization and increased healthcare costs. Traditional dressings mainly provide passive protection with limited support for tissue repair, and frequent replacement can cause pain and disrupt newly formed tissue. Advances in biomaterials and 3D printing enable personalized, multifunctional wound dressings that promote regeneration while preventing infection. This study aimed to develop biomimetic injectable bioinks for 3D printing therapeutic patches combining wound protection, tissue regeneration, and localized antimicrobial action.

Materials and Methods

Bioactive inks were formulated using gelatin particles mineralized with magnesium-doped hydroxyapatite (GelMgHA) dispersed in a gelatin-based matrix and functionalized with vancomycin for localized antibiotic release. Printed constructs were freeze-dried to create microporosity for nutrient diffusion and cell migration, and thermally crosslinked to improve mechanical stability and control degradation rate. A bilayer patch was designed by combining the vancomycin-loaded 3D printed layer with a compact, breathable upper film obtained via solvent casting of chitosan and glycerol enriched with gelatin mineralized with copper-doped hydroxyapatite (GelCuHA). Physicochemical and rheological analyses assessed printability and bioactivity, while microbiological tests and cell viability assays evaluated antibacterial effectiveness and biocompatibility.





Fig 1: design of the bilayer patch

Results

The bioinks showed suitable rheological properties for extrusion-based 3D printing. Printed patches exhibited controlled degradation, interconnected microporosity, and bioactivity. The vancomycin-loaded layer demonstrated antibacterial activity against common wound pathogens, while cell viability tests confirmed cytocompatibility. The bilayer design combined regenerative and antimicrobial functions: the porous inner layer supported tissue regeneration, whereas the copper-doped upper film provided antibacterial protection. The system also showed potential as a customizable scaffold for advanced in vitro tissue models and organoid engineering, offering an alternative to animal testing.

Conclusion

The multifunctional bilayer patch represents a promising platform for chronic wound management by integrating regenerative and antibacterial properties. Its tunable composition, porosity, and biocompatibility also support applications in in vitro tissue engineering, highlighting its potential for both therapeutic and research use.


Cation selective membrane
Template molecule
Anion selective membrane
Voltage
Cation reservoir
CaCl2 pH 8
Anion reservoir
NaHCO3 pH 11

D1 – P029

The forces in the balance: FRET-based molecular tension sensors reveal the forces within CCM disease

Vorsselmans S.*[1,2], Aytekin S.[1], Oddou C.[2], Manicom Ramsamy T.[2], Senger F.[2], Faurobert E.[2] and Rocha S.[1]
[1]Molecular Imaging and Photonics Division, Chemistry Dept., KU Leuven, Leuven, Belgium; [2]Institute for Advanced Biosciences INSERM 1209 CNRS 5309, University Grenoble Alpes, Grenoble, France

Introduction

Cerebral cavernous malformations (CCM) are vascular lesions characterized by clusters of dilated, leaky capillaries in the central nervous system, arising from loss-of-function mutations in CCM genes. Endothelial dysfunction in CCM has been associated with altered mechanobiology, particularly a shift in the balance between cell-matrix and cell-cell forces. Previous work using cell-level biomechanical assays suggested reduced traction on the extracellular matrix in CCM endothelial cells, however, these approaches lack the molecular resolution needed to determine how forces are transmitted through individual adhesion proteins.

Aim

This study addresses the unresolved question of whether CCM pathology stems from changes in per-molecule force transmission or from altered structural organization of focal adhesions and adherens junctions on glass or biomimetic matrices.

Materials and Methods

We apply FRET-based molecular tension sensors to quantify piconewton forces across vinculin and VE-cadherin, enabling direct comparison of molecular mechanics at cell-matrix versus cell-cell adhesions. These cellular mechanical responses are compared between glass, polyacrylamide (PAA) hydrogel and polyisocyanide (PIC) hydrogels.

Results

Using FRET-based vinculin and VE-cadherin tension sensors, we reveal the CCM molecular force balance: diseased endothelial cells exhibit increased molecular tension across vinculin (cell–ECM adhesions) and decreased tension across VE-cadherin (cell–cell junctions). These molecular signatures correlate with distinct morphological phenotypes. CCM cells form larger, rounder focal adhesions, while adherens junctions appear thinner and structurally compromised. When cultured on mechanically relevant hydrogels, CCM focal adhesions undergo pronounced shape remodeling, adopting elongated morphologies indicative of altered mechanosensing.

Conclusion

This work provides the first molecular-scale map of force transmission in CCM. By integrating FRET-based tension readouts with adhesion morphology or relevant substrates, we uncover how CCM mutations reshape endothelial mechanobiology and highlight molecular tension sensors as powerful tools for mechanistic disease research.

Acknowledgements

We acknowledge KU Leuven Facultaire Luik Onderzoeksfonds (FLOF) and FWO grant G0C2422N for financial support.

D1 – P030

Effect of antimicrobial peptide position on the mechanical and antibacterial properties of silk-elastin-like protein (SELP)-based biomaterials

Wang L.Y.[1,2], Jeffries J.[3], López Barreiro D.[2]
[1]Dept. Physics and Astronomy, UCL, London, UK; [2]Dept. Chemical Engineering, UCL, London, UK; [3]Dept. Biochemical Engineering, UCL, London, UK

Introduction

The global antimicrobial resistance (AMR) crisis presents major implications for the performance of medical devices and implants, where bacterial colonisation and biofilm formation can lead to persistent infections. Antimicrobial peptides (AMPs) are promising alternatives to conventional antibiotics due to their broad-spectrum activity and reduced propensity to develop resistance. However, their direct application is limited by toxicity, instability and rapid degradation. To tackle some of these issues, recombinant silk–elastin-like proteins (SELPs) provide a versatile biomaterial platform with tunable mechanical properties, temperature-responsive self-assembly, and biocompatibility. In this study, we incorporate the antimicrobial peptide CM4 into SELP-based constructs and investigate their antibacterial activity in solution- and contact-modes.

Aim

To engineer SELP-CM4 proteins and investigate how sequence design, protein structure, and material processing conditions influence the antibacterial activity of the resulting biomaterials.

Materials and Methods

Recombinant SELP constructs containing antimicrobial peptide CM4 sequences at different positions were expressed in *Escherichia coli* and purified using inverse transition cycling (ITC), a technique utilising the lower critical solution temperature (LCST) behaviour of elastin-like repeats in the protein construct. The purified proteins were drop-cast into solid films for preliminary characterisation. Film stability in aqueous media was investigated as a prerequisite for solid surface-based antibacterial testing. Antibacterial activity was evaluated using both solution-based minimum inhibitory concentration (MIC) testing and surface-based bacterial viability assays.

Results

Optimisation of expression conditions significantly improved protein production, while adjustment of purification temperature during ITC enhanced the separation of full-length protein from truncated species. The SELP-CM4 constructs successfully formed stable protein films under aqueous casting conditions with ethanol annealing. Preliminary antibacterial tests demonstrate inhibitory activity against *E. coli*.

Conclusion

The results demonstrate the potential of using recombinant SELP-AMP fusion proteins as antibacterial biomaterials. This modular approach enables precise control over peptide position within the sequence, which in turn influences material properties. Our results provide guidelines for the design and manufacture of protein-based materials fused to AMPs that lead to an enhanced combination of mechanical and antibacterial properties. Overall, this work demonstrates the potential of SELPs as a promising platform for developing antimicrobial coatings and implantable biomaterials to combat AMR in healthcare settings.

Acknowledgements

This work was supported by the Engineering and Physical Sciences Research Council and the Biotechnology and Biological Sciences Research Council through the Centre for Doctoral Training in Engineering Solutions for Antimicrobial Resistance [grant number EP/Y035658/1].

D1 – P031

Cracking the potential: Characterisation of avian eggshell membranes for clinical and biomedical innovation

Oyhanart S.R.[1], Chen X.J.[1], Lu J.[1,2], Jin Z.[1], Petrovova E.[3], Demcisakova Z.[3], Knowles J.C.[1], Chau D.Y.S.[1]
[1]Division of Biomaterials and Tissue Engineering, UCL Eastman Dental Institute, University College London, London, UK; [2]School of Biochemistry, Faculty of Life Sciences, University of Bristol, Bristol, UK; [3]Dept. of Morphological Disciplines, University of Veterinary Medicine and Pharmacy in Kosice, Kosice, Slovak Republic

Introduction

Disease, degeneration and traumatic injuries continue to present significant clinical challenges in the demand for replacement tissues/organs. The chicken eggshell membrane (c-ESM) has gained significant interest as a novel biomaterial and drug-delivery candidate due to its intrinsic characteristics that include robust biocompatibility, high collagen content, fibrous architecture, potential for modification/enhancement, as well as its innate appeal in terms of sustainability. Although, the c-ESM has been extensively well studied and demonstrates significant translational/clinical impact in orthopaedic, dermal, ocular and dental applications; a comparative evaluation of other avian species for biomedical translational applications remains limited.

Aim

This project aimed to assess the native physical, mechanical and biological properties of eggshell membranes derived from chicken (*Gallus gallus*, c-ESM), duck (*Anas platyrhynchos*, d-ESM), and ostrich (*Struthio camelus*, o-ESM). In addition, enhancement of these membranes via the incorporation of additional exogenous growth factors and drugs was also investigated with an endpoint application of exploitation in regenerative medicine.

Materials and Methods

ESM samples were isolated using an optimised extraction protocol, and the associated physical and mechanical characteristics profiled using SEM, FT-IR, DSC and DMA. Biocompatibility was assessed using HDF/HOB/MC3T3 cells, with cell viability/proliferation/functionality as the endpoint readings. Angiogenic potential was determined using a (quail) chorioallantoic membrane assay, alongside additional immunohistochemical (IHC) profiling for WFL lectin, QH1, α-SMA, PHH3, and H&E staining. Drug incorporation and release from the membrane samples were quantified using a combination of *in vitro* (Franz cell) diffusion assay, and ELISA techniques.

Results

All membranes possess a collagen-rich fibrous network with high porosity, thermal stability (T_m> 135°C) and maintained a hydrophilic characteristic *in situ* as seen in Figure 1. The d-ESM resisted hydration-induced changes, whereas the o-ESM demonstrated a superior extensibility profile. *In vitro* drug-release summarised a sustained API delivery profile within 72h for all membranes, with c-ESM and d-ESM providing more a stable release than o-ESM. Cytotoxicity (LDH release), viability/metabolic activity, and Live/Dead staining suggest high biocompatibility characteristics. All membranes were incorporated within the quail ectoderm, and IHC staining revealed distinct species-specific profiles for neovascularization, endothelial integration, and microvascular network remodelling.




Figure 1. SEM images of the outer layer of ESM derived (A) chicken (B) duck (C) ostrich at 500X and 5000X magnification

Conclusion

This structured characterisation assessment has demonstrated that the ESM has the potential to be exploited for therapeutic and/or biomedical use, with a species-specific profile that could be further adapted to suit a defined application. With the additional appreciation of repurposing waste eggshells, sustainability, ethics and NAM considerations, this novel biomaterial may have significant implications in the field of biotechnology.

D1 – P032

On mechano-compatibility in scaffolds and testing-chamber for mechano-transduction at the interface bone/cartilage

Kłusak A.[1], Alvarado E.J.[2], Gazińska M.[1], Mantovani D.[2]
[1]Dept. of Polymer Engineering and Technology, Wrocław University of Science and Technology, Wrocław, Poland; [2]Lab Biomaterials and Bioengineering, Dept. Min-Met-Materials Eng & Regenerative Medicine, CHU de Quebec, Laval University, Quebec City, Canada

Introduction

Osteochondral defects represent a major clinical challenge due to the limited regenerative capacity of these tissues and their role in joint function, leading to osteoarthritis and disability, affecting over 500 million people worldwide. While bone and cartilage are largely addressed in literature, their interface is not. The osteochondral interface exhibits a unique progressive transition in mechanical properties, enabling the shift from soft, viscoelastic cartilage to stiff bone. This ensures efficient load distribution which trigger cell activities in physiological conditions. Reproducing this mechanical gradient in physiologically relevant conditions remains a key challenge, as cell activity depends on the mechanical microenvironment. Substrate stiffness and viscoelastic properties (G′, and G″) regulate mechanosensitive pathways directing chondrogenic or osteogenic differentiation. Beyond scaffold design, mechano-transduction is governed by the transmission of externally applied forces within the experimental system. Therefore, mechanical compatibility between scaffold and testing chamber is critical to ensure accurate load transfer and reproduce physiologically relevant stimuli. Integrating these considerations is essential to establish microenvironments that guide cell mechano-sensing and support osteochondral differentiation.

Aim

The goals were i) to design a new class of polymers, i.e. poly(glycerol adipate) elastomers, for scaffolding the osteochondral regeneration[1]; ii) to identify key mechanical parameters enabling physiologically-relevant mechano-transduction at the bone–cartilage interface.

Materials and Methods

A series of elastomers based on poly(glycerol adipate) (PGA) were synthesized and crosslinked using a diisocyanate-based chemical crosslinking agent. Their linear viscoelastic properties were characterized by Dynamic Mechanical Analysis. In parallel, a literature analysis was focused on mechanotransduction mechanisms in osteochondral tissues and on experimental systems designed to apply controlled mechanical stimulation to cell-seeded scaffolds.

Results


In PGA-based elastomers, variations in the amount and type of crosslinking agent modulate crosslinking density, resulting in tunable linear viscoelastic properties (G′, G″), and plateau modulus. This enabled precise regulation of stiffness and viscoelastic behavior within ranges relevant to osteochondral activity. From the literature, cells exhibit sensitivity not only to stiffness but also to viscoelastic dissipation and dynamic mechanical loading, which regulate differentiation pathways and extracellular matrix production. Furthermore, studies on mechanically stimulated culture systems demonstrate that mismatch between scaffold and chamber can alter load transmission and affect cell response.

Conclusion

The ability to modulate viscoelastic properties in PGA elastomers enabled the design of physiologically relevant osteochondral microenvironments. Scaffold viscoelastic properties are essential to guide cell mechano-sensing and differentiation, while the testing chamber must ensure accurate transmission of applied mechanical stimuli to support mechano-transduction and cartilage-to-bone transition.

Funding

The research was funded by The National Center for Research and Development as a part of the project REGENESIS, REvolutionising bone and cartilaGE reconstruction through Novel cell-instructive biomaterial and peptide-Enhanced Stem cell Immobilization Strategy (M-ERA.NET3/2024/98/REGENESIS/2025).



Schematic illustration how modulation of viscoelastic properties (G′, G″) in PGA elastomeric scaffolds, combined with cyclic mechanical stimulation, regulates force transmission and cell mechanosensing, driving spatially controlled chondrogenic and osteogenic responses within the construct.

References

[1]Gazińska M.A., Krokos A. Tunable structure and linear viscoelastic properties of poly(glycerol adipate urethane)-based elastomeric composites for tissue regeneration. *Journal of the Mechanical Behavior of Biomedical Materials* 2024; 153.

D1 – P033

Development of oxidized alginate-bioactive solubilised ECM bioink to enhance osteogenic differentiation for 3D bioprinting

Anbazhagan B.[1], Tsigkou O.[1], Basu B.[2]
[1]Dept. of Materials, University of Manchester, Manchester, UK; [2]Laboratory for biomaterials and translational center on biomaterials for orthopedic and dental applications, Indian institute of science, Bangalore, India

Introduction

Critical sized-bone defects resulting from tumours, infection, disease or trauma do not heal spontaneously without intervention, requiring advanced strategies for effective repair. Three dimensional (3D) printed scaffolds have demonstrated superiority since scaffolds with required porosity can be fabricated suitable to fit the required defect[1]. Cell-derived extracellular matrix (ECM) contains a heterogeneous mixture of proteins and bioactive components that better mimic the native cellular microenvironment and support cell adhesion, proliferation, and differentiation in a more controlled and simplified system[2].

Aim

The aim of this study was to develop and evaluate a droplet-printed oxidized alginate-ECM bioink for providing a biomimetic microenvironment to bone marrow mesenchymal stem cells (BM-MSC) and promoting effective osteogenic differentiation.

Materials and Methods

BM-MSCs were osteogenically differentiated for 7 day and decellularized ECM was mechanically solubilised. Solubilised ECM (S-ECM) was mixed with alginate gel (Sigma Aldrich, UK) at 0.3% (w/v) and formed into beads of size 3 ± 0.1 mm. Beads were maintained in osteogenic medium (Sigma-Aldrich, UK) for 14 days and stained with 2% alizarin red. Subsequently, alginate was oxidized with sodium periodate (Sigma-Aldrich, UK) to obtain 5% degree of oxidation, and a composite bioink with alginate (ALG): oxidized alginate (OX): ECM (3:1:0.3 ratio) was tested for gel stability for 10 days on 3D-printed PCL scaffolds using phalloidin (Invitrogen, UK) and DAPI (Abcam, UK) staining.

Results

Alizarin red staining was performed on osteogenically differentiated BM-MSCs encapsulated in alginate–ECM beads, with alginate-only beads used as a control. Alginate was chosen as a bioinert encapsulation matrix to isolate the effect of solubilized ECM. Moreover, BM-MSCs in alginate–ECM beads enhanced biomineralisation and calcium deposition (Figure (A)). Phalloidin staining at day 10 (Figure (B)) revealed that BM-MSCs were fully released from all bioink formulations and had attached and spread along PCL scaffold, indicating that adopted gel concentrations provided a transient, permissive microenvironment that allowed cells to progressively migrate out.

Conclusion

This work highlights how BM-MSC derived extracellular matrix influences cell fate and osteogenic commitment within an oxidised alginate-based bioink. Novel data on the 3D printability of ECM-enriched bioink and its effect on MSC attachment, and osteogenic differentiation will be presented.




Figure.(A) Alizarin red staining of osteogenic differentiated BM-MSCs encapsulated in alginate-ECM beads and basal medium is kept as control; (B) BM-MSCs loaded gels were incubated in PCL scaffolds, and fixed constructs were stained with phalloidin (green) and DAPI (blue) to visualise cell release and attachment to the scaffold; scale bar 300µm, n=3.

References

[1]Menarbazari A.A., Mansoori-Kermani A. A. 3D-printed polycaprolactone/tricalcium silicate scaffolds modified with decellularized bone ECM-oxidized alginate for bone tissue engineering. *International Journal of Biological Macromolecules* 265; 130827.
[2]Assunção M., Dehghan-Baniani D., Später T. Cell-derived extracellular matrix for tissue engineering and regenerative medicine. *Frontiers in bioengineering and biotechnology* 8; p.602009.

D1 – P034
Melt electrowritten biphasic scaffolds for osteotendinous interface engineering

Mussoni C.[1], Aslam M.[1], Groll J.[1], Ahmad T.[1*]
[1]Dept. of Functional Materials in Medicine and Dentistry, Institute of Functional Materials and Biofabrication (IFB), and Bavarian Polymer Institute (BPI), Julius-Maximilians-Universität Würzburg, Würzburg, Germany

Introduction
Tendons are highly organized connective tissues that transmit mechanical forces from muscle to bone. Their biomechanical performance depends on a hierarchically structured extracellular matrix rich in aligned collagen fibers assembled into fascicles. At the osteotendinous interface, this collagen-rich tendon region gradually transitions into a mineralized matrix, enabling efficient force transfer between soft and hard tissues. Due to this structural and compositional complexity, regeneration of the tendon-to-bone interface remains a major challenge in musculoskeletal tissue engineering.

Aim
This study aimed to develop a continuously printed biphasic melt electrowritten scaffold that mimics key structural and biochemical features of the osteotendinous interface and supports mesenchymal stem cell differentiation toward tenogenic and osteogenic lineages.

Materials and Methods
Biphasic fibrous scaffolds were fabricated by melt electrowriting as a continuous construct comprising two distinct compartments: a sinusoidal tendon-mimicking region coated with gelatin and a linear bone-mimicking region functionalized with a mineralized coating. Scaffold printability and structural fidelity were evaluated to determine the suitability of the manufacturing strategy. Mechanical characterization was performed to assess scaffold behavior in relation to tendon and interface applications. Surface modification and coating quality were analyzed, and cytocompatibility was examined after cell seeding. Mesenchymal stem cells were cultured on the scaffolds to investigate their potential for lineage-specific differentiation in both compartments.

Results
The biphasic scaffolds were successfully fabricated with high printing fidelity and continuous integration between the tendon-like and bone-like regions. The sinusoidal architecture provided a compliant fibrous structure, whereas the mineralized compartment introduced features relevant to the hard tissue side of the interface. Surface functionalization was stable and supported cytocompatibility. Cellular evaluation indicated that the scaffold design and compartment-specific functionalization provided instructive cues for mesenchymal stem cells, supporting tenogenic commitment in the tendon compartment and osteogenic differentiation in the mineralized compartment.

Conclusion
Continuously printed biphasic melt electrowritten scaffolds represent a promising platform for engineering the osteotendinous interface. By combining defined microarchitecture with compartment-specific surface functionalization, this approach offers a biomimetic and versatile strategy for guiding stem cell fate and developing advanced in vitro models for tendon-to-bone regeneration.

Acknowledgements
This study was supported by the German Research Foundation (DFG) through the Collaborative Research Center SFBTRR225 (project number 326998133; subprojects C06, B02, A07).

D1 – P035

Development of extracellular matrix protein-decorated hydrogels for vascularisation

Chang Y.J.[1,2], Hosty L.[1], Petit N.[1], Hodgkinson T.[1], Browne S.[1,2]
[1]Tissue Engineering Research Group, Royal College of Surgeons in Ireland, Dublin; [2] CÚRAM Centre for Research in Medical Devices, University of Galway, Galway, Ireland

Introduction

The formation of vascular networks remains a major barrier in tissue engineering, as insufficient vascularisation limits size and complexity of tissue-engineered constructs. Extracellular matrix (ECM) composition regulates key cell behaviours, including vascular network formation, by engagement with integrins and sequestration of proangiogenic growth factors. Hyaluronic acid (HyA)-based hydrogels provide a biocompatible platform for synthetic ECMs with tuneable properties. However, HyA hydrogels lack ECM ligands to support cell adhesion and cell-ECM interactions. This study aims to develop HyA-based hydrogels decorated with ECM proteins to enhance network formation by encapsulated stem cell-derived human vascular cells.

Materials and Methods

HyA was functionalised with acrylate groups (AcHyA), with modification confirmed by nuclear magnetic resonance (NMR). Fibronectin (FN) or laminin (LM) was conjugated to AcHyA by Michael-type addition and crosslinked using a bis-cysteine-containing matrix metalloproteinase-cleavable peptide crosslinker. Hydrogel swelling, degradation, and storage modulus were characterised. Growth factor sequestration was assessed by fluorescence recovery after photobleaching (FRAP) of FITC-tagged vascular endothelial growth factor (VEGF), and confirmed by VEGF release evaluated using enzyme-linked immunosorbent assay (ELISA). Vascular cells were differentiated from human induced pluripotent stem cells using standard protocols, then encapsulated in HyA hydrogels and visualised using F-actin staining.

Results

^{1}H NMR confirmed ~26% HyA acrylation and consumption of acrylate groups following FN/LM conjugation. Decoration of HyA-based hydrogels with ECM proteins did not alter swelling, degradation, or storage modulus. FRAP demonstrated specificity of VEGF sequestration by reduced diffusion of VEGF but not of similarly-sized 20kDa FITC-dextran from ECM-decorated HyA hydrogels compared to HyA-only hydrogels [Fig 1]. HyA-based hydrogels decorated with ECM protein promoted spreading of encapsulated vascular cells over 7 days [Fig 2].

Conclusion

Decoration of HyA-based hydrogels with FN/LM enhances growth factor retention and vascular cell elongation without altering mechanical properties, enabling independent tuning of bioactive and mechanical properties of HyA-based hydrogels. ECM-decorated HyA hydrogels supported elongation of vascular cells, crucial for the development of vascular networks. This platform supports the development of vascularised 3D tissue constructs for *in vitro* models and tissue repair applications.

Acknowledgements

This research was supported by funding from the EPSRC-SFI LifETIME centre for doctoral training programme (18/EPSRC-CDT/3583) and CÚRAM Research Ireland Centre for Medical Devices (13/RC/2073_P2).




Fig 1: ECM protein-decorated hydrogels delayed release of VEGF without affecting diffusion of similarly-sized molecules. (A) Release of VEGF from hydrogels quantified by ELISA. Normalized fluorescence recovery and diffusion rates of (B) 20kDa FITC-Dextran and (C) FITC-conjugated VEGF. Data represents mean± SD (n=3). Analysis performed using one and two-way Anova;p<0.05.




Figure 2: Encapsulated induced pluripotent stem-cell derived endothelial cells and stromal cells demonstrate enhanced adhesion and spreading in ECM protein-decorated hydrogels. (A) Confocal images of day 14 encapsulated cells. Spreading noted by arrows. Scale bar is 200μm. (B) Metabolic activity of cells evaluated with Alamar blue. (C) Average cell area and (D) average feret diameter of encapsulated cells. Data represents mean± SD (n=3). Analysis performed using one-way Anova;p<0.05.

D1 – P036

Microdroplets-assisted fibroblast adhesion for advanced stent functionalization in vascular surgery

Di Cosmo S.[1], Vitaliti A.[2], Perilli G.[2], Tani A.[2], Valenzuela M.[2], Toumia Y.[3], Bedini A.[4], Da Ros V.[1], Domenici F.[2]
[1]Dept. of Biomedicine and Prevention, University of Rome "Tor Vergata", Rome; [2]Dept. of Chemical Sciences and Technologies, University of Rome "Tor Vergata", Rome; [3]National Institute for Nuclear Physics, INFN sez. Roma Tor Vergata; [4]INAIL, Italian Workers's Compensation Authority, Rome, Italy

Introduction

Flow diverter (FD) stents are widely used in the endovascular treatment of intracranial aneurysms. Their dense braided metallic structure reduces intra-aneurysmal flow, promotes thrombosis, and allows for progressive occlusion[1]. However, long-term effectiveness depends on rapid and complete re-endothelialization, which may be hindered by the inertness of metallic materials that trigger inflammatory responses and compromise device safety and performance[2]. ECM-based coatings present a promising strategy to reduce inflammation, support endothelialization, and improve tissue integration[3,4].

Aim

This study proposes a surface modification strategy based on a biocompatible three-dimensional scaffold composed of decafluoropentane (DFP) core and crosslinked telechelic polyvinyl alcohol (t-PVA) shell mesodroplets (DFP-PVA-DPs), functionalized with type I collagen (DPs-Col). The system is designed to promote indirect cell-mediated extracellular matrix (ECM) deposition, improving biological integration.

Materials and Methods

DFP-PVA-DPs were generated by emulsifying decafluoropentane (DFP) with 1% (w/v) telechelic polyvinyl alcohol (t-PVA) under stirring (1300 rpm, 6 h). Collagen functionalization was achieved at the droplet-water interface through reductive amination between the aldehyde moieties of the shell with the exposed collagen amines.
Human foreskin fibroblasts (HFFF2) and human aortic adventitial fibroblasts (HAoAF) were cultured on both collagen-functionalized droplets (DPs-Col) alone and within the previously co-added DPs-Col-nitinol stent system. Sterilized droplets were distributed in well plates, and pre-conditioned nitinol stents were positioned before cell seeding. Cell viability was evaluated using Calcein-AM staining. Extracellular matrix (ECM) deposition and cytoskeletal organization were assessed by immunofluorescence, while morphological characterization was performed by scanning electron microscopy (SEM).

Results

Calcein-AM assays demonstrated significantly increased adhesion and spreading of both HFFF2 and HAoAF cells on collagen-functionalized droplets (DPs-Col) compared to non-functionalized controls (DPs-No Col), while the latter confirmed the intrinsic biocompatibility of the scaffold (Fig. 1).
After 15 days in the DPs-Col–stent system, scanning electron microscopy analysis revealed HFFF2 clusters distributed along the stent struts. Filopodia and extracellular matrix bridges connecting adjacent filaments were observed, indicating possible active-matrix deposition and structural integration. These results underscore the scaffold's ability to support cellular colonization of otherwise biologically inert metallic surfaces (Fig. 2).

Conclusion

The collagen-functionalized droplets scaffold enhances cellular adhesion and extracellular matrix deposition on flow diverter stents, representing a promising strategy to mitigate foreign-body reactions. This biofunctionalization approach supports cellular integration and may improve long-term stent biocompatibility.




Fig.1: a): Schematic overview of the fibroblast seeding protocol. Sterilized collagen-functionalized (DPs-Col) and non-functionalized (DPs-No Col) droplets were distributed uniformly to cover each well. Human fibroblasts were seeded dropwise to ensure homogeneous distribution. Cell viability and surface coverage were evaluated at 7 and 15 days. Illustration created with BioRender.
b): Cellular coverage and viability analysis of HFFF2 and HAoAF cultured on DPs-Col and DPs-No Col. Confocal microscopy images (20X) show cells (green) and DFP-PVA droplets (red) at 15 days. Surface coverage was quantified. Compared to DPs-No Col, collagen functionalization resulted in increased cellular coverage for both cell lines. For HFFF2, a significant increase in cell growth was observed at 7 days, whereas for HAoAF enhanced coverage was evident at 15 days. In contrast, the DPs-No Col condition showed no significant differences between 7 and 15 days.




Fig. 2: Schematic representation of fibroblast seeding within the composite DPs-Col–stent system. The stent was pre-cultured with fibroblasts for 7 or 15 days to promote initial extracellular matrix (ECM) deposition and enhance subsequent cell seeding. Prior to reseeding, the stent was immersed in 90% ethanol for at least 10 minutes, washed, and reassembled with freshly prepared DPs-Col and cells of the same lineage. At 15 days, constructs were analyzed by SEM, immunofluorescence, or Calcein-AM confocal assay. Illustration created with BioRender. Call-out: Scanning electron microscopy (SEM) of the HFFF2 + DPs-Col + Silk Vista™ nitinol stent system, after droplet removal at 15 days of culture. SEM images at 2550X magnification show a fibroblast cluster adherent to the stent struts, with evident cytoplasmic protrusions and filamentous extensions, indicating active cell anchorage and matrix interaction (yellow arrows).

References

[1]Alderazi Y. J., Shastri D., Kass-Hout T., Prestigiacomo C. J., Gandhi C. D. Flow diverters for intracranial aneurysms. *Hindawi Publishing Corporation Stroke Research and Treatment* 2014.
[2]Manivasagam V. K., Sabino R. M, Kantam P., Popat K. C. Surface modification strategies to improve titanium hemocompatibility: A comprehensive review. *Mater. Adv.* 2021; 2; 5824-5842.
[3]Tu Q., Zhao Y., Xue X., Wang J., Huang N. Improved endothelialization of titanium vascular implants by extracellular matrix secreted from endothelial cells. *Tissue Eng Part A* 2010; 16(12).

D1 – P037

A nucleus pulposus–inspired microfluidic 3D culture-on-a-chip for modeling mechanical loading in intervertebral disc tissue

Torabi Rahvar P.[1], González-Blanco L. [1,2], Gantenbein B.[1,3]
[1]Tissue Engineering for Orthopaedics and Mechanobiology, Dept. for BioMedical Research (DBMR), Faculty of Medicine, University of Bern, Bern, Switzerland; [2] IDIS (Instituto de Investigación Sanitaria de Santiago), NEIRID Lab, Santiago de Compostela, Spain; [3] Dept. of Orthopaedic Surgery & Traumatology, Inselspital, Bern University Hospital, Faculty of Medicine, University of Bern, Bern, Switzerland

Introduction

Intervertebral disc degeneration (IVDD) is a leading cause of chronic low back pain, affecting over 500 million people worldwide. Degeneration typically initiates in the nucleus pulposus (NP), characterized by reduced cellularity and extracellular matrix (ECM) breakdown. While Organs-on-Chip (OoC) platforms offer promising avenues for modeling IVDD and drug screening, current systems often rely on simplified hydrogels such as agarose or fibrin, which fail to replicate the native NP microenvironment. Additionally, the mechanical complexity and compartmental crosstalk within the intervertebral disc remain challenging to reproduce *in vitro*.

Aim

This study aimed to develop a physiologically relevant NP-on-chip model using a biomimetic hydrogel and to evaluate its mechanical stability and suitability for downstream protein analysis under dynamic loading conditions.

Materials and Methods

HA and COL II were functionalized with tyramine groups to enable enzymatic crosslinking using horseradish peroxidase (HRP) and hydrogen peroxide (H_2O_2), yielding a gelation time of ~2 minutes. Human NP cells were encapsulated at a density of 8×10^6 cells/mL and introduced into a microfluidic chip (Re-plate™, Chiron on-chip biotechnologies B.V., Maastricht, NL). The chip design and loading strategy are illustrated in Figure 1a, and successful encapsulation of cells within the HA/COL II hydrogel is shown in Figure 1b. Constructs were cultured under static conditions for one week, followed by dynamic loading for an additional week using cyclic air pressure (400 mbar, 0.5 s frequency, 1 hour/day). The loading setup and hydrogel deformation under compression are presented in Figure 1c,d. After 14 days, hydrogels were retrieved, cell lysates were sonicated on ice, and protein concentrations were quantified using the Bradford assay.

Results

The HA/COL II hydrogel supported homogeneous cell encapsulation and stable integration within the microfluidic chip (Figure 1b). The constructs maintained structural integrity under repeated cyclic compression, demonstrating suitable mechanical properties without cracking or failure (Figure 1c,d). Quantitative analysis revealed no significant difference in total protein content between dynamically loaded and unloaded conditions (Figure 2a). Protein extraction yielded sufficient quantities for downstream applications, such as Western blotting (Figure 2b).

Conclusion

We developed a biomimetic NP-on-chip platform that combines physiologically relevant ECM components with controlled mechanical stimulation. The system demonstrates mechanical robustness and enables reliable protein recovery for molecular analysis. This platform provides a promising tool for studying IVDD pathogenesis and evaluating therapeutic strategies in a controlled microphysiological environment.

Acknowledgements

This work was supported by the SNSF Weave Grant (#320030E_224175) and the DFG (#437213841).




Figure 1. Human nucleus pulposus (hNP) cells encapsulated in a hyaluronic acid (HA)/collagen type II (COL II) hydrogel. **(a)** Schematic illustration of the microfluidic chip design. **(b)** Transmitted light image of the chip loaded with hNP cells at a density of 8 × 10^6 cells/mL. **(c, d)** Transmitted light images of the chip under unloaded (c) and loaded (d) conditions. Scale bars: 250 µm.




Figure 2. (a) Total protein content measured by Bradford assay (expressed as mg/ml) of cell-encapsulated samples extracted from the chips. (b) Ponceau S staining was performed to confirm successful transfer of total protein onto the membranes. Data are represented as mean ± SEM from two independent experiments.

D1 – P038

Harnessing natural–synthetic polymer synergy for multifunctional tissue engineering hydrogels

Deroose N.[1], Bogaert B.[1], Haddleton D.[2], Dubruel P.[1]
[1]Polymer Chemistry & Biomaterials Group, Centre of Macromolecular Chemistry, Dept. of Organic and Macromolecular Chemistry, Ghent University, Ghent, Belgium; [2]Dept. of Chemistry, University of Warwick, Coventry, UK

Introduction

Natural and synthetic polymers offer distinct advantages towards regenerative medicine, while their properties are often orthogonal, requiring trade-offs when used individually. Gelatin, the gold standard, naturally exhibits cell-adhesivity and biodegradability, whilst it suffers from low mechanical tuneability, a UCST around physiological conditions and inferior porosity after hydrogel production. In contrast, synthetic polyesters (e.g., PCL, PLA and PGA) or polycarbonates (e.g., PTMC) often display mechanical tuneability and low batch-to-batch variability, but lack bioactivity.

Materials and Methods

To overcome these limitations, we developed a modular strategy to graft amphiphilic polyesters and polycarbonates onto gelatin via thiol-ene chemistry, yielding a diverse library of brush-type polymers with variable grafting densities and graft lengths. This approach enables synergetic integration of the bioactivity of gelatin with the mechanical robustness and processability of synthetic polymers. Detailed characterization revealed high coupling efficiencies (>90%) and tuneable grafting densities (30–100% of available amine functionalities).

Results

The grafted materials exhibited self-assembly driven by hydrophobic interactions, leading to enhanced porosity (>200 µm) and a broad range of mechanical properties (E′: 1–70 kPa), suitable for soft to medium-soft tissue applications (see Figure 1). Dual cross-linking enabled rapid covalent gelation (1.7–2.3 s) following physical assembly, further increasing the application potential of the produced materials. Cytocompatibility assays confirmed high cell viability (>90%) without compromising cell interactivity, highlighting the potential of these materials for biofunctional scaffold development in tissue engineering. Furthermore, a translation to continuous flow syntheses was performed in collaboration with the University of Warwick (Prof. David Haddleton), enabling the introduction of highly reproductive and up-scalable synthetic conditions to this advanced, hybrid polymer system.




Figure 1. Overview of covalent cross-linking of physical hydrogels into covalent hydrogels, yielding highly tuneable swelling (A), porosity (B and D) and mechanical properties (C).[1]

Conclusion

By overcoming key limitations of natural polymers, these strategies provide a widely applicable platform to graft hydrophobic polyesters or polycarbonates onto hydrophilic (bio)polymers, enabling the next generation of multifunctional hydrogels for advanced tissue engineering.

Acknowledgements

N.D. acknowledges the financial support of the Research Foundation Flanders (FWO) in the form of an FWO SB PhD fellowship (1S27323N). B.B. also acknowledges the support of the Research Foundation Flanders (FWO) in the form of an FWO SB PhD fellowship (1SHE724N). The authors would also like to thank the NMR expertise center (Ghent University) for providing support and access to its NMR infrastructure. The 400 and 500 MHz used in this work have been funded by a grant/project of the Research Foundation Flanders (FWO) and the “Bijzonder Onderzoeksfonds” (BOF) (FWO I006920N, BOF.BAS.2022.0023.01, AUGE/09/2006).

References

[1]Deroose N., Bogaert B., Dubruel P. Amphiphilic Brush-Type Hybrid Gelatin-Based Materials Using Thiol–Ene Coupling: A Platform for Polyester or Polycarbonate Grafting. *ACS Applied Polymer Materials* 2026,;8 (2); 931–948. DOI: 10.1021/acsapm.5c03637

D1 – P039
Calcifying microalgae as functional nano-platforms for bone fillers


Galluppo E.[1], Bordiga M.[2], Marsich E.[1], Donati I. [1]
[1]Dept. of Life Sciences, University of Trieste; [2]National Institute of Oceanography and Applied Geophysics, Trieste, Italy

Introduction
Bone regeneration is a significant task within regenerative medicine, and one of the focusses has been the creation of novel biomaterials that restore structural integrity and promote biological healing. Bone fillers should promote and provide mechanical support, as well as being osteoconductive and biologically degradable. However, synthetic materials often fail to reproduce the hierarchical structures and nanoscale features found in natural biomineralized materials, which play a crucial role in cell-material interaction[1]. Because of this, natural nanostructured materials inspire the development of new scaffolds. Coccolithophores, a group of calcifying marine microalgae, produce mineral exoskeletons made up of nanometric calcite crystals, known as coccoliths, that are arranged in highly organised and species-specific architectures that current synthetic methods cannot replicate.

Materials and Methods
Gephyrocapsa huxleyi (formerly named *Emiliania huxleyi*) is a coccolithophore model, whose coccoliths, measuring 2–4 µm, feature a double shield oval ring linked by a central tube, made up of approximately 30-40 radially arranged calcite segments (Figure 1)[2]. *G. huxleyi* produces coccoliths that can be sourced reproducibly and comprised of well-defined structures, providing cover for coccoliths from polysaccharides that could enable biomimetic scaffolds to modulate osteoblastic activity. Research combines structural, biochemical, and cellular analyses.

Results
The first studies on the biological properties of coccoliths have shown that they can support the adhesion and spread of new osteoblastic cells since coccoliths have rigid mineral surfaces that are comparable to the mineralised part of the bone. The structural features of coccoliths, such as roughness, groove spacing, and order on the nanoscale, as seen through imaging techniques at the nanoscale, influence the orientation and behaviour of osteoblasts. Additionally, coccoliths have a large surface area, which may be a contributing factor to increased cell attachment. They were embedded in biocompatible hydrogels so that their nanotopography would be preserved, while the hydrogels would be sufficient to support osteoblastic cell culture in a stable environment.

Conclusion
The combination of a mineral skeleton and an organic matrix in coccoliths may also elicit favourable biological responses, demonstrating that coccolithophores can be an excellent bioderived source for the development of novel sustainable, nanostructured biomaterials.


Figure 1, *Gephyrocapsa huxleyi* coccolith examined at SEM[2].

References
[1]Ivanova N, Ivanov S, Peev S, Dikova T. Types of Bone Substitutes and Their Application in Regenerative Medicine: A Systematic Review. *Journal of Functional Biomaterials*. 2025; 16, 341.
[2]https://www.mikrotax.org/Nannotax3/maindb/Emiliania_huxleyi

D1 – P040

Multilayered extracellular matrix-derived scaffolds direct progenitor cell differentiation in vitro and osteochondral tissue formation in vivo

Gonnella G.[1,2,3], Karam A.[1,2], Strong O.[1,2], Kronemberger S.G.[1,2], Brama P.A.J.[5], Kelly D.J.[1,2,3,4]
[1]Trinity Centre for Biomedical Engineering, Trinity Biomedical Sciences Institute, Trinity College Dublin, Dublin, Ireland; [2]Dept. of Mechanical, Manufacturing and Biomedical Engineering, School of Engineering, Trinity College Dublin, Dublin, Ireland; [3]Advanced Materials and Bioengineering Research Centre (AMBER), Royal College of Surgeons in Ireland and Trinity College Dublin, Dublin, Ireland; [4]Dept. of Anatomy & Regenerative Medicine, Royal College of Surgeons in Ireland, Dublin, Ireland; [5]School of Veterinary Medicine, University College Dublin, Ireland

Introduction

Osteochondral defects remain difficult to repair because durable regeneration requires coordinated restoration of articular cartilage and subchondral bone, including appropriate regional phenotypes, matrix composition and tissue organisation. Tissue-specific extracellular matrix (ECM)-derived scaffolds provide native biological cues, but their regenerative performance also depends on scaffold stiffness and architecture, which influence cell infiltration, differentiation and neotissue development. The aim of this study was to develop a multilayer ECM-derived scaffold with mechanically tuned cartilage- and bone-like regions as an off-the-shelf implant for osteochondral repair.

Materials and Methods

Cartilage- and bone-ECM scaffold formulations were first screened to identify compositions that preferentially supported chondrogenic or osteogenic differentiation of mesenchymal stromal cells (MSCs). Soft 2% cartilage-ECM, stiffer 5% cartilage-ECM and 6% bone-ECM formulations were then combined into multilayer constructs using a lyophilisation protocol designed to increase pore size and promote pore alignment. Scaffolds were assessed in vitro, following subcutaneous implantation in nude mice, and in a preliminary caprine osteochondral defect study.

Results

Screening studies showed that 2% cartilage-ECM scaffolds enhanced expression of the chondrogenic markers COL2A1, ACAN and SOX9, whereas 5% cartilage-ECM scaffolds increased ALPL and COL10A1 expression, indicating a shift towards a more hypertrophic phenotype. Increasing the stiffness of bone-ECM scaffolds increased RUNX2 and IBSP expression, supporting their use as an osteogenic layer. These data informed the final multilayer design, comprising cartilage-ECM regions of 2-5% (w/v) and a 6% (w/v) bone-ECM region. In vitro, multilayer scaffolds supported robust extracellular matrix deposition, with cartilage regions favouring cartilage-like matrix production and the bone region showing greater expression of markers associated with hypertrophy and osteogenesis. Following subcutaneous implantation, cell-seeded scaffolds supported region-specific tissue formation, with enhanced mineralised, bone-like matrix deposition in the bone region, while the cartilage region supported more cartilage-like extracellular matrix deposition (Figure 1). This spatial patterning suggested that the scaffold architecture and tissue-specific matrix composition together helped guide local progenitor cell behaviour. In a preliminary analysis of an early explant from a caprine osteochondral defect model, acellular multilayer scaffolds showed cartilage bridging and osteointegration relative to empty controls (Figure 2).

Conclusion

Together, these findings demonstrate that multilayer, tissue-specific ECM-derived scaffolds can direct region-specific progenitor cell differentiation and tissue formation across osteochondral-like environments. By integrating compositionally distinct cartilage- and bone-ECM regions with aligned porous architecture, this platform offers a promising acellular and off-the-shelf strategy for guiding spatially organised repair. These results support continued evaluation of this system in orthotopic large-animal models for osteochondral defect repair.




Figure 3: In vivo evaluation of multilayer tissue-specific ECM scaffolds following 8 weeks of subcutaneous implantation in mice. Scaffolds were implanted as empty controls, MSC/MSC constructs, or ACP/MSC constructs and analysed in three predefined regions corresponding to the AC, interface, and BN phases (a). MicroCT images and quantification show mineral deposition within the explanted scaffolds (b, c). Representative H&E and Masson's trichrome staining are shown together with regional quantification of pore infiltration, vessel density, and collagenous matrix deposition (d – h). Biochemical analysis of DNA, sGAG, and collagen content was performed separately for the AC and BN regions (j – l). Data are presented as mean ± standard deviation, with statistical significance indicated in the figure. For microCT N = 8 samples per group, for histology n = 16 points (4 samples

per group x 4 slices per sample), for biochemical analysis N = 4 samples per group. *p < 0.05, **p < 0.005, ***p < 0.001, ****p < 0.0001. Scale bar = 500 µm, 200 µm.




Figure 4: Preliminary evaluation of multilayer ECM scaffolds in a goat osteochondral defect model. Schematic illustration of scaffold fabrication, surgical creation of the osteochondral defect, and implantation workflow (a, b). Representative gross images of empty and ECM-treated defects at the study endpoint are shown (c). MicroCT reconstructions and histological sections from an early explant collected 1 month after implantation are presented to provide preliminary assessment of tissue distribution and scaffold integration (d). H&E staining was used to

assess tissue infiltration and osseous integration, while Alcian Blue staining was used to evaluate cartilage-like matrix deposition and integration at the defect margins (e). Scale bar = 2 mm, 200 µm.

D1 – P041

Balancing mechanics and cell adhesion in elastin-like polypeptide–collagen hydrogels

Visser C.M.[1], Tam N.W.[1], Hodes L.[2], Daran J.[2], Koenderink G.H.[1]
[1]Dept.of Bionanoscience, Kavli Institute of Nanoscience; [2]Dept. of Biotechnology, Technical University Delft, Delft, The Netherlands

Introduction

The mechanical stability of mammalian tissues crucially depends on a biopolymer network known as the extracellular matrix (ECM). The ECM is not just a mechanical scaffold, but its unique mechanical and structural properties at the same time provide cues to regulate mechanosensitive cell behaviour needed for tissue homeostasis and wound repair. To replicate these properties in biomaterials useful for tissue engineering, hydrogels are widely used; however, many traditional hydrogel systems fail to capture the intricate balance between elasticity, viscous dissipation and nonlinear strain-stiffening found in native tissues.

Collagen and elastin are key ECM components that provide complementary mechanical functions: collagen forms a stiff fibrillar network that withstands tensile forces, while elastin imparts flexibility and resilience. We therefore hypothesized that composites of these two proteins provide a way to develop tuneable biomaterials that mimic the versatile mechanics of mammalian tissues.

Materials and Methods

In this study, we designed and characterized composite biomaterials combining native bovine collagen type I with elastin-like polypeptides (ELPs). ELPs are biomimetic proteins inspired by elastin that exhibit reversible coacervation above a sequence-dependent transition temperature (T_t), making them attractive for hydrogel design. Using shear rheology, we examined both the polymerization dynamics and the nonlinear mechanical response of these materials. Furthermore we visualized the network using confocal microscopy and we examined the ability of the material to promote cell adhesion.

Results

Our results demonstrate that the composite material undergoes a two-phase temperature-triggered gelation process, corresponding to ELP coacervation and collagen fibril formation (figure 1). After a thermal cycle, a residual network remains, indicating enhanced structural integrity. In the nonlinear regime, we observed that the composite material retains the characteristic strain-stiffening behaviour of collagen and ELP hydrogels and enhanced stiffness and rupture strength due to the interaction between ELP and collagen. Finally we show that cell adhesion can be modulated by including RGD-based cell adhesion motifs in the ELP sequence (figure 2).

Conclusion

Our findings highlight the potential of collagen-ELP composites as advanced biomaterials with tuneable mechanical properties. Future research will focus on refining the mechanical and biological functionality of the material and replacing native (animal-derived) collagen by recombinant collagen to enhance controllability.

Acknowledgements

This work is part of the research programme Open Technology Programme “SUSTAINER” with project number 19739, which is financed by the Dutch Research Council (NWO).




Figure 1. Structural and rheological characterization of ELP-collagen type I hydrogels. A) 10µm z-projection of a confocal microscopy image of fluorescently labeled ELP (cyan) and bovine atelocollagen type I (magenta) at 37°C. B) Storage modulus (G') of 10mg/ml ELP (dashed), 2.5mg/ml atelocollagen type I (dotted) and composite (solid) hydrogels during temperature ramps between 5 °C and 37 °C, with temperature profile shown in red.




Figure 2. Attachment and viability of HUVEC endothelial cells on ELP coatings. A) HUVECs cultured on a tissue culture polystyrene surface coated with ELP-RGD6. B) Quantified cell viability showing that ELP-RGD6 supports higher cell viability and promotes greater cell growth than uncoated surfaces, surfaces coated with base ELP, and even a gelatin coating.

D1 – P042

Optimization of cell encapsulation parameters in GelMA microgels using microfluidics

Marchena F.S.J.[1], Ipsic A.[1], Troncoso-Afonso, L.[3,4], Włodarczyk-Biegun M.K.[1,2]
[1]Zernike Institute for Advanced Materials, University of Groningen, Groningen, The Netherlands; [2]Biotechnology Centre, The Silesian University of Technology, Gliwice, Poland; [3]CIC BiomaGUNE, Basque Research and Technology Alliance (BRTA), 20001 Donostia-San Sebastián,Spain; [4] Centro de Investigación Biomédica en Red de Bioingeniería Biomateriales, y Nanomedicina (CIBER-BBN), Paseo de Miramón 182, 20014 Donostia-San Sebastián, Spain

Introduction

Jammed microgels are a versatile and universal material platform, very well suitable for processing using 3D printing and bioprinting approaches. The incorporation of cells inside of microgels, known as encapsulation, is a central focus of our work. This technique is valuable because it allows for combining multiple cells in one system, enabling complex co-culturing experiments, and provides a protective barrier for cells during printing conditions that would otherwise be too harsh for bare cells. However, before these applications can be fully realized, the specific parameters of the encapsulation procedure must be fine-tuned. This study focuses on three main areas: the optimization of the encapsulation setup, determining the best cell concentration to maintain viability, and improving the methods used to keep cells in suspension within the microfluidic system to ensure a homogeneous distribution.

Materials and Methods

We used flow-focusing microfluidic chips to generate the microgels. The material phase consisted of GelMA, while the continuous phase was oil supplemented with 3% Span 80. All fluids were operated using filtered pneumatic microfluidic pumps to ensure precise flow control. For the biological component, we used MDA-MB 231 cells. To prevent contamination during the collection process, the encapsulated cells were gathered in a tube maintained under positive filtered air pressure. To prevent the cells from settling and to keep the cell-GelMA mixture as homogeneous as possible before encapsulation, a magnetic stirrer bar was used within the supply tube.

Results

Initial trials were conducted using a concentration of 1 million cells/ml. We observed that the resulting distribution of cells within the microgels followed a wide Gaussian curve. This indicates a high level of variability in the number of cells per droplet rather than a consistent, uniform loading. Additionally, cell activity after encapsulation appeared to be at a minimum. These findings suggest that the current method of using a magnetic stirrer bar for agitation may be insufficient or too harsh, potentially contributing to the low cell viability observed in these trials.




Fig 1. Example image of encapsulated cells

Conclusion

The results of our initial trials show that while encapsulation is achievable with the current microfluidic setup, there are significant hurdles regarding distribution and cell health. The wide distribution of the cells suggests that the suspension was not as homogeneous as required. Furthermore, the low cell activity points to a need for a gentler or more effective method of keeping cells in suspension within the microfluidic system.

Acknowledgements

ERC-2024-Stg #101161716 JAM2PRINT

D1 – P044

Bioinspired xeno-free mesenchymal stem cells-based tissue engineered medicines combining macromolecular crowding and electrospinning technologies for wound healing applications

C. Gonçalves, D.[1], Zeugolis, D. I.[2], Walsh-Korb, Z.[3]
[1]Conway Institute of Biomolecular & Biomedical Research, School of Mechanical & Materials Engineering, University College Dublin, Dublin, Ireland; [2]Regenerative, Modular & Developmental Engineering Laboratory (REMODEL); [3]Dept. of Biomedical Engineering, University of Basel, Basel, Switzerland

Introduction

Commercially available advanced therapy medicinal products for wound healing applications are characterised by their long *in vitro* culture periods and supplementation with animal-derived sera, which are associated with high manufacturing costs and immunogenicity, respectively. Although mesenchymal stromal cells (MSCs) possess superior immunomodulatory and regenerative capacity to keratinocytes and fibroblasts, they have yet to be explored in this field. The use of an adequate scaffold should also be considered to provide architectural support for tissue regeneration. Taking this into account, we aim to develop a tissue engineered medicine using electrospun scaffolds, xeno-free human umbilical cord MSCs (XF hUC-MSCs) and macromolecular crowding (MMC). The combination of electrospun scaffolds that closely resemble native skin ECM, XF hUC-MSCs that have demonstrated superior healing capacity to any other cell population and MMC that has been shown to enhance and accelerate extracellular matrix (ECM) deposition makes this a safe and innovative approach that allies affordability with efficiency.

Materials and Methods

Poly(L-lactide-co-ε-caprolactone (PLCL) electrospun scaffolds were fabricated and surface and mechanical characterisation were performed using scanning electron microscopy, contact angle analysis and tensile testing.
XF hUC-MSCs from 3 donors were seeded on tissue culture polystyrene (TCP) and cultured without and with MMC agents (carrageenan (CR) and poly(acrylic acid) (PAA)). Basic cell functions and protein deposition were assessed after 4, 6 and 8 days in culture. To develop a three-dimensional (3D) tissue engineered construct, cells were seeded on electrospun scaffolds and cultured under MMC conditions. ECM deposition was assessed after 6, 10 and 14 days.

Results

Electrospun scaffolds exhibited a preferential fibre orientation with a low degree of fibre dispersion, low porosity and a considerable thickness. They also presented hydrophobic behaviour and mechanical properties within the range of human skin (Figure 1).
On TCP, CR and PAA induced an increase in ECM deposition without affecting XF hUC-MSC morphology, viability and metabolic activity. These data were confirmed among three donors. A similar trend in ECM deposition was verified for cells cultured on electrospun scaffolds (Figure 2).

Conclusion

In this study, a skin-like PLCL electrospun scaffold that mimicked natural skin ECM architecture, wettability and mechanical properties was developed. CR and PAA were considered as suitable MMC agents for higher ECM deposition in xeno-free hUC-MSCs cultures. Using an electrospun scaffold, a quasi-3D skin substitute was fabricated.

Acknowledgements

The authors would like to acknowledge European Commission, European Research Council (Grant Number: 866126) and UCD School of Mechanical & Materials Engineering.




Figure 1.
Surface and mechanical characterisation of poly(L-lactide-co-ε-caprolactone (PLCL) electrospun scaffold. **(A)** Fibres dispersion, porosity and thickness of the PLCL electrospun scaffold. **(B)** Wettability of the PLCL electrospun scaffold in ultrapure water. **(C)** Stress and strain curve of the PLCL electrospun scaffold. Blue region: toe/slack. Yellow region: pre-yield/elastic-like response. Red region: post-yield/plastic-like response. Blue dotted line: apparent modulus. N = 3.

Figure 2. Basic cell functions and protein deposition of xeno-free human umbilical cord mesenchymal stem cells (XF hUC-MSCs) under MMC conditions [carrageenan (CR) and polyacrylic acid (PAA)] on tissue culture plastic (TCP) and poly(L-lactide-co-ε-caprolactone (PLCL) electrospun scaffold. **(A)** Morphology of XF hUC-MSCs cultured under distinct macromolecular crowding agents after 4, 6 and 8 days. Scale bar: 200 µm. **(B)** Viability of XF hUC-MSCs without and with distinct macromolecular crowding agents after 4, 6 and 8 days in culture. Green: live cells. Red: dead cells. Scale bar: 200 µm. **(C)** Metabolic activity of XF hUC-MSCs without and with distinct macromolecular crowding agents after 4, 6 and 8 days in culture. **(D)** SDS-PAGE and corresponding densitometric analysis of XF hUC-MSCs after 4, 6 and 8 days of culture without and with macromolecular crowding agents. **(E)** SDS-PAGE and corresponding densitometric analysis of XF hUC-MSCs cultured on PLCL electrospun scaffolds for 6, 10 and 14 days without and with macromolecular crowding agents. N = 3. * and # indicates statistically significant difference ($p < 0.05$) to –MMC from the same timepoint and from day 4, respectively.

D1 – P045

Piezoelectric PLLA β-TCP 3D scaffolds with designed porous architectures for bone tissue engineering

Vasconcelos F.[1], Pinto J.[1], Fernandes M.M.[1]
[1]Center for MicroElectromechanical Systems (CMEMS), University of Minho, Campus de Azurém, Guimarães, Portugal

Introduction

Bone tissue engineering offers an effective alternative to conventional bone grafting, overcoming limitations such as donor site morbidity, limited availability, infection risk, and immune rejection. Nevertheless, it remains a critical need to design biomimetic scaffolds that mimic the structural, mechanical, and biological properties of native bone. In particular, pore size, interconnectivity, and scaffold geometry are key parameters influencing cellular behavior. Additionally, incorporating bioactive features such as piezoelectricity has gained attention for its ability to mimic the electromechanical behavior of bone tissue.

This work aims to exploit the biodegradable, biocompatible, and piezoelectric properties of Poly(L-lactic acid) (PLLA) to develop and characterize biomimetic scaffolds for bone tissue engineering. It evaluates the effects of pore size and geometry, β-tricalcium phosphate (β-TCP) incorporation (a bioactive ceramic that enhances osteoconductivity and mineralization), and electromechanical stimulation on scaffold performance.

Materials and Methods

Poly(vinyl alcohol) (PVA) filament was used to fabricate sacrificial molds via 3D printing, generating four architectures combining grid and honeycomb geometries with pore sizes of 200 and 400 µm. PLLA scaffolds with(out) β-TCP (5% and 10%) were produced through impregnation of these molds followed by PVA degradation in water. Morphological characterization was performed using scanning electron microscopy (SEM), while fluorescence imaging was used to evaluate structural integrity. Mechanical and physicochemical properties were assessed through compression testing, Fourier-transform infrared spectroscopy (FTIR), swelling and degradation studies. Biological performance was also evaluated. Cell viability and proliferation were assessed using CellTiter-Glo, complemented by DAPI/Phalloidin staining. Osteogenic differentiation was evaluated through alkaline phosphatase (ALP) activity, Alizarin Red staining for calcium deposition, and ELISA for BMP-2 production quantification, under static conditions or piezoelectric stimulation.

Results

PLLA scaffolds exhibited well-defined porous architectures, as observed by fluorescence microscopy and SEM imaging. Mechanical characterization indicated that scaffold properties were strongly influenced by pore size, geometry, and β-TCP incorporation. Similar effects were observed in biological assays. To add, the presence of β-TCP and piezoelectric stimulation, further enhanced osteogenic responses, as indicated by increased ALP activity, calcium deposition, and BMP-2 secretion.

Conclusion

This work highlights the importance of scaffold architecture in modulating mechanical and biological responses. By tailoring pore size and geometry, and integrating β-TCP, it's possible to enhance osteogenic differentiation and support tissue ingrowth, while PLLA's piezoelectricity offered potential for electromechanical stimulation to further promote bone regeneration.

Altogether, the developed scaffolds demonstrated to be a promising platform for advanced bone tissue engineering, warranting further optimization and in vivo validation.

Acknowledgements

This work was supported by the project CustomNiTi by Fundação para a Ciência e Tecnologia (FCT) national funds, under the national support to R&D units grant, through the reference projects CustomNiTi _17328_BIPD_03/2025-CMEMS and Physiplant 2023.28539.ICDT

D1 – P046

Flexible ceramic hydroxyapatite scaffolds with tuneable mechanical properties and degradation kinetics

Agut Lopez R.[1,2], Espanol M.[1,2,3]
[1]Biomechanics Biomaterials and Tissue Engineering, Universitat Politecnica de Catalunya, Barcelona; [2] Barcelona Research Centre for Multiscale Science and Engineering, Universitat Politècnica de Catalunya, Barcelona; [3]Centro de Investigación Biomédica en Red—Bioingeniería, Biomateriales y Nanomedicina, Instituto de Salud Carlos III, Spain

Introduction

Hydroxyapatite (HA) scaffolds are widely used in bone regeneration due to their chemical similarity to the inorganic phase of natural bone. However, their clinical utility remains limited by the inherent brittleness and slow degradation of stoichiometric HA. These limitations can be overcome by synthesizing HA nanofibers (NFs); their high aspect ratio enables unprecedented flexibility and stress tolerance by distributing small deformations axially along the fibre length. Unlike traditional brittle HA grafts, this adaptive architecture ensures better interfacial contact within complex defects. Furthermore, by modulating the NFs crystallite size, the scaffold degradation can be tuned to synchronize bone healing. This study aims to develop flexible, pure HA nanofibrous scaffolds with tunable stiffness and degradation by optimizing NFs concentration and synthesis duration.

Materials and Methods

HA NFs were synthesized via hydrothermal reaction using sodium oleate. Different reaction times from 2 to 24 h were explored to modulate NFs dimensions and crystallite size. Consolidation of the NFs into scaffolds was done by freeze-drying using different NFs concentrations. The morphology and composition of the NFs were evaluated by TEM and XRD. The scaffolds were characterized in terms of porosity, water uptake and mechanical properties. An accelerated degradation test was conducted to assess weight loss and ionic release, measured by ICP-OES**.**

Results

XRD analysis confirmed that the NFs were phase-pure HA, with crystallite sizes dependent on synthesis time (**Figure 1**). TEM observations confirmed a progressive increase in particle size from 5 nm at 2 h to 15 nm at 24 h. The NFs, assembled into 3D scaffolds by freeze-drying, exhibited mechanical properties that were influenced by the concentration of NFs, but not by the NFs synthesis time (**Figure 2**). By adjusting the NFs concentration, scaffolds with a Young's modulus between 5 and 100 kPa in wet conditions were produced. All the scaffolds exhibited porosities above 95% and had a high-water uptake capacity. The ceramic scaffolds were flexible, with elastic recoveries from 65% to 90% following 60% axial deformation. The degradation behavior of the scaffolds was successfully tailored adjusting the scaffold mass and the NF synthesis time.

Conclusion

This study demonstrates that flexible ceramic scaffolds with tailored mechanical properties and degradation rates can be produced from nanofibrous HA suspensions, overcoming the limitations of conventional ceramic grafts.




Figure 1: (A)Typical shape of the obtained HA scaffolds and TEM micrograph of the NFs, (B) XRD of NFs.




Figure 2: Mechanical characterization of the different scaffolds under soaked conditions (A-C)). Degradation characterization of the scaffolds (D-F).

Acknowledgements

This work was funded by the Spanish Government through the PID2022-142395OB-I00 project. M.E. acknowledges the Serra Hunter program of the Generalitat de Catalunya. This work is also part of Maria de Maeztu Units of Excellence Programme CEX2023-001300-M funded by MCIN/AEI/10.13039/501100011033. The first author gratefully acknowledges the Universitat Politècnica de Catalunya for the financial support of his predoctoral grant FPU-UPC (2023_FPU-UPC_39), with the collaboration of Banco de Santander.

D1 – P047

Polydopamine meets POSS: Engineering multimaterials for osteoporotic bone regeneration

Dinu A.I.[1], Lungu A.[1], Gherghinescu M.M.[1,2], Stavarache C.[1,3], Olăreț E.[1], Dobrănici A.[4], Dinescu S.[4], Iovu H.[1]
[1]Advanced Polymer Materials Group, National University of Science and Technology Politehnica, Bucharest, Romania; [2]Chimie ParisTech, PSL University, Paris, France; [3]C.D. Nenițescu Institute of Organic and Supramolecular Chemistry, Bucharest, Romania, [4]Dept. of Biochemistry and Molecular Biology, University of Bucharest, Bucharest, Romania

Introduction

Because of their distinctive configurations and surfaces full of functional groups, nanostructured materials are being studied progressively for the reconstruction of bone defects. They stand out as the "main character" whose screenplay can finally translate the intricate three-dimensional framework and multi-material constitution of bone. They also give patients with osteoporosis an opportunity to cure challenging bone defects marked by elevated reactive oxygen species (ROS). In this regard, polydopamine (PDA) and polyhedral oligomeric silsesquioxanes (POSS) nanoparticles are being investigated separately more and more as biomimetic and bioactive nanobiomaterials. Together, they can strengthen polymeric systems, supply bioactive functional groups that encourage attachment of cells, and scavenge free radicals that arise in the surroundings of osteoporotic bone healing. Additionally, a promising approach for bone tissue engineering is the reciprocal action of protein-polysaccharide hydrogels and nanomaterials in building multi-material networks. By integrating the advantages of POSS and PDA nanocompounds with the biocompatible matrix of methacrylated gelatin (GelMA) enriched with κ-carrageenan (KC) to form hybrid hydrogel network systems, we therefore set out to develop innovative formulations that can assist in the successful reconstruction of bone defects in osteoporotic patients.

Materials and Methods

Hydrogels constructed from PDA and POSS nanoparticles embedded in GelMA or dopamine-modified GelMA (GelMA-Dopa) and KC polymeric blends were developed to assess their physico-chemical properties and potential to induce osteoporotic bone regeneration. The assembled freeze-dried structures were evaluated for rehydration performance, morphology at microscale, mechanical characteristics (both bulk and nanoscale), biocompatibility, mineralization potential, and free radical removal capability.

Results

Our findings show that enriching GelMA-based scaffolds with dopamine-containing networks increases crosslinking density, most likely due to numerous catechol-mediated bonds, which have a major impact on water uptake behavior. Furthermore, the data indicates that the integration of organic-inorganic nanoparticles has a considerable impact on mechanical characteristics, substantially raising the force required to induce a 50% compressive displacement. In regard to cell attachment, fluorescent microscopy images show adherent preosteoblasts with a lengthened shape and clearly marked actin fibers, particularly on PDA-enriched platforms. Intracellular ROS elimination studies exhibited elevated activities for dopamine-containing materials, ability also confirmed through chemical methods.

Conclusion

This study shows that chosen components bring multiple benefits for the development of innovative multifunctional biomaterials for bone tissue engineering: biocompatibility, mechanical strength, and bioactivity being all balanced effectively. Furthermore, via the combination of two distinct strategies of dopamine inclusion: PDA nanoparticles and dopamine-modified GelMA, the coupling among the organic components was improved, resulting in greater stability, mechanical stiffness, and biological activity.

Acknowledgements

This work was supported by a grant of the Ministry of Research, Innovation and Digitization, CNCS/CCCDI - UEFISCDI, project number PN-IV-P8-8.1-PRE-HE-ORG-2023-0054 (contract no. 17PHE/2023) within PNCDI IV. Also, A. Dinu acknowledges the funding received from Romanian Ministry of Education and Research and National University of Science and Technology Politehnica Bucharest.

D1 – P048

Composite PLLA/PLLA-HAp gradient porous scaffolds fabricated by two-step TIPS for bone tissue regeneration

Davì D.[1,2], Carfì Pavia F.[2], Brucato V.M.B.[2], Ghersi G.[1]
[1]Dept. of Biological, Chemical and Pharmaceutical Sciences and Technologies (STEBICEF), University of Palermo; [2]Dept. of Engineering, University of Palermo, Palermo, Italy

Introduction

Bone tissue has an outer compact layer with low porosity and small pores and an inner highly porous cancellous bone with larger pores[1]. Its matrix consists of hydroxyapatite (HAp), organic components, and water. Developing three-dimensional (3D) composite gradient porous scaffolds remains a challenge in bone tissue engineering to mimic its heterogeneity.

Aim

This work presents the fabrication of composite scaffolds for bone tissue applications through the Thermally Induced Phase Separation (TIPS) technique[2], producing an Internal Gradient Porous Structure (IGPS) of Poly-L-Lactic Acid (PLLA) and an external PLLA-HAp Surface Porous Layer (SPL). The obtained structure mimics compact bone with the SPL and cancellous bone with the IGPS.

Materials and Methods

Composite scaffolds were fabricated using a two-step TIPS process. For the IGPS, a ternary PLLA solution was poured into a cylindrical high-density polyethylene (HDPE) sample holder and placed in a thermostatic bath to induce phase separation, then immersed in an ethyl alcohol bath at -20°C to freeze the scaffold structure. The external SPL was produced by performing TIPS around the IGPS. Specifically, a thin layer of PLLA-HAp solution was poured around the centered IGPS in the HDPE sample holder, and a second TIPS protocol was performed (Fig.1). The resulting composite scaffolds were characterized through scanning electron microscopy and micro-CT.

Results

Morphological analysis confirmed integration between the SPL and the IGPS, with interconnected pores. The internal PLLA structure exhibited a gradient morphology, whereas the PLLA-HAp layer showed homogeneous pore size, constant thickness, and suitable distribution of HAp particles within the layer pores, also confirmed by 3D micro-CT (Fig.2). The samples showed a suitable architecture to replicate bone tissue heterogeneity.

Conclusion

This work demonstrates the successful fabrication of composite scaffolds with a homogeneous PLLA-HAp surface porous layer and a PLLA gradient porous morphology using a two-step TIPS technique. This approach is a versatile method to produce customized structures for bone tissue regeneration by tuning the internal morphology and pore size of both the internal structure and the surface layer.




Figure 1: Schematic representation of the two-step TIPS process for the production of PLLA/PLLA-Hap composite scaffolds




Figure 2: SEM and micro-CT characterization of the composite PLLA/PLLA-HAp scaffolds: Higher-magnification SEM shows HAp particles within the pores of the SPL. Micro-CT shows HAp distribution (in red) in the SPL.

References

[1]Fang L., Lin X., Xu R., Liu L., Zhang Y., Tian F.,Li J.J., Xue J. Advances in the Development of Gradient Scaffolds Made of Nano-Micromaterials for Musculoskeletal Tissue Regeneration. *Nano-Micro Letters* 2025; 17(1); 75.

[2]Conoscenti G., Smith K.W.Y., Pirosa A., Carfì Pavia F., Zhang E.Y., La Carrubba V., Brucato V., Tuan R.S., Gottardi R. Continuous Pore Size Gradient Enhances Zonal-Specific Differentiation of Stem Cells in an Osteochondral Scaffold. *RSC Advances* 2025; 15(35); 28452-28463.

D1 – P049

Covalent surface engineering of polyester-based scaffolds with functionalized peptides for enhanced stability in cartilage regeneration

Pawłowski D.[1], Trepczyk K.[1], Kłusak A.[2], Domański S.[3], Klak M.[3], Rad N.[3], Gazińska M.[2], Rodziewicz-Motowidło S.[1], Szymańska A.[1;]
[1]Dept. of Biomedical Chemistry, Faculty of Chemistry, University of Gdańsk, Gdańsk; [2]Dept. of Polymer Engineering and Technology, Faculty of Chemistry, Wrocław University of Science and Technology, Wrocław; [3]Polbionica S.A., Zielona Góra, Poland

Introduction

Articular cartilage possesses limited intrinsic regenerative capacity due to its avascular and aneural structure. Consequently, its degradation leads to progressive osteoarthritis (OA), a primary cause of global chronic pain and disability. Conventional therapeutic interventions predominantly result in the formation of mechanically inferior fibrocartilage rather than functional hyaline tissue, underscoring the critical need for advanced biomaterial scaffolds in cartilage tissue engineering.
Polyester-based polymers has emerged as promising candidate for biodegradable and biocompatible scaffolds, offering tunable mechanical properties and an architectural environment that mimics the extracellular matrix of articular cartilage. However, they still lack the required functional bioactivity. This study aims to develop a robust and controllable method for the surface modification of these scaffolds using surface-reactive and cell-attracting, while simultaneously evaluating their stability and bioactivity in immobilized forms.

Materials and Methods

Polymeric scaffolds were prepared using casting of the prepolymer and curing at low temperature. Covalent surface modification was achieved using crosslinking method with the use of specific reactive groups. Process parameters were optimized to achieve precise control over surface coverage ratios. The stability of the functionalized surfaces was rigorously evaluated across four distinct environments: deionized water, selected physiological and inflammatory fluids, and culture media.

Results

The obtained results demonstrate that diazirine-mediated covalent attachment successfully anchored the target peptides to the polymer surface without compromising its structural integrity. Comparative analyses revealed that while free peptides undergo rapid proteolytic degradation in both physiological and inflammatory synovial fluids, the covalently immobilized variants exhibit significantly enhanced stability and sustained functionality. These results indicate that the developed coupling effectively addresses the limitations associated with peptide longevity within the implant environment.

Conclusion

This research provides significant insights into the role of covalent surface engineering in extending the functional lifespan of bioactive motifs within cartilage regeneration scaffolds. By shielding peptides against rapid enzymatic degradation in the synovial environment, this approach facilitates the development of more efficacious, polyester-based therapeutic implants for the treatment of osteoarthritis.

Acknowledgements

The research is supported by M-ERA.NET and The National Centre for Research and Development grant „REGenesis - REvolutionising bone and cartilaGE reconstruction through Novel cell-instructive biomaterial and peptide-Enhanced Stem cell Immobilization Strategy” (M-ERA.NET3/2024/98/REGENESIS/2025).

D1 – P050

Bioengineering a humanized bone-on-a-chip model leveraging human ECM-derived macroporous cryogels

Monteiro C.F.[1], Ferreira R.S.[1], Brandão M.F.[1], Martins E.A.G.[1], Custódio C.A.[1], Mano J..F[1]
[1]Chemistry Dept., CICECO – Aveiro Institute of Materials, University of Aveiro, Aveiro, Portugal

Introduction

There is an urgent need for robust and predictive platforms to test and optimize therapies for bone healing. Organ-on-chip (OoC) systems have emerged as powerful microscale platforms that recapitulate organ-level functions through perfusable microchannels and complex cellular architectures. However, their effectiveness depends on the scaffold's ability to mimic the structural intricacies of native tissues. In bone engineering, high porosity and interconnectivity are essential features, and cryogels provide highly porous, biocompatible structures with tunable mechanical properties that resemble *in vivo* architecture. The aim of this work is to develop a novel biomimetic 3D bone-on-a-chip model based on human extracellular matrix (ECM)-derived cryogels as an innovative platform to investigate the effects of advanced therapeutic medicinal products on bone regeneration at an injured site.

Materials and Methods

Human methacryloyl extracellular matrix-derived (hECM-MA) cryogels were fabricated via freeze-drying, followed by photocrosslinking, generating scaffolds with either aligned or random interconnected macroporous architectures to enhance cell infiltration and tissue formation. Moreover, different protein concentrations were explored to manipulate the cryogels mechanical properties. Structural features were characterized by scanning electron microscopy and 3D confocal imaging. Cryogels were fabricated inside a microfluidic device, enabling controlled and continuous perfusion. Human bone marrow-derived mesenchymal stem cells (hBM-MSCs) were seeded onto the scaffolds and cultured under dynamic flow conditions to promote osteogenic differentiation, assessed through osteogenic marker expression and matrix mineralization.

Results

The hECM-MA cryogels exhibited fully interconnected porous networks, with both aligned and random pore configurations, as well as shape memory and rapid swelling behavior (Fig.1). Mechanical and structural characterization demonstrated that cryogels' stiffness and pore size can be tuned through protein concentration. Integration into the microfluidic platform enabled stable perfusion, where the porous architecture supported efficient nutrient transport and oxygenation, maintaining high cell viability and promoting progressive cell infiltration over 21 days. Interestingly, pore alignment efficiently enhanced cell infiltration into the scaffold (Fig 2). Moreover, dynamic culture further enhanced osteogenic differentiation, evidenced by the expression of key markers and matrix mineralization.

Conclusion

This study demonstrates the successful integration of human ECM-derived cryogels with tunable pore architectures into a perfusable OoC system, generating a physiologically relevant 3D bone model. The platform supports cell viability, infiltration, and osteogenic differentiation, highlighting its potential as a predictive tool for evaluating advanced therapeutic medicinal products in bone regeneration.

Acknowledgements

This work was supported by CICECO, UID/50011/2025&LA/P/0006/2020, FCT/MCTES (PIDDAC); the ERC-AdG No.883370 (REBORN); and the HORIZON-RIA grant ORTHO-ALLO-UNION (no.101137464).




Figure 1. (A) (i) Schematic representation of human-derived extracellular matrix proteins (hECM) chemically modified with photoresponsive methacrylate groups (hECM-MA). **(ii)** Fabrication process of hECM-MA cryogels. **(B)** Photographs of hECM-MA cryogels produced with 1.5% (w/v) protein concentrations, along with confocal microscopy images revealing their macroporous structure in FITC-stained cryogels, with both random and aligned pores. **(C)** hBM-MSCs viability on the produced cryogels.




Figure 2. (A) (i) In-chip fabrication of the hECM-MA cryogel within the open-top tissue chamber. **(ii)** confocal microscopy image showing the macroporous structure of the cryogel polymerized inside the microfludic chip. **(iii)** Demonstration of easy dye diffusion through the cryogel. **(B)** Confocal microscopy image of hBM-MSCs infiltration into the hECM-MA cryogel, cultures for 7 days inside the microfluidic chip.

D1 – P051

Engineering functionalized Wharton's jelly extracellular matrix hydrogels as multifunctional biomaterials for bone repair

Lavrand A.[1], Lemaire F.[1], Da Rocha A.[2], Baldit A.[2], Edera P.[3], Rogel D.[1] Mauprivez C.[1], Brenet E.[1], Kerdjoudj H.[1]
[1]BIOS, Université de Reims Champagne Ardenne, Reims; [2]LEM3, Université de Lorraine, Metz; [3]C3M, ESPCI Paris, Paris, France

Introduction

Extracellular matrix (ECM)-based hydrogels are increasingly investigated in regenerative medicine for their bioactive properties, but their poor mechanical properties face limitations for clinical translation. We developed hydrogels derived from decellularized human Wharton's jelly ECM (WJ-ECM) as a biomaterial for bone tissue engineering. However, mechanical characterization revealed low stiffness and handling besides a decrease of anti-bacterial and immunomodulative activities probably due to the loss of bioactive proteins and peptides during the WJ-ECM processing to obtain hydrogels. To address this, we engineered and characterized WJ-ECM hydrogels functionalized with tannic acid (TA), an FDA approved polyphenol with antioxidant, antibacterial, and anti-inflammatory activities.

Materials and Methods

WJ-derived macromolecules were extracted from decellularized Wharton jelly through enzymatic digestion. The self-standing hydrogel was obtained following the re-equilibration of the pH, salt concentration and 40min at 37°C. The hydrogels were soaked in TA solution for 24h then periodate for 2h, and then washed in PBS. The physico-chemical, mechanical as well as the antibacterial, antioxidant and anticancer evaluations were carried out. Finally, the osteogenic properties of the hydrogels were evaluated in critical (i.e. 8 mm) parietal bone defect in rats.

Results

TA diffused through WJ-ECM hydrogels, and its cytotoxicity was circumvented by a partial oxidation with periodate which also improved mechanical stiffness and enzymatic stability. The hydrogels also show an elastic modulus recovery after shear thinning. TA oxidation (oTA) was limited to the edge of the hydrogels, suggesting the formation of a TA "reservoir". The resulting oTA-WJ-ECM hydrogels preserved antioxidant activity, reducing intracellular ROS accumulation in neutrophils, and inhibited bacterial proliferation. They also modulated macrophage polarization towards a hybrid M1/M2 phenotype and displayed favorable hemocompatibility with enhanced coagulative properties. This hydrogels present also an anti-cancer activity that make them interesting for reconstruction after tumor ablation. In a rat calvaria bone defect, oTA-WJ-ECM hydrogels exhibited osteoinductive properties and supported complete bone regeneration.

Conclusion

In conclusion, WJ-ECM hydrogels functionalized with oxidized TA produced a multifunctional biomaterial that recovers antibacterial, and immunomodulatory properties enhanced by osteoinductive properties. These results suggest that oTA-WJ-ECM hydrogels are promising materials for regenerative medicine targeting bone applications.

D1 – P052

Bioinspired hydrogels based on chitosan and hyaluronic acid containing cobalt and magnesium-doped monetite for bone regeneration

Almeida G.S.[1], Carra M.G.J.[1], Suter L.C.[1], Santos M.L.P.[1], Yokote Y.P.[1], Mantovani D.[2], Zambuzzi W.F.[1]
[1]Dept. of Chemistry and Biochemistry, Institute of Biosciences, UNESP - Universidade Estadual Paulista, Botucatu, São Paulo, Brazil; [2]Dept. of Min-Met-Materials Engineering and Regenerative Medicine, & Regenerative Medicine, CHU de Quebec Research Center, Laval University, Quebec City, Canada

Introduction

Bone tissue possesses a distinct capacity for self-repair, yet critical-size lesions require clinical interventions using biomaterial supports. Advanced strategies in tissue engineering focus on developing osteointegrative platforms capable of providing a suitable microenvironment for cell adhesion, proliferation, and differentiation. Monetite ($CaHPO_4$) is a promising bone substitute due to its high solubility and resorbability compared to hydroxyapatite.

Aim

This study aimed to develop and characterize biomimetic, ion-doped monetite-loaded chitosan/hyaluronic acid hydrogels for enhanced bone regeneration, focusing on the synergy between osteogenic and angiogenic signaling.

Materials and Methods

Pure monetite (CaP) and monetite doped with 2% cobalt (CoCaP) or magnesium (MgCaP) were synthesized via coprecipitation. Thermosensitive hydrogels were prepared using chitosan (3%) (CHI), β-glycerophosphate, and hyaluronic acid (HA) (1-2%). Characterization included XRD, FTIR, Raman, and SEM. Rheological properties were assessed to confirm sol-gel transition at 37◦C. In vitro assays using MC3T3-E1 pre-osteoblasts evaluated cell viability (MTT), adhesion (Crystal Violet), and gene expression (RT-qPCR) of markers such as Runx2, Hif1−α, and Col1a1.

Results

Physicochemical analysis confirmed high-purity monetite with plate-like morphology. Rheology showed a transition from viscous to elastic behavior upon heating, indicating stable network formation. CoCaP significantly increased cell adhesion and upregulated angiogenic markers Hif1−α and eNOS. MgCaP promoted the highest expression of Col1a1, crucial for matrix maturation. Among hydrogels, Chitosan/CoCaP + HA 1% showed superior biological performance, effectively replicating the bioactive profile of the doped particles within a 3D interconnected porous structure.

Conclusion

The developed composite hydrogels act as multifunctional platforms that modulate cellular behavior, promoting adhesion, migration, and differentiation. These materials represent a promising frontier for bone tissue engineering by mimicking the bone's hierarchical and bioactive nature.

Acknowledgements

This work was supported by FAPESP (Grants: 2024/03886-4, 2025/14873-3) and CAPES.

D1 – P053

Mechanically tuned dECM hydrogels via dipeptide reinforcement for cartilage repair

Pande S[1]., Pati F[1]., Chakraborty P.[2]
[1]Dept. of Biomedical Engineering, Indian Institute of Technology Hyderabad; [2]Dept. of Chemistry, Indian Institute of Technology Hyderabad, India

Introduction

Cartilage tissue engineering remains a significant clinical challenge owing to its avascular nature, complex zonal architecture, and limited regenerative capacity, with current interventions consistently failing to restore long-term biomechanical function. While dECM-based hydrogels offer retained bioactive composition, their inherently weak mechanical properties restrict load-bearing application. Conversely, peptide-based hydrogels effectively recapitulate fibrous extracellular architecture but lack sufficient biochemical complexity for chondrogenesis. To bridge these complementary limitations, we developed a mechanically robust yet bioactive hybrid hydrogel by integrating dECM with Fmoc-FF, a low molecular weight supramolecular gelator, and systematically evaluated their physicochemical, mechanical, and biological suitability for cartilage tissue engineering.

Materials and Methods

Caprine knee-derived dECM was obtained via the OSMODECELL process, and a series of hybrid hydrogels were fabricated at varying Fmoc-FF dipeptide concentrations (Figure 1a). Rheological characterization via Small Amplitude Oscillatory Shear determined storage modulus (G′), damping factor (tan δ), and viscoelastic behavior, while scanning electron microscopy assessed fibrillar microarchitecture. Biocompatibility was evaluated using chondrocyte-seeded constructs through Live/Dead staining and MTT assay at days 1, 3, and 7, with chondrogenic differentiation potential assessed by immunostaining for aggrecan (ACAN) and collagen type-II (Col-II).

Results

Morphological analysis confirmed that the hybrid hydrogel successfully recapitulates the native fibrillar architecture of dECM (Figure 1b-d). Quantitative rheological characterization revealed concentration-dependent mechanical reinforcement upon progressive Fmoc-FF incorporation, with G′ increasing from 2.40 to 40.37, 59.54, and 91.86 kPa at 0.25%, 0.50%, and 0.75% w/v Fmoc-FF respectively, representing an approximately 38-fold cumulative enhancement spanning the mechanical range of native articular cartilage zones (Figure 1e). The dECM/Fmoc-FF (0.50% w/v) formulation demonstrated the most physiologically relevant viscoelastic profile, exhibiting tan δ of 0.197^{1} with a frequency-independent plateau modulus, reflecting optimal equilibrium between elastic energy storage and viscous dissipation (Figure 1f). All formulations exhibited pronounced shear-thinning behavior, preserving injectability under physiological conditions. Biological evaluation demonstrated excellent biocompatibility, with chondrocytes maintaining their phenotype and exhibiting significantly enhanced expression of ACAN and Col-II at day 14, confirming the scaffold's capacity to mechano-biologically support chondrogenesis (Figure 1g-i).

Conclusion

The findings of this study establish that controlled Fmoc-FF incorporation systematically transforms the mechanically fragile dECM into a tunable, elastically dominant supramolecular scaffold, mechanical properties spanning the stiffness range of native articular cartilage zones, combined with cytocompatibility and pro-chondrogenic capacity, collectively positioning this platform as a mechanically adaptable scaffold for zone-specific cartilage tissue engineering applications.




Figure 1: a) Schematic showing the preparation of hybrid hydrogels. b-d) SEM micrographs for the hybrid hydrogel with dECM (2% w/v) and Fmoc-FF (0.25, 0.50, 0.75% w/v), respectively (Scale bar: 1 µm). e) Amplitude sweep measurements of hybrid hydrogel indicating the linear viscoelastic region and the yield point (0.1-200% strain, Frequency: 1Hz). f) Dynamic frequency sweep measurements of the hybrid hydrogel showing frequency-independent storage modulus across the range of angular frequency applied (0.1-100 rad/s; 0.1% strain). The immunostaining images Chondrocytes cultured on g) Control, h) dECM, and i) dECM (2.0%)/Fmoc-FF (0.5%) hydrogel (Scale bar: 50 µm).

References

[1]Chang A., Tang S.Y. Determination of the depth-and time-dependent mechanical behavior of mouse articular cartilage using cyclic reference point indentation. *Cartilage* 2020; 11.3; 358-363.

D1 – P054

Fetuin a-functionalized 3D-printed gyroidal scaffolds for enhanced bone-integration

Oschatz S., Seegemann L., Fiedler N., Grabow N., Markhoff J.
Insitute for Biomedical Engineering, University Medical Centre Rostock, Rostock, Germany

Introduction

3D-printed gyroid scaffolds represent a promising strategy for bone defect treatment due to their highly interconnected macro- and microporous architecture, allowing for efficient cell infiltration and tissue ingrowth[1]. However, current polymer-based scaffolds often lack intrinsic bioactivity required for robust bone integration. Previously, it has been shown that covalent functionalization of electrospun nonwovens with Fetuin A significantly enhances biomineralization by promoting calcium phosphate binding and subsequent formation of a biogeneous biomineralization layer on the material[2]. The present study utilizes this concept to gyroid scaffolds fabricated by additive manufacturing.

Materials and Methods

Gyroid scaffolds were fabricated by fused deposition modeling (FDM) using a modular and open-source CoreXY 3D printer (V-Core 3.1, Rat Rig). PLA-co-PEG (Resomer LPt 46, Evonik) was processed through a pellet extruder and a 200 µm nozzle. Surface functionalization of the gyroids with Fetuin A was achieved by covalent EDC/NHS coupling. Human MG-63 and SaOS-2 osteoblast cells were seeded onto functionalized and biomineralized scaffolds. Biocompatibility, cell proliferation, and cell morphology were investigated using metabolic cell activity assay, phalloidin/DAPI staining, and cell adhesion marker analysis. Furthermore, an IL-1β-based inflammation model in combination with live-cell imaging and ELISA was used to evaluate potential inflammation-modelling effects of Fetuin A.

Results

Fetuin A functionalization enabled enhanced biomineralization of PLA-co-PEG gyroid scaffolds, showing effective translation of the previously established approach to 3D-printed architectures. Compared to unmodified controls, functionalized and biomineralized scaffolds exhibited improved cell attachment, spreading, and proliferation. Preliminary results further suggest a modulatory effect on biomaterial-induced cellular inflammation responses under IL-1β stimulation.

Conclusion

The combination of biodegradable gyroid scaffolds with Fetuin A functionalization for enhanced biomineralization represents a promising strategy for the development of bioactive, biodegradable implants. This approach extends established concepts for additively manufactured structures and may contribute to improved biomimetic biomaterial application in large bone defects.

Acknowledgements

Financial support by the University Medical Centre Rostock is gratefully acknowledged.

References

[1]Karageorgiou V., Kaplan D. Porosity of 3D biomaterial scaffolds and osteogenesis. *Biomaterials* 2005; 26; 5474-5491.
[2]Oschatz S. *et al*. Fetuin A functionalisation of biodegradable PLLA-co-PEG nonwovens towards enhanced biomineralisation and osteoblastic growth behaviour. *Biomater Sci*. 2023; 15; 5240-5250.

D1 – P055

Biomimetic, bio-functionalised polymer implants to promote *in situ* repair of traumatic and early osteoarthritic cartilage defects

Taylor C.S.[1*], Haycock J.W.[1], Buttle D.[2], Pead M.[3], Meeson R.[3], Blunn G.[4], Crawford A.[5]
[1]School of Chemical, Materials and Biological Engineering, University of Sheffield; [2]Dept. of Infection, Immunity & Cardiovascular Disease, University of Sheffield; [3]Small Animal Medicine & Surgery Group, Royal Veterinary College, London; [4]School of Pharmacy and Biomedical Sciences, University of Portsmouth, Portsmouth, UK; [5]School of Clinical Dentistry, University of Sheffield, Sheffield, UK

Introduction

We are developing a biomimetic, implantable medical device which is bio-functionalised in a similar conformational and biochemical context to articular cartilage, to promote stem cell homing and retention in the implant and subsequent chondrogenesis and *de novo* cartilage formation. The aim of this study was to assess the efficacy of this technology on the regeneration of articular cartilage *in vitro* and *in vivo.*

Methods

Poly-L-lactic acid (PLLA) random-fibre scaffolds were electrospun and the surface charge was altered by plasma polymerisation. The surface-modified scaffolds were treated with heparin and pmol amounts of chondrogenic and stem-cell homing factors. The bio-functionalised scaffold was assessed *in vitro* for its ability to support long-term cell viability and chondrogenesis by bone-marrow MSCs and primary chondrocytes in the absence of other added growth factors or serum. Cell viability was assessed with PrestoBlue® and extracellular matrix (ECM) formation determined by measuring glycosaminoglycan content. The bio-functionalised scaffolds were assessed for *in vivo* activity by implantation into surgically created full-thickness chondral lesions, including subchondral bone micro-fracture, in the medial femoral condyles of sheep.by implantation into surgically-created 6mm chondral lesions in the medial condyles of sheep, with microfracture immediately before implantation. At 4 and 16 weeks, the treated joints were retrieved and cartilage regeneration assessed macroscopically and histologically.

Results

In vitro, functionalisation of the PLLA scaffold with a combination of TGFβ3 and CXCL12 promoted MSC attachment and ingress throughout the implant, and chondrogenic differentiation. Viability of the cells within the construct was maintained in the absence of added chondrogenic factors or serum for at least 5-6 weeks. The MSCs underwent chondrogenesis and produced significantly more ECM ($P \leq 0.05$) than non-functionalised or partially functionalised scaffolds. The scaffolds also promoted chondrocyte attachment, long-term cell viability and ECM formation under the same experimental conditions. *In vivo*, implantation of TGFβ3 and CXCL12 functionalised implants showed biological efficacy with regeneration of neocartilage with hyaline features (determined histologically) occurring at 4 weeks with the bio-functionalised implants but not with empty defects or control non-functionalised implants.

Conclusions

Bio-functionalisation of PLLA scaffolds with pmol quantities of TGFβ3 and CXCL12 promoted MSC migration and retention in the scaffolds and chondrogenesis with neocartilage tissue regeneration *in vitro* and *in vivo.*

D1 – P056

Bioadhesive hyaluronic acid hydrogels as therapeutic delivery platforms for neural tissue repair

Peixoto D.[1,2], Correia C.[1,2], Cruz-Moreira D.[1,2]; Reis L.R.[1,2], Pashkuleva I.[1,2], Alves N.M.[1,2]
[1]3B's Research Group, I3Bs – Research Institute on Biomaterials, Biodegradables and Biomimetics, University of Minho, Guimarães; [2]ICVS/3B's−PT Government Associate Laboratory, Braga, Portugal

Introduction

Spinal cord injury (SCI) is a severe condition affecting the central nervous system. SCI often results in permanent functional impairment due to disruption of neural connectivity. One of the main challenges in SCI treatment is the lack of a supportive extracellular matrix (ECM) to guide axonal regeneration across the lesion site. Biomaterial-based systems have emerged as promising platforms for local delivery of therapeutic agents while providing structural support to injured SC. Hyaluronic acid (HA)-based hydrogels are particularly attractive due to their high biocompatibility, biodegradability, and natural presence in the ECM of neural tissues. However, HA hydrogels often exhibit limited mechanical stability and weak adhesion at physiological conditions. To overcome these limitations, HA was functionalized with catechol groups inspired by mussel adhesive proteins, enhancing tissue adhesion in wet environments.

Aim

To develop injectable, self-healing, mussel-inspired HA hydrogels as carriers for localized delivery of therapeutic agents promoting neural tissue repair after SCI.

Materials and Methods

HA was modified with dopamine (HA-Cat) and with adipic acid dihydrazide (HA-ADH). HA-Cat was oxidized with $NaIO_4$ to generate aldehyde groups (HA-Cat-A). Hydrogels were formed via hydrazone bond formation between the hydrazide groups of HA-ADH and the aldehyde groups of HA-Cat-A (Fig. 1). Ibuprofen or anti-Nogo-66 receptor antibodies were incorporated as therapeutic agents.

Results

Catechol functionalization significantly improved hydrogel adhesion, as demonstrated *ex vivo* on mice spinal cord and porcine skin (lap-shear tests). The hydrogels were injectable and showed self-healing properties, enabling minimally invasive administration and filling of irregular injury sites. In vitro studies showed that HA-Cat hydrogels supported SH-SY5Y cell viability, attachment, and neuronal morphology, together with early upregulation of the neuronal marker β-III tubulin. Ibuprofen-loaded hydrogels did not affect cell growth, and successful incorporation of anti-NgR antibodies confirmed their potential as delivery platforms for therapeutic biomolecules (Fig. 2).

Conclusion

The injectable and self-healing bioadhesive hydrogels represent multifunctional platforms capable of transporting therapeutic agents, such as anti-inflammatory drugs or antibodies, highlighting their potential for localized delivery and neural tissue repair in SCI.

Acknowledgements

We acknowledge projects SHIFT (funded by the European Union's Horizon 2020 Research and Innovation Programme under the Maria Sklodowska-Curie grant agreement no. 101008041), SeaJellySpine – Operação nº15520 (COMPETE2030-FEDER-00653700) and Jelly4Bone – Operação nº15969 (COMPETE2030-FEDER-00710400), co-financed by ERDF through the Innovation and Digital Transition Thematic Programme (COMPETE 2030), under Portugal 2030. Also, TERM RES Hub-reference PINFRA/22190/2016 (Norte-01-0145-FEDER-022190), funded by the FCT in cooperation with CCDR-N and UID/50026/2025, financed by FCT I.P (component OE) (https://doi.org/10.54499/UID/50026/2025).




Fig 1. Synthetic pathways used for the preparation of: HA-Cat-A, HA-ADH and the formation of HA-Cat hydrogels via a hydrazone bond.




Fig 2. Representative confocal microscopy images of HA-Cat hydrogels SH-SY5Y

D1 – P058

Optimization and *in vitro* exploration of chitosan 3D-printed scaffolds for neural repair

Droubi-Harkassi D., Valdés-Portas P., Zayat M.D., Puerto Morales M., Serrano M.C.*
Instituto de Ciencia de Materiales de Madrid, Consejo Superior de Investigaciones Científicas, Madrid, Spain

Introduction

Spinal cord injury (SCI) is a severe neurological disorder causing irreversible functional loss and lacking effective curative treatments. Tissue engineering, particularly 3D bioprinting, offers promising strategies for neural regeneration. In this study, 3D scaffolds were fabricated using chitosan-based inks, a biopolymer with high biocompatibility, biodegradability, and structural similarity to the extracellular matrix. Scaffolds were also doped with superparamagnetic iron oxide nanoparticles (IONPs) to provide magnetic responsiveness for controlled drug delivery of therapeutics.

Materials and Methods

Lyophilized chitosan was dissolved in diluted acetic acid to prepare 3% w/v inks, some loaded with low (L) and high (H) IONP concentrations. Using a REGEMAT® bioprinter, 3D scaffolds with 500 µm pore size were fabricated. Stability was assessed through degradation over 14 weeks and mechanical properties by nanoindentation using the Piuma nanoindentor (Optics11Life). Iron content and magnetic behavior were measured via ICP-OES and SQUID magnetometry, respectively. Moreover, rat primary neural progenitor cells were seeded on scaffolds. After 14 days *in vitro*, cell adhesion, colonization, viability, and differentiation were assessed by using confocal microscopy and fluorescence tecniques. Neural network activity was also evaluated by intracellular calcium imaging with the Fluo-4 probe.

Results

Optimization of the 3D printing process enabled reproducible fabrication of scaffolds with and without IONPs **(Figure 1)**. Mechanical testing showed stiffness slightly above native neural tissues and a promising degradation profile for future in vivo implantation. ICP-OES and SQUID analyses demonstrated a direct correlation between iron content and the resulting magnetic properties. In vitro assays revealed neural cell colonization **(Figure 2A)**, high viability **(Figure 2B)**, and functional differentiation into neurons and astrocytes **(Figure 2C)**, with enhanced calcium responsiveness in IONP-containing scaffolds.




Figure 1. Stereomicroscope images (4×) of scaffolds fabricated from a 3% w/v chitosan ink (3DCHI) and containing low (3DCHI-L) and high (3DCHI-H) IONP concentrations.




Figure 2. (A) SEM image showing neural cell colonization of the 3D scaffold; (B) and (C) representative confocal microscopy images illustrating highly viable (calcein in green/EthD-1 in red) and matured (MAP-2 for neurons in green, GFAP for astrocytes in red and cell nuclei in blue) neural cultures, respectively.

Conclusion

3D-printed chitosan scaffolds, with and without IONPs, exhibited high biocompatibility and functional activity in primary neural cultures *in vitro*. Future studies will focus on their optimization, therapeutic functionalization and *in vivo* implantation in rat SCI models.

Acknowledgements

This research was funded by the European Union's Horizon Europe Research and Innovation Programme (GA No. 101098597; Piezo4Spine).

D1 – P059

Dual-crosslinked pectin-based hydrogels via Thiol–Ene Michael addition and photopolymerization for tunable cell–material interactions

Naik S.[1], Kellomaki M.[2]
[1]Biomaterials and Tissue Engineering Group, Faculty of Medicine and Health Technology, Tampere University, Tampere, Finland

Introduction

Engineering hydrogels with independently tunable network architectures is critical for understanding and directing cell behavior in 3D microenvironments. In this study, we develop a dual-crosslinking strategy using thiolated pectin and pectin methacrylate to fabricate hydrogels with controllable physicochemical and biological properties. The system leverages thiol–ene Michael addition for rapid, spontaneous network formation under mild conditions, followed by photocrosslinking of methacrylate groups to further stabilize and modulate the network.

Materials and Methods

By varying the ratio of thiol to methacrylate functionalities and the extent of photoexposure, we systematically tailor gelation kinetics, crosslinking density, mechanical stiffness, and degradation behavior. This modular platform enables decoupling of initial cell encapsulation conditions from subsequent network reinforcement. Encapsulated cells are evaluated for viability, proliferation, morphology, and mechanosensitive responses to elucidate how sequential crosslinking influences cell–matrix interactions.

Results

Our results demonstrate that the interplay between thiol–ene and photoinitiated crosslinking governs matrix elasticity and ligand presentation, which in turn regulate cell spreading and function. This study provides a versatile framework for designing pectin-based bioadhesive hydrogels with spatiotemporal control over material properties, with potential applications in tissue engineering, wound healing, and injectable therapeutics.

Conclusion

This study demonstrates that sequential thiol–ene and photoinitiated crosslinking provides an effective strategy to engineer pectin-based hydrogels with independently tunable network properties. By controlling the extent and timing of each crosslinking mechanism, hydrogel mechanics, degradation, and cellular microenvironment can be precisely modulated without compromising cell encapsulation. The results highlight the critical role of network architecture in regulating cell behavior, including viability, proliferation, and morphology. These findings establish a versatile platform for designing dynamic bioadhesive hydrogels with spatiotemporal control over material properties, offering significant potential for tissue engineering, regenerative medicine, and minimally invasive therapeutic applications.

Acknowledgements

The authors are grateful for financial support from The Centre of Excellence in Body-on-Chip Research (CoEBoC) (decision #336663) and SUSBIO PROFI7 (decision #352754), both funded by the Research Council of Finland.

D1 – P060
Decellularized CNS-derived hydrogels as neurotropic biomaterials for neural regeneration

Yilmaz-Dagdeviren H.D.[1], Arslan Y.E.[2], Arslan Yildiz A.A.[1]
[1]Dept. of Bioengineering, Izmir Institute of Technology (IZTECH), Izmir; [2]Dept. of Bioengineering, Canakkale Onsekiz Mart University (COMU), Canakkale, Turkey

Introduction
Regeneration within the central nervous system (CNS) remains limited due to the complex biochemical and structural microenvironment required for neuronal survival and axonal growth. Biomaterials capable of mimicking the native neural extracellular matrix (ECM) have therefore attracted considerable attention for neural tissue engineering[1]. Decellularized tissue-derived ECM biomaterials can preserve tissue-specific biochemical cues that regulate neuronal adhesion, proliferation, and differentiation[1,2].

The aim of this study was to fabricate tissue-specific ECM hydrogels from decellularized CNS tissues, including brain, spinal cord, and optic nerve, and to evaluate their structural characteristics and neurotropic potential for neural regeneration applications.

Materials and Methods
CNS tissues (brain, spinal cord, and optic nerve) were subjected to a pre-crosslinking-based decellularization protocol designed to remove cellular components while preserving the ECM architecture. Decellularization efficiency was assessed by histological staining and DNA quantification. Decellularized matrices were enzymatically digested and neutralized to obtain ECM hydrogels. FTIR, mechanical tests, swelling assays, and rheological tests were performed to evaluate physicochemical and structural properties of ECM hydrogels. For biological evaluation, SH-SY5Y neuroblastoma cells were cultured on CNS-derived ECM scaffolds. Cytocompatibility and metabolic activity were assessed using Live/Dead staining and MTT assays at days 1,3, and 7 time points. Neuronal adhesion and morphology were evaluated by immunofluorescence staining using F-actin, Collagen type I, and NeuN markers.

Results
Histological staining's confirmed effective removal of cellular components while maintaining ECM structural integrity. DNA quantification demonstrated a significant reduction of residual DNA <50 ng/mg, indicating successful decellularization. The digested ECM successfully formed hydrogels exhibiting fibrillar ECM organization and suitable physicochemical properties for neural tissue engineering. Rheological analysis demonstrated gel-like viscoelastic behavior with a higher storage modulus than loss modulus (G'>G"). Live/Dead staining and MTT assays revealed high cell viability (>80%) across all ECM-derived matrices. Brain- and optic nerve-derived ECM hydrogels supported higher metabolic activity and enhanced neuronal attachment compared to spinal cord-derived ECM. Immunofluorescence analysis demonstrated neuronal adhesion and axonal extension within the ECM hydrogels.

Conclusion
CNS-derived ECM hydrogels provide a supportive and neurotropic microenvironment that promotes neuronal viability, attachment, and neurite extension. By preserving tissue-specific biochemical signals, these biomaterials represent promising biomimetic scaffolds for neural tissue engineering. Furthermore, the hydrogel-forming capability and viscoelastic properties of these ECM materials suggest their potential applicability as injectable biomaterials for minimally invasive CNS repair strategies.

Acknowledgements
This study was financially supported by Health Institutes of Türkiye (TÜSEB) under project number 24418.

References
[1]Ozudogru E., Arslan Y.E. A preliminary study on the development of a novel biomatrix by decellularization of bovine spinal meninges for tissue engineering applications. *Cell and Tissue Banking* 2021; 22; 25–38.
[2]Arslan Y.E., Efe B., Sezgin Arslan T. A novel protocol to generate decellularized bovine spinal cord extracellular matrix-based scaffolds (3D-dCBS). *Bio-Protocol* 2019; 9; e3380.

D1 – P061

PEGDA based MG and TA containing, in situ forming hydrogels as new tissue adhesives

Dinçer İşoğlu S.,*[1] Yavrum, N.[1], Subay, L.B[1], Deneme, İ.[2], Usta,H.[3], İ İşoğlu, A.İ.[1], Toğuzoğulları, M.[4]
[1]Abdullah Gül University, Bioengineering Dept. and Bioengineering Graduate Program, Kayseri; [2]Abdullah Gül University, AGU Central Research Facility, Kayseri; [3]Abdullah Gül University, Materials Science & Nanotechnology Engineering Dept., Kayseri; [4]Yıldız Technical University, Bioengineering Dept., İstanbul, Turkey

Introduction


An ideal tissue adhesive should possess optimal mechanical stability, rapid gelation, and high adhesion, even in moist environments[1,2]. However, current tissue adhesives still suffer from low biocompatibility, cytotoxicity, slow adhesion, and weak bonding to moist biological surfaces. To address these challenges, we prepared a UV-induced tissue adhesive using PEGDA, a sugar moiety (MG), and tannic acid (TA). TA and MG were added to enhance adhesion and limit swelling capacity. The resulting hydrogel-based materials showed mechanical and physicochemical characteristics comparable to those in the literature.

Materials

Adhesive hydrogels were obtained by UV-induced (0.3% LAP) cross-linking of PEGDA and MG in the presence of TA. The effects of UV exposure time, PEG chain length, and initiator concentration were optimized. The hydrogels were first characterized by mechanical analysis, and their compressive modulus values were determined. The storage modulus and loss modulus of selected hydrogels were analyzed using rheometry (at 1 Hz frequency, 0.1–100% strain), and the effects of MG and TA on viscoelasticity were evaluated. A swelling test was conducted at 37°C in PBS solution for 24 hours to investigate the swelling limitation effect of TA. Additionally, a lap-shear test was performed on selected hydrogels to assess their adhesion strength. Finally, the cytotoxicity of the hydrogels was evaluated using the MTT assay with fibroblast cells in cell culture.

Results

We obtained PEGDA-based hydrogels containing MG and TA through UV-induced crosslinking. PEGDA and MG were cross-linked via photopolymerization with TA, which forms physical cross-links. Mechanical characterizations showed that adding MG and TA increased compressive modulus (0.3 to 4 kPa) and strength (30 to 270 kPa). We also investigated TA's effect: hydrogels with TA during polymerization showed lower mechanical strength than those with TA added afterward. Rheological tests showed viscoelastic behavior between 20% and 100% strain, with the strain threshold increasing with MG and TA. Swelling analyses revealed swelling ratios of 250%–1000%. Adding TA restricted swelling, which benefits adhesive materials. Adhesion strength reached 33 kPa for a selected PEGDA-MG-TA hydrogel. Moreover, the hydrogels showed high cell viability and adhesion.



Conclusion

The developed hydrogels exhibited good elasticity and biocompatibility with high cell adhesion upon contact with in vitro–cultured cells. Overall, this newly developed photocrosslinkable hydrogel shows strong potential as a biological glue for internal medical applications.

Keywords: Polyethyleneglycol diacrylate, tannic aicd, photocrosslinking, tissue adhesive, bioinspired

Acknowledgement

This project is supported by TÜBİTAK-222M111.

References

[1]Annabi, N., Zhnag, Y.N. vd., 2017. Engineering a highly elastic human protein–based sealant for surgical applications. *Sci Transl Med* 9(410).
[2]Fan, H., Wang, J.,and Jin, Z. 2018. Tough, Swelling-Resistant, Self-Healing, and Adhesive Dual-Cross-Linked Hydrogels Based on Polymer-Tannic Acid Multiple Hydrogen Bonds. *Macromolecules* 51(5); 1696–1705.

D1 – P062

Silk-elastin like polypeptides for electrospun small diameter vascular grafts

Thompson A.[1], Parhizkar M.[2], López Barreiro D.[1]
[1]Manufacturing Futures Lab, Dept. of Chemical Engineering, University College London, London; [2]Dept. of Pharmaceutics, University College London School of Pharmacy, London, UK

Introduction

Clinically available small diameter vascular grafts (SDVGs, internal diameter < 6mm) required for procedures such as coronary bypass surgery have lower patency compared to larger diameter grafts. This is due to multiple factors including the compliance mismatch between mechanically stiff, synthetic grafts and adverse immune responses. A common type of acellular tissue engineering SDVGs are decellularized natural matrices, however the decellularization process compromises the mechanical and biological properties of these scaffolds. To overcome the reduced mechanical properties, SDVGs can be reinforced via electrospinning of polymeric coatings. To this end, recombinant silk-elastin like polypeptides (SELPs) provide an alternative material for the development of SDVGs. SELPs combine the mechanical strength of silk fibroin and the stimuli-responsiveness of elastin.

Aim

In this work, we aim to electrospin SELPs to produce fibrous meshes that mimic the extracellular matrices of human arteries and can be used as reinforcement coatings. To that end, we systematically investigate the effect of SELP sequence design and post-processing treatments on the durability and biocompatibility of SELP films, to identify optimal SELPs for subsequent electrospinning studies.

Materials and Methods

Six recombinant SELP sequences with varying molecular weight (MW), charge and number of silk-like blocks were bio-fabricated using *E. coli* BL21* strain and purified through inverse temperature cycling. Aqueous SELP solutions were produced and used to cast films, and post-treatment methods (e.g., ethanol/methanol annealing) were applied to the films to vary their mechanical and structural properties. Cell viability testing carried out by seeding human dermal fibroblasts (HDFs) onto SELP films. MTT assay and fluorescence microscopy were performed to assess cell viability, cell adhesion and morphology. The mechanical properties of the various SELPs were assessed with rheology.

Results

Rheology demonstrates that higher MW SELP lead to more stable materials in cell cultures, which we attribute to their increased clustering of silk-like blocks. Mechanical properties are similar across neutral and negatively charged SELP sequences, while positively charged SELPs are significantly weaker. In terms of biocompatibility, preliminary studies indicate that neutral SELPs perform best in cell viability studies, leading to increased cell proliferation and more durable materials. Overall, our results provide guidelines on the influence of SELP charge, molecular weight and silk-like block distribution on the electrospinning parameters for the production of stable meshes.

Conclusion

SELPs are a strong candidate for the development of small diameter vascular grafts due to their biocompatibility and our ability to precisely tune their properties via sequence design and post-processing treatments.

Acknowledgements

This project is possible due to the H Walter Stern Scholarship, now part of the UCL-Research Opportunity Scholarship, and the Windsor Fellowship.

D1 – P063

Bioinspired design of hydrogel adhesives for lung tissue engineering

Harrison J.[1,3], Moise S.[2,3], Perge L.[1,3,4]
[1]Dept. of Mechanical Engineering, University of Bath, Bath; [2]Dept. of Chemical Engineering, University of Bath, Bath; [3]Centre for Bioengineering and Biomedical Technologies (CBio), University of Bath, Bath; [4]The Foundry, University of Bath, Bath, UK

Introduction

Persistent Air Leak (PAL) is one of the most common post-operative complications. It occurs following thoracic surgery due to current “gold standard” wound closure methods, staples and sutures, not mechanically matching lung tissue. There is a clinical need to develop biocompatible and safe adhesives that also match the mechanical properties of the lung to prevent PAL, improve post-operative patient outcome and reduce length of hospital stay. Furthermore, there is a drive to reduce carbon footprint within hospitals and find a sustainable alternative to synthetic medical adhesives. This research looks at functionalising natural polymers to improve adhesivity to wet tissues.

Aim

The aim of the study is to design a wet adhesive, from natural polymers and adhesion promoters. The results from this research will add to the development of a bioadhesive that can adhere to lung tissue and prevent PAL.

Materials and Methods

Alginate, chitosan, pectin and pullulan were screened for their capability to be functionalised with polyphenols, tannic acid and gallic acid, to improve their adhesivity. Solutions were prepared in aqueous conditions. Chemical composition of the solutions and bond formation were assessed using Proton Nuclear Magnetic Resonance (^{1}HNMR) and Fourier Transform Infrared Spectroscopy (FTIR). To assess the adhesivity of the materials, lap shear tests by tension loading (ASTM F2255) were conducted.

Results

Early results indicate the formation of covalent bonds between chitosan and tannic acid, and chitosan and gallic acid, due to precipitate formation indicating supramolecular complex formation. FTIR and ^{1}HNMR analysis showed alginate and pectin did not form covalent bonds with tannic acid. Chemical analysis using ^{1}HNMR and FTIR will be conducted on chitosan samples in anticipation that results will show the chemical bonding of polyphenols tannic acid and gallic acid with the polymer. Adhesion tests will indicate that the addition of polyphenols to natural polymers will improve the adhesivity and increase lap-shear strength in the wet tissue environment.

Conclusion

This work shows that the adhesivity of naturally derived polymers can be improved using polyphenols. This indicates that this technology could be suitable for use as a sustainable alternative to synthetic medical adhesives.

D1 – P064

Scalable strategy for structurally reinforcement architecture to improve toughness of elastomers

Zhang W.[1], Talebian S.[1], Dehghani F.[1]*, Naficy S.[1]*
[1]School of Chemical and Biomolecular Engineering, The University of Sydney, Sydney, Australia

Introduction

Elastomers are widely used in engineering and biomedical applications but often exhibit limited toughness and insufficient resistance to mechanical deformation under dynamic conditions, constraining their long-term durability. Conventional reinforcement strategies typically require additional processing steps or offer limited control over internal structural design.

Aim

In this study, benzophenone was employed as a photo-sensitive crosslinking agent to generate various reinforcing patterns within the polymeric system to address the limitations of conventional reinforcement strategies.

Materials and Methods

Four different thermoplastic elastomers were used in this study to explore the versatility of investigated method. Benzophenone (BP) was used as photo initiator.




Figure 1. Fabrication Methods for UV-Induced Reinforced Films and Prosthetic Heart Valves

Results




Figure 2. Images of (A) UV-line patterned tube and (B) Stress-Strain curve of no UV and UV-line patterned samples. Comparison of (C) Maximum stress, (D) Maximum strain and E. Tensile modulus for no UV crosslinked and UV line pattern crosslinked samples cut from tube.

Figure 2 shows that curved samples with the UV-line patterns exhibit superior stress-strain performance compared to their non-UV counterparts, achieving higher maximum stress, greater elongation at break, and increased tensile modulus. These finding confirm that UV crosslinking effectively enhances the mechanical performance of polymeric constructs with complex geometries, extending the applicability of the proposed reinforcement strategy beyond flat substrates.




Figure 3. Images of (A) UV-line patterned and (B) no UV prosthetic heart valves in pulse duplicator at closing and opening conditions. Comparison of (C) Regurgitation Fraction and (D) Effective Orifice Area for no UV crosslinked and UV line pattern crosslinked prosthetic heart valves, as well as the ISO-5480-2 standard values.

The hydrodynamic performance of both uncross-linked and line patterned polymeric heart valves fulfills ISO-5480-2 standard, with no significant change in RF and a slight improvement in EOA for the pattern reinforced SIS-22 PHV. Furthermore, both valves exhibited identical behaviour during systolic and diastolic cycles in the pulse duplicator. Overall, these results confirm that pattern reinforcement does not compromise hydrodynamic performance, supporting its potential for application in elastomeric devices with complex geometries.

Conclusion

A novel UV-Assisted method was developed for fabricating structurally reinforced polymeric film using benzophenone as a photo initiator, with the optimal concentration identified for effective crosslinking. This fabrication method demonstrated that the UV-patterned reinforcement structure significantly improves the mechanical performance of polymeric systems, particularly in terms of tensile modulus and toughness, while remaining scalable for mass production. Furthermore, the feasibility of this UV crosslinking method was validated in complex geometries, including heart valve and tubular constructs, without compromising functional performance. Overall, the UV crosslinking method offers a promising route to overcome limitations of existing reinforcement techniques, enabling the development of advanced polymeric materials with tailored properties for diverse applications—without additional post-processing steps.

D1 – P065

Making human ECM printable: A photocrosslinkable ink for extrusion bioprinting

Moreira R.S.[1,2], Santos S.C.[1], Oliveira I.M.[1], Mano J.F.[2], Custódio C.A.[1,2]
[1]Metatissue – Biossolutions, Lda; PCI · Creative Science Park Aveiro Region, Ílhavo; [2]Dept. of Chemistry, CICECO, University of Aveiro, Aveiro, Portugal

Introduction

The extracellular matrix (ECM) plays a central role in regulating cell behaviour and tissue mechanics, with collagen representing its most abundant structural component. Due to its intrinsic biocompatibility and low immunogenicity, collagen has been widely explored in tissue engineering, including applications in bioprinting.[1] 3D bioprinting enables the fabrication of complex constructs through the controlled deposition of biomaterial inks and living cells. Among these materials, decellularized ECM (dECM) is particularly attractive because it retains biochemical and structural cues that support cellular function.[2]

Aim

This work aims to develop and characterize a human dECM-derived photocrosslinkable ink with suitable rheological properties for extrusion bioprinting.

Materials and Methods

Human tissue was processed to isolate collagen from the dECM, and the resulting material was chemically modified with methacryloyl groups to obtain a photocrosslinkable derivative(dECM-MA). The obtained dECM-MA was further characterized in terms of composition and degree of modification, and its suitability for extrusion bioprinting and stem cell culture was evaluated. Mechanical properties and shear-thinning behaviour were assessed through compressive testing and rheological analysis.

Results

Printing parameters, including extrusion pressure, printing speed and needle gauge, were optimized to ensure high printing fidelity. Optimal conditions were obtained using a 27G needle, an extrusion pressure of 15 kPa and a printing speed of 12 mm/s following a preheating step to reach the appropriate viscosity. Under these conditions, grid-like structures were successfully fabricated(Figure1A), displaying good shape fidelity and well-defined architecture(Figure1B and 1C). Bioactivity assays performed with cardiac fibroblasts(hCFs) and endothelial cells(HUVECs) demonstrated high cell viability(Figure1D), indicating that the printed matrices provide a supportive microenvironment for cell survival.

Conclusion

The developed human-derived ink exhibited suitable rheological properties, good printability and high cytocompatibility. These findings highlight the potential of this material as a promising platform for the fabrication of biologically relevant constructs for cardiac tissue engineering.

Acknowledgements

This work was developed within the scope of the project CICECO Aveiro Institute of Materials, UID/50011/2025 (DOI10.54499/UID/50011/2025) & LA/P/0006/2020 (DOI10.54499/LA/P/0006/2020), financed by national funds through the FCT/MCTES (PIDDAC). The authors acknowledge the EIC Pathfinder project PULSE (European Union's Horizon 2020 research under grant agreement No 101099346) & COMPETE2030-FEDER00836800 (doi.org/10.54499/2023.17280.ICDT), financed by national funds through the FCT/MCTES (PIDDAC). RM thanks FCT through PDQI for her PhD grant ref. 2023.04155.BDANA (https://doi.org/10.54499/2023.04155.BDANA).




Figure 1. (A)Grid-like structure printed under optimized conditions using dECM-MA after light crosslinking. (B)Outer geometry of grid-like structures with different infill percentages; A–D indicate the four sides of the structure. (C)Ratio between the practical and theoretical perimeters of the inner squares at different infill percentages. (D)hCFs and HUVECs seeding on the printed structure.

References

[1]Dondi C.,Tsikritsis D.,Vorng J.,Greenidge G.,Kepiro I.E.,Belsey N.A.,McMahon G.,Gilmore I.S.,Ryadnov M.G.,Shaw M. Multiparametric physicochemical analysis of a type1 collagen 3D cell culture model using light and electron microscopy and mass spectrometry imaging. *Scientific Reports* 2025; 15; 9578.

[2]Bebiano L.B.,Presa R.,Vultaggio I.,Oliveira A.L. Design and bioprinting of decellularized extracellular matrix-based bioinks for skin tissue engineering. *Journal of 3D Printing in Medicine* 2023; 7; 3DP15.

D1 – P066

Catecholamine functionalisations tailor 3D printability of hyaluronan bioinks

Hopia K.[1,2], Vuorimaa-Laukkanen E.[2], Ylä-Outila L.[1], Skottman H.[1], Mörö A.[1]
[1]Faculty of Medicine and Health Technology, Tampere University; [2]Faculty of Chemistry and Advanced Materials, Tampere University, Tampere, Finland

Introduction

3D-bioprinting is an additive manufacturing method with the potential to create highly controlled structures from scaffolds to the ambitious goal of printing tissue substitutes. The rise of this technology has generated a demand for innovative and customizable 3D-printable bioinks. Many synthetic and natural materials have been investigated for their suitability as bioinks, which must support cell growth and be selected with care.

Aim

The aim was to observe the effect of catechol on both 3D-printability and mechanical properties of formed bioinks: four catechol derivatives were grafted to hyaluronic acid. We systematically compare
how these selected catecholamines influence the mechanical, adhesive and printability properties of HA-based bioinks

Materials and Methods

We modified hyaluronic acid with catechol derivatives and Schiff base crosslinkers. Degree of modification was determined with both NMR and UV-Vis spectroscopy and kept similar across all bioinks. Mechanical characterization included compression testing, rheological measurements to assess viscosity, shear thinning, stiffness (G' and G'') of formed hydrogels, and tensile testing for adhesion. Additionally, we printed bioinks with a 32G needle to characterise printability under two different conditions that aimed for high and low flow of bioink during the printing process.

Results

Catechol derivative affected mechanical properties, flow behaviour and printability of the bioinks. Tyramine, dopamine and levodopa improved printability while vanillylamine reduced it significantly as seen in Figure 1. Levodopa increased the viscosity which explains why the whole grid couldn't be printed with selected printing conditions.
Crosslinked bioink remains soft but could be handled and showed shear thinning behaviour critical for extrusion printing. Catechol modified hydrogels also showed self-healing properties.

Conclusion

Developed materials are elastic and adhere to surfaces and tissue. Since the Schiff base crosslinking method is dynamic; the structure can self-heal after subjected to deforming stress. These adhesive bioinks show potential for soft tissue engineering applications and have unique adhesive properties. Here we show that the selection of the catechol derivatives offers a new tool for designing 3D-bioprintable materials for various soft tissues and complex structures requiring different mechanical properties.

Acknowledgements

We are grateful for Business Finland, Vilho, Yrjö and Kalle Väisälä Foundation, Eye and Tissue Bank Foundation, Oscar Öflunds stiftelse, Foundation of Finnish Chemistry Congress, Research Council of Finland for supporting this study financially.




Figure 1. Images of bioinks containing different catechol derivatives grafted to hyaluronan. Images show printed structures with fast (16 mm/s speed and 0.6 bar pressure) and slow (6 mm/s speed and 1.0 bar pressure) printing conditions.

D1 – P067

Engineering a biomimetic 3D-printed hydrogel scaffold for pancreatic islet transplantation

Weerasinghe S.Y., Minsart M., Dubruel P.
Polymer Chemistry & Biomaterials (PBM) Group, Centre of Macromolecular Chemistry (CMaC), Dept. of Organic and Macromolecular Chemistry, Ghent University, Belgium

Introduction

Diabetes is a leading cause of death worldwide, with over half a billion adults living with the condition in 2024, out of which about 9 million individuals are diagnosed with type I diabetes (TID)[1]. There are various ongoing studies exploring different solutions to improve patients' quality of life and one possible solution is the islet cell transplantation that enables the natural functions of pancreatic beta cells, including insulin secretion[2]. Even though, islet transplantation has seen recent advancements in finding new transplantation sites, protecting the islets from autoimmune attack, increasing the supply of islets and finding new sources of islets, islet transplantation for TID treatment is still limited by complications like hypoxia[3,4].

Aim

In this work, we are exploring biocompatible engineered cell-based transplantation using hydrogels as a multi-component encapsulation system that resembles the extra-cellular matrix (ECM) of the islet cells.

Materials and Methods

To mimic the ECM environment formed by various proteins and polysaccharides, the photocrosslinkable derivatives of multiple biopolymers are selected, namely gelatin methacrylamide (GelMA), methacrylated hyaluronic acid (HAMA) and methacrylated alginate (AlgMA). These materials are characterized via ^{1}H NMR to confirm the chemical modifications while the print resins are investigated via in situ photo-rheology to explore the compatibility with subsequent photopolymerizing. The formulated resins are applied in digital light processing (DLP) printing to fabricate the various porous scaffold geometries with pore sizes ranging from 400-1000 µm and evaluated for their physiochemical properties.


Results

Multi-component resin formulations with viscosities below 5000 m Pa.s to enable effective subsequent DLP printing, are optimized to achieve a soft-tissue-like compressive modulus (1–10 kPa) consisting of gel fractions > 80%. Furthermore, both cubic, tricylindrical pore geometries of 500-800 µm pore sizes are designed to provide optimal islet cell integration, nutrient transport and immune protection.

Conclusion

The strategies used to enable printing, improve mechanical stability of the optimized 3D scaffold architectures, are reported with the aim to enhance oxygen transport and mechanical protection, improving the functionality post-transplantation of islets which will be evaluated in the future work.

CAD design of the scaffold



Cuboid with tricylindrical pores with 1 mm diameter circular opening

Printed scaffold



Figure: Multi-component hybrid 3D printed biopolymeric scaffold according to the CAD design of cuboid with tricylindrical pores with 1 mm diameter circular opening

References

[1]International Diabetes Federation. *IDF Diabetes Atlas 2025, 11th edn.* 2025. [Online]. Available: https://diabetesatlas.org/resources/idf-diabetes-atlas-2025/

[2]Abadpour S. et al., Adipose-Derived Stromal Cells Preserve Pancreatic Islet Function in a Transplantable 3D Bioprinted Scaffold. *Advanced Healthcare Materials*, 2023; vol. 12, no. 32; 2300640.

[3]Type 1 Diabetes Cure. *DRIF - Diabetes Research Institute Foundation* 2023. [Online]. Available: https://diabetesresearch.org/type-1-diabetes-cure/

[4]Farina M., Alexander J. F., Thekkedath U., Ferrari M., Grattoni A. Cell encapsulation: Overcoming barriers in cell transplantation in diabetes and beyond. *Advanced Drug Delivery Reviews* 2019; vol. 139; 92–115.

D1 – P068
Retrieved bacterial cells from nanopatterned substrates reveals hidden perforation events

Pirouz A.[1], Michalska M.[1], Papakonstantinou I.[2]
[1]Dept. Mechanical Engineering, University College London, London, UK; [2]Dept. Electronic and Electrical Engineering, University College London, London, UK

Introduction

Bioinspired nanotextured antimicrobial surfaces represent a promising frontier in the global effort to combat antimicrobial resistance (AMR). By imparting mechanical stress to the bacterial cell wall, these surfaces offer a physical kill mechanism that bypasses the need for traditional antibiotics. However, the development of these substrates remains in its infancy, hindered by several critical knowledge gaps. Chief among these is a lack of consensus regarding the primary driving forces behind cell wall perforation, the specific influence of substrate geometry, and a notable absence of standardised testing protocols.

Furthermore, the evaluation of these surfaces has historically been limited to a narrow range of microbial strains. Even within these limited studies, conflicting reports suggest that cell inactivation may not result solely from physical perforation. Advanced imaging has, in some instances, failed to reveal signs of cell wall rupture, particularly in Gram-positive bacteria. These species possess a significantly thicker, more robust peptidoglycan layer that is inherently more resistant to mechanical failure than their Gram-negative counterparts.

In this study, we address some of these contradictions by investigating the interface between Gram-positive *Bacillus subtilis (B. subtilis)* and sharp silicon nanocone (SiNC) substrates. We employ a novel mechanical extraction method using polydimethylsiloxane (PDMS) to retrieve the cells from the substrate after incubation, enabling direct imaging of the basal plane, the surface in immediate contact with the nanocones. Our results reveal clear evidence of perforation that remains hidden under conventional dorsal imaging (Figure 1A). This technique provides an accessible alternative to complex focused ion beam scanning electron microscopy or tomography, offering a more refined understanding of the mechanobiological interactions at the cell-nanopattern interface.

Materials and Methods

SiNC surfaces were fabricated via block copolymer lithography and dry etching. B. subtilis cells in deionised water were incubated on the SiNCs, allowing the inoculum to evaporate to induce capillary-driven contact. To image the hidden cell-surface interface, PDMS (1:10 ratio) was cast over the substrate and cured at 100°C. This PDMS layer was then peeled off to mechanically retrieve the bacteria, allowing for scanning electron microscopy (SEM) characterisation of the previously inaccessible basal plane to identify perforation events.

Results

Our results indicate that the robust, thicker cell wall of ***B. subtilis*** may appear undisturbed on the dorsal plane, closely resembling the morphology of healthy cells in standard imaging. However, analysis of the retrieved basal plane reveals significant perforation, suggesting that cell inactivation occurs most likely via mechanical rupture that is not visible from the top-down perspective.

A) B)




Figure 1. Micrograph of *B. subtilis*. (A) Displaying a seemingly undisturbed cell morphology on SiNC substrate. (B) Retrieved cell on PDMS, highlighting the contrast between the morphology of dorsal surface and the perforated basal plane, with the perforation pattern corresponding to the underlying SiNC topography.

Conclusion

These preliminary findings suggest that evaluating the antimicrobial efficacy of nanotextured substrates solely through conventional SEM imaging is insufficient, as it fails to capture perforation events that do not completely penetrate the dorsal cell wall. By revealing these hidden perforation events, our novel retrieval method provides a more accurate tool for studying the cell-nanopattern interface and optimising the design of next-generation mechano-bactericidal surfaces.

D1 – P069

Anti-adhesive surface performance of biomorphic calcium-phosphate scaffolds against planktonic bacteria

Restivo E.[1], Lo Bello G.[1, 2], Fassina L.[3], Ferrari A.[4], Ballardini A.[5], Raiteri R.[2], Sprio S.[6], Tampieri A.[6], Visai L.[1,6,7]
[1]Dept. of Molecular Medicine, University of Pavia, Pavia; [2]Dept. of Informatics, Bioengineering, Robotics and System Engineering (DIBRIS), University of Genoa, Genoa; [3]Dept. of Electrical, Computer and Biomedical Engineering, University of Pavia, Pavia; [4]Dept. of Industrial Engineering, University of Bologna, Bologna, Italy; [5]GreenBone Ortho SpA, Faenza; [6]Institute of Science, Technology and Sustainability for Ceramics - Italian National Research Council (ISSMC-CNR), Faenza; [7]UOR6 Nanotechnology Laboratory, Dept. of Prevention and Rehabilitation in Occupational Medicine and Specialty Medicine, Istituti Clinici Scientifici Maugeri IRCCS, Pavia, Italy

Introduction

In orthopedics field, scientists are continuing to research scaffolds to be used as bone implants capable on one side to guide and sustain the natural metabolism of cells towards tissue regrowth and on the other to confer antibacterial properties to face post-surgical infections.

Aim

The aim of the present work is to investigate the relationship between surface texture, topography and bacterial adhesion by comparing one wood-derived (GreenBone scaffold) and two sintered (MgHA and Comp-HA) calcium-phosphate based bone scaffolds with different synthesis and characteristics.

Materials and Methods

GreenBone scaffolds were prepared from Rattan wood pieces (*Calamus manan*) following a biomorphic transformation procedure. Two sintered hydroxyapatite scaffolds were used as comparison. The gamma sterilized scaffolds were characterized in terms of morphological and topographical properties through scanning electron microscopy (SEM) and atomic force microscopy (AFM), respectively. A texture analysis of surfaces was conducted through the Haralick computer-based approach. The anti-adhesive properties of the surfaces were investigated with planktonic cultures of a Gram-positive and negative bacteria in a time-dependent manner. Microscopy analyses (SEM) were performed on bacterial adhesion.

Results

The analyses of surfaces in terms of texture and topography demonstrated significant differences among all scaffolds. Preliminary results on bacterial adhesion exhibited a substantial reduction in the adhesion of both bacterial strains on calcium-phosphate scaffolds, particularly on GreenBone nature-based scaffolds. The obtained data demonstrated a difference in roughness and texture among all the scaffolds in terms of topography and morphology. Preliminary microbiological results indicated a reduced adhesion on surfaces, in particular on wood-derived scaffolds, suggesting a correlation between surface properties and bacterial adhesion behavior.

Conclusion

GreenBone scaffold is a nature-based synthetic, resorbable bone substitute, that is suitable for surgical reconstruction of bone defects and implantation in the human body. Further microbiological studies will be conducted to evaluate the anti-adhesive properties of the scaffold.

Acknowledgements

The authors acknowledge Prof. G.B. from the University of Pavia for SEM images. The study was supported by GreenBone Ortho SpA and by MUR (Italian Ministry of University and Research) with two grants to the Department of Molecular Medicine of the University of Pavia. The first under the initiative “Dipartimenti di Eccellenza (2018-2022) and (2023-2027)” and the second MUR Area Advanced Materials, FISA-2024-00376, “A natural regenerative solution for prevention and treatment of infections in orthopaedic surgery” (NatAnti).

D1 – P070

PVDF films incorporating zinc oxide tetrapods for enhanced piezoelectric and antibacterial performance

Silva P.F.[1,2], Moreira J.[1,2], Silva C. A.[1,2], Fernandes R.D.V.[3], Zille A.[3], Mishra K.Y.[4], Silva, F.[1,2], Fernandes M.M.[1,2]

[1]CMEMS, University of Minho, Guimarães, Portugal; [2]LABBELS, University of Minho, Braga, Portugal; [3]2C2T, University of Minho, Guimarães, Portugal; [4]Mads Clausen Institute, NanoSYD, University of Southern Denmark, Sønderborg, Denmark

Introduction

Poly(vinylidene fluoride) (PVDF) is a well-established electroactive polymer extensively employed in biomedical applications owing to its outstanding chemical stability, mechanical flexibility, and pronounced piezoelectric response[1]. In addition to these properties, previous studies have reported the intrinsic antimicrobial potential of PVDF-based systems, underscoring their suitability for applications where both functional performance and infection prevention are critical[2]. Zinc oxide tetrapods (t-ZnO) have attracted increasing attention due to their potential to enhance antibacterial activity and modulate the surface characteristics of polymer-based systems, which are key aspects in biomedical applications. Furthermore, their intrinsically anisotropic three-dimensional architecture may promote more efficient stress transfer and polarization under external mechanical stimuli, potentially contributing to an improved piezoelectric response. In this context, the incorporation of t-ZnO into PVDF represents a promising strategy to tailor the physicochemical, biological, and electromechanical performance of the resulting materials.

Materials and Methods

PVDF films were produced by solvent casting using N,N-dimethylformamide, incorporating t-ZnO from 0 to 20% (w/v). Processing temperature was varied to tailor PVDF crystallinity and surface properties, thereby influencing its electroactive and biological performance. Structural and thermal properties were analysed by FTIR, DSC, and STA, while morphology was evaluated by SEM. Wettability was assessed by contact angle measurements. Antibacterial activity against *Escherichia coli* was evaluated through CFU assays and biofilm formation tests. Cytocompatibility was assessed using MTS assays with HGF-1 cells.

Results

Films processed at RT and 40 °C exhibited high β-phase content, while those processed at 210 °C showed predominantly α-phase. The addition of t-ZnO increased β-phase content, suggesting a nucleating effect that may enhance electroactive behaviour.

Consistently, films with higher β-phase content also exhibited increased hydrophobicity and improved antibacterial performance. A reduction in *E. coli* viability was observed for all samples, being more pronounced at higher t-ZnO concentrations and lower processing temperatures, highlighting a synergistic effect between piezoelectric activity, surface properties, and ZnO antimicrobial mechanisms.

Cell viability results further confirmed the biocompatibility of the developed films, supporting their suitability for biological environments.

Conclusion

PVDF/t-ZnO films exhibit tunable piezoelectric, antibacterial, and biocompatible properties. The combined control of processing conditions and filler incorporation enables the design of multifunctional surfaces, highlighting their potential for advanced biomedical applications.

Acknowledgements

This work was supported by national funds through the Fundação para a Ciência e a Tecnologia (FCT) within the framework of the projects
2022.02697.PTDC and by the European Regional Development Fund through the Operational Competitiveness Program and the National Foundation for Science and Technology of Portugal (FCT) under the projects UID/04436/2025 of Center for Micro-Electro Mechanical Systems CMEMS, LA/P/0029/2020 (https://doi.org/10.54499/LA/P/ 0029/2020) of LABBELS-Associate Laboratory in Biotechnology, Bioengineering and Microelectromechanical and UID/CTM/00264/ 2023 of Centre for Textile Science and Technology (2C2T).

PFS thanks FCT for his PhD grant (2024.05793.BDANA) and MPF thanks European commission for VINNY project (ID: 101130039).

References

[1]Fernandes M.M. et al., Magnetoelectric Polymer-Based Nanocomposites with Magnetically Controlled Antimicrobial Activity. *ACS Appl. Bio Mater.* 2021; vol. 4, no. 1; 559–570.
[2]P. F. Silva *et al.*, “Surface & Coatings Technology Electroactive coatings on laser-textured titanium-based substrates for an improved antibacterial activity ☆,” vol. 519, no. November 2025, 2026
[3]Mishra Y.K., Adelung R., ZnO tetrapod materials for functional applications. *Mater. Today* 2018; vol. 21, no. 6; 631–651.

D1 – P071

In vitro and _in vivo_ evaluation of a novel biomimetic arteriovenous graft material

Tornby D.R.[1,2], Alm M.[3], Stenehjem M.[4,5], Lindholt J.S.[4,5], Andersen T.E.[1,2]
[1]Dept. of Clinical Microbiology, Odense University Hospital, Odense; [2]Research Unit of Clinical Microbiology, University of Southern Denmark; [3]Biomodics ApS, Rødovre; [4]Dept. of Cardiothoracic and Vascular Surgery, Odense University Hospital, Odense; [5]Research Unit of Cardiothoracic and Vascular Surgery, University of Southern Denmark, Odense, Denmark

Introduction

Haemodialysis relies on arteriovenous grafts (AVGs). Currently used ePTFE grafts, however, are limited by their poor long-term patency. Their non-optimal biocompatibility, triggers a foreign body response and a subsequent cascade of adverse events such as stenosis and thrombosis, that remains difficult to mitigate with current strategies. This study evaluates a novel AVG material designed to address these limitations. We assessed its potential from benchtop to large-animal application, focusing on long-term mechanical integrity and anticoagulation properties.

Materials and Methods

The AVG material tested in this study consisted of an interpenetrating polymer network (IPN) of hydrogel in a PDMS and PHEMA-co-PEGMEA, with the latter serving as guest polymer, introduced together with zwitterionic monomers. Sustained local therapy through drug loading and release profiles and support for cellular growth was assessed using functional cell culture assays. *In vivo* evaluation of the AVG included short-term implantation in a subcutaneous murine model to evaluate material tissue biocompatibility. Long-term performance of a functional graft was tested in sheep for up to one year (Figure 1A). Aging and antithrombotic properties of explanted AVG was assessed via tensile strength measurements and quantifying generation of Thrombin-Antithrombin (TAT) Complex levels using ELISA.

Results

The mechanical compliance showed no significant changes in stress tolerance when comparing the AVG before implantation with AVG explanted after one year in sheep (Figure 1B).




Figure 5. A) Implanted AVG in sheep. B) Failure stress tolerance of AVG pre- and post-implantation in sheep. Unpaired t-test showed no significant differences.

ELISA results showed significantly lower surface-activation of coagulation on the IPN AVG compared to the reference silicone material based on the TAT generation measurements (Figure 2).




Figure 6. TAT generation on AVG material in citrated plasma (A), in defibrated plasma (B) or on AVG material after 1 year in sheep in citrated plasma (C). Results are shown as percentage of silicone control (n=6 for A and B and n=4 for C) and compared to the silicone control using Dunnett's test for significance. ***:P<0.001, ****:P<0.0001.

Conclusion

The novel AVG integrated mechanical stability, biological tolerance, and functional performance in a large animal model, representing a step toward an improved solution for haemodialysis patients. Future work will focus on the ability of the graft to resist repeated cannulation necessary in haemodialysis patients.

Acknowledgements

This work was supported by the European Union's 9th Framework Program Horizon Europe [agreement NO. 101057673] and the Region of Southern Denmark's PhD fund.

D1 – P072

Surface coating with end-on PEGylated heparin enhances specific antithrombin binding

Costa R.R.[1,2], Brito A.[1,2], Novoa-Carballal R.[3,4], Reis R.L.[1,2], Pashkuleva I.[1,2]
[1]3B's Research Group, I3B's Research Institute on Biomaterials, Biodegradables and Biomimetics, University of Minho, Barco, Guimarães, Portugal; [2]ICVS/3B's – PT Government Associate Laboratory, University of Minho, Portugal; [3]CINBIO, Universidade de Vigo, Dept. de Química Orgánica, Vigo, Pontevedra, Spain; [4]Instituto de Investigación Sanitaria Galicia Sur, Vigo, Pontevedra, Spain

Introduction

The most common issue with blood-contacting medical devices is coagulation and consecutive thrombi formation. Heparinization, *i.e.,* the coating of surfaces with heparin (Hep), is commonly used to cope with this issue due to Hep capacity to bind antithrombin (AT) and boost its affinity to clotting factors such as thrombin (T). In these coatings, Hep is usually immobilized *side-on*, which differs from the *end-on* conjugation of Hep in natural proteoglycans. Herein we introduce a coating made of biomimicking *end-on* PEGylated Hep and compare it with an analogue *side-on* immobilization of Hep.

Materials and Methods

Hep (14 kDa) was *end-on* conjugated to a biotin-functionalized PEG (degree of modification of ≈70%).[1] Surface plasmon resonance (SPR, Biacore X100) was used to quantify affinity and mass deposition of coagulation proteins AT III and AT III:T mixture (1:1 molar). *End-on* biotin-PEG-Hep (25 µg/mL) and *side-on* biotin-Hep (25 µg/mL) were immobilized on a streptavidin chip (15 min, 5 µL/min). Proteins (270–4300 ng/mL) were injected at 30 µL/min for 180s (association) and washed for 180s.

Results

The molecular design of biotin-PEG-Hep contains three components: (i) biotin group, for fast and efficient "click" binding to streptavidin substrates, (ii) PEG portion, which grants flexibility of Hep segment and avoids non-specific protein adsorption, and (iii) Hep biofunctional moiety. SPR data (Table 1) showed that the dissociation constants (K_D) and saturation masses (m_{max}) for AT III over the *end-on* and *side-on* coatings are similar and within expected affinity range. When AT III was injected alongside with T, K_D did not vary significantly. However, m_{max} was two-fold higher on the *end-on* PEGylated Hep surface than on *side-on* Hep. This result suggests that the high flexibility of PEGylated Hep favours conformational changes of the bound AT III and consequent T retention, whereas *side-on* Hep remains more surface constricted and does not allow for AT III conformational adjustment towards T binding.

Conclusion

We showed that *end-on* Hep PEGylation favours the formation of the bioactive AT-Hep complex. Compared to conventional *side-on* heparinized surfaces, it allows capturing a higher amount of T from the bulk, potentially leading to T seizure and inhibition of the clotting process.

Acknowledgements

Portuguese FCT (2022.00764.CEECIND/CP1718/CT0020; 2022.03823.CEECIND/CP1718/CT0003; UID/PRR/50026/2025), Ministry of Science, Innovation and Universities of Spain (RYC2021-032344-I), EC (ArtPlac, HORIZON-EIC-2022-PATHFINDEROPEN-01-101099596).

Table 1. Quantitative data for the interactions between each heparinized surface and AT III or AT III:thrombin analytes, obtained from the SPR sensograms fitted to a two-state reaction model (n=3).

	AT III		AT III:thrombin (1:1 mol)	
	K_D (M)	m_{max} (ng/cm^2)	K_D (M)	m_{max} (ng/cm^2)
end-on PEGylated Hep	3.1×10^{-8}	2.9	6.7×10^{-8}	16.5
side-on Hep	2.5×10^{-8}	2.8	5.3×10^{-8}	8.1

References

[1]Amaral S. et al. End-on PEGylation of heparin: Effect on anticoagulant activity and complexation with protamine. *International Journal of Biological Macromolecules* 2023; 249; 125957.

D1 – P073

3D solvent-cast printing of electroactive PLLA scaffolds for piezoelectric and hybrid hydrogel-based tissue engineering

Gazvoda L., Spreitzer M., Fabijan D., Vukomanović M.
Advanced materials dept., Jožef Stefan Institute, Ljubljana, Slovenia

Introduction

Poly-L-lactic acid (PLLA) is a biodegradable and biocompatible polymer widely used in biomedical applications due to its favorable mechanical properties and controllable degradation. Importantly, PLLA can exhibit piezoelectric properties when sufficient molecular orientation and crystallinity are achieved. Since conventional methods such as drawing and nanotexturing are limited for high-molecular-weight and filler-rich systems, this study explores solvent-cast extrusion 3D printing to fabricate oriented PLLA 3D porous composites for piezoelectric scaffolds. Combined with cell-laden hydrogels, these scaffolds may support tissue regeneration and improve the cellular microenvironment.

Materials and Methods

PLLA solution was prepared in chloroform and processed into a highly viscous printable paste. Formulation was optimized to ensure shearing effect through the nozzle. For composite, 10 wt.% biomimetic hydroxyapatite nanoparticles were incorporated. Structural characterization was performed in detail. Piezoelectric response was measured as electrical response to ultrasound stimulation. Biocompatibility was performed against HaCaT cells by measuring cell viability using Presto Blue reagent. In addition, cell-laden hydrogel was introduced into the printed scaffolds and photo crosslinked to explore the formation of hybrid constructs.

Results

The optimized formulation enabled stable printing of at least three layers while preserving line geometry across different patterns (Fig. 1a, b). Composite PLLA/HAp scaffolds were successfully fabricated and exhibited a measurable piezoelectric response (Fig. 2a), confirming the feasibility of producing electromechanically active scaffolds via solvent-cast 3D printing. Cells cultured on the scaffolds for 2 days showed high viability, indicating good cytocompatibility. Hybrid scaffolds with hydrogels incorporated into the pore spaces enabled homogeneous cell distribution and improved the cellular microenvironment within the three-dimensional construct (Fig. 1c).

Conclusion

Solvent-cast extrusion printing represents a promising strategy for fabricating oriented PLLA composite scaffolds with controlled architecture, piezoelectric functionality, and good cytocompatibility. The combination of printed PLLA scaffolds with cell-laden hydrogels may further enhance mechanical support, improve nutrient diffusion, and facilitate cell incorporation within complex three-dimensional structures, supporting the development of hybrid piezoelectric scaffolds for tissue engineering and regenerative medicine.

Acknowledgements

This work was supported by the Regenesis project (PR-13605) and the research programme P2-0091. The author would also like to thank Dr. Ita Junkar (Jožef Stefan Institute) for providing access to the 3D bioprinter.




Figure 7. a) SC - 3D printing procedure of PLLA and different infill patterns as b_1) grid 25%, b_2) grid 35%, b_3) concentric 25% and c) image of matrix/cell-laden hydrogel scaffolds showing colour change of resorufin generated by metabolic reduction of the Presto Blue reagent within the scaffold confirming viability of cells inside gel.




Figure 8. a) Measured electrical output during 1 MHz ultrasound stimulation, b) cell viability of HaCaT cells seeded on solvent cast 3D printed samples (SC-printed).

D1 – P074

A lymph node-mimicking 3D hydrogel model for follicular lymphoma

Otín-Sánchez S.[1,2,3], Colomer D.[3,4,5,6], Pérez-Galán P.[3,4], Guasch J.[1,2]
[1]Institute of Materials Science of Barcelona (ICMAB-CSIC), Bellaterra; [2]Dynamic Biomimetics for Cancer Immunotherapy, Max Planck Partner Group, ICMAB-CSIC, Bellaterra; [3]Dept. of Hematology-Oncology, Institut d'Investigacions Biomèdiques August Pi I Sunyer (IDIBAPS), Barcelona; [4]Centro de Investigaicón Biomédica en Red-Oncología (CIBERONC), Madrid; [5]University of Barcelona, Barcelona; [6]Hematopathology Section, Pathology Dept., Hospital Clínic, Barcelona, Spain

Introduction

Although the advancement in therapies for the treatment of non-Hodgkin lymphomas, Follicular Lymphoma (FL), the most common one, is still incurable. FL consists on the accumulation of germinal center B cells in lymph nodes (LN) with, in most cases, the t(14;18) mutation leading to a defective apoptosis. However, this mutation alone is insufficient for the development of the disease, FL cells require of a supportive tumour microenvironment (TME) to survive and proliferate. Currently, *in vitro* models lack TME to replicate the interactions with FL cells, while *in vivo* models are costly and fail to capture interpatient variability.

Aim

In this work, we present a three-dimensional (3D) model based on a LN-mimicking poly(ethylene) glycol (PEG) heparin (Hep) scaffold for the co-culture of FL patient cells and stromal cells which faithfully recapitulate the complexity of FL and interpatient heterogeneity.

Materials and Methods

In this work, PEG-Hep hydrogels functionalized with adhesion peptides were made using the inverse opal (IOPAL) technique with PMMA microbeads as a templating suspension. PBMCs derived from FL patients were cultured into the hydrogels in co-culture with a modified dendritic cell line. Viability, attachment, and proliferation were assessed by confocal microscopy and flow cytometry.

Results

The hydrogels successfully incorporated adhesion ligands allowing dendritic cell adhesion and viability. Viability and proliferation of FL cells was maintained throughout the culture.

Conclusion

Adhesive PEG-Hep hydrogels are a good platform to develop a new in vitro patient-derived FL model.

D1 – P075

Melatonin-conjugated supramolecular peptide gel for wound healing applications

Bundel P.[1], Shounak P.[1], Vashisth A.[2], and Singh Y.[1,2]
[1]Dept. of Chemistry, Indian Institute of Technology Ropar, Rupnagar; [2]Dept. of Biomedical Engineering, Indian Institute of Technology Ropar, Rupnagar, Punjab, India

Introduction

Wounds represent a significant socioeconomic challenge worldwide, affecting millions of people each year. Elevated oxidative stress, heightened inflammation, and bacterial infections at the wound site impede healing and extend the duration of recovery. Therefore, a multifaceted strategy is required to manage wound care. The supramolecular assemblies formed by amphiphilic peptides, owing to their dynamic and adaptive nature, have been extensively utilized in the design of wound care materials. Although promising, developing the multifunctional material from a minimal peptide sequence to tackle the defective wound microenvironment remains a challenge. To address this gap, we have designed a melatonin-conjugated amphiphilic peptide that self-assembles into a nanofibrillar gel. This design combines the antioxidant and immune-regulating qualities of melatonin with the antibacterial properties of amphiphilic peptide nano-assembly.

Materials and Methods

The melatonin-conjugated peptide amphiphile was synthesized by solution and solid-phase synthesis. The heating-cooling method was used to fabricate the supramolecular nanofibrous gel network. The gel was characterised using FTIR, Circular Dichroism, FE-SEM, TEM, and Oscillatory Rheology. Antioxidant activity of the gel was assessed using the ABTS assay, while the optical density and colony count methods were used to assess antibacterial activity. The cytocompatibility of gels was studied in L929 and RAW 264.7 cell lines using the MTT assay and Live/Dead imaging. The scratch assay was used to assess wound-healing activity, while RT-qPCR and immunocytochemistry were performed to assess macrophage polarisation.

Results


In this work, we have designed a nanofibrous, viscoelastic, and self-healable gel from an ordered supramolecular assembly of a melatonin-conjugated peptide (**Scheme 1**). The inclusion of melatonin imparted the gel with radical-scavenging activity, while the amphiphilic nature of the nanofibrillar assembly enabled physical disruption of *S. aureus* bacterial cells. The peptide gels showed cytocompatibility against mammalian cells and allowed efficient cell adhesion and migration. Furthermore, treatment of gels with immune cells led to enhanced expression of anti-inflammatory factors and reduced expression of pro-inflammatory factors, thereby enabling effective wound management.

Conclusion

In contrast to traditional wound-healing materials, the present work emphasizes the development of a biologically active, multifunctional peptide scaffold that exhibits strong radical-scavenging activity, controls *S. aureus* infection, and promotes an anti-inflammatory phenotype in immune cells, thereby enhancing wound healing.

Acknowledgements

Financial support from DST/GITA (grant # GITA/DST/TWN/P-98/2022) to Y.S. is gratefully acknowledged, and PB thanks the DST India for the DST INSPIRE Fellowship (DST/INSPIRE/03/2022/002776).



Scheme 1: Self-assembled melatonin-conjugated peptide gel demonstrating multifunctional effects at the wound site.

D1 – P076

Biomimetic hydrated coatings for ultra-low friction ceramic applications

Börke J.M.[1,2], Rothe H.[1], Thiele D.[3], Grafahrend D.[4], Witt C.[5], Liebelt M.[5], Hildebrand G.[1], Liefeith K.[1], Kruppke B.[1,6]

[1]Institut für Bioprozess- und Analysenmesstechnik, Biowerkstoffe, Heilbad Heiligenstadt; [2]Technische Universität Dresden, Fakultät für Biologie, Dresden; [3]Universitätsmedizin Rostock, FORBIOMIT, Rostock; [4]Freudenberg Medical Hemoteq GmbH, Würselen; [5]Mathys Orthopaedie GmbH (Enovis), Moersdorf; [6]Friedrich-Schiller-Universität Jena, Institut für Organische Chemie und Makromolekulare Chemie, Jena, Germany

Introduction

Millions of people worldwide suffer from arthritis, an incurable disease that results in the gradual degeneration of articular cartilage. The final treatment option after cartilage loss is joint replacement. Orthopedic implants need to be especially durable over long-time. Potentially resulting debris is one of the main reasons for implant failure owing to aseptic inflammation of the surrounding tissue.

Our aim was to reduce the friction and potential debris formation in large joint prostheses by applying a biomimetic coating. Thereby, we focused on the principle of ‘hydration lubrication’, that can be found in the natural joint cartilage. Water molecules bind to the surfaces in the friction area, resulting in the two surfaces sliding on a thin film of water rather than on each other.

Materials and Methods

The coatings were based on polyelectrolyte multilayers (PEMs), which are both versatile and simple to manufacture. To ensure a stable connection to the alumina-toughened zirconia (ATZ) ceramics, we used a silane-based linker system that covalently bound amine groups to form a cationic layer on the surface. The PEMs were assembled via a dipping process, and the success of the coating was measured using water contact angle and zeta potential measurements. By advanced polarization-modulated infrared reflection absorption spectroscopy (PM-IRRAS), the ability of the coatings to bind water and form stable PEMs was tested. The friction and stability of the PEMs were analyzed by conducting tribological analysis and white-light interferometry.

Results

At first, a linker system for ATZ ceramics was evaluated, to overcome a chloroform-based approach and transfer it to a water-ethanol-based one. This makes the process more straightforward and environmentally friendly. PM-IRRAS measurements verified that the polyelectrolytes chosen for the top layer of the PEMs exhibited high water affinity. The coatings significantly decreased the friction coefficient to $\mu<0.05$, while the stability of the PEMs was crucially dependent on the stable linker-system.

Conclusion

We successfully developed a stable coating system for ceramics that significantly reduces friction and debris production. This biomimetic approach improves the functionality of joint endoprostheses and benefits the long-term treatment of patients with arthritis.

Acknowledgements

The results are part of the project “Self-X for Implants” (13XP5209C) funded by the BMFTR.

D1 – P077

Multiscale characterisation of SLM-printed Co–Cr–Mo porous lattice structures for bone tissue engineering in total knee arthroplasty implants

Paik S.[1,3], Basu B.[2], Withers P.J.[3]
[1]Laboratory for Biomaterials Science and Translational Research, Materials Research Centre, IISc Bangalore, Bangalore, India; [2]CSIR-CGCRI, Kolkata, India; [3]Dept. of Materials, University of Manchester, Manchester, UK

Introduction

Porous lattice architectures fabricated using additive manufacturing have emerged as promising solutions for improving osseointegration and long-term stability of total knee arthroplasty (TKA) implants. By mimicking the porous structure of trabecular bone, these architectures facilitate bone ingrowth, enhance implant fixation, and reduce stress shielding. In this study, selective laser melting (SLM) was used to fabricate porous lattice structures with a novel unit cell geometry from Co–Cr–Mo alloy, a clinically established material widely used in orthopaedic implants.

Aim

This work aimed to investigate the relationship between manufacturing accuracy, surface properties, mechanical performance, and biological response of porous lattice structures intended for bone tissue engineering applications in TKA implants.

Materials and Methods

High-resolution micro-computed tomography (micro-CT) was employed to quantify deviations between the designed and as-printed lattice geometries. Surface deviation mapping derived from micro-CT data provided a quantitative comparison between the CAD design and fabricated structures. Additionally, pore network modelling was conducted to evaluate pore size distribution and interconnectivity.
Surface morphology and microstructural characteristics were analysed using scanning electron microscopy (SEM) and energy-dispersive X-ray spectroscopy (EDS). Mechanical performance was evaluated through both ex-situ and in-situ compression testing using DEBEN load frames integrated with laboratory micro-CT systems to observe deformation mechanisms.




Fig 1: (a) Scanning Electron Microscopy Image, (b) Pore Network Model (PNM) of As-designed Model, (c) Pore Network Model of As-printed Model (from Micro-CT results)

Results

The integrated structural, mechanical, and biological analysis provides critical insights into the influence of manufacturing defects, surface properties, and lattice architecture on the performance of porous orthopaedic implants.

Conclusion

These findings contribute to the development of mechanically robust and biologically favourable lattice-structured TKA implants designed to promote bone tissue integration and improve long-term implant stability.

References

[1]Maurya A. K., Sivakumar G., Amirthalingam M., & Kamaraj M. Surface topography control in CoCrMo alloy additive manufacturing through laser powder bed fusion process. *Journal of Manufacturing Processes* 2026; 161, 14–33.
[2]Wanniarachchi C. T., Arjunan A., Baroutaji A., Singh M. Mechanical performance of additively manufactured cobalt-chromium-molybdenum auxetic meta-biomaterial bone scaffolds. *Journal of the Mechanical Behavior of Biomedical* 2022.
[3]Murr L. E., Amato K. N., Li S. J., Tian Y. X., Cheng X. Y., Gaytan S. M., Martinez E., Shindo P. W., Medina F., Wicker R. B. Microstructure and mechanical properties of open-cellular biomaterials prototypes for total knee replacement implants fabricated by electron beam melting. *Journal of the Mechanical Behavior of Biomedical Materials* 2011; 4(7); 1396–1411.
[4]Payungpisit K., Wongwitthayakoon P., Thongrod Y., Huadheng W., Jarungvittayakon C., Laoruengthana A., Uthaisangsuk V. Two-layered lattice structures of CoCr28Mo6 alloy for femoral component in total knee replacement. *Mechanics of Advanced Materials and Structures* 2026; *33*(1).

D1 – P078

Biological and microbiological properties of low-modulus Ti-35Nb-4Ag alloy fabricated by powder metallurgy for dental implants.

Roquette M.[1], Gil J.[1], Aparicio C.[1,2], Padrós N.[3], Muñoz M.[3], Nart J.[3], Vicente A.[4], Amigó V.[4]
Oral Biomaterials and Interfaces, Dept. of Science and Materials Engineering, EEBE, Universitat Politècnica de Catalunya, Barcelona; [2]ICREA-Catalan Institution for Research and Advanced Studies, Barcelona; [3]Dept. of Periodontology, Universitat International de Catalunya, Barcelona; [4]Instituto Universitario de Tecnología de Materiales, Universitat Politècnica de València, Valencia, Spain

Introduction

Metals as hard tissue substitutes is limited by the mismatch in elastic modulus with bone, leading to stress shielding, loss of implant integration. In addition, implant-associated infections caused by biofilm formation remain a major clinical challenge due to their resistance to antibiotics. To address mechanical incompatibility, low-modulus β-titanium alloys have been developed, offering favorable mechanical properties. Surface modification strategies and the incorporation of silver nanoparticles have shown antimicrobial potential, but concerns regarding stability, toxicity, and regulatory approval. The incorporation of silver directly into the titanium matrix via powder metallurgy provides a controlled antibacterial effect. However, controlling composition is essential to avoid the formation of detrimental intermetallic phases. In this work, low elastic modulus Ti-Nb alloys with 4 wt.% Ag were developed to evaluate their biological and bactericidal capacity.

Materials and Methods

Ti 35Nb4Ag samples were obtained by pressureless sintering using a cold compaction pressure of 800 MPa on a mixture of elemental powders. Sintering was carried out in a high-vacuum furnace. Surface roughness, wettability, and surface free energy, including its dispersive and polar components, were evaluated. Cytocompatibility was assessed in accordance with ISO 10993-5, using commercially pure grade 4 titanium as a control material. Cell adhesion and proliferation were investigated using human fibroblast cells (hFFs) and osteoblasts SaOS-2 at 2, 4, 7, and 14 days. Antibacterial activity was evaluated against three bacterial strains: *Streptococcus gordonii* (Gram-positive), *Staphylococcus aureus* (Gram-positive), and *Enterococcus faecalis* (Gram-positive). Colony-forming units (CFU) and metabolic activity were quantified

Results

With the new alloy, the elastic modulus decreased from 110 GPa to less than 70 GPa, and the porosity was less than 3%. The results showed that there were no statistically significant differences in roughness between the alloys tested. However, the Ti-35Nb-4Ag alloy had a lower contact angle (46°) than titanium (62°), and the surface free energy was higher (58 mJ/m^2)58 than for titanium (41mJ/m^2). Notably, this difference was mainly attributed to a higher polar component of the alloy (29 mJ/m2) compared to the one for pure titanium (16 mJ/m2) . Fibroblasts and osteoblasts adhesion as well as proliferation was higher for the low-modulus alloy (Figure 1). The new alloy also had better cytocompatibility. The results of microbiological studies proved the bactericidal potency of the alloy containing silver, both in terms of colony counts and bacterial metabolic activity, compared to titanium (Figure 2).

Conclusion

A cytocompatible, antimicrobial low elastic modulus alloy (69.8 ± 8.5 GPa) has been developed using powder metallurgy. The Ti-35Nb-4Ag alloy has greater hydrophilicity and total surface free energy, especially for the polar component, than the gold standard for dental implants, commercially pure grade 4 titanium. This resulted in a higher cellular activity of human fibroblasts and osteoblasts than that on commercially pure titanium. The presence of silver in the alloy imparted bactericidal effect to the alloy with reduced bacterial activity and viability compare to commercially pure titanium. Taking together, these results support Ti-35Nb-4Ag alloy as a candidate for future applications in hard tissue replacement where reducing the incidence of peri-implant infection is paramount.




Figure 1. Fibroblasts (hFFs) and osteoblast (SaOS-2) adhesion and proliferation on Ti-35Nb-4Ag and cp-Ti grade 4.




Figure 2. CFU count and Resazurin reduction of different bacteria strains grown on Ti-35Nb-4Ag and cp-Ti grade 4.

Acknowledgements
This work was funded by MCIN/AEI/10.13039/ 501100011033 and FSE+ under award PREVENTITIS-PID2022-137496OB-I00. The authors gratefully acknowledge to Klockner Medical Group for providing machined commercially pure titanium samples.

D1 – P079

Single-step femtosecond laser-induced hierarchical structuring of Ti6Al4V with LIPSS for enhanced osseointegration and reduced bacterial adhesion

Chettri S.[1], Seetharaman D.[1], Shetty P.[2], Krishnan S.[2]
[1]Dept. of Physics, Sri Sathya Sai Institute of Higher Learning, Andhra Pradesh; [2]Dept. of Physics, IIT Madras, Tamil Nadu, India

Introduction

Femtosecond micro-machining is an effective surface engineering technique for biomedical implants, capable of creating controlled hierarchical micro-nano structures through ultrafast laser pulses and cold ablation[1]. Such textured surfaces can reduce bacterial adhesion and enhance osseointegration. Titanium and its alloys are widely used for implants due to their excellent strength, corrosion resistance, and biocompatibility. However, peri-implant infections and delayed healing remain a challenge[2].

To address these issues, advanced surface modification strategies are needed to promote osseointegration while limiting bacterial colonisation. However, existing approaches often rely on multi-step fabrication and lack systematic control and repeatability, while the mechanical stability of laser-induced micro-nano structures under implant loading and their antibacterial performance remain insufficiently explored[3].

Therefore, this study employs an industrial-grade high-speed femtosecond laser to develop a single-step process for fabricating hierarchical surfaces with laser-induced periodic surface structures (LIPSS) and to evaluate their structural stability, osseointegration potential, and bacterial adhesion.

Aim

To develop hierarchical micro-nano structures with LIPSS on Ti6Al4V surfaces using a single-step femtosecond laser process and evaluate their effects on osseointegration, bacterial adhesion and structural stability.

Materials and Methods

Ti6Al4V samples with dimensions of 15mm × 15mm were used. The samples were first cleaned sequentially in acetone, ethanol, and distilled water to remove contaminants. An industrial-grade femtosecond laser operating at a wavelength of 1035 nm with a pulse duration of 275 fs, equipped with a high-speed galvanometric scanner, was used for surface texturing. Laser processing parameters such as repetition rate, scan speed, hatch spacing, and number of passes were systematically optimised to achieve the desired structures.

Results

Optimisation of ultrafast laser parameters resulted in controlled micro and nanoscale surface structures embedded with LIPSS on Ti6Al4V (Figure 1). Surface characterization revealed uniform geometries with periodicities in the order of visible light wavelengths.

Laser micro-machining also induced a significant change in surface wettability. The untreated titanium surface exhibited nearly hydrophobic behaviour, while the laser-textured surfaces showed superhydrophilic characteristics. This transition in wettability is attributed to the combined effect of multiscale surface roughness and laser-induced modifications in surface chemistry.

Conclusion

Femtosecond laser texturing successfully produced hierarchical structures with LIPSS on Ti6Al4V surfaces. The texturing altered wettability and created functional topographies that can potentially enhance osseointegration and reduce bacterial adhesion. The study demonstrates the potential of femtosecond laser surface engineering for improving the performance of biomedical implants and for other multifunctional surface applications.




Figure 1. SEM images of femtosecond laser textured surfaces at fluence: A) 0.05 J/cm^2, B) 0.26 J/cm^2 and C) 0.5 J/cm^2.

Acknowledgements

1. Femtosecond Laser Facility, Department of Physics, IIT Madras
2. Central Research Instrumental Facility (CRIF), SSSIHL, Prasanthi Nilayam, for various characterization facilities.

References

[1]Barylyak A., Wojnarowska-Nowak R., Kus-Liśkiewicz M. et al. Photocatalytic and antibacterial activity properties of Ti surface treated by femtosecond laser–a prospective solution to peri-implant disease. *Sci Rep* 2024;14; 20926.
[2]Seo B.Y., Son K., Son Y.T., Dahal R.H., et al. Influence of Dental Titanium Implants with Different Surface Treatments Using Femtosecond and Nanosecond Lasers on Biofilm Formation. *Journal of functional biomaterials* (2023); *14*(6); 297.
[3]Beltrán A.M., Giner, M., Rodríguez, Á., Trueba, P., et al. Influence of Femtosecond Laser Modification on Biomechanical and Biofunctional Behavior of Porous Titanium Substrates. *Materials (Basel, Switzerland)* 2022; *15*(9); 2969.

D1 – P080

Aqueous chemoselective conjugation of N-terminal L-cysteines to polysaccharides


Bucak Gasser D.[1], Steindorfer T.[1], Neshchadin D.[2], Gescheidt G.[2], Stana Kleinschek K.[1], Kargl R.[1]
[1]Institute of Chemistry and Technology of Biobased Systems, Graz University of Technology, Graz; [2]Institute of Physical and Theoretical Chemistry, Graz University of Technology, Graz, Austria

Introduction

Native chemical ligation (NCL) refers to the well-known formation of an amide bond between a C-terminal thioester and an N-terminal cysteine of peptides or proteins.[1] High chemoselectivity, complete avoidance of protective groups on amino acid residues and compatibility with aqueous, physiological conditions make NCL a biologically benign and effective method for synthesis of polysaccharide-peptide conjugates, which are becoming increasingly pivotal in the development of targeted drug delivery systems, vaccines and tissue engineering scaffolds.[2,3]

Aim

Our work introduces in situ, real-time monitoring of a highly robust method for traceless conjugation of N-terminal L-cysteines to polysaccharides (Scheme 1). The resulting covalent linkage incorporates solely stabile amino acid-based amide bonds under aqueous, pH-neutral conditions without any exogenous and potentially problematic linker molecules. Our ultimate aim is to develop this method into a convenient and efficient strategy for peptide-to-polysaccharide conjugation.



Scheme 1: Peptide-to-polysaccharide NCL method.

Materials and Methods

Thioester synthesis: glycine, ethyl-3-mercaptopropionate, carbonyldiimidazole (CDI)
Polysaccharide functionalization: sodium alginate, 4-(4,6-dimethoxy-1,3,5-triazin-2-yl)-4-methyl-morpholinium chloride (DMTMM)
Conjugation (NCL): L-cysteine hydrochloride (L-cys·HCl), L-cysteinylglycine (L-cys-gly), phosphate buffer
Characterization: elemental analysis, mass spectrometry, ATR-IR, $^{1}H/^{13}C$ NMR

Results & Conclusion

An alginate-thioester with a glycine linker bound as uronic acid amide was successfully synthesized and fully characterized by ATR-IR and ^{1}H-NMR spectroscopy. ^{1}H-NMR measurements confirmed its stability for at least 3 hours in an aqueous environment and in presence of L-lysine or glycine (0.1 M PO_4^{3-}, pH 7). Its reactivity against L-cys·HCl and L-cys-gly was monitored in situ using detailed kinetic ^{1}H-NMR measurements, confirming successful NCL reactions and formation of corresponding peptide conjugates.

References

[1]Agouridas V., El Mahdi O., Diemer V., Cargoët M., Monbaliu J.-C.M., Melnyk O. Native Chemical Ligation and Extended Methods: Mechanisms, Catalysis, Scope, and Limitations *Chem. Rev.* 2019; 119; 7328–7443.
[2]Mohan T., Kleinschek K.S., Kargl R. Polysaccharide peptide conjugates: Chemistry, properties and applications. *Carbohydr. Polym* 2022; 280; 118875.
[3]Boere K.W.M., Soliman B.G., Rijkers D.T.S., Hennink W.E., Vermonden T. Thermoresponsive Injectable Hydrogels Cross-Linked by Native Chemical Ligation. *Macromolecules* 2014; 47; 2430–2438.

D1 – P081

Influence of sequence arrangement and processing conditions on the self-assembly of biomineralising silk-elastin-like polypeptides

Shire E., López Barreiro D.
Manufacturing Futures Lab, Dept. of Chemical Engineering, University College London, London, UK

Introduction

Silk-elastin-like polypeptides (SELPs) are a class of recombinant protein biopolymers combining the strength and toughness of silk with the elasticity and thermoresponsiveness of elastin[1]. Minimal consensus repeats are derived from native silkworm silk (GAGAGS blocks) and tropoelastin (IPAVG or VPGXG blocks, with X being any amino acid except proline). Fusing copies of these blocks into a single SELP chain provides a modular assembly strategy for tuning material viscoelastic, structural, and dynamic properties in applications such as soft robotics and biomedicine[2-4]. There is currently a gap in understanding how sequence arrangement and processing conditions (e.g., ionic strength, shear) affect SELP self-assembly, especially when silk- and elastin-like blocks are fused with functional peptides (e.g., biomineralising peptides) that do not tend to self-assemble.

Aim

The aim of this work is to explore the effect of sequence arrangement and processing conditions on the self-assembly of biomineralising silk-elastin-like polypeptides.

Materials and Methods

A library of SELPs with silk-like (GAGAGS) and elastin-like (IPAVG, VPGVG, and VPGIG) building blocks, and statherin-like biomineralising domains (DDDEEKFLRRIGRFG) were designed and synthesised using microbial fermentation. SELPs were purified using an inverse temperature cycling method that leveraged their thermoresponsiveness. SELPs were processed in different environments (e.g., ionic strengths, shear stress), prior to characterisation. Viscoelastic and structural properties of these proteins were characterised across multiple scales (e.g., molecular, condensate and macroscopic level) to understand their self-assembly, using rheology, atomic force microscopy, fluorescence recovery after photobleaching and FTIR spectroscopy.

Results

SELPs show differing viscoelastic behaviour depending on the presence and location of a biomineralising domain. Addition of the domain decreases the storage and loss moduli compared to the structural equivalent when temperature exceeds the LCST. This reduction in viscoelastic properties can be partially overcome by the addition of calcium ions, which also appear to induce more order in SELPs when combined with shear.

Conclusion

The self-assembly and mechanical properties of SELPs are influenced by the sequence arrangement and presence of a functional domain. Our results shed light on the preferred sequence design aspects and processing conditions to self-assemble biomineralising SELPs.

Acknowledgements

The support provided by the Royal Society research grant RG/R2/232238 is acknowledged.

References

[1]Lopez Barreiro D. et al. Sequence Control of the Self-Assembly of Elastin-Like Polypeptides into Hydrogels with Bespoke Viscoelastic and Structural Properties. *Biomacromolecules* 2022; 24; 489-501.
[2]Narayan O. P. et al., Dynamically tunable light responsive silk-elastin-like proteins. *Acta Biomaterialia* 2021; 121; 214-223.
[3]Noh Y. et al., Exploring stimuli-responsive elastin-like polypeptide for biomedicine and beyond: potential application as programmable soft actuators. *Frontiers in Bioengineering and Biotechnology* 203; 11.
[4]Wang Y. S. *et al.*, Stimuli-responsive composite biopolymer actuators with selective spatial deformation behavior. *P Natl Acad Sci USA* 2020; 117; 14602–14608.

D1 – P082

Green solvent- based chitosan and PCL electrospun scaffolds for bone tissue engineering

Imhof I. C.[1,2,3], Krattiger L. A[1,3], Hoffmann C.[1,3], Nash M. A.[2,4], Guex A. G.[1,3]
[1]Dept. Research, University Center for Dental Medicine Basel UZB, University of Basel; [2]Dept. of Chemistry, Institute of Physical Chemistry, University of Basel; [3]Dept. of Biomedicine, University of Basel, Basel, Switzerland; [4]Dept. of Biosystems Science and Engineering, ETH Zurich, Basel, Switzerland

Introduction

The extracellular matrix (ECM) provides structural support and biochemical signals to the cells, which makes ECM-inspired scaffolds promising for tissue engineering. Electrospinning is a versatile technique to mimic this nanofibrous ECM environment. Often, the production is not sustainable due to toxic solvents or non-circular materials. Here, we electrospun nanofibrous scaffolds from chitosan and poly(ε-caprolactone) (PCL), using only benign solvents. Chitosan is a naturally-derived polymer with hydrophilic properties and free amino groups which can be used for functionalization. PCL is biodegradable and used for structural support. We then cultured human dental pulp stem cells (hDPSC) on these scaffolds under osteogenic conditions, to assess the scaffolds' osteoconductive potential.

Materials and Methods

We fabricated scaffolds from a blend of 10% w/v PCL and 1.5% w/v chitosan in 90% acetic acid, with pure PCL (10% w/v) as a control. Scaffold architecture was analyzed with SEM and wettability was determined via drop shape analysis. hDPSC were isolated from teeth extracted from patients based on clinical indication (e.g. wisdom teeth removal) and seeded onto the scaffolds. After osteogenic culture for 21 days, mineralization was assessed via Alizarin Red S staining and a Ca^{2+} quantification assay.

Results & Discussion

The incorporation of chitosan increased fiber diameters (0.277 ± 0.183 µm) compared to pure PCL (0.125 ± 0.06 µm), attributable to the blend's higher total polymer concentration (Fig. 1 A). Moreover, blended scaffolds resulted in significantly reduced contact angles (51 ± 0.14°) compared to PCL only (128.05 ± 0.07°), indicating successful surface enrichment with hydrophilic -NH_2 and -OH groups (Fig. 1 B). hDPSC attached to the scaffolds, and mineralization was observed in groups cultured under osteogenic medium conditions.

Conclusion

We developed a sustainable ECM-inspired scaffold model with a hydrophilic, cell-supportive interface and were able to induce hDPSC osteogenesis on both scaffold types. Moving forward, we will exploit chitosan's free amino groups to covalently link specific integrin-binding peptides with NHS/Maleimide chemistry to the scaffolds. Thereby, a targeted control of integrin-mediated molecular pathways for hDPSC differentiation will be enabled. This approach provides the foundation to develop bioactive scaffolds with osteoinductive potential through cell-scaffold interactions.

Acknowledgements

The Oral Implantology Lab is funded by Dr h.c. T. Straumann. This project received funding from the Swiss Nanoscience Institute (SNI). The SEM Images were acquired at the Nano Imaging Lab (SNI).




Figure 1 A) Fiber diameter was determined by SEM from three scaffold regions with 50 fiber measurements per region; data are shown as scaffold means, B) The contact angle of a water droplet on PCL is higher compared to PCL / CS.

D1 – P083

Chain-selective presentation of RGD in static and dynamic double-network hydrogels modulates hMSC mechanotransduction and secretome

Morgan F.L.C.[1,2], Joris V.[3], Aldana A.A.[2], van Griensven M.[3], Moroni L.[2], Baker M.B.[1,2]
[1]Dept. of Instructive Biomaterials Engineering, MERLN Institute, Maastricht University, Maastricht; [2]Dept. of Complex Tissue Regeneration, MERLN Institute, Maastricht University, Maastricht; [3]Dept. of Cell Biology-Inspired Tissue Engineering, MERLN Institute, Maastricht University, Maastricht, The Netherlands

Introduction

Cells respond to matrix mechanics at the scale of their adhesion sites, yet biomaterials are usually characterized only by bulk properties. We developed a double-network alginate hydrogel platform to decouple bulk mechanics from the molecular-scale mechanical environment presented to cells.

Aim

By selectively presenting RGD on either a static or dynamic network, we investigated how local chain-level mechanics regulate human mesenchymal stem cell (hMSC) morphology, mechanotransduction, and paracrine function.

Materials and Methods

Double-network hydrogels were formed from a dynamic oxidized alginate network crosslinked through hydrazone bonds and a static norbornene-alginate network crosslinked by thiol-ene chemistry. RGD was selectively conjugated to the dynamic network (Ox-RGD), static network (Cys-RGD), or both, while maintaining constant bulk composition, stiffness regime, and ligand concentration. Rheology was used to assess gelation, stiffness, and flow behavior. hMSCs were cultured on the hydrogels and analyzed by fluorescence imaging, qPCR, and microRNA profiling. Conditioned media from each condition were then applied to a separate hMSC culture to evaluate mineralization.

Results

The hydrogels were injectable before secondary crosslinking and formed stable double networks with comparable bulk mechanics. Despite this, chain-selective RGD presentation strongly altered hMSC behavior. Ox-RGD hydrogels promoted a spread morphology, whereas Cys-RGD hydrogels induced small cell aggregates. Static-network presentation also downregulated YAP1 and TWIST1, together with miR-125b-5p, miR-199a-5p, and miR-214-3p, while increasing Cx43 expression. Conditioned media from hMSCs cultured on Cys-RGD hydrogels enhanced mineralization in a separate hMSC population more strongly than media from dynamic-network or tissue-culture-plastic controls.

Conclusion

Molecular-scale presentation of adhesion ligands regulates hMSC morphology, gene expression, and secretome independently of bulk hydrogel mechanics. This platform highlights the importance of local mechanical cues in biomaterial design and provides a route to engineer metabiomaterials that direct both direct cell response and secondary paracrine effects for regenerative applications.

Acknowledgements

This work was supported by NWO through the DynAM project (731.016.202), the Marie Skłodowska-Curie Individual Fellowships (101028471), and the European Research Council Consolidator Grant SupraValent (101088285). M.v.G. and V.J. also acknowledge support from the Province of Limburg's Limburg Invests in its Knowledge Economy (LINK) program. The authors thank Timo Rademakers for assistance with the FRAP experiments.

D1 – P084

Engineering osteosarcoma In Vitro using 3D bioprinted tumor spheroids and cell-derived dECM-based bioinks for improved therapeutic discovery and drug screening

Domingues M.[1,2], Sanjuan-Alberte P.[1,2], Silva J.[1,2]
[1]Dept. of Bioengineering and iBB - Institute for Bioengineering and Biosciences, Instituto Superior Técnico; [2]Associate Laboratory i4HB – Institute for Health and Bioeconomy, Lisboa, Portugal

Introduction

Osteosarcoma (OS) is the most prevalent primary malignant bone tumor, primarily affecting children and adolescents. It is associated with high mortality rates due to its complex tumor composition, intrinsic heterogeneity, chemoresistance, and strong metastatic potential. Although chemotherapy combined with surgical resection has been the standard treatment for OS for decades, these approaches have undergone limited progress since the 1970s and remain largely insufficient. This underscores the urgent need for more effective therapeutic strategies, as well as advanced preclinical biomimetic 3D models that can accurately replicate OS pathophysiology. Compared to conventional two-dimensional (2D) cultures and animal models, 3D in vitro scaffold-based systems offer a more physiologically relevant platform by reproducing more closely the tumor's 3D architecture and cell–extracellular matrix (ECM) interactions, which are critical determinants of drug response. Thus, in this work, we present a novel 3D bioprinted osteosarcoma model based on MG-63 osteoblast-derived spheroids embedded within a specialized cell derived decellularized extracellular matrix (dECM)-based bioink engineered to mimic the native OS microenvironment. This represents the first study to successfully combine OS cell-derived dECM, preformed OS spheroids and 3D bioprinting into a single in vitro platform.

Materials and Methods

The bioink, composed of MG-63-derived dECM, alginate (ALG), methylcellulose (MC), and gelatin methacrylate (GelMA), was thoroughly characterized in terms of water content, rheological and mechanical properties, printability, and biocompatibility. In addition, an optimal spheroid pre-culture period was established to obtain spheroids with sizes suitable for the bioprinting process. The clinical relevance of the bioprinted model was further validated by evaluating its response to doxorubicin, a standard chemotherapeutic agent for osteosarcoma. This assessment included analysis of spheroid area, cell viability, and gene and protein expression using RT-qPCR and immunofluorescence staining analyses, respectively.

Results

The developed bioink proved suitable for extrusion-based 3D bioprinting, exhibiting excellent printability and supporting MG-63 cell culture while maintaining high cell viability (~90%) after 7 days. It also displayed high water content, minimal swelling and mass loss, rapid UV-induced gelation, and a compressive modulus of 7 kPa, within the stiffness range reported for OS tissue. The resulting bioprinted spheroid-based model preserved MG-63 spheroid morphology and viability, exhibited increased expression of OS prognostic gene markers (*MMP9*, *VEGF*, *RUNX2*), and demonstrated reduced sensitivity to doxorubicin, in comparison to both 2D cultures and scaffold-free 3D spheroids. This enhanced chemoresistance is likely due to the scaffold's ability to more accurately replicate the 3D architecture and biochemical composition of the OS ECM, partly attributed to the incorporation of OS-mimetic dECM.

Conclusion

Overall, our findings support that by recapitulating the 3D macroarchitecture of tumors and enabling native-like cell–cell and cell–ECM interactions, the developed 3D bioprinted model offers a more physiologically-relevant platform for drug screening towards the development of personalized OS therapies.

Acknowledgements

The authors acknowledge dedicated funding from FCT through the projects BIOMIMIC-CRC (2023.13896.PEX), iBB (UID/04565/2025), I4HB (LA/P/0140/2020), and Assistant Researcher FCT Tenure contract (iBB_U5_SCERG_FCT TENURE (121) iBB) awarded to JS.

D1 – P085

High-Z/Catalytic function-coupled all-in-one platform for enhanced tumor therapy

Chun-Yu H.[1,2], Qiao-Rong Z.[1], San-Yuan C.[1]
[1]Dept. of Materials Science and Engineering, National Yang Ming Chiao Tung University, Hsinchu; [2]Dept. of Orthopedic Surgery, Jen-Ai Hospital, Taichung, Taiwan

Introduction

A major challenge in cancer therapy is achieving tumor-specific cytotoxicity while avoiding systemic toxicity. The excessive accumulation of hydrogen peroxide (H_2O_2) in the tumor microenvironment (TME) provides an ideal target for selective therapy. Chemodynamic therapy (CDT) specifically converts H_2O_2 into highly toxic hydroxyl radicals (·OH) through Fenton/Fenton-like reactions, enabling precise tumor targeting without being limited by hypoxia, which represents its unique advantage over conventional cancer treatments. However, standalone CDT suffers from insufficient catalytic efficiency and poor reaction stability. To break through these limitations, this study successfully constructed a multifunctional nanozyme Hf-Fe@CeO_2@MSNs.

Aim

A mesoporous silica nanoparticle (MSN) framework ensures highly dispersed active sites, while Hf/Fe co-doping precisely regulates the Ce^{3+}/Ce^{4+} ratio and oxygen vacancy concentration in the CeO_2 lattice, significantly enhancing catalytic efficiency.

Materials and Methods

Mesoporous silica nanoparticles (MSNs) were synthesized via a template method. Then, 80 mg of MSNs were ultrasonically dispersed in 30 mL of ethylene glycol to ensure homogeneous dispersion and prevent particle agglomeration, which facilitates uniform crystallization. To coat Hf and Fe doped CeO_2 on the MSNs, the hydrothermal method was employed. Hafnium (IV) chloride ($HfCl_4$), ammonium iron (II) sulfate hexahydrate ($(NH_4)_2Fe(SO_4)_2·6H_2O$), and cerium(III) nitrate hexahydrate ($Ce(NO_3)_3·6H_2O$) were each dissolved in a small amount of double-distilled water. The total molar amount of cerium, iron, hafnium (Ce+Fe+Hf) was fixed at 1.88 mmol. For a fixed total metal amount, the molar percentages of Fe and Hf were designed as follows Fe/Hf molar ratio: 0.1/0.4, 0.4/0.1, and 0/0.5. The three solutions were added to the ethylene glycol containing the dispersed MSNs, followed by magnetic stirring and resting for 30 min. The mixture was transferred to a sealed Teflon-lined stainless steel autoclave, and heated at 180 °C for 14 h. The resulting precipitate was collected by centrifugation (10,000 rpm, 10 min) and washed several times with 50 % ethanol. The product was dried under vacuum at 80 °C for 16 h and calcined at 650 °C for 6 h under a nitrogen atmosphere (heating rate: 5 °C/min).The resulting Hf and Fe doped CeO_2-coated MSNs were labeled as HfxFey@Ce(1-x-y)O_2@MSNs, where x represents the mole fraction of Hf added, y represents the mole fraction of Fe added, and (1-x-y) indicates the mole fraction of Ce added.

Results

Based on meticulous material structural and catalytic activity analysis, we identified an optimal metal doping molar ratio of 0.5 %, which significantly enhances catalytic efficiency. Under acidic TME conditions, the nanozyme efficiently converts H_2O_2 into ·OH while simultaneously alleviating tumor hypoxia through oxygen generation. Furthermore, this study innovatively introduced the high-atomic-number element Hf, whose radiosensitizing effect not only enhances X-ray energy deposition efficiency but also promotes CDT(**Fig1,Fig2**). In vitro cytotoxicity tests confirmed the excellent tumor-killing efficacy of the designed nanocatalyst. This study presents a nano-catalytic biomedicine platform, offering a promising precision strategy for clinical translation.

Conclusion

This study successfully developed a novel multifunctional nanocatalyst, Hf-Fe@CeO_2@MSNs, whose unique structural design enables simultaneous excellent radiosensitization characteristics and high catalytic activity, pioneering a new paradigm for synergistic cancer therapy. At the material design level, mesoporous silica nanoparticles (MSNs) were employed as the carrier framework, which not only effectively addressed the technical challenge of CeO_2 nanoparticle aggregation but also significantly increased the number of exposed active sites through their high specific surface area, markedly enhancing the catalytic efficiency of CeO_2. In terms of catalytic activity regulation, systematic optimization of the calcination environment and precise control of iron doping levels

successfully achieved synergistic enhancement of the Ce^{3+}/Ce^{4+} ratio and oxygen vacancy concentration within the CeO_2 lattice. This key breakthrough enables the material to fully exert a dual catalytic mechanism. Regarding

radiosensitization, the successful incorporation of Hf significantly enhanced the X-ray energy absorption efficiency of material, demonstrating outstanding radiosensitization performance. When combined with radiotherapy, the material generates abundant secondary electrons under low-dose irradiation, substantially increasing local energy deposition and thereby enhancing radiotherapy effectiveness. The most significant innovation of this study lies in the successful construction of a synergistic platform integrating CDT and radiosensitization. This unique synergistic mechanism effectively overcomes the therapeutic limitations of conventional radiotherapy in hypoxic TME, achieving synergistic therapeutic effects through dual pathways of radiation-induced apoptosis and chemodynamically-driven apoptosis. This research not only provides an innovative solution for overcoming tumor hypoxia-related treatment resistance but also opens new avenues for low-dose, high-efficacy precision cancer treatment. It demonstrates excellent clinical translation prospects and establishes a solid foundation for the design and development of next-generation cancer nanomedicine platforms.




Fig1. FE-TEM images of (a,b) CeO_2@MSNs, (d,e) $Hf_{0.001}Fe_{0.004}$@$Ce_{0.995}O_2$@MSNs, and (g,h) $Hf_{0.004}Fe_{0.001}$@$Ce_{0.995}O_2$@MSNs. The high-resolution FE-TEM images (c, f, i) reveal clear lattice fringes




Fig2. Elemental mapping images of (a) CeO_2@MSNs, (b) $Hf_{0.001}Fe_{0.004}$@$Ce_{0.995}O_2$@MSNs, and (c) $Hf_{0.004}Fe_{0.001}$@$Ce_{0.995}O_2$@MSNs.

Acknowledgements
The authors acknowledge the National Synchrotron Radiation Research Center for assistance with the analysis of nanomaterial samples.

D1 – P086
BiFC reporter-based detection of influenza a virus

Moonil Kim*
Critical Diseases Diagnostics Convergence Research Center, Korea Research Institute of Bioscience and Biotechnology (KRIBB), Daejeon, South Korea

Influenza A virus (IAV) remains a major global health concern, necessitating rapid and accurate diagnostic methods. In this presentation, a highly sensitive and specific bimolecular fluorescence complementation (BiFC)-based sensing platform for IAV detection by combining a galactose/glucose-binding protein (GGBP) with split enhanced yellow fluorescent protein (eYFP) fragments is described. The assay exploits neuraminidase (NA)-mediated cleavage of 6′-sialyllactose to generate lactose, which induces conformational changes in GGBP and subsequently triggers fluorescence reconstitution of the split eYFP domains. The resulting fluorescence signal enables quantitative detection of IAV without the need for virus culture or RNA extraction. The BiFC sensor demonstrated a broad linear detection range from 1 × 10^0 to 1 × 10^7 TCID50/mL and achieved a limit of detection of 1.1 × 10^0 TCID50/mL for IAV (H1N1), indicating ultra-high sensitivity. Furthermore, the system exhibited strong fluorescence responses to IAV, whereas neuraminidase-deficient respiratory viruses, including respiratory syncytial virus A (RSV A), respiratory syncytial virus B (RSV B), adenovirus, and rhinovirus, produced negligible signals, confirming excellent specificity. These results demonstrate that the proposed BiFC-based platform provides a simple, rapid, highly sensitive, and selective strategy for influenza A virus detection and represents a promising diagnostic tool for influenza surveillance and point-of-care applications.




Figure. Schematic illustration of IAV detection using the GGBP-based BiFC reporter system. Neuraminidase-mediated cleavage of 6′-sialyllactose releases lactose, inducing GGBP conformational changes and eYFP fluorescence reconstitution. Red circle: neuraminidase (NA).

References

[1]Javanian M., Barary M., Ghebrehewet S., Koppolu V., Vasigala V., Ebrahimpour, S. A brief review of influenza virus infection. *J. Med. Virol* 2021; 93; 4638–4646.
[2]Lin X., Liu X.-Y., Zhang B., Qin A.-Q., Hui K.-M., Shi K., Liu Y., Gabriel D., Li X.J. A rapid influenza diagnostic test based on detection of viral neuraminidase activity. *Sci. Rep*. 2022; 12; 505.
[3]Kerppola T.K. Visualization of molecular interactions using bimolecular fluorescence complementation analysis: Characteristics of protein fragment complementation. *Chem. Soc. Rev.* 2009; 38; 2876–2886.
[4]Lee, U.J.; Oh, Y.; Kwon, O.S.; Shin, Y.-B.; Kim, M. Highly Sensitive and Specific Detection of Influenza A Viruses Using Bimolecular Fluorescence Complementation (BiFC) Reporter System. Biosensors 2023, 13, 782.

D1 – P088

Hierarchical supramolecular nanoneedles loaded with bio-ionic hydrogel mediated dense biofilm eradication in the deep tissue

Ghosh S.[1], Eriksson C.[1], Ren Q.[1]
[1]Laboratory for Biointerfaces, Empa, Swiss Federal Laboratories of Materials Science and Technology, St. Gallen, Switzerland

Introduction

In chronic or untreated conditions, skin and soft tissue infection can breach dermal barriers and form deep tissue abscesses, which can lead to devastating systemic infections with high morbidity. These deep biofilm abscesses can act as a reservoir that protects the persistent pathogens from external antimicrobial agents and can cause infection in distant sites, affecting nearly any internal organ (Figure 1). Managing these deep infections is challenging and often overlooked by traditional treatments, such as antimicrobial creams, lotions, or ointments, which provide limited drug penetration into deep tissues and thereby result in incomplete biofilm elimination. Therefore, there is an unmet clinical need to develop potent antimicrobial therapeutics with high tissue penetration and biofilm eradication ability.

Aim

The current study aims to develop adhesive hydrogels that can readily penetrate the superficial epidermal layers and eliminate dense biofilm abscesses in deep tissue niches by degrading their complex biofilm matrices.

Materials and Methods

We have fabricated a hierarchical nanoneedle framework using natural plant-derived polyphenols and enzymes that degrade the extracellular matrix. The fabricated supramolecular nanoneedles were characterized with FTIR, UV-Visible spectroscopy, SEM, HR-TEM, PXRD, and SAXS. Additionally, the nanoneedles encapsulated bio-ionic hydrogel (Figure 1) was developed by combining cationic choline-based ionic liquids with *Bombyx mori*-derived silk fibroin and characterized by NMR, FTIR, and rheology measurements. Next, we examined the antimicrobial activity, ROS scavenging, DNase-mimicking activity, and biofilm destruction using CFU counting, UV spectroscopy, CV assay, SEM, and CLSM imaging. Furthermore, the ability of the hydrogels to penetrate deep tissue and eliminate dense biofilms was evaluated in an ex vivo porcine skin model. Additionally, we assessed the hemocompatibility, cytocompatibility, and immunomodulatory effects of the bio-ionic hydrogel via RBC lysis, CCK-8 assay, and RT-qPCR, respectively.

Results

We synthesized a porous supramolecular nanoneedle by self-assembly of plant-derived polyphenols with natural enzymes, mediated by noncovalent interactions. The nanoneedles-loaded bio-ionic hydrogels demonstrated high stability and enhanced deep tissue permeation. Further, it exhibited excellent antioxidant and antimicrobial properties. The in vitro and ex vivo examinations revealed the potent antibiofilm efficacy of the hydrogels through the disruption of dense biofilm matrices by degrading eDNA and destroying bacterial membranes.

Conclusion

The novel nanoneedles embedded in bio-ionic hydrogels effectively penetrated deep tissues and dismantled pathogenic biofilms. After clearing the biofilm, these hydrogels promoted healing by providing antioxidant effects, reducing inflammation, and supporting tissue repair.




Figure 1. Schematic illustration of deep tissue abscess formation and working mechanism of Nanoneedles@SF-ILs Bioionic hydrogel.

D1 – P089

Electrospun probiotic fibers as a novel biomaterial strategy for managing chronic otitis media

Zergat S[1,2,3], Rovelli R[4], Amato B[1], Esin S[1], Batoni G[1], and Danti S[2,3]
[1]Dept. of Translational Research and New Technologies in Medicine and Surgery, University of Pisa, Pisa, Italy; [2]Dept. of Civil and Industrial Engineering, University of Pisa, Pisa, Italy; [3]National Interuniversity Consortium of Materials Science and Technology (INSTM), Florence, Italy; [4]PEGASO Doctoral School in Life Sciences, University of Siena, Siena, Italy

Introduction

Chronic Otitis Media (COM) is a leading cause of hearing loss, often driven by persistent bacterial infections and biofilm formation that reduce the effectiveness of antibiotics, particularly against multidrug-resistant pathogens such as *Streptococcus pneumoniae, Haemophilus influenzae, and Moraxella catarrhalis*. Conventional therapies are limited in their ability to eradicate these resilient infections, highlighting the need for innovative strategies. Electrospun probiotic fibers designed to host beneficial microbes represent a promising approach for modulating the middle ear microbiome and counteracting pathogenic biofilms.

Aim

This study focused on the development and optimization of an electrospun probiotic formulation as a potential therapy for managing COM.

Materials and Methods

Sodium alginate (low viscosity), polyethylene oxide (PEO, M_w 1000 kDa), Triton X-100 (1%), calcium chloride (2%), absolute ethanol, DAPI, resazurin, a commercial probiotic preparation (10^9 CFU/mL), alpha-lactalbumin (LALBA, 1–3%), D(+) Glucose, and deionized water were used. A 70/30 v/v sodium alginate/PEO solution was prepared, containing 1% Triton X-100 as a surfactant,1–3% LALBA and D (+) Glucose (2%) as a prebiotic. Probiotics were incorporated at 10^9 CFU/mL. The solution was electrospun under optimized conditions, and the resulting fibers were crosslinked in 2% $CaCl_2$ (ethanol/water 30/70 v/v). Fiber morphology was analyzed using scanning electron microscopy (SEM), probiotic encapsulation was visualized using DAPI staining, and post-encapsulation viability was assessed using a resazurin reduction assay.

Results

SEM analysis (Fig. 1a) revealed uniform, bead-free fibers with a mean diameter of 388.1 ± 85.3 nm, containing homogeneously distributed probiotics. DAPI staining (Fig. 1c) confirmed the encapsulation of probiotic cells within the polymer matrix. The Alamar Blue assay (Fig. 2) revealed that 87% of the probiotics maintained metabolic activity following electrospinning, suggesting that most cells remained metabolically active, although additional assays would be needed to confirm full viability and functional integrity.

Conclusion

The study developed electrospun alginate/PEO nanofibers containing probiotics and the prebiotic alpha-lactalbumin and glucose as a potential treatment platform for chronic otitis media. The fibers were uniform and successfully encapsulated probiotics with about 87% viability after fabrication, suggesting they could protect beneficial microbes and serve as a local delivery system to modulate the middle ear microbiome, though further studies on release behavior, microbial interactions, and safety are needed before clinical application.




Figure 1:(a) SEM micrograph of electrospun probiotic loaded fibers, (b): histogram showing the distribution of fiber diameters, (c): DAPI staining results obtained by fluorescent microscope.




Figure 2: Alamar blue test results.

Acknowledgements

This work was supported by PRIN 2022: Site-directed bacteriotherapy to prevent or treat infections in the era of multidrug-resistance (BENEFIT) Prot. 2022M7PFZS; CUP I53C24002820006.

D1 – P090
3D printing of responsive biomaterials for bacteria sensing

Mateo A.M.M.[1], Francesca Perin F.[1], Clara García-Astrain C.[1,2]
[1]POLYMAT and Dept. of Applied Chemistry, Faculty of Chemistry, University of the Basque Country (UPV/EHU), Donostia-San Sebastián; [2]Ikerbasque Basque Foundation for Science, Bilbao, Spain

Introduction
Antimicrobial resistance (AMR) is a major global challenge, underscoring the urgent need for new antimicrobials. Their development relies on accurately replicating in vivo bacterial environments within in vitro experimental models. In this context, (bio)printing has emerged as a promising strategy to recreate physiologically relevant tissue microenvironments, improving the predictive value of preclinical antibiotic screening. Additionally, integrating sensing elements into (bio)inks enables in situ monitoring of bacterial behaviour. Among different sensors, polydiacetylenes (PDAs) stand out due to their unique optoelectronic properties, given their ability to transition from blue, non-fluorescent states to red, fluorescent states in presence of pH variations, temperature changes or bacteria.

Aim
In this study, we aim not only to develop 3D infection models but also to incorporate PDA-based sensors into photo-crosslinkable hydrogel (bio)inks for stereolithography (SLA) printing, enabling real-time monitoring through colorimetric and fluorescent responses to various stimuli (Figure 1).




Figure 9. Schematic illustration of 3D printed hydrogels with incorporated sensors.

Materials and Methods
PDA sensors were synthesized by forming 10,12-pentacosadynoic acid (PCDA) and 1,2-dimyristoyl-sn-glycero-3-phosphocholine (DMPC) hybrid self-assembled liposomes via the solvent injection method. The synthetic phospholipid (DMPC) was added to the diacetylene monomer (PCDA) to enhance liposome stability. The sensors were characterized in terms of size (DLS), shape (TEM), biocompatibility, and colorimetric and fluorescent responses. PCDA/DMPC liposomes were incorporated into gelatin, hyaluronic acid and alginate methacrylated derivatives (GelMA, HAMA and AlgMA, respectively) by dissolving the polymers in the liposome suspension. Hydrogel-based inks and printed materials were characterized with respect to their surface structure (SEM), (photo)rheological properties, printability, biocompatibility, and colorimetric and fluorescent responses.

Results
Preliminary results show that PCDA/DMPC liposomes were successfully incorporated into the different hydrogel formulations whereas GelMA-based formulation provided the best sensing response. This system exhibits a pronounced blue-to-red transition, as well as increased fluorescence intensity, upon exposure to external stimuli. Additionally, the developed ink supports the fabrication of various 3D structures using an SLA printer.

Conclusion
These preliminary findings suggest that incorporating PCDA/DMPC liposomes into GelMA-based inks enables infection monitoring through visible color changes and fluorescent responses. Furthermore, the printability of the ink highlights its potential for fabricating 3D in vitro models upon cell incorporation.

Acknowledgements
Financial support was provided by the Spanish MICIU PID2024-162567OA-I00 and a 2025 Leonardo Grant for Scientific Research and Cultural Creation from the BBVA Foundation. We acknowledge support from the María de Maeztu Excellence Unit CEX2023-001303-M funded by MCIN/AEI/10.13039/501100011033.

D1 – P091

Exploring substrate stiffness and YAP/TAZ pathways in non-viral gene delivery applications

Fruzzetti F., Oldani C., Dieni C., Candiani G., Bono N.
genT_LΛB, Dept. of Chemistry, Materials and Chemical Engineering "Giulio Natta", Politecnico di Milano, Milan, Italy

Introduction

Non-viral gene delivery systems offer strong potential for therapeutic applications, yet their efficiency is hindered by several barriers, including poor cellular uptake and restricted access to the nucleus [1]. For this purpose, cellular adaptation pathways to mechanical cues could potentially impact transfection efficiency (TE) [2].

Aim

This study investigates how substrate stiffness influences non-viral gene delivery by modulating YAP/TAZ mechanotransduction pathways.

Materials and Methods

Biocompatible substrates with stiffnesses ranging from 1 kPa to 60 GPa were prepared using polyacrylamide (PAA), polydimethylsiloxane (PDMS), biocompatible glue, polystyrene, and glass. HeLa cancer cells and L929 fibroblasts were cultured on these substrates, and their responses, including nuclear morphology, YAP/TAZ localization, and nanoparticles uptake of *gold standard* branched polyethyleneimine (*b*PEI)/pDNA-based polyplexes was evaluated through fluorescence microscopy, cell viability assays, and transfection analysis after 24, 48, and 72 hrs.

Results

Substrates with stiffnesses of 1 kPa, 10 kPa, 1 MPa, 10 MPa, 400 MPa, 3 GPa, and 60 GPa were fabricated and mechanically validated (Figure 1A). Surface silanization yielded comparable amine densities across all materials, standardizing surfaces and isolating stiffness as the primary variable (Figure 1B). Cell proliferation was significantly higher on stiffer materials with respect to softer counterparts, particularly at later time points (Figure 1C). Immunofluorescence analysis revealed a clear stiffness-dependent regulation of mechanotransducer YAP localization, shifting from predominantly cytoplasmic on soft substrates to nuclear on stiff substrates. The extent of YAP nuclear translocation increased with longer culture durations (72 hrs), suggesting a time-dependent adaptation of cells to the biomechanical environment. Cells exhibited marked alterations in morphology and cytoskeletal organization, as staining F-actin demonstrated that cells cultured on stiffer substrates displayed increased spreading and enhanced formation of actin stress fibers. In contrast, cells on soft matrices maintained a more rounded shape with a less organized actin cytoskeleton (Figure 2A,B). These observations indicate that cytoskeletal remodeling accompanies the stiffness-induced nuclear translocation of YAP. Nuclear morphology followed a similar trend, with increased elongation correlating with higher substrate stiffnesses and later time points (Figure 2C). Nanoparticles uptake, quantified as the TE of *b*PEI/pDNA polyplexes, showed no differences at 24 hrs across all substrates, but became stiffness-dependent at 48 and 72 hrs, with higher TE on stiffer substrates, especially for Hela cells (Figure 2D). This enhanced nuclear entry in HeLa cells is closely linked to intrinsic properties of cancer cells that differ in terms of nuclear envelope dynamics and intracellular transport mechanisms.

Conclusion

This study demonstrates that substrate stiffness is a dominant regulator of cellular behavior, orchestrating a coordinated response that spans proliferation, cell morphology, mechanotransduction, and gene delivery efficiency through a time-dependent progression in cellular adaptation that culminates in enhanced nuclear elongation, cytoskeletal organization, and YAP activation on stiff substrates. Collectively, these findings provide a mechanistic framework linking substrate stiffness to functional cellular outcomes and offer valuable design principles for biomaterial platforms aimed at optimizing cell behavior and gene delivery in both fundamental research and translational applications.




Figure 10: (A) Mechanical tests on fabricated materials. Graphs report stress-strain curves for PAA samples developed at two different 40 % (v/v) unpolymerized acrylamide and 2 % (v/v) bis acrylamide ratios, PDMS samples developed at two different component A-component B ratios, and samples obtained from the biocompatible glue. Young's modulus, calculated from the linear region of the stress-strain graph, is reported for PAA samples, PDMS, and biocompatible glue. Reported Young's moduli represent the mean ± standard deviation of n≥3 specimens per condition**; (B) Normalized absorbance intensity from the Coomassie Brilliant Blue assay.** All substrates exhibit similar absorbance levels, indicating no significant differences in amino group content; **(C) Cell viability on selected materials.** Graphs show cell viability, expressed as RFU-blank signals, of the sample evaluated after 24 hrs, 48 hrs, and 72 hrs of culture on the selected materials within the desired stiffness range.




Figure 11: F-actin and YAP localization analysis. Hela cells cultured on 1 kPa and 60 GPa after 24 hrs **(A)** and 72 hrs **(B)** were stained for cytoskeleton (F-actin) and YAP**; (C) Nuclei aspect ratio:** Aspect ratio (AR) of HeLa cells nuclei measured at different time points across varying substrate stiffnesses**; (D) Transfection efficiency:** TE of *b*PEI/pDNA polyplexes delivered to HeLa cells after 24, 48, and 72 hrs of cell culture on different substrates.

References

[1]Bono N., Ponti F., Mantovani D., Candiani G. *Pharmaceutics* 2020; 12; 183.
[2]Nardone G., Oliver-De La Cruz, J., Vrbsky J., et al. *Nat Commun* 2017 ; 8; 15321.

D1 – P093


Amphiphilic gelator-based shear-thinning hydrogel for minimally invasive delivery via endoscopy catheter to remove gastrointestinal polyps

Harshil Dave (Presenter)[1#], Hitasha Vithalani[1#], Hemant Singh[1], Indu Yadav[1], Abhinav Jain[2], Ankit Pal[3], Nishant Patidar[4], Archana Navale[4], Mukesh Dhanka[1‡]
[1]Dept. of Biological Sciences and Engineering, Indian Institute of Technology Gandhinagar, Gandhinagar, Gujarat; [2]Gastro1 Hospital, Ahmedabad, Gujarat; [3]Muljibhai Patel Urological Hospital, Nadiad, Gujarat; [4]Parul Institute of Pharmacy, Parul University, Vadodara, Gujarat, India

Introduction

Injectable polymeric hydrogels delivered via endoscopic catheter have emerged as promising submucosal agents, offering durable, long-lasting cushions to enhance the efficacy of endoscopic submucosal dissection (ESD) for the removal of small, flat polyps from the gastrointestinal tract (GIT). However, polymer-based injections do not meet the easy-injectability criteria via catheter because their high viscosity tends to clog the catheter needle. To the best of our knowledge, for the first time, we report the fabrication of an amphiphile-based small molecule hydrogel of diglycerol monostearate (DGMS) that self-assembles to form a hydrogel (DGMSH) for delivery via an endoscopic catheter. Physicochemical characterization of the hydrogel reveals its fibrous morphology, shear-thinning behaviour, and easy injectability, along with its scalability and long shelf-life (6 months). Ex vivo studies on the goat's stomach and intestine demonstrate the ease of injectability through the catheters and the development of visible submucosal cushion depots with the desired height. Moreover, the hydrogel can encapsulate both hydrophobic and hydrophilic drugs/dyes. In vivo studies in small animals have found that the hydrogel depot is durable, biocompatible, non-immunogenic, and has a hemostatic effect. Endoscopic studies in the porcine model demonstrate a safe injection and endoscopic excision of GI polyps, acting as a suitable agent for ESD.

Results



Scheme 1: The schematic illustrates the following: A) The structure of DGMS and its self-assembly mechanism by encapsulating hydrophilic dye (Mb), blood clotting agent (6-ACA), and hydrophobic anticancer drug (PTX). B) The shear-thinning properties of DGMSH allow easy injection into the submucosa using a clinical endoscopic catheter needle, forming a durable, desirable submucosal cushion by reducing perforation and preventing bleeding risks while naturally degrading over time.

In vivo evaluation in small and large animals




Figure 1: *In vivo* Biocompatibility and efficacy in small and large animals.

D1 – P094

Development of antimicrobial 3D-printed bio-ink scaffolds incorporating nanoparticles and antibiotics for infection control in healthcare setting

Gupta D., Di Giambattista G., Lupetti V., Casadidio C., Vitali L., Censi R.
School of Pharmacy, University of Camerino, Camerino (MC), Italy

Introduction

Healthcare associated infections frequently occur in postoperative care, caused by both Gram-positive and Gram-negative bacteria, and pose a critical challenge. Chitosan scaffolds inherently offer intrinsic antimicrobial properties, however their efficacy is often limited by their activity in physiological environment and surface biofilm formation. To overcome these limitations, this study aims to develop a multi-drug delivery system using 3D-printed chitosan scaffolds with nanoparticle-encapsulated Piperacillin/Tazobactum (PIP/TAZ) and Vancomycin to be effective against both Gram-negative and Gram-positive pathogens.

Materials and Methods

PIP/TAZ-encapsulated chitosan/hyaluronic acid (CHI/HA) nanoparticles were synthesized using a microfluidics platform for consistent and precise size control. Separately, free Vancomycin was dissolved in a bio-ink prepared by dissolving 4% (w/v) chitosan in 2% (v/v) acetic acid solution. The multi-drug bioink was prepared by dispersing PIP/TAZ nanoparticles solution within the chitosan matrix. These scaffolds were 3D-printed with an extrusion-based machine at 55 kPa and neutralised in 50:50 ethanol:water with 5% (v/v) triethylamine for 60 min. This step was followed by an intense 20 mins wash performed in two batches with 80:20 ethanol:water and then freeze dried. Antimicrobial activity was evaluated against S. *aureus* (ATCC 6538) and P. *aeruginosa* (FM) using static agar diffusion, solid agar plate growth, and broth microdilution.

Results

PIP/TAZ incorporated nanoparticle formulation with average size of 330nm (Figure 1a) was tested against P. *aeruginosa* (FM) using broth microdilution. The formulation demonstrated complete inhibition at 1:8 dilution factor and partial inhibition at 1:16 dilution factor (Figure 1b). The dual-drug loaded scaffolds (Figure 1c) were tested against S. *aureus* (ATCC 6538) using static agar diffusion and solid agar plate growth. A diffusion zone (diameter = 16mm) based killing mechanism was successfully introduced, while the empty chitosan scaffolds showed no zone of inhibition (Figure 1d). Similarly, the empty chitosan scaffolds exhibited no inhibition after 24h in solid agar plate growth while dual-drug loaded scaffolds provided a sustained release, extending the antibacterial activity up to 24h (Figure 1e). Further planned experiments include prolonged antibacterial activity tests, rheological and morphological analyses of the scaffolds, and kinetic drug release studies.




Figure 1: a) DLS analysis of CHI-HA-PIP/TAZ nps as a function of Total Flow Rate (TFR) b) : Broth microdilution test performed on P. aeruginosa (FM) against PIP/TAZ encapsulated CHI-HA nanoparticles i) top view ii) bottom view c) 3D printed dual-drug loaded chitosan scaffolds d) Inhibition zone e) Inhibition at t=4hrs in suspension against S. aureus (ATCC 6538)

Conclusion

This study successfully demonstrates the adaptability of 3D-printed chitosan scaffolds as potential multi-drug delivery carriers. These scaffolds can be tailored to target specific bacterial strains by either free-loading of the drug or drug-encapsulated microfluidics-based nanoparticles, providing an alternative yet customizable strategy for prevention against healthcare associated infection.

Acknowledgements

This project is funded by Progetto ADMIRE “Advanced antimicrobial Surface Coatings for Biomedical Application” – FISA2022-00931.

D1 – P095

Development of a smart ultrasound-activated patch for localized oxygen delivery in chronic wounds

Roventini E.[1,2], Cafarelli A.[1,2], Pucci C.[1,2], Ricotti L.[1,2]
[1]The BioRobotics Institute, Scuola Superiore Sant'Anna; [2]Dept. of Excellence in Robotics & AI, Scuola Superiore Sant'Anna, Italy

Introduction

Chronic wounds, often resulting from persistent inflammation and hypoxia during the wound healing process, affect around 2% of the population, representing a major global health issue. Hypoxia sustains inflammation by altering metabolism, limiting macrophage polarization toward a reparative phenotype, inhibiting proteases, and impairing neutrophil bacterial clearance. Thus, restoring a physiological oxygen concentration would help the correct wound healing process. Oxygen-releasing wound dressings offer advantages over hyperbaric and topical oxygen therapies by avoiding systemic toxicity, maintaining moisture, and enhancing oxygen penetration. However, they lack external control over oxygen release.

Aim

This work aims to develop a hydrogel-based wound dressing designed for controlled on-demand oxygen delivery through ultrasound-triggered acoustic droplet vaporization (ADV) of perfluorooctyl bromide (PFOB)-loaded droplets, while minimizing passive diffusion through a poly(lactic-co-glycolic acid) (PLGA) shell.

Materials and Methods

Eight PFOB-core/PLGA-shell droplet formulations (PFOB/PLGA ratio: 0.1–0.8; PFOB volume: 47.1 µL) were prepared by single-emulsion/phase separation. Droplets were characterized for size, shell thickness, and polydispersity by confocal microscopy and Hirox imaging. Ultrasound-induced vaporization (38 kHz, PRF 100 Hz, duty cycle 20%, 80–105 kPa) was quantified by Bürker chamber counting before and after stimulation, normalized to mock controls. Alginate hydrogels containing PLGA/PFOB droplets (1:1 v/v) were prepared from 2% alginate and crosslinked with 8% $CaCl_2$.

Results

The single-emulsion/phase-separation process produced spherical core–shell droplets (Figure 1). The resulting droplets exhibited an average diameter of 8.84 ± 5.43 µm, while the PLGA content directly affected shell thickness. Shell thickness analysis revealed two distinct droplet families, from which the formulations with a PLGA/PFOB ratio of 0.8 and 0.3 were selected as representative (Figure 1a). Both formulations exhibited homogeneous shell morphology, with significantly different shell thicknesses (1.2 ± 0.4 µm and 0.8 ± 0.1 µm, respectively), which may influence passive oxygen release and their ultrasound response (Figure 1b,c; Table 1). Ultrasound stimulation induced an average droplet vaporization efficiency of approximately 50% (Figure 1d), consistent with ADV of the PFOB core. Notably, the droplets retained their structural integrity after encapsulation within alginate-based hydrogels (Figure 1e), supporting their potential use in smart wound patch applications.

Conclusion

Ultrasound-activated ADV of PLGA/PFOB droplets represents a promising approach for controlled oxygen delivery in chronic wounds, paving the way for the development of smart therapeutic patches and improved patient care.

Acknowledgements

This work received financial and technical support from INAIL, grant agreement No PR23-CR-Pe, project WOUND.




Figure 1: a)Thickness comparison between the eight formulations of droplets (Statistical analysis: Kruskal-Wallis (α=0.05) *p<0.05, ***p<0.001 and Dunn's post-hoc test). b) Representative Hirox images of the selected formulations (PLGA/PFOB=0.8 and 0.3). c) Representative confocal images of the selected formulations (PLGA/PFOB=0.8 and 0.3). d) Vaporized droplets after ultrasound stimulation of the selected formulations (PLGA/PFOB=0.8 and 0.3). e) Alginate-based hydrogel synthesis and representative confocal images (Statistical analysis: one-way ANOVA (α=0.05) and Holm-Sidak's post-hoc test).

PLGA/PFOB	Diameter [µm]	PDI	Thickness [µm]
0.8	8.7±5.1	0.35	1.2±0.4
0.3	9.9±6.5	0.28	0.8±0.1

Table 1:Comparison in terms of diameter, polydispersity index, and thickness of the selected droplets (PLGA/PFOB=0.8 and 0.3).

D1 – P096
Next-generation antibacterial poly(ionic liquid) nanoparticles

Romero-Antolín J.A.[1], Pablos J.L.[1], Manzano M.[1,2], Vallet-Regí M.[1]
[1]Dept. Chemistry in Pharmaceutical Sciences, School of Pharmacy, Universidad Complutense de Madrid, Madrid; [2]Networking Research Center on Bioengineering, Biomaterials and Nanomedicine (CIBER-BBN), Madrid, Spain

Introduction
The rising mortality rate resulting from antibiotic-resistant bacteria infections has become a major global health concern, emphasizing the pressing need to develop novel strategies to address this threat[1]. Ionic liquids (ILs) have emerged as an antibacterial alternative to conventional antibiotics, furnishing a versatile tool for the development of biomaterials. These compounds consist of a positively charged unit with intrinsic antibacterial activity and an anion, commonly a halogen, which can be exchanged with bioactive molecules to improve their biological performance[2]. Moreover, ILs can be modified with polymerisable groups, allowing the fabrication of biomaterials that incorporate ILs within their structure and broaden our arsenal to fight bacterial infection. Among them, nanoparticles have demonstrated their efficacy in treating infections, positioning themselves as a promising tool for managing these pathologies.

Aim
To develop, for the first time, anion-exchanged poly(IL) nanoparticles (PIL NPs) with superior antibacterial efficacy and biocompatibility.

Material and Methods
Two different PIL NPs were yielded through thermopolimerisation of ILs. Bromine-containing PIL NPs (PIL NPs Br) were synthesised following an existing method, and PIL NPs with salicylate (PIL NPs Sal), an anti-inflammatory drug, were synthesised through a novel method. Both PIL NPs were characterised by physicochemical and microscopy techniques. Their biocompatibility was evaluated in human mesenchymal stem cells and human macrophages, and reactive oxygen species (ROS) production of both cell lines was analysed through flow cytometry. Finally, the antibacterial activity of PIL NPs was assessed against *Staphylococcus aureus* and *Escherichia coli*, as models of Gram-positive and Gram-negative bacteria, respectively.

Results
PIL NPs were successfully synthesised and biologically evaluated. PIL NPs Sal exhibited superior biocompatibility than PIL NPs Br for both cell lines, and also achieved higher antibacterial effect than PIL NPs Br in both bacterial strains. The ROS production was evaluated solely for PIL NPs Sal due to their superior biological behavior, revealing that the optimal range to use without inducing cellular stress is between 12.5 and 25$\mu g \cdot mL^{-1}$.

Conclusion
These results deepen our understanding on IL-based biomaterials, postulating PIL NPs Sal as an excellent antibacterial biomaterial against Gram-positive and Gram-negative bacteria with low toxicity in human cells.

Acknowledgements
We acknowledge the support from the “(MAD2D-CM)-UCM” project funded by Comunidad de Madrid, by the Recovery, Transformation and Resilience plan, and by NextGenerationEU from the European Union (Ref:PR47/21-MAD2D-CM), from the European Research Council (ERC-2015-AdG, VERDI, GrantNo.694160). The project that gave rise to these results receive the support of a fellowship from Fundación Ramón Areces.

References
[1]Vallet-Regí M., Schüth F., Lozano D., Colilla M., Manzano M. Engineering mesoporous sílica nanoparticles for drug delivery: where are we after two decades? *Chemical Society Reviews* 2022; 51; 5365-5451.
[2]Romero-Antolín J.A., Gómez-Cerezo N., Manzano M., Pablos J.L., Vallet-Regí M. Anti-inflammatory and antibacterial hydrogel based on a polymerizable ionic liquid. *Acta Biomaterialia* 2025; 196; 78-92.

D1 – P097

Magnetically responsive, bio-adhesive peptide based composite hydrogels for soft robotics

Corrigan A.[1], Omara A.[2], Nabawy M.[2], Finegan K.[1], Seller W.[3], Elsawy M.[1]
[1]Dept. Pharmacy and Optometry, University of Manchester, Manchester; [2]Dept. of Mechanical and Aerospace Engineering, University of Manchester, Manchester; [3]School of Biological Sciences, University of Manchester, Manchester, UK

Introduction

Soft robotics has enjoyed rapid growth over the past decade. Their compliant nature lends them towards uses in healthcare, with technologies in rehabilitation and minimally invasive surgery being commercially available. High precision through sensing and suitable safety profiles also makes them excellent candidates for drug delivery, especially for colorectal cancer as the colon has a relatively stable enzymatic environment and pH.

Peptide hydrogels based on ultrashort peptide sequences have arisen as promising materials for drug delivery to colorectal cancer because of their rapid self-assembly, excellent biocompatibility and biodegradability, and high degree of tuneability, but suffer in soft robotics applications from poor mechanical strength.

Aim

To develop magnetically responsive, mechanically strong and bio-adhesive peptide based composite hydrogels.

Materials and Methods

We formed peptide gels through the ionic co-assembly of K-Phg-E-Phg-K and E-Phg-K-Phg-E sequences and combined these with polyvinyl alcohol (PVA) crosslinked by sodium tetraborate decahydrate. Iron oxide microparticles were physically mixed for magnetic responsiveness.

Mechanical properties and homogeneity were tested using oscillatory rheology amplitude sweeps (1 Hz) and frequency sweeps (0.1% strain). The gel's response to passive locomotion by an external magnetic field was tested using a custom experiment in which a magnet beneath the gel moved at a constant speed of 0.4 cms^{-1}. Iron oxide concentration and surface type were changed. Shear and normal strains were studied by measuring the evolution of distance / angles between markers on the gel surfaces over time. Oscillatory rheology was conducted after locomotion to measure material fatigue.

Bio-adhesion of the composite gels to porcine colon tissue at pH 6.4 (colonic tumour surface) and pH 7.5 was tested through tack tests. FTIR was used to assess peptide secondary structures.

Results

The composite gels showed excellent stiffness and elasticity (G' (1 Hz) up to 120 kPa). They also showed good homogeneity with any segment being within 10% of G' of any other segment in a single gel. Higher iron oxide concentration gels showed the least difference in G' before and after locomotion.

Gels had enhanced bio-adhesion at pH 6.4 compared to 7.5. FTIR showed the maintenance of beta-sheets at varied pH.

Conclusion

Concentration of iron oxide had little effect on storage modulus before locomotion, but higher concentration iron oxide gels showed improved resistance to fatigue. Hence, we believe that these are the most suitable for soft robotic applications. Additionally, enhanced bio-adhesion of the gels at pH 6.4 implies promise in tumour sensing.

Acknowledgements

I would like to acknowledge my funders, the EPSRC, for their continued support throughout this project.

D1 – P098

Innovative 3D bioprinting of breast cancer bio-units to model macrophage–tumor interactions and NAC response

Schell D.[1], Schurmans M.[1], Van Hees E.[1], Arnould A.[1], Pierreux C.[1]
[1]Cell Dynamics & Cancer, de Duve Institute, UCLouvain, Brussels, Belgium

Introduction

Breast cancer (BC) is the most prevalent cancer and leading cause of cancer-related deaths among women worldwide, with hormone receptor-positive (HR+), human epidermal growth factor receptor 2-negative (HER2-) being the most frequent subtype. Despite neoadjuvant chemotherapy (NAC), 80% of HR+/HER2- patients develop resistance and relapse. Understanding NAC resistance requires considering BC as a complex ecosystem where the tumor microenvironment (TME) significantly influences cancer progression. Macrophages are abundant in the TME and associated with worse prognoses, yet their role in tumor progression and response to NAC remains poorly understood. Advanced 3D models incorporating diverse human BC and TME cell types, enabling reliable and reproducible dynamic monitoring of NAC response, are urgently needed.

Materials and Methods

We employed computer-assisted 3D bioprinting to reproducibly generate multicellular, compartmentalized bio-units of patient-derived BC cells surrounded by TME components. These bio-units are designed to study NAC response and resistance while elucidating macrophage contributions during BC progression and treatment.

Results

We developed a range of hydrogels with tunable stiffnesses spanning soft to highly stiff Young's moduli (Figure 1), enabling investigation of NAC response in healthy-like (soft) versus advanced cancer-like (stiff) extracellular matrices. Our hydrogel formulations, composed of alginate-gelatin or methacrylated hyaluronic acid-gelatin, do not adversely impact survival and proliferation of BC cell lines (MCF7, T47D, ZR75.1) or THP1 cells. Notably, THP1 monocytes acquired macrophage markers upon embedding, suggesting spontaneous differentiation within the 3D environment. We are currently investigating how bio-units with different cellular compositions (monoculture versus co-culture) respond to NAC across varying matrix stiffnesses. Additionally, we are replacing cell lines with patient-derived cancer cells to validate whether our bio-units predict clinical observations (NAC sensitivity/resistance), thereby validating our 3D cancer model and enabling mechanistic studies of macrophage roles during BC progression and NAC treatment.

Conclusion

Extrusion-based bioprinting is thus an efficient technology to reproducibly generate bio-units of BC in different stiffness hydrogels, and advance NAC response prediction and cancer biology understanding. Extrusion-based bioprinting efficiently generates reproducible BC bio-units within stiffness-tunable hydrogels, advancing NAC response prediction and cancer biology understanding. This platform offers a physiologically relevant tool for personalized medicine approaches and investigation of TME-mediated therapy resistance mechanisms.

Acknowledgements

This work was supported by UCLouvain Action de Recherche Concertée (ARC23/28-129, BiDiTwins), by the Région wallonne, the Fédération Wallonie-Bruxelles and the Région bruxelloise, Belgium (Convention n° 2310113, Plateforme Technologique d'Excellence "Alternatives aux expérimentations animales »).




Figure 1: Hydrogel stiffness can be modulated by varying the composition of the hydrogel. Hydrogels were prepared by mixing methacrylated Hyaluronic Acid (HAstiff or HAsoft, 1%) with gelatin methacrylated or not at different ratio (GelMA or Gel, 7%) or Alginate with gelatin (A1G7). Stiffness measurements were done based on Young's modulus using a Chiaro nano-indenter, at S. Gabriele's laboratory in UMons. N=2, n=25. Please note that Young's modulus values are highly dependent on the measurement technique used; therefore, the reported range of values (in kPa) can vary substantially from one study to the other.

D1 – P099

Multimodal morpho-topological indicator of bone fragility across healthy, osteoporotic and COVID-19 bone using SR-µCT, SEM and in situ mechanical testing

Sanchez P.[1,2], Longo E.[2], Tromba G.[2], Buccino F.[1,3], Vergani L.[1,3]
[1]Dept. of Mechanical Engineering, Politecnico di Milano, Milan; [2]Elettra-Sincrotrone Trieste SCpA, Trieste; [3]IRCCS Galeazzi-Sant'Ambrogio, Milan, Italy

Introduction

Bone fragility is commonly assessed using mineral density–based metrics that do not capture the influence of microstructural organization on damage initiation and propagation. Osteocyte lacunae form a 3D network that may affect local stress distribution and crack development. Although lacunar alterations are reported in pathological conditions, their mechanical relevance remains unclear. Furthermore, the complementarity of different imaging modalities requires systematic evaluation.

Aim

This PhD project aims to identify and validate a multiscale morpho-topological indicator of bone fragility by correlating lacunar morphology and spatial organization with crack initiation and propagation under in situ compression. A key objective is to compare lacunar characteristics in healthy, osteoporotic and COVID-19 bone. A second objective is to develop a correlative fragility index integrating synchrotron radiation micro-computed tomography (SR-µCT), scanning electron microscopy (SEM) and histology.

Materials and Methods

Human cortical bone samples (ethical approval obtained) are formaldehyde-preserved and sectioned into 4 × 4 × ~10 mm parallelepipeds. Baseline lacunar morphology is assessed using SR-µCT at two synchrotrons. At Elettra (SYRMEP, Trieste, Italy), scans are acquired at 1.3 and 1.6 µm pixel size. At HZB (BAM, Berlin, Germany), acquisitions are performed at 3.6 µm and 0.72 µm to evaluate resolution effects. Pre compression scans are obtained at both facilities.
In situ compression at Elettra uses a custom micro compression device enabling real time load and apparent strain recording. At HZB, a Deben CT5000 rig with a 5 kN load cell (1% accuracy) is used. Compression steps are imaged to monitor damage evolution.
For higher resolution analysis, additional samples are prepared at IPCMS (Strasbourg, France). Resin embedded specimens are sectioned using the automated tape-collecting ultramicrotome (ATUM). Approximately 200 serial sections per sample (100 nm thickness, ~1.5 × 1 mm area) are collected and imaged by SEM at 25 nm pixel size. Lacunae are segmented from SR-µCT and SEM data to extract volume, anisotropy, elongation, density and orientation. Cracks are segmented from in situ SR-µCT to quantify length, width, thickness, surface and volume. Spatial distribution and connectivity are analyzed using skeletonization and graph-based descriptors and correlated with crack initiation sites.

Conclusion

This project will establish a correlative multi-modal fragility index linking lacunar morphology and topology to mechanical damage across healthy and pathological bone.

Acknowledgements

Funded by the European Union Horizon Europe programme (MSCA, Grant No. 101120290). Additional support from NRRP (Mission 4, Component 2, Investment 1.1), Italian MUR, NextGenerationEU – Project ARCHIMEDES (CUP D53D23003940006, Decree No. 2022R4KA9X).

D1 – P100

Preparation of autologous skeletal myoblast sheets via novel cell sheet engineering to treat ischemic cardiomyopathy in animal models

Tseng Y.[1], Tan T.[2], Li J.[3], Liang H.[1], Lin F.[1], Tseng H.[3]
[1]Dept. of Biomedical Engineering, National Taiwan University; [2]Ph.D. Program in Medical Biotechnology; [3]Dept. of Biochemistry and Molecular Cell Biology, Taipei Medical University, Taipei, Taiwan

Introduction

Schemic heart disease (IHD) currently lacks definitive curative treatments. To overcome the inefficiency and poor cell retention of traditional suspension injections, cell sheet engineering has emerged as a promising approach for cardiac regeneration, offering enhanced cell adhesion and viability.

Materials and Methods

Prioritizing clinical safety over the high-risk regenerative capacity of stem cells, we utilized terminally differentiated myocytes. We developed a novel culture insert featuring a disulfide bond oxidation-reduction detachment mechanism. For in vivo testing, moderate-to-severe heart failure (LVEF reduced to 20-35%) was induced in New Zealand white rabbits and Lee-Sung miniature pigs via left anterior descending (LAD) artery restriction. One week post-infarction, autologously cultured skeletal myocyte sheets were implanted. Cardiac function was monitored via echocardiography, followed by histological evaluations (H&E, ICC, IHC) after 96-100 days.

Results

The culture insert's surface stiffness decreased significantly (878.6 MPa to 1.5 MPa), as verified by AFM and ESCA. Primary cardiomyocytes and skeletal myocytes were successfully cultured, detached, and stacked. In vivo, implanting 6-10 layers of skeletal myocyte sheets effectively restored LVEF from 20-35% to approximately 50% in both animal models. Furthermore, histological staining confirmed the successful regeneration and structural normalization of the left ventricular muscle tissue.




Fig.1. Stiffness of culture inserts.




Fig.2. Cardio-myoblast sheet and multilayering.

Conclusion

Our novel cell sheet engineering technique for autologous skeletal myoblast-mediated cardiac reconstruction demonstrates high efficacy in treating moderate-to-severe heart failure. We anticipate initiating human clinical trials soon to advance this technology's clinical contribution to myocardial reconstruction.

Acknowledgements

Supported by NSTC/MOST, Taiwan (Grants: 109-2221-E-038-009, 110-2221-E-038-005, 111-2221-E-038-010).

References

[1]Boehm J.K., Kubzansky L.D. The heart's content: the association between positive psychological well-being and cardiovascular health. *Psychol Bull* 2012; 138(4); 655-91.
[2]Sanganalmath S.K., Bolli R. Cell therapy for heart failure: a comprehensive overview of experimental and clinical studies, current challenges, and future directions. *Circ Res* 2013; 113(6); p. 810-34.
[3]Shimizu T., et al., Electrically communicating three-dimensional cardiac tissue mimic fabricated by layered cultured cardiomyocyte sheets. *Journal of Biomedical Materials Research* 2002; 60(1); 110-117.
[4]Ptaszek L.M., et al. Towards regenerative therapy for cardiac disease. *The Lancet* 2012; 379(9819); 933-942.
[5]Pasumarthi K.B., Field L.J., Cardiomyocyte cell cycle regulation. *Circ Res* 2002; 90(10); 1044-54.

D1 – P101

Hyaluronic acid–extracellular vesicle bioactive hybrid systems for lung acute injury application

Della Sala F.[1], Longobardo G.[1], di Gennaro M.[1], Cicatiello A.G. [2], Sagliocchi S.[2], Dentice M.[2], Borzacchiello A.[1]
[1]Institute of Polymers, Composites and Biomaterials, National Research Council; [2]Dept. of Clinical Medicine and Surgery, University of Naples Federico II, Naples, Italy

Introduction

Acute Lung Injury (ALI)) are characterized by a hyperinflammatory state that can result in pulmonary edema, impaired gas exchange, and reduced lung compliance.[1] ALI treatments mainly involve managing the symptoms with lung-protective ventilation and corticosteroids administration. Preclinical studies highlighted the ability of mesenchymal stem cells secretome, in particular extracellular vesicles (EVs), to decrease neutrophil infiltration, enhance alveolar fluid clearance, and improve survival. Due to the instability of EVs in biological environments, their introduction into biomaterials represent a necessary strategy for translating them into clinical application.[2] Previous studies have shown that EVs blended with low molecular weight hyaluronic acid (LMWHA) promoted EVs stability inducing differentiation toward a lung-like phenotype.[3]

Aim

In this work a bioactive system, based on LMWHA and EVs, to modulate inflammatory conditions in ALI has been developed.

Materials and Methods

The morphology and structural properties (SEM, DLS, FT-IR, Raman) of LMWHA/EVs blends were investigated. The stability was evaluated by storage and freezing/thawing tests. The injectability of the blends was assessed by rheological analysis. The interaction with mucus was studied by UV-Vis spectroscopy analysis. *In vitro* biological response (cellular proliferation, migration and the uptake) of the LMWHA/EVs blends on Human Lung Fibroblasts (HLF), healthy and inflamed with LPS have been carried out. Finally, the treatment of LMWHA/EVs *on in vivo* ALI rat model was performed, investigating the expression of inflammatory markers by PCR, histology and immunofluorescence techniques.

Results

Morphological characterization and the physical-chemical analyses demonstrated an interplay between the HA and the EVs. The stability of the LMWHA/EVs blends have been proved compared the EVs alone at freezing/thawing temperature. Rheological analysis demonstrated the hybrid system injecatblity with a viscosity of about 1×10^{-6} kPa·s. The interaction study with mucin showed that LMWHA could embed EVs, enhancing their diffusion through mucus and improving lung delivery. In vitro studies showed that the LMWHA/EVs blend enhanced HLF viability and migration, especially under LPS-induced inflammation, suggesting a synergistic bioactive effect compared with HA and EVs alone. Cell uptake study indicated that the LMWHA/EVs hybrid are likely internalized by endocytic pathways (via CD44), with HA enhancing vesicle–cell interactions and aiding EV uptake. The LMWHA/EV hybrid significantly reduced LPS-induced inflammatory mediator expression (IL-6, TNF-α, IL-8, and IL-1β) in the ALI rat model, indicating attenuation of pulmonary inflammation. Histological analysis confirmed that the hybrid completely reversed LPS-induced lung tissue damage, which included alveolar destruction and inflammatory cell infiltration (Fig 1). Immunofluorescence showed that LPS increased $CD3^+$ T-cell infiltration and α-SMA expression in lung tissue, indicating activation of inflammatory and myofibroblast responses associated with ALI and potential fibrosis. These effects were markedly reduced in the treated groups, particularly with the LMWHA-EV hybrid.




Fig. 1: Histological and immunofluorescence on ALI rat lungs.

Conclusion

The results demonstrated that bioactive LMWHA/EVs system could facilitate the development of a medical device for the treatment of in ALI capable to exerted trophic effects by promoting tissue repair and modulating inflammation.

Acknowledgements

The authors acknowledge the research project “One Health Basic and Translational Research Actions addressing Unmet Needs on Emerging Infectious Diseases” – INF-ACT, CUP B53C20040570005”. This research has been supported by EU funding within the NextGenerationEU-MUR PNRR Extended Partnership initiative on Emerging Infectious Diseases (Project no. PE00000007, INF-ACT).

References

[1]Matthay M.A., et al. *Annu. Rev. Pathol* 2011; 6 (1); 147-163.
[2]Tang L., et al. *ACS omega* 2023; 8 (11); 10030-10039.
[3]Della Sala F., et al. *Int. J. Biol. Macromo* 2024; 276;133793.

D1 – P102

Development of tough, injectable hydrogels for cartilage regeneration and osteoarthritis treatment

Moon H., Oliva N.
Dept. of Bioengineering, Instituto Quimico de Sarria, Barcelona, Spain

Introduction

Osteoarthritis is the most common chronic joint disease, affecting more than 500 million individuals or 7 % of the global population[1]. Injectable hydrogels are a class of treatment strategy for cartilage defects and osteoarthritis that have the significant benefit of eliminating the need for invasive surgeries while replacing and regenerating native cartilage. Crucial considerations of such hydrogels for implementation in load-bearing joints include adequate mechanical properties and biocompatibility. From this perspective, polyethylene glycol-acrylate (PEG-AC), chondroitin sulphate (CS) and gelatin (Gel) were the components selected for the development of an injectable hydrogel to replace and regenerate cartilage due to their biocompatibility, regulatory approval, and superior mechanical properties.

Materials and Methods

Methacrylic anhydride was used to introduce methacrylate (MA) groups to CS and gelatin. Hydrogels were formed after mixing these components with PEG-AC in various ratios and crosslinking using UV light. Hydrogels were subsequently assessed mechanically using rheology, dynamic-mechanical-analysis and long-term cyclic compression. Cytotoxicity of hydrogels and their degradation products was assessed using Prestoblue following seeding of fibroblasts and chondrocytes. Cell behaviour following seeding within hydrogels was investigated using RT-qPCR to quantify chondrogenic gene expression.

Results

Hydrogels and their individual components were not cytotoxic (cell survival > 85%). Hydrogel's composition significantly influences their mechanical properties with PEG-AC being particularly significant. Hydrogels can withstand physiologically relevant compression over many cycles, highlighting their durability and applicability in cartilage defects and osteoarthritic joints.

Conclusion

Hydrogels composed of a mix of CS-MA, PEG-AC and GelMA as opposed to individual components seem to be the most attractive for use as an injectable cartilage replacement. These hydrogels have potential as a treatment for osteoarthritis due to their injectability, biocompatibility and promising mechanical properties in the context of native cartilage.

References

[1]Hunter D.J., March L., Chew M. Osteoarthritis in 2020 and beyond: a Lancet Commission. *The Lancet* 2020; 396(10264); 1711-2.

D1 – P103
AR biomass as a promising component in osteoactive implants

Nina D.G.N.[1], Grasser G.A.[2], Bonifacio M.[1], Sousa K.S.J.[1], Trichês E.S.[3], Longo E.[2], Rennó A.C.M.[1], Braga A.R.C.[1], Assis M.[1], Granito R.N.[1]
[1]Bioscience Dept., Federal University of São Paulo, Santos; [2]CDMF, Federal University of São Carlos, São Carlos; [3]Institute of Science and Technology, Federal University of Sao Paulo, Sao José dos Campos, Brazil

Introduction
The development of biomaterials derived from natural and sustainable sources represents a promising alternative to the widespread clinical use of bioinert metal and ceramic implants, providing structural support and exhibiting the ability to stimulate active regenerative responses in bone tissue. In this framework, this study aimed to develop 3D-printed constructs from a calcium alginate polymer base and biogenic hydroxyapatite with the innovative incorporation of AR biomass, an aquatic species considered GRAS.

Materials and Methods
The scaffolds were developed using 3D printing, containing CaAlg, 10% bHA, and increasing levels of 0.25, 0.5, 1, 2, 4, and 8% AR biomass. Physical-chemical characterization included crystallinity analysis, elemental composition, topographic evaluation, rheological analyses, and mechanical compressive strength evaluation. In vitro biological effects were evaluated with MC3T3-E1 pre-osteoblastic cells during acute and chronic exposure periods (1, 3, 7, and 14 days), investigating cytotoxicity, genotoxicity, proliferative capacity, oxido-nitrosative cell state, migratory profile, osteogenic effects, antibacterial activity, and mitochondrial respiration.

Results
Based on the results of X-ray diffraction, energy dispersive spectroscopy, and scanning electron microscopy analysis of the scaffolds, the ceramic portion of scaffolds was shown to have a hexagonal structure with similar elemental composition but with non-uniform topographical defects that increased with the amount of AR biomass. All inks exhibited a rheological profile that favored extrusion for 3D printing. FTIR spectra confirmed the successful formation of the composite with all components and the interaction between them. A directly proportional gain in the compression modulus was observed with the addition of AR biomass. The in vitro results with MC3T3-E1 cells validated the biocompatibility (Fig. 1), with no signs of toxicity. In addition, an inversely proportional profile was identified in relation to cell proliferation, adhesion, and migratory dynamics compared to the other experimental groups, the formulation with 0.25% AR biomass was the most promising, with no increase in reactive oxygen species (ROS) or nitrogen (RNS) (Fig. 2). Micronucleus assays with CHO-K1 cells confirmed the absence of genotoxicity.

Conclusion
These findings support the safety of using low concentrations of AR biomass in the development of scaffolds for bone regeneration, as they stimulate the proliferation of pre-osteoblastic cells without increasing pre-existing ROS and RNS levels that could exacerbate the inflammatory response associated with the fracture.

Acknowledgements
The authors would like to thank FAPESP n° #2024/11111-2; #2025/03246-8




Fig. 1. A–D) Metabolic activity on days 1, 3, 7, and 14, respectively, with data normalized relative to the control. E) Representative micrographs of the indirect cell viability assay obtained on days 1, 3, 7, and 14. F–I) Quantification of total DNA content (ng/mL) on days 1, 3, 7, and 14 after exposure to the conditioned medium, respectively. Results are presented as mean ± standard deviation (n = 9). Statistical analysis was performed using one-way ANOVA followed by a post hoc test, with *p < 0.05.




Fig 2. A–D) Extracellular levels of RNS, expressed in nM, measured 1, 3, 7, and 14 days after exposure to the conditioned medium. NO quantification was performed based on a standard calibration curve. E-H) Intracellular ROS levels determined by the DCFDA assay after 1, 3, 7, and 14 days of exposure to conditioned medium, respectively. Relative fluorescence values were normalized relative to the control group. Results are presented as mean ± standard deviation (n = 9). Statistical analysis was performed using one-way ANOVA followed by a post hoc test, with *$p < 0.05$

D1 – P104

Injectable functionalized hydrogel microspheres for osteoarthritic cartilage regeneration

Lei Y.[1,5*], Li Z.A.[1,2,3,4], Tuan R.S.[1,2,3], Wei H.[5]
[1]Dept. of Biomedical Engineering, The Chinese University of Hong Kong, Hong Kong SAR; [2]Institute for Tissue Engineering and Regenerative Medicine, School of Biomedical Sciences, The Chinese University of Hong Kong, Hong Kong SAR; [3]InnoHK Center for Neuromusculoskeletal Restorative Medicine, Hong Kong Science Park, SAR; [4]Peter Hung Pain Research Institute, Faculty of Medicine, The Chinese University of Hong Kong, Hong Kong SAR; [5]Dept. of Orthopaedic Surgery, The First Affiliated Hospital of Chongqing Medical University, Chongqing, China

Introduction

The differentiation potentials and viability of stem cells are often impaired during cell isolation and delivery. Inspired by the phenomenon where islands can recruit seabirds for nesting, we constructed “cell island” microgels (MGs) using microfluidic technology and photopolymerization processes. These growth factor-loaded methacrylated hyaluronic acid and heparin blend MGs non-covalently bind platelet-derived growth factor-BB (PDGF-BB) and transforming growth factor-beta3 (TGF-β3), aiming to recruit endogenous stem cells and promote chondrogenic differentiation **(Figure 1)**.

Materials and Methods

In vitro experiments were conducted to evaluate cell migration and chondrogenic differentiation; in vivo experiments used osteoarthritis models. Loading efficiency of growth factors was detected, with ethical approval.

Results

The loading efficiency of PDGF-BB and TGF-β3 reached 96% and 91%, respectively. In vitro and in vivo results showed that “cell island” MGs enhanced cell migratory capacity and recruited endogenous stem cells via releasing PDGF-BB. The MGs provided a suitable microenvironment for cell attachment and spreading, and induced chondrogenic differentiation of recruited cells by releasing TGF-β3, presenting favorable therapeutic effects for osteoarthritis.

Conclusion

The developed “cell island” MG acts as a temporary “nest site” to support the migration, adhesion, and differentiation of endogenous stem cells. It provides a promising alternative to conventional cell-seeded scaffolds for tissue regeneration and osteoarthritis treatment.




Figure 1. Illustration of the fabrication of "cell island" microgels.

References

[1]Lei Y., Wang Y., Shen J., Cai Z., Zeng Y., Zhao P., Liao J., Lian C., Hu N., Luo X., Cui W., Huang W. Stem Cell-Recruiting Injectable Microgels for Repairing Osteoarthritis. *Adv Funct Mater* 2021; 31 ;2105084.

D1 – P105

Development of a bacterial exopolysaccharide-enriched alginate hydrogel for mesenchymal stem cell compatibility and antimicrobial properties

Mesude B.
Bioengineering Dept., Faculty of Life and Natural Science, Abdullah Gul University, Kayseri, Turkey

Introduction

Hydrogels based on natural polymers have been widely investigated for biomedical applications due to their biocompatibility and structural similarity to the extracellular matrix (1). Alginate is frequently used in tissue engineering because of its biocompatibility; however, its biological activity can be limited in terms of cellular interactions (2). Bacterial exopolysaccharides (EPS) have attracted attention as bioactive polymers that may enhance cellular response and provide additional biological functions for alginate-based biomaterials. Beyond their role as natural biopolymers, EPS display antimicrobial, antibiofilm, antioxidant and immunomodulatory activities (3). These properties make EPS attractive candidates for controlling microbial growth in clinically relevant infection settings.

Aim

This study aimed to develop an alginate-based hydrogel enriched with bacterial EPS and evaluate in terms of its physicochemical characteristics, cytocompatibility and antimicrobial activity.

Materials and Methods

Alginate-based hydrogels were formulated under sterile conditions. EPS fractions were isolated and extracted from *Lactobacillus plantarum* and also purified under controlled conditions. The chemical structure of the fabricated hydrogel was characterized by Fourier Transform Infrared Spectroscopy (FTIR) spectroscopy. Cytocompatibility was evaluated using human mesenchymal stem cells (MSCs) cultured on the hydrogel scaffolds. Cell viability and cytotoxicity were assessed using the MTT assay and Live/Dead staining (Calcein-AM/Propidium Iodide). Antimicrobial activity was determined against *Staphylococcus aureus* and *Escherichia coli* using standard microbiological methods. The enriched hydrogel was also tested with MSCs, and their antimicrobial activity was compared with control samples.

Results

The incorporation of EPS within the alginate matrix was confirmed by FTIR analysis and the interactions between the polymer components were revealed. The developed hydrogels promoted MSC growth and maintained a favorable cellular response throughout the experimental period. Cytotoxicity analyses showed that the fabricated biomaterial did not produce significant toxic effects on the cells. In addition, the EPS-incorporated hydrogels exhibited inhibitory activity against *S. aureus* and *E. coli* compared to the control alginate hydrogel, suggesting that the incorporation of EPS contributed to the antimicrobial performance of the biomaterial. Cell viability exceeded 95%, while cytotoxicity remained below 5%. The EPS-incorporated alginate hydrogels reduced bacterial growth in *S. aureus* and *E. coli*.by approximately 92% and 96%, respectively, compared to control groups.

Conclusion

The findings demonstrate that the EPS-enriched alginate hydrogel supports the cytocompatibility and antimicrobial potential of MSCs and is therefore a promising candidate for future tissue engineering and regenerative medicine applications. Further studies will focus on optimizing the biomaterial properties and evaluating its performance in advanced biological models.

Keywords: Alginate hydrogel, bacterial exopolysaccharide, mesenchymal stem cells, antimicrobial activity, tissue engineering

References

[1]Sheard J.J., Bicer M., Meng Y., et al. Optically Transparent Anionic Nanofibrillar Cellulose Is Cytocompatible with Human Adipose Tissue-Derived Stem Cells and Allows Simple Imaging in 3D. *Stem Cells International* 2019; 2019; 3106929; 1-12.
[2]Neves M.I., Moroni L., Barrias C.C. Modulating Alginate Hydrogels for Improved Biological Performance as Cellular 3D Microenvironments. *Frontiers in Bioengineering and Biotechnology* 2020; 8:665; 1-16.
[3]Werning M.L., Hernández-Alcántara A.M., Ruiz M.J., Soto L.P., Dueñas M.T., López P., et al. Biological Functions of Exopolysaccharides from Lactic Acid Bacteria and Their Potential Benefits for Humans and Farmed Animals. *Foods* 2022; 11(9):1284; 1-34.

D1 – P106

Croaker hydroxyapatite scaffolds as promising regenerative candidates for bone implants

Nina D.G.N.[1], Grasser G.A.[2], Trichês E.S.[3], Longo E.[2], Rennó A.C.M.[1], Braga A.R.C.[1], Assis M.[1], Granito R.N.[1]
[1]Bioscience Dept., Federal University of São Paulo, Santos; [2]CDMF, Federal University of São Carlos, São Carlos; [3]Institute of Science and Technology, Federal University of Sao Paulo, Sao José dos Campos, Brazil

Introduction

The increasing incidence of fractures is an emerging public health challenge that impacts the quality of life of millions of people. In this scenario, the development of bioactive scaffolds that stimulate regeneration is essential to reduce the associated biopsychosocial complications. Considering the current scenario, this project aims to develop scaffolds from biogenic hydroxyapatite (bHA) extracted from croaker bones (*Micropogonias furnieri*) through a sustainable thermochemical route based on the reuse of biological waste, using calcium alginate (CaAlg) as a polymeric base.

Materials and Methods

Scaffolds were prepared containing CaAlg and concentrations of 10%, 15%, and 20% of bHA, using commercial hydroxyapatite (cHA) as the reference standard, under the same conditions. Physicochemical characterization and in vitro biological effects were evaluated with MC3T3-E1 pre-osteoblastic cells.

Results

It was observed that both samples exhibited a hexagonal structure, but bHA presented a higher degree of crystallinity, with a similar elemental composition but distinct morphology. The inks manufactured with both ceramics presented a rheological profile that favored extrusion for 3D printing. XRD and FTIR analyses did not reveal abrupt structural changes. A gain in the compression modulus was observed with the addition of both ceramics, although the maximum strength decreased with increasing HA content. This behavior is consistent with SEM images, which showed a denser and less porous structure in the samples with higher loading, a factor that influenced stability and nutrient diffusion. After 14 days in simulated body fluid, XRF and SEM analysis indicated that the formulation with 10% bHA favored apatite deposition, due to increased phosphorus levels on the scaffold surface. In vitro results with MC3T3-E1 cells validated the biocompatibility of the scaffolds, which maintained metabolic activity above 70%, without signs of toxicity. Furthermore, the formulation with 10% bHA promoted cell proliferation, adhesion, and migration compared to the other experimental groups, without an increase in reactive oxygen species (ROS) or nitrogen species (RNS). Finally, staining with Alizarin Red S indicated osteogenic potential for 10% bHA, while micronucleus assays with CHO-K1 cells confirmed the absence of genotoxicity.

Conclusion

The results indicate that bHA scaffolds are highly promising candidates for applications in bone tissue engineering. as they stimulate osteoblastic proliferation and differentiation without altering the redox state of the fracture site in a way that might interfere with regeneration.

Acknowledgements

The authors would like to thank FAPESP n° #2024/11111-2; #2025/03246-8

D1 – P107

Curcumin-loaded GelMA/PCL-MEW hybrid scaffolds: Assessing long-term release, antioxidant defense, and cytocompatibility

Tabakoglu S.[1], Moczulska-Heljak M.[1], Kołbuk D.[1], Sajkiewicz P.[1]
[1]Laboratory of Polymers & Biomaterials, Institute of Fundamental Technological Research, Polish Academy of Sciences, Warsaw, Poland

Introduction

Successful tissue regeneration requires multifunctional composite scaffolds that combine synthetic polymeric frameworks for structural integrity with bioactive hydrogels to provide a supportive microenvironment.

Aim

This study aimed to develop a hybrid hydrogel scaffold as a synergistic approach by combining Melt Electrowriting (MEW) of Polycaprolactone (PCL) for mechanical reinforcement with a Curcumin-loaded Gelatin Methacryloyl (GelMA) to create a multifunctional microenvironment for tissue regeneration. The biological functionality of the developed scaffolds was evaluated, focusing on their capacity for sustained drug delivery, antioxidant activity, and high cytocompatibility.

Materials and Methods

The hybrid scaffolds were fabricated by integrating a PCL-MEW structural framework into Curcumin-loaded GelMA hydrogels (GelMEW) with three different concentrations of Curcumin (30, 45, and 60 µg/ml). Curcumin release profile was analyzed over a 14-day period in physiological conditions. Antioxidant capacity was evaluated by quantifying free radical scavenging activity. Furthermore, to confirm the cytocompatibility of the scaffolds, *in-vitro* cell viability test and cellular morphology analysis were performed using L929 line of fibroblasts.

Results

The developed GelMA/PCL-MEW hybrid scaffolds demonstrated a sustained curcumin release profile over 14 days, reaching cumulative release up to 60% depending on the loading concentration (Fig.1). Moreover, the scaffolds exhibited radical scavenging activity in a dose-dependent manner, where it increased from 18% to 54% corresponding to higher curcumin content, providing antioxidant capacity. Additionally, cytocompatibility assays confirmed high cellular viability across all scaffolds, with cell viability above 92%. No morphological signs of cytotoxicity were observed in fluorescence microscopy imaging even at the highest curcumin concentration.

Conclusion

In conclusion, these results revealed that curcumin incorporated Gelma/PCL-MEW hybrid system is a promising multifunctional platform for tissue engineering. It provides a sustained curcumin release with a potent oxidative stress protection while maintaining high cytocompatibility. As part of an extensive ongoing research, further characterizations including mechanical properties and degradation profiles are being conducted to fully evaluate the long-term performance and structural stability of these hybrid scaffolds for tissue regeneration.




Figure 1. Multifunctional performance of hybrid scaffolds: (A) Sustained curcumin release over 14 days; (B) Dose-dependent radical scavenging activity (RSA); (C) Fluorescence image showing high cell viability and spreading on scaffolds with highest curcumin concentration.

Acknowledgements
This work was supported by the Narodowe Centrum Nauki (NCN), Poland, under grant no. 2024/53/N/ST11/03900.

D1 – P108

3D printed oak extract loaded alginate-gelatine scaffolds functionalized with mesoporous bioglass

Teterovska R.[1,2], Brangule A.[2,3], Harmanci S.[4], Boccaccini A.R.[4]
[1]Dept. of Applied Pharmacy, Riga Stradins University, Riga, Latvia; [2]Baltic Biomaterials Centre of Excellence, Headquarters at Riga Technical University, Riga, Latvia; [3]Dept. of Pharmacology and Pharmacotherapy, Riga Stradins University, Rīga, Latvia; [4]Institute of Biomaterials, Friedrich-Alexander University Erlangen-Nuremberg, Erlangen, Germany

Introduction

The use of natural bioactive compounds is increasingly explored for their antimicrobial and regenerative potential. Oak bark is rich in polyphenols (tannic , ellagic, gallic acids). It has antibacterial, anti-inflammatory, astringent properties. Despite its long-standing role in traditional medicine[1], has not yet been incorporated into printable hydrogel inks. Three-dimensional printing is widely employed to fabricate hydrogel-based biomaterials for wound healing and tissue regeneration[2,3]. Mesoporous bioactive glass (MBG) is frequently utilized in biomaterial engineering[3].

Aim

This study aimed to develop and characterize a printable alginate–gelatin matrix loaded with oak bark extract and MBG.

Materials and Methods

Ink base consisted of 3.5% alginate and 3.5% gelatin (ALG-GEL), 0.1% of oak bark extract and 0.02% of MBG was added. Four types of inks were compared: with Oak, with Oak and MBG, and both types with modified pH to 7. Extrusion-based 3D printer was using room temperature or cooled printing surface. Scaffolds were post-crosslinked with $CaCl_2$ and microbial transglutaminase. Scaffolds were measured; and materials were characterized using FTIR, XRD, rheology. Crosslinking and swelling degree of scaffolds measured in pH 7.4.

Results

Fife-layered scaffolds with different shapes (square, circle and hexagon) were printed. Printing parameters were adjusted to specific ink. FTIR data shows that oak extract was incorporated into ALG-GEL matrix, and also served as crosslinker. Addition of MBG further crosslinked ink. Addition of oak extract did not impact amorphous structure hydrogel. Hydrogel viscosity was impacted by several factors such as pH, temperature, addition of extracts, and MBGs. Both unmodified inks showed shear-thinning, LVR recovery, and suitable G' for reliable extrusion. ALG-GEL-OAK prints more easily due to lower G' and tanδ, while ALG-GEL-OAK-MBG offers greater mechanical strength, consistent with scaffold printing observations. Increase of pH reduced crosslinking and printability. The optimal printing was achieved using cooled ink and surface. Printed scaffolds rapidly swell in first minutes, then they gained 1215-1646% of initial weight in 24h, and swelling stopped after 72 hours.

Conclusion

Oak bark extract was successfully loaded in alginate-gelatine hydrogels and printed using cooled printing surface. Functionalization with MBG nanoparticles improves scaffold structure. This printing approach could be used to print other herbal-extract-loaded alginate-gelatin matrices.

Acknowledgements

The authors acknowledge financial support from the European Union's Horizon 2020 research and innovation program under the grant agreement No. 857287 (BBCE—Baltic Bio-materials Centre of Excellence).

References

[1]Şöhretoğlu D., Renda G. *Phytochemistry Reviews* 2020; 19; 1379.
[2]Matai G. Kaur, Seyedsalehi A., McClinton A., Laurencin C.T. *Biomaterials* 2020; 226.
[3]Bhatti S.S., Singh J. *International Journal on Interactive Design and Manufacturing (IJIDeM)* 2023.

D1 – P109

Smart 3D printed marine collagen dressings incorporating zinc-based nanoparticles for skin regeneration

Assis M.[1,2], Nina D.G.N.[1], Grasser G.A.[3], Sousa K.S.J.[1], Bonifácio M.[1], Silva Jr E.P.[1], Lambertucci R.H.[1], Longo E.[3], Braga A.R.C.[1], Rennó A.C.M.[1]
[1]Dept. Biosciences, Federal University of São Paulo, Santos; [2]Institute for Advanced Marine Research, São Paulo State University, São Vicente; [3]Dept. Chemistry, Federal University of São Carlos, São Carlos, Brazil

Introduction

Chronic and hard-to-heal skin wounds remain a major clinical challenge, requiring advanced biomaterials capable of promoting effective tissue regeneration. Marine-derived biomaterials have emerged as promising candidates due to their biocompatibility and sustainability. In parallel, zinc-based nanomaterials have attracted attention for their ability to modulate cellular responses through controlled reactive oxygen species (ROS) generation. Integrating such nanostructures into 3D-printed biomaterials represents a promising strategy to engineer smart wound dressings capable of actively supporting skin repair.

Aim

This study aimed to develop smart 3D-printed marine collagen dressings incorporating zinc-based nanoparticles ($ZnWO_4$ and $ZnMoO_4$) and evaluate their potential to promote cellular responses associated with skin regeneration.

Materials and Methods

Collagen extracted from croaker fish skin (*Micropogonias furnieri*) was blended with alginate to fabricate scaffolds using 3D printing. $ZnWO_4$ and $ZnMoO_4$ nanoparticles were incorporated at concentrations ranging from 0.25 to 4 wt%. The resulting scaffolds were characterized by X-ray diffraction (XRD), Fourier-transform infrared spectroscopy (FTIR), and scanning electron microscopy (SEM). Biological performance was evaluated using HDFn cells through alamarBlue® proliferation assays, migration assays, ROS/RNS detection, and cell adhesion analysis by confocal microscopy.

Results

All scaffolds were successfully fabricated and showed homogeneous nanoparticle distribution without compromising structural integrity. Structural analyses confirmed stable incorporation of Zn-based nanomaterials within the polymer matrix. Biological assays revealed that the network modifiers (Mo^{6+} or W^{6+}) had minimal influence on cellular responses, whereas Zn^{2+} ions and controlled ROS modulation played a key role in regulating cell behavior. Scaffolds containing 1 wt% nanoparticles significantly increased metabolic activity and proliferation of HDFn cells without detectable intracellular ROS/RNS production. In addition, migration assays demonstrated faster cell migration compared with controls, while cell adhesion remained unchanged, confirming the biocompatibility of the materials.

Conclusion

Smart 3D-printed marine collagen dressings incorporating $ZnWO_4$ and $ZnMoO_4$ nanoparticles exhibited high structural stability, excellent biocompatibility, and enhanced cellular responses associated with skin regeneration. These findings highlight the potential of zinc-based nanocomposite dressings as advanced bioactive platforms for skin wound healing.

Acknowledgements

FAPESP 2024/19218-0 and 2026/00695-9

D1 – P110

Development of a novel ROS scavenging electrospun PCL scaffold for wound healing applications

Oyhanart S.R.[1], Chau D.Y.S.[1], Knowles J.C.[1]
[1]Dept. of Biomaterials and Tissue Engineering, Eastman Dental Institute, UCL, London, UK

Introduction

Oxidative stress (OS) has a role in the pathogenesis of a variety of inflammatory conditions, including dental pulp inflammation (i.e. pulpitis). Ilex paraguariensis – commonly known as yerba mate (YM) – is known for its antioxidant, anti-inflammatory and antibacterial properties. Despite an increasing interest in the use of herbal extracts in biomaterial manufacturing, the applicability of yerba mate in this area remains largely unexplored. The **aim** of this work was to evaluate the potential of yerba mate extracts in displaying cytoprotective effects against oxidative stress in vitro and optimise its incorporation into electrospun fibres for controlled release.

Materials and Methods


YM extracts were prepared from the commercial product in different extraction media (i.e. 100% water, 50% ethanol in water and 100% ethanol) at 70°C, and lyophilised. Total phenolic content (TPC) and antioxidant activity were assessed by Folin-Ciocalteau and DPPH assays, respectively, to identify the extraction medium resulting in the highest content and activity. Cytocompatibility of serial dilutions of the extract was evaluated in vitro against an immortalised cell line from human stem cells of the apical papilla (DSCS) and human gingival fibroblasts (hGF) using MTS, LDH-release and Live/Dead assays. Their ability to protect cells against oxidative stress was evaluated in a H_2O_2 insult model. Different approaches at incorporating the YM extract into polycaprolactone (PCL) electrospun nanofibres were explored and evaluated chemically, thermally, and microscopically. The antioxidant ability of the YM-infused electrospun fibres was evaluated by DPPH assay and their cytocompatibility tested against DSCS and hGF.

Results

A combination of ethanol and water (50:50 v/v) was found to yield the highest TPC and antioxidant ability. The extract was found to be widely cytocompatible and to be able to protect cells against oxidative stress triggered by H_2O_2 in vitro. Furthermore, the extract was successfully incorporated into PCL electrospun fibres, as confirmed via spectroscopy, thermal analysis and fluorescence microscopy and the optimal manufacturing route for achieving it was identified and confirmed by thorough material characterisation, demonstrating that in the present system, emulsion electrospinning does not work as effectively as demonstrated for other types of extracts available in literature. YM-loaded PCL fibres exhibited extraordinary antioxidant ability and improved wettability when compared to native PCL, which led to enhanced cell-material interaction.

Conclusion

Yerba mate extracts were found to exhibit a strong antioxidant activity, wide cytocompatibility and display cytoprotective activity against oxidative stress in vitro. An optimised route for incorporation into PCL electrospun fibres was identified, which led to scaffolds supporting improved cell attachment and biocompatibility.



Confocal fluorescence microphotographs of lyophilised YM extract, native and YM-incorporated PCL electrospun mats. The natural autofluorescence of the YM extract conferred to it by the high content of polyphenols was taked advantage of to evaluate its overall distribution within the electrospun fibres following the emulsion and blended approaches, showcasing that the former appears to lead to a patchier distribution while the latter confers a more homongenous and continuous distribution along the fibres.

Acknowledgements
This work was supported by the Engineering and Physical Sciences Research Council (grant EP/R513143/1 and EP/W524335/1).

D1 – P111
Electrospun polyactive scaffolds for chronic wound healing applications

Ver Heyen W.[1], Morent R.[1], Ghobeira R.[1], De Geyter N.[1]
[1]Research Unit Plasma Technology (RUPT), Gent University, Gent, Belgium

Introduction

Chronic wounds arise from impaired healing associated with vascular disease, diabetes, or infection, and represent a significant clinical burden worldwide. Current treatment strategies, including autologous and allogeneic skin grafts, are limited by donor site availability, donor site morbidity, and the risk of immune rejection. Tissue engineering (TE) approaches have therefore emerged as a promising alternative for skin repair by aiming to mimic the nanofibrous architecture of the native extracellular matrix. Electrospinning is a well-established technique for nanofibrous scaffold fabrication, enabling precise control over fiber diameter, morphology, and composition. In addition to scaffold architecture, matching the mechanical properties of native skin is essential for successful tissue regeneration and depends strongly on the choice of base material. This study investigates, for the first time, the use of PolyActive (PA) in electrospun skin TE scaffolds. PA is a copolymer consisting of a soft poly(ethylene oxide terephthalate) (PEOT) segment and a hard poly(butylene terephthalate) (PBT) segment, whose mechanical properties can be tuned by varying the PEOT/PBT ratio and the molecular weight of the polyethylene oxide (PEO) segment. This tunability makes PA an attractive alternative to conventional polyesters for skin TE.

Materials and Methods

Two PA compositions, 300PEOT55PBT45 and 1000PEOT70PBT30, were used for scaffold fabrication and comparison. The first number denotes the molecular weight of the PEO segment, while the second and third numbers represent the PEOT/PBT weight ratio (wt%). Electrospun scaffolds were fabricated from 25% (w/v) PA solutions prepared in a 7:3 (v/v) chloroform/Hexafluoro-2-propanol solvent mixture using optimized electrospinning conditions. Scaffold morphology, surface chemistry, wettability, and mechanical properties were characterized using scanning electron microscopy (SEM), X-ray photoelectron spectroscopy (XPS), water contact angle (WCA) measurements, and mechanical testing.

Results

Bead-free nanofibrous scaffolds were successfully fabricated for both PA compositions, as confirmed by SEM imaging. The fibers exhibited nanoscale diameters ranging from approximately 700–1000 nm and showed random fiber alignment, which is favorable for skin tissue engineering. WCA measurements showed that PA scaffolds were inherently hydrophilic. In addition, the 1000PEOT70PBT30 scaffolds exhibited lower contact angles than 300PEOT55PBT45, indicating increased hydrophilicity associated with a higher PEO molecular weight and a greater PEOT-to-PBT weight ratio. XPS analysis and mechanical testing are ongoing to evaluate surface chemistry and mechanical performance differences between both compositions.

Conclusion

Electrospun PA scaffolds show promising physicochemical properties, supporting their potential as tunable biomaterials for skin tissue engineering.

This work was supported by the Research Foundation-Flanders (FWO) (G0AG525N).

D1 – P112

Organohydrogel bioinks based on engineered albumin nanosheet-stabilised microdroplets

Zhang Y., Marciano D., Nadal C., Gautrot J.
School of Engineering and Materials Science, Queen Mary University of London, London, UK

Introduction

Hydrogels are widely explored as biomimetic scaffolds for 3D cell culture due to their ability to recapitulate key biochemical, structural and mechanical features of the extracellular matrix (ECM). However, for many naturally derived materials, achieving control of the microstructure and mechanical behaviours still remains challenging. Here, we present a printable organohydrogel platform based on albumin-stabilised microdroplets analogous to high internal phase emulsions (HIPEs). These microdroplets can be cross-linked into interconnected networks to form macroscale gels after printing, displaying high intrinsic microporosity. The mechanical properties, printability and cytocompatibility of the resulting materials were systematically investigated.

Materials and Methods

As shown in Fig. 1, engineered albumins were used to stabilize oil-in-water (O/W) emulsions. Microdroplets in the emulsion were crosslinked via thiol-ene coupling, using PEG-thiol crosslinkers and photoinitiators, under mild ultraviolet photoirradiation. Photo-rheology was used to characterise the mechanical properties of the resulting organohydrogels. The corresponding printed material were exposed to UV layer by layer using a CELLINK bioprinter. Mesenchymal stem cells (MSCs) were loaded in the corresponding bioinks and the cytocompatibility of the resulting materials was eavluated.

Results

The mechanical properties of the organohydrogel bioink were systematically characterised and tuned to enable stable extrusion-based bioprinting. The material exhibited pronounced shear-thinning behaviour and rapid structural recovery, allowing the printed constructs to maintain their shape and achieve good interlayer integration. Confocal microscopy and electron microscopy revealed that the printed organohydrogel retained a network architecture dominated by jammed microdroplets with high porosity. In short-term (24 hours) cell culture experiments, live/dead staining indicated high cytocompatibility, and cells displayed spreading within the printed scaffolds.

Conclusion

Overall, this work demonstrates the design of organohydrogel bioinks based on albumin nanosheet-stabilised microdroplets that enables stable extrusion bioprinting while maintaining a jammed high internal phase network microstructure. The inter-droplet crosslinking strategy provides strong mechanical integrity and cytocompatibility. These results highlight the potential of this bioink as engineerable scaffolds for tissue engineering and regenerative medicine applications.

Acknowledgements

Funding from the ERC (ProLiCell, 772462) is gratefully acknowledged. The China Scholarship Council (202208060332) is acknowledged for a PhD studentship to Zhang Y.

Fig. 1. Schematic illustration of fabricating the organohydrogel bioink from microdroplets.

D1 – P113

Fabrication of 3D-printed adhesive microneedle patch loaded with codoped hydroxyapatite in deep-tissue infective wound healing

Anjali U., Sudip M.*
School of Biomedical Engineering, Indian Institute of Technology (BHU), Varanasi, India

Introduction

Deep-tissue wounds are difficult to treat due to poor penetration of therapeutics into damaged tissues and muscles. Although deep-penetrating microneedle patches (MNPs) show promise, existing systems often lack multifunctional therapeutics, strong tissue adhesion, and natural bioactive materials that support all stages of wound healing. Hydroxyapatite (HAP) has recently gained attention for regenerative applications due to its inherent biological activity. In this study, cerium- and magnesium-co-doped HAP was integrated into an adhesive 3D-printed microneedle patch to enhance antibacterial activity and promote efficient deep-tissue wound healing.

.

Materials and Methods

Codoped hydroxyapatite (2% = 1Ce-1Mg, 5% = 2.5Ce-2.5Mg, and 10% = 5Ce-5Mg) was synthesized by co-precipitation and characterized by X-ray diffraction, XPS, FTIR, and scanning electron microscopy. Antibacterial activity was evaluated against clinically relevant pathogens, including *E. coli and B. subtilis*. The lead (5% = 2.5Ce-2.5Mg) Co-doped hydroxyapatite was incorporated into a biodegradable polymer matrix and fabricated into a 3D-printed adhesive microneedle patch. In vitro cytocompatibility was assessed using mammalian (HEK-293) cell lines. The wound healing efficacy of the developed patch was further investigated in an infectious wound model.

Results

The synthesized Codoped HAP (2% = 1Ce-1Mg, 5% = 2.5Ce-2.5Mg, and 10% = 5Ce-5Mg) exhibited high crystallinity and uniform morphology (Figure 1 A-C). The material (5% = 2.5Ce-2.5Mg and 10% = 5Ce-5Mg) has significant antibacterial activity against Gram-positive and Gram-negative bacteria (Figure 1 D-E). In vitro studies confirmed good cytocompatibility and enhanced cellular proliferation. The microneedle patch demonstrated effective tissue penetration. In vitro studies confirmed good cytocompatibility and enhanced cellular proliferation. The results indicate that the developed bioactive MNP+2.5Ce−2.5Mg HAP has strong potential as a localized therapeutic strategy for treating deep-tissue infectious wounds and reducing inflammatory response (Figure 2A-F).




Figure 1: (A) Synthesis scheme of the different codoped HAPs. (B) X-ray diffraction (XRD) patterns of pure and Ce–Mg codoped HAPs. (C) Selected area FT-IR spectra of pure and codoped HAPs. (C) (A) Colony-counting assay against both *E. coli* and *B. subtilis* following the treatment with pure HAP, 1Ce–1Mg HAP, 2.5Ce–2.5Mg HAP, and 5Ce–5Mg HAP (100 µg/mL) (UN = untreated control and P.C. = positive control, i.e., ciprofloxacin at 100 µg/mL). In-cell ROS production in. (E) EPS calculation for *E. coli* and *B. subtilis* following the treatments with 2.5Ce–2.5Mg HAP and 5Ce–5Mg HAP at different concentrations (P.C. = positive control: ciprofloxacin). Data are presented as mean ± SD (n = 3 independent experiments). The statistical analysis was done using one-way ANOVA followed by the Tukey test, where $p < 0.05$.




Figure 2: (A) Schematic representation of the infective wound-healing study using various treatment groups (MNP, 2.5Ce–2.5Mg HAP, and MNP+2.5Ce–2.5Mg HAP) compared to the vehicle control (PBS-treated). (B) Optical images of the rat wounds from day 0 to day 12 for all groups: PBS-treated, only 2.5Ce–2.5Mg HAP, MNP-treated, and MNP+2.5Ce–2.5Mg HAP (n = 4 for all the groups). (C) % wound closure curve for all groups up to day 12. (D) Colony counting assay was performed after treatment of various groups (MNP, 2.5Ce–2.5Mg HAP, and MNP+2.5Ce–2.5Mg HAP) and compared to the vehicle control (PBS-treated) at day 3 by collecting the swabs from the wound area of the rat for the measurement of bacterial infection. (E) Cerium biodistribution by using EDX images after 6 days of treatment in rat skin and muscle. (F) Weight % of cerium in rat skin and muscle after treatment with only 2.5Ce–2.5Mg HAP and MNP+2.5Ce–2.5Mg HAP at day 6, measured using EDX. Data are presented as mean ± SD (n = 4 independent experiments, *p < 0.05, **p < 0.01, ***p < 0.001). The statistical analysis was done using one-way ANOVA followed by the Tukey test, where p < 0.05.

Conclusion

In summary, a series of cerium- and magnesium-co-doped HAP was synthesized and characterized, and its antibacterial efficacy was investigated against both Gram-positive and Gram-negative bacteria. Among these, 2.5Ce-2.5Mg co-doped HAP exhibited better antibacterial activity against both Gram-positive and Gram-negative bacteria, and eradicated bacterial biofilms through irreversible oxidative stress and direct interaction of the ions with bacterial cells. A 3D-printed microneedle patach loaded with 2.5Ce-2.5Mg co-doped HAP was developed that showed: (a) high adhesiveness on rat skin and other organs (lung, liver, kidney and heart) with deep tissue delivery of bioactive ceramics; (b) stopped liver bleeding rapidly; (c) promoted rapid wound repair in 12 days in an infective rat wound model by elevating the level of myofibroblasts, increasing collagen-1 deposition, vascularization, endothelial cell proliferation and elevated level of the Tgf-beta and reduced level of inflammatory markers like TNF-alpha and IL-6. This 3D-printed MNP loaded with bioactive ceramics will be clinically relevant for various tissue regenerative applications and antibacterial therapies in the near future.

D1 – P114

Porcine duodenum-derived extracellular matrix gel for enhanced diabetic wound healing

Kamble A.[1], Joshi M.[2]
[1]Dept. of stem cells & Regenerative Medicine, Dr. D Y. Patil Education Society, Kolhapur; [2]Stemplus Cryopreservation, Sangli, India

Introduction

The skin, the largest and most exposed organ, is prone to various injuries. In diabetes, wound healing is hindered by microvascular damage, Peripheral Artery Disease (PAD), and diabetic neuropathy, causing prolonged inflammation without progression, affecting the healing mechanism. Several products exist for diabetic wound healing, but their high cost and varied responses lack reliability. Innovative approaches are needed to heal wounds faster. This study advances skin tissue engineering by developing gel based on extracellular matrix (ECM) from Porcine duodenum, rich in nutrients and growth factors (IGF, EGF, TGF β-1) .

Aim

Bioactive extracellular matrix based hydrogel from porcine duodenum to enhance regenerative healing in diabetic wounds.

Materials and Methods

The Porcine duodenum sample was processed for sterility, and alkaline digestion turned tissue into slurry, which underwent polymerization with PVA and Gelatine through freeze-thaw cycles. Characterization studies included wetting properties, hemocompatibility, in ovo biocompatibility, in vitro and in vivo studies.

Results

The duogel showed positive outcomes in wetting properties (32.0±2.8), hemocompatibility (0.10± 0.00), and angiogenic potential like vessel area (63.9±0.7mm²), no. of junctions (1339.3±22.0), average vessel length (2010.7±1.8). In-vitro studies showed increased cell viability (195%) and proliferation (0.36± 0.05) compared to control. In-ovo studies confirmed biocompatibility and enhanced angiogenesis. In-vivo studies demonstrated enhanced angiogenesis (VEGF, COL-1; $P<0.05$), decreased inflammation (PECAM, EP; $P<0.06$) and tissue remodelling (MMP-1,2,3,9 &13; $P<0.01$).

Conclusion

These findings advance knowledge in diabetic wound healing using ECM-based gel, offering promise for accelerated healing.




Fig 1 Hemolysis test




Fig. 2 SEM analysis

D1 – P115

Green freeze–thaw fabrication of nano-dispersible sacchachitin diepoxy-crosslinked hydrogels for diabetic wound healing

Bang-Yu W.[1], Ming-Thau S.[2], Hong-Liang L.[3], Ray-Neng C.[4], Ling-Chun C.[1*]
[1]Dept. of Biotechnology and Pharmaceutical Technology, Yuanpei University of Medical Technology, Hsinchu, Taiwan, ROC; [2]Panion & BF Biotech Inc., Taipei, Taiwan, ROC; [3]School of Pharmacy, College of Pharmacy, National Defense Medical University, Taipei, Taiwan, ROC; [4]Dept. of cosmetic science and management, MacKay Junior College of Medicine, Nursing, and Management, Taipei, Taiwan, ROC

Introduction

Sacchachitin (SC) is a natural polysaccharide obtained from the fruiting body residue of Ganoderma tsugae, which is mainly composed of chitin and β-1,3-glucan, which has good biocompatibility and potential to promote wound healing. However, SC has high crystallinity and low solubility, limiting its application in biomedical materials[1].

Materials and Methods

In this study, nano-dispersed SC was prepared using NaOH/urea freeze-thaw cycling technology[2], and SC hydrogels were chemically cross-linked with 1,4-butanediol diglycidyl ether (BDDE) and polyethylene glycol diglycidyl ether (PEGDE). The structure and physical properties of the material were investigated by XRD, FTIR, solid-state NMR, rheological analysis, and scanning electron microscopy (SEM), and its liquid absorption capacity, antibacterial activity, cytocompatibility, and wound healing effect in diabetic animals were evaluated.

Results

The results showed that freeze-thaw treatment effectively reduced SC crystallinity and formed nanodispersive structures, while double epoxy crosslinking established a stable three-dimensional hydrogel network. The resulting hydrogel has appropriate water vapor transmission rate (approximately 2000 g/m²/day), good liquid absorption capacity, antibacterial effect, and good biocompatibility for WS-1 fibroblasts. In a diabetic rat model, SC hydrogel significantly promotes wound closure.

Conclusion

It was concluded that a green preparation strategy for the preparation of nano-dispersed SC by freeze-thaw treatment and the formation of hydrogels through double epoxy cross-linking is established, and the resulting material has excellent physical and chemical properties and the potential to promote diabetic wound healing, which can be used as a new biomaterial for chronic wound dressings and regenerative medicine applications.

Acknowledgements

This research was funded by National Science and Technology Council, grant number NSTC 113-2221-E-264-001-MY2.

References

[1]Wu M.-H., Wang W., Chao F.-C., Hsieh C.-M., Chen L.-C., Lin H.-L., Ho H.-O., Huang T.-J., Sheu M.-T. One-pot fabrication of sacchachitin for production of TEMPO-oxidized sacchachitin nanofibers (TOSCNFs) utilized as scaffolds to enhance bone regeneration. Carbo*hydrate Polymers* 2021; 254; 117270.
[2]Lewis L., Hatzikiriakos S.G., Hamad W.Y., MacLachlan M.J. Freeze–Thaw Gelation of Cellulose Nanocrystals. *ACS Macro Letters* 2019; 8; 486-491.

D1 – P116

ELIXIR-030, a dual-targeting small molecule, attenuates inflammatory responses in IBD by modulating HMGB1 and type I interferon signaling

Park S.[1], Priscilla L.[1], Yoo C.[2], Lee D.Y.[1, 2]
[1]R&D, Elixir Pharmatech Inc., Seoul, Republic of Korea; [2]Dept. of Bioengineering, College of Engineering, Hanyang University, Seoul, Republic of Korea

Introduction

Inflammatory bowel disease (IBD) is a chronic inflammatory disorder characterized by dysregulated immune responses and intestinal barrier dysfunction. High mobility group box 1 (HMGB1), a prototypical damage-associated molecular pattern (DAMP), is significantly elevated in the intestinal tissues of IBD patients. It exacerbates disease severity by mediating the crosstalk between epithelial cells and myeloid immune cells, acting as a key upstream driver of intestinal inflammation[1,2]. Furthermore, Toll-like receptor 4 (TLR4)-dependent TRIF–TBK1–IRF axis triggers type I interferon (IFN-I) responses, which amplify inflammation in IBD[3,4]. Unlike conventional therapeuties that target downstream cytokines, ELIXIR-030 is a first-in-class small molecule designed to simultaneously target upstream HMGB1 and IFN-I signaling pathways.

Materials and Methods

The anti-inflammatory effects of ELIXIR-030 were evaluated in murine RAW264.7 and human THP-1-derived macrophages stimulated with lipopolysaccharide (LPS) or HMGB1. The Direct interaction between ELIXIR-030 and HMGB1 was confirmed via surface plasmon resonance (SPR). Transcriptomic profiling (RNA-seq) was conducted to identify global gene expression changes, focusing on innate immune and interferon-related pathways. Key signaling molecules (TBK1, IRF, and STAT1) were analyzed using RT-qPCR and Western blot. Cytokine levels (TNF-α, IL-6, and IFN-β) were measured by ELISA. In vivo efficacy was validated using a dextran sulfate sodium (DSS)-induced colitis humanized mouse model.

Results

ELIXIR-030 significantly suppressed inflammatory responses induced by LPS and HMGB1. RNA-seq analysis revealed a robust downregulation of interferon-stimulated genes (ISGs).. Mechanistically, ELIXIR-030 inhibited the expression of TBK1 and IRF7and blocked STAT1 phosphorylation without altering total STAT1 levels. Notably, ELIXIR-030 selectively modulated the TRIF-dependent pathway while sparing MyD88-associated signaling. Treatement with ELIXIR-030 led to a dose-dependent reduction in TNF-α, IL-6, and IFN-β production. In the DSS-induced colitis humanized mouse models, ELIXIR-030 markedly improved clinical outcomes, including reduced disease activity index (DAI), preserved colon length, and attenuated histopathological damage.

Conclusion

ELIXIR-030 exerts potent anti-inflammatory effects by dually inhibiting HMGB1-mediated activation and TLR4-TRIF-IRF-IFN axis. By targeting upstream innate immune signaling rather than terminal cytokines, ELIXIR-030 represents a promising and novel therapeutic strategy for the treatment of IBD.

Acknowledgements

This work was supported by a grant from the Korea Technology and Information Promotion Agency for SMEs (TIPA) (RS-2023-00282845).

References

[1]Foelsch K., Pelczar P., Zierz E., et al. Intestinal epithelia and myeloid immune cells shape colitis severity via HMGB1. *Journal of Crohn's and Colitis* 2024; 18; 1122–1133.
[2] Palone F., Vitali R., Cucchiara S., et al. Role of HMGB1 in intestinal inflammation and inflammatory bowel disease. *Journal of Crohn's and Colitis* 2016; 10; 1415–1426.
[3]King M.R., et al. Type I interferons in inflammatory bowel diseases. *Frontiers in Immunology* 2025; 16; 12685839.
[4]Crammond P., et al. Taking its toll: the role of TLR4 in human disease. *Frontiers in Immunology* 2026; 17; 1761361.

D1 – P117

Evaluation of tolerance and efficacy of a cross-linked umbilical cord intracorneal ring model in a bioreactor

Martin L., Garcia P., Barnouin L.
R&D Dept., TBF - Tissue Engineering, Mions, France

Introduction

While intracorneal ring segments (CAIRS) and PMMA rings are standard treatments for advanced keratoconus, both face significant limitations: PMMA rings risk extrusion, infection, and poor long-term biocompatibility, whereas CAIRS are limited by the scarcity of donors. To address these challenges, we developed a cross-linked human umbilical cord-based intracorneal ring, offering a biocompatible and mechanically stable alternative for corneal reshaping and visual rehabilitation. This study evaluates the safety and efficacy in restoring corneal shape.

Materials and Methods

Umbilical cord lining was extracted from human placental tissue and viro-inactivated. Proteoglycans were removed soaking umbilical cord tissue in sodium hydroxide for multiple hours followed by rinsing. The tissue was UV cross-linked with riboflavin, on a curved support, then rinsed and freeze-dried. Half-rings were cut using round punch and scalpel.

Corneas were collected from dead donors and placed in a bioreactor. Half rings were inserted in a tunnel that was cut in each cornea by a femtosecond laser. Corneas were kept in the bioreactor for 14 days. Corneal thickness was monitored throughout the study duration by live and time laps Optical Coherence Tomography (OCT). At the end of the study, macroscopic aspect of the corneas, transparency of the rings, central corneal thickness and histology with HES staining were assessed.

Results

Umbilical cord corneal rings induced a distinct bulging of the posterior part of the cornea, which persists throughout the 14-day observation period, indicating the absence of macroscopic damage. The central radius of the cornea's curvature has not been significantly modified by the presence of the ring between the start and the end of the study. No transparency increase was noticed by biomicroscopy nor by a signal decrease of the ring observed by OCT.

Epithelial desquamation was observed in one cornea, the cause of which does not appear to be related to the umbilical cord ring.

Conclusion

First results are promising but a longer study period would be necessary to assess the ring degradation and transparency evolution. Histological results are expected to assess the ring's impact on the cornea and any degradation of the ring after 14 days in human cornea.

Acknowledgements

Thanks to the Biio Laboratory (St-Etienne, France) for the realization of the bioreactor study.

D1 – P118

Integrated electrochemical platform with 3D-printed electrodes and MIPs for oncological biomarker detection

Baldin E.K.[1,2], Oliveira D.[1], Martins G.V.[1], Freitas G.P.[2], Beppu M.M.[2], Moreira F.T.C.[1]
[1]CIETI-LabRISE, ISEP, Polytechnic of Porto, Porto, Portugal; [2]School of Chemical Engineering, University of Campinas, Brazil

Introduction

Circulating tumor cells (CTCs) have emerged as valuable biomarkers for cancer diagnosis, prognosis, and therapeutic monitoring, driving the development of increasingly sensitive and selective detection platforms. Electrochemical biosensors based on 3D-printed metallic electrodes offer significant advantages due to their tunable micro- and nanostructured surfaces, which improve analytical performance[1]. To further enhance selectivity, biospecific recognition strategies targeting CD44, a glycoprotein implicated in tumor progression and metastasis, have been widely explored. Molecularly imprinted polymers (MIPs) represent a promising alternative, as they contain tailor-made recognition sites capable of selectively binding tumor-related biomarkers[2,3]. Therefore, this study proposes the integration of additive manufacturing, electrochemical sensing, and MIP technology to enhance the capture and detection of CTCs, supporting the development of advanced liquid biopsy platforms for early cancer diagnosis and monitoring.

Materials and Methods

Ti6Al4V electrodes were produced by additive manufacturing using Electron Beam Melting (EBM). The electrodes were modified with gold nanoparticles (AuNPs) by cyclic voltammetry (CV), employing 40 cycles between -1.25 and -0.7 V. The AuNPs were analyzed by high-resolution scanning electron microscopy (SEM/FEG) using a TESCAN microscope (Mira 3 XMU). The molecularly imprinted polymer (MIP) was synthesized by electropolymerization of 2-aminophenol in PBS. The glycoprotein CD44 (5.0×10^{-3} mg.ml^{-1}) was used as a template molecule during MIP formation. After synthesis of the polymeric matrix, protein removal was performed with incubation in Proteinase K solution. As a control, a non-imprinted polymer (NIP) was prepared in the absence of CD44. All surface modification steps were monitored by CV and electrochemical impedance spectroscopy (EIS).

Results

Electrochemical characterization demonstrated an increase in electrode conductivity after functionalization with AuNPs compared to the unmodified Ti metal. During electropolymerization, a progressive decrease in the current density of the oxidation peak was observed after 10 cycles. Moreover, the absence of redox peaks for MIP and NIP confirmed the formation of an insulating polymeric layer on the Ti6Al4V-Au electrode. After the protein was removed, a considerable increased in system resistance was observed, consistent with the formation of cavities in the polymer. As expected, the calibration curve showed the opposite behavior, with the current increasing proportionally with different concentrations of CD44.

Conclusion

The synergistic combination of 3D-printed electrodes, AuNPs, and MIPs enabled the development of a highly efficient analytical platform for the direct electrochemical detection of proteins and, consequently, CTCs. The system demonstrated remarkable sensitivity, selectivity, and rapid analytical performance, supporting its applicability in liquid biopsy approaches and early cancer diagnostics.

Acknowledgements

To FAPESP for financial support (Grant n. 2020/12980-3 and n. 2025/26415-0).

References

[1]Yu L. et. Al. *Adv Healthc Mater* 2021; 100.
[2]Castaño-Guerrero Y. et. Al. *Adv. Mater. Interfaces* 2025; 12.
[3]Moreira F.T.C. et.al. *Sensors and Actuators B: Chemical* 2014; 196.

D1 – P119
Composite GelMA bioinks for volumetric bone bioprinting

Mihci H.E[1,2], Arslan A.[1], Van Hoorick J.[1], Aksu D.[1]
[1]BIO INX; [2]Dept. of Organic and Macromolecular Chemistry, Ghent University, Ghent, Belgium

Introduction
Traditional three-dimensional (3D) printing methods have limitations in their abilities to produce complex, functional structures with enhanced resolution and scalability. In this context, volumetric bioprinting (VBP) has emerged as a promising light-based fabrication method for rapid, layer-free production of complicated 3D structures (1). Gelatin Methacryloyl (GelMA) is a photo-crosslinkable, biocompatible hydrogel derived from gelatin, maintaining cell-responsive motifs and allowing tunable mechanical and degrading properties (2). Its rapid light-induced crosslinking and transparency make it highly suitable for volumetric bioprinting applications.

Aim
The main goal of this study is to enhance mechanically durable and physiologically active GelMA-based scaffolds by combining them with hydroxyapatite (HAp) and boric acid (BA) for bone tissue engineering applications.

Materials and Methods
BA and HAp were incorporated into GelMA-based bioinks READYGEL INX X100 (BIO INX BV, Zwijnaarde, Belgium) and X-Pure GelMA (160P60 RG, Rousselot Biomedical, Belgium) to enhance viscoelasticity, optical transparency, and bioactivity for VBP. Constructs were fabricated utilizing a Tomolite V2 printer (performance version, Readily3D, Switzerland). READYGEL INX X100 was printed using manufacturer's protocol, whereas X-pure GelMA was formulated with a photoinitiator and optimized towards volumetric printing. Rheological properties (G′, G″), mechanical strength, and optical transparency of printed constructs were characterized, along with swelling and degradation under physiological conditions. mCherry-labeled human osteoblasts (CI-huOBs) were used to assess biological functionality via PrestoBlue metabolic assays, LSM imaging (Figure 1B), and differentiation analysis.

Results
READYGEL INX and X-Pure GelMA were used for volumetric bioprinting at an optimal dosage of 188 mJ/cm², allowing reproducible printing performance. The HAp: BA formulation exhibited a stable swelling profile, maintaining higher levels at 72 hours (713%) and 336 hours (629%), indicating synergistic interactions among structural reinforcement and hydration stability. Based on the cell viability assay on day 7, X-Pure GelMA + HAp: BA demonstrated significantly higher metabolic activity compared to X-Pure GelMA ($p = 0.0002$) and X-Pure GelMA + HAp ($p = 0.0035$), indicating a time-dependent enhancement of cell viability (Figure 1A).

Conclusion
The dual incorporation of HAp and BA into GelMA bioinks synergistically improves printability and biological performance of READYGEL INX X100 and X-Pure GelMA.




Figure 12 A) Analysis of cellular viability of CI-huOB cells in different GelMA formulations throughout 7 days of incubation using the PrestoBlue assay. Data are shown as mean ± SD, n = 3. Statistical significance: *p < 0.05, **p < 0.01, ***p < 0.0001; **B)** Representative confocal images of CI-huOB (mCherry-labelled) encapsulated in various GelMA-based bioinks, including 1)READYGEL INX, 2) READYGEL INX + HAp, at days 1, 3, and 7. The red fluorescence visualizes cell distribution and morphology within the hydrogel constructs, obtained through z-stack imaging using LSM (The scale bar represents 200 µm).

References

[1]Bernal P.N., Delrot P., Loterie D., Li Y., Malda J., Moser C., Levato R. Volumetric bioprinting of complex living-tissue constructs within seconds. *Nature* 2019; 573; 568–572.

[2]Yue K., Trujillo-de Santiago G., Alvarez M.M., Tamayol A., Annabi N., Khademhosseini A. Synthesis, properties, and biomedical applications of gelatin methacryloyl (GelMA) hydrogels. Biomaterials. 2015; 73; 254–271.

D1 – P120

Bilayer electrospun membrane as a strategy to promote angiogenesis in advanced 3D skin model

Coviello L.[1], Villata S.[1], Vitale Brovarone C.[1], Napione L.[1], Frascella F.[1], Fiorilli S.[1]
[1]Dept. of Applied Science and Technology (DISAT), Politecnico di Torino, Torino, Italy

Introduction

The skin acts as a protective barrier against physical, chemical and biological factors while maintaining homeostasis, adjusting hydration and controlling temperature. Damages have detrimental consequences and require effective treatments. However, the market offers limited treatments, and the availability of new therapies is slowed down by the gap between pre-clinical testing and clinical translation. To overcome these limitations, 3D *in vitro* models are emerging as more realistic and cost-effective systems capable of mimicking tissue architecture and function. Nevertheless, developing 3D skin models remains challenging due to the complexity and heterogeneity of real skin, including vascularization, immune interactions and prolonged healing processes. Among these challenges, establishing an organised vascular network is essential to maintain homeostasis and the pathogenesis of the engineered tissue.
Aim. This study aims to promote angiogenesis and vascularization within a pre-existing dermis-epidermis 3D *in vitro* skin model[1] useful as a platform for drug screening.

Materials and Methods

Electrospinning was utilised to generate a structure comprising two overlapping layers, employing polycaprolactone for mechanical support and gelatin to promote cell adhesion, both dissolved in a 50:50 mixture of formic and acetic acid. The first layer was produced using a mixture of 12%(w/v) polycaprolactone and 9%(w/v) gelatin with a flow rate of 1mL/h and a voltage of 18kV. Aligned fibers were generated using a rotating collector at 2000rpm to guide endothelial organization. For the second layer, a 20%(w/v) polycaprolactone solution was employed, using a flow rate of 500µL/h and a voltage of 9kV. A flat collector was used to generate a random pattern, to facilitate the sprouting of vessels. Other process parameters were set at: 12cm distance needle-to-collector; 25°C temperature; and 35% humidity. The structures are engineered to deliver pro-angiogenic factors (VEGF and EGF) to promote angiogenesis and sprouting of blood vessels through the model. The growth factors will be delivered using two strategies: incorporation into mesoporous silica pores or surface anchoring.

Results

Preliminary results demonstrate the successful fabrication of a bilayered structure (Figure 1) with a thickness of 11µm, comparable to commercially available Transwell membranes, and capable of supporting the 3D model over time. Degradation tests (hydrolytic and enzymatic) showed that the structure retains its fibrous morphology, even after 14 days. Initial MSNs encapsulation studies showed that up to 5%(w/v) can be added to polymer solutions without affecting fibre formation.

Conclusion

The ambition is to demonstrate that the engineered membrane can support endothelial layer formation and vessel sprouting, which, after passing the membrane, vascularise the 3D skin model. Adding this vascular network is expected to improve the model's physiological relevance, enabling the development of a viable platform for drug screening.

Acknowledgements

Progetto PNC 0000001 D3 4 Health, CUP B83C22006120001, The National Plan for Complementary Investments to the NRRP, Funded by the European Union - NextGenerationEU




Figure 13: (A) Schematic illustration of the electrospun membrane mounted on the Transwell. Consisting of layer 1 of aligned fibres in contact with the medium and layer 2 of random fibres in contact with the 3D skin model. (B) Picture of bilayer structure mounted on the Transwell.

References

[1]Villata S., Baruffaldi D., Cue Lopez R., Paoletti C., Bosch P., Napione L., Giovannozzi A.M., Pirri C.F., Martinez-Campos E., Frascella F. Broadly Accessible 3D In Vitro Skin Model as a Comprehensive Platform for Antibacterial Therapy Screening. *ACS Applied Materials & Interfaces* 2024; 16; 70284-70296.

D1 – P121

An antioxidant nanoparticle-functionalized hydrogel for hormone deficient osteoporotic bone regeneration

Mallya D.[1], Cosgrave M.[1], Kaur K.[1,2], Murphy C.M.[1,3,4]
[1]Tissue Engineering Research Group, Dept. of Anatomy and Regenerative Medicine, RCSI University of Medicine and Health Sciences, Dublin; [2]School of Pharmacy and Biomolecular Sciences, RCSI University of Medicine and Health Sciences, Dublin; [3]Trinity Centre for Biomedical Engineering, Trinity College Dublin (TCD); [4]Advanced Materials and Bioengineering Research (AMBER) Centre, TCD, Dublin, Ireland

Introduction

Osteoporosis is a metabolic bone disease driven by age- and hormone-specific mechanisms. Age-related hormone deficiencies upregulate reactive oxygen species (ROS), promoting osteoclast activity, osteoblast apoptosis, and inhibiting mesenchymal stem cell differentiation, resulting in bone loss. This study aims to develop hydroxyapatite-based nanoparticles (nHA) for controlled release of antioxidant lanthanide (Ln) ions to reduce oxidative stress and promote bone regeneration. Cerium (Ce) has antioxidant and bone remodeling properties, while Neodymium (Nd) has antioxidant properties and unexplored osteogenic potential. Ln-doped nHA nanoparticles will be incorporated into a thermoresponsive chitosan-collagen hydrogel functionalized with tannic acid (TA) for dual antioxidant functionality.

Materials and Methods

Ce- and Nd-doped nHA (0.05-0.5 mol%) were synthesized by co-precipitation and characterized. Biocompatibility was evaluated in RAW 264.7 cells. Chitosan-collagen (90:10) hydrogels were prepared and functionalized with TA by two methods: (i) soaking of hydrogels in tannic acid solutions (5, 10, 15mg/ml) or (ii) direct incorporation during gel development (0.5-0.8mg/ml). Hydrogels will be characterized for antioxidant, biological, and physicochemical properties.

Results

FTIR confirmed retention of characteristic PO_4^{3-} bands in Ln-nHA, indicating successful nHA formation, with slight band broadening and intensity changes due to Ca^{2+} substitution with Ln^{3+} ions (Figure 1a). Antioxidant DPPH assay showed that 0.5% Ce-nHA exhibited the highest ROS scavenging activity, while undoped nHA showed lowest activity, confirming that enhanced antioxidant effect is primarily attributable to Ce doping (Figure 1b). Biocompatibility assessed in RAW 264.7 cells showed cell viability up to day 5 post-treatment, indicating no acute cytotoxicity (Figure 1c&d).

Unmodified 90:10 hydrogels showed thermoresponsive, shear-thinning, and viscoelastic behaviour near body temperature (32°C). FTIR confirmed TA incorporation in Method 1 gels and showed chitosan-TA interactions (Figure 2a). These gels exhibited burst TA release, likely due to surface localization of TA (Figure 2b). Method 2 gels showed no crossover between the storage modulus and the loss modulus, with storage modulus consistently remaining higher, indicating a pre-formed network (Figure 2d-g). These gels exhibited slower, sustained TA release compared to Method 1, making them more suitable for prolonged antioxidant delivery (Figure 2c).

Conclusion

FTIR confirmed successful Ln incorporation and TA functionalization. Ln-nHA showed no acute cytotoxicity up to day 5, with 0.5% Ce-nHA demonstrating superior ROS scavenging activity. TA incorporation during hydrogel formulation enabled sustained TA release, however, this affects thermoresponsivity. Future work includes complete characterization of Ln-nHA and evaluation of osteoclastogenesis and osteogenesis, and optimization of hydrogel properties to balance thermoresponsivity and sustained TA release.

Acknowledgements

This work is supported by the European Research Council Consolidator Grant under agreement GAP-101125820 (RESTORE).




Figure 14 - FTIR spectra of (a) Ce-nHA & Nd-nHA. (b) ROS scavenging ability of Ln-nHA. DNA content of RAW 264.7 cells treated with (c) Ce-nHA (d) Nd-nHA




Figure 15 - (a) FTIR spectra of hydrogels produced by Method 1. ROS scavenging ability of gels developed by (b) Method 1 (c) Method 2. Thermoresponsivity of 90:10 chitosan:collagen hydrogels with (d) 0.5 (e) 0.6 (f) 0.75 (g) 0.8 mg/ml tannic acid

D1 – P122

Improving neurite outgrowth in vitro by superparamagnetic nanoparticles loaded with nerve growth factor

Valdés Portas P.[1], Morales M. P.[1], Serrano M.C[1].
[1]Materials for Medicine and Biotechnology Group, Instituto de Ciencia de Materiales de Madrid, ICMM-CSIC, 28049-Madrid, Spain

Introduction

Spinal cord injury (SCI) is a serious neurological condition that heavily impacts the health conditions of more than 15 million people worldwide. Although therapeutic options for SCI remain limited, emerging fields such as biomaterials research, bioengineering, and nanomedicine are increasingly gaining relevance in this pathological context. In this work, we explore superparamagnetic iron oxide nanoparticles (IONPs) coated with biocompatible molecules such as hyaluronic acid (HA) and dimercaptosuccinic acid (DMSA) and loaded with nerve growth factor (NGF), a neurotrophic agent crucial for the development of sympathetic and motor neurons and the regulation of neurite outgrowth, as potential nanotherapeutics for neural repair in SCI.

Aim

The main goal of this study is to promote neurite outgrowth in embryonic neural progenitor cells (ENPCs) by conjugating neurotrophic factors to IONPs (Figure 1).

Materials and Methods

Single core IONPs were synthetized in a microwave reactor following the polyol method and using iron acetate(II) as precursor[1]. The nanoparticles were coated with DMSA and HA[2], and further functionalized with NGF at a theoretical 1:20 NGF/Fe ratio by absorption. ENPCs were cultured in complete Neurobasal media at a density of 50,000 cells/well. Cells were grown for 8 days in vitro (DIV) before the addition of NGF-functionalized nanoparticles. After 14 DIV, cell
viability and neural differentiation were evaluated by using confocal laser scanning microscopy (CLSM). Viability studies were carried out by using the Live/Dead Kit (Invitrogen), containing calcein and ethidium homodimer-1 as fluorescent probes. Cell differentiation was analyzed using anti-MAP-2 and anti-GFAP primary antibodies for labelling neurons and astrocytes, respectively. Cell nuclei were stained with Hoechst.

Results

IONPs were succesfully synthetized, presenting a spherical-like morphology and a mean diameter of 18 nm (±4 nm). The nanoparticles were efficiently coated using DMSA and HA, providing a negative surface charge at physiological pH (-37 and -41 mV, respectively). NGF functionalization was confirmed by zeta-potential and fluorescence measurements. After 14 DIV, DMSA-coated functionalized nanoparticles (SCMW15@DMSA:NGF) demonstrated higher cell viability than HA-coated counterparts (SCMW15@DMSA:NGF), remaining comparable to control samples. Furthermore, differentiation studies showed that SCMW15@DMSA:NGF enhanced the differentiation into neurons while supporting the formation of highly interconnected neural cultures (Figure 2).

Conclusion

Our study confirms that functionalization of coated IONPs with NGF promotes neuronal differentiation while maintaining high cell viability. These results highlight the potential of inorganic nanomaterials in biomedicine. Ongoing studies are focused on evaluating these nanoparticles as drug delivery systems for the controlled release of functional molecules upon external stimuli.

Acknowledgements
This work has been funded by grant PID2023-150170OB-I00 from MICIU/AEI/10.13039/501100011033 and FEDER, UE.




Figure 1. Therapy overview. Visual scheme for this study.




Figure 2. Representative CSLM images of ENPCs cultures at 14 DIV under the different conditions tested. IONPs were added at a concentration of 0.01 mg Fe/mL. MAP-2: neurons (green); GFAP: astrocytes (red); cell nuclei: Hoechst (blue).

References

[1]Gallo-Cordova A., Espinosa A., Serrano A., Gutiérrez L., Menéndez N., Morales M.P., Mazarío E. New insights into the structural analysis of maghemite and (MFe2O4, M = Co, Zn) ferrite nanoparticles synthesized by a microwave-assisted polyol process. *Materials Chemistry Frontiers* 2020; 4; 3063-3073.
[2]Martínez-Ramírez, J., Benayas E., Villar-Gómez N., Fernández-Méndez L., Espinosa F. M., García R., Veintemillas-Verdaguer S., Morales M.P., Serrano M.C. Hybrid hydrogels support neural cell culture development under magnetic actuation at high frequency. *Acta Biomaterialia* 2024; 176; 156-172.

D1 – P123

Engineering a biofunctionalized 3D-printed mesh for enhanced anastomotic healing

Borzouyan Dastjerdi M.[1,2,3], Masood A.[1,2], Raghavendra Rao G.[1,2], E. Kaiko G.[2,7], Vinu A.[3], Akhavan B.*[1,2,3,4,5,8]
[1]School of Engineering, The University of Newcastle, Callaghan, NSW 2308; [2]Hunter Medical Research Institute (HMRI), New Lambton Heights, NSW 2305; [3]Global Innovative Center of Advanced Nanomaterials, College of Engineering, Science and Environment, University of Newcastle, Callaghan, NSW, 2308; [4]School of Biomedical Engineering, The University of Sydney, Sydney, NSW 2006; [5]School of Chemical and Biomolecular Engineering, The University of Sydney, Sydney, NSW, 2006; [6]The University of Sydney Nano Institute, The University of Sydney, Camperdown, NSW 2050; [7]School of Biomedical Sciences and Pharmacy, The University of Newcastle, Newcastle, NSW; [8]School of Physics, The University of Sydney, Sydney, NSW 2006, Australia

Introduction

Anastomotic leakage (AL) remains a critical complication in colorectal surgery, contributing to significantly increased patient morbidity and mortality. While traditional mechanical reinforcements like sutures and staples provides structural support, it often fails to address the underlying biological requirements for tissue integration and infection control. Biofunctionalized meshes represent an advanced transition toward "instructive" scaffolds that actively modulate the healing microenvironment.

Aim

To engineer a biofunctionalized 3D-printed polycaprolactone (PCL) mesh that augments anastomotic healing through a synergistic combination of mechanical reinforcement, localized antimicrobial delivery, and stimulated tissue regeneration.

Materials and Methods

A biodegradable PCL scaffold was fabricated via fused deposition modeling (3D printing). To overcome the inherent hydrophobicity of PCL, surface functionalization was performed using an atmospheric pressure plasma jet (APPJ). This treatment was designed to enhance the interfacial bonding of a secondary bioactive layer.
A Gelatin Methacrylate (GelMA) hydrogel, loaded with Levofloxacin and Metronidazole, was then photopolymerized onto the treated PCL surface. Growth factors were incorporated into the hydrogel matrix to facilitate cellular recruitment and angiogenesis. Surface chemistry was characterized via X-ray photoelectron spectroscopy (XPS), and mechanical compliance was evaluated against native porcine gastrointestinal tissue.

Results

The APPJ-treated scaffolds exhibited a marked increase in oxygenated functional groups (confirmed by XPS), resulting in superior GelMA adhesion compared to untreated controls. The final biofunctionalized mesh demonstrated mechanical properties mirroring the compliance of gastrointestinal tissues, reducing the risk of stress shielding. *In vitro* studies showed that the GelMA layer provided a sustained release of antimicrobial agents, successfully inhibiting common enteric pathogens such as E. Coli. Furthermore, the bioactive microenvironment fostered significantly higher intestinal cellular proliferation and metabolic activity than bare PCL scaffolds. These findings suggest that the dual-action mesh provides both the structural integrity and the biological signals necessary to mitigate AL risk.

Conclusion

The integration of APPJ surface activation with a drug-loaded GelMA hydrogel on a 3D-printed PCL framework creates a promising platform for gastrointestinal repair. By addressing mechanical, microbial, and regenerative factors simultaneously, this biofunctionalized mesh offers a robust strategy for improving clinical outcomes in colorectal cancer surgeries.

D1 – P124

Optimizing *in-situ* oxidized hyaluronic acid-based hydrogels for 3d printing for soft tissue applications

Lorke M.[1], Moro Olea U. [2], Boccaccini A.R.[1]
[1]Institute of Biomaterials, Friedrich-Alexander University Erlangen Nürnberg, Erlangen, Germany; [2]Faculty of Engineering, Mondragon University, Mondragón, Spain

Introduction

Due to the presence of hyaluronic acid (HA) in the human body and the extracellular matrix (ECM)-mimicking properties of hydrogels, HA-based hydrogels are promising candidates for tissue engineering applications, particularly those designed to create scaffolds for repairing or regenerating tissue defects and diseases[1]. In this study, we developed stable, printable oxidized hyaluronic acid (OHA)-based hydrogels with ECM-mimicking properties for use in soft tissue applications.

Materials and Methods

HA was dissolved and oxidized with sodium metaperiodate ($NaIO_4$) to introduce aldehyde groups. Then, the solution was lyophilized. Then, hydrogels were prepared by mixing different ratios of HA and gelatin (GEL) with microbial transglutaminase (mTG) as an enzymatic crosslinker. Crosslinking was carried out at 37 °C for each polymer concentration and investigated. Printability parameters such as grid structure, filament fusion, and filament collapse were examined. Scanning electron microscopy was used to analyze pore structures. Bioprinting and cell viability were tested using BJ-1 cells with WST-8 assays and live/dead imaging.

Results


Higher gelatin concentrations lead to better printability, reduced gelation time, and smaller pore size. In general, higher polymer concentrations optimize printability and layer stacking (Fig. 1, left), even when the GEL concentration remains unchanged. Degradability of the Hydrogels was more pronounced with lower GEL concentration and led to a weight loss difference of 20% compared to their counterparts with higher polymer content. However, increasing OHA leads to a broader range of fabrication as well as improved cell viability and enhanced proliferation (Fig. 1, right).

Conclusion

The printability of *in situ* crosslinked hydrogels and the determination of optimal parameters remains a challenging task. Nevertheless, this study demonstrates that significant improvements in printability can be achieved by adjusting the printing time and polymer concentrations while maintaining good cell viability and proliferation.

Acknowledgements

We acknowledge the support by the Deutsche Forschungsgemeinschaft (DFG, German Research Foundation) project number 460333672 - CRC 1540 Exploring Brain Mechanics



Scalebar printing: 2 mm. Scalebar Live/dead 200 µm

Figure 1: left: Layer stacking of different OHA concentrations. Right: Calcein/DAPI (green/blue) staining of BJ-1 cells encapsulated in the hydrogel after 7d of incubation.

References

[1]Kuth S., Karakaya E., Reither N., Schmidt L., Paulsen F., Teßmar J., Budday S., Boccaccini A.R. Oxidized hyaluronic acid-gelatin based hydrogels for tissue engineering and soft tissue mimicking. *Mary Ann Liebert* 2022; Vol. 28, Iss 7; 301-313.

D1 – P125

PCL-based biomaterials with tunable properties for advanced tympanic membrane repair in chronic otitis media

Ooms A.[1], Van Durme B.[1], Livens P.[2], Roose P.[3], Van Rompaey V.[4], Van Vlierberghe S.[1]
[1]Polymer Chemistry and Biomaterials group (PBM), Centre of Macromolecular Chemistry (CMaC), Dept. of Organic and Macromolecular Chemistry, Ghent University, Ghent; [2]Laboratory of Biomedical Physics (BIMEF), University of Antwerp, Antwerp; [3]Allnex Belgium SA/NV, Drogenbos; [4]Dept. of Otorhinolaryngology and head & Neck Surgery, Antwerp University Hospital, Edegem, Belgium

Introduction

Chronic suppurative otitis media (CSOM) often leads to permanent tympanic membrane (TM) perforation and conductive hearing loss. Current clinical grafts (autografts/allografts) show several limitations including limited availability and revision surgeries. As a result, there is a critical need for engineered TM grafts that combine sufficient mechanical support together with biocompatibility to enable optimal tissue regeneration. In this project, 3D-printed structures were fabricated through digital light processing (DLP) and optimized to generate the optimal scaffold.

Materials and Methods

PCL was functionalized with acrylate moieties to obtain a UV-curable resin. Varying ratios of the crosslinker pentaerythritol tetrakis(3-mercaptopropionate) (PETA4SH) relative to the acrylate content were used to tune chain-growth versus step-growth polymerization, thereby mimicking the native properties of the TM. Subsequently, optimization of photo-initiator concentrations and print parameters was carried out through viscosity measurements, photo-rheology and through the development of working curves. The quality of the prints was evaluated through SEM images, mirroring the native TM's radial and circumferential fibre pattern. Next, the various crosslinker concentrations were assessed through physicochemical characterization of both 2D sheets and 3D-printed constructs. This included thermal analysis (TGA/DSC), gel fraction and swelling measurements, mechanical testing and degradation studies. Lastly, the biocompatibility of the material was evaluated, as well as the vibrational performance of the constructs using laser doppler vibrometry.

Results

The PCL modified inks allowed us to fabricate constructs with excellent network formation (gel fractions > 96%) with high CAD-CAM mimicry. A broad range of mechanical properties were obtained for the 3D-printed constructs, with Young's moduli spanning 8-32 MPa. Decreasing the crosslinker concentration produced stiffer scaffolds, with higher concentrations generating values more closely matching the Young's modulus of the native tympanic membrane (1.4 MPa). All samples displayed good biocompatibility, with both cell viability and metabolic activity exceeding 70%. Results indicated that 0.2 and 0.5 equivalents of PETA4SH represented the most favourable balance between mechanical performance and biocompatibility. These optimal formulations were subsequently examined using laser Doppler vibrometry to determine the construct thickness that provided the most successful vibrational behaviour.

Conclusion

Acrylate modified PCL with 0.2/0.5 equivalents of PETA4SH shows promising properties relating to the development of scaffolds to support TM regeneration.

Acknowledgements

BVD gratefully acknowledge financial support from the Research Foundation – Flanders (FWO-SB fellowship - 1SH3W24N). SVV and PR would like to acknowledge Flanders Innovation and Entrepreneurship (VLAIO) for funding of ICON project HBC.2023.0736

D1 – P126

TyraPi: A tyramine–piezo1 mechanochemical platform to dissect microglial reprogramming in glioblastoma

Nadig K.[2,3,4], Carreño A.P.[2,3,4], Fruleux T.[2,3,4], Hariharan A.V.[2,4], Pandit A.[4], Vallejo-Giraldo C.[1,2,3,4]
[1]Regenerative Medicine Institute (REMEDI), Advanced Therapies, School of Medicine, College of Medicine, Nursing and Health Sciences, University of Galway, Galway; [2]Biomedical Engineering, School of Engineering, College of Science and Engineering, University of Galway, Galway; [3]Institute for Health Discovery and Innovation, Bioscience Building, University of Galway, Galway; [4]CÚRAM - Research Ireland Center for Research in Medical Devices, Galway, Ireland

Introduction

Tyramine, a biogenic trace amine, exhibits neuroprotective effects in neurodegeneration models, reducing Aβ toxicity and microglial inflammation. However, at micromolar concentrations, tyramine can also induce genotoxic effects through MAO-dependent ROS production and tumor-promoting transcriptional changes[1].

Glioblastoma (GB) progression is critically driven by an immunosuppressive tumor microenvironment dominated by tumor-associated microglia expressing hybrid phenotypes that support tumor invasion and therapy resistance. The mechanosensitive ion channel Piezo1, upregulated in GB and highly expressed in reactive microglia, mediates stiffness-dependent activation, with context-dependent outcomes ranging from enhanced phagocytic clearance to ROS-driven dysfunction[2].

This study focuses on developing a tunable hydrogel platform to investigate how biochemical (tyramine) and mechanochemical (stiffness) cues regulate microglial activation, with a focus on Piezo1 signalling. This platform will further enable investigation of the complex crosstalk underlying GB–microglia interactions.

Materials and Methods

Material fabrication: TyraPi hydrogels were developed using physical and photochemical crosslinking at varying tyramine concentrations. They were characterized using rheology, nanoindentation, FTIR, NMR, swelling, and degradation assays.

Cell response: Healthy primary microglial cells were encapsulated within TyraPi hydrogels. Cytocompatibility and interactions with the material were evaluated through morphological analysis (ramification index and soma area), ROS production using cytokine profiling, and Piezo1 expression analysis through immunostaining.

Results

TyraPi platforms with tunable stiffness, shown in Figures 1A and 1B, support viable cell growth and display distinct cell morphologies and phenotypes. The varying stiffness regimes within TyraPi induced Piezo1 activation, confirming mechanosensitive signalling within the system (Figure 1C).

Conclusion

The TyraPi platform leverages mechanotransduction to investigate microglial heterogeneity through biochemical and mechanochemical cues in tunable hydrogels. Developing such tunable platform will enable further exploration of the complex phenotypic diversity influenced by GB-microglia crosstalk.

Funding

Funded by the European Union (ERC, TrapKill, 101163850). Views and opinions expressed are however those of the author(s) only and do not necessarily reflect those of the European Union or the European Research Council. Neither the European Union nor the granting authority can be held responsible for them. This work is also supported by the CoSE Scholarship, University of Galway.




Figure1. TyraPi stiffness regimes support cell growth and activate Piezo1. Varying stiffness regimes in the hydrogel matrix (A) supported viable cell growth and displayed distinct cell morphologies and phenotypes in 3D (B). F-actin (red, Rhodamine-phalloidin) and nuclei (blue, DAPI). Scale bar inset = 90 µm. Piezo1 activation was observed, confirming mechanosensitive signalling within the system (C). F-actin (red, Rhodamine-phalloidin), Piezo1 (green), and nuclei (blue, DAPI). Scale bar = 10 µm.

References

[1]Polini B, et al. T1AM/TAAR1 System Reduces Inflammatory Response and β-Amyloid Toxicity in HMC3 Cell Line. *Int J Mol Sci* 2023; 24(14); 11569.

[2]Zhou Y, et al. The mechanosensitive ion channel Piezo1 modulates the migration and immune response of microglia. *iScience* 2023; 26(1); 106176

D1 – P127

Carbon-carbon composites as materials that can stimulate neural tissue: comparison of pyrolytic carbon and functionalized carbon nanotubes

Wielowski R.[1], Zambrzycki M.[1], Czuk A.[2], Jantas D.[3], Fraczek-Szczypta A.[1]
[1]Faculty of Materials Science and Ceramics, AGH University of Krakow, Krakow; [2]Faculty of Electrical Engineering, Automatics, Computer Science, and Biomedical Engineering, AGH University of Krakow, Krakow; [3]Dept. of Brain Biochemistry, Maj Institute of Pharmacology, Polish Academy of Sciences, Krakow, Poland

Introduction

The development of advanced electrode materials is crucial for next-generation neural stimulation systems, particularly in the context of rising neurodegenerative disease incidence. Achieving long-term mechanical durability, chemical stability, and bioelectrochemical functionality remains a major challenge.

Aim

This study investigates hybrid carbon composites for deep brain stimulation (DBS) applications, comparing carbon fibers embedded in functionalized and non-functionalized pyrolytic carbon matrixs (CF/PyC) with an enhanced variant modified by oxygen-functionalized multi-walled carbon nanotubes (CF/PyC-CNT-OH).

Materials and Methods

Electrodes were fabricated using chemical vapor deposition (CVD) and subsequently functionalized via airbrush spraying of CNTs. Characterization involved CV, EIS, SEM, XPS, and mechanical fatigue testing under simulated conditions. Biological evaluation was performed using primary mesencephalic cell cultures. Cytotoxicity was assessed by LDH release, while immunostaining for dopaminergic (TH+) and general neuronal (NeuN+) markers enabled analysis after contact with the materials.

Results

Incorporation of CNT-OH significantly improved the electrochemical performance. CNT-coated samples showed higher charge storage capacity, lower impedance, and greater resistance to degradation compared to unmodified electrodes. The electrochemical modification of the pyrocarbon matrix using H_2O_2 as an additive resulted in the best capacity and pseudocapacitance behavior among all the electrode materials studied. Mechanical testing confirmed high tolerance to cyclic initial stress. Biological tests revealed no cytotoxic effects and, notably, a pro-survival influence on neuronal cells in proximity to CF/PyC/CNT-OH electrodes, especially within 1000–2000 microns. Durability tests, including simulated aging and accelerated degradation, confirmed the structural and functional stability of the electrodes.

Conclusion

Hybrid CF/PyC-CNT-OH and oxidized (CF/PyC-Ox) carbon composites demonstrate superior electrochemical, mechanical, and biological properties, positioning them as promising candidates for neural interface applications. Their robust performance and biosafety under simulated conditions support their potential for long-term, effective neural stimulation therapies.

Acknowledgements

Research on carbon nanotubes and their functionalization was funded by the National Science Center (Poland), grant number: UMO-2020/39/B/ST5/02126. Research on composites based on pyrolytic carbon matrix and its modification was funded by the National Science Center (Poland), grant number: UMO-2025/57/N/ST11/03480.

D1 – P128

Catheter-based aspiration thrombectomy via mechanical thrombus shattering in a pulsatile human circulation model

Fischbach A.[1], Briere C.[1], Pieper S.[2], Reinhardt J.[2], Hehrlein C.[1]
[1]Dept. of Cardiology and Angiology, University Heart Center, Freiburg; [2]MedFact Engineering GmbH, Lörrach, Germany

Background
Interventional treatment of coronary artery thrombus is currently performed with minor success in fibrin-rich, organized thrombi of human coronary artery circulation. A novel surgical device combining balloon dilatation for mechanical thrombus fragmentation with thrombus particle aspiration was tested in an *in vitro* model of human coronary circulation, targeting vessel diameters of 3-5 mm.

Methods
Catheter performance was tested under pulsatile flow conditions containing an artificial fibrin-based vessel narrowing consisting of a 30 mm long stenosis with a luminal diameter reduced from 3.0 mm to 2.1 mm and was compared to the use of a commercially available pure aspiration catheter (Terumo, Inc.) as a control. Aspiration efficiency was assessed gravimetrically by collecting, filtering, drying, and weighing stenotic material. Qualitative performance was evaluated using continuous digital microscopy recordings.

Results
Catheter expansion successfully dilated the artificial thrombotic vessel segment and shattered the thrombotic material, enabling subsequent aspiration. Digital microscopy demonstrated a thrombectomy effect due to the specially designed side-hole geometry of the novel catheter. Recoil of the expanded thrombotic segment resulted in entrapment into the catheter lumen and removal by aspiration. The novel thrombectomy catheter aspirated significantly more material than the Terumo control catheter across both tested flow rates, with approximately 15-fold and 12-fold higher aspiration weight at 50 and 100 ml/min, respectively ($p < 0.05$ for both comparisons).

Conclusion
A thrombectomy catheter applied to perform a combination of thrombus shattering and aspiration showed a clear advantage over a pure aspiration catheter in conditions of pulsatile vascular flow. Further preclinical animal studies are encouraged to confirm these findings.

D1 – P129

Engineered 3D human DMD muscle constructs enable optogenetic assessment of disease deficits

Kalkan A.K.[1], Pelarda A.J.[1], Bar-Nur O.[1]
Dept. of Health Sciences and Technology ETH Zurich, Institute of Human Movement Sciences and Sport, Schwerzenbach, Switzerland

Introduction

Duchenne muscular dystrophy (DMD) results from dystrophin deficiency, which renders muscle fibers vulnerable to mechanical stress and chronic injury. Modeling this pathology remains difficult because mdx mice show mild disease, rat and canine models are too heterogeneous for reliable translation, and conventional 2D cultures lack the structural and functional complexity needed to capture functional pathology. To address this gap, we developed a 3D skeletal muscle model using healthy and DMD primary human myoblasts with optogenetically controlled stimulation, enabling precise and contact-free functional assessment of disease phenotypes and therapeutic responses.

Materials and Methods

Human primary myoblasts were co-transduced with two lentiviral vectors encoding EF1α-Tet3G and TRE3G-ChR2-mCherry, enabling doxycycline-inducible expression of the optogenetic actuator channelrhodopsin-2 (ChR2). ChR2 expression was induced at two different time points to determine the optimal induction window for efficient expression. Subsequently, 3D engineered skeletal muscle constructs were generated using an extracellular matrix composed of fibrin, thrombin and Matrigel (Figure 1a). These constructs were then used to compare healthy and diseased muscle phenotypes in order to model key aspects of DMD pathology in a 3D *in vitro* human system (Figure 1b). Next, optogenetically engineered muscle constructs were tested over time to track progressive increases in contractile force.

Results

DMD-affected engineered muscles showed a ~34% force reduction at 1 Hz and ~65% at higher frequencies, alongside a ~164% increase in the twitch-to-tetanic ratio, indicating reduced force and impaired high frequency summation (Figure 1c, d). To enable temporal analysis of contractility, we developed a light-inducible model and optimized the ChR2 induction window, noting that early induction produced far fewer ChR2-positive myotubes than later induction. We therefore induced ChR2 on day 4 of differentiation and measured force on days 5, 7, and 9. Although only a slight impairment was evident at day 5, by day 9 DMD constructs showed a pronounced deficit, generating ~67% less force than healthy controls.

Conclusion

Human-derived 3D muscle constructs recapitulate DMD-associated functional impairments and, with temporally controlled ChR2 expression, enable longitudinal, non-invasive assessment of contractile function while minimizing animal use and supporting 3R-compliant DMD modeling.

Acknowledgements

This work was done within the framework of the ALIVE initiative (Advanced Engineering with Living Materials) and funded by the SFA-AM program (Strategic Focus Area – Advanced Manufacturing).



a
Mix of fibrinogen, thrombin, matrigel
Primary myoblasts
Dox
Blue light stimulation
ChR2
1 mm
Contraction analysis
Immunostaining
Muscle ring
Muscle generation
Proliferation
Early differentiation
Late differentiation
Analysis
b
Healthy (hMPC1)
DMD (hMPC2)
Dystrophin
DAPI
50 µm
c
Healthy
DMD
Contraction force (mN)
2.5
2.0
1.5
1.0
0.5
0.0
1 Hz
5 Hz
10 Hz
20 Hz
Frequency
d
Twitch-to-Tetanus Ratio
1.0
0.8
0.6
0.4
0.2
0.0
HDM
DMD

Figure 16

D1 – P130

A ring-core hydrogel platform for netrin-1-induced guidance of PC12 cells

Erdogan E.[1], Buyuksungur, S.[2], Banerjee S.[1]
[1]Dept. of Biological Sciences, Middle East Technical University, Ankara; [2]Center of Excellence in Biomaterials and Tissue Engineering (BIOMATEN), Middle East Technical University, Ankara, Turkey

Introduction

The native brain extracellular matrix (ECM) of the central nervous system (CNS) is structurally complex, comprising distinct regions known as gray and white matter. The interface between gray and white matter is a critical region for neurobiological research, as it is susceptible to morphological and functional changes in neurological disorders. Developing *in vitro* models that accurately mimic these regions is crucial for studying neurological disorders. This study aims to develop a biomimetic ring-core hydrogel platform to investigate the netrin-1-induced guidance of PC12 cell neurites to mimic the gray-white matter interface.

Materials and Methods

A 3D ring-core hydrogel system was fabricated using gelatin methacrylate (GelMA) and hyaluronic acid methacrylate (HAMA). The model was constructed in ring-core geometry, where the GelMA ring represented gray matter and the HAMA core mimicked white matter. PC12 cells were encapsulated within the GelMA ring, and netrin-1 guidance cue was loaded into the HAMA core to induce the guidance of PC12 neurites from the ring toward the core. Cell viability assay, cytoskeleton and nuclei staining, and βIII-tubulin immunostaining were conducted on days 1, 3, and 7 using confocal laser scanning microscopy (CLSM).

Results

GelMA hydrogel (10%, w/v) supported the high PC12 viability, exceeding 85% throughout 7 day experimental period. Quantitative analysis of CLSM micrographs on day 7 (Figure 1) demonstrated highly directed neurite outgrowth toward the core in scaffolds with netrin-1-loaded HAMA core. Directional analysis showed a toward-core neurite fraction of 0.98 in netrin-1-loaded scaffolds, showing the effective chemotactic response compared to the control group without netrin-1, with a toward-core neurite fraction of 0.50. Qualitative CLSM analysis will be further supported with βIII-tubulin staining to indicate robust neuronal differentiation.

Conclusion

A 3D brain tissue model was successfully developed using ring-core geometry and hydrogel matrices. Netrin-1 incorporation effectively guided PC12 cell neurite outgrowth, providing a robust platform for studying directed neurite growth and future neurodegenerative disease modeling.

Acknowledgements

This study was supported by the Presidency of Strategy and Budget (Project No: 08.11.KB.2016K121520), METU BIOMATEN and TÜBİTAK 2210-C Priority Areas MSc Scholarship program.




Figure 17. Neural cell guidance assesment under confocal microscope. Cytoskeleton and nuclei of the PC12 cells in the two-compartment model stained with Alexa Fluor 488 Phalloidin and DAPI, on days 1, 3, and 7. Magnification: 5X.

D1 – P131

3D tumor modeling: Exploring CSCs and MSCs interactions on bone-mimetic scaffolds

Apolloni L.[1,2], Saqawa M.[1,3], Bassi G.[1], Dow B. C.[4], Banche Niclot F.[4], Yustein J. T.[5,6], Panseri S.[1], Fulle S.[2], Taraballi F.[4], Montesi M.[1]

[1]Institute of Science, Technology and Sustainability for Ceramic Materials, National Research Council of Italy (ISSMC-CNR), Faenza, Italy; [2]Dept. of Neuroscience, Imaging and Clinical Sciences, University "G. D'Annunzio", Chieti, Italy; [3]Dept. of Chemical, Biological, Pharmaceutical and Environmental Sciences, University of Studies of Messina, Messina, Italy; [4]Center for Musculoskeletal Regeneration, Houston Methodist Academic Institute & Orthopedics and sports medicine, Houston Methodist Hospital, Houston, USA; [5]Texas Children's Cancer and Hematology Centers & The Faris D. Virani Ewing Sarcoma Center, Baylor College of Medicine, Houston, USA; [6]Aflac Cancer and Blood Disorders Center and the Winship Cancer Institute, Emory University, Atlanta, USA

Introduction

Bidimensional (2D) culture systems are still widely used for basic research. However, the development of more complex 3D in vitro cell culture systems can improve the modeling of diseases, such as osteosarcoma (OS), an aggressive primary bone tumor.

We developed a 3D model composed of cancer stem cells (CSCs), enriched by sarcosphere formation, and bone marrow-derived mesenchymal stem cells (BM-MSCs), cultured on different bone-mimetic scaffolds.

Materials and Methods

We initially optimized the co-culture growth medium and the BM-MSCs:CSCs ratio. CSCs were obtained either from the MG63 or MNNG-HOS osteosarcoma cell lines by formation of sarcospheres in a serum-free medium for 7 days, followed by a split of the sarcospheres and a growth of further 7 days. CSCs-enriched sarcospheres generated from both cell lines were cultured with BM-MSCs for an additional 10 days in two different settings: i) scaffold-free co-culture in liquid overlay, as a control; ii) co-culture on different hybrid hydroxyapatite/collagen-based scaffold types as a 3D bone-mimetic matrix. The viability of cells in the different co-culture settings was assessed by MTT assay and Live&Dead staining, while the cell morphology was investigated by F-actin staining. The spatial distribution of the spheres and BM-MSCs was observed in real-time by selectively staining the spheres with a tracking dye. Furthermore, to reveal possible changes in cell phenotype, we studied the expression of MSCs-specific markers (CD73, CD90 and CD105) and of CAFs-related markers, plus the pluripotency markers typical of CSCs (SOX-2, OCT4, Nanog).

Results

The outcomes allowed us to establish the optimal co-culture conditions to maintain the CSCs phenotype and the characteristics and cell viability of BM-MSCs. The differentiation of BM-MSCs into CAFs, induced by the tumoral microenvironment, was assessed by investigating the expression of α-SMA and FAP, specific markes of CAFs. We demonstrated the formation of spheres from MG63 cells, and that both spheres and BM-MSCs could colonize the scaffold and interact with each other and the ECM.

Conclusion

These results demonstrated the feasibility of establishing a CSCs-MSCs co-culture within a 3D environment. This provides a foundation for developing a more biomimetic multicellular OS model, enhancing its ability to replicate the distinct OS niches and the complex tumor microenvironment observed in vivo.

Acknowledgements

Funded by :PRIN2022 "MERCURY" and EU project PREDICTOS, HORIZON WIDERA 2021

D1 – P132

Cell-made scaffolds with mechanically induced alignment for tissue engineering

Valášková K.[1], Maňas L.[1,2], Humpolíček P.[1,2]
[1]Centre of Polymer Systems, Tomas Bata University in Zlín; [2]Faculty of Technology, Tomas Bata University in Zlín, Zlín, Czech Republic

Introduction

Cell-made scaffolds (CMSs) are fully biological structures synthesised by living cells *in vitro*, preserving native extracellular matrix features including collagen-rich composition and cell-instructive bioactivity. They have been shown to support cell adhesion, proliferation, and long-term function. Furthermore, the static mechanical stimulation can enhance CMS performance by inducing anisotropic fibre alignment. This better reflects the organisation of native tissue[1-3]. Therefore, CMSs can be processed into off-the-shelf scaffolds, offering a bioactive alternative to conventional synthetic scaffolds in tissue engineering.

Aim. The aim is to develop fibroblast-derived CMS, validate their structure and revitalisation capacity, and introduce static mechanical stimulation to generate anisotropic scaffolds for tissue engineering.

Materials and Methods

Human dermal fibroblasts (HDFs) were seeded at 1×10^4 cells·cm^{-2} and cultured for 8 weeks in DMEM/F12 supplemented with 20% FBS, 1% Pen/Strep and 500 µM sodium L-ascorbate to obtain cohesive CMS. Constructs were devitalised and then decellularised using 0.66% SDS for 60 min. To verify CMS structure and biofunctionality, CMS scaffolds were revitalized by reseeding with H9c2 cell line and cultured for 7 days and evaluated by fluorescence imaging. Based on these validated conditions, CMS were subsequently produced under static mechanical stimulation in a custom chamber with an actuated membrane, applying tensile deformation over a 25 mm area to induce fibroblast and ECM alignment.

Results

Long-term HDF culture produced cohesive scaffolds that were sufficiently large and easy to handle for devitalisation and decellularisation. These processes preserved ECM while removing cells. Revitalised CMSs supported H9c2 adhesion and proliferation with elongated morphology. Applying static tensile loading in the cultivation chamber induced pronounced fibroblast and ECM alignment, indicating mechanically induced anisotropy.

Conclusion

CMS generated by long-term culture, validated through H9c2 revitalisation, and subsequently exposed to static mechanical stimulation constitute robust, anisotropic constructs for tissue engineering. Combining stimulation with cell-instructive ECM introduces controlled anisotropy while preserving bioactive cues, enhancing organisation, and providing a versatile biological scaffold platform.

Acknowledgements

This work was supported by the Ministry of Education, Youth and Sports of the Czech Republic – DKRVO (RP/CPS/2024-28/001).

References

[1]Kawecki F. The potential of cell-assembled extracellular matrix for biological sutures: A promising innovation. *Sci Prog.* 2023.
[2]Saraswathibhatla A., Indana D., Chaudhuri O. Cell-extracellular matrix mechanotransduction in 3D. *Nature Reviews Molecular Cell Biology* 2023; 7; 495-516.
[3]Gauvin R., Parenteau-Bareil R., Larouche D. Marcouxm, H. Bisson, F. Bonnet A., Auger F.A., Bolduc S., Germain L. Dynamic mechanical stimulations induce anisotropy and improve the tensile properties of engineered tissues produced without exogenous scaffolding. *Acta Biomaterialia* 2011; 9; 3294-301.

D1 – P133

Matrix stiffness potentiates Piezo1-mediated hepatic stellate cell activation to reprogram pancreatic cancer lipid metabolism and modulate hepatic metastasis

Zhu B., Guo Y., Lu Y.
Nantong University School of Medicine, Affiliated Hospital of Nantong University

Introduction

Liver metastasis is the primary cause of mortality in pancreatic cancer. While collagen deposition by activated hepatic stellate cells (HSCs) creates a rigid fibrotic niche essential for metastatic colonization, the precise mechanisms translating this mechanical cue into biochemical pro-metastatic signals remain incompletely understood.

Aim

This study aims to investigate how matrix stiffness modulates HSC activation and subsequent crosstalk with pancreatic cancer cells (PCCs) to facilitate liver colonization and growth.

Materials and Methods

Substrate stiffness was manipulated using a GelMA hydrogel platform. Mechanosensing was evaluated via Piezo1 expression and calcium imaging. Conditioned medium (CM) from stiffness-primed HSCs was used to treat PCC lines (CFPAC-1, MIA-PaCa2). Lipid metabolism was assessed through Nile Red staining, TEM, and triglyceride ELISAs. Molecular interactions were validated via RNA-seq, Co-IP, and mass spectrometry. In vivo relevance was confirmed using a CCl4-induced liver stiffness mouse model and pharmacological Piezo1 inhibition.

Results

High substrate stiffness triggers Piezo1-gated Ca^{2+} influx in HSCs, inducing endoplasmic reticulum stress (ERS) via the IRE1α-XBP1 axis. This mechanotransduction drives HSCs to secrete glial maturation factor gamma (GMFG). Secreted GMFG binds to the tensin-4 (TNS4) receptor on PCCs, which coordinates a dual pro-metastatic program: enhancing cell-matrix adhesion via E-cadherin upregulation to establish a foothold, and fueling proliferative expansion by reprogramming lipid metabolism through the ACLY/ACC1/FASN pathway. In vivo, inhibiting Piezo1 significantly suppressed metastatic burden and metabolic reprogramming. Single-cell RNA-seq and spatial transcriptomics confirmed the clinical co-localization of the GMFG-TNS4-lipid metabolism axis in human metastases.

Conclusion

We identify the GMFG/TNS4 paracrine axis as a critical mechanical-biochemical link in the pancreatic cancer liver metastatic niche. Targeting the Piezo1-initiated HSC activation loop or its downstream metabolic effectors offers a promising therapeutic strategy against metastatic progression.

D1 – P135

Thiol-rich hyaluronic acid hydrogel drives spheroid formation and pro-regenerative secretory activity in human adipose-derived stem cells

Zhu R.[1,2], Song R.[1], Wang W.[1,2]
[1]Charles Institute of Dermatology, School of Medicine, University College Dublin, Dublin; [2]CÚRAM Research Ireland Centre for Medical Devices, Ireland

Introduction

Mesenchymal stem cells (MSCs) are promising for regenerative medicine, but their therapeutic efficacy is often limited by conventional two-dimensional culture, which fails to recapitulate the native cellular microenvironment. In contrast, three-dimensional (3D) spheroids better preserve cell–cell interactions, extracellular matrix (ECM) deposition, and paracrine activity. However, simple and translational biomaterial platforms that reliably induce spheroid formation remain scarce. Inspired by the natural stem cell nests, which are characterised by reductive microenvironments, low reactive oxygen species levels, and dense cellular organisation, this study exploits thiol engineering in low-adhesive hydrogels to explore the role of the thiol-rich extracellular environment in pro-regenerative phenotype development and to enhance the potential of human adipose-derived stem cells (hADSCs) for tissue repair.

Materials and Methods

Hydrogels with different thiol contents showed distinct free-thiol levels while maintaining comparable bulk mechanical properties, swelling behaviour and porous structure, enabling interrogation of thiol-dependent cell responses. Increasing thiol content significantly enhanced hADSC viability, proliferation and spheroid size in 3D culture. Thiol-rich matrices also promoted ECM deposition, particularly fibronectin and collagen, and increased secretion of the pro-regenerative factors VEGF and IL-10. Together, these findings suggest that thiol-rich extracellular environments actively regulate stem cell behaviour rather than functioning as passive carriers, and support a mechanism involving thiol–cell interaction, focal adhesion kinase activation and cytoskeletal remodelling.

Results


Injectable hyaluronic acid hydrogels with controllable thiol content, decoupled from mechanical properties, were constructed for rapid in-situ cell encapsulation. Upon cell encapsulation, thiol–cell interactions promote focal adhesion kinase (FAK) activation and cytoskeletal reorganisation. Increasing thiol content in the 3D extracellular environment significantly enhanced hADSC viability, proliferation and spheroid size. Furthermore, the thiol-rich hydrogel system significantly increased the production of ECM-related protein, as well as regenerative cytokines VEGF and IL-10, indicating enhanced pro-regenerative secretory activity and suggesting improved therapeutic potential in vivo.

Conclusion

A thiol-rich HA hydrogel provides a simple and injectable 3D microenvironment that promotes hADSC spheroid formation and enhances pro-regenerative secretory activity. This platform offers a translationally relevant strategy for engineering functional stem cell niches for soft tissue repair and regenerative medicine.

Acknowledgements

This work was supported by Research Ireland (Grant No. 13/RC/2073_P2) and co-funded by the European Union (Grant Agreement No. 101126640).



Scheme 1. Thiol-rich hyaluronic acid hydrogel drives spheroid formation and pro-regenerative secretory activity in human adipose-derived stem cells.

D1 – P136

Glucose-Induced adhesion reprogramming enables spontaneous cell sheet detachment without engineered surfaces or external stimuli

Choi S.[1,2*], Zo S.[1,2], Lee D.[3], Narayanan B.[1,2*], Bashkar R.[1,2,*], Han S.[1,2,*]
[1]Research Institute of Cell Culture, Yeungnam University; [2]School of Chemical Engineering, Yeungnam University; [3]Korea Dyeing & Finishing Technology Institute (DEYTEC), Republic of Korea

Introduction

Cell sheet engineering typically requires specialized culture surfaces, enzymatic treatments, or external stimuli to harvest intact cellular constructs. Here, we report a scaffold- and stimulus-free strategy in which fibroblast sheets spontaneously detach from conventional tissue culture polystyrene through glucose-induced adhesion reprogramming. NIH3T3 fibroblasts cultured under prolonged high-glucose conditions progressively accumulated extracellular matrix (ECM), formed cohesive multilayered sheets, and underwent complete spontaneous detachment between days 28 and 38 without thermoresponsive substrates, proteolytic treatment, or mechanical manipulation.

Morphological and confocal analyses demonstrated the formation of structurally uniform three-dimensional cell sheets with extensive ECM deposition. Immunofluorescence analyses revealed progressive collagen organization, enhanced collagen alignment, and increased α-SMA expression, indicating continuous matrix maturation during long-term culture. Mechanistically, spontaneous detachment was associated with attenuation of cell–substrate adhesion signaling. High-glucose cultures exhibited reduced phosphorylation of focal adhesion kinase (p-FAK, Y397) without substantial changes in total FAK expression, together with alterations in focal adhesion organization, suggesting weakened integrin-mediated anchorage to the underlying substrate.

Despite reduced substrate adhesion, detached sheets maintained structural integrity and viability, indicating preservation of cohesive cell–cell and cell–ECM interactions. These findings support a model in which prolonged high-glucose culture shifts the adhesion balance from substrate-dependent attachment toward ECM-supported tissue cohesion. As ECM maturation progresses, cell–substrate adhesion falls below a critical threshold, ultimately enabling spontaneous sheet release while preserving tissue integrity.

Collectively, this work establishes a cell-directed and material-free approach for generating transferable ECM-rich cell sheets using standard culture platforms. The proposed adhesion reprogramming mechanism provides new insight into scaffold-free tissue assembly and offers a simple strategy for regenerative medicine, tissue manufacturing, and cell-sheet-based biofabrication.

Keywords: Cell sheet engineering, adhesion reprogramming, extracellular matrix maturation, focal adhesion kinase, scaffold-free tissue assembly

References

[1]Haraguchi Y., Shimizu T., et al. Fabrication of functional three-dimensional tissues by stacking cell sheets in vitro. *Nat Protoc* 2012; 7; 850-858.
[2]Kobayashi J., Kikuchi A., Aoyagi T., Okano T. Cell sheet tissue engineering: Cell sheet preparation, harvesting/manipulation, and transplantation. *J Biomed Mater Res A* 2019; 107; 955-967.
[3]Chen W., Nie M. et al. Tailoring cell sheets for biomedical applications. Smart Med 2024; 3; e20230038.
[4]Mitra S.K., Hanson D.A., Schlaepfer D.D. Focal adhesion kinase: in command and control of cell motility. *Nat Rev Mol Cell Biol* 2005; 6; 56-68.
[5]Hynes R.O. Integrins: bidirectional, allosteric signaling machines. *Cell* 2002; 110; 673-687.
[6]Lamers M.L., Almeida M.E.S., et al. High glucose-mediated oxidative stress impairs cell migration. *PLos One* 2011; 6; e22865.
[7]Zhao X.K., Cheng Y., et al. Focal adhesion kinase regulates fibroblast migration via integrin beta-a and plays a central role in fibrosis. *Sci. Rep* 2016; 6; 19276.

D1 – P137

Enhancing bone regeneration in femoral critical-size defects using regulatory T cells

Dederen A.[1,2], Nasello G.[1,2], Verbraeken T.[1,2], Bosmans K.[1], Ricciardi C.[1,3], Borgiani E.[2,4], Geris L. [1,2,4]
[1]Skeletal Biology and Engineering Research Center, KU Leuven, Leuven; [2]Division Prometheus - Skeletal Tissue Engineering Leuven, KU Leuven, Leuven; [3]Dept. of Engineering, University of Messina, Messina, Italy; [4]BioMechanics (BMe), KU Leuven, Leuven, Belgium

Introduction

Critical-size bone defects represent a major clinical challenge due to their limited intrinsic healing capacity and the presence of persistent immune dysregulation. Current therapeutic strategies fail to restore immune homeostasis and are often associated with broad immunosuppression and adverse effects. Localized delivery of regulatory T cells (Tregs), key mediators of immune tolerance, has emerged as a promising immunomodulatory approach to promote tissue regeneration.

Aim

This study aimed to evaluate whether localized delivery of *in vitro* induced regulatory T cells (iTregs) can enhance bone regeneration in a murine femoral critical-size defect model.

Materials and Methods

Naive murine $CD4^+$ T cells were isolated and differentiated *in vitro* into iTregs, which demonstrated the Treg phenotype and a potent immunosuppressive capacity in functional immunosuppression assays by inhibiting $CD8^+$ T cell proliferation. To enable localized delivery *in vivo*, iTregs were incorporated into cylindrical collagen hydrogels and implanted into a surgically created murine femoral critical-size defect model. Outcomes in bone healing, were assessed after 21 days using micro-computed tomography (µCT) and (immuno)histological analysis. In addition, immune responses at the inguinal lymph nodes were evaluated using histological analysis.

Results

After induction, by anti-CD3/CD28 activation in TGF-β and IL-2 supplemented medium, the iTregs showed a robust Treg phenotype (84.38% ± 10.23% $CD25^+Foxp3^+$ cells) and a dose-dependent suppression of $CD8^+$ T cell proliferation, indicating their immunosuppressive capacity. *In vivo*, localized delivery of iTregs using collagen hydrogels proved to be technically feasible and resulted in a trend toward improved bone healing, as indicated by a reduced defect size and increased mineralized tissue compared to controls. Histological analyses suggested increased cartilage formation, alterations in immune cell distribution and changes in draining lymph node morphology, indicative of local immunomodulatory activity, after localized iTreg delivery. Despite these promising observations, no statistically significant enhancement of bone regeneration was achieved under the tested conditions.

Conclusion

In conclusion, this study demonstrates that localized delivery of functional iTregs is feasible and results in biological changes in a critical-size defect environment but does not significantly improve bone regeneration at the evaluated time point. These findings highlight key challenges related to timing, cell stability, and complex immune interactions. Future studies should focus on optimizing delivery strategies, evaluating earlier and later time points, and exploring combinatorial approaches with regenerative cell populations such as skeletal progenitors.

D1 – P138

A high-resolution approach to visualize subcellular interface biology in opaque biomaterials with defined topographies

Mathur A.K.[1], Fratila-Apachitei E.L.[1], Zadpoor A.A.[1], Tas R.P.[1]
[1]Dept. Biomechanical Engineering, Delft University of Technology (TU Delft), Delft, The Netherlands

Introduction

In recent years, the early-phase interactions of preosteoblasts with titanium implant surfaces have attracted increasing attention because surface topography has been shown to directly influence cellular responses. A better understanding of which specific surface features elicit favourable cellular responses could impact design strategies to promote bone growth and implant integration. However, simultaneously resolving the subcellular organizational dynamics within the complex multiscale topographical landscapes of 3D printed titanium surfaces has remained challenging.

Aim

Here we aim to develop a fast, efficient, and advanced imaging approach capable of enabling volumetric, high-resolution, and simultaneous acquisition of opaque, impervious biomaterials and subcellular components, thereby expanding our current understanding of biointerfaces.

Materials and Methods

To achieve this, we employed a confocal-based imaging approach and developed a probe that labels surface topography of 3D printed Ti6Al4V substrates while simultaneously acquiring confocal images of multiple stained subcellular components of fixed MC3T3-E1 preosteoblasts cultured on the substrates. Using this approach, we successfully reconstructed scanning electron microscopy (SEM)-comparable two-dimensional surface representations while also capturing 3D cellular–biomaterial interactions that conventional SEM techniques cannot resolve.

Results

Our results suggest that heterogeneity in topographical features introduced by different 3D printing profiles leads to distinct temporal and spatial patterns of cellular organization, likely driven by varied physical cues propagated through the Ti6Al4V interface.

Conclusion

These findings establish a novel imaging method that enables the simultaneous acquisition of Ti6Al4V surface topography and multiple stained subcellular components, allowing three-dimensional reconstruction of the cell-material interface. Furthermore, the 3D capability provides deeper insight into how cells navigate the complex topographies of 3D-printed Ti6Al4V surfaces. Overall, these new insights can provide new cues for biomaterial implant surface designs that enhance cellular interaction and integration, overall impacting implant performance.

D1 – P139

Thermo-adaptive hydrogels for dynamic mechanical stimulation of encapsulated chondrocytes in cartilage engineering

van de Looij S.M.[1], Vasilopoulou A.G.[2], Di Marco G.[1], Aksu T.[1,2], Ciccarelli I.[1], Mihăilă S.M.[3], Korpershoek J.V.[2,4], Malda J.[2,4], van Ravensteijn B.G.P.[1], Vermonden T.[1]

[1]Division of Pharmaceutics, Utrecht University, Utrecht, The Netherlands; [2]Dept. of Orthopaedics, University Medical Centre Utrecht, Utrecht; [3]Division of Pharmacology, Utrecht University, Utrecht; [4]Dept. of Clinical Sciences, Faculty of Veterinary Medicine, Utrecht University, The Netherlands

Introduction

With material characteristics that can easily be tuned to mimic the natural tissue environment, hydrogels are interesting biomaterials for tissue engineering. Of particular interest are dynamic hydrogels that provide mechanical cues to encapsulated cells. As highly mechanosensitive cells, chondrocytes are known to respond to mechanical stimulation in native cartilage. In this research, we developed a thermoresponsive polymer by grafting chains of *N*-isopropylacrylamide (NIPAM) and 2-hydroxylethyl acrylate (HEA) onto a gelatin backbone, and methacrylating (Ma) the HEA groups. The resulting GelNHMa polymer was used to form hydrogels able to provide cyclic mechanical stimulation to encapsulated Articular Cartilage Progenitor Cells (ACPCs) by repeated shrinking and swelling of the material over time (Fig. 1).

Materials and Methods

GelNHMa was synthesised by grafting chains of NIPAM and HEA onto a bromine-modified gelatin backbone via an atom transfer radical polymerization (ATRP) reaction. Subsequent methacrylation of the HEA moieties yielded the photocrosslinkable polymer GelNHMa. Hydrogels were formed by photo crosslinking on ice, and shrunken by incubation at 37 °C for 24 hours. Cell compatibility was determined by encapsulating ACPCs and monitoring the cell viability and metabolic activity. The shrinking kinetics at 37 °C and swelling kinetics at room temperature (RT) were determined by measuring the hydrogel diameter at regular intervals. A mechanical stimulation cycle was defined as 3 hour swelling at RT followed by 20 hour shrinking at 37 °C (Fig. 2A).

Results

The shrinking extent and gel stability were tuned by adjusting the NIPAM/HEA chain lengths and the degree of methacrylation, respectively, yielding a hydrogel that shrinks up to 65% in volume at 37°C. ACPCs encapsulated in these gels showed good viability in the material, and did not show signs of cellular stress upon repeated shrinking and swelling of the material. Different regimen of swelling-shrinking cycles were then tested for their influence on chondrocyte differentiation and extracellular matrix deposition. Over a period of 29 days in culture, ACPCs were shown to produce cartilaginous ECM, with presence of glycosaminoglycans (Fig. 2B) and collagens (Fig. 2C) detected.

Conclusion

In this study, we developed a thermo-adaptive hydrogel based on the polymer GelNHMa. The material showed good stability, temperature-based shrinkability and cycleability. Encapsulated ACPCs showed good viability and functionality by producing cartilaginous ECM. Future experiments will include detailed investigations into mechanotransduction pathways that are activated upon cyclic stimulation.

Acknowledgements

We thank the Dutch Research council (NWO) for funding: LS-NeoCarE (NWA.1389.20.192) and VICI (18673).




Figure 1. Schematic overview of how thermo-adaptive GelNHMa hydrogels can be used to provide cyclic mechanical stimulation to encapsulated cells.




Figure 2. (A) Shrinking kinetics: a single stimulation cycle of GelNHMa hydrogels. (B) Histological analysis of the deposition of glycosaminoglycans and (C) collagens after 29 days in culture, when stimulated twice every week.

D1 – P140

Biomimetic engineered living hydrogels with tunable dynamics for cellular encapsulation and delivery

Dimech D.[1,2], Kupiec K.A.[1], Joglekar M.M.[1,2], Giselbrecht S.[2], Baker M.B.[1]
[1]MERLN Institute, Instructive Biomaterials Engineering (IBE), Maastricht University, Maastricht; [2] MERLN Institute, Cell Biology Inspired Tissue Engineering (cBITE), Maastricht University, Maastricht, The Netherlands

Introduction

The human body has a limited ability to repair large tissue defects, so external support is often needed. Local delivery of human mesenchymal stem cells, hMSCs, is a promising approach, but its therapeutic potential is still limited by poor cell retention, the need for repeated dosing, and the risk of off target effects. This creates a need for a material platform that can act as a localized cell depot while also giving control over when and how cells are released. Dynamic hydrogels are particularly interesting for this because their network connections can be adjusted over time, which may help support a more controlled and tailored release profile. In this work, we explored whether multivalent crosslinking within an oxidized alginate hydrogel could be used to influence network dissociation, and in turn tune degradation and cellular release while maintaining cell depot function.

Materials and Methods

Oxidized alginate and hydrogel crosslinkers were prepared and characterized, including the synthesis of aminooxy terminated bifunctional and multivalent PEG crosslinkers. Hydrogels were then formed using oxidized alginate with different combinations of bifunctional and multivalent crosslinkers, after which gelation kinetics and rheological behaviour were evaluated. hMSCs were encapsulated in the hydrogels to assess cell viability and behaviour during encapsulation. In parallel, we examined time dependent network weakening, hydrogel degradation, cell motility, cellular release kinetics, viability of released cells, and therapeutic activity. Statistical analysis was performed throughout.

Results

Changes in crosslinker composition led to clear differences in gelation and network behaviour in oxidized alginate hydrogels. Over time, the dynamic hydrogels showed network weakening, degradation, and cellular release, alongside changes in cell motility. Selected multivalent formulations maintained hMSC viability and supported cell behaviour during encapsulation. Together, these findings suggest that hydrogel network composition can be used to influence the cellular release profile.

Conclusion

We developed a multivalent crosslinked hydrogel in which network dissociation kinetics influence degradation and cellular release. Different hydrogel network combinations gave rise to distinct time dependent release profiles. These findings support multivalent hydrogel design as a useful strategy for cell depot applications and controlled cell delivery and provide a basis for the development of future responsive therapeutic materials with more advanced delivery functions.

D1 – P141

Fibrin-supported cardiac stem cell sheets for diabetic wound regeneration

Jung Y.[1], Han S.[2], Draugelyte G.[3], Park J.C.[1,2,3,*]
[1]Dept. of Biomedical Engineering, Yonsei University; [2]Dept. of Medical Device Engineering and Management, Yonsei University College of Medicine; [3]Dept. of Medical Science, Yonsei University College of Medicine, Seoul, Republic of Korea

Introduction

Chronic diabetic wounds remain a major clinical challenge due to impaired angiogenesis, persistent inflammation, and delayed tissue remodeling. While stem cell-based therapies offer promising regenerative potential, limited cell retention and survival at the wound site often hinder therapeutic efficacy. Cell sheet engineering preserves endogenous extracellular matrix and cell–cell junctions, thereby improving cell delivery and viability. Fibrin-based biomaterials provide a biocompatible matrix that supports structural stability and integration within the wound bed. Therefore, integrating fibrin matrices with cardiac stem cell (CSC) sheets may provide a promising platform for enhancing chronic wound repair.

Aim

To evaluate the feasibility and regenerative potential of fibrin-supported CSC sheets in a diabetic mouse model of excisional skin wounds.

Materials and Methods

Human CSCs were fabricated into cohesive sheets and integrated within a fibrin-based matrix to form hybrid constructs. Diabetes was induced in nude mice using streptozotocin (STZ), followed by the creation of full-thickness excisional skin wounds. The constructs were transplanted onto the wound surface immediately after injury. Wound healing responses were evaluated using histological and immunohistochemical analyses. Hematoxylin and eosin (H&E) staining and Masson's trichrome staining were performed to assess tissue morphology and collagen deposition. Immunohistochemical staining for CD31 and α-smooth muscle actin (α-SMA) was conducted to evaluate vascular structures and vessel maturation. Cytokeratin 14 (K14) and CD45 staining were used to examine epithelial regeneration and inflammatory cell infiltration.

Results

Preliminary histological observations indicated differences in tissue responses between treated and control wounds. Granulation tissue formation and collagen deposition were observed in the fibrin-supported CSC sheet group compared with control wounds. Immunohistochemical staining demonstrated the presence of CD31-positive vascular structures and α-SMA-positive vessels within the treated wound bed, suggesting vascular responses during the healing process. Quantitative analyses of epithelial regeneration (K14) and inflammatory cell density (CD45) are currently in progress.

Conclusion

Fibrin-supported CSC sheets demonstrated feasibility as a bioengineered platform for localized stem cell delivery in diabetic wound models. These preliminary findings suggest that integrating fibrin matrices with CSC sheets may support a regenerative microenvironment conducive to tissue repair.

Acknowledgements

This research was supported by the Korean Fund for Regenerative Medicine (KFRM) grant funded by the Korea government (the Ministry of Science and ICT, the Ministry of Health & Welfare) (code: KFRM RS2023-00215084).

D1 – P142

Preliminary in vivo assessment of PEGylated fibrin to fabricate engineered ovarian tissue

Dadashzadeh A.[1], Moghassemi S.[1], Storder S.[1], Felipe Ferreira Da Silva[1,2], Santos F.C.A.D.[3], Amorim C.A.[1,*]
[1]Pôle de Recherche en Physiopathologie de la Reproduction, Institut de Recherche Expérimentale et Clinique, Université Catholique de Louvain, Brussels, Belgium; [2]Laboratory of Biotechnology and Physiology of Reproduction, Federal University of Ceara, Sobral, State of Ceará, Brazil; [3]Laboratory of Microscopy Applied to Reproduction, Dept. of Histology, Embryology and Cell Biology, Institute of Biological Sciences, Federal University of Goiás, Goiânia, Goiás, Brazil

Introduction

Fertility preservation remains a major challenge for female cancer patients, particularly those at high risk of ovarian metastasis. Bioengineered ovaries have emerged as a promising approach, aiming to recreate a functional ovarian microenvironment through biomaterial-based support of follicles and stromal cells.[1] We previously developed a PEGylated fibrin hydrogel with mechanical properties tailored to the human ovarian cortex, supporting survival and development of isolated human preantral follicles in vitro.[2,3] Building on these findings, this study aims to evaluate its in vivo performance and test whether controlled delivery of basic fibroblast growth factor (bFGF) via liposomes enhances graft survival and integration. We hypothesized that sustained bFGF release would improve cell viability and reduce hypoxia compared to free bFGF or non-functionalized constructs.

Materials and Methods

Human ovarian stromal cells were encapsulated in a PEGylated fibrin hydrogel (PF10:1) forming the core construct. To enable functionalization without compromising core properties, constructs were either left uncoated (Core-Shell) or surrounded by hydrogel shells (PF10:1 (Core+PF10:1) or PF5:1 (Core+PF5:1), with or without blank liposomes, free bFGF, or liposomal bFGF (bFGF@Lip). Constructs were transplanted subcutaneously into nude mice (n=4) and retrieved after 7 days. Grafts were analyzed for cell density, extracellular matrix deposition, immune cell infiltration (CD11b), endothelial cells (CD31), proliferation (Ki67), hypoxia (Ca9), and apoptosis (Annexin V).

Results

Transmission electron microscopy confirmed that the liposomes were spherical and well dispersed. bFGF-loaded liposomes exhibited nanoscale size with good homogeneity, with a mean diameter of 135.80±17.90 nm, a polydispersity index of 0.29±0.04, a zeta potential of –11.66±2.73 mV, and an encapsulation efficiency of 78.54±0.53%. In vitro release studies demonstrated sustained bFGF release, reaching approximately 30% after 24h in PBS at 37°C, while storage stability was maintained for up to 3 months at −20°C without significant loss of encapsulation efficiency (Fig.1).

In vivo, the bFGF@Lip group exhibited significantly higher cell density (cells per mm^2, 627±112.62), than the Core-Shell (185±106.75%; $p<0.05$), Core+PF10:1 (210±98.53%; $p<0.05$), and Core+PF5:1 groups (214± 58%; $p<0.05$), indicating enhanced graft survival. This was accompanied by reduced Annexin V expression. Collagen deposition and CD11b-positive cell infiltration were similar among groups (Fig. 2), as well as Ki67-positive cells. CD31 staining revealed no detectable vascularization in any condition after 7 days. The Ca9 expression was higher in Core+PF5:1 (56.48±9.83%) and Core+PF10:1 (52.78±8.99%) compared to Core-Shell (37.43±5.98%; $p>0.05$), blank liposomes (33.68±9.68%; $p>0.05$), free bFGF (18.19±4.57%; $p<0.05$), and bFGF@Lip (19.33±5.13%; $p<0.05$).

Conclusion

Controlled delivery of bFGF via liposomes improves early graft survival by reducing hypoxia and apoptosis, but remains insufficient to induce vascularization. These findings highlight the value of sustained growth factor delivery in engineered ovarian constructs and support the need for combinatorial strategies, including additional pro-angiogenic cues, to achieve functional tissue integration. This platform represents a promising step toward the development of bioengineered ovarian grafts for fertility preservation and endocrine restoration.

Acknowledgements
This study was supported by grants from the Fonds de la Recherche Scientifique (grant FC 51543 awarded to A.D. and grant FC 46825 awarded to S.M.).




Figure 1. Characterization of bFGF-loaded liposomes. TEM images of (a) blank liposomes and (b) bFGF-loaded liposomes. DLS analysis showing size distribution of (c) blank and (d) bFGF-loaded liposomes. (e) In vitro release profile of bFGF over 24 hours in PBS at 37 °C (mean±std; n=3). (f) Storage stability of bFGF-loaded liposomes based on entrapment efficiency (EE%) after storage at -20 °C for up to three months (mean±std; n=3).




Figure 2. Representative images of (a) Masson's trichrome staining of grafted hydrogels, shown as overview, center, and edge regions. (b) Immunostaining for CD11b indicating immune cell infiltration. Quantitative analysis of (c) fibrotic capsule thickness (mean ± SD; n = 4) and (d) CD11b expression (mean ± SD; n = 3). Scale bars: 500 µm (overview) and 100 µm (center, edge, and CD11b).

References

[1]Dadashzadeh S., Moghassemi A., Shavandi C.A., Amorim A. review on biomaterials for ovarian tissue engineering. *Acta biomaterialia* 2021; 135; 48–63.
[2]Dadashzadeh A., Moghassemi S., Peaucelle A., Lucci C.M., Amorim C.A. Mind the mechanical strength: tailoring a 3D matrix to encapsulate isolated human preantral follicles. *Human reproduction open* 2023; 2023(2); p.hoad004.3.
[3]Dadashzadeh A., Moghassemi S., Amorim C.A. Evaluation of PEGylated fibrin as a three-dimensional biodegradable scaffold for ovarian tissue engineering. *Materials Today Chemistry* 2021; 22; p.100626.

D1 – P143

ATMP classification challenges illustrated through a spinal cord injury biomaterial–cell combination case

Duarte L.[1,2,*], Castellà M.[4], Marques P.A.A.P.[1,3], Gago B.[3]
[1]TEMA - Centre for Mechanical Technology and Automation, Dept. of Mechanical Engineering, University of Aveiro, 3810-193 Aveiro, Portugal; [2]iBiMED - Institute of Biomedicine, Dept. of Medical Sciences, University of Aveiro, Portugal; [3]LASI – Intelligent Systems Associate Laboratory, Portugal; [4]Development and writing unit, Asphalion, Barcelona, Spain

Introduction

The process of determining how Advanced Therapy Medicinal Products (ATMPs) should be classified under European regulatory rules is often complex, particularly for therapies that pair biomaterials with living cells, such as those being developed for spinal cord injury (SCI). Although research in this field continues to show considerable promise, many candidates fail to advance toward clinical testing because developers (especially within academic settings) face uncertainty about the appropriate regulatory category for their products.

Materials and Methods

This review synthesizes the regulatory principles guiding the classification of ATMPs within the European Union, with emphasis on tissue-engineered products (TEPs). To structure this analysis, we examined the key concepts used by regulators: namely, the primary mechanism of action, the extent of tissue or cell manipulation, and the intended clinical role of the product. These criteria were evaluated across EU legislation, EMA guidance documents, and relevant scientific literature.

To demonstrate how these principles apply in practice, we assessed 1394UA, an amniotic membrane–derived extracellular matrix hydrogel combined with induced neural stem cells. This case example illustrates challenges faced when classifying complex biomaterial–cell combination products.

Results

Our analysis shows that determining the regulatory category of therapies such as 1394UA requires careful interpretation of the interplay between biological activity and structural function. In this case, the hydrogel provides a supportive matrix, whereas the incorporated neural stem cells drive the therapeutic effect, which makes the the definition of the principal mode of action a central factor in the classification process.

Applying the EU's ATMP decision-making framework revealed that early classification of 1394UA has consequences. The designation influences the design of quality control systems, expectations for non-clinical evidence, and the overall clinical development strategy. This case demonstrates how timely regulatory assessment can guide development more efficiently and reduce uncertainty for future translational steps.

Conclusion

Establishing the regulatory status of a product at an early stage is essential for minimizing uncertainty throughout development, particularly for academic teams working with sophisticated combinations of biomaterials and living cells. When developers understand the regulatory criteria that apply to their product and ensure its characteristics align with the correct ATMP category, they are better equipped to design coherent and realistic translational plans. This review aims to facilitate that process by offering practical insights that help embed regulatory considerations into the earliest phases of ATMP development for SCI and related therapeutic areas.

Acknowledgements

This work was funded by FEDER - Fundo Europeu de Desenvolvimento Regional funds through the COMPETE 2030 in the framework of the project COMPETE2030-FEDER-00744900.The authors gratefully acknowledge the support provided by national funds from FCT – Fundação para a Ciência e a Tecnologia, I.P., under the projects UID 00481/2025, Centre for Mechanical Technology and Automation (TEMA), https://doi.org/10.54499/UID/00481/2025 and UID/04501/2025, Institute of Biomedicine (iBiMED, https://doi.org/10.54499/UID/04501/2025, both from the University of Aveiro. We extend our sincere thanks to Asphalion for facilitating expert input.

D1 – P144

A structured risk-management approach in preclinical ATMP development: Insights from a spinal cord injury biomaterial case study

Duarte L.[1,2,*], Castellà M.[4], Marques P.A.A.P.[1,3], Gago, B.[3]
[1]TEMA - Centre for Mechanical Technology and Automation, Dept. of Mechanical Engineering, University of Aveiro, 3810-193 Aveiro; [2]iBiMED - Institute of Biomedicine, Dept. of Medical Sciences, University of Aveiro, Portugal; [3]LASI – Intelligent Systems Associate Laboratory, Portugal

Introduction

Early recognition of safety challenges is essential for the successful development of ATMPs for spinal cord injury (SCI). To support this, we established a structured approach to preclinical risk assessment, enabling consistent prioritization of key risks in emerging ATMP candidates.

Materials and Methods

We first performed a targeted literature search (2019–2025) in PubMed, Scopus, and Web of Science to map recurrent safety issues relevant to ATMP development. The evidence base consistently pointed to concerns such as immune reactivity, tumorigenic potential, procedure-related tissue damage, degradant toxicity, sterility assurance, and limitations in animal model relevance.

Guided by these findings, we then implemented a Failure Mode, Effects and Criticality Analysis (FMECA) for a representative case product, 1394UA, a placenta-derived, methacryloyl, photocrosslinkable hydrogel scaffold. During a cross-disciplinary workshop, experts independently rated each failure mode on Severity (S), Occurrence (O), and Detectability (D) using 1–5 scales, and we calculated Risk Priority Numbers (RPN = S × O × D) to rank and triage the most consequential risks.

Results

FMECA ranking highlighted toxicity-related hazards as the most urgent issues to address, alongside several additional medium-to-high priority failure modes. For items with RPN ≥ 50, we defined concrete mitigations, including validated GC/HPLC procedures to quantify residual solvents/monomers, standardized qPCR to measure residual DNA, and explicit endotoxin and sterility criteria to reinforce microbiological quality.

Conclusion

By combining insights from the literature with regulatory guidance and input from experts across different fields, this approach offers a systematic but flexible method for reducing preclinical risks in ATMP development. Iterative re-scoring after implementing targeted controls is expected to lower residual risk, strengthen regulatory alignment, and facilitate progression of SCI ATMP candidates toward clinical testing.

Acknowledgements

This work was funded by FEDER - Fundo Europeu de Desenvolvimento Regional funds through the COMPETE 2030 in the framework of the project COMPETE2030-FEDER-00744900.The authors gratefully acknowledge the support provided by national funds from FCT – Fundação para a Ciência e a Tecnologia, I.P., under the projects UID 00481/2025, Centre for Mechanical Technology and Automation (TEMA), https://doi.org/10.54499/UID/00481/2025 and UID/04501/2025, Institute of Biomedicine (iBiMED, https://doi.org/10.54499/UID/04501/2025, both from the University of Aveiro. We extend our sincere thanks to Metatissue and Paracelsus Medizinische Privatuniversität (PMU) for the support during the risk assessment process.

D1 – P145

Development of an iPSC-derived foetal liver-like niche in a chemically defined hydrogel for the assessment of HSC homing and expansion

Brice C.[1], Gueye M.[1], Nùnez Bernal P.[1], Rezvani M.[2], Levato R.[1]
[1]Regenerative Medicine Centre Utrecht, University Medical Centre Utrecht and Utrecht University, Utrecht, The Netherlands; [2]Dept. of Pediatric Gastroenterology, Nephrology and Metabolic Medicine, Charité – Universitätsmedizin Berlin, Germany

Introduction

Most in vitro haematopoietic models focus on recreating the adult bone marrow niche, however, the foetal liver serves as a critical reservoir for definitive haematopoietic stem cell (HSC) expansion prior to bone marrow colonisation. A recently established protocol[1] demonstrated the development of an induced pluripotent stem cell (iPSC)-derived foetal hepatic–haematopoietic niche, relying on Matrigel for 3D maturation and self-organisation. Replacing Matrigel with a fully defined and printable hydrogel would enable greater control over niche architecture and would allow investigation of how tissue organisation influences HSC behaviour.

Aim

To investigate the use of HybriGel, a gelatine-derived covalent-supramolecular biomaterial shown to support organoid proliferation and cell migration[2], as a platform for the development of a foetal liver niche for HSC culture.

Materials and Methods

After initiation of the differentiation protocol, at the 2D-to-3D transition, clusters of cells were embedded in HybriGel or Matrigel (as the gold-standard control). Resulting morphologies and spatial structure were evaluated using brightfield and immunofluorescence (IF) imaging, and emerging cell populations were quantified by fluorescence-activated cell sorting (FACS). Additionally, through IF imaging and FACS, the model was evaluated for its capacity to support homing and expansion of donor CD34+CD38- haematopoietic stem and progenitor cells (HSPCs), both when using HybriGel- or Matrigel-derived niches. (*Fig1A*)

Results

Brightfield imaging and cell cluster morphology analysis showed that differentiating cells embedded in HybriGel produced hepatocyte, hepatobiliary, and cholangiocyte organoids, as well as mesenchymal stromal cells and red blood cells (*Fig1B*). Evaluation of HybriGel variants with different stiffness and viscoelastic properties revealed that softer matrices were associated with increased cell death and fragment dissociation, indicating that matrix mechanics influence niche stability during differentiation. FACS analysis demonstrated no significant differences in major cell populations between Matrigel and HybriGel, confirming that our fully chemically defined gel could be used as Matrigel replacement to support this factor-free differentiation stage. Donor-derived $CD34^{+}CD38^{-}$ cells seeded together with the foetal liver niches demonstrated homing within the 3D environment and exhibited early expansion, with an increase in the proportion of committed progenitor cells (*Fig1C*).

Conclusion

These findings support HybriGel as a tunable, fully defined platform for foetal liver niche engineering, enabling more reproducible and mechanistic studies of human HSPC-niche interactions, with next steps focusing on leveraging its printability to fabricate perfusable architectures for dynamic culture and expansion of HSPCs.




Figure 1. A. Schematic overview of the FLO differentiation workflow, starting from naïve iPSCs at day 0, embedding clusters of cells into 3D matrices (Matrigel or HybriGel) at day 6, followed by the subsequent factor-free differentiation resulting in niches that were further used for testing with donor haematopoietic stem and progenitor cells (HSPCs). B. Brightfield images of the niches at day 21, revealing a heterogenous population of cells and red blood cell colony apparition. C. Brightfield and immunofluorescent images of the niches after seeding fluorescently labelled HSPCs, revealing homing and retention of the HSPCs. All scale bars represent 500 µm.

References

[1]Rezvani M., et al. Modeling immune lineage co-development in human pluripotent stem cell-derived liver organoids. *Journal of Hepatology* 2025; S0168-8278(25); 02657-1.
[2]Falandt M., et al. Hybrid supramolecular-covalent bioresin promotes cell migration and self-assembly in light-based volumetric bioprinted constructs. *bioRxiv 2025*.

D1 – P146

Electrophoretically deposited collagen films containing human dermal fibroblast- and human dermal microvascular endothelial cells support angiogenesis

Wai S.Y., Bax D.V., Cameron R.E., Best S.M.
Dept. of Materials Science and Metallurgy, University of Cambridge, Cambridge, UK

Introduction

Electrophoretic deposition (EPD) is a rapid and versatile technique that enables the assembly of collagen into multilayered films under an applied electric field[1]. Recent advances have demonstrated that EPD can be used to fabricate cell-containing collagen films, providing precise control over film architecture and short processing times[2]. EPD can be performed either directly onto an electrode (on-electrode deposition) or onto a suspended membrane (off-electrode deposition). However, it remains unclear whether cells embedded within the collagen matrix can effectively communicate with cells in adjacent layers. Fibroblasts are known to promote angiogenesis through extracellular matrix (ECM) remodelling and paracrine signalling[3]. In this study, we investigated whether human dermal fibroblasts (HDFs) embedded within EPD-deposited collagen films can interact with human dermal microvascular endothelial cells (HDMECs) seeded on the surface and promote angiogenesis in a layered co-culture system.

Materials and Methods

HDF-containing collagen films were fabricated using both on-electrode and off-electrode EPD (Fig. 1). Cell viability within the films was assessed using live/dead staining to compare the effects of deposition methods. To evaluate interlayer interaction, HDMECs were seeded as a concentrated droplet onto the surface of the HDF-collagen films to establish a layered co-culture system. The films were cultured for four days. After culture, samples were fixed with 4% paraformaldehyde and immunostained for platelet endothelial cell adhesion molecule-1 (PECAM-1) to visualise endothelial cell-cell junctions. Nuclei were counterstained with DAPI, and two-photon imaging was used to assess endothelial cell morphology and organisation.

Results

Live/dead staining demonstrated that off-electrode deposition resulted in a more consistent and viable HDF distribution throughout the film, but with fewer total cells deposited due to reduced densification (Fig. 2a). In endothelial cell monoculture on collagen film, HDMECs formed a confluent and uniform cobblestone monolayer, characterised by continuous PECAM-1 staining at cell-cell junctions. In contrast, HDMECs cultured on HDF-containing EPD films exhibited elongation and alignment, assembling into vessel-like structures with localisation of PECAM-1 staining, which are characteristic of angiogenic tube formation (Fig. 2b). Despite the dense structure of the EPD films, the embedded HDFs were able to influence endothelial cell behaviour, suggesting effective interlayer communication. This capillary-like organisation was observed in films fabricated using both deposition methods, but no significant difference in tube formation was observed (Fig. 2b).

Conclusion

Off-electrode deposition provides more consistent fibroblast viability, while both on- and off-electrode films support endothelial remodelling and comparable angiogenic organisation. These findings demonstrate that dense EPD-deposited collagen membranes enable interlayer cellular crosstalk for layered tissue engineering applications.

Acknowledgements

The authors would like to thank St John’s College, Cambridge for providing financial support to this project.




Figure 1. Experimental design and variables investigated in this study. Collagen-only or HDF-collagen suspensions were prepared and subjected to either on-electrode or off-electrode EPD to fabricate collagen films. In the on-electrode deposition, collagen and HDFs were deposited directly onto the electrode, whereas in the off-electrode deposition, the co-deposition occurred on a suspended collagen membrane positioned between the electrodes. Following film fabrication, HDMECs were seeded onto the surface of the films on the side furthest from the substrate for either HDMEC monoculture or HDF/HDMEC co-culture conditions, with HDF-only films serving as controls. Samples were cultured for 4 days and subsequently stained for PECAM-1 (endothelial cell-cell junctions) and DAPI (cell nuclei), followed by two-photon imaging to assess endothelial cell morphology and organisation.




Figure 2. a) Number of cells per image volume for different film samples, and distributions of live and dead cells as a function of distance from the film surface following a 6-min deposition at a direct voltage of 30 V. Off-electrode deposition results in a more consistent and viable HDF distribution throughout the film, but with fewer total cells deposited compared to on-electrode deposition due to reduced densification. b) Representative two-photon images of HDF-only control, HDMEC monoculture and HDF/HDMEC co-culture stained for PECAM-1 (endothelial cell-cell junctions) and DAPI (nuclei). For both on- and off-electrode depositions, HDMEC monoculture on collagen films forms a confluent cobblestone monolayer, whereas in co-culture with HDF-containing films, HDMECs exhibit elongation and alignment to form vessel-like structures, indicating endothelial remodelling and angiogenic tube formation.

References

[1]Barrett D.J., Linley M.D., Best S.M., Cameron R.E. Fabrication of free standing collagen membranes by pulsed-electrophoretic deposition. *Biofabrication* 2019; 11(4); p.045017. doi:https://doi.org/10.1088/1758-5090/ab331d.
[2]Bonfield J. Production of Multi-layer and Cell-Containing Collagen Membranes Using Direct Electrophoretic Deposition. *Apollo - University of Cambridge Repository* 2025. doi:10.17863/CAM.117921.
[3]Costa-Almeida R., Gomez-Lazaro M., Ramalho C., Granja P.L., Soares R., Guerreiro, S.G. Fibroblast-Endothelial Partners for Vascularization Strategies in Tissue Engineering. *Tissue Engineering Part A* 2015; 21(5-6); 1055–1065. doi:https://doi.org/10.1089/ten.tea.2014.0443.

D1 – P147

Mechanics-informed design rules for modular vascular tissue engineering

Lizar M.[1]*, Ma X.[1]
[1]The Key Laboratory of Biorheological Science and Technology, Ministry of Education, College of Bioengineering, Chongqing University, Chongqing 400044, China

Introduction

The development of perfusable vascular networks remains a major bottleneck in modular tissue engineering, as most bottom-up biofabrication strategies rely on empirical selection of geometry, material properties, and assembly parameters. Although recent modular vascular constructs have demonstrated improved perfusion and biological performance, the absence of predictive mechanical design principles continues to limit reproducibility, scalability, and functional robustness. In particular, biomechanical factors such as flow-induced shear stress, structural deformation, and inter-module mechanical compatibility are often evaluated only after fabrication, rather than being used to guide design decisions upfront.

Aim

The aim of this study is to establish a mechanics-informed design framework for modular vascular tissue engineering in which biomechanical parameters are incorporated as pre-fabrication design constraints rather than post-hoc analytical metrics.

Materials and Methods

A computational–experimental framework was developed by integrating fluid–structure interaction (FSI) modeling with modular vascular biofabrication workflows. Parametric FSI simulations were performed to evaluate the coupled effects of vascular geometry, material compliance, and perfusion conditions on wall shear stress distributions, structural deformation, and inter-module mechanical compatibility. Based on simulation outputs, mechanically favorable regimes were identified and translated into quantitative design rules. These rules were then applied to the fabrication of modular vascular elements using tunable, cell-instructive biomaterials and controlled perfusion systems. Experimental evaluation focused on early-stage biological and functional indicators to enable direct comparison with predicted mechanical environments.

Results

FSI simulations revealed distinct mechanical regimes associated with uniform perfusion, reduced structural mismatch, and physiologically relevant shear stress levels. Design rules derived from these simulations guided the fabrication of modular vascular constructs that exhibited improved perfusion homogeneity and enhanced endothelial stability compared to empirically designed counterparts. Experimental observations of endothelial viability, alignment, and perfusion uniformity were consistent with the predicted mechanical conditions, supporting the validity of the mechanics-informed design approach (Figure 1).

Conclusion

This study demonstrates that integrating biomechanics into the early design stage enables a transition from heuristic modular vascularization toward predictive engineering. By redefining fluid–structure interaction metrics as design constraints, the proposed framework provides a generalizable strategy for constructing mechanically optimized, perfusable vascular modules. This approach has direct implications for modular tissue engineering, organ-on-chip systems, and scalable bottom-up tissue assembly.

Acknowledgements

This work did not receive specific external funding.




Figure 18 Mechanics-Informed Design Framework for Modular Vascular Tissue Engineering

References

[1]Baeyens N., & Schwartz M. A. Biomechanics of vascular mechanosensation and remodeling. *Molecular biology of the cell* 2016; 27(1); 7–11. https://doi.org/10.1091/mbc.E14-11-1522

[2]Bazilevs Y., Takizawa K., Tezduyar T. E. Computational fluid–structure interaction: Methods and applications. *John Wiley & Sons* 2013. https://doi.org/10.1002/9781118483565

[3]Chaudhuri O., Cooper-White J., Janmey P. A., Mooney D. J., Shenoy V. B. Effects of extracellular matrix viscoelasticity on cellular behaviour. *Nature* 2020; 584(7822); 535–546. https://doi.org/10.1038/s41586-020-2612-2

[4]Daly A.C., Prendergast M.E., Hughes A.J., Burdick J.A. Bioprinting for the Biologist. *Cell* 2021; 184(1); 18–32. https://doi.org/10.1016/j.cell.2020.12.002

[5]Davies P.F. Hemodynamic shear stress and the endothelium in cardiovascular pathophysiology. Nature clinical practice. *Cardiovascular medicine* 2009; 6(1); 16–26. https://doi.org/10.1038/ncpcardio1397

[6]Engler A.J., Sen S., Sweeney H.L., Discher D.E. Matrix elasticity directs stem cell lineage specification. *Cell* 2006; 126(4); 677–689. https://doi.org/10.1016/j.cell.2006.06.044

[7]Holzapfel G. A., Ogden R. W. Biomechanics of soft tissue in cardiovascular systems. *Springer* 2003. https://doi.org/10.1007/978-3-7091-2736-0

[8]Humphrey J.D., Taylor C.A. Intracranial and abdominal aortic aneurysms: Similarities, differences, and need for a new class of computational models. *Annual Review of Biomedical Engineering* 2008; 10; 221–246. https://doi.org/10.1146/annurev.bioeng.10.061807.160439

[8]Kolesky D.B., Homan K.A., Skylar-Scott M.A., Lewis J.A. (2016). Three-dimensional bioprinting of thick vascularized tissues. *Proceedings of the National Academy of Sciences of the United States of America* 2016; 113(12); 3179–3184. https://doi.org/10.1073/pnas.1521342113

[9]Skylar-Scott M.A., Uzel S.G.M., Nam L.L., Ahrens J.H., Truby R.L., Damaraju S., Lewis J.A. Biomanufacturing of organ-specific tissues with high cellular density and embedded vascular channels. *Science advances* 2019; 5(9); eaaw2459. https://doi.org/10.1126/sciadv.aaw2459

[10]Zhang Y.S., Khademhosseini, A. Engineering in vitro human tissue models through bio-design and manufacturing. *Bio-des. Manuf.* 2020; 3; 155–159 (2020). https://doi.org/10.1007/s42242-020-00080-w

D1 – P148

Engineering a MASLD-liver fibrosis model recapitulating the liver microenvironment with collagen type I and alginate hydrogels

Carvalho A.M.[1,2,3], Sousa A.B.[1,2], Viegas J.[1], Bansal R.[3,4], Barrias, C.C.[1,5], Sarmento B.[1,6]
[1]i3S - Instituto de Investigação e Inovação em Saúde, Universidade do Porto, Porto, Portugal; [2]International Doctoral Program in Molecular and Cellular Biotechnology Applied to Health Sciences (BiotechHealth), ICBAS - Instituto de Ciências Biomédicas Abel Salazar, Universidade do Porto, Porto, Portugal; [3]Dept. of Gastroenterology and Hepatology, University Medical Center Groningen (UMCG), University of Groningen, Groningen, The Netherlands; [4]Dept. of General, Visceral and Transplantation Surgery, Universitätsklinikum Münster, University of Münster, Münster, Germany; [5]ICBAS - Instituto de Ciências Biomédicas Abel Salazar, Universidade do Porto, Porto, Portugal; [6]IUCS - Instituto Universitário de Ciências da Saúde, CESPU, Gandra, Portugal

Introduction

Metabolic dysfunction-associated steatotic liver disease (MASLD) is the most common etiology of chronic liver disease to-date, and is characterized by hepatic fat accumulation, inflammation and fibrosis. Lack of physiologically relevant models for drug testing that replicate human disease's features hinders the development of therapies for MASLD and liver fibrosis.

Aim

The goal of this work is to create an advanced in vitro model of human MASLD-fibrosis that can be employed for testing the safety and efficacy of antifibrotic drug candidates using a mechanically tunable hydrogel replicating the composition of the fibrotic liver extracellular matrix and embedding the most relevant hepatic cell types to mimic the liver microenvironment.

Materials and Methods

Our hydrogel is composed of 3 mg/mL collagen type I and 2% alginate, with gelification achieved by internal gelation of alginate using $CaCO_3$ and glucono-delta-lactone[1]. It was used for embedding hepatocytes (HepG2), hepatic stellate cells (LX-2), human hepatic sinusoidal endothelial cells (HHSECs), and primary M1 macrophages. On day three, hydrogels were stiffened by incubation with $CaCl_2$ or $BaCl_2$[2] and cultured for a total of seven days. Cell viability and proliferation were evaluated by Live/Dead and Ki-67 stainings. Model composition at the end of culture was characterized by confocal microscopy using CellTrackers™ and immunofluorescence staining of cell specific markers.

Results and Discussion

Our hydrogel presented tunable mechanical properties, with stiffness ranging from 753 Pa (no stiffening), 1090 Pa (stiffening with $CaCl_2$) up to 1755 Pa (stiffening with $BaCl_2$), mimicking the increase in stiffness observed in progressive liver disease. By day 7, cellular composition resembles the composition of the fibrotic liver: 50% HepG2, 30% LX-2, 15% M1 macrophages, and 5% HHSECs (Figure 1). For stiffer hydrogels, the number of HepG2 and HHSECs cells decreased, while LX-2 showed improved viability and proliferation across all hydrogel types (72% of $Ki67^+$ LX-2 cells vs 17% of $Ki67^+$ HepG2 and 8% of $Ki67^+$ HHSECs).

Conclusion

We were able to induce in our model essential features of human liver disease. To further increase the physiological relevance of the model, we are in the process of embedding in the hydrogel patient-derived human liver organoids differentiated towards hepatocytes and subjected to a MASLD stimulus[3]. These organoids will replace HepG2 in the co-culture with LX-2, HHSECs, and M1 macrophages inside the hydrogel to create a model that better resembles MASLD. We will also subject the model to antifibrotic drugs to evaluate its potential as a drug testing platform.

Acknowledgments

This work was funded by Gilead Sciences through the project FibHep: um modelo 3D in vitro de fibrose humana em hepatite (program Gilead GENESE 2024). A.M.C. acknowledges the financial support of Fundação para a Ciência e Tecnologia (2022.11341.BD) and of the IMMUNO-model COST action (CA21135).




Figure 1. Representative images of collagen type I and alginate hydrogels embedding HepG2, LX-2, HHSECs, and M1 macrophages. (A) Live/Dead assay, (B) and (C) immunofluorescence stainings. (A) Green: live cells; red: dead cells. (B) Cyan: EpCAM (HepG2), magenta: α-SMA (LX-2), yellow: UEA-I (HHSECs), blue: nuclei. (C) Cyan: EpCAM (HepG2), yellow: UEA-I (HHSECs), white: CD68 (M1 macrophages), blue: nuclei. Scale bars: 100 µm.

References

[1]Bidarra S.J., Oliveira P., Rocha S., Saraiva D.P., Oliveira C., Barrias C.C. A 3D in vitro model to explore the inter-conversion between epithelial and mesenchymal states during EMT and its reversion. *Scientific Reports* 2016; 6(1); 27072.
[2]Barros da Silva P., Zhao X., Bidarra S.J., Nascimento D.S., LaLone V., Lourenço B. N., Paredes J., Stevens M.M., Barrias C.C. Tunable Hybrid Hydrogels of Alginate and Cell-Derived dECM to Study the Impact of Matrix Alterations on Epithelial-to-Mesenchymal Transition. *Advanced Healthcare Materials* 2024; 13(29); 2401032.
[3]Li M., Larsen F.T., van den Heuvel M.C., Gier K., Gorter A.R., Oosterhuis D., Bijzet J., de Meijer V.E., Ravnskjaer K., Nagelkerke A., Olinga P. Metabolic Dysfunction-Associated Steatotic Liver Disease in a Dish: Human Precision-Cut Liver Slices as a Platform for Drug Screening and Interventions. *Nutrients* 2024; 16(5); 626.

D1 – P149

High-throughput screening of surface chemistries and topographies for macrophage immune modulation using the ChemoTopoChip platform

Gonzalez-Martinez N.[1], Du, Q.[1], Kämmerling L.[1], Sabri A.[2], Tuck B.[3], Sefton J.[3], Dubern J.[1], Figueredo G.P.[4], Irvine D.[3], Alexander M.R.[2], Ghaemmaghami A.M.[1]
[1]School of Life Sciences, Faculty of Medicine and Health Science, University of Nottingham; [2]School of Pharmacy, Faculty of Science, University of Nottingham; [3]Faculty of Engineering, University of Nottingham; [4]Centre for Health Informatics, School of Medicine, University of Nottingham, Nottingham, UK

Introduction

Adverse inflammatory responses to implanted medical devices are a major barrier to their success and could cause tissue damage[1]. Macrophages are key components of this so-called foreign body response, but these can play a key role in wound healing and device integration. Modifying the surface topography and/or chemistry of implanted biomaterials presents an opportunity to modulate macrophage polarisation by leveraging their phenotypic plasticity to promote a pro-healing, anti-inflammatory response. Here, we utilise the ChemoTopoChip to enable high-throughput screening of cellular responses to different topographies, surface chemistries and their combinations. We aim to discover clinically relevant immuno-instructive chemistry and topography combinations to implement into medical devices[3].

Materials and Methods

Microscale topographies were printed (by two-photon polymerisation) or cast in silanised glass slides using a diurethane dimethacrylate resin containing 1% of a trithiocarbonate reagent to functionalise with relevant immuno-modulatory polymer chemistries[2]. A commercially available microarray system (ProPlate®) was placed on the slides to adapt this device for macrophage cell culture, with separate wells to evaluate different conditions. Monocytes were isolated from healthy human donors by positive selection of CD14+ cells, differentiated into naïve macrophages by adding 10 ng/mL M-CSF and cultured for 6 days at 37 °C. Immunofluorescence staining was performed to assess macrophage polarisation by quantifying the surface expression of calprotectin and mannose receptor as markers for M1 and M2-like phenotypes, respectively. The immune modulation potential of topographies and chemistries was evaluated by comparing M2/M1 ratios to flat controls and/or unfunctionalised surfaces. Additionally, the number of total nuclei was quantified to evaluate surface attachment.

Results

To validate the high-throughput approach, a topography resembling a “dog-like” shape and previously shown to promote an M2-like phenotype was selected as a control to assess the robustness of the methodology. This showed consistent results in both datasets[1]. Currently, multiple topographies, chemistries, and their combinations are being evaluated in vitro. We screen for features promoting an anti-inflammatory macrophage phenotype, whilst discouraging bacterial attachment. After screening in separate cultures, candidates will be evaluated in vivo and in a bacterial-macrophage co-culture, to model infection after implantation. These “hits” are further evaluated using monocyte-derived macrophages from young and elderly donors, to establish whether there are any differences in macrophage immune modulation and plasticity in clinically relevant populations.

Conclusion

This in vitro study using the ChemoTopoChip will help inform the next-generation of machine learning-generated micro-topographies, surface chemistries and their combinations, as well as providing candidates for in vivo evaluation.

References

[1]Vassey M.J., Figueredo G.P., Scurr D.J., Vasilevich A.S., Vermeulen S., Carlier A., Luckett J., Beijer N.R.M., Williams P., Winkler D.A., de Boer J., Ghaemmaghami A.M., Alexander M.R. Immune Modulation by Design: Using Topography to Control Human Monocyte Attachment and Macrophage Differentiation. *Adv Sci (Weinh)* 2020; 7(11); 1903392.
[2]Rostam H.M., Fisher L.E., Hook A.L., Burroughs L., Luckett J.C., Figueredo G.P., Mbadugha C., Teo A.C.K., Latif A., Kämmerling L., Day M. Lawler, K.; Barrett, D.; Elsheikh, S.; Ilyas, M.; Winkler, D.A.; Alexander, M.R. and Ghaemmaghami, A.M. Immune-Instructive Polymers Control Macrophage Phenotype and Modulate the Foreign Body Response In Vivo. *Matter*, 2020; 2(6); 1564–1581.
[3]Burroughs L., Amer M.H., Vassey M., Koch B., Figueredo G.P., Mukonoweshuro B., Mikulskis P., Vasilevich A., Vermeulen S., Dryden I.L. Winkler D.A., Ghaemmaghami A.M., Rose F.R.A.J, de Boer J., Alexander M.R. Discovery of synergistic material-topography combinations to

achieve immunomodulatory osteoinductive biomaterials using a novel in vitro screening method: The ChemoTopoChip. *Biomaterials* 2021; 120740.

D1 – P150
Bioinspired wrinkle engineering of 2D materials and its applications

Zengyong C.
College of Science, National University of Defense Technology, Changsha, P.R. China

Introduction
Wrinkle is a common physical phenomenon in nature. Bionic artificial surface wrinkling has been developed as a universal surface structural method. Two-dimensional (2D) material is a new material system with a single atomic layer thickness represented by graphene. Due to the influence of thermodynamic fluctuations, 2D materials are inherently wrinkled. Associated with the increase in the curvature control factors caused by surface wrinkling, the surface wrinkling in two-dimensional materials is currently the new research topic.

Aim
Inspired by the wrinkling morphology of biological surfaces and the tendency of 2D materials to wrinkle, this report focuses on the methods, processes, properties, and applications of artificial wrinkling of two-dimensional materials on curved surfaces.

Material and Methods
Latex balloons were used as the substrates and graphene oxide (GO) dispersion (1.0 wt%) were used as the coatings. The aqueous GO suspension is rotation-dip-coated and air-dried on the surface of an inflated latex balloon, forming a thin and uniform GO coating. Highly Wrinkled-GO surfaces can be induced by deflating the air slowly.

Results
The wrinkling morphologies on core–shell spheres and cylinders have been simulated and selectively produced (Fig.1a). Beyond the film thickness, modulus ratio, and mismatch strain, the substrate curvature is one more significant parameter controlling the surface wrinkling. Emerging applications of the curved topographic patterns have been found in smart wetting surfaces, cell culture interfaces, healthcare materials, and actuators (Fig.1b).




Fig. 1 Bio-inspired wrinkling morphology of GO (a) and its applications (b).

Conclusion
Fundamental wrinkling mechanics and recent advances in both fabrications and applications of the wrinkling patterns on curved substrates are summarized. The mechanics behind the wrinkles is compared between the planar and the curved cases. Bioinspired wrinkle engineering of 2D materials may accelerate the development of artificial organs, stimuli-responsive devices, and micro/nano fabrications with higher dimensions.

D1 – P151

Preparation and characterization of GelMA/PEGDA hydrogel containing BG S53P4 for periodontal bone defect repair

Sirkiä SV.[1,2,3], Bruzell E.[1], Eqtesadi S.[1], Grutle L.[1], Croff Larsen S.[1], Samuelsen J-T.[1], Uhlig S.[1], Vallittu PK.[2,3]
[1]Nordic Institute of Dental Materials (NIOM), Oslo, Norway; [2] Dept. of Biomaterials Science and Turku Clinical Biomaterials Centre - TCBC, Institute of Dentistry, University of Turku, Turku, Finland; [3] Southwest Finland Wellbeing Services County, Finland

Introduction

Highly biodegradable and nutrient-permeable gelatin methacryloyl (GelMA), combined with the high mechanical strength and low degradation of poly(ethylene glycol) diacrylate (PEGDA), could form a feasible bone-filling material[1-2]. The hydrogel incorporating bioactive glass (BG) particles may enhance bone regeneration, angiogenesis, and osteoinductivity in the bone defect[3]. The dispersibility of BG particles and ability to form covalent bonds with the hydrogel matrix may be improved through particle silanization using γ-MPS (3-(methacryloyloxy)propyltrimethoxysilane)[4].

Materials and Methods

GelMA/PEGDA-based hydrogels with BG and with silanized BG were prepared in high ionc strength solution (PBS) and characterized physicochemically and biologically. Commercial GelMA and PEGDA materials were used in the study for comparison with literature. The physicochemical characterization included swelling, degradation, pH changes, compressive strength and surface SEM-EDX analyses, while the hydrogel was immersed in PBS. Additionally, the leaching of the photoinitiator (Irgacure 2959) and its degradation products were quantified by UHPLC–HRMS during hydrogel immersion. Biological characterization included human osteoblastic (SaOS-2) cell line viability with MTT test and IL-6 and IL-8 cytokine release.

Results

Particularly, the hydrogel groups were not significantly different with respect to the physicochemical quantification. The pH increases were similar in both bioactive glass-containing hydrogels independent of silanization. None of the photoinitiator degradation products were detected, only the photoinitiator itself, and its leaching was similar in both hydrogel groups (<130 μg/mL). In biological characterization, the high concentration of conditioned media (100-50%) resulted in decreased cell viability ($p<0.001$) compared with the negative control (0%), but good cell viability (>70%) was observed in low conditioned media (5-25%). The cytokine release was measured in the MTT test for all hydrogel groups, and the release was below the detection limit.

Conclusion

Hydrogels may be suitable as bone-filling materials, as a combination of an optimal biodegradable matrix with bioactive particles. The hydrogel itself is modifiable after polymerization and highly biodegradable, which could be suitable for periodontal bone-filling materials. In this study, the hydrogel incorporated with BG was prepared under a high-ion solution (PBS), which caused too high osmolarity. However, in the future the preparation should be made under physiological conditions.

Acknowledgements

The study was supported by NIOM visiting scientist program and the Business of Finland Co-Innovation Grant IMD1 11/31/2023.

References

[1]He J., Sun Y., Gao Q., He C., Yao K., Wang T., Xie M., Yu K., Nie J., Chen Y., He Y. Gelatin Methacryloyl Hydrogel, from Standardization, Performance, to Biomedical Application. *Adv Healthc Mater* 2023; 12; 2300395.
[2]Long J., Luo Y., Wang Y., Etxeberria A.E., Xing F., Li Z., Zhou Y., Lu M., Gong T., Sun Y., Min L., Fan Y., Tu C., Zhang X. Nanosilicate-reinforced GelMA-PEGDA hydrogel promotes angiogenesis for bone regeneration. *Int J Biol Macromol* 2024; 133202.
[3]Hench L.L. Bioceramics: From Concept to Clinic. *Journal of the American Ceramic Society* 1991; 74; 1487–1510.
[4]Chen H., Lin Y.M., Bupphathong S., Lim J., Huang J.E., Huang W., Hsieh T.A.S., Lin C.H. Synthesis of Silanized Bioactive Glass/Gelatin Methacrylate (GelMA/Si-BG) composite hydrogel for Bone Tissue Engineering Application. *J Mech Behav Biomed Mater* 2023; 147; 106159.

D1 – P153
Delivery of cells using innovative nanoclay gels for cartilage regeneration

Hosseinzadeh Z.[1], Dawson J.[1], Agnieszka J.[2], Oreffo R.[1], Sanchez R.R.[2]
[1]Dept.of Human Development and Health, University of Southampton; [2]Renovos Biologics Limited, Southampton, UK

Introduction

Osteoarthritis affects approximately 8% of the global population, creating a pressing need for minimally invasive and cost-effective strategies for cartilage repair. Cartilage regeneration remains challenging due to the tissue's limited self-healing capacity. While cell-based therapies have emerged as potential alternatives to joint replacement, inefficient cell delivery and poor cell retention remain major limitations, highlighting the need for biomaterials that offer both structural support and biochemical signals for improved cartilage repair. Synthetic nanoclays form biocompatible colloidal hydrogels with high surface area and dual-charged surfaces that promote protein adsorption and cell adhesion. Although nanoclay has been explored in several biomedical applications, its potential as a cell-encapsulation matrix for cartilage regeneration has not been widely investigated. Here, we evaluate nanoclay hydrogel–cell constructs as a tunable and cytocompatible platform for cartilage tissue engineering.

Materials and Methods

Nanoclay hydrogels were prepared and used as matrices for cell encapsulation. Primary human bone marrow stromal cells (hBMSCs) and human articular chondrocytes (HACs) were encapsulated within the hydrogels to evaluate cytocompatibility and suitability for cartilage regeneration. Cell viability following encapsulation was assessed using a Live/Dead assay over a 14-day culture period. To determine whether hydrogel stiffness affected cell survival, hBMSC viability was compared across the different nanoclay concentrations including 2.5%, 3%, and 3.5% (w/v).

Cartilage matrix formation and cellular morphology were evaluated through histological staining, including Alcian Blue/Sirius Red and Safranin O to detect glycosaminoglycan and collagen deposition. Immunohistochemical staining for SOX9 and collagen type II (COL2) was performed to assess chondrogenic phenotype and cartilage extracellular matrix production.

Results

Live/Dead assays demonstrated high cytocompatibility of the nanoclay hydrogels, with both hBMSCs and HACs maintaining greater than 90% viability after 14 days of encapsulation. Increasing nanoclay concentration (2.5–3.5%) did not significantly affect cell survival, indicating that hydrogel stiffness can be tuned without compromising cell viability.

Histological analyses revealed cartilage-like extracellular matrix formation within the constructs. Safranin O and Alcian Blue staining confirmed glycosaminoglycan production. Notably, 2.5% and 3.5% nanoclay hydrogels supported the formation of lacuna-like structures containing rounded chondrocytes, resembling native cartilage morphology. Immunohistochemical staining further showed positive expression of SOX9 and collagen type II, confirming maintenance of a chondrogenic phenotype and active cartilage matrix production.

Conclusion

Nanoclay hydrogels demonstrated excellent cytocompatibility and supported cartilage-like matrix formation following cell encapsulation. Importantly, the system allows tunable mechanical properties without negatively affecting cell viability, highlighting its potential as a versatile biomaterial platform for cell-based cartilage regeneration. These findings suggest that nanoclay-based hydrogels could provide a promising, minimally invasive strategy for cartilage repair.

D1 – P154

Polycaprolactone (PCL) fibers grafted with phosphatidylserine and Arg-Gly-Asp (RGD) for immunomodulation and enhanced osteogenesis

Yang H.-C., Yoon J.H.
Dept. Dental Biomaterials Science and Dental Research Institute, Seoul National University, Seoul, Republic of Korea

Introduction

Macrophages regulate the innate immune system and can be polarized into a pro-inflammatory M1 phenotype and anti-inflammatory M2 phenotype. M2 macrophages contribute to a favorable immune microenvironment for bone regeneration. Phosphatidylserine (PS), an “eat-me” signal of apoptotic cells, induces M2 polarization, while the RGD peptide, an integrin-binding motif of MFG-E8, further promotes M2 macrophage polarization. Therefore, incorporating PS and RGD into scaffolds may enhance immunomodulation and bone regeneration.
Aim. This study aimed to develop a PS-RGD-PCL fiber scaffold and evaluate its ability to induce M2 macrophage polarization and promote bone regeneration.

Materials and Methods

A PS-RGD-PCL fiber scaffold was fabricated by electrospinning a PCL (0.125 g/mL) solution containing PS (0.6 mM) and RGD-phosphoethanolamine. Surface morphology and fiber diameter were analyzed using scanning electron microscopy. M2 polarization of bone marrow-derived macrophages (BMDMs) cultured on the scaffolds was evaluated by measuring the expression of M2-associated genes (Arginase-1, TGF-β, and FIZZ1) using RT-qPCR. For in vivo evaluation, a rat calvarial defect model was used. Critical-sized defects (8 mm) were created in 8-week-old male Sprague-Dawley rats, and scaffolds were implanted into the defect sites. Bone volume/total volume (BV/TV) was assessed every two weeks using in micro-computed tomography. Immunohistochemical analysis was performed to assess macrophage responses in the soft tissue surrounding the defect area.

Results

Electrospun scaffolds exhibited uniform fibrous structures, with an average fiber diameter of 1.00 ± 0.18 μm for the PS-RGD-PCL scaffold. In vitro, the PS-RGD (3%)-PCL scaffold induced the strongest expression of M2 macrophage markers in BMDMs compared with the PCL and PS-PCL scaffolds. In the rat calvarial defect model, bone formation in the PCL group was limited, with only partial defect closure observed after 8 weeks. In contrast, the PS-RGD-PCL scaffold promoted early bone formation at 2 weeks and rapid defect closure by 4 weeks. At 8 weeks, the BV/TV value reached 44% in the PS-RGD-PCL group, whereas it remained 8.3% in the PCL group (Table 1). Immunohistochemical analysis further showed a significantly lower iNOS/CD206 ratio in the PS-RGD-PCL group than in the PS-PCL group, indicating enhanced M2 macrophage polarization by RGD grafting.

Conclusion

The PS-RGD-PCL scaffold demonstrated potential as an immunomodulatory biomaterial for bone tissue engineering by regulating immune responses and promoting tissue regeneration.

Acknowledgements

This work was supported by the Basic Science Research Program through the National Research Foundation of Korea (NRF) funded by the Ministry of Education (2021R1A6A1A03039462).

Table 1. Quantitative analysis of BV/TV at 0, 2, 4, 6, and 8 weeks after implantation

BV/TV (%)	Sham (mean ± SD)	PCL	PS-PCL	PS-RGD-PCL
0 week	1.0 ± 0.9	1.2 ± 0.7	0.9 ± 0.6	1.1 ± 0.9
2 week	6.1 ± 3.0	1.9 ± 1.2	7.6 ± 5.5	10.7 ± 2.0*
4 week	9.8 ± 4.7	5.1 ± 4.3	16.0 ± 10.6	23.4 ± 4.5*
6 week	11.9 ± 5.1	6.7 ± 5.1	25.9 ± 15.8	37.2 ± 9.9*
8 week	13.7 ± 6.0	8.3 ± 4.9	29.1 ± 18.0	44.0 ± 9.1*

* Statistically significantly different compared with the sham group

D1 – P155

3D-printed multi-doped calcium phosphate cement scaffolds: in vivo biocompatibility

Baltazar C.S.[1#], Felix G.S.[2#], Cavalcante R.B.[2], Abrantes J.C.C.[3], Carvalho T.S.S.[1], Ribeiro N.[1], Correia T.[4], Mano J.F.[4], Raposo R.S.[5], Olhero* S.M.[1], Gurgel-Filho E.D.[2*], Torres P.M.C.[1*]
[1]Dept. of Materials and Ceramic Engineering, CICECO-Aveiro Institute of Materials, University of Aveiro, Portugal; [2]Faculty of Dentistry, University of Fortaleza, Fortaleza, Brazil; [3]proMetheus Research Unit, Polytechnic Institute of Viana do Castelo, Portugal; [4]Dept. of Chemistry, CICECO-Aveiro Institute of Materials, University of Aveiro, Aveiro, Portugal; [5]Experimental Biology Center, University of Fortaleza, Brazil
[#]These authors share first authorship. *These authors share senior authorship.

Introduction

Ion doping of calcium phosphate (CaP) systems is a widely investigated strategy to mimic biological apatite and enhance bone regeneration through sustained release of bioactive ions. However, excessive ion release may lead to cytotoxic effects on surrounding tissues. This study aimed to synthesize multi-doped β-tricalcium phosphate (β-TCP) powders and evaluate *in vitro* biological performance and *in vivo* biocompatibility of CaP cement composite scaffolds manufactured by robocasting, incorporating Sr^{2+}, Zn^{2+}, Mg^{2+}, and Mn^{2+} at two concentrations.

Materials and Methods

Single-and multi-doped β-TCP powders were synthesized via aqueous precipitation, heat-treated at 1000 °C, then characterized by XRD with Rietveld refinement, elemental analysis, SEM, and particle size distribution. *In vitro* cytotoxicity was assessed using MC3T3-E1 cells (ISO 10993-5). Apatite cement composite scaffolds (3 × 3 × 3 mm^3) containing undoped (C), low-doped (C1, within recommended values), and high-doped (C2, 10× higher) powders were 3D printed using a 410 µm nozzle, with 300 µm inter-filament spacing. *In vivo* biocompatibility was evaluated by dorsal subcutaneous implantation in 18 male Wistar rats (~250–300 g) for 7 and 30 days, with histological assessment of inflammatory cell quantity (ICQ) and fibrous capsule thickness. Statistical analyses: ANOVA, Kruskal–Wallis, Student–Newman–Keuls.

Results

Multi-doped β-TCP powders were successfully synthesized, with ion incorporation confirmed by Rietveld refinement, and demonstrated no cytotoxic effects in vitro. *In vivo*, no difference in ICQ was observed among groups at 7 days. At 30 days, group C showed a statistically significant increase in ICQ compared to C1 and C2 ($p < 0.05$). Fibrous capsule thickness did not differ at 7 days; at 30 days, C exhibited significantly thicker capsules than C2 ($p < 0.05$), while capsule thickness in C1 significantly decreased between 7 and 30 days.

Conclusion

Unlike undoped scaffolds, which showed a more pronounced inflammatory reaction at 30 days, both multi-doped formulations induced a moderate inflammatory response at 7 and 30 days, indicating improved biocompatibility over time. These findings support the potential of multi-doped CaP cement scaffolds as bone graft substitutes with enhanced bioactivity.

Acknowledgements

The authors acknowledge the European Union's Horizon 2020 programme for funding the InterLynk project (GA 953169); CICECO – Aveiro Institute of Materials (UID/50011 and LA/P/0006/2020; DOI: 10.54499/LA/P/0006/2020), financed by national funds through FCT/MCTES (PIDDAC), and the Unifor Vice-Rectorate for Research for supporting the in vivo study. P.M.C. Torres acknowledges FCT for contract CEECIND/CP2840/CT0022 (DOI: 10.54499/2023.07934.CEECIND/CP2840/CT0022). T. S. S. Carvalho acknowledges FCT for her PhD grant (2021.06481.BD; DOI: 10.54499/2021.06481.BD).

D1 – P156
3D scaffolds from titanium alloys for bone regeneration

Filová E.[1], Voltrová B.[1], Daňková J.[1], Müllerová[1], Oliveira R.L.M.S.[2], Drotárová L.[2], Oliver-Urrutia C.[2], Filipová A.[3], Diaz D.[3], Filip S.[3], Hympanová M.[4], Marek J.[4], Montufar E.B.[2]
[1]Dept. of Tissue Engineering, Institute of Experimental Medicine CAS, Prague; [2]High Performance Materials and Coatings for Industry, Central European Institute of Technology, Brno University of Technology, Brno; [3]Faculty of Medicine in Hradec Králové, Charles University, Hradec Králové; [4]Biomedical Research Centre, University Hospital Hradec Králové, Hradec Králové, Czechia

Introduction
The bone scaffolds should be biocompatible, support cell growth, osteogenic differentiation and should possess adequate biomechanical properties. TiNb alloys have showed suitable cytocompatibility and biomechanical properties. In addition, antibacterial properties are favourable for the prevention of bacterial attachment and growth, and the alpha-beta titanium alloys may provide better properties than cpTi.

Aim
The aim was to find the 3D titanium scaffold supporting MSC growth, osteogenic differentiation and with improved antibacterial properties.

Materials and Methods
3D titanium scaffolds prepared by robocasting – Ti, Ti10Nb10Cu, Ti13Nb2Cu and Ti20Nb5Cu and visualized using SEM. The diameter of the scaffold was 1 cm with a lamellae diameter of 450 µm, and 50 % of porosity. Scaffolds' cytotoxicity was tested using leachates and direct culture with 3T3 fibroblasts for 7 days. Metabolic activity, dsDNA amount and cell viability were tested. In addition, 100,000 MSCs/scaffold were seeded on the scaffolds. Cells on the scaffolds were stained with Phalloidin-TRIC and visualized using confocal microscope BC43 with spinning disc. Alkaline phosphatase (ALP) activity and ALP staining on day 7 were evaluated. Type I collagen (D14) and osteocalcin (D28) have been visualized using BC43 microscope. Antibacterial effects were tested by incubation in *S. aureus* suspension for 1 min and 24 h; samples were subsequently rinsed with PBS. Bacteria viability was tested with Alamar blue. Shapiro-Wilk normality test was performed followed by non-parametric One-Way ANOVA and Kruskal-Wallis test for statistical evaluation.

Results
The scaffolds had rough surface features at the microscale and low porosity within lamellae. Ti10Nb10Cu scaffolds showed slight microstructural heterogeneity. No cytotoxicity was observed, and 3T3 cells' viability was more than 90%. MSCs were homogeneously seeded and proliferated on the surface of all scaffolds. ALP activity was significantly lower on Ti10Nb10Cu scaffolds than on Ti scaffold on day 1. The amount of collagen I was slightly lower in Ti10Nb10Cu, and osteocalcin synthesis was uneven in both Ti10Nb10Cu and Ti20Nb5Cu scaffolds, and lowest intensity of osteocalcin was found in T13Nb2Cu alloy scaffold. Lower bacteria adhesion was detected in alloys with Ti10Nb10Cu and Ti20Nb5Cu compared to Ti scaffolds. The lowest antibacterial effect was observed on Ti13Nb2Cu.

Conclusion
All 3D printed scaffolds supported the growth of 3T3 cells, MSCs, and both collagen and osteocalcin synthesis. The findings indicate reduced bacterial attachment on both alloys with higher Cu amount (Ti10Nb10Cu and Ti20Nb5Cu) relative to Ti scaffold.

Acknowledgements
The project was supported by Ministry of Health of the Czech Republic, project AZV VES NW24-10-00195.

D1 – P157

Alginate hydrogel enriched with dysidea robusta bioactive for cartilage regeneration: An in vivo evaluation in an osteoarthritis rat model

De Souza D.V., de Souza A., Martignago C.C.S., Ribeiro D.A., Renno A.C.M.
Dept. of Biosciences, Federal University of São Paulo, Santos, Brazil

Introduction

Osteoarthritis (OA) is a degenerative disease characterized by progressive cartilage degradation, oxidative stress, and inflammation. Marine-derived metabolites, such as those from the sponge *Dysidea robusta*, are promising candidates due to anti-inflammatory properties. Alginate hydrogels mimic the cartilage matrix, allowing sustained intra-articular release.

Aim

This study evaluated the in vivo effects of an alginate hydrogel enriched with *Dysidea robusta* bioactive on cartilage tissue in a Wistar rat model of OA.

Materials and Methods

Metabolites with anti-inflammatory potential were extracted from marine sponges (*Dysidea robusta*) collected on the southeast coast of Brazil (Rio de Janeiro), following previously established protocols. The hexanic fraction (DRMH4) was selected due to its antioxidant activity and IL-6 modulation. OA was induced in male Wistar rats via anterior cruciate ligament transection. OA was induced in male Wistar by anterior cruciate ligament transection (ACLT). Four weeks post-surgery, treatment began with two intra-articular injections of 30 µL of alginate (ALG) hydrogel, administered 15 days apart. Groups: Saline (CG), Enriched Hydrogel 0.125 µg/mL (GF), and Enriched Hydrogel 0.250 µg/mL (GE). Euthanasia occurred at 8 and 10 weeks post-surgery. Analyses included semi-quantitative histomorphology, collagen density, isogenous group quantification, and immunohistochemistry for Ki-67, NF-κB, NOS3, 8-OHdG, and Caspase-3.

Results

Semi-quantitative histomorphology at 8 weeks revealed tissue impairment in CG, while GF and GE showed moderate alterations. At this period, GE exhibited significant anti-apoptotic activity via reduced Caspase-3 ($p<0.05$ vs. CG), and GF showed significantly reduced DNA damage via 8-OHdG ($p<0.05$ vs. CG). At 10 weeks, CG showed advanced degeneration and failed regenerative capacity (isogenous groups). Conversely, GF and GE sustained chondrocyte proliferation, with GE reaching the highest activity ($p<0.05$ vs. CG). Immunohistochemistry at 10 weeks indicated successful inflammatory (NF-κB) modulation in GE.

Conclusion

The intra-articular delivery of *Dysidea robusta* bioactive via alginate hydrogel effectively attenuated OA progression by modulating inflammatory and apoptotic pathways, especially at the 0.250 µg/mL concentration.

Acknowledgements

This work was supported by Fundação de Amparo à Pesquisa do Estado de São Paulo - FAPESP grants #2025/13279-0 and #2019/10228-5. The authors also acknowledge Coordenação de Aperfeiçoamento de Pessoal de Nível Superior – CAPES and Conselho Nacional de Desenvolvimento Científico e Tecnológico – CNPq for financial support.

D1 – P 158

Low-temperature synthesized α-TCP as a bioactive biochemical cue for next-generation bone regenerative biomaterials

Demir Ö.[1,2], Loca D. [1,2]
[1]Institute of Biomaterials and Bioengineering, Faculty of Natural Sciences and Technology, Riga Technical University; [2]Baltic Biomaterials Centre of Excellence, Headquarters at Riga Technical University, Riga, Latvia

Introduction

Successful bone regeneration requires biomaterials capable of recapitulating both the biochemical and biophysical complexity of natural bone healing[1]. In particular, calcium phosphate phases can act as bioactive mineral cues that dynamically interact with the cellular microenvironment. Low-temperature synthesis routes may enhance the reactivity of calcium phosphates by preserving structural disorder and increasing surface area[2]. In this study, α-tricalcium phosphate (α-TCP) was synthesized via a low-temperature route to serve as a tunable biochemical cue within next-generation bone regenerative biomaterials.

Materials and Methods

α-TCP powders were synthesized using a low-temperature route (<700 °C) to preserve high surface reactivity and fine crystallinity[2]. Phase composition and structural properties were characterized using X-ray diffraction (XRD) and Fourier-transform infrared spectroscopy (FTIR), while Brunauer–Emmett–Teller (BET) analysis was used to determine the specific surface area. The ion release behavior and pH evolution of the powders were evaluated during immersion in cell culture media to assess dissolution–reprecipitation processes and mineral phase evolution. Cytocompatibility and early osteogenic response were preliminarily evaluated using human mesenchymal stem cells (hMSCs), including alkaline phosphatase (ALP) activity measurements after 7 days.

Results

The synthesized α-TCP exhibited a Ca/P ratio of approximately 1.5 and a relatively high specific surface area (11.3 m^2 g^{-1}) (Figure 1), indicating partial structural disorder favorable for enhanced bioactivity. Immersion experiments in cell culture media revealed progressive mineral transformation toward octacalcium phosphate (OCP) phases, suggesting a biomimetic dissolution–reprecipitation mechanism. Preliminary in vitro evaluation with hMSCs confirmed good cytocompatibility and showed increased ALP activity after 7 days compared with control conditions, indicating promotion of early osteogenic differentiation.




Figure 19 Characterization of low-temperature synthesized α-TCP powders. (A) XRD pattern confirming the formation of α-TCP (ICDD PDF 00-009-0348); inset shows average particle size and BET surface area. (B–C) SEM micrographs revealing a morphology (scale bars: 5 μm and 1 μm).

Conclusion

Low-temperature synthesized α-TCP demonstrates promising characteristics as a bioactive mineral cue capable of supporting mineral remodeling and early osteogenic activation. These findings highlight the potential of structurally reactive α-TCP phases for incorporation into advanced biomaterial systems aimed at mimicking early bone healing environments. Initial investigations suggest that integrating this mineral phase into tunable viscoelastic matrices may provide a platform to study the synergistic interaction between biochemical and mechanical cues during bone regeneration.

Acknowledgements

This work was supported by the Latvian Council of Science under the Activity 1.1.1.9 “Post-doctoral Research” (Project No. 1.1.1.9/LZP/2/25/268, SynerMat) and infrastructure from H2020 Grant No. 857287 (BBCE).

References

[1]Wu D.T., Jeffreys N., Diba M., Mooney D.J. Viscoelastic Biomaterials for Tissue Regeneration. *Tissue Engineering Part C: Methods* 2022; 28(7); 289-300. doi:10.1089/ten.tec.2022.0040

[2]Demir Ö., Pylostomou A., Loca D. Octacalcium phosphate phase forming cements as an injectable bone substitute materials: Preparation and in vitro structural study. *Biomaterials Advances* 2024; 157; 213731.

D1 – P159

Electron microscopy investigation of 3D-printed surface-treated PCL fiber reinforced hydroxyapatite calcium phosphate cement for bone regeneration

Jangda S.J.[1], Salman [2], Kruppke B.[3], Alt F.[4]
[1]Chair of Biomaterials, Technical University of Dresden, Dresden; [2]Dept. of Biomaterials, Institute for Bioprocessing and Analytical Measurement Techniques e.V., Heilbad Heiligenstadt, Germany; Institute for Organic and Macromolecular Chemistry, Friedrich Schiller University Jena, Jena, Germany

Introduction

Calcium phosphate cements (CPCs) are promising biomaterials for bone regeneration due to their biocompatibility and chemical similarity to the mineral phase of bone. However, their inherent brittleness and low fracture resistance restrict their use in mechanically demanding environments. Fiber reinforcement has been explored to overcome these limitations, yet the reinforcing mechanisms strongly depend on the fiber-matrix interface and microstructural interactions. In this study, hydroxyapatite (HAp)-based CPC reinforced with in-house developed 3D-printed polycaprolactone (PCL) fibers was investigated with a particular focus on electron microscopy-based microstructural analysis. A tailored surface treatment was developed to improve the interfacial bonding between the fibers and the CPC matrix.

Materials and Methods

Hydroxyapatite-based CPC was reinforced with surface-treated PCL fibers fabricated through an in-house 3D printing process. The fibers were incorporated into the cement matrix during paste preparation to achieve homogeneous distribution. Mechanical performance was evaluated through compressive strength (CS), diametral tensile strength (DTS), and biaxial flexural strength (BFS) tests. Detailed microstructural characterization was carried out using scanning electron microscopy (SEM) to analyze fiber distribution, fiber-matrix interfacial bonding, and fracture mechanisms within the composite. Phase composition of the cement after setting was investigated using X-ray diffraction (XRD).

Results

The incorporation of surface-treated 3D-printed PCL fibers resulted in improved mechanical performance of CPC. Compressive strength, diametral tensile strength, and biaxial flexural strength showed enhancement compared with non-reinforced CPC. In addition, the work of fracture increased significantly, indicating improved fracture resistance and energy absorption of the composite material. SEM analysis revealed strong interfacial bonding between the fibers and the CPC matrix due to the developed surface treatment. Electron microscopy observations demonstrated typical toughening mechanisms such as crack bridging, crack deflection, and fiber pull-out (as shown in figure 1), which contribute to improved load transfer and structural stability of the cement matrix. XRD analysis confirmed hydroxyapatite as the dominant crystalline phase.



Figure 20-SEM images of (a) Surface treated polycaprolactone fibers, (b) Fibre pull-out and crack bridging, and (c) Fractured surface of CPC with pulled and stretched fibers

Conclusion

Electron microscopy-based analysis revealed that the developed surface-treated 3D-printed PCL fibers enable effective reinforcement of hydroxyapatite CPC through improved fiber-matrix interaction and crack-bridging mechanisms. The observed microstructural features correlate with the enhanced mechanical performance and increased work of fracture, demonstrating the potential of this composite system for mechanically improved CPCs in bone regeneration applications.

Acknowledgements

- Sächsisches Landesstipendium
- Arbeitsgemeinschaft für Electronenoptik e.V.

D1 – P160

Bioactive $SrMoO_4$-chitosan-hydroxyapatite scaffolds for bone tissue engineering

Grasser G.[1], Souza K.[2], Nina D.[2], Bonifácio M.[2], Granito E.[2], Rennó A. C[2]., Longo E.[1], Assis M.[2].
[1]CDMF, LIEC, Federal University of São Carlos, São Carlos; [2]Dept. of Biosciences, Federal University of São Paulo, Santos, Brazil

Introduction

Tissue engineering aims to develop advanced materials for tissue regeneration, where scaffolds provide a three-dimensional structure that supports cell growth and tissue formation [1]. Chitosan is a promising matrix due to its biocompatibility. The incorporation of $SrMoO_4$ can enhance osteogenic properties, while hydroxyapatite improves bioactivity and bone integration [2]. The combination of these components may optimize the performance of biomaterials for regenerative applications.

Aim. To develop chitosan-based scaffolds containing hydroxyapatite and $SrMoO_4$ and evaluate their structural, thermal, mechanical, and biological properties for potential applications in bone tissue regeneration.

Materials and Methods

$SrMoO_4$ was synthesized by microwave-assisted hydrothermal method, while chitosan scaffolds were prepared by freeze-drying and hydroxyapatite by coprecipitation. Materials were characterized. Biological assays evaluated ROS/RNS production and cell viability using L929 fibroblasts and MC3T3 pre-osteoblasts, providing insights into their structural and biological properties for tissue engineering and bone regeneration.

Results

The analyses indicated that chitosan scaffolds containing $SrMoO_4$ and hydroxyapatite exhibit promising properties for tissue engineering applications. As shown in Figure 1, X-ray diffraction (XRD) confirmed the presence of the crystalline phases of $SrMoO_4$ and hydroxyapatite, indicating successful incorporation of these components into the scaffolds. Scanning electron microscopy (SEM) images also presented in Figure 1 revealed a porous and interconnected morphology, which is favorable for cell adhesion, proliferation, and nutrient transport. Furthermore, Figure 2 presents the biological evaluation of the scaffolds. Cell viability assays, including Alamar Blue, demonstrated good viability for both L929 fibroblast and MC3T3 pre-osteoblast cells. In addition, the analyses of reactive oxygen species and reactive nitrogen species indicated controlled levels, suggesting that the materials do not induce harmful oxidative stress. These results collectively demonstrate good biocompatibility and highlight the potential of the developed scaffolds for regenerative and tissue engineering applications.

Conclusion

Chitosan scaffolds incorporating $SrMoO_4$ showed strong potential for biomedical applications, particularly in tissue engineering and bone regeneration. Structural analysis revealed a porous architecture favorable for cell adhesion, while biological tests indicated good biocompatibility, enhanced cell viability, and antioxidant activity. These results highlight their promise as bioactive materials for regenerative therapies.

Acknowledgements

Fundação de Amparo à Pesquisa do Estado de São Paulo – FAPESP (2024/15977, 2026/00695-9, and 2013/07296-2).

References

[1]Zefei Zhang, et al. A review of preparation methods of porous skin tissue engineering scaffolds. *Materials Today Communications* 2022; Volume 32; 104109. ISSN 2352-4928.
[2]Koç Demir A., et al. Strontium-modified chitosan/montmorillonite composites as bone tissue engineering scaffold. *Mater Sci Eng C Mater Biol Appl* 2018; Aug 1; 89:8-14.




Figure 1: Structural and morphological characterization of the materials. XRD of the pure materials and the composites. Scanning electron microscopy (SEM) images of the chitosan-based.




Figure 2: Biological evaluation of the scaffolds using L929 fibroblast and MC3T3 pre-osteoblast cell lines.

D1 – P161

Chitosan as a biomaterial for the delivery of adipose-derived mesenchymal stromal cells and chondroinductive peptides in cartilage regeneration

Tymińska A.[1#], Karska N.[2], Skoniecka A.[1], Zawrzykraj M.[3], Banach-Kopeć A.[4], Mania S.[4], Kondej K.[5], Gurzawska-Comis K.[6], Tylingo R.[4], Rodziewicz-Motowidło S.[2], Pikuła M.[1]

[1]Dept. of Anatomy, Faculty of Medicine, Laboratory of Tissue Engineering and Regenerative Medicine, Division of Embryology, Medical University of Gdańsk, Gdańsk, Poland; [2]Dept. of Biomedical Chemistry, Faculty of Chemistry, University of Gdańsk, Gdańsk, Poland, [3]Dept. of Anatomy, Division of Clinical Anatomy, Medical University of Gdańsk, Gdansk, Poland; [4]Dept. of Chemistry, Technology and Biotechnology of Food Gdańsk, University of Technology, Gdańsk, Poland; [5]Dept. of Plastic Surgery, Medical University of Gdańsk, Gdańsk, Poland; [6]Dept. of Dentistry and Oral Health, Aarhus University, Aarhus, Denmark

Introduction

Articular cartilage has very limited intrinsic regenerative capacity, and current clinical interventions offer only modest long-term benefits. To address this, an innovative chitosan-based biomaterial was developed as a dual carrier for adipose-derived mesenchymal stromal cells (ADMSC) and the chondroinductive peptide UG28 from the copine (CPNE) family. ADMSC, due to their availability, immunomodulatory activity, and chondrogenic potential, represent a promising regenerative cell source. UG28 enhances chondrogenic signaling and upregulates key cartilage markers such as SOX9, COL2A1, and aggrecan. The combination of ADMSC and UG28 within a chitosan matrix forms a synergistic system that supports cell survival, directed differentiation, and formation of hyaline-like cartilage. This approach may improve outcomes in articular cartilage regeneration compared with current therapies.

Materials and Methods

ADMSCs were isolated from adipose tissue using enzymatic digestion with collagenase. Cells were cultured on 75/500 chitosan membranes, which were evaluated for biocompatibility, cytotoxicity, and immunogenicity using PBMCs. Cell viability was assessed with the XTT assay, and cytotoxicity with the LDH test. The chondroinductive peptide UG28 was covalently bound to the chitosan matrix to enable controlled local activity. Cellular responses were evaluated based on collagen production, intracellular glycosaminoglycan (GAG) synthesis, and the degree of chondrogenic differentiation. Cell organization and matrix structure were analyzed histologically and using transmission electron microscopy (TEM).

Results

The chitosan scaffolds supported high viability and proliferation of AD-MSCs without signs of cytotoxicity. Incorporation of the UG28 peptide enhanced extracellular matrix production and strengthened chondrogenic differentiation. Histological and TEM analyses confirmed the formation of a collagen type II–rich matrix closely associated with the scaffold, demonstrating the strong chondrogenic potential of the chitosan-UG28 composite.

Conclusion

The chitosan-UG28 composite provides an effective platform for simultaneous delivery of cells and bioactive peptides, creating a synergistic environment that promotes chondrogenesis. This biomaterial shows strong potential for cartilage defect repair and may become a promising candidate for future orthopedic and regenerative medicine applications.

Acknowledgements

This work was supported by the National Center for Research and Development, Poland (Grant TECHMATSTRATEG2/ 410747/11/2019, acronym BIONANOVA)

D1 – P162

In vivo effects of biosilica and spongin-like collagen scaffolds on the healing process in osteoporotic rats

Renno ACM.
Dept. of Biosciences, Federal University of São Paulo, Santos, Brazil

Introduction

Osteoporosis is characterized by reduced bone mass and impaired bone regeneration, increasing the risk of delayed healing, pseudoarthrosis and non-union fractures. In severe osteoporotic fractures, surgical interventions and biomaterials are often required to improve fracture fixation and promote osteointegration. Natural biomaterials have gained attention in tissue engineering due to their bioactive properties. Marine sponge-derived materials include the inorganic biosilica (BS) and the organic spongin-like collagen (SPG), which have demonstrated beneficial effects on osteoblast and fibroblast proliferation and on tissue healing.

Materials and Methods

Biosilica (BS) and spongin-like collagen (SPG) scaffolds were characterized by scanning electron microscopy (SEM) to evaluate morphology and by Fourier transform infrared spectroscopy (FTIR) to identify chemical bonds. For the *in vivo* study, osteoporotic female Wistar rats were submitted to a surgical procedure to create tibial bone defects, followed by implantation of the scaffolds. Animals were euthanized after 15 and 30 days. Bone repair was evaluated through histological analysis, histomorphometry and immunohistochemistry.

Results

SEM analysis demonstrated porous scaffolds with characteristic biosilica spicules and fibrous spongin-like collagen structures. FTIR spectra confirmed the characteristic peaks of BS and SPG. In the *in vivo* experiments, after 30 days the BS and BS/SPG groups showed a higher amount of newly formed bone compared to the first experimental period, both in the peripheral and central regions of the defect. Histomorphometric analysis demonstrated that the BS/SPG group presented higher bone volume fraction (%BV/TV) compared to the other experimental groups. Immunohistochemical analysis showed higher collagen type I volume in the BS group after 15 days. After 30 days, all groups presented increased collagen type III levels compared to 15 days. In addition, the BS/SPG group showed higher osteoprotegerin immunostaining compared to the other groups at the same experimental period.

Conclusion

The results suggest that BS/SPG scaffolds are biocompatible and support bone repair in osteoporotic bone defects. These marine-derived biomaterials may represent a promising alternative for bone tissue engineering applications. Further studies should investigate the long-term effects of BS/SPG scaffolds in bone defect models.

Acknowledgements

This work was supported by “Fundação de Amparo à Pesquisa do Estado de São Paulo - FAPESP” through the grant #2019/10228-5.

D1 – P163
Advanced biomaterials for additive manufacturing of orthopaedic implants

Murab S.
School of Biosciences and Bioengineering, Indian Institute of Technology Mandi, Mandi, India

Introduction
Bone related pathologies constitute a significant burden on the global medical system. These pathologies include critical sized bone defects, osteomyelitis, avascular necrosis, osteoporosis, osteosarcoma etc. The most critical part of making scaffolds for regeneration of bone tissue is that the scaffolds must be able to mechanically support the physiological loading on the bone tissue, while acting as a template for mineralization and bone regeneration. Metallic implants have been widely used surgically for the treatment of damaged and diseased bone tissue. Though, widely used they suffer from implant associated infection, bone shielding effect, heavy metal toxicity and poor osteointegration. 3D-printed thermoplastic scaffolds provide an excellent alternative, as they can be printed into patient specific geometries using 3D medical images like CT and MRI. Though, they also suffer from limitations like low surface energy, bioinert surface that results into low protein and cell adhesion on the surface of these scaffolds, which leads to both reduced osteointegration, mineralization and functional bone regeneration. Thus, strategies that can modify the surface or matrix of these 3D-printed thermoplastic scaffolds to make them bio-inductive for bone regeneration and mineralization are greatly needed to translate them into clinics.

Materials and Methods
We have developed 3D-printed dual functionalized scaffolds with osteogenic and antibacterial properties for treatment of critical sized bone defects. While we have also developed oxygen generating 3D-printed scaffolds that can help in treating conditions like avascular necrosis. We have also developed 3D-printed/bioprinted scaffolds for osteosarcoma management post resection, that helps in regeneration of lost bone tissue while obliterating residual osteosarcoma cells.

Results and Discussion
Citric acid-linked chitosan coating on oxygen plasma etched 3D-printed PLA scaffolds through an EDC-NHS coupling reaction, resulted in significant increase in acellular mineralization, antibacterial and osteogenic properties of the scaffolds. Hydroxyapatite nanospicule coating on 3D-printed thermoplastic scaffolds kills both gram positive and negative bacteria through contact killing, while significantly improving the osteogenic potential of these scaffolds both in vitro and in vivo. Further, the cost-effective oxygen producing 3D-printed scaffolding system can help in the induction, survival, proliferation of stem cells post implantation in defect sites with avascular necrosis, to help regenerate the bone tissue with the regeneration of the vasculature itself. Drug loaded multivesicular liposomes incorporated bioinks created in our lab demonstrated both osteogenic and angiogenic potential both in vitro, in ovo and in vivo. Selenium-Strontium doped bioglass incorporated bioink demonstrated 4D-bioprinting by covering an in ovo tumor model and decreasing it in size, while showing osteogenic properties. Hydroxyapatite nanowire incorporated stiff bioinks demonstrated significant shear thinning during printing as compared to even alginate, decreasing the shear on cells resulting in increased cellular viability post printing even in a mineral based composite bioink. Post printing these composite constructs regain their mechanical strength and have demonstrated higher mechanical properties in an ex-vivo bone defect model, as compared to even native bone.

Conclusion
These advanced biomaterial-based strategies can improve the performance of the current thermoplastic and bioink platforms to significantly enhance the clinical translational potential of these 3D-printed implants.

Acknowledgements
SM acknowledges the funding support from IIT Mandi (IITM/SG/SUM/88), Anusandhan National Research Foundation (ANRF, India) (SRG/2023/002182), IIT Mandi iHub and HCI Foundation (IIT MANDI iHub/RD/2023/012), and DST-FIST (SR/FST/LS-II/2022/950).

D1 – P164
Integration of polymeric multilayered scaffolds and hydrogel for osteochondral in vitro modeling

Krugly E.[1], Pupiute A.[1], Ciuzas D.[1], Martuzevicius D.[1], Bagdonas E.[2], Bernotiene E.[2],
[1]Faculty of Chemical Technology, Kaunas University of Technology, Kaunas; [2]Dept. of Regenerative Medicine, State Research Institute Centre for Innovative Medicine, Vilnius, Lithuania

Introduction
Degenerative joint diseases such as osteoarthritis require biomimetic in vitro models that closely reproduce the structural and functional complexity of the osteochondral interface. This study aimed to develop an integrated multilayer polymeric scaffold/hydrogel system for osteochondral in vitro modeling, combining fibrous architecture, compositional gradients and region specific bioactive cues to support spatially organized cell growth.

Materials and Methods
Multilayer osteochondral scaffolds were fabricated by combining melt and solution electrospinning. The cartilage region was composed of poly(ε-caprolactone) (PCL), whereas the bone region consisted of PCL supplemented with 5% hydroxyapatite (HAp). A nanofibrous tidemark interlayer was introduced to mimic the native interface and restrict cell migration between phases. To improve hydrophilicity and cell attachment, scaffolds were treated with non-thermal plasma. Hyaluronic acid methacrylate hydrogel was integrated with the fibrous scaffold; the chondral side was supplemented with 1% chondroitin sulphate, while the osseous side contained 1% HAp. Human chondrocytes and osteoblasts were cultured on their respective regions, and scaffold morphology, wettability, surface roughness, cell viability, proliferation and distribution were evaluated.

Results
The scaffolds exhibited interconnected porosity with gradient pore sizes ranging from 51.4 ± 11.2 µm to 112.1 ± 28.0 µm, supporting nutrient transport and region-specific architecture. The tidemark-like interlayer displayed very small pores (0.87 ± 0.18 µm) and thin fibers (0.42 ± 0.08 µm), effectively limiting cell migration across the interface. Non-thermal plasma treatment reduced the water contact angle from 108.0 ± 1.7° to 49.6 ± 1.5° and increased surface roughness (Ra) from 10.2 ± 0.9 nm to 36.0 ± 2.1 nm. The integrated scaffold-hydrogel construct supported high cell viability, robust proliferation and homogeneous colonization, with a gradual transition between chondrocyte- and osteoblast-populated regions.




Fig. 1. Cross-sectional SEM image of the integrated multilayer osteochondral scaffold–hydrogel construct showing the chondral and osseous hydrogel regions and representative microstructures across the scaffold thickness.

Conclusion

The integrated multilayer PCL/PCL-HAp scaffold/hydrogel system successfully mimicked key structural features of native osteochondral tissue and supported spatially organized growth of chondrocytes and osteoblasts. This biomimetic in vitro platform shows strong potential for investigating osteochondral regeneration, disease mechanisms and therapeutic strategies while supporting reduction of animal based experimentation.

Funding

This study was supported by Research Council of Lithuania “New Generation In Vitro Model of Osteochondral Tissue: Synergistic Engineering of Multilayered 3D Polymer Scaffolds and Smart Hydrogels” (Grant No. S-MIP-24-38).

D1 – P165

3D-printed hybrid PCL composites for osteoporotic bone regeneration

Soriente A.[1], Guidone A.[2], Coppola P.[2], Sardo C.[2], Mariano A.[1], Ambrosio L.[1], Raucci M. G.[1], Auriemma G.[2]
[1]Institute of Polymers, Composites and Biomaterials - National Research Council of Italy (IPCB-CNR), Naples; [2]University of Salerno, Dept. of Pharmacy, Fisciano (SA), Italy

Introduction

Osteoporosis is a chronic, progressive skeletal disorder characterized by reduced bone mass and microarchitectural deterioration. The growing clinical burden associated with osteoporotic fractures has prompted the development of innovative therapeutic strategies to promote bone regeneration. In this context, advances in three-dimensional printing (3DP) have enabled the development of highly precise, patient specific scaffolds tailored to individual anatomical and pathological needs [1]. To enhance their performance, hybrid systems incorporating bioinspired materials are increasingly investigated. In this study, a novel 3D-printed scaffold based on polycaprolactone (PCL), Inulin-g-poly(D,L-lactide) (INU-PLA), and strontium-doped nano-hydroxyapatite (Sr-nHA) was developed to improve bioactivity, mechanical properties, and osteogenic potential. The scaffold is further functionalized with raloxifene to enable localized and sustained drug delivery, promoting bone regeneration. This multifunctional approach aims to provide both structural support and therapeutic effects for the treatment of osteoporotic fractures.

Materials and Methods

In vitro studies were performed using 7F2 cells. Cell morphology was assessed after 24 hours via CellMask™ and DAPI staining, while proliferation was evaluated at different time points (1–21 days) using CCK-8 assay. Osteogenic differentiation was analyzed by measuring early and late markers, including alkaline phosphatase (ALP) and osteocalcin (OCN).

Results

Cell adhesion results showed that IP5 improved scaffold hydrophilicity, enhancing cell attachment. Fluorescence staining confirmed good cell spreading and uniform distribution, indicating high biocompatibility. Cell viability over 21 days revealed no cytotoxicity, with strontium-doped scaffolds exhibiting higher viability than non-doped ones. Additionally, increased ALP and OCN expression in Sr-nHA scaffolds ($p < 0.001$) indicated enhanced osteogenic differentiation.

Conclusion

The results demonstrated the strong potential of PCL-based hybrid scaffolds for bone tissue engineering, particularly in the treatment of osteoporosis-related defects. The integration of PCL with INU-PLA and Sr-nHA, combined with advanced fused filament fabrication (FFF) 3D printing, enables the development of multifunctional scaffolds with improved biological and therapeutic performance.

Acknowledgements

This work was founded under the National Recovery and Resilience Plan (NRRP), Mission 4, Component 2, Investment 1.1, Call for tender No. 1409 published on 14.9.2022 by the Italian Ministry of University and Research (MUR), founded by the European Union – NextGenerationEU–CUP D53D2301871 0001- Grant Assignment Decree No. 1389 01/09/2023 adopted by the Italian Ministry of Ministry of University and Research (MUR).

References

[1]Auriemma G., Tommasino C., Falcone G., Esposito T., Sardo C., Aquino R.P. Additive Manufacturing Strategies for Personalized Drug Delivery Systems and Medical Devices: Fused Filament Fabrication and Semi Solid Extrusion. *Molecules* 2022; 27(9); 2784.

D1 – P166

Facile synthesis and characterization of bioactive advanced scaffolds for regenerative medicine

Srividhya RV[1], Dr. S. Manisha Vidyavathy[2]
[1]Dept. of Ceramic Technology, Anna University, Chennai, India; [2]Dept. of Ceramic Technology, Anna University

Introduction

Bone defects and tissue loss remain one of the most pressing challenges in modern medicine, affecting millions of patients worldwide each year. Conditions such as osteoporosis, tumours, and infections often lead to bone damage where the body's own healing ability is insufficient. Despite the widespread use of grafting procedures, existing solutions such as autografts and allografts continue to face major limitations, including a shortage of donor tissue, risk of immune rejection, infection, and complications at the donor site. These shortcomings emphasize the urgent need for advanced strategies that can effectively promote bone regeneration. Tissue engineering addresses these through 3D scaffolds combining biomaterials, cells, and signaling molecules to provide temporary templates for cell attachment, proliferation, and functional bone regeneration.

This work focuses on the facile synthesis and characterization of a bioactive scaffold based on strontium-doped bredigite (Sr-BRT) and a zinc oxide-chitosan–montmorillonite (ZCM) composite for potential application in bone tissue engineering. Sr- Bredigite, a calcium–magnesium silicate ceramic, is particularly attractive due to its excellent bioactivity, osteoconductivity, and strong integration with natural bone. Meanwhile, incorporating ZCM significantly enhances scaffold performance: zinc ions stimulate bone-forming cells and impart antibacterial effects, while the clay improves structural stability. Together, these components yield a hybrid scaffold designed to create an optimal microenvironment for bone regeneration..

Aim

This study aimed to synthesize and characterize strontium-doped bredigite (Sr-BRT) and zinc oxide-chitosan-montmorillonite (ZCM) composites for bioactive scaffolds in bone tissue engineering.

Materials and Methods

Sr-BRT was synthesized via sol-gel method using calcium nitrate tetrahydrate, magnesium nitrate hexahydrate, strontium nitrate, and TEOS, followed by controlled calcination. Multiple synthesis trials were conducted by varying processing parameters to optimize phase formation and crystallinity. ZCM was prepared by intercalating montmorillonite (MMT) with chitosan in acetic acid, centrifuging and washing, then reacting with zinc acetate at 60°C, followed by drying and calcination. Scaffolds used foam replica (Coated Sr-BRT/ZCM slurry & sintered at 1350°C) and direct ink writing (DIW) with inks printed, crosslinked in $CaCl_2$ (Fig 1). Characterization involved XRD for phase analysis, SBF immersion for bioactivity, MTT Assay and SEM for morphology.

Results

Systematic variation of various parameters in Sr-BRT trials led to progressive sharpening and intensification of diffraction peaks, with the final composition Sr-BRT6 exhibiting dominant orthorhombic bredigite together with well-resolved CSMS reflections, indicating high crystallinity, effective Sr^{2+} incorporation, and negligible amorphous residue. Complementary XRD analysis showed chitosan-MMT retaining layered silicate structure as a semi-crystalline hybrid, with ZnO introduction yielding crystalline ZnO nanoparticles in the ZCM. The SBF showed apatite within 7 days upon immersing Sr-BRT samples. Also, MTT assay on MC3T3 cells showed 90.5% viability up to 200% extract (Fig 2), while dose-dependent antibacterial activity against E. coli (10 mm ZOI) and S. aureus (9 mm), confirming suitability for bone tissue engineering.

Conclusion

A multifunctional bioactive scaffold based on Sr-BRT and ZCM was successfully developed. The scaffolds exhibit crystallinity, apatite formation, antibacterial activity, and cytocompatibility, ideal for bone regeneration. Overall, the integrated scaffold exhibit crystallinity, apatite formation, antibacterial activity, and cytocompatibility, ideal for bone regeneration.



Fig 1. Scaffold




Fig 2. MTT Assay

D1-P167

Anti-aging hydrogel microspheres regulate mitochondrial function for osteoarthritis therapy

Yibo F.[1], Meng Z.[2], Hao Z.[3], Jun X.[4]
[1]HUST; [2]Tongji Hospital Tongji Medical College of HUST; [3]Tongji Hospital Tongji Medical College of HUST; [4]Tongji Hospital Tongji Medical College of HUST, Wuhan, China

Introduction


Osteoarthritis (OA) is a prevalent degenerative joint disease characterized by cartilage degradation accompanied by chronic inflammation, in which cellular senescence plays a critical role in disease progression. Senescent chondrocytes exhibit markedly increased catabolic activity, along with alterations in mitochondrial morphology, membrane potential, and quality control. Therefore, targeting mitochondrial dysfunction and cellular senescence represents a promising therapeutic strategy for OA.Hydrogel microspheres have attracted increasing attention due to their large specific surface area, tunable mechanical properties, and excellent biocompatibility. Taurine (TR), one of the most abundant endogenous micronutrients, has been reported to suppress inflammatory senescence, reduce DNA damage, and improve mitochondrial function. In this study, taurine (TR) and choline chloride (CL) were grafted onto methacrylated hyaluronic acid (HAMA). TR/CL-functionalized hydrogel microspheres (TR/CL-HM) were subsequently fabricated using a microfluidic-assisted photopolymerization approach. The negatively charged taurine and positively charged choline formed a hydration layer on the microsphere surface, contributing to enhanced lubrication performance.

Material characterization demonstrated that TR/CL-HM exhibited uniform size distribution and superior lubrication properties compared to conventional HAMA microspheres. In vitro studies in chondrocytes revealed that taurine released from the microspheres significantly downregulated the expression of inflammatory, catabolic, and senescence-related genes, while inhibiting the cGAS–STING signaling pathway. Moreover, taurine enhanced oxidative phosphorylation and restored mitochondrial membrane potential, effectively improving mitochondrial function. In macrophage models, taurine and choline synergistically suppressed M1 polarization while promoting M2 polarization, thereby modulating the inflammatory microenvironment.In vivo experiments further demonstrated that TR/CL-HM promoted cartilage regeneration and significantly alleviated OA progression.

Materials and Methods

Taurine and choline chloride were respectively grafted onto methacrylated hyaluronic acid via amide and ester reactions, and TR/CL-HMwere subsequently fabricated using a microfluidic-assisted approach. The successful grafting of the bioactive components was confirmed. The size, morphology, and microstructure of TR/CL-HM were characterized, and their uniformity, degradation behavior, and lubrication properties were systematically evaluated. In vitro, chondrocytes were used to investigate the anti-inflammatory, anti-senescent, and mitochondrial function–restoring effects of TR/CL-HM. In addition, macrophages were employed to assess the immunomodulatory effects of the microspheres. For in vivo studies, a rat osteoarthritis model was established using destabilization of the medial meniscus (DMM) combined with anterior cruciate ligament transection (ACLT). The therapeutic efficacy of TR/CL-HM in osteoarthritis was evaluated through Micro-CT analysis and histological assessments.

Results



Conclusion

In conclusion, TR/CL-HM hydrogel microspheres effectively inhibit chondrocyte senescence, regulate immune responses, and enhance cartilage regeneration, showing great potential as a multifunctional therapeutic strategy for osteoarthritis.

D1 – P168

Injectable hydrogel for antimicrobial and regenerative therapy of bone fracture-related infections

Rubina A.[1,2], Sceglovs A.[1,2], Skadins I.[3], Salma-Ancane K.[1,2]
[1]Institute of Biomaterials and Bioengineering, Riga Technical University; [2]Baltic Biomaterials Centre of Excellence, Riga Technical University; [3]Dept. of Biology and Microbiology, Riga Stradins University, Riga, Latvia

Introduction

Fracture-related infections (FRIs) remain a major clinical challenge due to biofilm formation, antimicrobial resistance, and impaired bone regeneration. Current local therapies rely on antibiotic-loaded carriers that show burst release, limited biofilm eradication, and lack regenerative function. Injectable biomaterials that combine antimicrobial and osteogenic activity without antibiotics are not available.

Aim

The developed antibiotic-free bone biomaterials address this gap through a dual-functional hydrogel system based on an antimicrobial polypeptide, hyaluronic acid, and nano-hydroxyapatite.

Materials and Methods

The system was designed for *in situ* gelation after mixing via chemical cross-linking and optimized for minimally invasive delivery using a dual-syringe approach. Rheological evaluation was performed to assess viscoelastic behavior and structural recovery. Injectability and handling performance were tested under clinically relevant conditions. Antimicrobial activity was evaluated against clinically isolated multidrug-resistant *ESBL E. coli* and *MRSA* strains. Cytocompatibility was assessed using human mesenchymal stem cells, and osteogenic potential was evaluated through biochemical and mineralization assays.

Results

The hydrogels showed stable viscoelastic properties and clinically relevant injectability. Increasing mineral content improved structural stability and extended degradation over several weeks. Sustained antibacterial activity was observed against Gram-positive and Gram-negative multidrug-resistant bacterial strains, with effective biofilm inhibition. Cytocompatibility assays confirmed cell viability and proliferation.

Conclusion

The developed mineralized dual-functional injectable hydrogel combines intrinsic antimicrobial activity with bone regenerative capacity. The system addresses key limitations of current therapies by eliminating antibiotics while maintaining biofilm control and osteogenic performance. These findings support further development toward translational validation for the treatment of fracture-related infections.

Acknowledgements

The authors acknowledge financial support from the “Biomedical and Photonics Research Platform for the Development of Innovative Products (Project No IVPP-EM-Innovation-2024/1-0002 "Biomedical and Photonics Research Platform for Innovative Products (BioPhot))” project No. OSI_PIP_BioPhoT-2025/2-0071 “Injectable Hydrogel for Antimicrobial and Regenerative Therapy of Fracture-Related Bone Infections (BoneART)” and access to the infrastructure and expertise from Horizon 2020 project No. 857287 (BBCE – Baltic Biomaterials Centre of Excellence).

D1 – P169

Calcium/magnesium carbonate microbeads enriched with heparin or tinzaparin for potential use in bone healing applications

Pawlak-Likus Z.[1], Platania V.[2], Tavernaraki N.N.[2], Smith A.M.[3], Douglas T.E.L.[4], Handke B.[5], Chatzinikolaidou M.[2,6], Domalik-Pyzik P.[7]

[1]AGH University of Krakow, Faculty of Electrical Engineering, Automatics, Computer Science and Biomedical Engineering, Dept. of Biocybernetics and Biomedical Engineering, Kraków, Poland; [2]University of Crete, Dept. of Materials Science and Engineering, Heraklion, Greece; [3]University of Huddersfield, School of Applied Sciences, Dept. of Pharmacy, Huddersfield, UK; [4]Lancaster University, School of Engineering, Lancaster, United Kingdom; [5]AGH University of Krakow, Faculty of Materials Science and Ceramics, Dept. of Silicate Chemistry and Macromolecular Compounds, Kraków, Poland; [6]Institute of Electronic Structure and Laser, Foundation for Research and Technology Hellas, Heraklion, Greece; [7]AGH University of Krakow, Faculty of Materials Science and Ceramics, Dept. of Biomaterials and Composites, Kraków, Poland

Introduction

Calcium-based materials are widely used in the field of bone regeneration due to calcium being the main constituent of bone tissue. Calcium carbonate ($CaCO_3$) is a biodegradable and bioavailable material that releases calcium ions during degradation. The incorporation of heparin (HP), tinzaparin (TP), or magnesium into $CaCO_3$ microbeads may beneficially influence its properties. HP and TP are well-known anticoagulants, while magnesium is recognized for its role in promoting osteogenesis and angiogenesis. The effects of these modifications were evaluated in terms of physicochemical properties, including morphology, microstructure, and crystalline structure. The osteogenic potential was assessed by measuring alkaline phosphatase (ALP) activity, calcium deposition, and collagen production. Additionally, a scratch assay was used to investigate the potential of the modified microbeads to support cell migration.

Materials and Methods

Calcium carbonate microbeads were fabricated with the addition of 20% (w/v) heparin (HP) or tinzaparin (TP), with or without 10% (w/v) magnesium incorporation. The structural properties of the materials were analysed using Fourier-transform infrared spectroscopy (FTIR) and X-ray diffraction (XRD), while their microstructure was evaluated by scanning electron microscopy (SEM). Biological evaluation was performed to assess the osteogenic and angiogenic potential of the obtained materials. Osteogenic properties were determined using alkaline phosphatase (ALP) activity, cumulative calcium deposition, and collagen production assays.

Results

FTIR analysis confirmed the successful incorporation of HP and TP into the microbeads' structure. XRD results indicated that only pure $CaCO_3$ and $CaCO_3$-HP samples exhibited the vaterite phase, whereas all other samples were characterised by the calcite phase. The incorporation of magnesium resulted in a shift of 2θ peaks toward higher values. SEM observations revealed that magnesium addition disrupted the crystallisation process, leading to the formation of larger microbeads. All tested materials enhanced ALP activity compared to the control, with the highest values observed for samples without magnesium. Cumulative collagen production and calcium deposition were most pronounced in samples containing TP. Similarly, the scratch assay demonstrated the highest cell migration potential for TP-modified microbeads.

Conclusion

Microbeads functionalised with tinzaparin exhibited the most favorable osteogenic properties. These findings suggest that TP-modified calcium carbonate materials are promising candidates for further investigation in bone tissue engineering applications, with additional potential to support cell migration.

Acknowledgements

This study was supported by the Program "Excellence Initiative – Research University" for the AGH University of Krakow, the subsidy (No 16.16.160.557) for the AGH University of Krakow

D1 – P170

Injectable liquid bioactive matrix enables cytocompatible silica delivery and hybrid MBGN-based osteoinductive platforms for bone regeneration

Mahmoudifard M.[1], Andrade J.C.[1,2], Kito L.T.[2], Boccaccini A.R.[1], Thim G.P.[1,3]
[1]Institute of Biomaterials, Dept. of Materials Science and Engineering, Friedrich-Alexander-Universität Erlangen-Nürnberg (FAU), Erlangen, Germany; [2]Federal University of Santa Catarina (UFSC), Florianópolis, Brazil; [3]Instituto Tecnológico de Aeronáutica (ITA), São José dos Campos, Brazil

Introduction

Minimally invasive biomaterials that can adapt to irregular defects and stimulate bone formation in situ are highly attractive for regenerative therapies, particularly for difficult-to-access skeletal sites such as the spine and for disorders associated with impaired bone remodelling, including osteoporosis. Soluble silica has long been associated with beneficial effects on bone biology, and orthosilicic acid, $Si(OH)_4$, has been shown to stimulate osteoblastic differentiation while modulating signalling pathways linked to osteogenesis and osteoclast regulation. Nevertheless, the biological utility of soluble silica is strongly dose-dependent, and earlier studies identified only a relatively narrow concentration range as cytocompatible and osteogenic. Mesoporous bioactive glass nanoparticles (MBGNs) provide an additional advantage through their high surface area, controlled ion release, and capacity to act as nucleation sites for hydroxyapatite formation, but their application is often tied to solid scaffold-based systems. In the present work, we introduce an injectable liquid bioactive matrix (LBM) based on $Si(OH)_4$ conceived to transport, stabilize, and modulate bioactive ionic species and to function either as a stand-alone osteoinductive liquid or as a carrier phase for MBGNs. This concept establishes a modular platform comprising ionic, particulate, and hybrid architectures, with the aim of combining immediate soluble-ion signalling with longer-term mineral-forming potential in minimally invasive bone-regenerative applications

Materials and Methods

LBM formulations were prepared from aqueous Si(OH)4 systems by adding osteogenic ions, and compared with mesoporous bioactive glass nanoparticles (MBGNs) and hybrid LBM-MBGN systems. A 50 ppm Si formulation, selected from the soluble-silica literature, was used as a reference, while optimized compositions were developed to increase silica loading without loss of cytocompatibility. The in vitro evaluation was performed in a stepwise manner. Cytocompatibility and adhesion were first assessed after 24 h by Live/Dead staining, cell attachment, and spreading. Metabolic activity and proliferation were then analysed from 48 h to 3 days to define the cytocompatibility threshold of Si/Ca/MBGN formulations. Early osteogenic differentiation was evaluated after 7–10 days by ALP activity and ALP staining, while gene expression analysis of RUNX2, COL1A1, OPN, OCN, and NF-κB-related pathways was used to investigate osteogenic and inflammatory signalling. Late mineralization was finally assessed after 21 days by Alizarin Red S staining. This design enabled comparison of ionic, particulate, and hybrid systems with respect to cytocompatibility, signalling activity, and osteogenic potential.

Results

Preliminary results showed a marked composition-dependent biological response of the liquid bioactive matrix formulations. Whereas Si(OH)4-only systems displayed a limited cytocompatible range, ion-modified formulations tolerated substantially higher soluble silica concentrations without evidence of acute cytotoxicity in the initial screening. The optimized LBM extended the usable silica concentration range from approximately 128 ppm to 625 ppm, corresponding to an approximately four-fold increase over the literature-derived reference condition. Qualitative cell morphology and metabolic activity data further supported a more favourable early cellular response in the ion-modified groups. These findings suggest that ionic modification plays a stabilizing role in defining the biological tolerance window of soluble silica and support the further evaluation of LBM-based ionic, particulate, and hybrid systems in osteogenic studies.

Conclusion

These preliminary findings identify the liquid bioactive matrix as a promising injectable platform for bone regeneration. By broadening the cytocompatible range of soluble Si(OH)4 through ionic modification, the system addresses a key limitation of conventional silica-based formulations and provides a basis for the development of modular ionic, particulate, and hybrid bioactive systems.

Acknowledgements
The authors acknowledge the support of the Institute of Biomaterials, Friedrich-Alexander-Universität Erlangen-Nürnberg (FAU), the PROBAL/CAPES-DAAD collaboration, and FAPESP (grant no. 2023/18405-9).

D1 – P171

Development and evaluation of a decellularized human bone scaffold for skeletal repair and reconstruction

Menini A.[1], Izzo G.[1], Romano V.[1], Sacco A.M.[1], Ricci G.[2], Nurzynska D.[3], Sorrentino C.[1], De Giovanni R.[1], Di Meglio F.[1], Castaldo C.[1]
[1]Dept. of Public Health, University of Naples Federico II, Naples; [2]Dept. of Experimental Medicine, Università della Campania, Napoli; [3]Dept. of Medicine, Pharmacy and Dentistry, University of Salerno, Baronissi, Italy

Introduction

The extracellular matrix (ECM) is a crucial component of biological tissues, providing both structural support and biochemical signals that regulate cellular activities such as adhesion, proliferation, migration, and differentiation. In bone, the ECM constitutes approximately 90–95% of the total volume, it surrounds and sustains resident cells, confers mechanical strength and rigidity, and maintains the complex three-dimensional architecture necessary for proper skeletal function. Reproducing the structural and biological complexity of native bone ECM remains a central challenge in tissue engineering and regenerative medicine. Although synthetic biomaterials have significantly advanced, they still fall short of replicating the heterogeneity and functional properties of natural bone ECM. As a result, naturally derived scaffolds from biological tissues have gained prominence, as they preserve native biochemical cues and microstructural organization, making them highly suitable for bone repair and regeneration. This study presents a reliable and reproducible method for generating decellularized ECM (d-ECM) from human trabecular bone for applications in tissue engineering, regenerative medicine, and orthopedic research.

Materials and Methods

Bone samples were obtained from the humeral heads of patients undergoing orthopedic surgery (n=9). The samples were decalcified using a 14% EDTA solution, then trimmed and subjected to a decellularization process, using a combination of sodium dodecyl sulfate (SDS), Triton X-100 and antibiotics, under constant agitation. The effectiveness of decellularization was evaluated through histological analysis and quantification of residual double-stranded DNA (dsDNA), a key indicator of cellular remnants. Additionally, the structural and biochemical integrity of the d-ECM was assessed using SEM, histochemical staining, immunohistochemistry, and quantitative assays to confirm the preservation of essential matrix components and architecture. Biocompatibility was tested in vitro using human adipose-derived mesenchymal stem cells (hADMSCs) obtained from sixteen patients undergoing abdominoplasty. Cells were seeded onto the d-ECM scaffolds, and their viability was measured using Trypan Blue exclusion and CellTiter-Glo luminescence assays, which assess cell survival and metabolic activity.

Results

Results demonstrated complete removal of cellular nuclei and low residual dsDNA levels (30.6 ± 2.14 ng/mg), confirming effective decellularization. Staining techniques, including Masson's trichrome, Mallory, and Van Gieson, and quantitative specific assays showed preservation of the ECM's three-dimensional architecture and protein composition. Furthermore, hADMSCs viability onto bone d-ECM scaffolds exceeded 90%, indicating excellent cytocompatibility.

Conclusion

Overall, the study validates an effective protocol for producing structurally preserved and biocompatible d-ECM from human trabecular bone, highlighting its strong potential for applications in bone repair, reconstruction, and regenerative therapies.

D1 – P172

High shape fidelity 3D printed scaffolds from sustainable marine-derived materials for bone tissue engineering

Serafim A.[1], Olaret E.[1], Vasile B.S.[2], Dobranici A.-E.[3], Dinescu S.[3] Stancu I.C.[4,5]
[1]APMG, CAMPUS Research Institute, NUSTPB; [2]National Research Center for Micro and Nanomaterials, Faculty of Chemical Engineering and Biotechnologies, NUSTPB; [3]Dept. of Biochemistry and Molecular Biology, University of Bucharest; [4]APMG, Faculty of Chemical Engineering and Biotechnologies, NUSTPB; [5]Faculty of Medical Engineering, NUSTPB, Bucharest, Romania

Introduction

The development of sustainable, marine-derived biomaterials for bone tissue engineering (BTE) represents a promising alternative to synthetic and mammalian-derived scaffolding systems. Starting from previous work of our group on fish gelatin (FG)-based composite inks, we report the formulation of a novel bioinspired paste composed of diatomite earth - a natural source of biosilica and cold-water fish skin gelatin. The study demonstrates the printability of this bioinspired high viscosity ink and investigates the physicochemical and structural properties of the 3D printed scaffold.

Materials and Methods

The composite ink was prepared by mixing the two components: biosilica and 50%wt FG solution in a mass ratio of 1.56:1. The rheological behavior of the paste-like ink was characterized through viscosity measurements and thixotropy tests. Printability was assessed via filament drop test, spreading ratio (Sr), and printability index (Pr). Four scaffold architectures were fabricated by extrusion-based technology combining two filament path strategies - linear (L) and curvilinear (C) - with two inter-filament spacings (1 mm and 0.5 mm). Scaffolds characterization included morphological and architectural evaluation through micro-CT and SEM/EDAX investigations, crosslinking efficiency through gel fraction (GF), behaviour in simulated physiological conditions investigated through maximum swelling degree (MSD) and degradation degree (DD) in PBS, pH7.4 at 37°C, and mechanical properties by uniaxial compression tests. Cytocompatibility and the ability to stimulate osteogenic differentiation *in vitro* was also investigated.

Results

Sr values of 0.7–0.8 and Pr values of 1.15–1.26 confirmed adequate printability. Micro-CT revealed fabrication-induced intra-filament open porosity of 11% (2–46 μm), generated intrinsically without freeze-drying. Among the four architectures, L1 most closely mimicked human trabecular bone porosity (52.3%, pore sizes 604–909 μm). The recorded elastic moduli ranged between 0.78–1.09 MPa. Curvilinear scaffolds demonstrated superior stability in PBS (C1: 97.37%; C05: 96.59%) compared to linear configurations (L1: 89.57%; L05: 88.73%). All scaffolds showed good biocompatibility and sustained osteodifferentiation.

Conclusion

The bioinspired ink enables self-supporting extrusion at ambient temperature, generating intrinsic porosity covering 2–909 μm without post-processing steps. Curvilinear scaffold architectures demonstrated superior degradation resistance attributed to their greater filament network connectivity. All scaffolds exhibited good biocompatibility and sustained osteodifferentiation, establishing this sustainable marine-derived composite as a promising platform for bone tissue engineering with tunable architecture.

Acknowledgements

This research was funded through PN-IV-P7-7.1-PED-2024-2663, no. PED44/2025 and ERANET-M-3-Cellu4Heal. The 3D printing, and micro-CT tests were possible due to ERDF/COP 2014-2020, ID P_36_611, MySMIS 107066, INOVABIOMED.

D1 – P173
PTHrP-functionalized hyaluronic acid hydrogels for growth plate biomimicry

Choi Y.S., Kim J.S., Lee K.Y.
Dept. of Bioengineering, Hanyang University, Seoul, Republic of Korea

Introduction
Biomimicking the hierarchical structure of the growth plate remains challenging, as its highly organized zones require strict spatial regulation of chondrocyte proliferation and hypertrophic differentiation. In the native proliferative zone in the growth plate, parathyroid hormone-related protein (PTHrP) is critical for maintaining chondrocyte proliferation and delaying hypertrophy. Although soluble PTHrP can modulate chondrocyte behavior, its rapid diffusion from conventional hydrogel scaffolds restricts stable and localized biochemical signaling. To overcome this, we developed a PTHrP-immobilized hyaluronic acid (HA)-based hydrogel system to regulate the proliferative activity of chondrocytes, aiming to engineer a biomimetic, proliferative zone-like microenvironment.

Materials and Methods
Carbodihydrazide-modified HA (HA-CDH) and oxidized diol-modified HA (odHA) were synthesized to fabricate self-healing hydrogels through dynamic hydrazone bond formation. PTHrP was chemically immobilized onto HA-CDH using carbodiimide chemistry, and the resulting conjugate was crosslinked with odHA to form hydrogels. ATDC5 cells were encapsulated within these hydrogels and cultured in vitro. Cell viability and proliferation were comprehensively evaluated using live/dead assay, histological analysis, and cell counting compared against a soluble PTHrP-treated group. Furthermore, the gene expression levels of key chondrogenic and hypertrophic marker genes (SOX9, COL2, and COL10) were quantitatively assessed.

Results
The HA-based hydrogel system provided a cytocompatible three-dimensional environment for ATDC5 cells, successfully maintaining its structural integrity during the culture period. The chemical immobilization of PTHrP ensured the localized presentation of biochemical cues within the hydrogel network. Consequently, PTHrP-immobilized hydrogels showed enhanced ATDC5 cell proliferation compared to non-treated controls. Furthermore, the presence of PTHrP effectively suppressed the hypertrophic tendency of the cells. These findings demonstrated that PTHrP-immobilized HA hydrogels were a highly promising platform for establishing a proliferative zone-like microenvironment in growth plate-mimetic scaffolds.

Conclusion
PTHrP-immobilized HA hydrogels enhanced ATDC5 cell proliferation within a three-dimensional culture environment. By enabling the localized and sustained presentation of PTHrP, this hydrogel system provided the spatially controlled biochemical cues essential for regulating chondrocyte behavior. Overall, this approach offers a promising strategy for engineering multilayered, 3D-bioprinted growth plate-mimetic hydrogel scaffolds.

References
[1]Kim H.S., Kim J.S., Hwang J.W., Lee I.Y., Lee K.Y. Decoupling stiffness and toughness of self-healing hydrogels for complex tissue regeneration via 3D bioprinting. *Chemical Engineering Journal* 2024; 487; 150551.

D1 – P174

Fabrication of compartmentalized bone tissue construct by using 3D dual bioprinting

Rinnekari K.[1,2], Ohlsbom R.[1,2], Dixit K.[1,2], Hopia K.[3,4], Puistola P.[3], Mörö A.[3], Massera J.[5], Koivisto J.T.[6], Miettinen S.[1,2]

[1]Adult Stem Cell Group, Faculty of Medicine and Health Technology, Tampere University; [2]Tays Research Services, Wellbeing Services County of Pirkanmaa, Tampere University Hospital; [3]Eye Regeneration Group, Faculty of Medicine and Health Technology, Tampere University; [4]Chemistry and Advanced Materials, Faculty of Engineering and Natural Sciences, Tampere University; [5]Bioceramics, Bioglasses and Biocomposites Group, Faculty of Medicine and Health Technology, Tampere University; [6]Biomaterials and Tissue Engineering Group, Faculty of Medicine and Health Technology, Tampere University, Tampere, Finland

Introduction

Current treating options of bone defects rely on autografts and synthetic implants, which are limited by issues related to donor site complications, limited availability, inadequate bioactivity, and poor biodegradability. Bone tissue engineering provides a promising alternative by combining cells, biomaterials, and bioactive cues. Among emerging technologies, three-dimensional (3D) bioprinting enables fabrication of cell-laden constructs with tunable architecture and composition, supporting the development of patient- and defect-specific implants. In particular, dual material bioprinting allows spatial organization of distinct compartments, more closely replicating the hierarchical complexity of native bone tissue.

Hyaluronic acid (HA)-based bioinks supplemented with collagen type I support osteogenic differentiation, while the incorporation of cellulose nanofibers (CNF) improves the rheological properties and mechanical strength, in addition to, offering a fibrous structure resembling native extracellular matrix. Additionally, bioactive glass (BaG), particularly S53P4, is well-known to stimulate osteogenesis through the release of biologically active ions such as calcium and silicon.

This study aimed to fabricate compartmentalized bone tissue constructs using extrusion-based 3D dual bioprinting combining cell-laden, animal-free bioink containing human bone marrow stem/stromal cells (BMSCs), with a stiffer acellular animal-free ink.

Materials and Methods

Compartmentalized constructs, combining distinct cellular and acellular compartments, were produced via extrusion-based dual bioprinting (Fig.1.). The cell-laden bioink consisted of human BMSCs embedded in an HA-based bioink supplemented with collagen type I and CNF. The acellular compartment utilized a modified HA-based bioink containing collagen type I with higher concentrations. Constructs were cultured in osteogenic medium supplemented with S53P4 BaG dissolution products. Cell viability and morphology were assessed using a Live/Dead assay, and osteogenic differentiation was evaluated by immunocytochemical analysis of specific osteogenic markers.

Results

The human BMSCs remained viable throughout the bioprinting process and subsequent culture period. The cells exhibited elongated morphology and expressed key osteogenic markers, including osteocalcin and collagen type I. The compartmentalized architecture of the constructs was retained throughout the culture.

Conclusion

This study demonstrates the successful fabrication of compartmentalized constructs using extrusion-based 3D dual bioprinting. The observed cell viability, morphology, and marker expression suggest the early osteogenic differentiation within the fabricated constructs. Furthermore, this biofabrication approach shows strong potential for engineering more complex, multi-tissue structures, including the integration of vascular components alongside osteogenic regions, advancing the development of functional engineered bone tissue.




Figure 21. Schematic description of the used inks and fabricated constructs. Created in BioRender.com. Scale bar: 500 µm. BMSC: bone marrow stem/stromal cells, CNF: cellulose nanofibers, HA: hyaluronic acid, *: different modifications.

D1 – P175

A shrinkage-free, antibacterial and osteogenic electrospun composite scaffold for bone tissue engineering

Sedaghat A., Shokrolahi P., Shokrolahi F.*
Dept. Biomaterials, Institution IPPI, Tehran, Iran

Introduction

Electrospun poly (lactic-co-glycolic acid) (PLGA) scaffolds are widely investigated for biodegradable biomedical devices due to their favorable biocompatibility and tunable degradation behavior[1]. However, significant dimensional shrinkage under physiological conditions remains a major limitation for tissue engineering such as bone tissue applications[2-4]. This study presents a combined structural and compositional strategy to eliminate shrinkage in electrospun PLGA scaffolds by integrating strontium-doped hydroxyapatite (St-HAp) nanoparticles, and a multilayer fiber-orientation design. Strontium is a natural element that can increase the activity of osteoblasts while reducing the function of osteoclasts[5].

Materials and Methods

PLGA electrospun mats were fabricated using hexafluoroisopropanol as solvent. The influence of fiber orientation on dimensional stability was investigated using random (R), oriented (O), and oriented-random-oriented (ORO) architectures. St-HAp nanoparticles were synthesized (FTIR spectrum of the Sr-doped HA particles is shown in Figure 1) and incorporated into PLGA at different concentrations (1, 2, 4 wt%) to enhance structural stability. Scaffold shrinkage was evaluated after incubation in phosphate-buffered saline (PBS, pH 7.4) at 37 °C for 24 h. Surface area changes before and after incubation were used to calculate shrinkage. Based on the optimal formulation, 0.5 wt% chitosan was subsequently introduced to investigate its influence on scaffold performance.




Figure 1. FTIR spectrum of Sr-HAp particles.

Results

Pure randomly oriented PLGA scaffolds exhibited severe dimensional contraction, with shrinkage reaching 74.6 ± 3.7%. Alignment of fibers reduced shrinkage to 53.2 ± 4.3%, indicating the beneficial effect of molecular orientation generated during electrospinning. Incorporation of HAp nanoparticles further improved dimensional stability, with 2 wt% HAp providing the optimum performance and reducing shrinkage to 35.5 ± 4.6%. Higher nanoparticle loading (4 wt%) resulted slight increase in shrinkage, likely due to the nanoparticles aggregation.

A more substantial improvement was achieved through multilayer structural engineering. The ROR architecture reduced shrinkage to 6.4 ± 2.1%, whereas the ORO configuration decreased shrinkage to only 1.9 ± 1.8%. Remarkably, incorporation of 0.5 wt% chitosan into the ORO-PLGA/HAp scaffold eliminated measurable shrinkage under physiological conditions.

The enhanced dimensional stability can be attributed to synergistic effects between the nanoparticles reinforcement and fiber-orientation control. HAp nanoparticles act as reinforcing fillers and nucleating agents, restricting polymer-chain mobility and promoting structural stability. Simultaneously, highly oriented outer layers generated under elevated collector speeds induce stress-assisted crystallization and reduce relaxation of polymer chains during hydration. The ORO architecture effectively balances internal stresses throughout the scaffold thickness, thereby preventing contraction in aqueous environments.

Conclusion

The combination of St-HAp reinforcement and multilayer fiber-orientation engineering provides an effective strategy for eliminating physiological shrinkage in electrospun PLGA scaffolds. The optimized ORO-PLGA/chitosan/HAp structure exhibited virtually zero shrinkage in PBS while maintaining desirable mechanical characteristics.

Fiber Orientation Engineering Combined with Sr-Doped Hydroxyapatite Enables a Shrinkage-Free Osteogenic Electrospun Scaffold

References

[1]Oliveira Castro V., Livi S., Sperling L.E., Garrido dos Santos M., Merlini C. Biodegradable Electrospun Conduit with Aligned Fibers Based on Poly (lactic-co-glycolic Acid) (PLGA)/Carbon Nanotubes and Choline Bitartrate Ionic Liquid, ACS Applied Bio Materials, Cite this: ACS Appl. *Bio Mater* 2024; 7, 3, 1536–1546.
[2]Engineering Antibacterial Shrinkage-free Trinary PLGA-Based GBR Membrane for Bone Regeneration. *Polymers for Advanced Technologies* 2024; 35, 1; e6263.
[3]Rabbandoust A., Shokrolahi F., Shokrolahi P., Barzin J., Hosseini S. Engineering antibacterial shrinkage-free trinary PLGA-based GBR membrane for bone regeneration. 2024; 35, 1; e6263.
[4]Abdelhakk H.M., Issa A., Shin C.S., Zhan F. Melt-Extruded Paclitaxel Nanocrystal-Loaded Sutures for Sustained Local Drug Delivery. *Pharmaceutical Research* 2026. https://doi.org/10.1007/s11095-026-04075-7.
[5]Prabha R.D., Nair B.P., Ditzel N., Kjems J., Nair P.D., Kassem M. Strontium functionalized sca2old for bone tissue engineering. *Materials Science and Engineering: C* 2019; 94; 509–515.

D1 – P176

Exploring the effects of human bone-derived ECM hydrogels on the crosstalk between endothelial cells and bone stromal cells in vascular osteogenesis

Doulah A.[1], Kanczler J.[2], Kim Y.[2]
[1]University of Southampton, Southampton; [2]Bone and Joint Research Group in Human Development and Health University of Southampton, Southampton, UK

Introduction

The current gold-standard of treatment for critical-sized bone defects, which fail to heal spontaneously leading to non-union formation, remains autologous bone grafts. However, this intervention carries a high risk of post-operative complications.

Human-bone derived extracellular matrix (bECM) hydrogels provide a therapeutic alternative, which has demonstrated significant osteogenic potential due to its ability to maintain the diverse structural and functional composition of native bECM.

However, previous studies have focused on singular cell type performance within these gels, failing to recognise the vital cross talk between endothelial cells (angiogenic) and bone forming cells (osteogenic) to form healthy bone with sufficient vascular supply.

This study aims to evaluate the influence of a bECM hydrogel matrix on the crosstalk between these two cell types.

Materials and Methods

We evaluated the osteogenic and angiogenic potential of human bone marrow stromal cells (HBMSCs) and human umbilical vein endothelial cells (HUVECs) within 2D monocultures and co-cultures on the surface of bECM hydrogels, using histochemical staining and proteomic analysis compared to tissue culture plastic (TCP) (negative) and type I collagen (positive) controls.

Results

Our results demonstrate co-culturing HBMSCs and HUVECs leads to enhancement of early vascular osteogenesis, including increased levels of von Willebrand Factor and alkaline phosphate. However, we demonstrated the presence of a bECM hydrogel limits the crosstalk between these two cell types, hindering these factors in vascular osteogenesis compared to TCP controls. However, bECM hydrogels promoted cell proliferation in co-cultures, enhanced HBMSCs enzymatic bECM remodelling activity in mono/co-cultures and promoted osteogenic activity in HBMSCs monocultures.

Conclusion

This study provides further evidence for crosstalk enhancement of vascular osteogenesis by endothelial cells and bone forming cells. Additionally, it provides understanding of potential mechanisms of action of bECM hydrogels in an in vivo environment, influencing cell-cell and cell-bECM interactions, translating to further optimisation of bECM hydrogels for potential clinical application.

D1 – P177

Shear stress-driven Vascularization and osteogenesis in a co-cultured 3D bone regeneration model

Jieun K., Young Min S., Jung Bok L.*
Dept. of Biological Science, Research Institute of Women's Health, Brain Korea 21 Project, Sookmyung Women's University, Seoul, Republic of Korea

Introduction


Bone regeneration requires the coordinated development of mineralized tissue and a functional vascular network, both of which are strongly influenced by the local mechanical microenvironment. Among various biophysical cues, fluid shear stress plays a critical role in regulating cellular behavior, including osteogenic commitment and endothelial organization. However, its integration into pre-vascularized bone tissue engineering systems remains insufficiently explored.

Materials and Methods

Adipose-derived stem cells (ADSCs) and human umbilical vein endothelial cells (HUVECs) were used to generate ADSC spheroids with AggreWell™800 (STEMCELL Technologies). Chips were designed in Autodesk Fusion 360 and fabricated by DLP 3D printing using professional gray resin, followed by PDMS mold formation after UV curing. After cell loading, the chip cultured under fluidic shear stress for 14 days. Total RNA was isolated from static and microfluidic culture samples, reverse-transcribed to cDNA, and analyzed by SYBR Green-based qRT-PCR with gene-specific primers. Expression was normalized to GAPDH and calculated by the 2-ΔΔCt method. Statistical analyses were performed using GraphPad Prism 10; unpaired two-tailed t-tests were used for between-group comparisons, with significance defined as $P<0.05$.

Results

Live/Dead staining showed higher cell viability in the fluidic shear stress group than in the non-stimulated group. Dynamic culture also increased VEGF utilization in EGM compared with static culture, suggesting enhanced angiogenic factor consumption under flow conditions. qRT-PCR analysis after 14 days revealed marked up-regulation of osteogenic and angiogenic markers, including OPN, RUNX2, VE-cad, and Flk-1, in the shear stress group relative to static controls. Fluorescence imaging further showed improved vascular network formation and increased tissue density under perfusion culture, with longer vessel structures and stronger CD31, Col1a, and RUNX2 signals.



Conclusion

These findings indicate that combining ADSC spheroid self-assembly, endothelial co-culture, and fluid shear stress can enhance both vascular network formation and osteogenic differentiation in a 3D bone regeneration model. This biomimetic platform may provide a promising strategy for engineering pre-vascularized bone grafts with improved structural and functional readiness prior to implantation.

Acknowledgements

Chronic and Metabolic Diseases Research Center (CMDRC)
Research Institute of Women's Health (RIWH)

References

[1]Mercado-Pagán Á.E., Stahl A.M., Shanjani Y., Yang Y. Vascularization in bone tissue engineering constructs. *Annals of Biomedical Engineering* 2015; 43(3); 718–729.
[2]Jiang M., Shen Q., Zhou Y., Ren W., Chai M., Zhou Y., Tan W. Fluid shear stress and endothelial cells synergistically promote osteogenesis of mesenchymal stem cells via integrin β1-FAK-ERK1/2 pathway. *Turkish Journal of Biology* 2021; 45(6); 683–694.

D1 – P178

Non-thermal plasma-assisted immobilization of nanohydroxyapatite on electrospun polycaprolactone nanofibers for bone tissue engineering

Hoebus L., Ver Heyen W., Aliakbarshirazi S., Morent R., Ghobeira R., De Geyter N.
Research Unit Plasma Technology, Faculty of Engineering and Architecture, Ghent University, Ghent, Belgium

Introduction

With an aging population, the prevalence of musculoskeletal disorders continues to grow. To address these conditions, bone grafts are often required. However, current grafting techniques have limitations, highlighting the need for better alternatives. Nanofibrous scaffolds combined with nanohydroxyapatite (nHA) particles present a promising solution due to their enhanced osteoinductivity, osteoconductivity, and osseointegration. However, the efficient incorporation of nHA particles onto nanofibers (NFs) remains challenging. Current strategies often rely on prolonged immersion times or multiple dipping cycles, generating considerable waste and leading to time-consuming processes. This study aims to develop a simple and effective strategy for incorporating nHA particles onto polycaprolactone (PCL) NFs using non-thermal plasma treatment. Non-thermal plasma efficiently introduces functional groups onto the NF surface which can subsequently interact with nHA particles, enabling a straightforward immobilization process.

Materials and Methods

PCL NFs were fabricated from a 24 wt% PCL solution, dissolved in a mixture of formic acid and acetic acid (9:1). The NFs were activated by a dielectric barrier discharge plasma using either air (0-20 s) or N_2 (0-150 s). Water contact angle (WCA) analysis was used to determine the optimal treatment time. Next, samples were developed at this optimal treatment time and immersed in a 1 wt% nHA solution for 1, 2 and 4 hours. Finally, the samples were rinsed and dried and further characterized using scanning electron microscopy (SEM), X-ray photoelectron spectroscopy (XPS) and Fourier transform infrared spectroscopy (FTIR).

Results

After plasma treatment, SEM images showed no morphological changes to the NFs. XPS results indicated that air and N_2 plasma treatment introduced different surface chemistries. Air plasma treatment mostly incorporates oxygen-containing functional groups while N_2 plasma treatment mostly introduces nitrogen-containing functional groups. After immersion in nHA, FTIR, SEM and XPS measurements showed negligible nHA attachment on untreated NFs. Similarly, the nHA attachment on the N_2 plasma-treated NFs remained limited. In contrast, air plasma-treated samples showed excellent nHA retention while preserving the porous NF structure after 1 and 2 hours of immersion. However, after 4 hours of immersion, SEM images showed significant pore obstruction. As such, a 1 hour immersion was selected as optimal, as it achieves effective nHA incorporation in the shortest time frame while preserving porosity. These results highlight the key role of the type of plasma-induced surface functional groups in governing nHA attachment to PCL NFs.

Conclusion

These results demonstrate that air plasma treatment can efficiently activate PCL NFs, enabling enhanced nHA immobilization.

Acknowledgements

This work was supported by the Research Foundation-Flanders (FWO) (G0AG525N and G0A7N24N)

D1 – P179

Celecoxib-loaded 3D printed drug delivery systems for orthodontic implants

Markhoff J.[1], Eickner T.[1], Sannan A.[2], Riess A.[2], Seitz H.[2,3], Grabow N.[1,3], Teske M.[1]
[1]Institute for Biomedical Engineering, Rostock University Medical Center; [2]Chair of Microfluidics, University of Rostock, Rostock, Germany; [3]Dept. Life, Light & Matter (LLM), University of Rostock, Rostock, Germany

Introduction

Orthodontic implants are widely used as temporary anchorage devices but may induce local inflammatory reactions that impair peri-implant bone stability. Local drug delivery systems integrated into implant-associated biomaterials could help modulate inflammation and support bone regeneration. Cyclooxygenase-2 (COX-2) inhibitors such as celecoxib have demonstrated anti-inflammatory potential and may influence osteogenic responses.

Aim

This study investigates the feasibility of 3D-printed poly(ethylene glycol) diacrylate (PEGDA) copolymer structures as potential drug delivery platforms for celecoxib in orthodontic implants.

Materials and Methods

N-Hydroxyethyl-acrylamid (HEAA, monomer), PEGDA (crosslinker, MW = 250 g/mol), Lithium phenyl-2,4,6-trimethylbenzoylphosphinate (LAP, photoinitiator) and Chlorophyllin, coppered trisodium salt, were prepared in various compositions and processed using Digital Light Processing (DLP) to fabricate test specimens. The biocompatibility of the printed materials was evaluated using both eluate and direct-contact approaches with human osteoblasts and THP-1 monocyte-derived cells. Celecoxib was tested separately to determine its cellular effects at concentrations ranging from 1–10 µg/mL to isolate its effect from the 3D-printed material. Cell behavior was assessed by real-time impedance monitoring and metabolic viability assays. Cytoskeletal organization and cell morphology were analyzed using phalloidin/DAPI staining. Inflammatory mediator profiles were investigated using a multiplex bead-based immunoassay (MACSPlex). In addition, an *in vitro* bone inflammation model was conducted to further evaluate the immunomodulatory effects of celecoxib under inflammatory conditions. Finally, 3D-printed specimens were combined with celecoxib to enable localized drug delivery.

Results

Preliminary data indicate good cytocompatibility of the HEAA-PEGDA materials in both eluate and direct contact conditions depending on material composition. Celecoxib exposure showed concentration-dependent effects on osteoblast and THP-1 cell responses, with indications of altered inflammatory mediator expression in immune cells. Cytoskeletal staining revealed preserved cell morphology at lower drug concentrations, supporting the potential applicability of the investigated range.

Conclusion

These findings suggest that 3D-printed HEAA-PEGDA-containing structures represent promising candidates for localized drug delivery around orthodontic implants. Incorporation of celecoxib may provide a strategy to modulate inflammatory responses and improve peri-implant tissue integration. Ongoing studies will investigate drug loading and release behavior as well as the performance of celecoxib-loaded constructs in inflammatory bone models.

Acknowledgements

The funding within the Central Innovation Programme for Small and Medium-Sized Enterprises (ZIM) of the German Federal Ministry for Economic Affairs and Energy (FKZ: KK5364801RU1) is gratefully acknowledged.

D1 – P180

Modular Synthesis of Large Poly(amide-carbosilane) Dendrimers Approaching Virion Dimensions

Konhefr M., Edr A.1, Krupková A.1, Červenková Šťastná L.1, Bernášková J.1, Strašák T.
Institute of Chemical Process Fundamentals, The Czech Academy of Sciences, Prague, Czech Republic

Introduction

Dendrimers represent a unique class of well-defined macromolecules with high structural precision, tunable surface functionality, and potential for biomedical applications, including drug delivery and regenerative medicine. However, the synthesis of dendrimers, particularly the larger ones, remains challenging, often limited by purification difficulties and the presence of structural defects. We introduced a modular approach to the synthesis of poly(amide-carbosilane) (PAMCAS) dendrimers1, enabling rapid growth and fine-tuning of internal architecture, which is particularly relevant for nanomedicine applications requiring control over dispersity, size, surface charge, etc.

Materials and Methods

The dendrimers were synthesized using a combination of orthogonal reactions, namely amide coupling and thiol–ene click chemistry. A modular design based on AB_3 and AB_6 building blocks enabled systematic variation of branching density and molecular architecture. The synthesis protocol was complemented by organic solvent nanofiltration (OSN) as an essential and efficient purification method for the removal of low-molecular-weight impurities. Structural and physicochemical characterization was performed using NMR spectroscopy, dynamic light scattering (DLS), asymmetric flow field-flow fractionation (A4F), MALDI-HRMS mass spectrometry and other related techniques.

Results

The proposed strategy enabled the construction of dendrimers with high degree of branching and controlled size within fewer synthetic steps compared to conventional methods. Incorporation of AB_6 units significantly accelerated dendrimer growth and increased the number of terminal functional groups. The use of OSN proved to be a highly robust and scalable purification approach, addressing a key limitation in dendrimer synthesis. Physicochemical analyses confirmed narrow size distributions and predictable structural evolution across generations. Furthermore, we investigated the size limits of the protocol, enabling the preparation of water soluble, low-dispersity macromolecules with AB3 branching with MW exceeding 106 Da and dimensions approaching those of small virions.

Conclusion

Our work demonstrates an efficient approach to the synthesis of structurally controlled dendrimers in wide-range sizes for applications in regenerative medicine and nanomedicine. The ability to tune dendrimer architecture within a single generation, combined with a scalable purification process, enables access to high-generation megadalton systems with controlled density and internal structure.

Acknowledgements

We acknowledge the Ministry of Education, Youth, and Sports ExRegMed project CZ.02.01.01/00/22_008/0004562, cofounded by the European Union.

References

1Edr A., Konhefr M., et al. A Modular Synthetic Strategy toward Fast-Growing Poly(amide-carbosilane) Dendrimers Based on Click Chemistry and Organic Solvent Nanofiltration. ACS Polymers Au 2026; 6, 1; 454-467.

D1 – P181
A ready-to-use material for osteomyelitis management

Padrão T.[1,2,3], Dias J.[1,2], Carvalho A..[,2], Pinto M.T.[1,4], Monteiro F.J.[1,2,3], Sousa S.R.[1,2,5]
[1]i3S - Instituto de Investigação e Inovação em Saúde, Universidade do Porto; [2]INEB – Instituto de Engenharia Biomédica, Universidade do Porto; [3]FEUP- Faculdade de Engenharia, Universidade do Porto; [4]IPATIMUP – Instituto de Patologia e Imunologia Molecular, Universidade do Porto; [5]ISEP - Instituto Superior de Engenharia do Porto, Instituto Politécnico do Porto, Porto, Portugal

Introduction
Osteomyelitis is a severe bone ailment infection caused by pathogenic organisms, which poses a serious health issue, affecting millions of people worldwide. The standard treatment is often ineffective, and associated with severe side effects, involving at least two surgeries, one for debridement of infected bone and another one for bone reconstruction after systemic administration of antibiotics.

Aim
This work aims the development of lyophilized vancomycin-loaded heparinized nanohydroxyapatite/collagen granules to ease clinical application, eradication of infection due to local administration of antibiotics, and for bone regeneration.

Materials and Methods
A bone substitute delivery system was developed [1] and characterised as a better alternative relatively to the current treatment, but it is not yet commercially available.

Results
The lyophilisation process has proven to be effective with a controlled release of the antibiotic for an adequate period, above the minimum inhibitory concentration for methicillin-resistant Staphylococcus aureus (MRSA), compared with non-lyophilised granules.
This system totally inhibited the growth of planktonic and sessile MRSA (Figure 1). Moreover, the material promoted osteoblasts' metabolic activity and proliferation, while inducing neovascularisation.




Figure 1 – Antibacterial activity of lyophilised vancomycin-loaded heparinised nanohydroxyapatite/collagen granules after 24 h of incubation with Methicillin-resistant *Staphylococcus aureus* (MRSA). Quantification of A) planktonic bacteria, and B) sessile bacteria, both expressed in $\log_{10}$ (CFU/mL).

Conclusion
Overall, this work presents a trustworthy solution for clinical practice, by developing a ready-to-use drug-delivery system, avoiding the prior surgical preparation of materials. This solution has the potential to reduce the healing period, thereby improving patients' quality of life.

Acknowledgements
The authors acknowledge: the support of the i3S Scientific Platform Bioimaging, member of the PPBI (PPBI–POCI-01-0145-FEDER-022122), and in SEM by CEMUP. The provision of HAp (nanoXIM.HAp202) by FLUIDINOVA, S.A. (Portugal) is acknowledged. Finally, Tatiana Padrão, acknowledges to Fundação para a Ciência e a Tecnologia (FCT), Portugal, for the PhD grant (2020.09198.BD).
This work was financed by Portuguese funds through FCT/MCTES in the framework of the project "Institute for Research and Innovation Health Sciences UIDB/04293/2020". The project leading to these results have also received funding from Fundación Bancaria "la Caixa" (HECOLCAP - Code CI18-00021).

References
[1]Padrão T., Dias J., Carvalho A., Pinto M.T., Monteiro F.J., Sousa S.R.· Vancomycin-loaded bone substitute as a ready-to-use drug delivery system to treat osteomyelitis. *in Ceramics International* 2023*;* 49; 24771–24782.

D1 – P182

Effect of the synthesis method on the structure and bioactivity of borate glasses

Kozubal K., Gaćkowska-Gondek P., Dziadek M., Cholewa-Kowalska K.
Faculty of Materials Science and Ceramics, AGH University of Krakow, Poland

Introduction

Bioactive glasses are biocompatible and promote the formation of new bone tissue, supporting the regeneration process. They can be used as bone defect fillers, coatings for implants, scaffolds, dental cements and composites, contributing to the treatment of both soft and hard tissues. The most commonly used bioactive glasses are silicate-based glasses, which are primarily applied in bone tissue regeneration. However, due to their slow degradation rate and incomplete dissolution, they are less suitable for soft tissue regeneration. For this reason, alternative materials with faster degradation rates (phosphate or borate glasses) are being developed.
Bioactive borate glasses (BBGs) are a group of materials that can be used in the treatment of chronic wounds, provide controlled ion release, and serve as biodegradable scaffolds for cells. BBGs convert to hydroxyapatite (HA) much faster than silicate glasses, which gives them a significant advantage in medical applications. Boron is believed to influence bone growth and metabolic processes. The ion release process from bioactive glasses can also be utilized in soft tissue applications by stimulating natural healing mechanisms.

Aim

This study aims to synthesize and characterise bioactive borate glasses and to evaluate how different preparation methods affect their structural properties and bioactivity.

Materials and Methods

Bioactive borate glasses were prepared in a ternary oxide system using two different methods: conventional melt-quenching and the sol-gel technique. The materials were characterised in terms of their structure (FTIR, Raman), phase composition (XRD) and bioactivity (SEM, FTIR, ICP-OES).

Results

The obtained glasses exhibited differences in both structural features and morphology depending on the synthesis method (melt-derived / sol-gel). FTIR and Raman analyses confirmed the presence of borate structural units in all samples, while SEM microphotographs provided information about microstructure. These structural and morphological differences influenced their bioactivity. To evaluate bioactivity, the samples were immersed in simulated body fluid (SBF), and the formation of an apatite layer was an indicator of bioactive potential. The sol-gel derived glasses demonstrated enhanced bioactivity compared to melt derived ones, which can be attributed to their higher surface area and faster degradation rate in an aqueous environment.

Conclusion

The synthesized bioactive borate glasses show strong potential as therapeutic materials. Their properties suggest they could be effectively used in powder form to support the regeneration of both soft and hard tissues.

Acknowledgements

This work was supported by The National Science Centre, Poland grant no. 2024/55/I/ST11/00648 and within the program “Excellence Initiative – Research University” for the AGH University of Krakow.

D1 – P183

High-calcium bioactive borate glasses modified with copper for tissue engineering applications

Gaćkowska-Gondek P., Kozubal K., Dziadek M., Cholewa-Kowalska K.
Faculty of Materials Science and Ceramics, AGH University of Krakow, Poland

Introduction

Chronic and acute wounds remain a significant global healthcare challenge, affecting a substantial proportion of the population and requiring advanced therapeutic strategies. In response to the complex and dynamic nature of the healing process, modern wound dressings are evolving toward bioactive systems capable of actively modulating inflammation, cell migration, and tissue regeneration. Bioactive borate glasses (BBGs) represent a promising class of materials due to their rapid degradation, high reactivity and ability to convert into hydroxyapatite (HA). Compared to silicate-based glasses, BBGs exhibit enhanced dissolution rates and more complete transformation into HA. Additionally, the incorporation of therapeutic ions, such as copper, enables the design of multifunctional biomaterials with proangiogenic and antibacterial properties.

Aim

The aim of this study was to synthesize and characterize copper-modified bioactive borate glasses from the CaO–B_2O_3–P_2O_5 system and to evaluate their physicochemical properties and *in vitro* bioactivity.

Materials and Methods

Bioactive borate glasses from the CaO–B_2O_3–P_2O_5 system with the composition $40B_2O_3$–49CaO–$6P_2O_5$–5CuO (mol%) were synthesized using both conventional melt-quenching and the sol–gel method. Phase composition and crystallization tendencies were evaluated using X-ray diffraction (XRD), while Fourier transform infrared spectroscopy (FTIR) was employed to investigate the structural characteristics. Morphology and elemental composition were analyzed using scanning electron microscopy coupled with energy-dispersive spectroscopy (SEM–EDS). The *in vitro* bioactivity was assessed in simulated body fluid (SBF), and ion release kinetics were determined using inductively coupled plasma optical emission spectroscopy (ICP-OES).

Results

XRD analysis confirmed that all obtained materials were fully amorphous, with no detectable crystalline phases. FTIR spectra revealed the presence of boron structural units in both trigonal and tetrahedral coordination. SEM observations revealed a characteristic “cauliflower-like” morphology of the materials after immersion in SBF, while EDS analysis confirmed the formation of calcium–phosphate-rich phases. ICP-OES analysis showed the release of therapeutic ions and changes in phosphorus concentration, reflecting ongoing surface reactions and material transformation.

Conclusion

The obtained copper-doped bioactive borate glasses exhibit physicochemical properties suitable for biomedical applications, particularly in the context of wound healing and soft tissue regeneration. Their ability to undergo structural transformation in physiological conditions and release therapeutically active ions highlights their potential as multifunctional biomaterials.

Acknowledgements

This work was supported by The National Science Centre, Poland grant no. 2024/55/I/ST11/00648 and within the program “Excellence Initiative – Research University” for the AGH University of Krakow.

D1 – P184
Effect of the parameters of GelMA synthesis on the rheology and printability

Głuski G., Tabakoglu S., Moczulska-Heljak M., Zaszczyńska A., Kołbuk D.
Laboratory of Polymers & Biomaterials, Institute of Fundamental Technological Research, Polish Academy of Sciences, Warsaw, Poland

Introduction
Gelatin methacryloyl (GelMA) is a widely used biomaterial in tissue engineering due to its tunable physicochemical properties and biocompatibility. However, its performance in additive manufacturing strongly depends on synthesis and purification parameters, which influence rheological behavior and printability.

Aim
The aim of this study is to investigate the effect of GelMA synthesis parameters on its rheology and suitability for three-dimensional (3D) printing applications.

Materials and Methods
GelMA was synthesized using three different protocols and subjected to two purification methods to evaluate how processing conditions affect material properties. The obtained polymers were characterized using nuclear magnetic resonance (NMR) spectroscopy to confirm chemical structure, while viscosity measurements were performed to assess rheological behavior. Printability was evaluated based on extrusion stability and shape fidelity of printed structures. Cytotoxicity tests were also conducted to verify viability.

Results
The results demonstrate that both synthesis route and purification process significantly impact the rheological properties of GelMA, which directly determine its printability. Variations in viscosity and flow behavior influence extrusion performance and the structural integrity of printed constructs. These findings indicate that careful control of synthesis parameters and prevention of degradation on the level of synthesis is essential to optimize GelMA-based, noncytotoxic bioinks for additive manufacturing.

Conclusion
This work highlights the relationship between material processing and functional performance, providing guidance for the design of bio-based inks for tissue engineering applications, particularly in cartilage regeneration.

Acknowledgements
This research was supported by the M-ERA.NET 3 2024 call, financed by the European Union's Horizon 2020 research and innovation programme (grant agreement no. 958174) through the Polish National Science Centre (no. 2024/06/Y/ST11/00225).

D1 – P185

Development and characterization of bioinks for i*n situ* osteochondral regeneration through microextrusion and filamented light bioprinting

Torres García R.[1,2], Agten H.[1,2,3], Van Hoorick J.[3], Van Hoven I.[1,2], Häusner S.[4], Korpershoek J.[5], Ivkovic A.[6], de Vivans R.[7], Zenobi-Wong M.[8], Vozzi G.[9], Arslan A.[3], Bloemen V[1,2]
[1]Skeletal Biology and Engineering Research Center, KU Leuven, Leuven; [2]Prometheus, Division of Skeletal Tissue Engineering, KU Leuven, Leuven, Belgium; [3]BIO INX BV, Ghent, Belgium; [4]University Hospital Würzburg, Würzburg, Germany; [5]University Medical, Center Utrecht, Utrecht, The Netherlands; [6]University of Zagreb, Zagreb, Croatia; [7]European Fund Management Consulting, Tallinn, Estonia; [8]ETH Zurich, Zurich, Switzerland; [9]University of Pisa, Pisa, Italy

Introduction

Osteoarthritis is a degenerative disease affecting osteochondral tissue, leading to pain and joint dysfunction. Current treatments are limited, highlighting the need for innovative therapies. To address this challenge, we propose EndoFLight, a minimally invasive in situ 3D bioprinting platform that combines bioink microextrusion with filamented light (FLight) printing to precisely deposit and crosslink cell-laden photoresins at the injury site. This study presents the formulation and characterization of photoresins for EndoFLight technology.

Materials and Methods

Photoresins were developed using gelatin methacrylamide (GelMA, X-pure grade, Rousselot), either alone or blended with methacrylated hyaluronic acid (LifeCore Biomedical) or hydroxyapatite (CAM Bioceramics). These formulations were designed to regenerate cartilage and bone regeneration, respectively, with lithium phenyl-2,4,6-trimethylbenzoylphosphinate as the photoinitiator. Rheological properties of the photoresins were analyzed using an Anton Paar MCR 702 rheometer. Photocrosslinked bulk hydrogel samples (Dose = 250 mJ/cm^2, λ = 405 nm) were characterized in depth. Finally, FLight constructs were fabricated using a FLight bioprinting unit and analyzed using ImageJ to assess the microfilaments and microchannels generated by this novel technology.

Results

Most compositions exhibited an appropriate viscosity for the microextrusion system of EndoFLight (< 100 mPa*s) at 37°C. As for the compressive modulus, cartilage photoresins displayed values resembling the modulus of the perichondral space which guides chondrocytes in their matrix production. Except for the stiffest GelMA composition, all cell-laden hydrogels showed excellent biocompatibility (>70%) after 24h of encapsulation as assessed by in vitro LIVE/DEAD™ assays. FLight constructs were successfully fabricated with highly aligned microfilament and microchannel structures featuring diameters ranging from 2 to 20 µm (Fig. 1).

Conclusion

This characterization yielded critical insights into the material properties of the synthesized bone and cartilage resins, thereby informing the selection of suitable candidates for the research outlined in subsequent work for the EndoFlight technology.

Acknowledgements

Funded by the European Union (GA: 101191804). Views and opinions expressed are however those of the author(s) only and do not necessarily reflect those of the European Union or the European Health and Digital Executive Agency (HADEA). Neither the European Union nor the granting authority can be held responsible for them.




Fig. 1. Z-stack projection image of FLight construct fabricated through FLight printing technology. (A) highly aligned unidirectional microfilaments (arrows) and microchannel voids (arrowheads). (B) Distribution of microfilaments and percentage along the direction of projection defined as an angle between -10° and 10° from the peak of the orientation distribution.

D1 – P186

Characterization of surface properties, cytocompatibility, and immunomodulatory effects of 3D-printed hydroxyapatite/polycaprolactone composites for interaoral bone regeneration

Ivanets M.[1,2], Bekisz S.[1], Anania S.[2], Janssen C.[2], Hocquet S.[3], Kermel C.[3], Van hede D.[2], Lambert F.[2], Geris L.[1]
[1]Biomechanics Research Unit (BIOMECH), GIGA ULiège, Liège; [2]Dental Biomaterials Research Unit (d-BRU), ULiège, Liège; [3]Belgian Ceramic Research Centre, Mons, Belgium

Introduction

Tooth loss is frequently associated with alveolar bone resorption, often compromising dental implant placement. Guided bone regeneration (GBR) surgery is widely used to restore alveolar bone volume through the combination of a barrier membrane and a bone graft material that supports cellular attachment and bone neoformation. While deproteinized bovine hydroxyapatite (HA) particles remains the clinical gold standard, its particulate nature limits its mechanical stability and adaptation to large or complex bone defects. In this context, patient-specific 3D-printed HA/polycaprolactone (PCL) composites represent a promising alternative for personalized bone regeneration.

Aim

This study aimed to explore the suitability of 3D-printed HA/PCL composites with varying HA contents for intraoral bone regeneration by assessing their surface characteristics, cytocompatibility, and immunomodulatory properties.

Materials and Methods

The surface properties of 3D-printed HA/PCL discs with different HA/PCL ratios were characterized by contact angle measurements and scanning electron microscopy (SEM). Human bone marrow-derived mesenchymal stem cells (hBM-MSCs) and L929 fibroblasts were cultured on the discs for up to 21 days to evaluate cell viability (Live/Dead staining, LDH assay), proliferation (DNA quantification), and morphology (SEM). Immunomodulatory properties were investigated using THP-1-derived macrophages. Following differentiation into M0 macrophages, cells were cultured on the different HA/PCL formulations and macrophage polarization toward M1- and M2-like phenotypes was analyzed by RT-qPCR and flow cytometry.

Results

Differences in wettability and surface morphology were observed among the HA/PCL formulations. All compositions supported high cell viability and sustained proliferation of both hBM-MSCs and fibroblasts throughout the culture period. Preliminary immunological analyses further suggest an influence of HA content on macrophage polarization toward the pro-regenerative M2-like phenotype.

Conclusion

In vitro studies demonstrated the potential of 3D-printed HA/PCL composites for bone regeneration applications and highlighted the influence of material composition on cellular and immunological responses. Ongoing studies are evaluating their osteogenic potential of the different formulations. The immunomodulatory properties of the composites will be further validated using primary PBMC-derived macrophages. In addition, the effects of macrophage-conditioned media on hBM-MSC differentiation will be investigated to better recapitulate the crosstalk between immune and progenitor cells occurring at the implantation site during bone regeneration. The most promising formulations will subsequently be integrated into 3D gyroid scaffolds to investigate extracellular matrix deposition and early bone tissue formation.

D1 – P187

Development and characterization of fiber-reinforced hydrogel scaffolds for osteochondral repair

Niendorf C.[1], Barkow P.[1], Waletzko-Hellwig J.[2], Freiin Grote V.[2], Polley C.[2], Kissel H.[3], Boccaccini A. R.[3], Bader R.[2,4] and Seitz H.[1,4]

[1] Faculty of Mechanical Engineering and Marine Technology, Chair of microfluidics, University of Rostock, Rostock, Germany; [2]Rostock University Medical Center, University of Rostock, Rostock; [3]Institute of Biomaterials, Friedrich-Alexander-University Erlangen-Nuremberg, Erlangen; [4]Dept. Life, Light & Matter, University of Rostock, Rostock, Germany

Introduction

Cartilage and osteochondral defects remain a major clinical challenge in regenerative medicine. Despite advances in current treatments such as microfracture or matrix-assisted autologous chondrocyte implantation, the resulting repair tissue can consist of fibrocartilage rather than native hyaline cartilage. It therefore fails to meet the mechanical and tribological demands of load-bearing joints. Hydrogels represent promising candidates for cartilage repair because they provide a supportive matrix for chondrocytes and mesenchymal stem cells. However, tailoring hydrogel systems to withstand the mechanical environment of articular cartilage while maintaining cell-permissive conditions remains difficult. Here, we present an approach that integrates melt electrowritten (MEW) fiber scaffolds with hydrogels to create fiber-reinforced constructs for osteochondral tissue engineering.

Materials and Methods

In the present study, we combined an extracellular-mimicking matrix made of alginate-dialdehyde-gelatin formulations with highly oriented MEW meshes fabricated from polycaprolactone that functions as a bone phase. Two scaffold architectures with rectangular and triangular pore geometries were investigated. The hydrogels were subsequently stabilized using a dual-crosslinking strategy involving Ca^{2+} ions and microbial transglutaminase. The resulting reinforced hydrogels underwent comprehensive mechanical characterisation, including compressive testing, dynamic-mechanical analysis, and relaxation assays, and were compared with non-reinforced hydrogels.

Results

Preliminary results suggest that MEW reinforcement significantly improves the mechanical performance of the hydrogel constructs, indicating greater potential for load-bearing cartilage applications.

Conclusion

In summary, our findings highlight the capability of combining MEW-fabricated scaffolds with tailored hydrogel systems to engineer functional substitute materials for osteochondral defects.

Acknowledgements

Research funding: This study is funded by the Deutsche Forschungsgemeinschaft (DFG, German Research Foundation) – SFB 1270/3,4-299150580.

D1 – P188

Dual crosslinked Interpenetrating polymer network (IPN) of GelMA and sodium alginate for fibrocartilage tissue engineering

Sharma A.[1], Kalyanasundaram D.[1,2]
[1]Centre for Biomedical Engineering (CBME), Indian Institute of Technology (IIT), Delhi; [2]Dept. of Biomedical Engineering, All India Institute of Medical Sciences (AIIMS), New Delhi, India

Introduction

Biofabrication of fibrocartilaginous tissue has remained a pressing challenge owing to its limited regeneration capability, high stress conditions, and unique pathophysiological conditions. The limited availability of biomaterials further makes it challenging to develop tissue engineering constructs with load-bearing capability.

Aim

Development of GelMA-alginate dual crosslinked interpenetrating hydrogel networks for tissue engineering of fibrocartilage.

Materials and Methods

GelMA was synthesized by methacrylation of Gelatin (Type A, bloom strength 300G) with 1% w/v Methacrylic anhydride at 60°C in 0.25M carbonate buffer (pH 9.3). The solution was dialyzed for 72 hours before lyophilization. After FTIR and 1H-NMR confirmation, GelMA was combined with sodium alginate in DI water at various ratios and concentrations until homogeneous. For hydrogel photo-crosslinking, 0.25% w/v LAP (Lithium phenyl-2,4,6-trimethylbenzoylphosphinate), 0.1% v/v TEA (triethanolamine), and 0.05% w/v NVP (N-vinylpyrrolidone) were added as photoinitiator, co-initiator and co-monomer respectively. Dual crosslinked hydrogel was made by curing the solution with UV light at 405 nm and then with 0.2% w/v calcium chloride. Morphological and mechanical tests of the hydrogels determined the concentration and ratio required for the formation of IPN.

Results

FE-SEM images of dual crosslinked hydrogels show that only the 2:3 hydrogel with 5%w/v GelMA and 7.5%w/v sodium alginate formed a homogeneous matrix (Figure 1), suggesting an IPN. Other hydrogels showed salting out or separate upon crosslinking.




Figure 1: FE-SEM images of dual crosslinked (UV and $CaCl_2$) GelMA and Sodium Alginate bioinks at 10000x

A crucial aspect of fibrocartilage tissue engineering is preserving flexibility while ensuring the requisite strength for tissue activity. Tensile testing was conducted on the hydrogels to determine Young's modulus and the % elongation at break. The hydrogel comprising 5% w/v GelMA and 7.5% w/v sodium alginate demonstrated both higher strength and improved elongation at break (see Figure 2). This strongly suggests the formation of an interpenetrating polymer network that resists fracture due to an interlocking matrix, while enabling polymer chains to slide past one another without breakage.




Figure 2: Mechanical testing of different compositions of GelMA Alginate bio-inks at 1 mm/min strain rate. (a) Young's modulus (b) percentage elongation at break

Conclusion

The results indicate that GelMA and sodium alginate form an IPN at a ratio of 2:3, which provides it better strength and higher flexibility required for fibrocartilage tissue engineering.

D1 – P189

3D-printed multi-layer composite membrane combining placental tissue and plga-ha for bone regeneration applications

Galvez P.[1,2*], Pagin E.[1], Stachowicz M.L.[1], Torres Y.[1], Lafarge X.[3,4], Sentilhes L.[5], Catros S.[1,2], Fricain J.C.[1,2,6], L'Heureux N.[1], Fenelon M.[1,2,6]

[1]Univ. Bordeaux, INSERM, BioTis, U1026, Bordeaux; [2]CHU Bordeaux, Service de chirurgie orale, Bordeaux; Etablissement Français du Sang Nouvelle-Aquitaine, Laboratoire d'ingénierie tissulaire et cellulaire, Bordeaux; [4]Univ. Bordeaux, INSERM, U1211, « Maladies Rares: Génétique et Métabolisme », Bordeaux; [5]CHU Bordeaux, Service de gynécologie-obstétrique, Bordeaux; [6]CHU Bordeaux, Centre de compétence des maladies rares orales et dentaires, O-RARES, Pôle d'odontologie et santé buccale, Bordeaux, France

Introduction

Thanks to their unique biological properties, placental membranes (i.e. amnion and chorion) have shown promising results for various biomedical applications. However, they have some mechanical shortcomings, such as weak mechanical strength and poor space-maintaining ability. To overcome those limitations for load-bearing applications, we developed a novel composite membrane (CM) that combined the biological benefits of the amnion/chorion membrane (ACM) with the mechanical reinforcement of a synthetic poly(lactic-co-glycolic acid)-hydroxyapatite (PLGA-HA) layer through 3D printing for guided bone regeneration (GBR).

Materials and Methods

A bilayer CM was engineered by printing a porous PLGA-HA scaffold layer onto the ACM via fused deposition modeling (FDM) (Figure 1). FDM reliability was assessed through pores area reproducibility, HA spatial distribution (micro-CT), and interlayer adhesion assessment (T-peel test). Biological contents of CM were compared to ACM regarding collagen, sulfated glycosaminoglycan and growth factors. In vitro degradation was assessed over 12 weeks by measuring mass loss, pH variation, and calcium release. Furthermore, mechanical properties relevant to GBR were evidenced from suture retention, uniaxial tensile testing, and three-point bending. Finally, the biocompatibility of CM was then assessed in vivo in a rat subcutaneous model.

Results

FDM enabled reliable printing of a CM with consistent pores area, homogeneous HA distribution and interlayer adhesion, while preserving ACM biological contents. In vitro degradation of CM showed significantly lower mass loss than ACM at several time points, with substantial calcium release and pH values consistently maintained between 6.5 and 7. Furthermore, CM demonstrated significantly greater suture retention and tensile strength than ACM, along with significant improved bending properties than PLGA-HA alone. In vivo, histological analysis of explanted rat subcutaneous samples indicated a slightly inflammatory reaction.

Conclusion

Thanks to the reliability of the FDM process, a biocompatible and structurally uniform CM was developed that effectively combined the biological components of placental tissue with the physicochemical and mechanical benefits of the polymeric layer. Together with the HA enrichment displaying osteoconductive properties, these results support its promising suitability for bone regeneration applications.

Acknowledgements

This study was supported by the « Agence Nationale de la Recherche » of the French Republic (AmnioMb-3D ANR-24-CE52-4385 grant) and by the «Institut Français pour la Recherche Odontologique». Histological analysis was performed with the help of Samantha Roques Delmond. Authors also thank Laetitia Medan as manager of animal facility, and Nestor Pallares-Lupon for micro-CT acquisitions.




Figure 1. Schematic illustration of the 3D-printed multi-layer composite membrane preparation for bone regeneration.

D1 – P190

3D printed zirconia-nanoclay scaffolds for bone-tissue engineering

Memioğlu D.[1], Tufan Y.[1], Park J.H.[2,]3, Öztürk A.[1], Park J.[4], Koh Y.H.[2,3], Ercan B.[1,5],
[1]Dept. of Metallurgical and Materials Engineering, Middle East Technical University, Ankara, Turkey; [2]School of Biomedical Engineering, Korea University, Seoul, Republic of Korea; [3]Interdisciplinary Program in Precision Public Health, Korea University, Seoul, Republic of Korea; [4]Dept. of Metallurgical and Materials Engineering, ATILIM University, Ankara, Turkey; [5]BIOMATEN, METU Center of Excellence in Biomaterials and Tissue Engineering, Ankara, Turkey

Introduction

Porous ceramic scaffolds are promising candidates for bone tissue engineering. They both have good mechanical properties that mimic bone tissue and biological properties that promote cellular proliferation and bone regeneration[1,2]. Yttria-stabilized zirconia (YSZ) is one of those materials that possesses superior mechanical properties, such as good aging resistance, flexural strength, and fracture toughness, compared to many conventional ceramics[1]. Yet, its low-temperature degradation (LTD) behavior, its bioinert nature, and the effect of its pore architecture on the cellular response are still investigated.

Aim

This study aims to analyze the effect of nanoclay incorporation on pore structure, structural, mechanical, and biological properties of porous YSZ/nanoclay nanocomposite bone grafts.

Materials and Methods

This study focuses on the effects of nanoclay incorporation on the structural, mechanical, and biological performance of porous YSZ/nanoclay nanocomposite scaffolds produced by Digital Light Processing (DLP) for use as bone grafts. Nanoclay is used as a multifunctional additive to stabilize tetragonal zirconia (TZP), tailor the scaffold microstructure, pore morphology, and surface properties, and finally enhance the cell-material interactions.

Results

4% Nanoclay incorporation decreased the water contact angle to 40° from 54°. This change in contact angle increased the hydrophilicity of the nanoclay containing YSZ. The surface roughness was comparable, but the surface chemistry changed. The combination of these properties both affected the cell spreading on the surface. So, as the incorporated nanoclay amount in YSZ increased, cell spreading increased as well. Another effect of the cell behavior is observed by the MTT assay; the proliferation has considerably increased by the nanoclay incorporation. Also, cell function differentiation has been observed; the calcium mineral deposition significantly increased as the nanoclay amount increased. Another effect was the retention of the tetragonal zirconia phase of YSZ with nanoclay incorporation. 4% nanoclay incorporation has successfully minimized the monoclinic phase, stabilized TZP, limited LTD, and thus, enhanced the aging resistance of YSZ.

Conclusion

The porous YSZ/nanoclay nanocomposites produced by DLP are a promising alternative for bone graft applications. Nanoclay incorporation may overcome current limitations of other porous YSZ biomaterials by enhancing the phase stability and biological response through modification of pore architecture.

Acknowledgements

This work was supported by the Scientific and Technological Research Council of Türkiye (TÜBİTAK) under Project No: 123R056

References

[1]Huang B., Chen M., Wang J., Zhang X. Advances in Zirconia-based dental materials: Properties, classification, applications, and future prospects. *Journal of Dentistry* 2024; 147; 105111.
[2]Zhang Y, Lawn B.R. Novel zirconia materials in Dentistry. *Journal of Dental Research* 2017; 97; 140–147.

D1 – P191

Differential effects of local surface curvature on human macrophages and mesenchymal stromal cells

Mooij, I., Kemps, G., Apachitei, I., Zadpoor, A.A., Fratila-Apachitei, L.E.
Dept. of Biomechanical Engineering, Faculty of Mechanical Engineering, Delft University of Technology, Delft, The Netherlands

Introduction and Objective

Bone healing relies on a tightly coordinated osteoimmune response in which macrophages and mesenchymal stromal cells (MSCs) interact to resolve inflammation and drive tissue regeneration. Orthopedic biomaterials increasingly target this interplay through osteoimmunomodulation (OIM). How biomaterial surface curvature influences these two cell types at the single cell level is poorly understood, yet critical for designing surfaces that harness OIM. This study examines the spatiotemporal organization, migration behavior, and morphological dynamics of human THP-1 macrophages and human MSCs (hMSCs) cultured separately on concave and convex unduloid curvature fields with controlled local curvatures.

Materials and Methods

Convex and concave polystyrene (PS) unduloid substrates and flat PS controls were fabricated by micro-digital light processing, replica molding into polydimethylsiloxane, and thermal imprinting onto PS. THP-1-derived M0 and M1 macrophages and hMSCs were seeded separately on curved and flat PS. F-actin and nuclear staining at day 1 and day 3 were used to quantify morphological changes and spatial organization relative to local curvature. Migration behavior and morphological dynamics were assessed by live imaging and confocal fluorescence microscopy.

Results

hMSCs showed clear curvature-dependent responses: convex regions ($\kappa_1 > 0$, $\kappa_2 > 0$) promoted isotropic spreading and nuclear flattening, while concave ($\kappa_1 < 0$, $\kappa_2 < 0$), and saddle regions ($\kappa_1 > 0$, $\kappa_2 < 0$) induced a lift-off, paired with reduced cell area, high elongation, and curvature-dependent orientation. Live imaging revealed active curvature-sensing behavior, with hMSCs spreading across the curved landscape and repositioning according to local geometry over time. Macrophages, which are smaller than the hMSCs, showed no equivalent curvature-dependent spatial organization. Both M0 and M1 macrophages explored the surface with higher motility than hMSCs, independent of local curvature, and M1 displayed more elongated morphologies at early time points than M0. Together, these findings reveal differential curvature sensing by these cell types, with possible effects on their functions and crosstalk.

Conclusion

This study demonstrates the early responses of two key OIM cell types to local curvature. The results showed distinct cellular behavior, suggesting a potential role for local surface curvature as an osteoimmunomodulatory cue that warrants further exploration in coculture models.

Acknowledgements

The research for this paper was financially supported by the PRosPERoS-II project, funded by the Interreg VA Flanders—the Netherlands program, CCI grant no. 2021TC16RFCB041

D1 – P192

Smart biomaterial coatings with dual antimicrobial and regenerative properties

Bačáková L.[1], Sedlář A.[1], Svobodová L.[1], Rimpelová S.[2], Erzina M.[3], Lyutakov O.[3], Slepička P.[3], Siegel J.[3], Švorčík V.[3]

[1]Laboratory of Biomaterials and Tissue Engineering, Institute of Physiology of the Czech Academy of Sciences; [2]Dept. of Microbiology, University of Chemistry and Technology in Prague; [3]Dept. of Solid State Engineering, University of Chemistry and Technology in Prague, Prague, Czech Republic

Introduction

Smart biomaterial coatings with dual functionality mark a significant shift from passive implants to active healing systems. These materials are designed to address two major challenges simultaneously: preventing infection (whether external or blood-borne) and promoting tissue regeneration—specifically, cell adhesion, growth, and differentiation.

Aim

Our goal was to modify the material's surface with silver nanoparticles to make it as non-cytotoxic as possible while providing the greatest possible antibacterial effect. At the same time, we studied the adhesion, growth, and osteogenic differentiation of mesenchymal stem cells on MXene-coated surfaces, as MXenes are also known for their antibacterial properties.

Materials and Methods

In the first set of experiments, silver nanoparticles were deposited on polyether ether ketone (PEEK) or polyethylene terephthalate (PET), which are polymers commonly used in the construction of body implants, using the Laser-Induced Forward Transfer (LIFT) technique through a metallic (Al) mask. This process created hexagonal silver microdomains of various sizes (100-1000 µm in diameter) and spacing (50-250 µm). In the second set of experiments, MXenes in the form of titanium carbides ($Ti_3C_2T_x$), either unmodified or functionalized with -COOH or $-NH_2$ groups, were deposited on either polymeric or metallic substrates.

Results

On silver microdomain-patterned surfaces, human cells such as adipose-derived stem cells (ADSCs) or dermal fibroblasts initially adhered and grew in the spaces between the microdomains, eventually forming confluent layers on the material surface. In contrast, cell growth on continuous silver layers was significantly restricted or even prevented (Figure 1). At the same time, the patterned surface demonstrated an antibacterial effect against S. epidermidis and E. coli, even exceeding that of continuous silver coverage. MXene-coated surfaces supported ADSC proliferation when functionalized with -COOH groups and enhanced osteogenic differentiation when functionalized with $-NH_2$ groups, as indicated by increased collagen 1 and alkaline phosphatase expression.

Conclusion

We have developed a relatively simple and “elegant” method to reduce the cytotoxicity of silver nanoparticles while maintaining their antibacterial properties and the ability of human tissue cells to adhere and grow. Polymers modified with silver-containing microdomains can be used in dentistry, orthopedics, cardiovascular implantology, or skin grafts and wound dressings. Using MXenes, the osseointegration of bone implants can be controlled.

Acknowledgements

Supported by the Czech Health Research Council, Ministry of Health of the Czech Republic (grant No. NW26-09-00043) and the Czech Science Foundation (grant No. 26-21031S).




Figure 1. A PEEK foil patterned with microdomains containing silver nanoparticles (A), Human ADSCs on day 7 after seeding on the patterned foil (B), and on a foil with a continuous layer of silver nanoparticles (C). Cell nuclei were stained with DAPI (blue), and the actin cytoskeleton with TRITC-conjugated phalloidin.

D1 – P193
Novel sustainable composites for bone tissue engineering developed via cold sintering

Ceglarski L.S., Reilly G., Roy I., Reany I.M.,
School of Chemical, Materials, and Biological Engineering, The University of Sheffield, Sheffield, UK

Introduction
Age-related bone diseases, such as osteoporosis and degenerative disc disease, alongside the requirements for reconstruction following oncological bone resection, represent significant clinical challenges.
This research evaluates the cold sintering of Bioglass® and Bioglass®/Polymer composites as potential bone graft substitute materials. The aim is to utilise the unique low-temperature profile of cold sintering to prepare sustainable composites of Bioglass® and polymer, creating materials suitable for higher load bearing applications.

Materials and Methods
Selected microorganisms were tested using shake-flask experiments. The post-fermentation mass was analysed via gas chromatography (GC) and gas chromatography-mass spectrometry (GC-MS) for the presence of intracellular polymers. Bioactive composites were fabricated by integrating Bioglass® with polymers via a cold sintering process at ≤100°C and ≤250 MPa. Surface morphology and porosity were characterised using Scanning Electron Microscopy (SEM). The dissolution of the composites was tested in both ultra-pure water (UPW) and simulated body fluid (SBF) using Inductively Coupled Plasma Mass Spectrometry (ICP-MS) and Inductively Coupled Plasma Optical Emission Spectroscopy (ICP-OES) to assess ion release. X-ray Diffraction (XRD) was performed on samples submerged in UPW and SBF. Finally, cell study was performed in Dulbecco's Modified Eagle's Medium (DMEM) using Y021 immortalised mesenchymal stem cells (MSC) to assess cell attachment and proliferation.

Results
GC and GC-MS confirmed presence of intracellular homopolymers such as P(3HB), P(3HV), and the copolymer P(3HB-co-3HV) with varying ratio of monomers. SEM revealed that a 75:25 wt% Bioglass®:P(3HB) composition yielded best surface properties with some artefacts and pore structures present. Cell study using resazurin assay indicated initial metabolic activity for 3 days. Moreover, ion release assessed in UPW and SBF demonstrated initial burst release followed by sustained levels of ionic concentration, while XRD confirmed the formation of a hydroxyapatite surface layer.

Conclusion
In conclusion, this study demonstrates the successful fabrication of bioactive Bioglass®/polymer composites through a low-temperature cold sintering process. P(3HB) was identified as a successful polymeric phase, specifically in a Bioglass®:Polymer 75:25 wt% ratio, which yielded a scaffold with superior surface morphology and porosity that was effective for cell attachment. The confirmed formation of a hydroxyapatite surface layer after immersion in SBF highlights the potential osteoconductivity of these composites.

Acknowledgements
The authors would like to thank the EPSRC funded Centre for Doctoral Training in Advanced Biomedical Materials grant reference EP/S022201/1 for funding this work.

D1 – P194

Niobium-substituted α-tricalcium phosphate: Tuning phase stability, solubility and biological response for bone regeneration

Bünecker Cassel J., Richter R.F., Gelinsky M.
Centre for Translational Bone, Joint and Soft Tissue Research, University Hospital Carl Gustav Carus and Faculty of Medicine, Technische Universität Dresden, Dresden, Germany

Introduction

α-Tricalcium phosphate (α-TCP) is widely investigated for bone regeneration due to its biocompatibility, bioactivity and high solubility. However, its clinical application remains limited by suboptimal resorbability and lack of intrinsic antibacterial properties. Ionic substitutions have emerged as promising strategies to tailor physicochemical and biological properties of TCPs and, since they affect the material's crystallography, they can potentially increase resorbability. Although niobium (Nb) incorporation into hydroxyapatite has enhanced biocompatibility, ALP activity and antibacterial effects, it remains unexplored in α-TCP.

Aim. This study aimed to synthesize and characterize Nb-substituted α-TCP (Nb-α-TCP) and evaluate how pH-controlled Nb incorporation affects phase composition, solubility, ion release and cytocompatibility, with the goal of developing α-TCP materials with improved biological performance for bone regeneration.

Materials and Methods

α-TCP and Nb-α-TCP powders were synthesized by wet chemical precipitation under acidic (pH 0.5) and alkaline (pH 9) conditions to favour Nb incorporation into Ca^{2+} and PO_4^{3-} sites, respectively. Substitution ratios of 0, 1, 2, 3, 5 and 10 mol% Nb were investigated, and powders were calcined at 1300ºC. The materials' composition was analysed by XRD and XRF. Solubility and ion release were evaluated by incubating samples in HEPES buffer and HPLM at 37ºC for up to 28 days and quantifying Ca, P and Nb via ICP-OES. Cytocompatibility was assessed using indirect culture of L929 fibroblasts with 72 h material extracts. After 24 h incubation, cell number quantification was performed using CellTiter-Glo assay. Additional analyses of particle morphology, osteogenic activity, and antibacterial properties are ongoing.

Results

Increasing Nb substitution in acidic synthesis promoted stabilization of β-TCP phase. In contrast, alkaline synthesis increased the α-TCP fraction with higher Nb substitutions. These trends correlate with lattice parameter changes, where lattice contraction in acidic samples may stabilize β-TCP. Above 3 mol% substitution, Nb-derived secondary phases were detected, indicating reduced substitution efficiency. Nb-substituted alkaline samples exhibited higher solubility than acidic and non-substituted samples. L929 viability was maintained in all groups and increased metabolic activity was observed for samples containing 2 mol% Nb.

Conclusion

Nb incorporation into α-TCP can be modulated through synthesis pH, enabling tuning of phase composition and solubility. Alkaline synthesis favours α-TCP stabilization and enhances solubility, while acidic conditions promote β-TCP formation. 2 mol% Nb substitution maintained cytocompatibility and increased cell metabolic activity in both groups, suggesting a promising strategy for tailoring α-TCP properties for bone regeneration biomaterials.

Acknowledgements

This work was supported by the German Academic Exchange Service (DAAD).

D1 – P195

Needle-like hydroxyapatite particles as immunological modulator for enhanced osteoinduction

Piot J.[1;2], Maazouz Y.[2], Saulacic. N.[3], Gantenbein B.[4;5], Bohner M.[2]
[1]Graduate School for Cellular and Biomedical Sciences, University of Bern; [2]RMS Foundation, Bettlach; [3]Dept. of Cranio-Maxillofacial Surgery, Inselspital, University of Bern; [4] Dept. for BioMedical Research (DBMR), Faculty of Medicine, University of Bern; [5] Dept of Orthopaedic Surgery and Traumatology, Faculty of Medicine, Inselspital, University of Bern, Bern, Switzerland

Introduction

It is well established that inflammation and physiological bone healing are tightly interconnected processes.[1] The early inflammatory phase regulates angiogenesis, recruitment of progenitor cells, and subsequent tissue formation. This immune response is also crucial for successful regeneration in the case of bone graft implantation. While excessive or persistent inflammation may impair regeneration, insufficient immune reaction can also limit new bone formation.[2] These observations suggest that tuning the magnitude and duration of the early inflammatory phase could serve as a design parameter to enhance material-induced bone formation.
This project aims to study whether bone substitute materials inducing a tailored boosted transitory immune response could generate more potent bone formation. This is studied in the context of calcium phosphate (CaP)-based osteoinductive materials and using particles as immunological modulators.

Materials and Methods

Needle-like hydroxyapatite (HA) particles were synthesised via hydrothermal processes, namely α- and β-tricalcium phosphate (α-TCP, β-TCP) hydrolysis and hydrothermal homogeneous precipitation. Physicochemical characterisation was performed using scanning electron microscopy (SEM), X-ray diffraction (XRD) and inductively coupled plasma mass spectrometry (ICP-MS). Bone marrow cells were isolated from FVB/NJ mice and differentiated into primary macrophages by exposure to macrophage colony-stimulating factor (M-CSF). Macrophages were cultured in direct and indirect contact with the particles. After 6, 24, 48, 72, 96 h and 7d culture media and cells were collected. Macrophage activation was assessed by quantification of secreted cytokines and gene expression. At later stages of the project, these particles will be implanted with CaP bone grafts in vivo to study bone formation related to observed inflammatory reactions.

Results

Needle-like HA particles with mean lengths of 1-100 µm were fabricated while maintaining similar aspect ratios (20-30) and comparable Ca/P ratios (~1.55) (Fig. 1-2). It is expected that increasing particle length will lead to more pronounced inflammatory signalling. At larger particle sizes, we may observe frustrated phagocytosis. This could lead to enhanced inflammatory activation and prolonged cytokine signalling, both of which are known to influence early regenerative processes. In addition to the intensity of the response, particle length may also affect the kinetics of macrophage activation, with longer particles potentially inducing more sustained inflammatory signalling. These effects could play an important role in shaping the early immune environment that precedes tissue formation.

Conclusion

These findings may support the concept that the use of particles could be leveraged as an immunological design parameter in bone substitute materials. Such combined approach may guide the development of improved design strategies for osteoinductive biomaterials.




Figure 1: SEM micrographs of the needle-like HA particles produced for the in vitro studies.




Figure 2: Particle size distribution of the needle-like HA particles produced for the in vitro studies.

References

[1]Burgan J., Rahmati M., Lee M., Saiz A. M. Innate immune response to bone fracture healing, *Bone* 2025; 190; 117327.
[2]Zhao Z., Zhao Q., Gu B., Yin C., Shen K., Tang H., Xia H., Zhang X., Zhao Y., Yang X., Zhang Y. Minimally invasive implantation and decreased inflammation reduce osteoinduction of biomaterial. *Theranostics* 2020; 10(8); 3533-3545.

D1 – P196

Impact of ionic release from mg-doped mesoporous carriers on fibroblast behaviour in hypoxic environments

Mirt A.L.[1,2,3], Kaňková H.[4], Vasilievici G.[3], Ficai D.[2,5], Rodrian G.[6], Gölz L.[6], Stürzl M.[7], Ficai A.[2,5], Boccaccini A.R.[1]
[1]Institute of Biomaterials, Dept. of Materials Science and Engineering, University of Erlangen–Nuremberg, Erlangen, Germany; [2]National University of Science and Technology Politehnica Bucharest, Bucharest, Romania; [3]National Institute for Research & Development in Chemistry and Petrochemistry—ICECHIM Bucharest, Bucharest, Romania; [4]FunGlass - Centre for Functionaland Surface Functionalized Glass, Alexander Dubček University of Trenčín, Slovakia; [5]Academy of Romanian Scientists, 1-3 Ilfov st., Bucharest, Romania; [6]Dept. of Orthodontics and Orofacial Orthopedics, Universitätsklinikum Erlangen and Friedrich-Alexander Universität (FAU) Erlangen-Nürnberg, Erlangen, German; [7]Dept. of Surgery, Universitätsklinikum Erlangen, Erlangen, Germany

Introduction

The integration of therapeutic ions into mesoporous frameworks represents an advancement in regenerative medicine. Mesoporous silica nanoparticles (MCM-41) and mesoporous bioactive glass nanoparticles (MBGN) serve as versatile carriers for magnesium (Mg), a key regulator of cell - matrix interactions.
Nevertheless, hypoxia within injured tissue (<5% O_2) places metabolic stress on cells and alters how they interact with biomaterials [1]. Currently, the comparative performance of these two delivery systems in supporting cell survival under hypoxic stress has not been fully explored.

Aim

This study aims to compare the structural characteristics of Mg-doped MCM-41 (MCM-41-Mg) and MBGN (MBGN-Mg) and evaluate the influence of their ionic release products on the viability and morphology of Normal Human Dermal Fibroblasts (NHDF) under both normoxic and hypoxic conditions.

Materials and Methods

MCM-41 particles were obtained via a soft-templating route [2], while MBGN were synthesised through a sol-gel method [3]. Physicochemical characterization was performed using SEM, XRD and nitrogen adsorption-desorption to check the mesopore architecture and specific surface area. For biological evaluation, ionic extracts were prepared by incubating the particles in culture media for 24h and NHDF cells were exposed to these extracts and cultured under normoxia (21% O_2) and hypoxia (1% O_2). Cell viability was assessed via metabolic activity assays, while cellular architecture was visualized using fluorescence microscopy (DAPI/Phalloidin staining).

Results

SEM and XRD confirmed the formation of highly ordered, amorphous mesoporous frameworks, while nitrogen adsorption – desorption study showed high specific surface areas for all the analysed particles. In normoxic conditions, both MCM-41-Mg and MBGN-Mg extracts supported high levels of NHDF viability. Fluorescence microscopy revealed that the transition to 1% O_2 hypoxic stress induced morphological alterations, including a notable reduction in cell density and a less organized actin cytoskeleton. Despite the low oxygen level, the presence of Mg ions in the extracts, particularly within the Ca-containing MBGN group, had a protective effect, maintaining higher cell viability compared to the silica framework of MCM-41.

Conclusion

The results demonstrate that evaluating ionic release under both normoxic and hypoxic conditions is essential for predicting the regenerative potential of mesoporous platforms. While both systems are highly biocompatible under standard culture, the dynamic ionic environment created by Mg-doped MBGN is offering a higher cell viability in maintaining fibroblast functionality during hypoxic challenge. This suggests that the simultaneous release of Mg and Ca ions from the reactive glass carrier provides a better metabolic buffer for cells in compromised tissue environments.

Acknowledgements

The authors acknowledge the institutional and technical support from the Institute of Biomaterials (FAU) and the Department of Science and Engineering of Oxide Materials and Nanomaterials (UNSTB). This work was supported

financially by the Free State of Bavaria through BAYHOST program and the Romanian Ministry of Education through the National Agency for Student Loans and Scholarships.

References

[1]Xu L., Willumeit-Römer R., Luthringer-Feyerabend B. Hypoxia influences the effects of magnesium degradation products on the interactions between endothelial and mesenchymal stem cells. *Acta Biomaterialia* 2020; 101; 624–63.
[2]Petrisor G., et al. Mesoporous silica materials loaded with gallic acid with antimicrobial potential. *Nanomaterials* 2022; 12(10); 1619.
[3]Damian-Buda A.I., Nawaz Q., Unalan I., Beltrán A.M., Boccaccini A.R. Quaternary and pentanary mesoporous bioactive glass nanoparticles as novel nanocarriers for gallic acid: Characterisation, drug release and antibacterial activity. *Ceramic International* 2023; 49(18); 29923–29932.

D1 – P197

Selenium loaded mesoporous bioactive glass for bone infection treatment

Rubina A.[1,2], Harmanci S.[2,3], Boccaccini A.R.[2,3], Salma-Ancane K.[1,2]
[1]Institute of Biomaterials and Bioengineering, Riga Technical University, Riga, Latvia; [2]Baltic Biomaterials Centre of Excellence, Riga Technical University, Riga, Latvia; [3]Institute of Biomaterials, Dept. of Materials Science and Engineering, Friedrich Alexander University Erlangen-Nuremberg, Erlangen, Germany

Introduction

Bioactive glasses are silicate-based materials that bond with bone, stimulate new growth, and gradually dissolve in the body. Their ability to form a hydroxyapatite layer similar to natural bone mineral enables strong bonding and has supported their clinical use since 1985. Mesoporous bioactive glass nanoparticles (MBGNs) have a highly porous nanoscale structure that increases surface area and ion release, leading to enhanced and faster bioactivity compared to conventional bioactive glass. The performance of MBGNs can be further improved by loading them with therapeutic ions, such as selenium, which can provide antibacterial properties. Selenium loaded MBGNs (Se-MBGNs) are a promising nanofiller for biomaterials for bone infection treatment.

Aim

The aim of this study was to synthesize mesoporous bioactive glass nanoparticles (MBGNs) loaded with various amounts of selenium (Se-MBGNs), and characterise their physicochemical and biological properties.

Materials and Methods

Se-MBGNs with 1,2,5, and 10 mol% SeO were synthesized via the sol-gel method. The physicochemical properties of the Se-MBGNs were evaluated by XRD, FTIR, EDX, BET, and other methods. The antibacterial activity of the Se-MBGNs was evaluated against *E. coli* and *S. aureus* via the broth microdilution method. Cytocompatibility was assessed on MC3T3-E1 mouse preosteoblast cells.

Results

In the XRD patterns of MBGNs and Se-MBGNs (Fig. 1), formation of a crystalline phase is observed at SeO concentrations above 5 mol%, indicating limited loading capacity of selenium in MBGNs. STEM images of MBGNs and Se-MBGNs reveal highly porous spherical particles approximately 100 nm in diameter. BET specific surface analysis results demonstrate that the specific surface area of these particles decreases with increasing selenium concentrations. MBGN and Se-MBGN bioactivity assessment in simulated body fluid revealed particle crystallization into hydroxyapatite over a period of 28 days. MBGNs and Se-MBGNs also show promising antibacterial activity against Gram positive and Gram negative bacteria and cytocompatibility.

Conclusion

Selenium loaded mesoporous bioactive glass nanoparticles can be successfully synthesized via the sol-gel method with selenium oxide content up to 4 mol%, and demonstrate promising antibacterial activity and cytocompatibility.

Acknowledgements

The authors acknowledge financial support from the “Biomedical and Photonics Research Platform for the Development of Innovative Products (Project No IVPP-EM-Innovation-2024/1-0002 "Biomedical and Photonics Research Platform for Innovative Products (BioPhot))” project No. OSI_PIP_BioPhoT-2025/2-0071 “Injectable Hydrogel for Antimicrobial and Regenerative Therapy of Fracture-Related Bone Infections (BoneART)” and access to the infrastructure and expertise from Horizon 2020 project No. 857287 (BBCE – Baltic Biomaterials Centre of Excellence).




Figure 1. X-ray diffraction patterns of MBGNs and Se-MBGNs




Figure 2. Scanning transmission electron microscopy image of 1% Se-MBGNs

D1 – P198

Reindeer bone protein extract enhances bone healing properties of Beta-tricalcium phosphate granule matrix in sheep critical size bone defect model

Baixauli Marin L.[1], Vuononvirta L.[1], Viitanen M.[2], Kauppinen S.[1], Finnilä M.[1], Jalovaara P.[2]
[1]Health and Sciences Technology Research Unit, University of Oulu, Oulu, Finland; [2]Translational Medicine Research Unit, Medical Research Center Oulu, Oulu University Hospital, and University of Oulu

Introduction

Reindeers are unique animals known to fully regenerate their antlers annually, producing bone at high rates. Native reindeer bone protein extract (NBP) has demonstrated its osteoinductive potential, promoting ectopic bone formation[1] and regeneration in a critical-size rat femur defect[2]. This extract contains a combination of morphogenetic proteins (BMPs), growth factors, and other bioactive proteins, making it a strong candidate for enhancing osteoconductive ceramic matrices. Beta-tricalcium phosphate granules (β-TCP) combined with Native Bone Proteins (β-TCP-NBP) is a bone graft substitute paste formulation having osteoinductive and osteoconductive properties of the materials.

Aim

This study evaluates whether β-TCP–NBP, a bone graft paste enriched with reindeer bone proteins, can enhance bone regeneration of β-TCP in a sheep femur and tibia drilling defect model.

Materials and Methods

A sheep bone drilling defect model was employed to evaluate the efficacy of NBP. Four experimental groups were included: β-TCP-NBP (n=5), β-TCP (n=6), NBP (n=6), and empty control (n=4). Animals were treated for 8 weeks prior to sample collection. Bone regeneration in the defects was assessed in femur and tibia using micro-computed tomography with 16 µm resolution (Figure 1). Quantitative morphometric analysis was performed to evaluate bone formation and carrier material resorption. A linear mixed-effects model was used to compare bone regeneration across treatment groups and locations.

Results

Morphometric analysis revealed significantly higher bone volume fraction in the β-TCP-NBP group compared to β-TCP ($p<0.01$). β-TCP-NBP samples showed a more organized trabecular networks and higher connectivity density than both β-TCP and NBP groups. Additionally, β-TCP-NBP exhibited a faster resorption rate compared with β-TCP.

Conclusion

β-TCP-NBP enhances bone healing by increasing bone volume and improving trabecular structure compared with β-TCP or NBP alone. It speeds up old bone resorption, thus supporting its potential as a bone graft material.

Acknowledgements

This work was supported by the Jane and Aatos Erkko Foundation and the Finnish Ministry of Education and Culture's Pilot for Doctoral Programmes (Pilot project Mathematics of Sensing, Imaging and Modelling).




Figure 22. Micro-computed tomographic images of bone samples of treated bone defect from each group. Treatment paste is marked in orange (β-TCP-NBP and β-TCP), bone is marked in grey.

References

[1]Pekkarinen T., Lindholm, T. S., Hietala, O., Jalovaara, Pekka. The effect of different mineral frames on ectopic bone formation in mouse hind leg muscles induced by native reindeer bone morphogenetic protein. *Archives of Orthopaedic and Trauma Surgery 2004*; 125; 10-15
[2]Tölli, H., Kujala, S., Jämsa, T., Jalovaara, P. Reindeer bone extract can heal the critical-size rat femur defect. *International Orthopaedics* 2010; 35; 615-622.

D1 – P199

3D-printed biosilica-spongin scaffolds promote bone regeneration: An in vivo evaluation

Sousa K.S.J.[1], Cruz M.A.[2], de Souza A.[1], Bonifácio M.[1], Souza-Silva L.C.[1], Prado J.P.S.[1], Assaf A.S.A.[1], Soares-Silva B.[1], de Souza D.V.[1], Martignago C.C.S.[1], Parisi J.R.[2], Assis L.[1], Assis M.[1], Granito R.N.[1], Renno A.C.M.[1]
[1]Dept. of Biosciences, Federal University of São Paulo; [2]Dept. of Physiotherapy, Metropolitan University of Santos, Santos, Brazil

Introduction

Osteoporosis is a progressive systemic skeletal disease characterized by reduced bone mass and microarchitectural deterioration, leading to increased fracture risk and impaired bone healing. Under osteoporotic conditions, the compromised regenerative capacity of bone tissue often limits the success of conventional grafting strategies, highlighting the need for biomimetic materials capable of enhancing bone repair. Marine-derived biomaterials such as biosilica (BS) and spongin (SPG) have attracted increasing interest due to their osteogenic potential, biocompatibility, and structural similarity to components of the native bone extracellular matrix. When combined into composite scaffolds, these materials may better mimic the organic-inorganic architecture of bone and support tissue regeneration. In addition, 3D printing enables the fabrication of scaffolds with controlled porous architectures that favor cell infiltration and bone ingrowth.

Aim

This study evaluated the in vivo performance of 3D-printed BS and BS-SPG scaffolds in osteoporotic bone defects.

Materials and Methods

Biosilica (BS) and spongin (SPG) were extracted from marine sponges collected on the northern coast of São Paulo, Brazil, following previously established protocols. The biomaterials were incorporated into alginate-based inks to fabricate 3D-printed scaffolds using an extrusion bioprinting system. Two scaffold compositions were produced: BS and BS-SPG composites. Physicochemical characterization was performed using Fourier transform infrared spectroscopy (FTIR) and scanning electron microscopy (SEM), and printing performance was evaluated through shape fidelity and reproducibility analyses. For the in vivo study, osteoporosis was induced in female Wistar rats by bilateral ovariectomy. After nine weeks, critical-sized (8 mm) calvarial defects were created and randomly treated with BS scaffolds, BS-SPG scaffolds or left untreated (control). Animals were euthanized at 15 and 30 days post-surgery. Bone regeneration was evaluated by histological and histomorphometric analyses, including bone volume fraction and osteoblast-related parameters. In addition, immunohistochemical staining for RUNX-2, osteoprotegerin (OPG), and RANKL was performed to assess osteogenic activity and bone remodeling.

Results

Physicochemical characterization confirmed the preservation of BS and SPG structures after printing. BS–SPG scaffolds showed improved shape fidelity and printing reproducibility compared with BS scaffolds. Histology revealed progressive bone formation in all groups, with more extensive and mature bone in scaffold-treated defects, particularly in the BS–SPG group at 30 days. Histomorphometry showed significantly higher bone volume fraction in BS and BS–SPG groups at 30 days. Immunohistochemistry indicated enhanced early osteogenic activity in the BS–SPG group, with increased RUNX-2 expression at 15 days and balanced OPG and RANKL expression over time.

Conclusion

Overall, the BS–SPG scaffold enhanced osteogenic response and bone regeneration in osteoporotic defects, supporting its potential as a biomimetic strategy for bone repair under compromised healing conditions.

Acknowledgements

This work was supported by “Fundação de Amparo à Pesquisa do Estado de São Paulo - FAPESP” through the grants n° #2023/08525-7, #2024/19218-0, #2026/00695-9, #2024/19218-0, #2024/06598-0, #2022/13515-8, #2021/13056-0, #2019/10228-5, and #2021/11845-8. The authors also acknowledge “Coordenação de Aperfeiçoamento de Pessoal de Nível Superior – CAPES” and “Conselho Nacional de Desenvolvimento Científico e Tecnológico – CNPq” for financial support.

D1 – P200




Figure 1 – SEM micrographs of ion-doped CaP coatings deposited on ACC (Sr, Zn, Mn and Cu systems) showing dopant-dependent morphologies. Scale bars: 10 µm.

D1 – P201

Bioinspired polydopamine functionalization of PLLA and PLGA scaffolds: Dual strategies for improved surface hydrophilicity

Krokos A., Gazińska M.A.
Dept. of Polymer Engineering and Technology, Wrocław University of Science and Technology, Wrocław, Poland

Introduction

Polydopamine (PDA) is a bioinspired surface modification agent that readily deposits on a wide range of materials via oxidative self-polymerization of dopamine. Due to the presence of catechol groups, PDA coatings exhibit high hydrophilicity, which plays a key role in protein adsorption and subsequent cell adhesion. Biodegradable polymers such as poly(L-lactide) (PLLA) and poly(lactide-co-glycolide) (PLGA), commonly used in bone tissue engineering, are inherently hydrophobic, which limits their biological performance. Therefore, effective strategies to improve their surface wettability are required. In this study, two modification approaches were investigated: (i) incorporation of PDA-modified hydroxyapatite (HAP) as a filler in PLLA and PLGA porous matrices, and (ii) post-fabrication coating of porous PLLA/PLGA-HAP composites with a PDA layer.

Aim

The aim of this study was to design porous PLLA- and PLGA-based composites to maximize hydrophilicity via polydopamine functionalization, thereby enhancing their suitability for tissue-specific cell adhesion.

Materials and Methods

Hydroxyapatite particles were modified with PDA via *in situ* polymerization of dopamine (2 mg/mL) in Tris buffer. Porous PLLA and PLGA composites containing either unmodified HAP or PDA-modified HAP were fabricated using the thermally induced phase separation method. Porous scaffolds PLLA/PLGA-HAP were coated with PDA by immersion in alkaline dopamine solutions (2, 6, and 10 mg/mL) under continuous shaking (300 rpm). All materials were characterized by water contact angle measurements, scanning electron microscopy (SEM), and thermal analysis.

Results

PDA modification resulted in improved surface hydrophilicity, particularly for scaffolds coated with PDA over the entire surface. Unmodified PLLA and PLGA foams exhibited hydrophobic behavior (~120°), whereas PDA-functionalized samples showed markedly enhanced wettability (~35°). Thermal analysis demonstrated that PDA-modified HAP particles act as multifunctional fillers within polymer matrices, exhibiting nucleating and plasticizing effects. Similar behavior were observed for composites coated with PDA. These findings confirm improved physicochemical properties of the developed materials and highlight their potential for biomedical applications.

Conclusion

Polydopamine functionalization is an effective and simple strategy to enhance the hydrophilicity of porous PLLA- and PLGA-based biomaterials. Both approaches—PDA-modified fillers and surface coating—significantly improve wettability and may promote cell adhesion and tissue integration. The high hydrophilicity of PDA coatings arises from the presence of catechol and amine functional groups, which enable hydrogen bonding and increase surface energy. These features make the developed materials promising candidates for applications in bone tissue engineering.

Acknowledgements

This research was supported by the statutory research framework of Wrocław University of Science and Technology.

References

[1]Maiti B., Van der Eycken E., Coppola G. Catechol modification as a platform for functional coatings. *Biomaterial Science* 2026; 14; 81-99.
[2]Orlacchio R., Zuppolini S., Cruz-Maya I., Pragliola S., Borriello A., Guarino V., Fittipaldi R., Lettieri M., Venditto V. Polydopamine-Coated Poly-Lactic Acid Aerogels as Scaffolds for Tissue Engineering Applications. *Molecules* 2022; 27(7); 2137.

D1 – P202

Dual-crosslinked injectable hydrogel reinforced with phyto-loaded mesoporous hydroxyapatite for minimally invasive bone defect repair

Sreena R.[1,2], Dr. Joseph Nathanael A.[1]
[1]Centre for Biomaterials, Cellular and Molecular Theranostics, Vellore Institute of Technology; [2]School of Biosciences and Technology, Vellore Institute of Technology, Vellore, India

Introduction

Repair of bone defects are explored using injectable biomaterials since they can be used in a minimally invasive way. They have the ability to conform to irregular defect sites and can aid in localized drug delivery. Conventionally fabricated injectable hydrogels suffer from poor mechanical properties and result in quick dissolution under physiological conditions. Traditional bone cements are made of polymers such as PMMA that has no bioactivity. Hydrogel systems duly crosslinked combining thermo and chemical strategies offer a promising strategy that can aid in improving the stability of the structure and also injectability. Incorporation of bioactive ceramics such as mesoporous hydroxyapatite aids in enhancing the osteogenic potential of the hydrogel bone cement. Further, functionalization with traditional phyto-therapeutics to impart anti-microbial properties. Therefore, integrating phyto-therapeutic loaded mesoporous hydroxyapatite within a dual-crosslinked injectable hydrogel matrix may enable the formation of a multifunctional bone cement that can be used for bone repair.

Aim

The aim was to develop and evaluate an injectable dual-crosslinked hydrogel cement incorporating phyto-loaded mesoporous hydroxyapatite for enhanced bone regeneration and antimicrobial functionality.

Materials and Methods

The injectable hydrogel bone cement was formulated using a thermo responsive polymer, Pluronic F 127 and poly (ethylene glycol) diacrylate (PEGDA) as a photo-crosslinkable network former and lithium phenyl-2,4,6-trimethylbenzoylphosphinate (LAP) was used as the photo-initiator. Phyto-loaded mesoporous hydroxyapatite particles were fabricated using a microwave assisted technique and was incorporated within the hydrogel matrix to provide bioactivity and anti microbial properties. The formulation will be maintained at low temperature to and subsequently gelled at physiological temperature followed by UV-induced crosslinking to obtain stable hydrogel constructs. The physicochemical properties of the hydrogel cement were evaluated through injectability testing, gelation behavior, and stability in phosphate buffered saline (PBS). The constructs were assessed for various physiochemical, mechanical and biological properties.

Results




Figure 1 shows the inversion gel test of injectable hydrogel cement comprising PEGDA, PF127, mesoporous hydroxyapatite (mHA) or phyto-therapeutic loaded mesoporous hydroxyapatite (P-mHA)




Figure 2 shows the cured injectable gel disks (left: mesoporous hydroxyapatite; right: phyto incorporated mesoporous hydroxyapatite) stable after 24 hours after immersion in phosphate buffer saline

Conclusion

This study deals with developing an injectable dual-crosslinked hydrogel cement reinforced with phyto-loaded mesoporous hydroxyapatite. The combination of thermal and photo-crosslinking enables injectability and structural stability, while the incorporation of bioactive phyto loaded mesoporous hydroxyapatite offers potential for osteogenic and antimicrobial activity. The developed system shows promise as a minimally invasive platform for bone repair.

Acknowledgements

I would like to thank Centre for Biomaterials, Cellular and Molecular Theranostics and School of Biosciences and Technology, VIT, Vellore. I would like to thank UGC-Savitribai Jyotirao Phule Fellowship for Single Girl Child (202223UGCES-SJSGC-14584). The authors are grateful to Department of Biotechnology –Ramalingaswami Re-entry Fellowship (BT/HRD/35/02/2006) for the funding.

References

[1]McAvoy K., Jones, D., Thakur R.R.S. Synthesis and Characterisation of Photo-crosslinked poly (ethylene glycol) diacrylate Implants for Sustained Ocular Drug Delivery: McAvoy, Jones and Thakur. *Pharmaceutical research* 2018; *35*(2); 36.

[2]Kheradmandfard M., Sadeghian A., Kouhi, M., Sajadi-Javan Z.S., Varshosaz J., Savabi O., Kim D. E. High drug loading mesoporous hydroxyapatite nanoparticles for periodontal bone regeneration: A facile microwave-assisted synthesis approach. *Surfaces and Interfaces* 2025; 68; 106626.

D1 – P203

3D-printed polycaprolactone-bioactive glass composite scaffolds for bone tissue engineering: The effect of filler content on different surface modifications

Kim M.[1,2,3], Nawaz Q.[2], Hartmann B.[1,3,4,5], Cheers G.M.[1], Niesner I.C.C.[1], Clausen-Schaumann H.[3,4,5], Boccaccini A.R.[2], Holzapfel B.M.[1], and Mayer-Wagner S.[1]

[1]Dept. of Orthopaedics and Trauma Surgery, Musculoskeletal University Center Munich (MUM), Ludwig Maximilian University (LMU) of Munich University Hospital, Munich; [2]Institute of Biomaterials, Dept. of Materials Science and Engineering, University of Erlangen-Nuremberg, Erlangen; [3]Center for Applied Tissue Engineering and Regenerative Medicine (CANTER), Munich University of Applied Sciences, Munich; [4]Center for NanoSciences (CeNS), LMU Munich, Munich; [5]Dept. of Applied Sciences and Mechatronics, Munich University of Applied Sciences, 80335, Munich, Germany.

Introduction

Composite materials and biofunctional coatings are both of substantial importance for designing and engineering an effective bone scaffold. Although a collective and comprehensive investigation into the synergistic effects of composite materials and coatings is necessary, such practices are rarely undertaken and are combined only at a later stage. In this study, we extruded polycaprolactone (PCL)-45S5 bioactive glass® (BG) composite filaments with different filler contents of 1, 2, and 5 wt%. The composite filaments were three-dimensional (3D)-printed into PCL-BG composite scaffolds. The PCL-BG composite filaments and 3D-printed PCL-BG scaffolds were analysed and compared with the industrial-grade PCL filaments and the 3D-printed PCL scaffolds. Following the composite material development and processing, the PCL and PCL-BG composite scaffolds were modified on their surfaces using three different methods—subtractive chemical etching, conventional biomimetic calcium phosphate (CaP) coating, and bioinspired polydopamine (PDA) modification—with a special interest in PDA-modified PCL-BG composite scaffolds. A comprehensive analysis package was performed on 16 scaffold groups to understand the effect of filler content on different surface modifications and their properties.

Materials and Methods

First, the PCL pellet-BG particle mixtures were extruded into composite filaments with a target diameter of 1.75 mm. The morphology, BG distribution within the matrix, and tensile performance were assessed, and the extruded PCL-BG composite filaments were compared to an industrial-grade PCL filament. The PCL-BG composite filaments were then 3D-printed and compared with the PCL scaffolds in terms of microstructure and morphology. Three different surface modifications—subtractive chemical etching, conventional biomimetic CaP coating, and bioinspired PDA modification—were performed. The modified PCL and PCL-BG composite scaffolds were comprehensively compared with the non-modified PCL and PCL-BG composite scaffolds for their microstructure, morphology, topography, mechanical performance, and scaffold-cell interactions, including cell adhesion, cytotoxicity/viability, and proliferation. A schematic illustration of the study package is shown in Figure 1, and the abbreviations of the scaffold groups and summaries of each surface modification process are shown in Table 1.

Results




Figure 1. Schematic illustration of the methods of the study package (not to scale).

Table 1. Abbreviation of the scaffold groups and the summary of each surface modification process.

Surface Modification	Abbreviations	Scaffold Composition	Surface Modification
No Modification	**PCL**	PCL	No surface modification applied
	PCL-1BG	PCL-1 wt% 45S5 BG	
	PCL-2BG	PCL-2 wt% 45S5 BG	
	PCL-5BG	PCL-5 wt% 45S5 BG	
Subtractive Chemical Etching	**etched@PCL**	PCL	5 M NaOH, 37 °C & 24 h
	etched@PCL-1BG	PCL-1 wt% 45S5 BG	
	etched@PCL-2BG	PCL-2 wt% 45S5 BG	
	etched@PCL-5BG	PCL-5 wt% 45S5 BG	
Conventional Biomimetic CaP-coating	**CaP@PCL**	PCL	Pre-processing: 5 M NaOH, 37 °C & 24 h CaP-coating: SBF 10X, 37 °C & 1 h Post-processing: 0.5 M NaOH, 37 °C & 30 min
	CaP@PCL-1BG	PCL-1 wt% 45S5 BG	
	CaP@PCL-2BG	PCL-2 wt% 45S5 BG	
	CaP@PCL-5BG	PCL-5 wt% 45S5 BG	
Bioinspired PDA-modification	**PDA@PCL**	PCL	2 mg dopamine chloride/mL Trizma® base solution (pH 8.5-8.6), 37 °C & 24 h
	PDA@PCL-1BG	PCL-1 wt% 45S5 BG	
	PDA@PCL-2BG	PCL-2 wt% 45S5 BG	
	PDA@PCL-5BG	PCL-5 wt% 45S5 BG	

The extruded PCL-BG composite filaments showed filament quality and tensile performance comparable to that of the industrial-grade PCL filament. The PCL-BG composite filaments were 3D-printable using the same processing parameters as for the PCL filaments, without requiring a complicated process optimisation. The 3D-printed PCL and PCL-BG constructs and scaffolds did not show a clinically effective difference in the printed microstructure, as assessed by 3D-rendered micro-computed tomography (microCT) scans of the 3D-printed constructs and the strut thickness of the 3D-printed scaffolds.

There were visible effects for all three surface modifications—subtractive surface etching, conventional biomimetic CaP coating, and bioinspired PDA modification—with increasing filler content from 1 wt% to 5 wt% based on digital light microscopy (DLM) and scanning electron microscopy (SEM). The different coating deposition behaviour was especially apparent for CaP coating based on Alizarin Red S (ARS) staining. The optical density (OD) of PDA coating media showed a decrement with increasing filler content, which was the opposite to the increasing coating yield of PDA visible from the color indication, suggesting that the higher polymerization of PDA does not necessarily lead to higher yield of PDA deposition of the substrate. The higher PDA deposition is likely correlated with increased hydrophilicity, leading to a greater tendency for PDA grafting on the surface of the 3D-printed PCL-BG composite scaffolds.

Topography was strongly affected by the surface modification, with the highest measured roughness for the etched PCL and PCL-BG scaffolds, and a certain decrease in surface roughness with increasing filler content. The non-modified PCL and PCL-BG scaffolds showed a similar surface roughness without any statistical difference, as well as the PDA-modified PCL and PCL-BG scaffolds. However, the surface roughness of the PDA-modified PCL and PCL-BG scaffolds showed a certain increase in surface roughness with increasing filler content, again confirming the higher yield of PDA deposition compared to that of the PCL and PCL-BG composite scaffolds with a lower filler content.

Mechanical performance was one of the most interesting results of this research, showing an increase in brittleness for the PCL-5BG scaffolds, which was apparent only after surface modification. This indicates that, with an increase in filler content, the effect of surface modification may be more substantial. The etched PCL and PCL-BG composite scaffolds showed a ductile behaviour comparable to the non-modified PCL and PCL-BG composite scaffolds, and the CaP-coated PCL and PCL-BG composite scaffolds were also relatively more ductile, except for the CaP@PCL-5BG scaffold, which expressed a rather brittle behaviour. PDA-modified PCL and PCL-BG composite scaffolds also hinted at a comparably ductile behaviour than non-modified PCL and PCL-BG composite scaffolds, but not as much as the etched and CaP-coated PCL and PCL-BG composite scaffolds. Interestingly, the PDA@PCL-5BG scaffold showed a rather brittle behaviour even when compared to the non-modified PCL-5BG scaffold. The compressive modulus of the PCL-5BG scaffolds decreased compared to the PCL, PCL-1BG, and PCL-2BG scaffolds, but was again improved after surface modification, indicating a trade-off between the two mechanical properties: strength and toughness. The etched PCL and PCL-BG scaffolds showed a similar compressive modulus, and CaP-coated scaffolds indicated an improvement of compressive modulus with an increased filler content, especially for the CaP@PCL-5BG scaffolds. The PDA-modified PCL and PCL-BG scaffolds showed similar compressive moduli without a clear trend. SEM micrographs of the cracks initiated near the node (intersection of the fused struts) allowed a hint at the ductility of the PCL and PCL-BG scaffolds, where all three surface modifications introduced a more ductile behaviour based on the observation on the cracks. Also, the non-modified and PDA-modified PCL-2BG scaffolds displayed superior crack resistance compared to other scaffold groups.

Cell adhesion was observed using SEM, with a clear trend of improved adhesion and attachment with an increase in filler content from 1 wt% to 5 wt%. Interestingly, the etched PCL and PCL-BG scaffolds showed the lowest cell attachment among all study groups, indicating the need to optimise hydrophilicity. And while non-modified PCL and PCL-BG scaffolds showed increased cell adhesion by 7d, etched PCL and PCL-BG scaffolds clearly showed insufficient cell adhesion even at 7d. The PDA-modified PCL and PCL-BG scaffolds showed superior cell adhesion and attachment overall, and this was already evident at 2d. The CaP-coated PCL and PCL-BG scaffolds also showed excellent cell adhesion by 7d.

From the cell cytotoxicity/viability study, the non-modified PCL and PCL-BG composite scaffolds were not statistically distinct from each other. The etched PCL and PCL-BG composite scaffolds were similar or lower in terms of cell viability to non-modified PCL and PCL-BG scaffolds, which was predictable from cell adhesion. The scaffold groups did not show statistically significant differences in cell viability at 2d. At 7d, it was evident that CaP-coating and PDA-modification are not only non-cytotoxic but also support cell viability. The PDA-modified PCL and PCL-BG scaffolds showed the highest cell viability. However, there was a significant decrease in cell viability for the PDA@PCL-5BG scaffolds, indicating that the effective known parameter for PDA modification might require adjustment and fine-tuning for composites with a high filler content.

From the immunofluorescence (IF) live/dead staining of the non-modified PCL and PCL-BG composite scaffolds, it was evident that the non-modified PCL scaffold showed the least cell adhesion, with cells clustered on top of the strut rather than spreading around it, as observed in cell adhesion from the SEM micrographs. And while the PCL-5BG scaffold appeared to have the most populated living cells between the non-modified PCL and PCL-BG composite scaffolds, there were comparably more dead cells, indicating that the live-stained cell population might not be adhered onto the strut, but sitting on top of the scaffold as a large cell cluster, which may not survive and support the osteogenic performance of the scaffold in practice. Overall, the non-modified PCL-1BG and PCL-2BG scaffolds showed the most favourable live/dead staining. From the IF calcein, DAPI, and phalloidin staining of the non-modified PCL and PCL-BG composite scaffolds, there was a certain improvement of proliferation with increased filler content. From IF micrographs of the etched PCL and PCL-BG composite scaffolds, the etched@PCL-2BG scaffold was evidently more proliferative than other scaffold groups, for both cell spread and cytoskeleton development, even at 14d. However, the intensity of live-staining decreased at 28d for all the etched PCL and PCL-BG composite scaffolds, indicating that surface etching may be insufficient for cell proliferation, even for PCL-BG composite scaffolds. The CaP-coated PCL and PCL-BG composite scaffolds also showed the most proliferative behaviour for the CaP@PCL-2BG scaffold, where the CaP@PCL-5BG scaffold was comparable to the CaP@PCL-2BG scaffold at 14d. However, by 28d, the CaP@PCL-1BG and CaP@PCL-2BG scaffolds were shown to be comparable as a platform for cell proliferation. A similar trend was observed for the PDA-modified scaffolds, with the PDA@PCL-2BG scaffold showing better cell proliferation at both time points, 14d and 28d. The PDA@PCL-5BG scaffold clearly indicated insufficient osteogenic performance compared to the PDA@PCL-1BG and PDA@PCL-2BG scaffolds.

Conclusion

The findings show that the surface-modified substrates generally follow the properties of the non-modified substrate, as hypothesised, and a clear trend toward an optimal BG filler content of 2 wt% was observed. However, the selection of the surface modification strongly governed the osteogenic behaviour of the scaffolds. In addition, there were details on mechanical performance and osteogenic properties for different surface modifications and different filler content composites, which will be worth investigating for designing and engineering patient-specific bone scaffolds.

Acknowledgements

The authors would like to acknowledge Munich Medical Devices GmbH (Munich, Germany; formerly Kumovis GmbH–a 3D Systems Company) for technical support for the 3D printer EXD 220 MED (3D Systems, USA). The authors also acknowledge Yasemine Annamaria Geider, M.Sc. (CANTER, Munich University of Applied Sciences, Munich, Germany) for technical support for the microtester.

Fundings

This research project was supported by Bayersiches Verbundforschungsprogramm (BayVFP) (Funding Indicator: LSB-2203-0004 and LSB-2203-0005) of Bayern Innovativ (Nuremberg, Germany).

D1 – P204

Nanocomposite injectable hydrogels as support systems for mandibular fracture healing

Giuliano F., Galvano S., Barrino F., Muscolino E., Dispenza C.
Dept. of Engineering, University of Palermo, Palermo, Italy

Introduction

Non-critical mandibular fractures require mechanical stabilization and a regenerative microenvironment to support bone healing. Current treatment strategies may involve rigid fixation systems[1], which, although effective, are invasive and associated with complications. Injectable hydrogels represent a minimally invasive alternative[2]; however, their application in oral environments is often limited by insufficient structural stability under physiological conditions and variable pH.

Materials and Methods

Nanocomposite hydrogels based on k-carrageenan (kC) and guar gum (GG), reinforced with fluorapatite nanoparticles (FA NPs), were developed as injectable systems. FA NPs were synthesized via a sol–gel approach and incorporated at different loadings (0.5 % and 1.0 % w/w) into the polymer matrix. Hydrogel formulations were prepared with fixed GG content (2% w/w) and varying kC concentrations (1 and 2% w/w),and subjected to characterization with rheological, morphological, and swelling analyses. The stability of the systems was evaluated under physiologically relevant conditions, including different pH levels and simulated biological fluids, to reproduce the oral microenvironment.

Results

The hydrogels exhibited shear-thinning behaviour and solid-like viscoelastic properties, with G′ > G″ maintained across the 0.1–10 Hz frequency range at 37 °C, confirming stable gel-like networks under physiologically relevant dynamic conditions. The incorporation of FA NPs shifted the sol–gel transition to higher temperatures, indicating nanoparticle-assisted network formation. Swelling studies revealed progressive structural weakening in aqueous conditions, highlighting a critical limitation for in vivo applications. The introduction of ionic interactions improved hydrogel integrity, reducing swelling-induced disruption and enhancing macroscopic stability. Data collecting suggest that environmental factors, such as ionic strength and pH, play a key role in modulating network stability.

Conclusion

The developed kC/GG–FA nanocomposite hydrogels highlight the role of polymer ratio and nanoparticle loading as key parameters governing network organization and mechanical behaviour, enabling compositional tunability toward injectable systems for oral bone repair. The oral microenvironment, particularly ionic strength and pH, emerges as a central design variable that must be addressed to ensure in vivo performance. These findings provide a basis for the development of clinically relevant injectable hydrogels for oral bone repair.

References

[1]Dewey M.J., Harley B.A.C. Biomaterial design strategies to address obstacles in craniomaxillofacial bone repair. *RSC Adv*. 2021; 11, 29; 17809-17827.
[2]Piantanida E., Alonci G., Bertucci A., De Cola L. Design of Nanocomposite Injectable Hydrogels for Minimally Invasive Surgery. ACS Acc. Chem. Res 2019; 52, 8; 2101-2112.

D1 – P205

Effect of formulation parameters in mechanical properties of coordination hydrogel

Kaneko K., Zhong L., van Herck S., van Rijt S.H.
Dept. of Instructive Biomaterials Engineering, MERLN Institute for Technology Inspired Regenerative Medicine, Maastricht University, Maastricht, The Netherlands

Introduction

Dynamic synthetic hydrogels are promising biomaterials because their reversible networks allow adaptation to external stimuli and mechanical stress. This dynamic behavior enables properties such as self-healing and stress relaxation. However, achieving hydrogels that combine high stiffness with dynamic adaptability remains a major challenge. Metal-coordinated hydrogels offer a potential solution by forming robust yet reversible networks through metal–ligand interactions. The coordination bonds are significantly stronger than the intermolecular interactions typically used to crosslink dynamic hydrogels, thereby contributing to higher stiffness. At the same time, the dynamic and reversible nature of these coordination bonds allows network rearrangement under stress, which can improve the toughness of the material. However, key knowledge gaps remain in understanding how metal–ligand bond dynamics govern bulk mechanical properties and how to predict trade-offs between stiffness, toughness, and responsiveness. **Aim.** This project aims to investigate how key formulation parameters, including the combination of metals ions and ligands, the coutneranion of the metal salts, and other compositional variables, influence the resulting mechanical properties of coordination hydrogel.

Materials and Methods

Polyethylene glycol (PEG) was activated by an NHS- esterification, followed by functionalization with terpyridine (TPY) as a ligand to synthesize polymer backbone (PEG-TPY). Different transition metal (II) ions were investigated, with different ratio of metal ions to ligands. Effect of counteranion was also investigated using different Cobalt (II) salts. Rheometric characterization of hydrogels was performed as time sweep, frequency sweep, stress relaxation, and amplitude sweep.

Results

Gel-like materials were formed upon addition of metal chloride solution to the PEG-TPY solutions. Rheological characterization revealed that different metal ions – TPY coordination results in variety range of stiffness and toughness of the hydrogels, reflecting variations in metal–ligand coordination strength and dynamics.

Conclusion

The first libraries of rheological properties of PEG-TPY were investigated with different metal ions. Such knowledge is important for understanding how coordination chemistry controls macroscopic material properties and will guide the design of tunable supramolecular hydrogels. Future studies will investigate the influence of cobalt salt counteranions on hydrogel behavior.

Acknowledgements

This research was supported by European Research Council (ERC) ERC-CoG (Nano4Bone; van Rijt).

D1 – P206
Computational–experimental symbiosis to design functional supramolecular peptide assemblies

Sasselli I. R.
Materials Physics Center (CFM), CSIC–UPV/EHU, Donostia-San Sebastián, Spain

Introduction
The functional versatility of peptides, together with their inherent capacity to spontaneously organize into ordered structures through self-assembly with minimal external control, has fueled increasing interest in their use as supramolecular materials for nanotechnology and biomedicine. As in the natural systems that inspire them, peptide sequences encode structural information that ultimately determines function. However, in contrast to proteins, the sequence–structure–function relationships governing supramolecular peptide assemblies (SPAs) remain insufficiently understood, posing a major challenge for rational materials design.

Aim
We aim to address this limitation by combining computational modeling with experimental characterization, enabling molecular-level insight into supramolecular organization that cannot be obtained using either approach in isolation. By extending this strategy, we seek to move beyond existing functionalities and advance peptide-based materials toward realistic, multifunctional platforms for tissue regeneration therapies.

Materials and Methods
In our group, we develop computational and experimental methodologies in parallel, allowing us to systematically benchmark and refine simulation tools for their application to complex supramolecular systems. This integrated framework supports the rational design of SPAs and peptide–protein co-assemblies with controlled architectures and emergent functional properties.

Results
This combined computational–experimental strategy has led to substantial advances in SPA development, including a clearer understanding of co-assembly effects, the generation of new architectures, and the identification of structural features that regulate bioactivity. We demonstrated how clustering behavior depends on peptide sequence and co-assembly composition, and how this interplay is further modulated by concentration, as well as how internal molecular motion within assemblies promotes regenerative outcomes in spinal cord injury models. More recently, we have applied this framework to design peptide–protein co-assemblies with controlled dimensionality and emergent conductive properties, and to show that electrostatic patterning, including negative charge, can modulate neural cell responses.




Figure 23. Self-assembly of Short Peptides into a short peptide assembly (SPA) and further into a fiber Network, giving rise to a material suitable for applications such as Artificial Extracellular Matrix.

Conclusion
These results highlight the power of a combined computational–experimental approach to both elucidate SPA organization and guide the rational design of new supramolecular architectures. Using this framework, we achieved controlled-dimensionality peptide–protein co-assemblies and demonstrated how electrostatic patterning, including negative charge, directly modulates neural cell responses. Overall, this symbiotic strategy enables the deliberate programming of peptide structure and bioactivity toward multifunctional platforms for tissue regeneration.

Acknowledgements
This work was supported by Spanish Research Agency (AEI) under grants: RYC2021-033294-I and PID2022-136392NA-I00.

D1 – P207

Genotoxicity and cytotoxicity evaluation of marine sponge-derived biosilica and spongin scaffolds for bone tissue engineering

Avanzi I.R.[1], Cruz M.A.[2], Sousa K.S.J.[1], de Souza A.[1], Nina-Nina D.[1], Mesquita-Ferrari R.A.[3], Assis M.[1], Granito R.N.[1], Renno A.C.M.[1]
[1]Dept. of Biosciences, Federal University of São Paulo, Santos; [2]Dept. of Physiotherapy, Metropolitan University of Santos, Santos, Brazil, [3]Dept. of Physiotherapy

Introduction

Bone fractures represent an important public health concern, with their incidence increasing worldwide in recent years. The treatment of non-consolidated fractures frequently involves surgical fixation using metallic devices, often combined with biomaterials that support bone regeneration. Among the emerging alternatives, biosilica (BS) and marine spongin (SPG), obtained from the skeletons of marine sponges, have attracted attention as natural biomaterials. Their distinctive structural organization and physicochemical properties suggest that they may serve as suitable scaffolds for bone tissue regeneration. In this context, the present study investigates whether scaffolds composed of BS and BS/SPG can enhance the biological performance of materials intended for bone repair.

Aim

Scaffolds. This study aimed to evaluate and compare the physicochemical and morphological characteristics, cytotoxicity, genotoxicity, and biomineralization potential of BS and BS/SPG scaffolds.

Materials and Methods

Scaffolds based on biosilica (BS) and biosilica combined with spongin (BS/SPG) were characterized by scanning electron microscopy (SEM) and Fourier-transform infrared spectroscopy (FTIR) to assess their morphology and chemical structure. The biological effects of these materials were investigated using in vitro assays with L929, MC3T3-E1, and CHOK-1 cell lines. Cell viability was determined by the MTT assay after exposure to scaffold extracts for 1 and 3 days. Possible genotoxic effects were evaluated using comet and micronucleus assays. In addition, the capacity of the scaffolds to promote biomineralization was assessed through alizarin red staining.

Results

Morphological analysis revealed a needle-like structure for biosilica, while the presence of spongin was associated with fibrillar structures and granules. Cytotoxicity assays indicated approximately 70% cell viability for both L929 and MC3T3-E1 cells after 1 and 3 days of exposure to BS and BS/SPG extracts. Genotoxicity analyses showed no evidence of DNA damage in MC3T3-E1 and CHOK-1 cells after 24 hours of exposure at all tested concentrations. Regarding biomineralization, BS scaffolds exhibited strong alizarin red staining after 7 days, whereas BS/SPG scaffolds showed weaker staining after 14 days.

Conclusion

Overall, the results indicate that both BS and BS/SPG scaffolds are biocompatible in vitro, do not induce detectable genotoxic effects, and present the ability to support biomineralization. These findings suggest that marine sponge–derived biosilica and spongin may represent promising natural biomaterials for applications in bone tissue engineering.

Acknowledgements

This work was supported by “Fundação de Amparo à Pesquisa do Estado de São Paulo - FAPESP” through the grants n° #2019/10228-5, #2024/19218-0 and #2021/04957-4.

D1 – P208

Novel 3D open-cell lattices for bone tissue engineering: Mathematical models, flow permeability, additive manufacturing, and mechanical characterisation

Sharma A.[1], Kalyanasundaram D.[1,2]
[1]Centre for Biomedical Engineering (CBME), Indian Institute of Technology (IIT), Delhi; [2]Dept. of Biomedical Engineering, All India Institute of Medical Sciences (AIIMS), New Delhi, India

Introduction

Bone fractures frequently require orthopaedic substitutes, but the mechanical mismatch between native bone and solid titanium implants causes stress shielding and subsequent implant failure. Furthermore, native bone exhibits anisotropic mechanical properties, which remains a challenge for current isotropic triply periodic minimal surface (TPMS) designs.

Aim

The study aims to mathematically design, fabricate, and characterize novel bio-inspired 3D open-cell lattices. These structures are methodically designed to offer programmable, anisotropic mechanical properties that closely resemble biological bone tissue, while retaining high fluid permeability to facilitate cell adhesion and nutrition transfer.

Materials and Methods

Four distinct 3D open-cell lattices (*Quadragon trabecula, Pentagon trabecula, Quadragon trigono*, and *Quadragon papilio*) were mathematically modelled using trigonometric continuous functions in MATLAB® 2025b. The structures were generated in a 10 mm^3 Euclidean space with a targeted 50% porosity and additively manufactured from Ti6Al4V alloy via the laser powder bed fusion (LPBF) process. Permeability was evaluated via Computational Fluid Dynamics (CFD) using an incompressible non-Newtonian fluid model and experimentally validated using water under modified Darcy's law. Effective Young's modulus, compressive strength, and fatigue life were quantified across all three orthogonal directions.

Results

The fabricated lattices demonstrated exceptional manufacturing precision via LPBF, achieving volume fraction deviations below 5% for specific architectures. Permeability assessments revealed excellent interconnected fluid flow capabilities. The Quadragon trabecula notably exhibited highly anisotropic flow properties, achieving peak permeability in the *X*-direction (3.1×10^{-12} m^2) due to its continuous, straight ovoid pore network. Mechanically, the effective Young's moduli across the different lattice directions ranged from 3.4 to 4.6 GPa, with ultimate compressive strengths between 284.4 and 475.9 MPa, successfully overlapping with target native bone properties. During ultra-high cycle fatigue testing, all lattices excluding the *Pentagon trabecula* successfully endured 10^6 cycles at worst-case physiological loads without catastrophic failure.

Conclusion

Mathematical modelling of bioinspired 3D open-cell lattices provides a highly tuneable platform for altering anisotropic mechanical and fluidic properties. The *Quadragon trabecula* architecture optimally overcomes the limitations of isotropic TPMS implants by mimicking the mechanical anisotropy of native bone, offering a durable, highly permeable framework for next-generation patient-specific orthopaedic implants.

D1 – P209

Homogeneous-phase crosslinking of biotechnological and animal-derived chondroitin: A comparative physicochemical and biological study

Di Meo C.[1], Vassallo V.[2], Bedini E.[3], La Gatta A.[1], Cimini D.[4], Schiraldi C.[1]
[1]Dept. of Experimental Medicine, University of Campania "Luigi Vanvitelli", Naples; [2]Dept. of Life Sciences, Health and Health Professions, Link Campus University, Rome; [3]Dept. of Chemical Science, University of Naples "Federico II", Naples; [4]Dept. of Environmental, Biological and Pharmaceutical Sciences and Technologies, University of Campania "Luigi Vanvitelli", Caserta, Italy

Introduction

Chondroitin-based biomaterials are widely used in regenerative medicine, particularly for cartilage repair, due to their bioactivity and role in extracellular matrix homeostasis. However, conventional chondroitin sulfate (CS) is typically animal-derived, raising concerns related to ethical issues, batch variability, and potential contaminants. Biotechnological unsulfated chondroitin (BC) represents a promising non-animal alternative with improved purity and reproducibility.
Nevertheless, both sulfated and unsulfated chondroitin in solution exhibit poor mechanical and viscoelastic properties, limiting their effectiveness in applications such as viscosupplementation. Therefore, chemical crosslinking is required to enhance their structural stability and functional performance.

Materials and Methods

In this study, shark-derived CS and BC, both with an initial molecular weight of approximately 35 kDa, were chemically crosslinked in homogeneous phase using 1,4-butanediol diglycidyl ether under alkaline conditions at room temperature. The resulting products (XBC, XCS) were purified by dialysis, resuspended in PBS at 40 g/L, and sterilized by autoclaving prior to further use.
Physicochemical characterization was performed by size exclusion chromatography coupled with triple detector array (SEC-TDA) at T0 and after enzymatic degradation with ABC chondroitinase. Rheological measurements were carried out to evaluate viscoelastic properties, while biological performance was assessed using primary human chondrocytes and synoviocytes.

Results

NMR analysis revealed a significantly higher degree of modification for BC, approximately twice that of CS. SEC-TDA confirmed these findings, showing a marked increase in molecular weight for XBC (≈85 kDa) along with a decrease in intrinsic viscosity, whereas XCS remained close to its initial values, indicating limited crosslinking. Enzymatic degradation studies further demonstrated enhanced stability for both crosslinked samples compared to their native counterparts.
Rheological measurements highlighted a clear difference between the two systems: XBC exhibited a substantial enhancement in viscoelastic behavior compared to both native BC and XCS, showing increased stiffness and elastic response, whereas XCS displayed properties comparable to native CS, confirming the limited effectiveness of the crosslinking process.
Biological assays on primary human chondrocytes and synoviocytes confirmed good cytocompatibility for all samples. Cells maintained their phenotype and showed increased extracellular matrix (ECM) production, particularly collagen type II and aggrecan, with differences observed between modified and unmodified materials.

Conclusion

This study demonstrates that biotechnological chondroitin not only eliminates ethical concerns associated with animal-derived materials but also provides superior chemical modifiability and rheological performance. XBC emerges as a highly promising candidate for the development of advanced biomaterials for cartilage regeneration and intra-articular applications.

Acknowledgements

This work was partially supported by the MIMIT project "CROSS GAG" CUP B29J24001220005 (Italy).

D1 – P210

Ultra-long ion-doped hydroxyapatite nanofibers: From brittle ceramics to flexible bioactive scaffolds

Tabatabaei Koupaei F.[1,2,3], Morel T.[1], Ginebra M.P.[1,2,3], Espanol M.[1,2,3]
[1]Biomaterials, Biomechanics and Tissue Engineering Group, Dept. of Materials Science and Engineering and Institute for Research and Innovation in Health (IRIS), Universitat Politècnica de Catalunya - BarcelonaTech, Barcelona; [2]Barcelona Research Center in Multiscale Science and Engineering, Universitat Politècnica de Catalunya - BarcelonaTech, Barcelona; [3]Centro de Investigación Biomédica en Red - Bioingeniería, Biomateriales y Nanomedicina (CIBER-BBN), Instituto de Salud Carlos III, Madrid, Spain

Introduction

Hydroxyapatite (HA) is widely used for bone regeneration due to its chemical similarity to bone mineral and its osteoconductive properties. However, conventional HA ceramics are intrinsically brittle and poorly resorbable. Recently, ultra-long HA nanofibers (NFs) have gained attention due to their high aspect ratio and structural flexibility (1). In natural bone, hydroxyapatite also contains trace ions such as Mg^{2+}, Sr^{2+} and Zn^{2+} that enhance biological activity. Incorporating these ions into HA nanofibers, followed by their assembly into scaffolds, could therefore combine structural flexibility with improved biofunctionality.

Materials and Methods

Ultra-long HA nanofibers were synthesized via sodium-oleate-assisted hydrothermal processing. Two doping strategies were compared: a one-step route, where ions were added during precursor preparation, and a two-step route, where doping was performed after nanofiber formation. The resulting NFs were assembled into nanofibrous scaffolds by ice templating. Structural and compositional characterization was performed using XRD, TEM and ICP-OES. The mechanical properties of the scaffolds, together with an initial *in vitro* screening, were also evaluated.

Results

NFs prepared through one-step synthesis produced structural and morphological alterations as observed by XRD and TEM, including peak broadening, secondary phases and shorter fibers. In contrast, the two-step strategy preserved the ultralong one-dimensional morphology. XRD patterns remained dominated by HA (Figure 1). TEM confirmed continuous nanofibers with diameters of ~4–10 nm. ICP analysis showed decreasing Ca/P ratios with increasing dopant concentration and increasing (Ca+M) /P ratios (Figure 2). This suggests a dual mechanism of lattice substitution and surface-associated ion adsorption, which is important for controlled therapeutic ion release. The mechanical properties of the nanofibrous doped scaffolds (prepared via two-step synthesis route) were observed to improve with doping content. The initial *in vitro* screening using human fibroblasts proved differences in cell adhesion and proliferation between samples.

Conclusion

Ion-doped ultra-long HA NFs were successfully synthesized though a two-step reaction involving the initial formation of pure HA NFs followed by doping**.** This approach allowed for the creation of flexible scaffolds with tailored chemical, mechanical, and *in vitro* cell behavior.




Figure 1. XRD patterns and TEM images comparing one-step and two-step synthesis of ion-doped HA nanofibers. * Indicates Zn-containing calcium phosphate phases and dots denotes Sr-apatite.




Figure 2. ICP analysis of ion-doped HA nanofibers synthesized via the two-step route showing Ca/P and (Ca+M) /P ratios and the proposed ion incorporation mechanism.

References

[1]Lu B.-Q., Zhu Y.-J., Chen F. Highly Flexible and Nonflammable Inorganic Hydroxyapatite Paper. *Chem. Eur. J* 2014; 20; 1242-1246.

D1 – P211

Electrospun polylactic acid scaffolds enhanced with shrimp shell-derived chitosan and carboxymethyl chitosan for meniscus tissue engineering

Jeencham R.[1,6], Ruksakulpiwat J.[2,6], Sukpatrapirom P.[3,6], Cherdpan A.[4,6], Numpaisal P.[5,6]
[1]Faculty of Textile Industry, Rajamangala University of Technology, Bangkok, [2]Faculty of Medicine, Prince of Songkla University, Songkhla; [3]Faculty of Medicine, Chulalongkork University, Bangkok; [4]Faculty of Medicine, King Mongkut's Institute of Technology Ladkrabang, Bangkok; [5]Institute of Medicine, Suranaree University of Technology, Nakhon Ratchasima; [6]Research Center for Biocomposite Materials for Medical Industry and Agricultural and Food Industry, Nakhon Ratchasima, Thailand

Introduction

Polylactic acid (PLA) is widely utilized in medical applications and tissue engineering due to its excellent mechanical strength and biodegradability. However, its inherent hydrophobicity significantly limits biocompatibility and optimal cellular interaction. To overcome this, incorporating a natural bioactive polymer is essential. Among various alternatives, chitosan (CS) uniquely addresses multiple objectives. It not only improves the biological interface but, when extracted from abundant marine biowaste like shrimp shells, also mitigates environmental pollution and adds economic value through upcycling. Since pure CS exhibits poor aqueous solubility at physiological pH, carboxymethylation is employed. This creates carboxymethyl chitosan (CMCs) with hydrophilic groups, profoundly enhancing neutral-pH solubility, biocompatibility, and cellular affinity. This study investigates integrating upcycled, shrimp shell-derived CS and CMCs into electrospun PLA nanofibers to develop highly functional biomimetic scaffolds for meniscus tissue engineering.

Materials and Methods

Chitosan (CS-S) and carboxymethyl chitosan (CMCs-S) were successfully synthesized and extracted from the shrimp shells. These biopolymers were subsequently blended with PLA at specific ratios. The composite solutions were electrospun to fabricate complex nanofibrous scaffolds. The physicochemical properties, surface morphology, and mechanical strength of the scaffolds were systematically evaluated using Fourier-transform infrared spectroscopy (FTIR), scanning electron microscopy (SEM), contact angle measurements, and tensile testing to assess their overall suitability for demanding meniscal applications.

Results

The extraction yielded CS with a 93.10% degree of deacetylation. CMCs carboxymethylation was confirmed by a 2.78 degree of substitution. Incorporating these biopolymers reduced the average nanofiber diameter (0.65–1.05 μm), creating a finer network mimicking the native extracellular matrix. CMCs notably enhanced surface wettability, reducing the water contact angle from 146° (pure PLA) to 126° (composite). While blending PLA with commercial CS maximized tensile strength at 5.69 MPa, the novel PLA/CMCs composite scaffold maintained functional mechanical robustness with a tensile strength of 3.70 MPa, sufficient for physiological load-bearing.

Conclusion

Enhancing electrospun PLA scaffolds with shrimp shell-derived CMCs successfully addresses the inherent hydrophobicity of PLA, substantially improving surface wettability and the biological interface. Concurrently, utilizing this specific natural polymer upcycles marine biowaste, adding economic value while maintaining the essential mechanical strength required for meniscal repair. This composite scaffold exhibits high potential as a functional biomaterial, offering both biomedical advancements and environmental sustainability.

Acknowledgements

The authors gratefully acknowledge the financial support provided by Suranaree University of Technology.

D1 – P212

Biomimetic electrospun nanofibrous scaffolds from silk fibroin and polyvinyl alcohol for meniscus tissue engineering

Ruksa A.[1,5], Jeencham R.[2,5], Numpaisal P.[3,5], Ruksakulpiwat Y.[4,5]
[1]Faculty of Science and Liberal Arts, Rajamangala University of Technology Isan, Nakhon Ratchasima; [2]Faculty of Textile Industry, Rajamangala University of Technology, Bangkok; [3]Institute of Medicine, Suranaree University of Technology, Nakhon Ratchasima, Thailand; [4]Institute of Engineering, Suranaree University of Technology, Nakhon Ratchasima; [5]Research Center for Biocomposite Materials for Medical Industry and Agricultural and Food Industry, Nakhon Ratchasima, Thailand

Introduction

Meniscal injuries present a significant clinical challenge due to the tissue's limited intrinsic healing capacity. Electrospun nanofibrous scaffolds that closely mimic the native extracellular matrix (ECM) offer a promising strategy for meniscus tissue engineering. Silk fibroin (SF) is a natural biopolymer widely utilized in medical applications due to its excellent biocompatibility, slow biodegradability, and high mechanical resilience. Furthermore, silk is a highly abundant local resource in our region. Utilizing it for advanced biomedical applications not only provides a sustainable material source but also adds substantial economic value to the local community. However, pure SF is challenging to electrospin. Blending it with polyvinyl alcohol (PVA), a highly hydrophilic and biocompatible synthetic polymer, significantly enhances its electrospinnability. This study aims to develop and characterize biomimetic SF/PVA nanofibrous scaffolds for meniscal regeneration.

Materials and Methods

Silk fibroin was extracted and degummed from *Bombyx mori* cocoons and subsequently blended with PVA at optimal weight ratios. The blended polymer solutions were fabricated into nanofibrous scaffolds via an optimized electrospinning process. The morphological, physicochemical, and mechanical properties of the resulting scaffolds were systematically characterized. Scanning electron microscopy (SEM) was utilized to assess fiber diameter, distribution, and pore size. Fourier-transform infrared spectroscopy (FTIR) was employed to evaluate the secondary structure of SF and the chemical interactions between SF and PVA. Additionally, the mechanical properties were determined through tensile testing to ensure the scaffolds could withstand joint-like loads.

Results

The electrospinning process successfully yielded highly uniform, bead-free nanofibrous structures that closely replicate the architectural complexity of the native meniscal ECM. The incorporation of PVA significantly improved the spinnability and stability of the SF solution. SEM analysis revealed an interconnected porous network with an average fiber diameter highly conducive to cellular infiltration. FTIR spectra confirmed the successful blending and physical interaction between SF and PVA, primarily through hydrogen bonding. Furthermore, the resulting SF/PVA scaffolds demonstrated favorable surface wettability and porosity, which are crucial for optimal cellular attachment and proliferation. Mechanical evaluation showed that the structural integrity and tensile strength of the blended scaffolds were well-maintained, exhibiting load-bearing capacities comparable to those required for physiological meniscus tissue function.

Conclusion

The biomimetic electrospun SF/PVA nanofibrous scaffolds possess highly favorable morphological, physicochemical, and mechanical properties. By successfully combining the biological advantages of a locally abundant natural resource with the spinnability of PVA, these composite scaffolds demonstrate significant potential as a supportive microenvironment for meniscus tissue engineering. This approach not only advances functional tissue regeneration but also promotes the value-added utilization of local agricultural resources.

D1 – P213

Plasma-modified exosome-functionalized surgical sutures for meniscal tear repair

Yong-Ji Chen, Wei-Fu Lee, Jhe-Lun Hu, Shwu-Jen Chang*
Dept. of Biomedical Engineering, I-Shou University, Kaohsiung City, Taiwan

Introduction

The meniscus is a vital fibrocartilaginous structure in the knee responsible for load distribution and joint stabilization [1]. Due to limited vascularization, its intrinsic regenerative capacity is extremely low. While surgical suturing remains the primary clinical treatment for meniscal tears, suboptimal biological integration and postoperative inflammation frequently compromise long-term healing outcomes. Although exosomes have emerged as potent regenerative agents, their rapid clearance from the injury site limits therapeutic efficacy [2]. Consequently, developing localized delivery systems capable of maintaining bioactive factor retention is critical for improving clinical repair outcomes [3]. To address this challenge, we developed a plasma-modified surgical suture platform designed to enhance exosome immobilization. This platform facilitates stable exosome adsorption for localized, sustained delivery at the meniscal repair site.

Materials and Methods

To fabricate this system, commercial multifilament surgical sutures were subjected to atmospheric nitrogen plasma treatment. This process modified the surface topography, increasing roughness to facilitate exosome immobilization. Surface properties and elemental composition were then characterized via Scanning Electron Microscopy (SEM) and Energy-Dispersive X-ray Spectroscopy (EDX), respectively. Mechanical integrity was evaluated through tensile testing to ensure the preservation of suture strength, while in vitro cytocompatibility and cell proliferation assays were conducted to assess the biological performance of the exosome-loaded sutures. Chondrocyte gene expression (COL I, COL II, SOX9) analyzed by qRT-PCR at days 1, 3, and 5.

Results

SEM analysis confirmed that plasma treatment significantly increased surface roughness, while tensile testing demonstrated that this modification preserved the bulk mechanical integrity of the fibers required for surgical fixation. EDX spectra further validated the successful surface modification. Following incubation, spherical vesicle-like structures were observed on the plasma-treated surfaces, confirming stable exosome adsorption. In vitro evaluations indicated excellent cytocompatibility and significantly enhanced cellular proliferation, highlighting the platform's capacity to provide a sustained bioactive environment. qRT-PCR analysis showed that the plasma-treated sutures with exosomes group progressively increased COL II and SOX9 over time, while COL I remained relatively low, indicating a gene expression profile favorable for cartilage formation.

Conclusion

This study demonstrates that atmospheric plasma modification effectively functionalizes surgical sutures for exosome immobilization. The resulting bioactive sutures maintain their mechanical robustness while providing localized delivery of regenerative factors. This strategy offers a promising approach to improve the biological microenvironment at meniscal injury sites, potentially leading to superior clinical repair outcomes.

Acknowledgements

This work was supported by the National Science and Technology Council, Taiwan, Grant No. NSTC113-2221-E-214 -003 -MY3.

References

[1]Mordecai S.C., et al. Treatment of meniscal tears: An evidence based approach. *World J Orthop* 2014; 5(3); 233-41.
[2]Nakama G.Y., et al. Biomechanical Comparison of Vertical Mattress and Cross-stitch Suture Techniques and Single- and Double-Row Configurations for the Treatment of Bucket-Handle Medial Meniscal Tears. *The American Journal of Sports Medicine* 2019; 47(5); 1194-1202.
[3]LaPrade C.M., et al. Concurrent Repair of Medial Meniscal Ramp Lesions and Lateral Meniscus Root Tears in Patients Undergoing Anterior Cruciate Ligament Reconstruction: The "New Terrible Triad". *Arthroscopy Techniques* 2023; 12(9); e1565-e1578.

D1 – P214

Development of an Electrospun PCL-Based Bilayer Membrane for Guided Bone Regeneration in Periodontal Applications

Schlinkmann R., Becker F., Paland F., Gries T.
ITA – Institut für Textiltechnik, RWTH Aachen University, Aachen, Germany

Introduction

Periodontal bone defects affect approximately 750 million people worldwide and require surgical intervention. Guided bone regeneration (GBR) employs barrier membranes to separate soft tissue from bone defects, enabling unimpeded osteogenic regeneration.

Aim

Current GBR membranes are predominantly non-resorbable or collagen-based, each with inherent clinical limitations. Electrospun polycaprolactone (PCL) nanofibrous membranes offer a tuneable, resorbable alternative[1]. This study investigates the influence of electrospinning process parameters on membrane morphology to establish a foundation for a bilayer GBR membrane combining a cell-occlusive epithelial-facing layer with an osteoconductive bone-facing layer.

Materials and Methods

PCL (Purasorb PC12, Mn = 72,000 g/mol) was dissolved in chloroform/methanol (75/25 vol%, 14 wt%) and processed using a Fluidnatek LE-500 electrospinning system equipped with a rotating drum collector (150 rpm, Ø 25 mm). A full factorial design varied flow rate (2, 4, 8 ml/h) and spinning time (10, 30 min), yielding 6 experimental conditions with n = 5 specimens each (30 total). Fiber diameter was measured by light microscopy (Leica DM4000M, n = 10). Membrane thickness was determined by digital micrometry according to DIN EN ISO 9073-2. Pore size distribution was assessed by capillary flow porometry (Topas PSM 165.

Results

Fiber diameters ranged from 0.41 to 2.16 µm, with mean values between 0.99 and 1.18 µm. A statistically significant increase in fiber diameter was observed when flow rate was increased from 4 to 8 ml/h ($p < 0.05$, t-test). Membrane thickness ranged from 0.028 to 0.386 mm and correlated significantly with both flow rate (near-linear relationship) and spinning time ($p < 0.05$). A flow rate of 4 ml/h yielded the target thickness of ~0.10 mm for the PCL layer within the planned bilayer construct. Mean pore sizes ranged from 26.3 to 35.1 µm — below the threshold required for osteogenic cell ingrowth (> 100 µm) but above the limit for adequate epithelial cell occlusion (< 10 µm).

Conclusion

Electrospun PCL membranes demonstrate highly tuneable fiber and thickness characteristics suitable for bilayer GBR membrane development. While fiber diameter and membrane thickness targets were successfully met at a flow rate of 4 ml/h, pore size optimisation remains critical. Strategies under evaluation include modified collector geometries and increased polymer solution viscosity to achieve the requirements for a functional bilayer GBR membrane[2].

Acknowledgements

This work was funded by the “Zentrales Innovationsprogramm Mittelstand (ZIM)” and supported by Fibrothelium GmbH (Germany).

References

[1]Dimitriou R., Mataliotakis G.I., Calori G.M., Giannoudis P.V. The role of barrier membranes for guided bone regeneration and restoration of large bone defects: current experimental and clinical evidence. *BMC Medicine* 2012; 10; 81.
[2]Ameer J.M., Pr A.K., Kasoju N. Strategies to Tune Electrospun Scaffold Porosity for Effective Cell Response in Tissue Engineering. *Journal of Functional Biomaterials* 2019; 10(3).

D1 – P215

A biomimetically inspired collagen scaffold with graduated pore structure for meniscal repair

Wang Y., Shepherd J.
School of Engineering, University of Leicester, Leicester, UK

Introduction

Meniscal tears affect 60–70 per 100,000 individuals annually, leading to pain, instability, and progressive joint degeneration.[1] Although tissue engineering offers promising strategies for meniscal regeneration [2], the limited self-healing capacity of the meniscus, particularly in avascular regions, remains a major challenge.[3]

This study aims to develop a biomimetic collagen scaffold with a graduated pore structure and fibre reinforcement, and to evaluate its performance through mechanical testing, degradation analysis, and in vitro cell culture.

Materials and Methods

Type I collagen slurry was iteratively layered in a freeze-dryer at pre-freeze temperatures of −20°C and −40°C to generate a graduated pore architecture. The fabrication process of the multi-sectional scaffold is illustrated in Figure 1. Cross-linked collagen fibres extruded in PEG/PBS buffer and electrospun gelatine fibres were incorporated to enhance structural integrity. EDC/NHS cross-linking was applied post-freezing.

Scaffolds were characterised using scanning electron microscopy (SEM), micro-computed tomography (micro-CT), and mechanical testing. For biological evaluation and as part of a wider study, sterilised scaffolds were seeded with tenocytes at a density of 1×10^4 cells per scaffold. Cell viability (Live/Dead assay), proliferation (alamarBlue), morphology, and infiltration (confocal microscopy) were assessed at days 1, 3, and 7.




Figure 1. Flowchart of making multi-sectional scaffolds with collagen fibres




Figure 2. SEM images of collagen materials: (a) two-layer collagen scaffold; (b) −40°C layer; (c) −20°C layer; (d) collagen fibre; (e) composite materials with cross-linked fibres; (f) cells seeded on the collagen scaffold showing adhesion and spreading

Results

The scaffold exhibited distinct regional variations in pore size and interconnectivity, with seamless integration between layers. Representative SEM images of the scaffold structure and fibre-reinforced composites are shown in Figure 2. Incorporation of collagen fibres significantly enhanced mechanical strength and porosity. Degradation studies demonstrated a controlled reduction in mass and mechanical properties over time.

Cell culture results showed robust cell attachment and sustained viability over 7 days, with increasing metabolic activity indicating active proliferation. Confocal imaging revealed elongated cell morphology aligned along collagen fibres, suggesting contact guidance and fibre-directed cell organisation.

Conclusion

The developed scaffold successfully combines a graduated pore structure with fibre reinforcement to achieve enhanced mechanical performance and controlled degradation behaviour. It supports cell viability, proliferation, and alignment, demonstrating strong potential for guiding tissue regeneration in meniscal repair.

Acknowledgements

This work was supported by the School of Engineering, University of Leicester, and China Scholarship Council (CSC). The author also acknowledged the MRC CiC funding provided through LD3, Hercules facility at school of engineering (EPSRC grant EP/X014614/1), and Materials Centre, University of Leicester.

References

[1]Ahmed I., Khatri C., Parsons N., and et al. Meniscal Tear Outcome (METRO) review: a protocol for a systematic review summarising the clinical course and patient experiences of meniscal tears in the current literature. *BMJ Open* 2020; 10(8); e036247.

[2]Yan R., Chen Y., Gu Y., and et al. A collagen-coated sponge silk scaffold for functional meniscus regeneration. *Journal of Tissue Engineering and Regenerative Medicine* 2019; 13(2); 156-173.

[3]Shepherd J.H., Howard D., Waller A.K., and et al. Structurally graduated collagen scaffolds applied to the ex vivo generation of platelets from human pluripotent stem cell-derived megakaryocytes: Enhancing production and purity. *Biomaterials* 2018; 182; 135-144.

D1 – P216

Development of a multilayer controlled-release surface coating on endotracheal tubes to prevent ventilator-associated pneumonia

Ayasreh R.[1], Rabi A.[2], McCoy C.P.[1], Wylie M.P.[1].
[1]Dept. of Pharmacy, Queen's University Belfast, Belfast, UK; [2]Dept. of Pharmacy, Jerash University, Jerash, Jordan

Introduction

Endotracheal tubes (ETs) play a vital role in maintaining an open airway and facilitating mechanical ventilation for patients who are unable to breathe independently. However, ETs introduce a foreign surface within the body, providing an opportunity for pathogens to colonise and increasing the risk of ventilator-associated pneumonia (VAP) [1]. VAP, defined as pneumonia occurring 48 hours or more after mechanical ventilation, is often associated with the colonisation of ETTs by pathogenic and antibiotic-resistant bacteria. Despite advances in treatment, VAP remains a leading cause of morbidity and mortality in healthcare settings, especially in intensive care units, with mortality rates reaching up to 76% within the vulnerable subpopulation [1,2]. Addressing this issue requires innovative approaches to prevent bacterial colonisation and reduce the incidence of VAP. This research aims to develop a multi-layered antimicrobial coating for ETTs, exploiting silver-thiol interactions to adhere a stable HEMA-MMA hydrogel to the ETT surface, providing a sustained release profile potentially to reduce infection risk during intubation.

Materials and Methods

The development of a multilayer coating on ETs for controlled release involved a systematic multi-step surface modification process. Initially, polyvinyl chloride (PVC) substrates were chemically pre-sensitised to enhance surface receptivity for adherent silver attachment facilitated by immersion in Tollen's reagent, creating a robust metallic silver surface coating of PVC (Ag-PVC). Ag-PVC was functionalized with allyl mercaptan, establishing a critical adhesive bridge between the silver layer (through sulfur) and the subsequent hydrogel matrix (through the copolymerisbale allyl group) (AM-Ag-PVC). A hydrogel layer was synthesized using a mixture of hydroxyethyl methacrylate (HEMA) and methyl methacrylate (MMA) in varying concentrations with ethylene glycol dimethacrylate (EGDMA) as a crosslinking agent and a photoinitiator for curing of the coating by UV irradiation. Levofloxacin was used as a model antibiotic drug, incorporated through a post-loading method into the polymeric network. Comprehensive characterisation included coating adhesion testing under extreme and mild conditions to assess the coating's structural integrity through the insertion and removal process, and its durability throughout the intubation time. Swelling and in vitro drug release kinetics studies were conducted to evaluate the sustained release profile during simulated intubation.

Results

PVC surfaces were successfully treated and functionalised with allyl mercaptan as confirmed by contact angle analysis. Three distinct hydrogel compositions were synthesized on the AM-Ag-PVC surface: p[PHEMA]-AM-Ag-PVC, p[HEMA-co-MMA(10%)]-AM-Ag-PVC, and p[HEMA-MMA(25%)]-AM-Ag-PVC. As shown in Figure 1, swelling studies revealed a progressive decrease in swelling degree with increasing methyl methacrylate (MMA) concentration, attributed to enhanced surface hydrophobicity introduced by the hydrophobic monomer. Specifically, the difference in swelling degree between the 0% (w/w) MMA and 25% (w/w) MMA compositions was approximately 6%, with the 0% (w/w) MMA composition swelling to 21% and the 25% (w/w) MMA composition swelling to 15%. In vitro drug release studies a sustained release profile correlating with MMA monomer concentration as demonstrated in Figure 2. The hydrogel composition with 0% (w/w) MMA (p[HEMA]-AM-Ag-PVC) showed fastest drug release, reaching nearly 100% cumulative release within 12 days. In contrast, the hydrogels with 10% (w/w) MMA (p[HEMA-co-MMA (10%)]-Am-Ag-PVC) and 25% (w/w) MMA (p[HEMA-co-MMA(25%)]-Am-Ag-PVC) both reached 100% cumulative release after 14 and 16 days respectively. With a median intubation time of 8.2 days, the observed sustained drug release of up to 16 days could provide protection from VAP for the lifespan of the ETT for the majority of patients. Coating adhesion testing validated the model's structural integrity under both mild and extreme conditions. Silver-thiol-treated PVC samples demonstrated significantly higher coating retention relative to untreated PVC, with retained coating mass exceeding 88% across all HEMA-MMA hydrogel formulations compared to approximately 7% for untreated PVC. These results highlight the enhanced

durability and adhesion properties of the treated samples, emphasizing their potential to maintain consistent performance throughout the intubation period.

Conclusion

The multi-layered endotracheal tube coating demonstrates promising potential for preventing VAP through sustained drug delivery from a durable surface coating. AM-Ag-PVC exhibited superior adhesion and structural stability, while copolymerization with HEMA-MMA provided extended drug release profiles lasting up to 16 days, aligning with typical clinical intubation durations.




Figure 1: Percentage of water content (%) of various p[HEMA-co-MMA]-AM-Ag-PVC in phosphate buffered saline (pH =7.4), n=5, error bars indicate ± SD.




Figure 2: Release profile of Levofloxacin from various [p(HEMA-co-MMA)]-AM-Ag-PVC samples at 37 °C with shaking at 100 rpm (n=5, error bars indicate ± SD)

References

[1]Howroyd F., et al. Ventilator-Associated Pneumonia: Pathobiological Heterogeneity and Diagnostic Challenges. *Nature Communications* 2024; vol. 15, no. 1; Nature Portfolio, July 2024, https://doi.org/10.1038/s41467-024-50805-z.
[2]Spalding M.C. et al. Ventilator-Associated Pneumonia. *Critical Care Clinics* 2017; vol. 33, no. 2, Apr. 2017; 277–92. https://doi.org/10.1016/j.ccc.

D1 – P217

Biological Effects of Plant Viruses on Cancer Cell–Macrophage Crosstalk in the Tumor Microenvironment

Jie Li[a*] (lij@blsa.com.cn), Luyuan Yang[a], Zhi-Can Fu[a], Fen Xie[a], Yunu Ma[a], Lingling Yun[a], Yan Qian[a], Yaning Fu[a#], Hongwei Hou[a#], Pengfei Zhang[b#]


a. Beijing Life Science Academy, Beijing, China, Email:

b. Shenzhen Institutes of Advanced Technology(SIAT), Chinese Academy of Sciences(CAS), Shenzhen, China Email: pf.zhang@siat.ac.cn

Corresponding author; *Presenter

Background

- Cancer therapy is often limited by drug resistance, off-target toxicity, and an immunosuppressive tumor microenvironment (TME).
- Plant virus nanoparticles (PVNPs) have emerged as promising biomaterials owing to their:
  - Excellent biocompatibility
  - Structural uniformity
  - Ease of large-scale production
  - Intrinsic immunostimulatory properties



- Among them, **Tobacco Mosaic Virus (TMV)** is a highly stable rod-shaped plant virus that has been explored as a nanocarrier and immunomodulatory platform.
- However, the intrinsic biological effects of TMV itself and its interactions with tumor–immune cells remain poorly understood.

Objective

To systematically investigate:

- Cellular interactions of TMV with tumor cells and macrophages
- TMV-mediated immune regulation
- Mechanisms underlying macrophage–tumor cell communication
- The potential of TMV to enhance mild photothermal therapy (PTT)

Conclusion

- TMV exhibits excellent biocompatibility and negligible direct cytotoxicity.
- TMV is preferentially internalized by macrophages rather than tumor cells.
- TMV activates TLR7-mediated inflammatory signaling and induces robust cytokine production.
- Activated macrophages suppress tumor cell viability through paracrine communication.
- TMV-derived inflammatory responses attenuate HSP70 expression and sensitize tumor cells to mild photothermal therapy.

Results




Figure 1. The extraction and characterization of TMV




Figure 2. The cellular uptake and cytotoxicity study of TMV.




Figure 3. Molecular mechanism of TMV-induced macrophage activation and potential paracrine signaling.




Figure 4. Biological effects of TMV on cancer cell-macrophage crosstalk and regulation of HSP70-mediated stress response in tumor cells.




Figure 5. *In vivo* antitumor efficacy of TMV combined with PTT.

D1 – P218

From cell source to bone formation: Comparative osteogenic performance of exosomes in a HOB–HUVEC co-culture system

Cheng R.; Yun Ye C.; Neelam Gurav; Ana Angelova A.; Di Silvio L.
Faculty of Dentistry, Oral & Craniofacial Sciences, King's College London, UK

Introduction


Exosomes are extracellular vesicles (40–150 nm) that mediate intercellular communication through the transfer of bioactive molecules. Mesenchymal stem cell-derived exosomes (MSC-exo) have shown promising potential for bone regeneration owing to their biocompatibility and low immunogenicity. Exosomes from different stem cell sources exhibit different osteogenic potentials, while HUVEC-derived exosomes contribute to osteogenesis–angiogenesis coupling by promoting communication between endothelial and osteoblast cells. This study will compare the effects of stem cell derived exosomes and human umbilical vein endothelial cells (HUVEC) derived exosomes on early osteogenic differentiation in a co-culture system to identify the most promising exosome source for future studies.

Materials and Methods

Exosomes were isolated from human bone marrow mesenchymal stem cells (hBMSCs), human dental pulp stem cells (hDPSCs), and HUVEC conditioned media using size-exclusion chromatography and characterized by nanoparticle tracking analysis. A 1:1 human osteoblast (HOB)–HUVEC co-culture system was treated with the different exosome types. Cell viability was assessed by Alamar Blue assay. Osteogenic differentiation was evaluated by ALP activity and Alizarin Red S staining, while angiogenic potential was detected using a tube formation assay. Expression of osteogenic and angiogenic markers (RUNX2, ALP, and VEGF etc) are going to be analysed by qPCR.

Results

Cell viability remained stable among all groups throughout the 7-day culture period. ALP staining was greater in HOB–HUVEC co-cultures than in HOB monocultures, reaching its maximum at day 5 before gradually decreasing. Exosome stimulations further increased ALP activity, with hDPSC-Exo producing the strongest response and approximately 4% greater stained area than the untreated co-culture control. Mineralisation increased progressively over the 21-day culture period, with significantly greater calcium deposition observed in the hBMSC-Exo and hDPSC-Exo groups at day 21, and HUVEC-Exo did not produce a measurable effect(Figure1). In angiogenesis assays, hBMSC-Exo promoted the formation of more complex and highly branched tube-like networks in HUVEC monocultures. Quantitative assessment of angiogenesis in HOB–HUVEC co-cultures was not comparable because of high density cellular aggregation led to collapse of the network structures(Figure 2).






Figure1(left): Alizarin Red staining images at 4x magnification
Figure2(right): Fluorescence images of tube formation assays acquired at 10x magnification.

Conclusion

In this in vitro HOB–HUVEC co-culture model, exosome treatment significantly enhanced osteogenic differentiation while simultaneously supporting angiogenic activity, highlighting their potential as multifunctional mediators of bone regeneration. The observed effects were dependent on exosome source, with stem cell-derived exosomes exhibiting greater pro-osteogenic potential than HUVEC-derived exosomes. These findings demonstrate the value of a co-culture model for investigating osteogenesis–angiogenesis coupling and suggest that stem cell-derived exosomes may be more suitable candidates for bone regeneration applications.

References

[1]Kalluri R., LeBleu V.S. The biology, function, and biomedical applications of exosomes. *Science* 2020; 367(6478). doi: 10.1126/science.aau6977

[2]Li X. et al. Challenges and opportunities in exosome research: Perspectives from biology, engineering, and cancer therapy. *APL Bioeng* 2019; 3(1); 011503. doi: 10.1063/1.5087122

[3]Tan S.H.S. et al. Mesenchymal stem cell exosomes in bone regenerative strategies-a systematic review of preclinical studies. *Mater Today Bio* 2020; 7; 100067. doi: 10.1016/j.mtbio.2020.100067

[4]Malik S., Muhilan Y., Nordin F. et al. Stem cell derived exosome trilogy: an epic comparison of human MSCs, ESCs and iPSCs. *Stem Cell Res Ther* 2025; 16; 318. https://doi.org/10.1186/s13287-025-04440-0

D1 – P219

Pyroptosis-triggerable multifunctional nanotherapeutics for PTT/PDT therapy with synergistic immune activation against TNBC

Iong W.C. [1], Song X.Y. [1], Shen M.Y.[1,2], Chiu H.C.[1]*
[1]Dept. of Biomedical Engineering and Environmental Sciences, National Tsing Hua University, Hsinchu; [2]Dept. of Surgery, China Medical University Hsinchu Hospital, Hsinchu County, Taiwan

Introduction

As an emerging programmed cell death pathway, pyroptosis has shown a strong capacity to induce anticancer immune responses by activating cysteine-aspartic proteases (caspases) in response to specific stimuli and cleaving downstream members of the gasdermin protein family. Herein, we developed a multifunctional Bi_2O_3/Bi_2S_3 heterojunction nanoplatform integrated with lipopolysaccharide and calcium carbonate to trigger pyroptosis-mediated immune activation while simultaneously enabling synergistic photothermal and photocatalytic therapy under near-infrared irradiation. The combined phototherapeutic effects promote tumor ablation and oxidative stress, whereas pyroptotic cell death facilitates the release of inflammatory cytokines and tumor-associated antigens, thereby enhancing antitumor immunity.

Aim

This study aims to develop a new multifunctional therapeutic nanoparticle (NPs) to effectively combat triple-negative breast cancer (TNBC) through combined photothermal/photodynamic therapy, with immune system activation via cellular pyroptosis. The NPs were prepared using a Bi_2O_3/Bi_2S_3 heterojunction structure as the core and were further elaborated with two pyroptosis stimulants: lipopolysaccharide and calcium carbonate. With these two stimulants inducing both canonical and non-canonical pyroptotic pathways, along with cell rupture and death, abundant inflammatory cytokines and cancer-associated antigens were released, thereby triggering subsequent immune responses that inhibit late-stage metastasis and recurrence in TNBC.

Materials and Methods

Bi_2O_3/Bi_2S_3 heterojunction nanoparticles were synthesized and modified with LPS and $CaCO_3$. Their structure and composition were characterized by TEM, XRD, XPS, and EPR, and their photothermal performance was evaluated through in situ heating tests. In vitro therapeutic effects were evaluated by measuring Ca^{2+} release, ROS generation, and LPS-induced levels of inflammatory cytokines using fluorescence imaging, flow cytometry, and ELISA. In vivo antitumor efficacy was assessed in TNBC tumor-bearing mice by monitoring tumor growth and performing H&E staining, immunohistochemistry, and flow cytometry to analyze immune responses.

Results

Under NIR irradiation, a strong hyperthermic effect for tumor ablation was observed, and ROS were generated via photocatalytic reactions, achieving a synergistic effect between photothermal and photocatalytic therapy. Both in vitro and in vivo studies under NIR activation revealed significant inhibition of tumor growth, suppression of metastasis and recurrence, and markedly elevated expression of pyroptosis- and immune-related biomarkers, highlighting its strong potential for immune-potentiated combination therapy in TNBC.

Conclusion

The developed Bi_2O_3/Bi_2S-based multifunctional nanoplatform successfully integrates photothermal/ photodynamic therapy with pyroptosis-mediated immunotherapy, resulting in enhanced tumor eradication and systemic antitumor immune responses.

D1 – P220

H_2S-responsive CuSe nanoparticles convert into CuSSe in situ with band gap modulation for oxygen self-supply and enhanced colon cancer phototherapy

Kandel M., Chiu HC.*
Dept. of Biomedical Engineering and Environmental Sciences, National Tsing Hua University, Hsinchu, Taiwan

Introduction

Colorectal cancer (CRC) exhibits elevated hydrogen sulfide (H_2S) levels (0.01–3 mM) due to overexpression of cystathionine-β-synthase (CBS). Aberrant H_2S production promotes tumor initiation and progression by enhancing cellular bioenergetics, angiogenesis, proliferation, and metastasis. Transition metal chalcogenides have emerged as promising nanotherapeutics for cancer therapy due to their tunable electronic structures, catalytic activity, and photothermal properties. Therefore, developing H_2S-responsive metal chalcogenide nanoparticles (NPs) represents a promising strategy for tumor-specific therapy.

Aim


The aim of this study is to develop an in situ self-engineering nanoplatform based on H_2S-depleting CuSe NPs that transform into CuSSe within the tumor microenvironment, enabling anion–doping–mediated bandgap modulation to achieve synergistic photothermal therapy (PTT), chemodynamic therapy (CDT), and photocatalytic therapy (PCT).

Materials and Methods

CuSe NPs were synthesized via a hydrothermal method at 100 °C for 12 h and subsequently coated with albumin through metal-amine interactions to enhance biocompatibility and colloidal stability. In vitro studies were performed using CT26 murine colon carcinoma cells. For in vivo evaluation, a subcutaneous CT26 tumor model was established in mice, followed by intravenous administration of CuSe NPs to assess antitumor efficacy and phototherapeutic performance.

Results

Hexagonal disc-like CuSe NPs exhibited high reactivity toward overexpressed H_2S in colon tumors, enabling in situ conversion into S-doped CuSSe with copper vacancies and a modulated bandgap. This transformation enhanced photothermal and photocatalytic performance compared to pristine CuSe. The engineered CuSSe facilitated efficient ROS generation through optimized band alignment, enabling superoxide radical ($O_2^{\cdot-}$) production and H_2O_2-driven oxygen generation. Additionally, the coexistence of Cu^+ and Cu^{2+} within the NPs further enhances catalytic activity, thereby promoting ROS generation. Albumin functionalization improved colloidal stability, cellular uptake, and tumor accumulation. In vivo studies further confirmed effective tumor nanoparticle accumulation, H_2S depletion, and enhanced phototherapeutic efficacy, demonstrating the potential of this self-engineering nanoplatform for synergistic PTT, CDT, and PCT (Scheme 1).



Scheme 1. Schematic illustration of the synthesis and the therapeutic mechanisms of CuSe NPs operated by reaction with H_2S and conversion into CuSSe NPs in situ, enabling H_2S depletion and enhanced photothermal, chemodynamic, and photocatalytic effects for synergistic cancer therapy.

Conclusion

The CuSe nanoplatform demonstrated significant tumor suppression with excellent biocompatibility, highlighting its potential as a promising strategy for modulating the tumor microenvironment and for phototherapy.

D1 – P221
Engineered liposomes for pulmonary drug delivery

Aparecida Paes Dutra J., Chorilli M.*
São Paulo State University, School of Pharmaceutical Sciences, Innovative Pharmaceutical Technology Group (IphaTec Group), Araraquara, Sao Paulo, Brazil

Introduction

Mycobacterium tuberculosis is the causative agent of human tuberculosis and is one of the most adaptable human pathogens. Infection by Mycobacterium tuberculosis results from a complex interplay between the host's immune system and the bacterium, making it one of the most adaptable human pathogens. Conventional therapy results in low pulmonary drug concentration, high systemic toxicity, high difficulty of eradication due to the survival of bacteria in alveolar macrophages, and low therapeutic adherence due to prolonged therapy (Warner *et al.*, 2025; Mohammadnabi *et al*., 2024). In this scenario, liposomes represent a promising strategy for pulmonary administration by spraying, since they allow direct deposition in the lungs, controlled release of the drug at the site of infection, and direct targeting of alveolar macrophages.

Materials and Methods

Liposomes composed of DPPC: Cholesterol: DSPE-PEG_{2000}-NH_2 (6.0: 3: 0.4; %mol) were produced using the lipid film hydration technique followed by the extrusion process to reduce size (Bangham et al. 1965). Solvent was removed by evaporation at 50 ºC for 40 minutes in a rotary evaporator, and the film was hydrated with 4 mL of sodium phosphate buffer (30 mM, pH 6.4) at 60 ºC for 60 minutes. The formulation was extruded through 200 nm (15 cycles) and 100 nm (10 cycles) membranes (Avanti®). The samples were stored at 4 ºC for at least 24 hours before the characterization analyses. The average hydrodynamic diameter of the particles and the intensity distribution, represented by the polydispersity index (PDI) and the surface charge of the particles was determined by the electrophoretic mobility were analyzed by the dynamic light scattering technique (Nano ZS, Malvern Zetasizer). These properties were assessed for 21 days to analyze the preliminary stability of liposomes. Particle size distribution and liposome concentration were additionally determined by NTA (NanoSight NS300). For analysis, formulations were diluted 1:3,000 in Milli-Q® water.

Results and Conclusions

The liposomes exhibit suitable properties for pulmonary applications. DLS data showed a monodisperse population (PDI < 0.2), with an average hydrodynamic diameter of 130.6 ± 34.79 nm and a negative zeta potential (−3.84 ± 5.24 mV), indicating good colloidal stability. This stability was further confirmed by the maintenance of colloidal properties for 21 days. Complementary NTA analysis indicated an average particle size of 126.5 ± 52.0 nm and a particle concentration of $1.31 \times 10^{12} \pm 1.33 \times 10^{11}$ particles/mL, suggesting good dispersion and a high vesicle density enough to deliver a therapeutically relevant dose within a limited spray volume. The nanometric size (~130 nm) aids a deep lung penetration and interaction with alveolar macrophages, host cells of the pathogen. The near-neutral/slightly negative zeta potential reduces aggregation under physiological ionic conditions and may contribute to enhanced stability during aerosolization. DPPC provides biocompatibility by similarity to pulmonary surfactants, while cholesterol increases membrane rigidity and stability during nebulization (Back *et al*, 2024; Morrow *et al,* 2007). DSPE-PEG-amine may provide a site for surface functionalization with ligands such as mannose targeting the CD206 receptor, increasing macrophage uptake.

Keywords: Tuberculosis, Lipid-based nanoparticles, Pulmonary drug delivery, CD206 targeting

References

[1]Warner D.F., Barczak A.K., Gutierrez M.G. et al. Mycobacterium tuberculosis biology, pathogenicity and interaction with the host. *Nat Rev Microbiol* 2025; 23; 788–804. 10.1038/s41579-025-01201-x
[2]Mohammadnabi N., Shamseddin J., Emadi M., Bodaghi A.B., Varseh M., Shariati A., Rezaei M., Dastranj M., e Farahani A. Mycobacterium tuberculosis: o mecanismo de patogenicidade, respostas imunológicas e desafios diagnósticos. *J Clin Lab Anal* 2024; 38; e25122. Doi: 10.1002/jcla.25122
[3]Bangham A.D., Standish M.M., Watkins J.C. Diffusion of univalent ions across the lamellae of swollen phospholipids. *J Mol Biol* 1965; 13; 238–252. https://doi.org/10.1016/S0022-2836(65)80093-6
[4]Back P.I., Yu M., Modaresahmadi S., Hajimirzaei S., Zhang Q., Md Islam R., Schwendeman A.A., La-Beck N.M.. *ACS Nano* 2024; *18* (42); 28480-28501. Doi: 10.1021/acsnano.4c06369
[5]Morrow M.R., Temple S., Stewart J., Keough K.M. Comparison of DPPC and DPPG environments in pulmonary surfactant models. *Biophys J.* 2007; Jul 1, 93(1);164-75. doi: 10.1529/biophysj.106.102681.

D1 – P222

Bioengineering a mucoadhesive hydrogel-nanofibre composite for ocular chemotherapy: Preliminary validation in a novel CAM model of conjunctival melanoma

Desai N.[1], Krishna Y[1,2], Kalirai H.[1,2], Aughton K.[1], Barnett S. E.[3], Denisova K.[4], Duke E.[4], Colley H. E.[5], Bosworth L. A.[1], Kearns V. R.[1,*]

[1]Dept. of Eye and Vision Science, Institute of Life Course and Medical Sciences, University of Liverpool, Liverpool; [2]Liverpool Clinical Laboratories, Royal Liverpool University Hospital, University Hospitals of Liverpool Group, Liverpool; [3]Egg Facility, Liverpool Shared Research Facilities, University of Liverpool Faculty of Health and Life Sciences, Liverpool; [4]European Molecular Biology Laboratory, Hamburg Unit c/o DESY, Hamburg, Germany; [5]School of Clinical Dentistry, University of Sheffield, Sheffield, UK

Introduction

Conjunctival melanoma is a rare but aggressive ocular malignancy with a high recurrence rate and metastatic potential. Although topical mitomycin C (MMC) is widely used as adjuvant therapy, its clinical benefit is limited by poor ocular retention, epithelial toxicity, and poor patient compliance. Biomaterial systems that extend residence time and enable controlled release are therefore required to improve therapeutic precision and minimise off-target effects.

Aim

To engineer and translationally validate a mechanically reinforced, mucoadhesive poly(ε-lysine) (PeK) hydrogel–nanofibre composite for sustained local MMC delivery, and to assess anti-tumour efficacy in a vascularised chorioallantoic membrane (CAM) xenograft model.

Materials and Methods

A chemically crosslinked PeK hydrogel was reinforced with electrospun polycaprolactone nanofibre layers to produce composite discs with improved load-bearing capacity and mucoadhesion while preserving porosity. Microstructural integration was examined using Cryo-SEM. Compressive testing quantified stiffness, and mucin depletion assays evaluated adhesion. In vitro release studies compared MMC loading strategies and diffusion kinetics. Cytotoxicity was assessed in CRMM1 (BRAF V600E mutant), CRMM2 (BRAF wildtype, NRAS mutant), and CM2005.1 (recurrent, BRAF V600E mutant) cell lines with time-dependent IC_{50} analysis. A vascularised CAM xenograft model enabled in vivo evaluation. Synchrotron phase-contrast X-ray imaging provided three-dimensional assessment of tumour architecture and vascular networks, complemented by histological and immunohistochemical analyses (H&E, Melan-A, Ki67, α-SMA).

Results

Cryo-SEM demonstrated uniform nanofibre integration within the porous hydrogel matrix. Nanofibre reinforcement significantly increased compressive stiffness and mucin depletion compared with hydrogel alone, indicating improved mechanical robustness and ocular retention potential (Fig. 1). Release modelling supported sustained, diffusion-controlled MMC delivery. MMC exhibited time-dependent cytotoxicity, with IC_{50} reductions of 45–59% between 24 and 72 h across cell lines. CRMM1 and CM2005.1 formed vascularised CAM tumours with organised three-dimensional architecture and functional microvasculature, confirmed by synchrotron imaging. Vehicle-loaded composites showed 100% embryo survival without detectable CAM toxicity. MMC-loaded composites demonstrated enhanced anti-tumour effects compared with free MMC, including increased necrosis, reduced viable tumour volume, decreased proliferation, and reactive stromal/epithelial changes (Fig. 2).

Conclusion

A mechanically reinforced, mucoadhesive PeK hydrogel–nanofibre composite was successfully engineered to integrate structural strength, prolonged ocular retention, and tunable drug release within a single hierarchical platform. Validation in a vascularised CAM model demonstrated excellent biocompatibility and enhanced anti-tumour performance relative to free MMC. These findings position the PeK-based composite as a promising strategy for site-precise topical ocular chemotherapy and establish the CAM model as a robust translational platform for biomaterial-enabled therapeutic evaluation.

Acknowledgements
This work is supported by the MRC DiMeN DTP [MR/W006944/1], EPSRC [EP/X525741/1], and MRC [MR/X502765/1] Impact Acceleration Accounts. K. Denisova acknowledges funding from the EU IMAGINE project (GA #101094250). This work made use of shared equipment at the Materials Innovation Factory (MIF), created as part of the UK Research Partnership Investment Fund (UKRPIF) and co-founded by the Sir Henry Royce Institute. We gratefully acknowledge the Egg Facility (RRID: SCR_026195) and Histology SRF (RRID: SCR_026606) provided by Liverpool Shared Research Facilities (LIV-SRF), University of Liverpool.




Fig. 1. Functional and mechanical reinforcement of the hydrogel–nanofibre composite. (A) Schematic and SEM images showing the porous hydrogel matrix integrated with electrospun nanofibres. (B) Mucin depletion (%) after 3 h for hydrogel, nanofibre, and composite discs, used as a proxy for mucoadhesive interaction. (C) Compressive stress–strain curves demonstrating improved mechanical strength of the composite compared with hydrogel alone (5 N static load cell; strain rate 1 mm min^{-1}). Shaded regions represent SD (n = 3).




Fig. 2. CAM model imaging and histological evaluation of conjunctival melanoma. (A) Snapshot from high-resolution 3D reconstruction of a CAM-grown conjunctival melanoma using synchrotron phase-contrast X-ray imaging. (B) Volumetric reconstruction highlighting the segmented tumour vasculature within the CAM. (C–D) H&E sections of untreated control tumour and MMC-loaded composite–treated tumour; histological features were evaluated 48 h post-treatment. Higher-magnification views highlight invasive melanoma and viable tumour regions (Ci–Cii), and treatment-associated tumour necrosis with reactive CAM epithelial changes (Di–Dii).

D1 – P223

Angiogenic potential of estrogen loaded chitosan/PVA microneedles

Salamati S.[1], Conger-Onder E.[1,2], Ozturk S.[2], Akdemir A. A[2], Shirinli K.[4], Tatar S.B.[3], Zeybek N.D.[3], Mangir N.[4], Ulubayram K.[1,2]

[1]Dept. of Bioengineering; [2]Dept. of Basic Pharmaceutical Sciences; [3]Dept. of Histology and Embryology; [4]Dept. of Urology, Hacettepe University, Ankara, Turkey

Introduction

Estrogen derivatives (E1: Estrone, E2: β-estradiol, E3: Estriol) are involved in various biological processes in both female and male physiology, including wound healing and angiogenesis[1]. Although, in hormone-based therapies maintaining structural stability and minimizing off-target effects are challenging. Microneedles (MNs) are minimally invasive platforms for controlled drug delivery and stability. Estrogen-based studies have limited with E2 focusing and a comprehensive comparison between different estrogen derivatives need further investigations. Here, the angiogenic potential of E1, E2 and E3 was comparatively evaluated using a chitosan/polyvinyl alcohol (PVA) MN-based drug delivery platform.

Materials and Methods

Polydimethylsiloxane (PDMS), E1, E2, E3, chitosan, PVA and glutaraldehyde were used. First, safe dose ranges of estrogens were determined using vascular endothelial and fibroblast cells. Their angiogenic potential was evaluated via an aortic ring assay. MNs were fabricated from chitosan/PVA using PDMS molds and crosslinked with glutaraldehyde vapor at different durations (15, 30, 60 min). Estrogen loaded MNs were characterized in terms of physical properties, chemical structure, and biocompatibility. Mechanical performance was assessed through Parafilm® penetration and compression tests. Finally, the angiogenic potential of estrogen loaded MNs were evaluated using the Chorioallantoic Membrane (CAM) assay, followed by *in vivo* evaluation.

Results and Conclusion

The safe estrogen dose was determined as 10^5 nM, and the angiogenic responses evaluated with aortic ring assay. SEM images demonstrated well-defined and uniformly microneedle with sharp, with an average height 650 µm (Figure 1). Physicochemical analyses confirmed the success of fabrication method. In Parafilm® penetration test, MN formulations penetrated up to 4rd layer under 49 N force, corresponding to an approximate 500 µm penetration depth which is sufficient to reach viable skin layers. The CAM assay was conducted prior to *in vivo* studies to identify most promising formulations and to reduce animal use. Based on CAM assay and previous characterizations results, E2 loaded MNs were selected for further investigation. The angiogenic activity of E2 loaded MNs were significantly higher compared to blank MNs. As a result, E3 showed limited compatibility with designed MN platform, while E1 and E2 were successfully incorporated. E2 loaded MNs showed better angiogenic response in both CAM and *in vivo* experiments. These results indicate the importance of selection of estrogen derivatives in terms of material performance and therapeutic efficacy.

Figure 1. The SEM images of estrogen loaded MNs.

Acknowledgements

This study is supported by TÜBİTAK, grant number 220N323.

References

[1]Horng H.C., Chang W.H., Yeh C.C. Estrogen Effects on Wound Healing. *International Journal of Molecular Sciences* 2017; 18(11); 2325.

D1 – P224

Cerium–catalyzed synthesis of PLGA and PLGA–PEG copolymers for advanced nanoparticle engineering

Di Giambattista G.[1], Gupta D.[1], Casadidio C.[1], Gabrielli S.[2], Censi R.[1]
[1]School of Pharmacy, Drug Delivery Division, University of Camerino, ChIP Chemistry Interdisciplinary Project Research Centre, Camerino (MC); [2]School of Science and Technology, Organic Chemistry Division, University of Camerino, ChIP Chemistry Interdisciplinary Project Research Centre, Camerino (MC), Italy

Introduction

Poly(lactic–co–glycolic acid) (PLGA) is a cornerstone of biomedical nanotechnology. However, conventional synthesis relies on organotin catalysts like Tin(II) 2-ethylhexanoate ($SnOct_2$), which pose toxicity risks and regulatory challenges due to persistent residues. This study aims to develop a sustainable, bio-friendly alternative using cerium(III) laurate ($Ce(Lau)_3$) for the ring-opening polymerization (ROP) of lactide and glycolide.

Materials and Methods

$Ce(Lau)_3$ was synthesized and employed for PLGA and PLGA–PEG synthesis. Polymers were characterized via NMR, SEC, and thermal analysis (TGA/DSC). Nanoparticles (NPs) were formulated using a hydrodynamic flow-focusing (HF) microfluidic platform, varying the total flow rate (TFR) and flow rate ratio (FRR). The particle size, polydispersity index (PDI) and ζ-potential of the prepared PLGA and PLGA–PEG NPs were measured using dynamic light scattering (DLS). Cell viability experiments were carried out on the NCTC clone L-929 mouse fibroblasts cell line. MTT (3-(4,5-dimethylthiazolyl-2)-2, 5-diphenyltetrazolium bromide) assay was used to assess the cell viability of NCTC fibroblasts after the treatment with all formulations.

Results

$Ce(Lau)_3$ was identified as the most effective sustainable alternative to organotin catalysts producing PLGA with a molecular weight (M_w) of 17,600 Da, matching the physicochemical properties of conventional tin catalysts and commercial standards (Table 1). The method was equally effective for PLGA–PEG copolymers (PEGs M_w of 340, 550 and 2000 Da).

NPs formulated using HF microfluidics demonstrated that PLGA-$Ce(Lau)_3$ maintains excellent microfluidic responsiveness, yielding tunable sizes (171–250 nm) and narrow polydispersity (PDI 0.05–0.19). PEGylation further expanded formulation versatility; PLGA-PEG_{2000} produced smaller NPs (130–290 nm) than PLGA-PEG_{550} (>350 nm), indicating that total polymer M_w and chain entanglement govern NP size. PEGylation also successfully reduced surface charge (average –38 mV) through steric shielding.

Storage studies at 4°C revealed that PLGA-$Ce(Lau)_3$ and PEGylated NPs maintain superior long-term stability over 4 weeks, whereas commercial PLGA NPs underwent dramatic aggregation (>750 nm) within the first week (Figure 1). Finally, MTT assays on L-929 fibroblasts confirmed high cytocompatibility with viability exceeding 90% across all concentrations, validating the safety of cerium-based catalysis for biomedical grade polymers.


Conclusion

Polymers synthesized with $Ce(Lau)_3$ exhibit physicochemical and thermal properties comparable to commercial PLGA. These polymers show excellent compatibility with HF microfluidics, yielding NPs with tunable sizes, narrow distributions, and superior colloidal stability over 4 weeks compared to commercial alternatives. High cytocompatibility (>90% viability) validates cerium-based catalysis as a safe, robust, and scalable route for engineering advanced nanoparticle systems for biomedical and industrial use.

Table 1. Catalyst screening for PLGA synthesis.

Polymer	Catalyst	Mn (Da)[a]	MW (Da)[a]	PDI[a]	L/G[b]	DP[a]
PLGA–$CeCl_3$	$CeCl_3 \cdot 7H_2O$	3,400	4,500	1.3	43/57	53
PLGA–$Ce(OAc)_3$	$Ce(OAc)_3$	6,600	14,000	2.1	42/58	103
PLGA–$Ce(Lau)_3$	$Ce(C_{12}H_{23}O_2)_3$	10,900	17,600	1.6	45/55	169
PLGA–$InCl_3$	$InCl_3$	5,000	7,300	1.5	42/58	78
PLGA–DBTDL	DBTDL	12,200	20,160	1.7	47/53	190
PLGA–$CeCl_3$–NaI	$CeCl_3 \cdot 7H_2O$–NaI	3,100	8,100	2.6	45/55	48

Figure 1. Colloidal stability of PLGA-based NPs stored at 4°C over 4 weeks. (a) Hydrodynamic diameter (Z-average), (b) polydispersity index (PDI), and (c) ζ-potential of PLGA–$Ce(Lau)_3$ (TRF of 200 µL/min, FRR of 1:1), PLGA–commercial (TRF of 200 µL/min, FRR of 1:1), and PLGA–PEG_{2000} (TRF of 1000 µL/min, FRR of 1:1) NPs measured freshly after preparation and after 1 and 4 weeks of storage.



D1 – P225

Evaluation of cytotoxicity of the surfactant Pluronic F-127

Aoki K.[1], Kang C.S.[2], Okamoto M.[3], Kito M.[3], Takazawa A.[3], Idea H.[3], Taruta D.[3], Nemoto K.[3], Takahashi J.[3], Saito N.[1,4]

[1]Dept. of Physical Therapy, Shinshu University School of Health Sciences, Matsumoto; [2]National Institute of Technology (KOSEN), Nagano College, Nagano; [3]Dept. of Orthopaedic Surgery, Shinshu University School of Medicine, Matsumoto; [4]Nagano University of Health and Medicine, Nagano, Japan

Introduction

Chemotherapy for bone and soft tissue sarcomas is often associated with severe adverse effects, and satisfactory therapeutic outcomes are not achieved in a considerable number of cases[1]. To enhance the efficacy of chemotherapy while reducing its adverse effects, we have been developing a drug delivery system (DDS) using nanocarbon materials[2]. Nanocarbons are generally hydrophobic and therefore require surfactants to achieve uniform dispersion in liquid media. This study aimed to evaluate the cytotoxicity of the surfactant Pluronic F-127 (PF127) used in the development of a nanocarbon-based drug delivery system (DDS).

Materials and Methods

Chinese hamster alveolar fibroblast V79 cells and the human osteosarcoma cell line 143B were used. Cells were seeded in 96-well plates at a density of 1.0 × 10⁴ cells/well. After 24 h, Pluronic F-127 (PF127) was added to achieve final concentrations of 0.1, 1.0, 10, 100, and 1000 µg/mL. At 24 and 48 h after treatment, cell viability was evaluated using the alamarBlue assay and Hoechst staining.

Results

In the alamarBlue assay, cell viability of 143B cells significantly decreased to 65.8% at 24 h with 1000 µg/mL of Pluronic F-127 (PF127) ($p = 0.0328$). At 48 h, significant decreases in cell viability were observed at 100 µg/mL (67.2%, $p = 0.0336$) and 1000 µg/mL (65.3%, $p = 0.0228$). In contrast, no significant decrease in cell viability was observed in V79 cells at any concentration (Figure). Hoechst staining also confirmed a reduction in cell number in 143B cells at PF127 concentrations of 100 µg/mL or higher.

Conclusion

These findings suggest that PF127 at concentrations of ≤10 µg/mL, which are sufficient for nanocarbon dispersion, may have minimal cytotoxic effects.

Acknowledgements

This work was supported by JSPS KAKENHI Grant Number 24K12414.




Figure. Cell viability of cultured cells treated with different concentrations of PF127.The viability of 143B cells decreased with increasing PF127 concentration.

References

[1]Wang Y., Jin L., Zong C. Effects of cisplatin, paclitaxel combined with high-dose methotrexate as adjuvant therapy on survival rates in osteosarcoma patients, and analysis of influencing factors. *Am J Cancer Res* 2025; 15; 2618-2630.

[2]Aoki K., Ogihara N., Tanaka M. Carbon nanotube-based biomaterials for orthopaedic applications. *J Mater Chem B*; 8; 9227-9238.

D1 – P226

Bioadhesive and thermosensitive poloxamer-based hydrogel with tannic acid and hyaluronic acid for sustained bladder cancer treatment

Della Sala F.[1], di Gennaro M.[2], Longobardo G.[3], Nappi A.[2], Dentice M.[2], Crocetto F.[3], Russo P.[4], Borzacchiello A.[1]
[1]Institute of Polymers, Composites and Biomaterials, National Research Council, Naples; [2]Dept. of Clinical Medicine and Surgery, University of Naples Federico II, Naples; [3]Unit of Urology, Dept. of Neurosciences, Reproductive Sciences, and Odontostomatology, University of Naples "Federico II, Naples; [4]Institute of Polymers, Composites and Biomaterials, National Research Council, Pozzuoli, Italy

Introduction

Bladder cancer is the tenth most diagnosed cancer and represents a significant cause of morbidity and mortality worldwide.[1] Current therapies involve local chemotherapy or immunotherapy, whose efficacy is reduced by limited retention times of antitumor agents caused by the reticuloendothelial system and by the natural urination process. In this frame, injectable, mucoadhesive hydrogels appear as apt solution for the delivery of chemotherapy drugs. Pluronic F-127 and F-68 (PP) are FDA-approved co-polymers, known for their temperature depending sol-gel transition and widely used for local drug delivery.[2] PP-based materials can be mixed with bioadhesive molecules such as hyaluronic acid (HA) and tannic acid (TAand loaded with chemotherapy drugs, such as mitomycin C (MMC).

Aim

The aim of this work has been to develop thermosensitive hydrogels based on PP, HA and TA (HGT), with improved viscoelastic and bioadhesive properties able to release MMC, as strategy for efficient target therapy of bladder cancer.

Materials and Methods

The thermosensitive hydrogel HGT was prepared at composition of 15% PF-127 and 10% PF-68, 1% HA and 4% w/w of TA. The viscosity of the HGT in sol state, the sol gel transition and the viscoelastic properties in gel state were evaluated by rheological analysis. The mucoadhesive properties were investigated by rheological analysis of HGT/mucin mixtures at pH 1 and 5.5. The injectability was asessed measuring the extrusion force of HGT using an universal testing machine. The physical chemical analysis of the materials was performed by FT-IR and Raman spectroscopy. HGT was loaded with mytomicin C 20 µg/mL, and the release over time in PBS was quantified by GC-MS analysis. The *in vitro* anticancer activity of HGT was studied by the evaluation of viability (MTT) of 5637 cell line, used as bladder cancer model.

Results

The thermosensitive hydrogel HGT in the sol state at room temperature exhibited the viscoelastic properties of an entangled polymer solution, and a shear thinning behaviour, fit-for-purpose for injectable devices. The rheological results were confirmed by the low extrusion force measured. At physiological temperature, HGT exhibited viscoelastic properties of an hydrogel. The FT-IR and Raman analysis highlighted the establishment of non covalent interactions among the components. HGT mucoadhesivity resulted high both at ph 5.5 and at pH 1. HGT alone did not affect cancer cell viability, while Mitomycin-loaded HGT potently induced cell death (Fig. 1).




Fig. 1: Cell viability percentage of 5637 cells determined by MTT assay

Conclusion

HGT possessed injectable and bioadhesive capabilities, intrinsic antimicrobial activity and the ability to load and release chemiotherapy drugs, resulting promising for the treatment of bladder cancer.

Acknowledgements

The authors acknowledge the project PRIN PNRR 2022 P20225CXTH - “NEWSLETTER” - CUP B53D23026760001

References

[1]van Hoogstraten L.M., Vrieling A., van der Heijden A.G., Kogevinas M., Richters A., Kiemeney L.A. Global trends in the epidemiology of bladder cancer: challenges for public health and clinical practice. *Nature reviews Clinical oncology* 2023; 20(5); 287-304.

[2]Wu Y., Gu X., Chen X., Cui Y., Jiang W., Liu B. Hydrogel: a new material for intravesical drug delivery after bladder cancer surgery. *Journal of Materials Chemistry B* 2024; 12(12); 2938-2949.

D1 – P227
Changes to improving the user experience in DIW 3D printer

Giuliatti B.[1], Barbosa da Silva, K.[1], dos Reis Faria Neto, A.[4], Siqueira Guidi, E.[4], Dias Castilho, M.[3], de Oliveira Hein, L.R.[2], Rosifini Alves, A.P.[2]
[1]Faculty of Engineering and Sciences, Guaratinguetá, Brazil; [2]Dept. Materials and Technology, Faculty of Engineering and Sciences, Guaratinguetá, Brazil; [3]Dept. Biomedical Engineering, Institution Eindhoven University of Technology, Eindhoven, The Netherlands; [4]Dept. Mechanical, Institution Faculty of Engineering and Sciences, Guaratinguetá, Brazil

Introduction
The operating principles behind 2D and 3D printers are similar. Since both of them can use specific inks, in the 3D printer we can also use powder, gel, or filament whether made of metal, plastic, or even ceramic. Whereas ink is deposited in two directions on a planar surface, 3D printing fabricated objects, typically performed on a build plate layer by layer, forming three dimensional structures.

Aim
In this work we will discuss a series of modifications implemented in a low-cost, open-source DIW (Direct Ink Writing) printer in order to improve its performance, safety and the overall user experience.

Materials and Methods
The first change involved the material used for the part that holds the syringe, because it's always brake, we had to test three different materials to find the best solution. The material responsible for this problem was PLA (Polylactic Acid), that it came with the printer. The first tested material was ABS (Acrylonitrile Butadiene Styrene), followed by ASA (Acrylonitrile Styrene Acrylate), until we tested the TPU (Thermoplastic Polyurethane). TPU was ultimately select due to its greater flexibility and lower risk of breakage. Furthermore, fracture tests were conducted to assess and compare each material. The second modification was to place both the bed sheet and the magnetic base under the print bed to prevent damage to the bed and make it easier to remove the printed part. Finally, the creation of a case made of PETG (Polyethylene Terephthalate Glycol), which features a fan on the top (lid) for heat dissipation, a breadboard located inside the case that controls the printer, and an LCD display that will be used to control the printer, both in Touch Mode and Marlin Mode.

Results
The results are shown in Figures 1 and 2. In Figure 1 were shown 4 barrel holders, two of them are represents the best solution made with TPU and ASA (Left side).




Figure 1 – Barrel Holder

Figure 2 shows the box that brings more facilities and safety for the user.



Figure 2 – Box (PETG material)

Conclusion

To sum up, that modifications are so important to the printer and to the user. The barrel holder is necessary to make a good print, because it stabilizes the syringe. The bed sheet and magnetic base are necessary to help the user to withdraw the print and to protect the bed printer. The box will help to organize by accommodating and protecting the cables and electronic components the box increases operational safety by isolating the electronic circuitry and provides an easier control to the printer with the LCD.

Acknowledgements

The authors acknowledge the financial support provided by the São Paulo Research Foundation (FAPESP) through the Thematic Project BioFusion (Grant No. 2022/14790-2). This study was also supported by a FAPESP doctoral fellowship (Process 2024/07141-3).

References

[1]D. Weiss J.D., Mermin-Bunnell A., Solberg F.S., Tam T., Rosalia L., Sharir A., Rütsche D., Sinha S., Choi P.S., Shibata M., Palagani Y., Nilkant R., Paulvannan K., Ma M., Skylar-Scott M.A. A Low-Cost, Open-Source3DPrinterforMultimaterialand High-Through put Direct Ink Writing of Soft and Living Materials, *Adv. Mater* 2025; 37; 2414971.

D1 – P228

Engineering periodontal cell sheets from bench to application: Protocol development and assessment of osteogenic capacity

Tsamesidis I.[1], Theocharidou A.[1], Axypolitou S.[1], Bousnaki M.[1], Chatzistavrou X.[2], Kontonasaki E.[1]
[1]School of Dentistry, Aristotle University of Thessaloniki, Thessaloniki; [2]Dept. of Chemical Engineering, School of Engineering, Aristotle University of Thessaloniki, Thessaloniki, Greece

Introduction

Implant prosthodontic treatment enhance chewing capacity and function. The annual placement of dental implants exceeds 10-15 million procedures worldwide, restricting bone atrophy at edentulous sites[1]. Primary stability and osseointegration are crucial in implant survival rate. Despite enhancing Bone-to-Implant-Contact (BIC), dental implants cannot replicate the biomechanics of dental roots due to the absence of periodontal ligament (PDL) and dental cementum. Challenges arise from unbalanced mechanical stresses, and biological conditions that lead to tissue inflammation, and infectious diseases, such as periimplantitis. These complications can lead to bone resorption, compromising the success of prosthodontic treatment and increasing the risk of implant failure[2]. The scientific community aims to bioengineer dental implants that mimic dental roots, requiring a comprehensive understanding of periodontal cell behavior.

Materials and Methods

Human periodontal ligament cells (hPDLCs) were obtained from human biopsies of periodontal ligament tissues of healthy donors, after informed consent and ethics approval taken, during routine third molar extractions at the department of Dentistry, Aristotle University of Thessaloniki. hPDLCs were characterized by flow cytometry and by their capacity to differentiate towards multiple lineages using common assays (osteogenic, chondrogenic and adipogenic). Flow cytometry was performed using specific direct conjugated antibody to CD34, CD45, CD73, CD105, CD146 and STRO-1, in accordance with manufacturer guidelines. hPDLCs were cultivated in common medium for 12 days at temperature-responsive culture dishes (NUNC thermofisher) in order to collect cell sheets for 3D tissue models and characterize the periodontal ligament cell sheets. Real time PCR was performed to assess their osteogenic (BMP-2, RUNX-2, OCN, ALP) cementogenic (SPON1, CEMP1 and CAP) and angiogenic (PLAP-1, COL1A1) differentiation capacity. The study was approved by the Institutional Ethical Committee (#309351/2025).

Results

Human periodontal ligament cells (hPDLCs) were successfully isolated from periodontal ligament biopsies and expanded in vitro. Flow cytometry confirmed their mesenchymal phenotype, with positive expression of CD73, CD105, CD146, and STRO-1, and absence of hematopoietic markers CD34 and CD45. When cultured on temperature-responsive dishes, hPDLCs formed intact multilayered cell sheets that were harvested without enzymatic digestion, preserving extracellular matrix and cell–cell interactions. Real-time PCR analysis showed increased expression of osteogenic markers in PDLC sheets compared to monolayer cultures, with significantly higher levels of RUNX2 and ALP, indicating enhanced early osteogenic differentiation.

Conclusion

A rapid two-step protocol was developed for the isolation and fabrication of human periodontal ligament cell sheets. These PDLC sheets demonstrated enhanced early osteogenic potential, as indicated by increased RUNX2 and ALP expression. This simplified approach is proposed as a clinically applicable strategy in implant dentistry. Future studies will focus on applying the engineered cell sheets onto titanium implants with different surface coatings and investigating the synergistic use of platelet-rich plasma (PRP) to further enhance implant integration and regenerative outcomes in oral rehabilitation.

Acknowledgment

The research project is implemented in the framework of H.F.R.I call “4th Call for H.F.R.I.’s Research Projects to Support Postdoctoral Researchers” (H.F.R.I. Project Number: 28997), Title: Periodontal cell Sheets for Implant Long-term Establishment in oraL rehabilitation with acronym SMILE.

References

[1]Çolak S., Demïrsoy M.S. Retrospective analysis of dental implants immediately placed in extraction sockets with periapical pathology: immediate implant placement in infected areas. *BMC Oral Health* 2023; May 18, 23(1); 304. doi: 10.1186/s12903-023-02986-0.
[2]Mordini L., Sun N., Chang N., De Guzman J.P., Generali L., Consolo U. Peri-Implantitis Regenerative Therapy: A Review. *Biology (Basel)* 2021; Aug 13, 10(8); 773. doi: 10.3390/biology10080773. PMID: 34440005; PMCID: PMC8389675.

D1 – P229

Modified citrus pectin/resveratrol based nanoparticles for treatment of aortic dissection

Chi Lin[1], Hsin-Ying Lu[2], Chun-Che Shih[2] and Fwu-Long Mi*[1,2,3]
[1]Dept. of Biochemistry and Molecular Cell Biology, School of Medicine, College of Medicine, Taipei Medical University; [2]Taipei Heart Institute, Taipei Medical University; [3]Graduate Institute of Medical Sciences, College of Medicine, Taipei Medical University, Taipei, Taiwan

Introduction

Aortic dissection (AD) is a catastrophic vascular disease characterized by rapid progression, high mortality, and the absence of effective pharmacological treatments. Because AD involves complex interactions among multiple vascular cell types and dynamic inflammatory–degenerative processes, therapeutic strategies require precise spatial and cellular regulation.

Materials and Methods

We integrated modified citrus pectin, protamine, carboxymethyl-β-cyclodextrin and resveratrol to form Galectin-3 (Gal-3) targeting nanoparticles to achieve precise lesion targeting, on-demand NO release, and controlled delivery of resveratrol for modulating inflammatory and degenerative processes through multimodal therapeutic synergy. Nanoparticles were characterized by dynamic light scattering for hydrodynamic size and ζ-potential, transmission electron microscopy for morphology, and circular dichroism spectroscopy with BeStSel™ analysis to determine peptide secondary structure. Nanoparticles were evaluated for antioxidant activity, colloidal stability, encapsulation efficiency, and drug release. Cellular assays assessed viability, NO/ROS generation, and uptake in inflammatory vascular cells. In vivo efficacy, biodistribution, pharmacokinetics, and toxicity were examined in a mouse aortic dissection model.

Results

Gal-3 is identified as a disease-associated targeting ligand for cardiovascular nanotherapy, and a modular, pathology-adaptive nanoparticle system is developed to enable combined nitric oxide (NO) therapy and multi-pathway intervention. The designed nanoparticles enable stimulus-triggered NO release together with controlled co-delivery of resveratrol. *In vitro* studies demonstrate enhanced uptake of the nanoparticles by pathological vascular cell populations and significant suppression of inflammatory and degenerative phenotypes. *In vivo*, the nanoparticles exhibit efficient early lesion targeting, achieving approximately 20-fold enrichment in the aorta and markedly reducing the incidence of AD, vascular degeneration, and mortality.

Conclusion

We developed a Gal-3–targeted multiresponsive nanoparticle platform for precision therapy of aortic dissection. The system enables lesion-specific targeting, stimulus-triggered NO release, and controlled delivery of resveratrol for nanotherapeutic treatment of AD.

Acknowledgements

The authors gratefully acknowledge funding from the National Science and Technology Council of Taiwan, ROC (grant no. NSTC 114-2314-B-038 -159 -).

References

[1]Nienaber C.A., Eagle K.A. Aortic dissection: new frontiers in diagnosis and management: part II: therapeutic management and follow-up. *Circulation* 2003; 108; 772–8.

D1 – P230

Development of peptide-functionalized lipid nanoparticles for enhanced mucus penetration and endosomal escape

Wan-Lun T.[1], Chien-Ming H.[2], Jing-Ping L.[1], Pu-Sheng W.[1*]
[1]School of Pharmacy, College of Pharmacy, Taipei Medical University, Taipei, Taiwan; [2]Dept. of Pharmaceutics, School of Pharmacy, University College London, London, UK

Introduction

While lipid nanoparticles (LNPs) are effective for systemic nucleic acid delivery, intranasal siRNA administration remains limited by airway mucus and inefficient endo-lysosomal escape. This study addresses this critical gap by developing an integrated framework that links peptide-modified LNP surface engineering to siRNA delivery efficiency across multiple biological scales.

Materials and Methods

LNPs were prepared using SM-102, DSPC, cholesterol, and DMG-PEG2000 at a molar ratio of 50:10:38.5:1.5. The N/P ratio of SM-102 to siRNA was set to 6:1. The formulated siRNA-loaded LNPs were physically mixed with varying ratios of the PEG12-KL4 peptide[1] to form KL4-LNPs. The physicochemical properties of these nanoparticles, including size, polydispersity index (PDI), zeta potential, and RNA recovery, were characterized. Additionally, the penetration efficiency of KL4-LNPs through artificial bronchial mucus and their siRNA transfection efficacy in pulmonary epithelial cells were evaluated. Furthermore, hemolysis analysis and confocal imaging were employed to verify the impact of KL4-LNPs on the delivery mechanism.

Results

Dynamic light scattering showed control LNPs were approximately 100 nm. With KL4 incorporation, diameters increased amount-dependently, reaching up to 160 nm and 180 nm for 3KL4-LNPs and 5KL4-LNPs, respectively. Despite this, the PDI remained below 0.2, indicating a narrow size distribution. Additionally, zeta potential shifted from +3 mV (control) to +7 mV (5KL4-LNPs), confirming the successful surface integration of positively charged KL4 peptides.

The 3KL4-LNP formulation also demonstrated optimal biological efficacy. While naked siRNA exhibited poor airway mucus penetration (<10%), 3KL4-LNPs significantly enhanced penetration efficiency, particularly under acute asthma conditions. Furthermore, Western blot analysis of GAPDH expression confirmed superior GAPDH siRNA delivery. While the control LNP, 3KL4-LNP, and 5KL4-LNP formulations all exhibited excellent gene knockdown efficacy, the 3KL4-LNP formulation demonstrated the most optimal silencing trend.

Conclusion

Surface modification with the positively charged peptide PEG12-KL4 alters the surface properties of LNPs, facilitating their penetration through the bronchial mucus barrier and enhancing siRNA delivery efficiency. This establishes the formulation as a promising platform for pulmonary RNA drug delivery.

Acknowledgements

This research was funded by National Science and Technology Council, grant number NSTC 115-2222-E-038 -001 -MY2.

References

[1]Qiu Y., Man R.C.H., Liao Q., Kung K.L.K., Chow M.Y.T., Lam J.K.W. Effective mRNA pulmonary delivery by dry powder formulation of PEGylated synthetic KL4 peptide. *Journal of Controlled Release* 2019; Volume 314; 102-115.

D1 – P231

A multifunctional ZnO: Cu/FTO/Ag nano-heterostructure platform for high-performance surface-enhanced Raman scattering

Chiao Y.C.[1], Wu W.W.[1], Chang Y.C.[2]
[1]Dept. of Materials Science and Engineering, National Yang Ming Chiao Tung University, Hsinchu; [2]Dept. of Materials Science and Engineering, Feng Chia University, Taichung, Taiwan

Introduction

Surface-enhanced Raman scattering (SERS) has emerged as a powerful analytical tool for ultrasensitive molecular detection. However, the practical performance of semiconductor-based SERS substrates is often restricted by limited charge transfer efficiency, insufficient hotspot density, and poor structural reproducibility. Designing a multifunctional nano-heterostructure that combines semiconductor activity with plasmonic enhancement is therefore important for improving both sensitivity and reliability.

Aim

This study aimed to develop a ZnO: Cu/FTO/Ag nano-heterostructure SERS platform with enhanced interfacial charge transfer and electromagnetic coupling for highly sensitive and stable detection of probe and antibiotic molecules.

Materials and Methods

The ZnO: Cu/FTO/Ag nano-heterostructure was fabricated through sequential deposition of a Cu-doped ZnO layer, an ultrathin fluorine-doped tin oxide (FTO) interlayer, and Ag nanoparticles. The structural design was optimized by varying the precursor concentration and deposition conditions. Surface morphology and SERS performance were evaluated using rhodamine 6G (R6G) as a model analyte, while amoxicillin was selected to assess practical sensing capability. Signal enhancement, detection limit, stability, uniformity, and reusability were systematically examined.

Results

The optimized substrate prepared using a 20 mM ZnO: Cu precursor with 1 min FTO deposition and 1 min Ag deposition showed the best SERS performance. The inserted FTO interlayer effectively improved interfacial electronic interaction and promoted plasmon-assisted enhancement, leading to stronger Raman signals than control structures without the optimized interlayer. As illustrated in Figure 1, the ZnO: Cu/FTO/Ag platform exhibited an enhancement factor of 5.95×10^8, an ultralow detection limit of 1 fM for R6G, and a detection limit of 10 pM for amoxicillin. In addition, the substrate maintained good signal stability over 21 days and demonstrated acceptable uniformity and reusability.

Conclusion

The proposed ZnO: Cu/FTO/Ag nano-heterostructure provides an effective strategy for integrating semiconductor and plasmonic functions within a single SERS platform. The enhanced sensing performance originates from the synergistic effect of the Cu-doped ZnO layer, the ultrathin FTO interlayer, and Ag nanostructures. This platform shows strong potential for ultrasensitive chemical and biomedical detection.

Acknowledgements

Supported by the National Science and Technology Council, Taiwan (NSTC 112-2221-E-035-017-MY3 and NSTC 113-2221-E-035-023-MY3).




Figure 1. Graphical abstract.

D1 – P232

Integration of lattice doping and nanocrystal engineering for a synergistic nanoplatform of tumor treatment

Zhang Q.R.[1], Lin Z.K.[1], Chiang C.S.[2], Chen S.Y.[1]
[1]Dept. of Materials Science and Engineering, National Yang Ming Chiao Tung University, Hsinchu, Taiwan; [2]Cell Therapy Center, China Medical University Hospital, Taichung, Taiwan, Republic of China

Introduction

Clinical translation of CDT as cancer treatment is restricted by kinetic and selectivity bottlenecks, including insufficient H2O2 conversion efficiency and accessibility of catalytic sites within the complex microenvironment. Cerium dioxide (CeO2) nanozymes have demonstrated significant potential in addressing this challenge due to their unique microenvironment-responsive enzyme-like activities. In the acidic microenvironment of tumor tissue, CeO2 primarily catalyzes the conversion of hydrogen peroxide into highly toxic ROS to kill tumor cells. In contrast, in the neutral or alkaline environment of normal tissues, CeO2 effectively scavenges radiation-induced ROS and protecting normal cells from oxidative damage. This intelligent bidirectional regulatory function positions CeO2 nanozymes as a highly promising agent for microenvironment modulation, offering new avenues for achieving precise and personalized tumor therapy. To further improve CeO2 dispersibility and structural stability, inorganic or layered supports are often used as coatings or matrices. Mesoporous silica nanoparticles (MSNs) serve as the mass transport scaffold with Hf/Fe-codoped CeO2 nanocrystals grown on the outside shell. This integration of lattice doping and nanocrystal engineering forms a synergistic nanoplatform that effectively achieves multifunctional cooperative catalysis, enabling dynamic fine-tuning of oxygen supply (SOD-like) and cytotoxic enhancement (POD-like) pathways in the TME (Figure 1).

Aim

This study demonstrates a nanocatalytic biomedical Hf-Fe@CeO_2@MSNs platform that achieves CDT-RT synergy and offers a promising precision treatment strategy for clinical translation.




Figure 1. Schematic illustration of the synergistic mechanism between CDT and RT for Hf-Fe@CeO_2@MSNs.

Materials and Methods

Mesoporous silica nanoparticles (MSNs) were synthesized via a well-known template using tetraethyl orthosilicate (TEOS), cetyltrimethylammonium bromide (CTAB), n-octane. Next, MSN was subjected to hydrothermal treatment to precipitate CeO_2 nanocrystals to form CeO_2@MSNs. To modify the synergistic effect, Hafnium (IV) chloride ($HfCl_4$), ammonium iron (II) sulfate hexahydrate ($(NH_4)_2Fe(SO_4)_2 \cdot 6H_2O$), combined with cerium(III) nitrate hexahydrate ($Ce(NO_3)_3 \cdot 6H_2O$) were used to control the synthesis of the Hf-Fe@CeO_2@MSNs.

Results

The in vitro catalytic performance of Hf-Fe doped CeO2@MSNs nanocatalyst was assessed by analyzing both peroxidase-like (POD-like) and superoxide dismutase-like (SOD-like) activities. Figure 2a showed the TMB colorimetric catalytic assay was used to quantitatively evaluate the capability of the materials to catalyze H2O2 for ·OH radical generation. Simultaneously, the NBT photoreduction assay (Figure 2b) was employed to measure the efficacy of the materials in catalyzing the dismutation of superoxide anions, thereby assessing their kinetic characteristics for producing O2 and H2O2. The experimental results revealed that the Fe and Hf co-doping effectively increases the Ce3+ ratio and oxygen vacancy concentration in CeO2, thereby enhancing Fenton-like reactivity, indicating superior cytotoxicity and antitumor therapeutic efficacy compared to most catalyst systems.




Figure 2. Catalytic activities of $Hf_xFe_y@Ce_{1-x-y}O_2$@MSNs. (a) UV-vis spectra after the POD-like reaction. (b) Inhibition rate of NBT after the SOD-like reaction.

Conclusion

In conclusion, this research integrates dual advantages of CDT and radiosensitization: oxidative stress and oxygen from CDT enhance radiotherapy efficacy, while radiation promotes ROS generation and metal valence cycling, forming a positive feedback loop. This strategy overcomes conventional radiotherapy limitations within the hypoxic tumor microenvironment (TME), offering a clinically translatable approach for low-dose, high-efficacy combination cancer treatments.

Acknowledgements

This project is funded by the National Science and Technology Council (NSTC) (NSTC 114-2223-E-A49-005).

D1 – P233

Electrospun PLA/PCL-based multilayer biomaterials with antimicrobial functionality and controlled surface topography: Preliminary research

Cholewa K.[1,2], Kurtyka P.[2], Włodarczyk J.[3], Szuber-Dynia A.[1,2], Kapis A.[2], Orłowska A.[1], Gawlikowski M.[1,2]
[1]Faculty of Biomedical Engineering, Silesian University of Technology; [2]Institute of Heart Prostheses, Foundation of Cardiac Surgery Development; [3]Centre Of Polymer and Carbon Materials Polish Academy Of Sciences PAN, Zabrze, Poland

Introduction

Local bacterial colonization and biofilm formation remain critical challenges in the development of biomaterials intended for long-term tissue contact. This problem is particularly relevant for materials utilized at tissue-contacting or percutaneous sites, including components applied in mechanical circulatory support, where prolonged biological exposure, repeated local manipulation and surface susceptibility to microbial adhesion may increase the risk of local infection. Since the early stages of colonization are strongly influenced by material-related factors, including surface topography, porosity and chemical composition, antibacterial strategies should be considered already at the stage of material design. Electrospinning offers a suitable approach for this purpose, as it enables the fabrication of fibrous polymeric structures with adjustable morphology and high surface area. In multilayer systems, this technique allows the combination of different material functions within a single structure, which is particularly relevant for designing polymeric biomaterials with controlled surface characteristics and potential antibacterial functionality.

Aim

The objective of this preliminary study was to fabricate PLA/PCL-based multilayer fibrous biomaterials containing active substances with potential antibacterial activity and to perform their initial material and biological evaluation.

Materials and Methods

Multilayer fibrous structures were fabricated by electrospinning from poly(lactide) (PLA) and polycaprolactone (PCL)-based polymer blends. Active substances with potential antibacterial properties were incorporated into selected formulations. The obtained materials were subjected to preliminary microscopic characterization using complementary imaging methods, including scanning electron microscopy, to evaluate fiber morphology, continuity, surface topography and structural organization of the fibrous mats. Initial biological evaluation included cytotoxicity assessment and analysis of cellular metabolic activity in accordance with ISO 10993-5.

Results

The obtained materials formed multilayer fibrous mats suitable for further physicochemical and biological characterization. Microscopic observations enabled preliminary assessment of the morphology of the electrospun mats and the influence of polymer composition and functional modification on the fibrous structure. Biological evaluation, including cytotoxicity assessment and analysis of cellular metabolic activity, provided an initial indication of the biological response to the developed materials. The multilayer approach enables the integration of complementary material functions within a single fibrous structure while maintaining the characteristic morphology of electrospun biomaterials.

Conclusion

The preliminary results indicate that electrospun PLA/PCL-based multilayer biomaterials may serve as a promising solution for the development of sandwich-type functional materials with controlled surface topography and high potential for the incorporation and controlled release of active substances. Further studies will focus on the influence of morphology on material performance, release kinetics of incorporated compounds, cytocompatibility and antimicrobial activity.

Acknowledgements

This work was carried out and financed within the statutory research project no. 07/010/BKM26/1067, entitled “Tailoring the surface properties of polymeric biomaterials by electrospinning with active substances exhibiting antimicrobial activity”. Further development of the research topic is continued within the “Implementation Doctorate 2024” program, financed by the Ministry of Science and Higher Education (DWD/8/0117/2024), under the project

entitled “Development of innovative cannulas with increased biocompatibility for use particularly in mechanical circulatory support systems”.

D1 – P236

3D hydrogel biomaterial bio-anodes for biophotovoltaic energy harvesting

Bütün İ.[1,2], Muganlı Z.[1,2], Koşar A.[1,2,3,4,*]
[1]Faculty of Engineering and Natural Sciences, Sabancı University, İstanbul, Turkey; [2]Sabancı University Nanotechnology Research Centre (SUNUM), İstanbul, Turkey; [3]Centre of Excellence (EFSUN), Sabancı University, İstanbul, Turkey; [4]Turkish Academy of Sciences (TUBA), Ankara, Turkey

Introduction

Biophotovoltaic (BPV) cells convert solar energy into bioelectricity via photosynthetic microorganisms without carbon feedstock[1]. However, low power output and limited long-term stability hinder their practical deployment[2]. Here, we present a microfluidic-integrated BPV device incorporating a 3D cellulose nanofiber (CNF)/alginate hydrogel scaffold as a solid bio-anode. The scaffold provides a structurally stable and biocompatible microenvironment that immobilizes photosynthetic bacteria while maintaining their metabolic activity over extended operation periods. Integration with a microfluidic chamber enables precise control of nutrient delivery and gas exchange, further enhancing cell viability and electron transfer efficiency. The device architecture combines a gas-permeable PDMS membrane with an air cathode, facilitating oxygen management critical for sustained electrochemical performance. Open-circuit voltage measurements under alternating light/dark cycles demonstrate stable and reproducible biotic responses, highlighting the potential of this platform for scalable and long-lived BPV applications.

Aim

We aimed to fabricate a biocompatible, transparent 3D bio-anode supporting Synechocystis sp. PCC 6803 biofilm formation and efficient extracellular electron transfer, while enabling continuous microfluidic nutrient delivery for self-sustainable long-term electricity generation. We targeted a peak open-circuit voltage exceeding 150 mV, a short-circuit current density above 50 $\mu A.cm^{-2}$, and a maximum power density of at least 10 $\mu W.cm^{-2}$, a tenfold improvement over conventional planktonic BPV systems. The scaffold was designed to maintain greater than 80% bacterial viability over a minimum of 30 days of continuous light/dark cycling, with a microfluidic flow rate of 5–10$\mu L.min^{-1}$ to ensure stable nutrient delivery and sustained electrochemical performance.

Materials and Methods

CNF and alginate (4% wt each in BG-11 medium) were mixed with Synechocystis sp. PCC 6803 (OD750 = 1), cast into a cylindrical PDMS mold (r = 1 cm, h = 0.4 cm) and crosslinked with 1 M CaCl2 for 1 hour. An air cathode (PVDF/activated carbon/carbon black on stainless steel mesh) improved gas exchange. The device was fed continuously at 40 $\mu L.min^{-1}$ under alternating 12-hour light (16.7 $W.m^{-2}$)/dark cycles for 14 days. Characterisation included open circuit voltage (OCV) measurements, electrochemical impedance spectroscopy (EIS), hybrid pulse power characterisation (HPPC), SEM and confocal microscopy.

Results

Scaffold internal resistance was 174.4 Ω[2]. OCV measurements confirmed light-dependent electron transport: negative values under illumination and positive values in darkness, consistent with cyanobacterial linear electron transport via PSII/PSI[3]. Maximum power densities within the first five days reached 0.0534 $W.m^{-2}$ (dark) and 0.0391 $W.m^{-2}$ (light), corresponding to a light-to-electricity conversion efficiency of 0.32%. Over 14 days, power generation progressively shifted toward the light phase as the biofilm matured and chlorophyll activation intensified. HPPC testing recorded absolute peak densities approaching 0.08 $W.m^{-2}$. SEM and confocal microscopy confirmed that Synechocystis sp. PCC 6803 retained spherical morphology (~2 µm diameter) throughout, demonstrating scaffold biocompatibility and unimpaired electron transfer.

Conclusion

The 3D CNF/alginate bio-anode achieved power densities competitive with 2D BPV systems while sustaining photosynthetic cyanobacterial activity for two weeks. Beyond energy harvesting, the ionically conductive, optically transparent and biocompatible scaffold holds broad potential as a 3D culture matrix for electrogenic cells[4] (cardiomyocytes, neurons) requiring electrical monitoring, for organ-on-chip systems and for live-cell electrochemical biosensors. Future work should focus on serial/parallel scaling of bio-anode units, scaffold

thickness reduction, mesh electrode integration and genetically engineered cyanobacterial strains, ultimately targeting self-powered lab-on-a-chip and point-of-care applications.




Figure 1: a) Exploded schematic of the 3D bio-anode embedded BPV cell[2]. b) Long-term open-circuit voltage under alternating 12 h light / 12 h dark cycles: biotic (blue) vs. abiotic control (black)[2].

Acknowledgements

This research was funded by the Turkish Academy of Sciences (TUBA) under the Member Research Incentive Grant. The authors gratefully acknowledge the support of Sabanci University Faculty of Natural Sciences and Engineering and SUNUM Nanotechnology Research and Applications Center.

References

[1]Liu L., Choi S. Self-sustainable, high-power-density bio-solar cells for lab-on-a-chip applications. *Lab Chip*. 2017; 17(22); 3817-3825.
[2]Muganlı Z., Bütün İ, Gharib G., Koşar A. Electricity generation using a microbial 3D bio-anode embedded bio-photovoltaic cell in a microfluidic chamber. *Energy Adv*. 2024; 3(10); 2439-2452.
[3]Berla B.M., Saha R., Maranas C.D., Pakrasi H.B. Cyanobacterial Alkanes Modulate Photosynthetic Cyclic Electron Flow to Assist Growth under Cold Stress. *Scientific Reports*. 2015; 5(1); 14894.
[4]Zhang H.W., Hu X.B., Qin Y., et al. Conductive Polymer Coated Scaffold to Integrate 3D Cell Culture with Electrochemical Sensing. *Anal Chem*. 2019; 91(7); 4838-4844.

D2 – P001

Modulating drug delivery from porous titanium implants through hydrogel design and titanium surface functionalization

Mehdi-Sefiani H.[1], Mateo-Morales C.[1], Romero-Carballar C.[1], Granados-Carrera C.Mª.[2], Sepúlveda R.[1], Romero A.[2], Chicardi E.[1], Perez-Puyana V.M.[1]
[1]Dept. of Engineering and Materials Science and Transportation, University of Seville; [2]Dept. of Chemical Engineering, University of Seville, Seville, Spain

Introduction

Titanium implants are widely used for bone tissue replacement due to their excellent biocompatibility and mechanical properties that closely mimic those of natural bone. However, postoperative infections remain a major complication, often leading to poor clinical outcomes. Conventional systemic treatments frequently fail to deliver adequate drug concentrations at the infection site and may cause adverse effects. Therefore, local drug delivery systems based on antibiotic-loaded biomaterials have emerged as a promising strategy to provide sustained and localized antibacterial therapy. In this work, we propose an approach to modulate drug delivery from porous titanium implants by functionalizing the titanium surface and designing hydrogels.

Materials and Methods

Titanium foams with 60 vol.% of porosity were fabricated using the space-holder technique. To functionalize the titanium surface, an anodization treatment was applied. In parallel, enzymatic crosslinking using transglutaminase was explored to improve the thermal stability of gelatin type A-based hydrogels at physiological temperature. Tetracycline-loaded hydrogels were subsequently infiltrated into the open porosity of the titanium foams. Drug release studies were then conducted to evaluate the influence of both hydrogel design and titanium surface functionalization on release kinetics.

Results

Enzymatic crosslinking improved the thermal stability of gelatin type A-based hydrogels at physiological temperature, resulting in a more sustained release profile due to the formation of a more stable and resistant polymeric network. Meanwhile, surface functionalization of titanium foams influenced the interaction between the hydrogel and the titanium surface. In anodized samples, drug release was accelerated after 1 min of anodization, reaching 100% cumulative release after approximately 13 days, while a delayed release was observed after 5 min of treatment, resulting in a cumulative release of only 30% over the same period. These findings suggest that changes in the nanostructure of the oxide layer may enhance hydrogel adhesion within the pores, thereby contributing to a slower release process.

Conclusion

These results highlight the role of hydrogel design and titanium surface functionalization in modulating drug release from porous titanium implants. This approach represents a promising strategy for the development of advanced orthopedic implants capable of controlled and localized delivery of therapeutic agents. Such systems may benefit elderly patients or those with neurodegenerative disorders, for whom consistent medication adherence remains a challenge.

Acknowledgements

Authors acknowledge the financial support for Project PID2024-155967OB-I00 funded by MICIU/AEI/10.13039/501100011033 and by “ERDF A way of making Europe” and the University of Seville for the VPPI-US (PIF—VIIPPITUS 2022) grant of Hanaa Mehdi Sefiani.

D2 – P002

Functionalizing biologically inert textile implants with a drug-laden, bioactive coating

Schneider K., Melcher C., Menant T., Gries T.
Institut für Textiltechnik, RWTH Aachen University, Aachen, Germany

Introduction

Surgical sutures and other medical textile implants currently are predominantly made from synthetic polymers. These materials have excellent mechanical properties and processibility; however, they are biologically inert and thus do not positively influence the physiological milieu in which they are used. By coating these inert fibers with a bioactive agent, we can potentially create a versatile platform for advanced medical products—such as wound dressings, sutures, implants, and drug-delivery textiles — where tailored surface functionality could improve biocompatibility and enable antimicrobial performance and healing outcomes.

Aim

The objective was to design a lab-scale dip-coating prototype that minimizes the mechanical abrasion of the sensitive drug-laden coating.

Materials and Methods

The experimental setup was designed with a vertically aligned pre-wetting bath, an alginate coating bath, and $CaCl_2$ coagulation baths, thus minimizing changes in fiber direction and eliminating friction between the fiber and deflection rollers. To demonstrate the functionality of the dip-coating prototype we coated biologically inert, melt-spun PCL and PET fibers with alginate. Bovine serum albumin (BSA) was employed as a model protein to demonstrate the formation of a bioactive, drug-laden alginate coating.

We investigated the impact of fiber diameter (0.1 mm, 0.2 mm), fiber pre-treatment (0 h, 1 h 24 h in a 10%-NaOH bath), alginate concentration (1 wt%, 2 wt%, 4 wt%), and winding speed (1 m/min, 2 m/min, 4 m/min) on the thickness and homogeneity of the resulting alginate coating through scanning electron microscopy (SEM) and Fourier transform infrared spectroscopy (FTIR). Furthermore, we investigated the BSA release from the BSA-loaded alginate coatings via ultraviolet-visible spectroscopy.

Results

We successfully developed an experimental setup to functionalize biologically inert PET and PCL melt-spun fibers with a bioactive, drug-laden alginate coating. FTIR results of coated fibers compared to uncoated fibers show a broad peak at ~3330 cm^{-1} which corresponds to O-H stretching vibrations. This indicates successful coating of the PCL fiber with alginate by the dip-coating prototype. Initial release kinetics of fibers coated with BSA-laden alginate show effective release of BSA with promising release kinetics.

Conclusion

We developed a vertically aligned dip-coating prototype capable of functionalizing biologically inert materials with a BSA-laden, bioactive coating. Future adjustments to the coating material and the integration of pharmaceuticals could lead to higher biocompatibility of synthetically produced polymers and the targeted release of active substances at the target location.

D2 – P003

Synergistic antibacterial and cytocompatible effects of mn-doped mesoporous bioactive glass nanoparticles loaded with MEL-B

Matosinhos, R.D.[1,3], Calado, H.D.R.[2], De Andrade, C.J.[1], Boccaccini, A.R.[3*]
[1]Dept. of Chemical and Food Engineering, Federal University of Santa Catarina (UFSC), Florianópolis, Brazil; [2]Dept. of Chemistry, Federal University of Minas Gerais (UFMG), Minas Gerais, Brazil; [3]Institute of Biomaterials, Dept. of Materials Science and Engineering, University of Erlangen-Nürnberg (FAU Erlangen-Nürnberg), Erlangen, Germany

Introduction

Mesoporous bioactive glasses nanoparticles (MBGNs) synthesized via the sol-gel route enable the production of nanoscale materials with tunable compositions and the incorporation of therapeutic ions, allowing for controlled and sustained release profiles. Due to their intrinsic osteoconductive and osteoinductive properties, bioactive glasses have been extensively investigated for biomedical applications, particularly due to their ability to form strong interfacial bonds with biological tissues and to release bioactive species *in situ* [1]. Biosurfactants such as mannosylerythritol lipids (MELs) exhibit low toxicity, high biodegradability, and significant antimicrobial activities, and also bioactive potential [2]. Thus, MELs can be used for multifunctional biomedical platforms.

Aim

To develop MBGNS, surface-functionalized with 3-aminopropyltriethoxysilane and loaded with the MEL-B, and to evaluate the potential for biomedical applications. The study was structured as follows: (i) synthesis and physicochemical characterization of a binary Mn-doped MBGN system (70 mol% SiO_2-25 mol% CaO-5 mol% MnO) before and after MEL-B incorporation; (ii) assessment of cytocompatibility using MG-63 human osteoblast-like cells; and (iii) evaluation of antibacterial activity against *Escherichia coli* and *Staphylococcus aureus*.

Material and Methods

MBGNs were synthesized via a modified Stöber sol-gel process [3]. Morphological, elemental, and physicochemical characterization was performed using FE-SEM, ATR-FTIR, and XRD. Cytocompatibility was assessed in MG-63 cells (ISO 10993-5). Antibacterial activity against *S. aureus* and *E. coli* followed Unalan et al. [4].

Results

The analysis of SEM micrographs (Fig 1a) showed that all samples were well-dispersed, predominantly spherical nanoparticles with homogeneous nanometric size, typical of MBGNs synthesized via microemulsion-assisted sol-gel routes. Neither Mn^{2+} doping nor MEL-B loading altered particle morphology or dispersion. ATR-FTIR (Fig 1b) spectra confirm preservation of the silicate bioactive glass network, with characteristic Si-O-Si stretching (1057-1070 cm^{-1}), non-bridging oxygen-related bands (806-810 cm^{-1}), and Si-O-Si bending modes (445-462 cm^{-1}). XRD patterns display broad amorphous halos (2θ=20-34°), indicating the absence of crystallization after functionalization. Cytocompatibility assays revealed cell viability (Fig 2a) above 80% for all MBGNs, satisfying ISO 10993-5 criteria. Mn-containing systems exhibited concentration-dependent cellular responses, with Mn-doped MBGN@MEL-B showing enhanced viability at 0.01 µg mL^{-1}, suggesting synergistic effects. Antibacterial assays against *E. coli* demonstrated dose-dependent activity (Fig 2b), with Mn-doped MBGN@MEL-B showing strong antimicrobial performance.

Conclusion

It was proved that Mn-doped MBGN@MEL-B preserved the amorphous structure. Mn-doped MBGN@MEL-B presents excellent cytocompatibility and also enhanced antibacterial properties. The synergistic combination of Mn incorporation and MEL-B loading highlights their potential as multifunctional platforms for advanced biomedical applications.

Acknowledgements

The authors gratefully acknowledge the Department of Chemical and Food Engineering at the Federal University of Santa Catarina (UFSC) and the Institute of Biomaterials, Friedrich-Alexander University Erlangen-Nürnberg (FAU Erlangen-Nürnberg), for institutional and technical support. The authors also
acknowledge the financial support provided by FAPESC (Fundação de Amparo à Pesquisa e Inovação do Estado de Santa Catarina) Public Call Notice No. 24/2022.




Figure 1. (a) SEM image illustrating the spherical morphology and homogeneous nanoscale distribution of Mn-doped MBGN@MEL-B; (b) ATR-FTIR spectrum evidencing characteristic silicate network vibrations following Mn doping and MEL-B loading.




Figure 2. (a) Fluorescence microscopy images (DAPI/Calcein staining) of MG-63 cells exposed to MBGN and Mn-doped MBGN@MEL-B, illustrating cell adhesion and viability; (b) antibacterial activity of MBGN-based formulations against *E. coli*, showing concentration-dependent antimicrobial effects.

References

[1]Damian-Buda A.I., et al. *ACS Biomaterials Science & Engineering* 2024;10; 6860-6873.

[2]Matosinhos R.D., Cesca K., Carciofi B.A.M., Oliveira, D., de Andrade C.J. Mannosylerythritol Lipids as Green Pesticides and Plant Biostimulants. *Journal of the Science of Food and Agriculture* 2022; 103(1); 37-47.

[3]Nawaz Q., Rehman M.A.U., Burkovski A., Schmidt J., Beltrán A.M., Shahid A., Alber N.K., Peukert W., Boccaccini A.R. Synthesis and Characterization of Manganese Containing Mesoporous Bioactive Glass Nanoparticles for Biomedical Applications. *Journal of Materials Science: Materials in Medicine* 2018; 29; 6860-6873.

[4]Unalan I., Schruefer S., Schubert D.W., Boccaccini A.R. 3D-Printed Multifunctional Hydrogels with Phytotherapeutic Properties: Development of Essential Oil-Incorporated ALG-XAN Hydrogels for Wound Healing Applications. *ACS Biomaterials Science & Engineering* 2023; 9(7); 4149-4167.

D2 – P004

Dissolvable polymeric microneedles for localized delivery of citric acid in the treatment of calcinosis

Elashmouny H.[1], Ahmad Z.[1], Herrick A.[2], Elsawy M.[1]
[1]Division of Pharmacy and Optometry, University of Manchester; [2]Musculoskeletal & Dermatological Sciences, University of Manchester, Manchester, UK

Introduction

Calcinosis cutis involves deposition of insoluble calcium salts in skin and is associated with connective tissue disorders[1,2]. Treatments involve procedures or systemic therapies with variable efficacy. Local delivery of chelating agents dissolves calcium deposits minimizing systemic exposure. Dissolvable microneedles (DMNs) provide minimally invasive drug delivery into dermal layer. This study investigates polymeric DMNs for localized delivery of citric acid (CA), a calcium-chelating agent reported by us facilitating calcified deposits dissolution[3].

Materials and Methods

Formulations were prepared using solutions of polyvinyl alcohol (PVA; Mw 85-124 kDa) with sodium hyaluronate (HA; Mw 1.5-2.2 MDa). CA was incorporated by direct dissolution in polymer matrix or by tip-loading to concentrate the drug within microneedle tips. Preparation happened under heating and stirring then degassing. DMNs arrays were micromoulded using silicone microneedle moulds. Film casting was used to screen formulations for mechanical integrity and dissolution before fabrication. Drug release and permeation were evaluated using in-vitro diffusion studies across synthetic membranes.

Results

Blends of PVA and HA produced films suitable for microneedle fabrication. Micromoulding generated conical MN arrays with heights of 500-700 µm and base widths of 250-300 µm as determined by optical microscopy. CA was incorporated at concentrations of 2-5% (w/v), producing formulations with efficient drug loading. In-vitro studies demonstrated measurable CA release from the MNs, confirming drug dissolution under conditions relevant to transdermal delivery.

Conclusion

Findings demonstrate the feasibility of developing DMNs for localized delivery of CA in calcinosis treatment. Results provide initial framework for producing MNs delivering chelating agents to dermal calcium deposits. Future work will focus on mechanical characterization, drug loading optimization and evaluation of calcium dissolution efficiency in relevant in-vitro models.

Acknowledgements

The authors thank Myositis UK for funding this project through the Myositis Small Grant (016_SG_MyositisUK_ME) awarded to M.E. and A.H.

References

[1]Ariane H., et al. Frontiers in translational systemic sclerosis research: A focus on the unmet'cutaneous' clinical needs. *Experimental Dermatology* 2020; 1144-1153.
[2]Caitlan P., et al. Calcinosis in juvenile dermatomyositis: Updates on pathogenesis and treatment. *Frontiers in Medicine* 2023; 1155839.
[3]Kyle B., et al. Citric acid is more effective than sodium thiosulfate in chelating calcium in a dissolution model of calcinosis. *Scientific Reports* 2024; 30645.

D2 – P005

Superior immunological shielding of protein conjugates via poly(sarcosine) conjugate

Okuno Y.[1,2], Tsuda N.[3], Yasuda A.[3], Ando M[4]. and Iwasaki Y.[1,2]
[1]Kansai Univ., Chem. Mater. Bioeng.; [2]Kansai Univ., ORDIST; [3]Kansai Univ., Grad. Sch. of Sci. Eng.; [4]Kyoto Univ. Institute for Life and Medical Sciences, Kyoto, Japan

Introduction

Polymer conjugation is a widely used strategy to prolong the blood circulation time of therapeutic proteins while maintaining their bioavailability. Although poly(ethylene glycol) (PEG) remains the gold standard, the emergence of anti-PEG antibodies has become a significant clinical concern.[1] Polysarcosine (PSAR) has emerged as a promising alternative to PEG due to its nonionic and highly hydrophilic nature;[2] however, the effects of PSAR conjugation on protein properties remain poorly understood. Herein, we investigated the impact of PSAR conjugation on the structure and biological activity of proteins and compared the immune responses elicited by PSAR and PEG conjugates.

Materials and Methods

PSAR was synthesized via the ring-opening polymerization of sarcosine-*N*-carboxyanhydride. The carboxyl groups of PSAR and PEG were conjugated to the primary amines of model proteins—bovine serum albumin (BSA) and ovalbumin (OVA)—using an amide coupling agent. The conjugates were characterized by SDS-PAGE. Secondary structures and enzymatic activities were evaluated using circular dichroism and UV-Vis spectroscopy, respectively. Finally, the conjugates were injected subcutaneously into BALB/c mice, and the immune responses against both the proteins and the polymers were quantified via enzyme-linked immunosorbent assay (ELISA).

Results

We synthesized PSAR-modified BSA with 9, 18, and 22 chains per molecule. Although higher modification degrees increased the hydrodynamic size and slightly reduced secondary structure and enzymatic activity, at least 80% of the original activity was maintained. To evaluate immunogenicity, OVA was modified with 21 chains of PSAR (M_w: 9,000 or 5,000) or PEG (M_w: 5,000) and injected subcutaneously into mice. PSAR (M_w: 9,000) modification significantly reduced the production of anti-OVA antibodies. Additionally, PSAR showed a tendency to induce lower anti-polymer antibody levels than PEG.




Figure Time-course of anti-OVA antibody production after administration to mice determined by ELISA.

Conclusion

PSARylation effectively preserves protein structure and activity. Notably, high-molecular-weight PSAR suppresses immune responses against both the protein and polymer more efficiently than PEG. We acknowledge that this study alone cannot definitively conclude the overall superiority of PSAR to PEG This study highlights PSARylation as a powerful strategy for next-generation drug delivery systems.

Acknowledgements

This work was supported by JSPS KAKENHI, the Mukai Science and Technology Foundation, TOBE MAKI Foundation (25-JA-013), and Kansai University Research Branding Project (2024–2025).

References

[1]Gao Y., Joshi M., Zhao Z., Mitragotri S., Pegylated Therapeutics in the Clinic. *Bioengineering & Transla Med.* 2024; 9 (1); e10600.
[2]Hu M., Taguchi K., Matsumoto K., Kobatake E., Ito Y., Ueda, M. Polysarcosine-Coated Liposomes Attenuating Immune Response Induction and Prolonging Blood Circulation. *J. Colloid Inter. Sci.* 2023; 651; 273–283.

D2 – P006

Nanofibrous peptide hydrogels as biomimetic platforms for localised delivery of lipid nanoparticles in glioblastoma

Ali H., Tapeinos C., Elsawy M.
Dept. of Pharmacy and Optometry, University of Manchester, Manchester, UK

Introduction

Glioblastoma remains an aggressive brain tumour with limited responsiveness to conventional therapies. A major challenge is achieving localised, sustained delivery within dense brain tissue. Biomimetic nanofibrous peptide hydrogels offer a promising strategy by mimicking the extracellular matrix (ECM) while providing a framework for controlled delivery. Integrating lipid nanoparticles (LNPs) into these hydrogels presents a potential approach to enhance delivery efficiency and retention.

Aim

To develop and evaluate ultra-short \β-sheet forming peptide hydrogels as a biomaterial platform for localised delivery of lipid nanoparticles in glioblastoma.

Materials and Methods

A peptide-based hydrogel was engineered to self-assemble into a nanofibrous network via pH-mediated transition using 0.5 M NaOH titration. Characterisation was conducted using Transmission Electron Microscopy (TEM) to visualise morphology, oscillatory rheology to evaluate viscoelastic properties, and Fourier-transform infrared spectroscopy (FTIR) to verify secondary structure. LNPs were encapsulated, and their retention and release behaviour were systematically evaluated.

Results

The hydrogel formed a stable, ECM-mimetic nanofibrous architecture with mechanical properties (storage modulus G') tailored for soft brain tissue. FTIR confirmed the \beta-sheet structure, while TEM visualised the dense nanofibrous network. Investigation into release kinetics revealed that LNP retention is significantly modulated by the surface charge of the nanofibers. Comparing anionic, neutral, and cationic environments showed distinct release profiles, indicating that electrostatic interactions between LNPs and the scaffold play a critical role in controlling delivery. The system maintained high cytocompatibility and enhanced cellular internalisation.

Conclusion

This study successfully engineered a pH-responsive peptide hydrogel for glioblastoma therapy. By triggering molecular assembly through titration, we developed a scaffold matching the mechanical compliance of brain tissue. LNP release kinetics are significantly modulated by nanofiber surface charge, providing a programmable mechanism for delivery. This research aligns with the philosophy: 'The future depends on what you do today.' We are laying the groundwork for a future where complex brain tumours are no longer untreatable.

References

[1]Elsawy M.A., et al. *Biomacromolecules* 2022; 23; 2624-2634.
[2]Soliman M.A.N., et al. *Small* 2025; 21; 2408213.
[3]Khedr A., et al. *Small* 2026; 22; e13140.
[4]Tapeinos C., et al. *Advanced Healthcare Materials* 2024; 13; 2301500.

D2 – P007

Charge switching mechanism in multilayered silk films allows controlled and long-term release of multiple drugs

Valente F.[1], Bacal C.J.[1], Dorishetty P.[1], Allardyce B.[2], Ezehian F.[3], Razmjou A.[3], Atlas M.[1]
[1]Ear Science Institute Australia; [2]The University of Western Australia; [1]Deakin University, Geelong, Australia; [3]Edith Cowan University, Perth, Australia

Introduction

Chronic Suppurative Otitis Media (CSOM) is a biofilm-driven middle ear infection common in children in remote and developing regions 1, 2. The condition features a perforated eardrum that can cause hearing loss. Treatment involves myringoplasty and antibiotic drops, but drugs often fail to reach therapeutic levels in children, requiring repeated dosing and increasing resistance risk. Silk films loaded with ciprofloxacin and dexamethasone, tuned with sodium deoxycholate, directly applied to patch the perforation offer sustained drug release to reduce repeat surgeries.

Aim


Develop and innovative system for sustained drug delivery from silk films combining versatility in tissue repair and reconstruction with controlled release depending on environmental pH.

Materials and Methods

A sequentially assembled, acidic silk fibroin system was created using sodium deoxycholate as a charge-interfacing surfactant and the drugs ciprofloxacin and dexamethasone to form drug-eluting, multi-layered films. Two configurations were produced, both with dexamethasone-loaded silk (SD) as the outer layers. In the first, sodium deoxycholate films (SN) separated dexamethasone layers from an inner ciprofloxacin layer (SC) to form SD-SN-SC-SN-SD multi-layered film. In the second, a ciprofloxacin-deoxycholate complex formed the inner layer (SCN) to form SD-SCN-SD multi-layered film. Drug release was quantified spectrophotometrically 3, 4 and modelled, while morphology, chemistry, mechanics, and biocompatibility were evaluated for suitability as middle ear graft supports.

Results

The two multilayered silk film designs showed that layer number did not significantly affect ciprofloxacin or dexamethasone release at physiological pH, but did influence release when environmental pH changed – an important factor given pH variations at infected sites. Both drugs exhibited a consistent linear increase in cumulative release across pH conditions. Chemical and surface charge characterization revealed that the sodium deoxycholate governed charge tunability and had driven sustained release over 45 days in both film configurations. Biocompatibility tests confirmed that sodium deoxycholate did not reduce viable human keratinocyte numbers or proliferation, supporting its use as an effective charge-modulating component.



Conclusion

Conventional ear infection drug systems show limited scalability due to complex, low-yield synthesis. A multi-layered silk platform enables facile component blending for commercial production. Using sodium deoxycholate boosts antibiotic activity, has its own antibacterial effects 5, did not cause cell death, therefore expands options for combination therapies.

Acknowledgements

The authors acknowledge the philanthropic support of Channel 7 Telethon and The Ian Potter Foundation for funding the research and essential equipment, including the Jeol 7000 SEM and sputter coater.

References

[1]Morris P.S., Leach A.J., Silberberg P., Mellon G., Wilson C., Hamilton E., Beissbarth J. *BMC Pediatr*, 2005; 5: 27.
[2]DeAntonio R., Yarzabal J.-P., Cruz J. P., Schmidt J. E., Kleijnen J. *Int J Pediatr Otorhinolaryngol*, 2016, 85, 65-74.
[3]Eticha T., Kahsay G., Asefa F., Hailu T., Gebretsadik H., Gebretsadikan T., Thangabalan B. *J Anal Methods Chem*, 2018; 2018; 9538435.
[4]Xiao K.P., Xiong Y., Rustum A. M. *J Chromatogr Sci*, 2008; 46; 15-22.

D2 – P008

Exploring the potential of biopolymer matrices for dual chemo-thermal therapy in colorectal cancer

Maryam S.[1,2], Carmignani A.[3], Ciofani G.[3], Krukiewicz K.[1,4]
[1]Dept. of Physical Chemistry and Technology of Polymers, Silesian University of Technology, Gliwice, Poland; [2]Joint Doctoral School, Silesian University of Technology, Gliwice, Poland; [3]Smart Bio-Interfaces, Istituto Italiano di Tecnologia, Viale Rinaldo Piaggio 34, 56025 Pontedera, Italy; [4]Centre for Organic and Nanohybrid Electronics, Silesian University of Technology, Gliwice, Poland

Introduction

The development of advanced biomaterials for targeted drug delivery has become a key strategy for improving cancer therapy outcomes. In colorectal cancer, biopolymers are a versatile class of materials capable of enabling controlled drug loading, protecting therapeutic agents, and targeted release within the tumor microenvironment. Furthermore, superparamagnetic iron oxide nanoparticles (SPION)-containing systems offer the possibility of magnetic hyperthermia therapy. The integration of SPIONs within the biopolymer not only facilitates magnetic guidance of the carriers toward tumor sites but also provides the potential for externally triggered therapeutic effects, resulting in a synergistic chemo-thermal therapeutic effect.

Aim

In this study, naturally derived biopolymers were investigated as carriers for the controlled delivery of the anticancer agent 5-fluorouracil (5-FU), targeting colorectal cancer. Ongoing investigations aim to evaluate the hyperthermic performance of the SPION-embedded biopolymer matrix and assess its potential as a multifunctional platform for targeted colorectal cancer therapy.

Materials and Methods

A biopolymeric matrix composed of agar-alginate was employed to fabricate micro-sized particles capable of encapsulating chemotherapeutic drugs using ionic gelation and crosslinking techniques. The structural and chemical characteristics of the drug-loaded particles were analyzed using Fourier-transform infrared spectroscopy (FTIR), scanning electron microscopy (SEM), and energy-dispersive spectroscopy (EDS). Superparamagnetic iron oxide (II,III) nanoparticles (5 mg/mL in chloroform) with the average particle size of 5 nm (TEM) were incorporated into the biopolymeric matrix after functionalization with chitosan to modify their surface properties during the particle fabrication process. Human colorectal carcinoma (HCT-116) cells were subjected to a magnetic hyperthermia experiment using the MagneTherm system with an applied magnetic field strength of 10 mT and a coil consisting of 17 turns with a diameter of 56 mm. The cells were exposed to a magnetic field for two treatment cycles of 60 min each. Following hyperthermia exposure, cell viability was evaluated using a viability assay.

Results

SEM morphological transitions and EDS profiling confirmed the successful incorporation of 5-FU, as evidenced by the presence of nitrogen (5.85 ± 0.2 at.%) and fluorine (1.51 ± 0.5 at.%) signals characteristic of the drug molecule. Importantly, the preservation of the oxygen-rich composition indicates the maintenance of the biopolymer backbone structure. FTIR showed C-F stretching around 1100-1000 cm^{-1} and N-H stretching region 3300-3100 cm^{-1}, also suggesting successful incorporation of 5-FU into the matrix. The *in vitro* drug release pattern was gradual during the first 30 min (13 mM), followed by a steady increase to 16.9-17.6 mM at 120 min. The particles showed the swelling ratio of 670±10% in PBS (pH 7.4) at 37°C. The formulations demonstrated enhanced cytotoxic efficiency, leading to a dose- and time-dependent reduction in cell viability after 24 h of treatment (11.1 ± 0.5%).

Conclusion

These results highlight the potential of natural polymer-based systems as effective carriers for combination therapy in the treatment of colorectal cancer.

D2 – P009

Injectable photocrosslinkable hyaluronic acid hydrogel with PLGA/Amifostine and ion-releasing nanoparticles for radioprotection and tissue repair in HNSCC radiotherapy

Castellana D.[1,2], Castaño O. [3], Engel E.[1,2,4]
[1]Biomaterial for regerative therapies group, Institute for Bioengineering of Catalonia, Barcelona Institute of Technology (BIST), Barcelona; [2]Ciber en Bioingenieria, Biomateriales y Nanomedicina (CIBER-BBN), Madrid; [3]Electronics and Biomedical Engineering, University of Barcelona (UB), Barcelona; [4]IMEM-BRT group, Materials Science and Engineering, Polytechnical University of Catalonia (UPC), Barcelona, Spain

Introduction

Radiotherapy is the gold standard for Head and Neck Squamous Cell Carcinoma (HNSCC) but causes severe side effects such as mucositis in up to 90% of patients due to ROS and DNA damage. Amifostine, the only FDA-approved ROS scavenger, has poor local retention and systemic toxicity. To improve the cytoprotection of X-ray treated tissues, we introduce a dual-function injectable, photocrosslinkable hyaluronic acid hydrogel: PLGA nanoparticles for sustained local Amifostine release and inorganic Ca and Zn-releasing nanoparticles to accelerate post-radiation regeneration through angiogenesis and reepithelialization, forming an adhesive dressing.

Materials and methods

The drug was encapsulated in PLGA nanoparticles via a double emulsion method, while the inorganic nanoparticles were obtained using a wet methods developed in our laboratory. The hydrogel was formed by hyaluronic acid (HA) modified with methacrylic acid (MA) and enriched with 4-aminomethyl-phenylboronic acid (PBA) through a DMTMM-driven reaction. Radiotherapy was emulated using an X-ray irradiator at a dose of 5 Gy; the generated ROS was measured by the DCFDA-DH kit, while the biological state of cells was investigated by cytotoxic test and immunofluorescence assay.

Results

Polymeric nanoparticles, with a size of ~ 240 nm, were loaded with ~80% Amifostine. The release profile was sustained under a therapeutic concentration over 24 h. Ca and Zn-releasing particles were in the nanometer range, and the release of Ca and Zn ions enhanced fibroblast wound healing and angiogenesis H-NMR characterization of HAMA-PBA confirmed a high degree of MA substitution and PBA conjugation, while hydrogel mimicked oral mucosa mechanics (rheology). The HAMA-based hydrogel, crosslinked in-situ via blue light stimulation, enabled localized and prolonged release of Amifostine and therapeutic ions from the embedded nanoparticles around the implantation site. Upon X-ray irradiation, immunofluorescence tests revealed enhanced cellular activity and reduced ROS levels in cells treated with the Amifostine-loaded hydrogel, indicating mitigation of radiation-induced damage to healthy tissue.

Conclusion

This first dual PLGA/Ca and Zn releasing hydrogel improves Amifostine delivery, protects irradiated mucosa, and accelerates regeneration, advancing HNSCC radiotherapy support by protecting irradiated mucosa and enhancing its regeneration.

D2 – P010

Lipid nanoparticles as an inhalable drug delivery platform for budesonide and ensifentrine in COPD: Formulation design and physicochemical characterisation

Reczyńska-Kolman K., Kwiecień K., Domalik-Pyzik P., Kusibab A., Walczak K., Pamuła E.
Dept.of Biomaterials and Composites, Faculty of Materials Science and Ceramics, AGH University of Krakow, Krakow, Poland

Introduction

Chronic obstructive pulmonary disease (COPD) is a progressive, irreversible respiratory condition and a leading cause of global morbidity and mortality. Its pathophysiology is characterised by chronic airway inflammation, oxidative stress, mucus hypersecretion, and progressive destruction of the pulmonary epithelial barrier. Current pharmacological management relies primarily on inhaled bronchodilators and corticosteroids, yet disease-modifying efficacy remains limited by poor drug deposition, rapid mucociliary clearance, and inability to overcome the mucus barrier. Budesonide, an inhaled corticosteroid widely used to reduce airway inflammation in COPD, and ensifentrine, a first-in-class dual phosphodiesterase 3/4 inhibitor recently approved for maintenance treatment of COPD, represent two mechanistically distinct and clinically relevant therapeutic agents. However, both drugs face delivery challenges that constrain their full therapeutic potential when administered via conventional inhalation devices. Lipid nanoparticles (LNPs) offer a promising strategy to address these limitations, combining biocompatibility, tunable surface properties, and capacity for sustained and controlled pulmonary drug release[1].

Materials and Methods

This study describes the design and physicochemical characterisation of two separate LNP formulations loaded with budesonide and ensifentrine, respectively, intended for pulmonary delivery in COPD. LNPs were fabricated using an oil-in-water emulsification/solvent evaporation method, with systematic optimisation of formulation parameters, including lipid composition (lauric acid, acid stearic acid, cetyl palmitate) and concentration (1-5%), organic solvent (chloroform, dichloromethane), and surfactant type and concentration, alongside process parameters such as homogenisation speed and duration. Characterisation included DLS for size and zeta potential, AFM for morphology, and nanoIR spectroscopy for intrananoparticle drug distribution. Drug encapsulation efficiency and loading were quantified by HPLC. *In vitro* drug release was also assessed in MilliQ water and PBS.

Results

Preliminary optimisation indicates that formulation and process variables critically govern nanoparticle size, polydispersity, and encapsulation efficiency. Nanoparticles based on stearic acid and cetyl palmitate were of 50–100 nm with narrow size distribution, high encapsulation efficiency, and colloidal stability. NanoIR mapping will provided molecular-level insight into drug distribution within the lipid matrix, informing interpretation of release kinetics. Comparative profiling of the two formulations will highlight drug-specific physicochemical challenges and guide further optimisation.

Conclusions

This study establishes a rational formulation framework for LNP-based pulmonary delivery of budesonide and ensifentrine in COPD. By systematically linking formulation design to physicochemical outcomes, the work aims to generate transferable design principles for inhalable LNP therapeutics and provide the foundation for subsequent aerodynamic characterisation and biological evaluation in relevant COPD models.

Acknowledgements

This study was supported by the National Science Centre, Poland (project no. 2025/56/Q/ST5/00240).

References

[1]Reczyńska-Kolman K., Ochońska D., Brzychczy-Włoch M., Pamuła E. Engineered lipid nanoparticles loaded with LL-37 peptide as inhalable drug delivery carriers for the treatment of bacterial infections. *Biomaterials Advances* 2025; 176; 214363.

D2 – P011

A novel drug delivery platform based on electrospun fibres dedicated to endometriosis treatment

Urbanek O.[1]*, Luśtyk L.[1,2], Pietrzyk-Thel P.[1], Osial M.[1]

[1]Institute of Fundamental Technological Research, Polish Academy of Sciences, Warsaw, Poland; [2]Faculty of Materials Science and Engineering, Warsaw University of Technology, Warsaw

Introduction

Endometriosis is an inflammatory disease characterized by the presence of tissue resembling endometrium outside the uterus. The endometrial foci cause symptoms such as severe, life-impacting pain, dysmenorrhea, and dyspareunia. Infertility and difficulties in maintaining pregnancy may also be one of the consequences of this condition.[1] Despite the prevalence of this disease and its enormous impact on the health and lives of patients, no dedicated therapy has been developed to date. Medical help is usually focused on controlling the symptoms. In the most serious cases, surgical intervention is needed.[1] Currently, pharmacotherapy plays a crucial role in the treatment of endometriosis. Progestins and estroprogestines, used as contraception, are one of the most often used for endometriosis treatment. The only currently used route of administration of pharmaceuticals is oral, which affects the size of the drug dose and the scale of systemic side effects.[1] To date, few preclinical studies have attempted to develop local drug delivery methods for endometriosis therapy.[2]

Aim

The research aims to develop, optimize, and characterize a material system based on electrospun fibers that will serve as a carrier for selected active substances to limit the development of endometrial foci.

Materials and Methods

Poly(lacide-*co*-glicolide)(PLGA) with two different monomer ratios (50/50 and 75/25) was used separately to form fibres containing a selected amount of progesterone (P4). Fibres were formed via electrospinning and post-processed by cryocut to obtain short fibrous drug carriers, which were finally embedded in a hydrogel. The samples were imaged by scanning electron microscopy (SEM). The encapsulation efficiency % (EE%), drug loading (DL), and drug release of the progesterone encapsulated in fibers were analysed. Additionally, gel permeation chromatography (GPC), differential scanning calorimetry (DSC), and infrared spectroscopy (FTIR) were used. The *in vitro* studies were conducted to analyse system biocompatibility.

Results

SEM imaging confirmed effective fragmentation and separation of electrospun fibres. Fibrous drug carriers with a length of approximately 50 mm and a diameter of approximately 1.5 um were obtained and effectively integrated with the hydrogel. Also, its presence and distribution in the hydrogel were confirmed. DSC revealed differences in the glass transition temperature and melting temperature of PLGA depending on P4 content. GPC analysis revealed a decrease in PLGA average molecular weight and an increase in chain polydispersity during a one-month degradation test. Also, drug release profile differences were characterized between the two proposed materials.

Conclusion

An effective method for obtaining a new drug carrier dedicated to local drug delivery in the treatment of endometriosis was developed.

Acknowledgements

This work was supported by the National Science Center, funded by the SONATA program, grant no. 2022/47/D/ST5/01395.

Additionally, O.U. would like to acknowledge the financial support from the Polish Ministry of Science and Education through scholarships for outstanding young scientists (decision No. SMN/18/1755/2022).

References

[1]Parasar P., Ozcan P., Terry K.L. Endometriosis: Epidemiology, Diagnosis and Clinical Management. *Curr Obstet Gynecol Rep* 2017; 6; 34–41**.**

[2]Friend, D. R. Drug delivery for the treatment of endometriosis and uterine fibroids. *Drug Deliv. Transl. Res.* 2017; 7.6; 829-839.

[3]Moses, A. S., Demessie, A. A., Taratula, O., Korzun, T., Slayden, O. D., & Taratula, O. Nanomedicines for endometriosis: lessons learned from cancer research, *Small* 2021; 17.7; 2004975.

D2 – P012

Amazonian lipid-derived nanostructured lipid carriers for topical delivery of tacrolimus: Development and physicochemical characterization

Silva J.R.[1], Magalhães N.S.[2], Machado G.[1], Oliveira M.L.[1]
[1]CETENE, Recife; [2]Dept. de Ciências Farmacêuticas, Universidade Federal de Pernambuco, Recife, Brazil

Introduction

Atopic dermatitis (AD) is a chronic inflammatory skin disorder characterized by epidermal barrier dysfunction, with recurrent eczematous lesions[1]. Although topical application remain the main therapeutic options, their efficacy may be limited by poor skin penetration. In this context, lipid-based nanosystems have emerged as promising drug delivery platforms due to their ability to improve drug stability, skin retention, controlled release, and therapeutic efficacy. Moreover, the growing demand for sustainable pharmaceutical products has encouraged the exploration of natural and biodegradable materials, including Amazonian lipid resources.

Aim

To develop and characterize nanoparticulate delivery systems based on Amazonian lipids (murumuru butter and copaiba oil) for the encapsulation of tacrolimus (TAC), and to evaluate their potential application in the treatment of AD.

Materials and Methods

Nanostructured lipid carriers (NLCs) were prepared by a combination of hot emulsification and high pressure homogenisation. The lipid phase (solid + liquid lipids) was heated to 60 ± 5 °C above the solid lipid melting point and the aqueous phase containing surfactant was heated in a similar way. The aqueous phase was added to the molten lipids under high-speed Ultra-Turrax® stirring to form a coarse pre-emulsion, which was then processed in a Microfluidizer M110-P for several cycles. After cooling, the NLC matrix was formed by lipid recrystallisation and samples were kept in refrigeration until characterisation[2].

Results

The obtained results have demonstrated the successful development of tacrolimus-loaded NLCs, with copaiba oil/murumuru butter core, exhibiting HD of 100nm range, high physicochemical stability, and excellent batch-to-batch reproducibility, with a drug-loading capacity of 1 mg mL^{-1}. TEM analysis revealed predominantly spherical-shaped NLCs with no visible aggregation. Particle sizes (<150 nm) were consistent with DLS measurements. The images also confirmed the presence of the solid lipid matrix within the NLC core.

Conclusion

The favorable physicochemical properties obtained demonstrate the feasibility of using Amazonian lipid-based NLCs for tacrolimus carriers. These results provide a robust experimental basis for the development of advanced topical delivery platforms, including hydrogels and polymeric membranes, with the potential to enhance local drug delivery, improve therapeutic performance, and support new treatment strategies for AD and other inflammatory skin diseases.

Acknowledgements

This work was supported by the MCTI/CNPq through a PCI fellowship.

References

[1]Weidinger S., Beck L.A., Bieber T., Kabashima K., Irvine A.D. Atopic dermatitis. *Nat Rev Dis Primers* 2018; Jun 21; 4(1):1.
[2]Gomaa E., Fathi H.A., Eissa N.G., Elsabahy M. Methods for preparation of nanostructured lipid carriers. *Methods* 2022; 199; 3.

D2 – P013

Development And Design Of Zein Nanoparticles For Colon-Specific Release of propionate

Ribeiro Mantovanelli V., Gonçalves Carvalho S., Chorilli M.
Dept. of Drugs and Medicines, School of Pharmaceutical Sciences, São Paulo State University (UNESP), Araraquara, Brazil

Introduction

It is known that oral drug delivery is considered one of the most convenient forms of administration for most patients. However, the complexity of the gastrointestinal tract (GIT) presents a problem for the oral administration of drugs to the colon. In this sense, colon-specific delivery systems can be studied as alternatives. For this, protein nanoparticles are a good strategy, with zein being a potential material, which has mucoadhesive characteristics and is able to resist degradation caused by gastric acid, but has low colloidal stability (De Marco, 2022). The association with polysaccharides (PS) is a strategy, since this increases the stability of the system. Among the available PS, chitosan (QS) and sodium alginate (AS) stand out, being a cationic and anionic, respectively (Cai et al., 2022; Zhu et al., 2023). Postbiotics are defined as soluble products or byproducts released by live intestinal bacteria, whether probiotic or not, after cell lysis. Among postbiotics, propionate has stood out for its beneficial effects on intestinal health (Osto, 2021). Therefore, this work aims to develop an oral nanocarrier based on zein and polysaccharide for colon-specific delivery of propionate.

Materials and Methods

Zein nanoparticles containing propionate were produced by nanoprecipitation, and the physicochemical parameters of the system were evaluated in the presence of different polysaccharides at three concentrations: 0.2, 0.5, and 1.0 mg/mL. The average hydrodynamic diameter, the polydispersity index (PdI), and the zeta potential were evaluated using DLS. The encapsulation efficiency (EE%) of propionate was also evaluated. The physical stability of the system was assessed against pH, ionic strength, and also over 120°C.

Results and Conclusions

Nanoparticles prepared with AS varied their DHM between 184.1 and 235.2 nm, and those containing QS varied between 128.5 and 177.1 nm. The PdI of nanoparticles containing AS ranged from 0.143 to 0.146, and those containing QS from 0.231 to 0.339. The PZ of particles containing QS ranged from 47.1 to 52.2 mV, while those containing AS ranged from -38.0 to -46.1 mV. The formulations containing QS showed EE% of propionate between 23 and 46%. Those containing AS showed EE% of propionate between 7 and 46%. In the pH stability test, nanoparticles containing QS remained stable, except at pH 8.0. Those with AS showed stability under all tested conditions. Regarding ionic strength, formulations containing QS in their composition were more stable at all NaCl concentrations. Throughout the 120 days of analysis, all particles remained stable. The results obtained point to the potential of alginate-stabilized zein nanoparticles for oral delivery in the colon of propionate.

Acknowledgements

CAPES (Convênio PROEX 1601/2024), CNPq (Proc. 303344/2026-1) and FAPESP (Proc. 2025/12801-5)
Keywords: postbiotics; zein; oral delivery; colon-specific delivery.

References

[1]De Marco I. Zein microparticles and nanoparticles as drug delivery systems. *Polymers* 2022, v.14, n. 11; p. 2172. doi.org/10.3390/polym14112172
[2]Cai Z., et al. Effect of molecular weight of chitosan on the formation and properties of zein-nisin-chitosan nanocomplexes. *Carbohydrate Polymers* 2022; v. 292; p. 119664. doi.org/10.1016/j.carbpol.2022.119664
[3]Osto E. The promise of the gut metabolite propionate for a novel and personalized lipid-lowering treatment. *European Heart Journal* 2021; v. 43, n. 6; p. 534–537. doi.org/10.1093/eurheartj/ehab723

D2 - P014

Development of alginate-based biomaterial microparticles for the protection and controlled release of a photosensitive antioxidant Amazonian fungal endophytic extract

Felix da Costa M.R.[1], Sousa Fonseca M.E.[1], Fardim P.E.[2], Agostini de Moraes M.[1]
[1]Dept. of Materials and Bioprocess Engineering, School of Chemical Engineering, University of Campinas (UNICAMP), Campinas, São Paulo, Brazil; [2]Dept. of Chemical Engineering, Faculty of Engineering Science, KU Leuven, Leuven, Belgium

Introduction

The Amazon rainforest is a vast reservoir of biodiversity, where fungal endophytes produce unique bioactive secondary metabolites with high pharmaceutical potential. Extracts rich in phenolic compounds from Amazonian endophytes offer remarkable antioxidant properties. However, their biomedical application is limited by high sensitivity to light and temperature, leading to rapid degradation. Encapsulating these sensitive molecules into biocompatible hydrogel-based biomaterials is essential to preserve their therapeutic bioactivity.

Aim

The aim of this work is to develop alginate microparticles via a water-in-oil (W/O) emulsion system to effectively encapsulate a thermosensitive and photosensitive antioxidant extract from an Amazonian fungal endophyte, ensuring bioactive protection and establishing a controlled release profile.

Materials and Methods

Alginate matrices (1% and 2% w/v) containing the Amazonian endophytic extract will be emulsified in a vegetable oil continuous phase with Span 80 (2% v/v) using a mechanical stirrer (2000 RPM, 15 min). Tween 80 (1% v/v) will be incorporated into the aqueous phase to prevent active phase partitioning. Ionic gelation will be achieved by adding calcium chloride (1% and 2% w/v). Microparticles (~20 µm) will be isolated by vacuum filtration. Encapsulation efficiency, antioxidant activity preservation, and the controlled release profile of total phenolics will be quantified via UV-Vis spectrophotometry using a matrix-matched calibration curve.

Results

The system is expected to successfully produce spherical microparticles with an average size of 20 µm. The addition of Tween 80 is anticipated to significantly enhance encapsulation efficiency, preventing extract migration to the oil phase. The alginate biomaterial matrix is expected to provide a robust physical barrier, effectively protecting the Amazonian fungal phenolics against thermal and light-induced degradation while delivering a sustained, diffusion-controlled release profile of the antioxidant payload.

Conclusion

The developed alginate biomaterial represents a promising and sustainable platform for the valorization and encapsulation of sensitive natural compounds from Amazonian biodiversity. By overcoming degradation and partitioning challenges, these microparticles show great potential for future applications in targeted drug delivery and active biomaterial coatings.

Acknowledgements

This study was supported by the National Council for Scientific and Technological Development (CNPq) through a Sandwich Doctoral Scholarship, process number 201478/2025-0.

D2 – P015

DNA origami nanostructures as a modular platform for growth factor delivery

Jung Y.[1,2]*, Ryu J.H.[3,4]*
[1]Biomaterials Research Center, Korea Institute and Science Technology (KIST); [2]School of Electrical and Electronic Engineering, YU-KIST Institute, Yonsei University; [3]Medicinal Materials Research Center, (KIST); [4]KU-KIST Graduate School of Converging Science and Technology, Korea University, Seoul, Republic of Korea

Introduction

Severe peripheral nerve injuries often lead to substantial functional deficits because of the limited regenerative capacity of nerve tissue. Although neurotrophic factors such as brain-derived neurotrophic factor (BDNF) can promote neuronal differentiation and nerve regeneration, their therapeutic application is limited by poor stability and the lack of precise delivery systems. To address these challenges, we developed square block DNA nanostructures (SQBs) as a programmable and modular platform for the spatially controlled presentation of growth factor-mimicking peptides and evaluated their potential for peripheral nerve repair.

Materials and Methods

Square block DNA nanostructures were assembled using DNA origami and functionalized with BDNF-mimicking peptides at defined nanoscale spacings. The ability of peptide-functionalized SQBs to induce neuronal differentiation was evaluated in human mesenchymal stem cells (hMSCs) using microscopy, Western blot analysis, and ELISA. To demonstrate the modularity of the platform, dual-ligand SQBs displaying FITC and Cy5.5 were prepared, and intracellular colocalization was assessed by confocal microscopy. Therapeutic efficacy was further evaluated in a mouse sciatic nerve crush injury model through functional, morphological, and histological analyses.

Results and Conclusion

Peptide-functionalized SQBs enabled the precise spatial presentation of BDNF-mimicking peptides at defined nanoscale intervals. SQBs displaying 38 BDNF-mimicking peptides at 5 nm spacing significantly enhanced neuronal differentiation of hMSCs, as confirmed by microscopy, Western blot analysis, and ELISA. Furthermore, dual-ligand SQBs displaying FITC and Cy5.5 demonstrated controllable ligand incorporation and efficient intracellular colocalization, enabling the simultaneous delivery of multiple ligands to individual cells.
In a sciatic nerve crush injury model, BDNF-functionalized SQBs enhanced nerve regeneration and promoted functional recovery. Collectively, these results demonstrate the potential of SQBs as programmable and modular platforms for the spatially controlled delivery of therapeutic ligands for peripheral nerve repair.

Acknowledgements

This work was supported by the National Research Foundation of Korea grant funded by the Korea government (MSIT; No. RS-2024-00463774) and the Intramural Research Program of KIST (No. 26Z9081).

D2 – P016

Iron-modulated α-synuclein aggregation and its inhibition by polyphenols and nanoparticle-based formulation

Roy B., Deep S.
Dept. of Chemistry, Indian Institute of Technology Delhi, New Delhi, India

Introduction

Parkinson's disease (PD) is a progressive neurodegenerative disorder characterized by the misfolding and aggregation of α-synuclein into toxic oligomeric and fibrillar species. Among the various factors implicated in disease progression, metal ion dyshomeostasis, elevated Fe^{3+} levels, has been shown to promote oxidative stress and stabilize aggregation-prone conformations of α-synuclein. Natural polyphenols have emerged as promising therapeutic candidates owing to their anti-amyloidogenic and antioxidant properties.

Aim

The present study aimed to investigate the influence of Fe^{3+} ions on α-synuclein aggregation and to evaluate the inhibitory potential of polyphenols and its nanoparticle-based formulation using complementary experimental and computational approaches.

Materials and Methods

Recombinant α-synuclein was incubated in the absence and presence of Fe^{3+} and polyphenols under aggregation-promoting conditions. Aggregation kinetics and structural transitions were monitored using fluorescence spectroscopy, turbidity measurements, SDS-PAGE, size-exclusion chromatography (SEC), Fourier-transform infrared spectroscopy (FTIR), transmission electron microscopy (TEM), scanning electron microscopy (SEM), and atomic force microscopy (AFM). The cytotoxicity of the resulting protein aggregates was assessed using MTT assays. Furthermore, molecular dynamics simulations were performed on α-synuclein monomeric and fibrillar systems to elucidate the molecular interactions between polyphenols and α-synuclein.

Results

Fe^{3+} significantly accelerated α-synuclein aggregation, promoting rapid conversion into β-sheet-rich fibrillar structures and enhancing aggregate-induced cytotoxicity. Morphological analyses confirmed the formation of dense fibrillar networks in iron-treated samples. In contrast, polyphenols effectively inhibited fibril formation, reduced β-sheet content, and stabilized less toxic oligomeric intermediates. SEC and spectroscopic analyses demonstrated a shift toward lower-order aggregate populations in the presence of polyphenols. Molecular dynamics simulations revealed persistent interactions between polyphenols and key aggregation-prone regions of α-synuclein, which disrupted intermolecular association and fibril growth. The nanoparticle-based formulation further improved the delivery potential of polyphenols, highlighting its suitability for therapeutic applications targeting protein aggregation.

Conclusion

This study provides a comprehensive multi-scale understanding of Fe^{3+}-induced α-synuclein aggregation and its suppression by polyphenols. The combined experimental and computational findings demonstrate that polyphenols effectively modulate aggregation pathways and mitigates aggregate-associated toxicity. These results support the development of polyphenol-based nanotherapeutic strategies for targeting protein misfolding and aggregation in Parkinson's disease and related neurodegenerative disorders.

D2 – P017

Injectable amyloid-alginate composite hydrogels enable sustained insulin release and glycemic regulation

Shaw R.[1], Chimthanawala N.M.A.[3], Manna S.[1], Sathaye S.[3], Maji S.K.[1,2,*]
[1]Dept. of Biosciences and Bioengineering, IIT Bombay, Powai; [2]Sunita Sanghi Center of Aging and Neurodegenerative Diseases (SCAN), IIT Bombay, Powai; [3]Dept. of Pharmaceutical Sciences and Technology, Institute of Chemical Technology, Mumbai, India

Introduction

Type 1 diabetes mellitus requires lifelong administration of exogenous recombinant insulin to compensate for the loss of endogenous insulin production. However, the rapid clearance and short biological half-life of insulin necessitate frequent subcutaneous injections, often leading to poor patient compliance and an increased risk of hypoglycemia. To address these limitations, we developed a peptide-based functional amyloid and composite hydrogel designed for sustained insulin delivery and prolonged glycemic control.

Methods

A functional amyloid hydrogel was fabricated from self-assembling peptides and combined with sodium alginate to form a composite injectable hydrogel with enhanced sustained-release properties. The hydrogel was characterized for its structural and rheological properties, including injectability and thixotropic behavior. Recombinant insulin was encapsulated within the hydrogel, and its loading efficiency and *in vitro* release kinetics were evaluated. The therapeutic efficacy and biosafety of the insulin-loaded functional amyloid hydrogel were assessed following subcutaneous administration in a streptozotocin-induced Type 1 diabetic rat model.

Results

The functional amyloid hydrogel demonstrated sustained insulin release for 72 hours in an *in vitro* setting. It achieved an insulin encapsulation efficiency exceeding 90% at insulin concentrations up to 5 mg/mL. Further, the composite hydrogel exhibited excellent biocompatibility, injectability, and shear-thinning behavior, making it suitable for minimally invasive administration. Incorporation of sodium alginate further improved the release profile, with *in vitro* release kinetics demonstrating sustained insulin release for up to 90 hours. Following a single subcutaneous injection of the insulin-encapsulated functional amyloid hydrogel, the formulation reduced blood glucose levels to normoglycemic values within 30 minutes and maintained effective glycemic control for approximately 60 hours in diabetic rats (Fig.2). Histological and biochemical analyses indicated no significant toxicity.

Conclusion

The developed peptide amyloid hydrogel provides a safe, injectable, and biodegradable platform for sustained insulin delivery (Fig.1). Its high insulin-loading capacity, prolonged-release profile, and extended glucose-lowering efficacy following a single administration highlight its potential as an advanced biomaterial to improve diabetes management and reduce the burden of frequent insulin injections. Even the sodium alginate composite hydrogel possesses immense potential to serve as a drug depot for treating diabetes.




Figure 1: Schematic illustration of the fabrication and application of peptide-inspired functional amyloid hydrogel for treating hyperglycemia in diabetes.




Figure 2: *In vivo* hypoglycemic effect of the amyloid hydrogel and insulin formulation. A) Schematic representation of the induction of diabetes in a male Wistar rat and the subsequent assessment of glycemic control post-subcutaneous administration of hydrogel-insulin composite. B) The blood glucose level at various time points after subcutaneous administration of FA1 in the diabetic rat model. C) AUC analysis of the four treatment groups of rats. D) Level of serum insulin in rats of different groups at various time points. E) Schematic illustration of the IPGTT test, demonstrating different treatment groups in rat groups and monitoring their blood glucose level at pre-defined time points. F) Blood glucose level of rats in the IPGTT test in different groups. G) AUC of the three groups indicating the significance of our formulation. H) Blood glucose levels of the rats after administration of our formulation subcutaneously for 15 days. For C and G, the data represent the mean ± S.D. (n=6), and the statistical significance was determined using a one-way ANOVA, followed by a Dunnett's post hoc analysis [****$p < 0.0001$, ***$p < 0.0002$, **$p < 0.0021$ and $^{ns}p > 0.1234$ with a 95% confidence interval].

Acknowledgements
We acknowledge Wadhwani Research Center for Bioengineering (WRCB), ANRF-ARG (ANRF/ARG/2025/002507/LS), DST-SUPRA (SPR/2021/000103), and JC Bose Fellowship (JCB/2023/000027) for financial support. We are also thankful to the Sunita Sanghi Center for Aging and Neurodegenerative Diseases (SCAN) at IIT Bombay for its financial support. R.S. acknowledges the Ministry of Human Resource Development (MHRD), Government of India, for the Prime Minister's Research Fellowship (PMRF ID: 1301600).

D2 – P018

Development of pH-responsive hydrogel in gastro-resistant capsules for colon targeted drug delivery

Rabeh M.[1,2], McCoy C.P.[2], Alqudah A.[3], Rabi A.[1], Tayyem M.[4], Wylie M.P.[2]
[1]Jerash University, Jerash; [2]Queen's University, Belfast, UK; [3]Hashemite University, Zarka; [4]Middle East University, Amman, Jordan

Introduction

Colon-targeted drug delivery systems are a promising strategy for improved treatment of local diseases affecting the colon, such as inflammatory bowel disease (IBD). IBD is associated with significant patient morbidity with more than 6.8 million patients globally suffering from IBD complications [1]. The physiology of the gastrointestinal tract (GIT), which has a variable pH environment, has encouraged the development of novel pH-responsive delivery systems able to protect water-soluble drugs from the harsh GIT environment and deliver high drug payload to the colon for colonic therapies.

Methods

A free radical polymerization method was used to prepare four copolymer hydrogel films of HEMA, MAA and MMA using EGDMA as a crosslinking agent and AIBN as thermal free radical initiator of 4 compositions, denoted H1-H4 (2). ATR-FTIR was used to confirm the polymerization of the network. A model BCS Class I drug was employed in the study. The post-loading method was used to load the drug in the polymeric network. Swelling and in-vitro release studies were performed in different buffer conditions mimicking the pH of the stomach, colon, and small intestine (pH 1.2, 6.5 and 7.4), respectively. In vitro cytotoxicity of hydrogels was evaluated on CT-26 and L- 29 cell lines using an MTT assay to assess the potential cytotoxicity of hydrogels.

Results

Acrylate-based pH-responsive hydrogels were successfully synthesized. ATR-FTIR confirmed hydrogel polymerization. The swelling study shows the protective effect of gastro-resistant capsules in pH 1.2, as the capsule shell remained intact and resisted dissolution during the first 6 h of immersion in the swelling media, in contrast to neutral conditions where the capsule disintegrated within the first two h. This observation was further confirmed by drug release studies where the release of module drug was not detected in the acidic condition release media over 6 h. While the release was observed in the condition mimicking the small intestine in the requirement for capsule disintegration before hydrogel swelling limited premature drug release during transit through the small intestine (and stomach) to < 24% for H4 and < 28% for H3, compared to 37% and 56% without capsule, thereby improving the delivery of a drug payload available for release in the colon. MTT assay confirmed no significant potential cytotoxicity of all hydrogels on the L929 and CT-26 cell lines.

Conclusion

Developing a drug delivery system that can precisely control and target drugs to the colon is crucial for enhancing the treatment of colonic diseases. The findings highlight the potential of capsule-hydrogel systems for the controlled release of water-soluble drugs specifically to the colon part of the GIT, emphasizing their promise as effective carriers for improving colonic drug delivery.

Learning Objectives

1. Demonstrate the applicability of an acrylate-based hydrogel as an inexpensive drug delivery carrier.
2. Understand the effect of gastro-resistant capsules on the pH-responsiveness of hydrogel carriers.
3. Demonstrate the ability of capsule-hydrogel delivery systems for targeted colonic drug delivery.

References

[1]Jairath V., Faegan B.G. *The Lancet Gastroenterology & Hepatology* 2020.
[2]Rabeh M. E., et al. *Biomaterials Advances* 2024.

D2 – P019

"Matrioska" GelMA hydrogels for sharp on-off ultrasound-triggered drug delivery

Sirolli S.[1,2], Bakht S. M.[3], Ricotti L.[1,2], Mano J. F.[3], Cafarelli A.[1,2]
[1]The Biorobotics Institute, Scuola Superiore Sant'Anna, Pisa, Italy; [2]Dept. of Excellence in Robotics & AI, Scuola Superiore Sant'Anna, Pisa, Italy; [3]CICECO – Aveiro Institute of Materials, Dept. of Chemistry, University of Aveiro, Aveiro, Portugal

Introduction

Hydrogels activable through external stimuli are extremely promising platforms for drug delivery, as suitable timing and localized release are crucial for maximizing efficacy and reducing side effects. Among biophysical stimuli, ultrasound (US) has outstanding safety and non-invasiveness. Perfluorocarbon (PFC) droplets are promising carriers for US-triggered drug delivery, with good stability and sharp on-off release behavior. However, when included in hydrogels, they require extremely high pressures for activation. While it's possible to activate droplets with low-frequency US at very low and safe pressures in liquid environment, in a hydrogel thresholds for triggering are much higher.
Here, we developed a US-responsive hydrogel including PFC droplets that can release its cargo in response to pressures as low as 125 kPa, using a "matrioska" approach: droplets were included in liquid-core capsules, that were in turn incorporated within the hydrogel (Fig. 1a).

Materials and Methods

The droplets, consisting of a perfluoropentane core and a surfactant shell and encapsulating fluorescein sodium salt (4 mg/mL) as a drug model, were synthesized through a microfluidic technique (1 µL/min core, 5 µL/min shell). The microcapsules, with a permeable alginate and poly-L-lysine shell, were produced using electrospray. Photocrosslinked gels consisted of 5% GelMA and 0.5% LAP and included either droplet-containing capsules or droplets only. They were stimulated with low-intensity pulsed US at 38 kHz and 125 kPa. Samples were imaged through fluorescence microscopy and drug release was quantified through fluorescence analysis of the supernatant.

Results

This droplet formulation was previously proven to release 35% of its cargo when stimulated with 38 kHz US at 100 kPa in liquid environment. However, when included in GelMA, they didn't vaporize consistently, even in response to a higher pressure of 125 kPa (Fig. 1c), showing a release of just 5%. Conversely, "matrioska" gels stimulated at the same pressure displayed rupture of encapsulated droplets (Fig. 1b) and much more significant release (>30%). This confirms that capsules create efficient liquid pockets within the gels, allowing droplets to be within a compact system while having performances comparable with the ones displayed in suspension. "Matrioska" gels also displayed very low passive leakage (~1%), confirming droplets stability post-encapsulation (Fig. 1d).

Conclusions

The "matrioska" approach maintains droplet responsiveness to safe US pressures, while allowing their inclusion in hydrogels. This permits their use for long-term localized release, and to contain damage from potential cavitation effects.

Acknowledgements

This work received financial and technical support from INAIL, project WOUND (grant agreement PR23-CR-Pe).




Figure 1: a) Schematic representation of the “matrioska” concept: fluorescein-loaded PFC droplets are included in liquid-core capsules, incorporated within the GelMA hydrogel. b) Fluorescence microscopy images of “matrioska” gels, with and without US stimulation; scalebar 100 µm. c) Fluorescence microscopy images of droplets-including gels, with and without US stimulation; scalebar 100 µm. d) Drug released by “matrioska” gels, including droplets-containing capsules, and by gels including only droplets, when stimulated with US at 38 kHz and 125 kPa.

D2 – P020

Polyoxazoline glycopolymers as galectin-3 inhibitors for treatment of cardiovascular diseases

Sedlář A.[1], Vrbata D.[2], Kurfiřt M.[3], Krčil A.[3], Červený J.[2], Holzerová K.[4], Benák D.[4], Červenková Šťastná L.[3], Hamala V.[3], Křen V.[2], Kolář F.[4], Karban J.[3], Bačáková L.[1], Bojarová P.[2]

[1]Laboratory of Biomaterials and Tissue Engineering, Institute of Physiology of the Czech Academy of Sciences, Prague, Czech Republic; [2]Laboratory of Biotransformation, Institute of Microbiology of the Czech Academy of Sciences, Prague, Czech Republic; [3]Research Group of Bioorganic Chemistry and Biomaterials, Institute of Chemical Process Fundamentals of the Czech Academy of Sciences, Prague, Czech Republic; [4]Laboratory of Developmental Cardiology, Institute of Physiology of the Czech Academy of Sciences, Prague, Czech Republic

Introduction

Galectin-3 is a β-galactoside-binding lectin that drives pathological extracellular matrix remodeling and fibrosis across organs, including liver (non-alcoholic steatohepatitis), lungs (idiopathic pulmonary fibrosis), and cardiovascular tissues (heart failure, atherosclerosis, pulmonary hypertension). Small-molecule carbohydrate-based galectin-3 inhibitors suffer from poor *in vivo* pharmacokinetics (short plasma elimination half-life), limiting their clinical application. Polyoxazoline (POx) polymers provide a versatile, tunable drug delivery platform, enhancing affinity to galectin-3 through multivalent presentation while improving the *in vivo* stability of glycomimetic inhibitors.

Aim

This study develops POx glycopolymers bearing lactose mimetics as stable, *in vivo*-effective galectin-3 inhibitors for antifibrotic therapies targeting pulmonary hypertension and other cardiovascular diseases.

Materials and Methods

POx polymers were synthesized via cationic ring-opening polymerization and functionalized with lactose or its fluorinated or coumarylated derivatives using CuAAC click chemistry. Galectin-3 binding affinity was quantified by biolayer interferometry. Antifibrotic effects on markers related to pulmonary hypertension (α-SMA, calponin, collagen I) were evaluated in hypoxic rat cardiac fibroblasts and pulmonary artery smooth muscle cells. Pharmacokinetics and biodistribution were assessed in rats using fluorescently labeled polymers. Endothelial permeability was evaluated in human umbilical vein endothelial cell (HUVEC) transwell assays.

Results

POx glycopolymers exhibited subnanomolar Gal-3 affinity and significantly suppressed pulmonary hypertension-related fibrotic markers in hypoxic rat cardiac fibroblasts. Fluorination and coumarylation of lactose ligands extended plasma half-life approximately 3-4-fold by evading C-type lectin-mediated clearance, enabling accumulation in heart and lungs comparable to unmodified POx. All showed limited permeability across the HUVEC monolayer.

Conclusion

POx-based glycopolymers exhibited high galectin-3 affinity, suppressed pulmonary hypertension-related fibrotic markers *in vitro* in cardiac fibroblasts and pulmonary artery smooth muscle cells, and achieved favorable accumulation *in vivo* in the heart and lungs. Selective fluorination or coumarylation of lactose ligands dramatically enhanced *in vivo* stability and circulation half-life by evading C-type lectin-mediated clearance while preserving potent multivalent galectin-3 binding, offering a broadly applicable strategy for galactose-terminated glycotherapeutics. This tunable POx platform holds strong promise for the treatment of pulmonary hypertension and other cardiovascular diseases.

Acknowledgements

Supported by the Czech Science Foundation (26-20451S), and by the Ministry of Education, Youth and Sports of the Czech Republic, co-funded by the European Union (CZ.02.01.01/00/22_008/0004562).

D2 – P021

Targeted nanoparticle delivery of metal-based drugs in a biomimetic 3D glioblastoma model

Fontanini V.[1], Salerno D.[1], Habich-Crayton A.[2], Sesana S.[1], Salassa L.[3], Krzykawski M.[2], Nicolini G.[1], Russo L.[1,4,5], Re F.[1,5]

[1]School of Medicine and Surgery, University of Milano-Bicocca, Vedano al Lambro (MB), Italy; [2]Real Research S.A., Krakow, Poland; [3]Donostia International Physics Center, University of the Basque Country, San Sebastián, Spain; [4]CURAM Research Ireland Centre for Medical Devices, University of Galway, Ireland; [5]Fondazione IRCCS San Gerardo dei Tintori, Monza, Italy

Introduction

Glioblastoma Multiforme (GBM) is the most aggressive primary brain tumor, with a median survival of only 15 months[1]. Despite surgical resection and chemo-radiotherapy, recurrence is nearly inevitable[2]. This failure is mainly driven by the blood-brain barrier, intratumoral heterogeneity, and a lack of specificity for tumour cells, which leads to significant off-target toxicity[2,3]. Furthermore, GBM cells infiltrate healthy tissue adjacent to the resection cavity, facilitating relapse.

Aim

This study aims to replicate the post-operative microenvironment using a three-dimensional (3D) culture system for superior drug screening and to develop tunable protein-based hydrogels for the controlled local release of functionalized nanoparticles (Figure 1).

Materials and Methods

This study utilizes LifeGel® technology to replicate the post-operative resection cavity by tuning stiffness, cell density, and elasticity. U87 MG spheroids, generated via the liquid-overlay method, were embedded into LifeGel® formulations and compared against an agarose control matrix. The model was characterized through proliferation kinetics assays, brightfield microscopy, live/dead assays, immunofluorescence, and H&E staining. Moreover, the efficacy and selectivity of a novel metallic drug encapsulated in liposomes, functionalized with a modified Apolipoprotein E peptide (mAPOE), targeting Low-Density Lipoprotein Receptor (LDLR), were evaluated against healthy astrocytes using MTT and morphological assays. Finally, protein-based hydrogels will be investigated as biomaterials for localized nanoparticle release.

Results

Preliminary studies demonstrated that LifeGel® technology enables U87 spheroids to exhibit key biological behaviours that are absent in agarose-based 3D culture, including the formation of epithelial-like structures and active proliferation, allowing for a more reliable evaluation of drug efficacy (Figure 2A,B). To enhance cellular targeting while minimizing systemic toxicity and improving drug stability, nanoparticles surface-modified with the mAPOE peptide, capable of selectively targeting the overexpressed LDLR in glioma cells, will be used to encapsulate innovative metal-based drugs. Preliminary studies have confirmed the effectiveness of this targeting strategy, showing significantly increased targeting and cellular uptake of mAPOE-functionalized nanoparticles in GBM cells compared with non-functionalized controls (Figure 2C,D). Furthermore, a protein-based hydrogel has been prepared, characterized (Figure 2E,F) and validated as local nanoparticle-release biomaterial using a 'donut-like' 3D model. The results demonstrated efficient nanoparticle diffusion and targeted delivery to glioblastoma cells within a 3D architecture[3,4].

Conclusion

This project establishes a physiologically relevant 3D microenvironment model using LifeGel® and tunable hydrogels to enhance drug screening and enable the targeted, sustained local delivery of nanomedicines for glioblastoma recurrence. Through this interdisciplinary effort, the project seeks to bridge the gap between benchtop research and personalized GBM therapy.




Figure 1. Project graphical abstract. Generated by FigureLabs.




Figure 2. Preliminary results.

References

[1]Yalamarty S.S.K., Filipczak N., Li X., Subhan M.A., Parveen F., Ataide J.A., Rajmalani B.A., Torchilin V.P. Mechanisms of Resistance and Current Treatment Options for Glioblastoma Multiforme (GBM). *Cancers (Basel)* 2023; Apr 1; 15(7):2116.

[2]Yadav N., Purow B. W. Understanding current experimental models of glioblastoma-brain microenvironment interactions. *J. Neurooncol* 2024; 166; 213–229.

[3]Viale F., Ciprandi M., Leoni L., Sierri G., Renda A., Barbugian F., Koch M., Sesana S., Salvioni L., Colombo M., Mantegazza F., Russo L., Re F. Biodegradable SPI-based hydrogel for controlled release of nanomedicines: a potential approach against brain tumors recurrence. *Journal of Drug Delivery Science and Technology* 2024; 96; 105672.

[4]Ciprandi M.*, Fontanini V.*, Sommi P., Anselmi-Tamburini U., Sesana, S., Re, F. Tunable SPI hydrogel for nanoparticles brain release. *Journal of Materials Science: Materials in Medicine* submitted paper.

D2 – P022

Polymeric nanogels as targeted drug delivery systems for prostate cancer treatment

Foto F.[1,2], Seidita F.[1,3], Bouchikhi N.[4], Benfante V.[5], Alongi P.[5,6], Comelli A.[2], Dispenza C.[1]
[1]Dipartimento di Ingegneria, Università degli Studi di Palermo, Palermo, Italia; [2]Ri.MED Foundation, Palermo, Italy; [3]Institute for Bioengineering of Catalonia (IBEC), Les Corts, Barcelona, Spain; [4]Centre de Recherche Scientifique et Technique en Analyses Physico-chimiques, Tipaza, Algeria; [5]Advanced Diagnostic Imaging-INNOVA Project, Dept. of Radiological Sciences, A.R.N.A.S. Civico Di Cristina e Benfratelli Hospitals, Palermo, Italy; [6]Dept. of Biomedicine, Neuroscience and Advanced Diagnostics (BiND), University of Palermo, Palermo, Italy

Introduction

Poly(N-vinylpyrrolidone)-based nanogels obtained by electron beam irradiation are promising systems for applications in prostate cancer (PCa). They combine a simple synthesis without surfactants, a tunable surface chemistry, and good stability. Starting from the physicochemical characterization of formulations copolymerised with acrylic acid, this work focuses on the preliminary biological evaluation of two nanogel systems, 05AA50 and 03AA50, with different hydrodynamic size. A cellular localization study was conducted using two different cell lines, LNCaP and SW982, with the first overexpressing the prostate-specific membrane antigen (PSMA), and the second acting as a negative control.

Materials and Methods

The analyzed samples included nanogels loaded only with doxorubicin and nanogels loaded with doxorubicin and functionalized with PSMA, in order to compare passive uptake with the possible effect of active targeting. Both 05AA50 and 03AA50 were designed to use the carboxyl groups derived from the acrylate monomer and formed after irradiation for the conjugation of the drug and the targeting agent. Doxorubicin was used both as a therapeutic molecule and as an intrinsic fluorescent probe, making it possible to monitor the nanogel-associated signal inside the cells without using additional markers. Samples containing PSMA were also prepared to evaluate whether receptor-mediated recognition could improve cell-associated localization in different cellular models. In parallel, fluorescence analyses were performed by using the intrinsic fluorescence of doxorubicin (and of PSMA, due to the presence of its aromatic ring) to quantify the amount of compound bound to the nanogels. Dimensional analyses were also carried out by multi angle dynamic light scattering (MADLS).

Results

Localization experiments performed at 3 time points showed that all doxorubicin-containing formulations interacted with both cell lines and, in most cases, were localized inside the cells. However, some differences were observed between the two cell lines and between targeted and non-targeted samples. In particular, PSMA-functionalized nanogels showed a clear intracellular localization pattern in the PSMA+ LNCaP cell line of interest, as we expected. The comparison between the two base nanogel formulations, 05AA50 and 03AA50, did not show significant differences in cellular interaction, suggesting that the size difference between the two systems does not strongly affect biological behavior.

Conclusion

These preliminary biological results support further in vitro studies on these nanogels and suggest a possible role of PSMA as a targeting agent in specific cellular contexts. The biological localization data, together with the dimensional analyses and the spectrofluorometric characterization, provide a positive preliminary basis for future studies.

D2 – P023

Ex vivo permeation of thymoquinone from transfersome formulations: Deformable vesicular carriers and their potential for localised transdermal delivery to breast tissue

Ghazali Y., Conway B., Adebisi A.
Dept. of Pharmacy, School of Applied Science, University of Huddersfield, England

Introduction

Thymoquinone (TQ; 2-methyl-5-(propan-2-yl)cyclohexa-2,5-diene-1,4-dione) is a bioactive monoterpene quinone isolated from the seeds of *Nigella sativa* (black cumin) with documented anticancer activity against breast carcinoma, mediated in part through natural killer (NK) cell immune modulation and the release of perforin, granzyme and interferon-α (Alshaibi et al., 2022). Its clinical translation is constrained by poor aqueous solubility and limited oral bioavailability (Alkharfy et al., 2015), providing a rationale for encapsulation within ultra-deformable transfersomes for localised transdermal delivery. This study evaluates the *ex vivo* transdermal permeation of TQ from transfersome formulations across porcine ear skin and quantifies the contribution of the vesicular carrier relative to free drug.

Materials and Methods

Transfersome formulations of TQ at 5, 10 and 20 mg·mL^{-1}, together with a saturated free-drug positive control (0.62 mg·mL^{-1}), were applied to fresh porcine ear skin mounted in Franz diffusion cells (diffusion area = 3.142 cm^2; 20 mm orifice) at 37 °C, with PBS (pH 7.4) as the receptor medium. Donor volumes were adjusted (2, 1 and 0.5 mL for the 5, 10 and 20 mg·mL^{-1} formulations, respectively) to deliver an equivalent nominal TQ dose (10 mg) across all transfersome arms. Receptor samples were withdrawn at 0, 0.5, 1, 2, 4, 6, 8 and 24 h and quantified by HPLC. Cumulative permeated drug per unit area (Qt, µg·cm^{-2}) was calculated, and steady-state flux (Jss, µg·cm^{-2}·h^{-1}), and permeability coefficient (Kp = Jss/C_0) were estimated from the linear region of the cumulative permeation versus time profile.

Results

Over 24 h, cumulative permeation increased with donor concentration, with the 20 mg·mL^{-1} transfersome producing the highest Qt (8.35 µg·cm^{-2}), followed by the 10 mg·mL^{-1} (6.96 µg·cm^{-2}) and 5 mg·mL^{-1} (4.27 µg·cm^{-2}) formulations (Figure 1.0). Estimated Jss were 0.58, 0.30 and 0.56 µg·cm^{-2}·h^{-1} for the 5, 10 and 20 mg·mL^{-1} formulations, with corresponding lag times of 0.40, 0.91 and 2.06 h, indicating a non-monotonic relationship between donor concentration and flux. Critically, the saturated free drug positive control produced no detectable permeation at any timepoint (Qt = 0; Jss = 0), confirming that intact porcine skin is effectively impermeable to unformulated TQ over 24 h.




Figure 1.0: Ex vivo transdermal permeation profiles of thymoquinone (TQ) from deformable transfersome formulations. The cumulative mass of TQ permeated per unit area (Qt) across porcine ear skin over 24 hours is shown for the 5 mg per mL, 10 mg per mL, and 20 mg per mL transfersomes (each delivering an equivalent 10 mg

nominal dose), compared with a saturated free drug control. Data represent mean values from Franz diffusion cell experiments conducted at 37 degrees Celsius using PBS pH 7.4 as the receptor medium.

Discussion

Cumulative Qt increased with donor concentration, but Jss did not scale proportionally, reflecting the competing influence of donor volume on stratum corneum hydration, formulation spreading and persistence of the concentration gradient. The larger 2 mL donor at 5 $mg \cdot mL^{-1}$ achieved faster early permeation but rapid reservoir depletion, while the smaller, more concentrated donors preserved a steeper gradient for longer: the 10 $mg \cdot mL^{-1}$ formulation delivered the most sustained release, and the 20 $mg \cdot mL^{-1}$ formulation the highest Qt at 24 h. The complete absence of permeation from the saturated free-drug control, demonstrates that the intrinsic physicochemical properties of TQ present an absolute barrier to passive diffusion that is overcome by the deformable transfersome carrier.

Conclusion

Transfersome formulations enabled measurable *ex vivo* transdermal permeation of thymoquinone, with the 20 $mg \cdot mL^{-1}$ formulation yielding the highest cumulative Qt and the 10 $mg \cdot mL^{-1}$ formulation the most sustained flux, whereas free TQ did not permeate at all. These results establish deformable transfersomes as effective carriers for the controlled transdermal permeation of TQ, supporting further development toward potential localised delivery to breast tissue.

Keywords: Thymoquinone; transfersomes; ex vivo permeation; transdermal delivery; flux; breast cancer

References

[1]Alkharfy K. M., Ahmad A., Khan R. M. A., Althagafi M. New HPLC-DAD method for the determination of thymoquinone in rat plasma: Application to a pharmacokinetics study. *European Journal of Drug Metabolism and Pharmacokinetics* 2015; *40*(3); 375–382.

[2]Alshaibi H. F., Al-Shehri B., Baazm M., Alghamdi S. S. Thymoquinone: An anticancer compound from *Nigella sativa* with potential activity against breast carcinoma. *Evidence-Based Complementary and Alternative Medicine* 2022; Article 6175535.

D2 – P024

Accelerated mucopermeation and -penetration of the polypeptide antibiotic Colistin via ionic complexation with polyphosphazene carriers

Stadler P.[1], Kehrer S.[2], Strasser P.1, Roschger C.[2], Loretz B.[3] and Teasdale I.[1]
[1]Johannes Kepler University Linz, Institute of Polymer Chemistry, Linz, Austria; [2]Johannes Kepler University Linz, University Clinic for Cardiac-, Vascular- and Thoracic Surgery, Linz, Austria; [3]Helmholtz Institute for Pharmaceutical Research Saarland (HIPS), Helmholtz Center for Infection Research (HZI), Saarbrücken, Germany

Introduction

The mucus barrier plays a vital protective role for non-keratinized epithelia in the body, yet its complex structure poses a significant obstacle to effective non-invasive drug delivery. In particular, molecules with higher molecular weight and interaction potential require strategies for facilitated transport. A common strategy involves the use of polyethylene glycol (PEG) for encapsulation. In this research, we will focus on two alternative polymers, poly(α-glutamic acid) (PGA) and poly[di(carboxylatophenoxy)phosphazene] (PCPP). Both polymers are highly water-soluble, biodegradable and widely reported to be biocompatible in various applications. Their anionic nature as a polyacid makes them promising for mucopenetrative drug delivery and complexation with cationic peptides, as shown here with the antibiotic colistin.

Materials and Methods

A series of three water-soluble polymeric carriers, PCPP, PEG, and PGA with comparable hydrodynamic diameters of 7-8 nm were synthesized, containing a cyanine-5 label and their permeability through an artificial pulmonary mucus was tested (Figure 1). Polymer complexes of PGA and PCPP with colistin were formed via electrostatic binding and characterized with dynamic light scattering, zeta potential, stability studies and testing of antibacterial activity. Mucopermeation studies of the complexes were performed with FITC-labelled colistin.

Results

The biodegradable polyacids PGA and PCPP exhibited mucus permeability similar to PEG up to 50 mg/mL. Colistin-binding studies of the polymer complexes confirmed effective encapsulation by both polymers, with PCPP-colistin complexes exhibiting the highest stability. Mucopermeation studies of the polymer-colistin complexes, illustrated in Figure 2, revealed enhanced colistin mucopermeation, with an enhanced effect observed for PCPP-complexes. Furthermore, the broth microdilution assay revealed no differences in the minimum inhibitory concentrations of colistin and the polymer-colistin complexes. Overall, PCPP showed significantly superior performance due to its higher colistin encapsulation efficiency, attributed to its unique chemical structure, thereby highlighting its potential as a mucus-penetrating carrier for cationic therapeutic peptides.

Conclusion

This study demonstrates that the biodegradable polyacids PGA and PCPP exhibit mucopermeation capabilities comparable to those of the “gold-standard” PEG, highlighting their potential as alternative carriers. Both polymers effectively encapsulate colistin, with PCPP forming the most stable complexes. Furthermore, conjugation with these polymers enhanced colistin transport across the mucus layer, with more pronounced effects observed at higher polymer-to-colistin ratios. The superior mucopenetration of PCPP conjugates is attributed to their higher encapsulation efficiency, highlighting PCPP as a promising biodegradable platform for the mucus-mediated delivery of cationic therapeutics, while preserving their antibacterial activity.

Acknowledgements

This study was funded by LIT project LIT-2022-11-SMED-419 “PEPTECH”.




Figure 1: Accelerated mucopermeation and -penetration of Colistin via ionic complexation with polymer carriers.




Figure 2: Mucopenetration of Polymer-colistin conjugates.

D2 – P025

Antioxidant conjugated chitosan for localized controlled delivery of antibiotics for chronic wounds

Rekha M.R.*, Lekshmi D., Annie M.R., Linju M.C.
Division of Biosurface Technology, Biomedical Technology Wing, Sree Chitra Tirunal Institute for Medical Sciences & Technology, Poojappura, Thiruvananthapuram, Kerala, India

Introduction

Chronic wounds are a major clinical challenge and impose a significant burden on patients and healthcare systems. Conditions such as diabetes, vascular insufficiency, and persistent microbial infection often impair the normal wound healing process. In chronic wounds, prolonged inflammation, microbial biofilm formation, and excessive production of reactive oxygen species (ROS) disrupt tissue repair and delay healing. Conventional treatment strategies commonly involve systemic administration of antibiotics, which may result in low drug concentrations at the wound site and potential systemic toxicity.

Localized therapeutic strategies that directly deliver antimicrobial agents to the wound bed offer a promising alternative for improving treatment outcomes. In addition, controlling oxidative stress through antioxidant therapy can further support the healing process by reducing ROS-mediated tissue damage.

Aim

The present study aims to develop a polymeric sponge-based drug delivery system (DDS) with antioxidant (Anti-ROS) functionality for the management of chronic infectious wounds. The dressing is designed to deliver antibiotics locally to combat biofilm-associated infections while simultaneously scavenging excess ROS to promote tissue repair. The material is engineered to provide essential characteristics of an ideal wound dressing, including non-adherence, high absorbency, maintenance of a moist wound environment, and appropriate water vapor transmission.

Materials and Methods

Chitosan (High molecular weight, DDA-85%) was conjugated with antioxidant molecule chlorogenic acid using EDC chemistry. The resultant derivative was solubilised in water and freeze-dried. The resultant scaffolds were evaluated for its mechanical strength, WVTR, antioxidant properties, biocompatibility, loaded with antibiotics and the release profile were evaluated.

Results

The chitosan–chlorogenic acid (CCLA) scaffolds demonstrated good stability across different pH conditions (pH 5.8, 6.8, and 7.4) in phosphate buffer, indicating their suitability for the varying microenvironment of chronic wounds. The scaffolds also exhibited a favorable water vapor transmission rate (WVTR) of 1676 ± 24 g/m²/24 h, which is within the optimal range required to maintain a moist wound environment while preventing excessive dehydration. In addition, mupirocin-loaded CCLA sponges showed strong antimicrobial activity. The antimicrobial efficacy was evidenced by a zone of inhibition comparable to that of a standard mupirocin-loaded disc, despite containing only half the drug dose, indicating enhanced antibacterial efficiency of the scaffold-based drug delivery system (Fig1.) . In vivo experiments in rabbit model demonstrated better healing in drug loaded CCLA group (Fig 2.)



CCLA- Mupirocin loaded

Figure1: Antimicrobial effect of mupirocin loaded CCLA against S. aureus



Figure 2: Wound healing efficacy of drug loaded CCLA sponges in comparison with free drug and scaffold alone at day 21

Conclusion

The developed scaffold showed appropriate swelling behavior, optimal WVTR, effective antimicrobial activity, strong free radical scavenging ability, and improved mechanical strength compared to native chitosan, supporting its potential as a multifunctional wound dressing material.

Acknowledgements

DST, TRC funds, SCTIMST is acknowledged for the financial support.

D2 – P026

Reprogramming the dermal microenvironment via hyaluronic acid hydrogels encapsulating extracellular vesicles

Kang J., You D.G.*
Dept. of Chemical Engineering and Biotechnology, Tech University of Korea, Siheung, Republic of Korea

Introduction

Although hyaluronic acid–based hydrogels (Hyal-Gels) are gold-standard dermal fillers, their inability to stimulate endogenous collagen remains a clinical challenge. To address this, we developed extracellular vesicles (EVs) encapsulating Hyal-Gels (EVHyal-Gels) that aim to reprogram the dermis environment for long-term functional recovery.

Materials and Methods

Adipose-derived stem cell extracellular vesicles (ADSC-EVs) were isolated via tangential flow filtration method. Hyal-Gels were prepared by cross-linking and loaded with ADSC-EVs to from EVHyal-Gels. Properties of EVHyal-Gels including rheology, injection force, and degradation were assessed. In vitro, ADSC-EV's effects on macrophage CD301b expression, fibroblast proliferation, and collagen synthesis were investigated, with miRNA inhibition studies included. Subsequently, EVHyal-Gels were administered to mice to evaluate dermal microenvironment reprogramming, including macrophage phenotype and fibroblast presence. Finally, long-term collagen synthesis was assessed through histological and immunofluorescent analyses.

Results

EVs were evenly distributed within the Hyal-Gels without significantly altering the intrinsic properties. Small RNA sequencing revealed that let-7b-5p and miR-24-3p, known for promoting anti-inflammatory macrophage phenotypes, were abundant in EVs. Inhibition of let-7b-5p and miR-24-3p suppressed CD301b expression, indicating that EVs induce the reprogramming macrophages into a CD301b^{high} phenotype. These reprogrammed macrophages effectively trigger fibroblast activation, leading to increased collagen synthesis. In vivo, locally injected EVHyal-Gels induced a higher number of CD301b^{high} macrophages and an increased fibroblast population in the dermis layer compared to bare EV treatment. Four weeks after treatment, EVHyal-Gels resulted in a 2.4-fold larger collagen layer compared to conventional Hyal-Gels, and this increased collagen layer was maintained for up to 24 weeks in the dermis. Immunohistochemical analyses confirmed enhanced collagen I and III generation in an EV dose-dependent manner.

Conclusion

These results highlight EVHyal-Gels as a next-generation functional filler capable of long-term dermis environment reprogramming.

References

[1]You D.G., An J.Y., Um W., Jung J.M., Oh B.H., Nguyen V.Q., Jeon J., Lee J., Jo D.G., Cho Y.W., Park J.H. Stem Cell-Derived Extracellular Vesicle Bearing Dermal Filler Ameliorates the Dermis Microenvironment by Supporting CD301b Expressing Macrophages. *ACS nano* 2021; 16(1); 251-260.

D2 – P027

Comparing bulk-doping to an innovative click-chemistry surface grafting approach towards antibacterial melt electrowritten polycaprolactone membranes

Le Brun A.[1], Roux M.[2], Servantie A.[1,2], Jallot E.[1], Charbonnel N.[3], Vareille-Delarbre M.[3], Lao J.[1], Daumar P.[2], Abdellaoui N.[1]

[1]Laboratoire de Physique de Clermont Auvergne (LPCA), Université Clermont Auvergne, CNRS, Clermont-Ferrand; [2]Laboratoire d'Imagerie Moléculaire et Stratégies Théranostiques (IMoST), Université Clermont Auvergne, INSERM, Clermont-Ferrand, France; [3]Laboratoire Microorganismes: Génome Environnement (LMGE), Université Clermont Auvergne, CNRS, Clermont-Ferrand, France

Introduction

Bacterial infections remain a major obstacle to proper tissue healing in the context of open wounds and surgical implants. As the use of antibiotics is becoming increasingly controversial due to the emergence of bacterial resistance, there is a critical need to find alternatives, among which the use of phytochemical compounds (PhyC) appears promising. In this context, fiber-based membranes enriched with PhyC designed by Melt electrowriting (MEW) have been explored as bioactive patches or wound dressings. One challenge remains: how can PhyC be efficiently introduced into these precisely structured materials? Current approaches generally rely on direct incorporation of bioactive molecules into the polymer before printing. While this strategy can impart biological activity, it often suffers from important limitations such as burst release, degradation of heat-sensitive compounds during processing such as additive manufacturing, degradation during storage due to weak bonds and molecules volatility, and PhyC release limited to adsorbed molecules on the surface.

Aim

This study compares bulk-doping to an innovative click-chemistry surface grafting approach for developing antibacterial melt electrowritten polycaprolactone membranes.

Materials and Methods

Two functionalization strategies are investigated: (1) Bulk-doping: phytochemicals with antibacterial properties (thymoquinone (TQ), epigallocatechin gallate (EGCG)) are incorporated into PCL before MEW (1% and 2.5% w/w). (2) Click-chemistry surface grafting via azide-alkyne reaction: modified PCL is printed and then PhyC is covalently bound to the membrane surface. Antibacterial activity and cytotoxicity are evaluated through *in vitro* assays. Physico-chemical characterization of the membranes is also underway.

Results

Antibacterial studies with TQ and EGCG bulk-doped PCL show strong activity against *Staphylococcus aureus* in suspension (10-log and 6-log reduction for TQ and EGCG respectively, Fig. 1a) but limited efficacy against surface-attached biofilms (Fig. 1b). We hypothesize that click-based surface functionalization could outperform bulk-doping by positioning bioactive agents on the membrane surface and improve the release profile (plateau reached within the first 2 hours for bulk-doping). We are able to fabricate clickable membranes (Fig 1c): in a proof-of-concept experiment, functionalized PCL is successfully clicked with FITC fluorophore (green signal), while unfunctionalized PCL shows no signal (red cross), confirming covalent attachment.




Figure 1: (a,b) Bacterial growth curves (CFU counting) of *Staphylococcus aureus* comparing PCL membranes (black) and PCL bulk-doped with 2.5 wt% TQ (red) and 2.5 wt% EGCG (green) for: (a) planktonic bacteria in suspension; (b) bacteria in biofilms attached to membranes surface. (c) Functionalized PCL membrane printed by MEW and clicked with FITC fluorophore (green fluorescence signal). Control: unfunctionalized PCL membrane exposed to FITC shows no signal (red cross), confirming covalent attachment rather than physical adsorption.

Conclusion

Our study demonstrates the potential of using MEW to obtain functionalized polycaprolactone membranes with phytochemical compounds, by bulk-doping or surface grafting, for the prevention of tissue infections. Looking ahead, click-chemistry could enable the production of modular membranes, providing control over doping rates and release kinetics.

D2 – P028

Development of degradable hybrid dermal substitute loaded with bioactive compounds from the biodiversity of Reunion Island

Fontaine L.[1,2], Pinese C.[1,3], Checkouri E.[2], Nottelet B.[1,3]
[1]Polymers for Health and Biomaterials, IBMM, ENSCM, University of Montpellier, CNRS, Montpellier; [2]Skinegy, Saint Pierre, Ile de la Réunion, France; [3]Dept. of Pharmacy, Nîmes University Hospital, Nîmes, France

Introduction

Dermal substitutes are widely used to support tissue regeneration in chronic wounds such as pressure injuries and diabetic foot ulcers. However, current matrices exhibit limited conformability to irregular wound beds and require invasive procedures that sustain inflammation and delay healing. They also lack integrated bioactivity and fail to adequately regulate exudate, hydration, and infection, highlighting the need for advanced scaffolds tailored to the wound microenvironment.

Aim

This study investigates the design of a hybrid, bioactive, degradable dermal substitute engineered as a porous scaffold to promote cell colonization. It further enables the incorporation of plant-derived bioactive compounds from Réunion Island with antioxidant, anti-inflammatory, and antimicrobial properties.

Materials and Methods

Hybrid hydrogels were synthesized by combining a synthetic copolyester and a natural polymer, both methacrylated to enable UV-mediated crosslinking. The network structure was tuned by adjusting the copolymer branching degree and polymer ratio, enabling control of mechanical strength, porosity, swelling, and degradation. These formulations were evaluated for the release kinetics of bioactive compounds, assessing how network structure governs drug–matrix interactions. Biological response was examined using normal human dermal fibroblasts (NHDFs) through viability assays, proliferation quantification, and fluorescence microscopy. Ongoing experiments address wound-healing-related parameters, extracellular matrix deposition and evaluation of antioxidant and anti-inflammatory activity. All discussed concepts are summarized in Figure 1.

Results

Highly branched copolymers formed denser networks with greater stiffness compared to less branched systems. Increasing the natural polymer content did not affect the gel fraction but modified the network structure, resulting in enhanced swelling capacity (up to 1700% after 24 h). These matrices exhibited larger and more interconnected pores, accelerated degradation (~70% mass loss in 25 days) and reduced stiffness (~5 kPa). This composition-dependent behavior provides adjustment of properties to specific wound requirements (residence time, tissue properties, exudate level, etc.) Active compounds release profiles confirmed short-term delivery, primarily governed by the physicochemical profile of each active. Fibroblast proliferation was observed across all formulations over ten days. Microscopy revealed homogeneous, infiltrative growth within natural-polymer-rich hydrogels, contrasting with localized clustering in copolyester-dominant networks. Experiments on extracellular matrix secretion and compound bioactivity are currently in progress.

Conclusion

The hybrid system constitutes a tunable substitute with adjustable performance tailored to specific wound types, swelling to accommodate exudates and degrading at a healing-compatible rate. It promotes uniform cell proliferation throughout the gel, which remains to be confirmed in vivo. Current process optimization aims at more porous and conformable materials.




Figure 1. Schematic overview of key concepts

D2 – P029

3D-printed fish skin collagen dressings enriched with microalgae biomass: In vitro biological and antimicrobial evaluation

Souza-Silva L.C., Sousa K.S.J., Simões M., de Souza A., Bonifácio M., Luche L.D. , Assis M., Renno A.C.M.
Dept. of Biosciences, Federal University of São Paulo, Santos, Brazil

Introduction

The development of multifunctional wound dressings capable of preventing infection while supporting cellular regeneration remains a major challenge in regenerative medicine. Marine-derived biomaterials have attracted attention due to their biocompatibility and bioactive potential. Fish skin collagen provides a biomimetic extracellular matrix environment, while microalgae such as *Chlorella vulgaris* contain bioactive compounds including phenolics, peptides, and pigments with antioxidant and antimicrobial properties. The combination of these materials may improve biological performance and infection control in wound dressings.

Aim

This study aimed to develop and evaluate collagen-based wound dressings enriched with *C. vulgaris* biomass, focusing on their *in vitro* biological performance and antimicrobial activity.

Materials and Methods

Collagen extracted from fish skin was used to fabricate dressings incorporating different concentrations of *C. vulgaris* biomass. The release of soluble bioactive compounds and antioxidant activity were evaluated. *In vitro* biological performance was assessed using murine fibroblasts through metabolic activity and intracellular reactive oxygen species assays. Antimicrobial activity was tested against *Staphylococcus aureus* and *Pseudomonas aeruginosa* by colony-forming unit quantification.

Results

The incorporation of *C. vulgaris* biomass for bioactive release assays demonstrated a dose-dependent release behavior, where lower biomass concentrations promoted a more sustained release profile while higher concentrations resulted in a stronger initial release. All dressings showed cytocompatibility, maintaining fibroblast viability. Additionally, biomass dressings reduced intracellular ROS levels compared with the control, suggesting modulation of oxidative balance without inducing oxidative stress. Antimicrobial assays revealed bacterial inhibition against both *S. aureus* and *P. aeruginosa*, with greater effectiveness observed for intermediate biomass concentrations. These results indicate that controlled release of microalgae-derived bioactive compounds plays a key role in antimicrobial performance.

Conclusion

Collagen dressings enriched with *C. vulgaris* biomass exhibited cytocompatibility, antioxidant activity, and antimicrobial effects, highlighting their potential as multifunctional wound dressings.

Acknowledgements

This work was supported by “Fundação de Amparo à Pesquisa do Estado de São Paulo - FAPESP” through the grants Numbers: 2024/06598-0. The authors also acknowledge “Coordenação de Aperfeiçoamento de Pessoal de Nível Superior – CAPES” and “Conselho Nacional de Desenvolvimento Científico e Tecnológico – CNPq” for financial support.

D2 – P030

Engineering a human umbilical cord-based biomaterial for fistula treatment and controlled delivery of therapeutic exosomes

Garcia P., Martin L., Barnouin L.
R&D Dept., TBF - Tissue Engineering, Mions, France

Introduction

Current treatments for fistulas require either invasive surgical procedures, such as fistulotomy and seton placement, or less invasive options, including collagen plugs and fibrin glues, which are not fully biological and may not integrate completely. The human umbilical cord, comprising the amniotic membrane and Wharton's jelly, appears well-suited for fistula treatment and tissue regeneration, as it is naturally rich in glycosaminoglycans, collagen fibers, and growth factors, but also contains proteoglycans, enabling the tissue to retain fluids and function as a drug-delivery system. Additionally, a recent multicenter clinical trial (NCT05638139) has confirmed the safety of this biomaterial when used as a plug for fistula treatment. Meanwhile, the use of exosomes appears promising as they can promote wound healing, but local injection is challenging for both patients and practitioners. Our study thus aims to engineer a safe and efficient allograft derived from human umbilical tissue, which would then be tested as a drug-delivery system to promote the controlled release of therapeutic exosomes.

Materials and Methods

Human placental tissues were first collected with consent at French hospitals. Our engineered biomaterial was produced from a qualified umbilical cord that had been virus-inactivated, shaped to the required specifications, then freeze-dried before sterilization by gamma irradiation. Exosomes were initially isolated from C2C12 cell culture medium through centrifugation using 0.22µm and Amicon® filters, then loaded onto the dehydrated biomaterial. The resulting preparations were then immersed in PBS, and the supernatant was collected at multiple time points from 30 minutes to 48 hours. CD63, an exosome marker, was quantified in those collected samples using ELISA. Additionally, exosome integrity was assessed in the initial solution and the 6-hour extract by transmission electron microscopy using 1% uranyl acetate as a staining agent.

Results

Quantitative analysis indicated that the biomaterial allowed a gradual release of microvesicles over time (Figure 1). Examination of both the initial solution and the 6-hour extract showed the presence of structurally intact microvesicles of various sizes (Figure 2). A higher density of microvesicles was observed in the initial solution than in the 6-hour extract, suggesting a gradual release of vesicles from the biomaterial during incubation.

Conclusion

Our results indicate that an umbilical cord–derived biomaterial can enable the controlled release of intact exosomes, supporting its potential use as a localized drug-delivery system. Given its safety and stability in the human body, its use as an exosome delivery system appears promising for fistula treatment and tissue regeneration.




Figure 1. Cumulative exosome release over time




Figure 2. Exosome observation through microscopy

D2 – P031

Nanbiosis: A distributed research infrastructure bridging academia and industry up to preclinical development

Alfranca G., Casado M., Checa E., Martínez-Mañez R.
NANBIOSIS-ICTS, CIBER-BBN, Valencia, Spain

Introduction

Researchers in academia and industry face growing challenges in translating biomedical discoveries into validated preclinical solutions. These include limited access to specialized technologies, regulatory expertise, and multidisciplinary collaboration (Figure 1). NANBIOSIS is a Spanish national research infrastructure designed to address these gaps. It operates as a distributed platform composed of 26 Units located at publicly funded institutions and led by expert academic researchers.

Aim

NANBIOSIS provides centralized, one-stop-shop access to advanced services in biomedicine and nanomedicine, supporting efficient translation from basic research to preclinical development.

Materials and Methods

The capabilities of NANBIOSIS are organized into five thematic Programs (Figure 2). The infrastructure follows a demand-driven and market-oriented model, identifying emerging biomedical challenges through continuous interaction with researchers, clinicians, and industry stakeholders. Tailored solutions are developed by combining the specialized expertise of individual Units, fostering internal collaboration and engaging strategic external partners. Services are integrated into packages called Cutting-Edge Biomedical Solutions (CEBS), accessible through the NANBIOSIS website via a one-stop-shop system. The impact of this model was evaluated through a four-year analysis of service utilization data based on access requests and the competitive projects supported.

Results

NANBIOSIS provides a broad portfolio of CEBS addressing diverse biomedical needs. These include production of anti-peptide antibodies for diagnostics; recombinant protein production, purification, and characterization; peptide synthesis and monitoring for biomedical applications in animal models; preparation and evaluation of antimicrobial nanoparticles; development of enzyme-loaded nanovesicles for Fabry disease (Smart4Fabry); and peptide-functionalized nanoparticles, among other services.

By the end of 2024, NANBIOSIS had supported 619 projects. The infrastructure has also coordinated major collaborative initiatives such as Safe-N-Medtech, which provided specialized services across the nanomedicine innovation cycle at the European level and validated the NANBIOSIS model in an international context. Other initiatives include Smart4Fabry, which obtained Orphan Medicinal Product Designation in 2021 and contributed to the OITB-Phoenix project, and Chipr R Us, a collaboration developing lung-on-chip models to study pediatric bronchiolitis using patient samples and advanced imaging analysis.

Conclusion

These results demonstrate that the NANBIOSIS model is effective in supporting translational biomedical research. Its distributed structure, integrated service packages, and coordinated one-stop-shop access enable efficient use of public research capabilities, promoting innovation, collaboration, and progress toward preclinical validation at both national and European levels across academia and industry.




Figure 1 – Schematic representation of the workflow of NANBIOSIS and the fields covered by the network.




Figure 2 – The 5 Programs of NANBIOSIS.

D2 – P032

Additive manufacturing of porous ceria-stabilized zirconia ceramics for drug delivery

Farrokhnemoun D.[1], Damghani H.[2], Čokić S.[2], Koos E.[3], Van Meerbeek B.[2], Vleugels J.[1], Braem A.[1]
[1]KU Leuven Dept. of Materials Engineering; [2]KU Leuven Dept. of Oral Health Sciences; [3]KU Leuven Dept. of Chemical Engineering, Leuven, Belgium

Introduction

Infections caused by bacterial colonization of implant surfaces remain a major challenge in biomedical applications, particularly in transcutaneous systems such as dental implants. One strategy to reduce this risk is the use of drug delivery systems that release antibacterial agents at restoration site. Porous ceramic biomaterials are promising candidates for this purpose because their pore structure can host drug carriers while enabling release through an interconnected network while maintaining adequate mechanical properties. For dental applications, zirconia ceramics exhibit good biocompatibility. Ceria-stabilized zirconia (Ce-TZP) is particularly attractive due to its high fracture toughness and resistance to low-temperature degradation, making it suitable for porous structural scaffolds requiring long-term stability. To enable controlled drug release, mesoporous silica well known for its high surface area and drug loading capability can be incorporated into the pore network. Additive manufacturing techniques allow the fabrication of ceramic structures with controlled geometry, which can influence drug release behavior. However, the potential of porous Ce-TZP ceramics fabricated by digital light processing (DLP) as drug-delivery carriers remains unexplored.
The objective of this work is to evaluate the feasibility of drug delivery using Ce-TZP fabricated by DLP and functionalized with mesoporous silica. It is hypothesized that the interconnected pore network provides diffusion pathways, while the mesoporous silica phase controls antibacterial drug release.

Materials and Methods

Porous Ce-TZP discs were produced by DLP using starch as a pore-former. The discs were infiltrated with a colloidal silica suspension followed by gelling, ageing and calcination to achieve silica nanoparticles. The pore morphology and their connectivity were characterized using mercury intrusion porosimetry, scanning electron microscopy and X-ray computed tomography. Silica filling efficiency was evaluated by air permeability test. Drug-release experiments were conducted with chlorhexidine because of its molecular size as an antibacterial agent to evaluate the release behavior. Furthermore, in-vitro cell viability tests were performed to assess the cytocompatibility of the materials.

Results

Microstructural characterization revealed that DLP-printed discs enhanced interconnectivity and larger pore throats compared to pressed specimens, despite identical powder compositions. These architectural variances influenced the sol infiltration. In pressed discs, restricted channel dimensions led to sol occlusion. The release of chlorhexidine was analyzed to evaluate the influence of the porous architecture on the drug-release. Particular attention was given to whether the release profiles fall within therapeutically relevant concentration ranges reported for chlorhexidine mouth rinses, in order to assess the potential suitability for local antibacterial delivery.

Conclusion

The results demonstrate the feasibility of fabricating porous Ce-TZP structures by additive manufacturing for drug-delivery applications. The controlled pore architecture enables infiltration of the mesoporous silica phase and provides pathways for antibacterial drug release while maintaining suitability for biomedical use.

Acknowledgements

This research received funding from the European Union’s Horizon Europe programme under grant agreement no. 101091669 (NOMAD).

D2 – P033

Bioadhesive hyaluronic acid microneedle patch for pH-responsive riboflavin delivery in recurrent aphthous stomatitis

Chen Y.-J., Wu C.-H., Chang S.-J.*
Dept. of Biomedical Engineering, I-Shou University, Kaohsiung City, Taiwan

Introduction

Recurrent aphthous stomatitis (RAS) is one of the most common oral mucosal diseases and is characterized by recurrent painful ulcers that significantly impair patients' quality of life [1]. These ulcers are typically covered by a yellowish gray pseudomembrane composed of necrotic debris, fibrin, and inflammatory cells. Although this pseudomembrane helps protect the wound bed and maintain a moist environment conducive to healing, it also forms a physical barrier that significantly limits drug penetration into deeper ulcer tissues, thereby reducing the efficacy of conventional topical treatments [2]. Recently, microneedle-based drug delivery systems have attracted increasing attention as minimally invasive platforms capable of penetrating biological barriers and enabling localized drug delivery in mucosal tissues [3]. However, the development of adhesive microneedle systems suitable for the moist oral environment remains challenging.

Materials and Methods

A bioadhesive hydrogel microneedle patch (DAHA-Fe MN) was developed using dopamine-modified hyaluronic acid (DAHA) crosslinked through catechol–Fe^{3+} coordination. The AHA:DA grafting ratio was adjusted to 1:0.5, and Fe^{3+} concentration was optimized to obtain precursor solutions suitable for microneedle fabrication. Riboflavin (RF), a bioactive molecule known for its antioxidant and tissue regenerative properties, was incorporated into the microneedle matrix to enable localized and pH-responsive drug release within the acidic microenvironment of RAS lesions. Rheological properties, puncture capability, mechanical strength, wet adhesion, drug release behavior, cytocompatibility, cell migration, and in vivo therapeutic efficacy were systematically evaluated. The overall design and therapeutic mechanism are illustrated in Figure 1.

Results

Rheological analysis demonstrated that DAHA concentrations exceeding 15% produced highly viscous and shear-thinning precursor solutions suitable for microneedle fabrication. Both 15% and 20% DAHA-Fe formulations showed sufficient mechanical strength for tissue penetration; however, adhesion testing revealed superior wet adhesion with the 20% DAHA formulation, which was therefore selected for subsequent experiments. The optimized 20% DAHA-Fe microneedles effectively penetrated Parafilm® and porcine skin models and achieved more than 97% riboflavin release within 60 minutes at pH 6.0. In vitro assays confirmed excellent cytocompatibility with L929 fibroblasts, while RF@DAHA-Fe MN significantly enhanced cell migration and achieved nearly complete wound closure within 36 hours. In vivo experiments further demonstrated that RF@DAHA-Fe MNs adhered stably to the oral mucosa and significantly reduced ulcer areas in RAS rat models after seven days of treatment, accompanied by enhanced epithelial regeneration and collagen deposition (Figure 1). These findings highlight the effectiveness of microneedle-assisted drug delivery for overcoming biological barriers in mucosal tissues.

Conclusion

The DAHA-Fe hydrogel microneedle patch developed in this study combines strong wet adhesion, sufficient mechanical strength, pseudomembrane penetration capability, and pH-responsive riboflavin release. This system effectively improves drug bioavailability at ulcer sites and significantly accelerates tissue repair in RAS models. The RF@DAHA-Fe MN platform therefore represents a promising localized therapeutic strategy for recurrent aphthous stomatitis.

Acknowledgements

This work was supported by the National Science and Technology Council (NSTC), Taiwan, under grant number NSTC 114-2314-B-214-006-MY2. and NSTC 113-2221-E-214 -003 -MY3.




Figure 1. Design and therapeutic performance of RF@DAHA-Fe hydrogel microneedle patch for RAS treatment.

References

[1]Jones K., Klein O. Oral epithelial stem cells in tissue maintenance and disease: the first steps in a long journey. *Int J Oral Sci* 2013; 5; 121-129.
[2]Wood N.K., Goaz P.W. Differential diagnosis of oral lesions. *Mosby-Year Book* 1991; 287-302.
[3]Gill H.S., Prausnitz M.R. Coated microneedles for transdermal delivery. *J Control Release* 2007; 117; 227-237.

D2 – P034

Connecting siRNA release kinetics to cellular silencing in chitosan–PEI polyplexes

Dumolard S.[1], Robin P.[1], Spinozzi S.[2], Diviani D.[2], Gerber-Lemaire S.[1]
[1]Institute of Chemical Sciences and Engineering, EPFL, Lausanne, Switzerland; [2]Dept. of Biomedical Sciences, UNIL, Lausanne, Switzerland

Introduction

Polymeric carriers for siRNA delivery offer precise control over molecular weight, architecture, and charge density. However, translating physicochemical properties into predictable intracellular silencing remains a central challenge in biomaterials-based gene delivery.[1] In particular, the relationship between polyplex stability, cell internalization, siRNA release behavior, and functional gene knockdown is poorly defined. This study aims to determine whether distinct siRNA release profiles, governed by systematic structural variations within a chitosan–PEI copolymer platform, translate into predictable cellular silencing outcomes and mechanistic differences in intracellular processing.

Materials and Methods

We synthesized a library of chitosan–PEI copolymers with controlled variations in molecular weight, chemical spacers, branching, and charge density (Figure 1A). Representative polymers were screened to generate siRNA polyplexes and characterized by DLS (size, polydispersity, count rate variations), ζ-potential and encapsulation efficiency. Release kinetics were then quantified using a competitive displacement assay against heparin (Figure 1B), enabling classification into three distinct profiles. These formulations are currently evaluated in HEK293T-GFP cells to assess functional silencing using time-resolved fluorescence microscopy (IncuCyte). To gain mechanistic insight, chloroquine rescue experiments are incorporated to probe endosomal escape limitations, together with quantitation of internalized siRNA (RT-qPCR) to distinguish internalization from intracellular release barriers.

Results

Structural tuning of the chitosan–PEI platform generated distinct encapsulation–release behaviors, *i.e.* highly stable/non-releasing systems, controlled-release systems, and burst-release systems (Figure 2). Polymers with the highest branched PEI (BPEI) content (P1) produced highly stable polyplexes, indicating strong electrostatic association. In contrast, polymers incorporating linear PEI (P2) generally formed polyplexes with reduced colloidal stability. Both systems coincided with poor siRNA release in displacement assays. Reduced charge density within branched architectures of lower molecular weight (P3) induced a progressive transition to controlled release profiles, while the lowest BPEI content (P4) resulted in burst-release behavior. Based on these predefined release categories, we hypothesized that the most stable polyplexes will exhibit limited silencing due to restricted intracellular release, whereas burst-release systems may show reduced activity due to premature extracellular siRNA dissociation. Polyplexes exhibiting controlled release are expected to achieve measurable GFP knockdown. The cellular assay is designed to validate these structure–release–function relationships and identify mechanistic bottlenecks in intracellular delivery.

Conclusion

This study connects defined polymer design parameters to measurable cellular outcomes within a chitosan–PEI siRNA delivery platform. The proposed approach represents a first step toward improving preclinical evaluation through standardized, mechanistically informed testing. Such systematic structure–properties–function mapping may support more rational biomaterial development and ultimately facilitate clinical translation.




Figure 2. Experimental design. (A) Schematic representation of the chitosan-PEI copolymer platform with defined structural variation based on different PEI architecture and molecular weight, as well as chemical spacer to graft PEI. (B) Schematic representation of the heparin competition assay. siRNA polyplexes are subjected to an excess of competing heparin, which triggers siRNA decomplexation. The released, accessible fraction of siRNA is quantified by fluorescence detection of intercalated SYBR Gold dye over 48h at r.t. using a plate-reader setup. The release is calculated based on linear fitting of a calibration curve, and normalized by the encapsulation without heparin at each time point.




Figure 3. Competitive displacement of siRNA from chitosan-PEI polyplexes over time, using a heparin-to-siRNA mass ratio (H/P) of two. Representative chitosan-PEI polymers (P1-P4) with defined charged density, branching and molecular weight can be classified into three release profiles: stable/non-releasing systems (P1, P2), controlled-release system (P3) and burst-release system (P4).

References

[1]Porello I., Bono N., Candiani G., Cellesi F. Advancing nucleic acid delivery through cationic polymer design: non-cationic building blocks from the toolbox. *Polymer Chemistry* 2024; 15, 28; 2800-2826.

D2 – P035

Novel protein-nanoencapsulation platforms, overcoming the protein-delivery challenges for protein therapeutic applications

Makwana V.[1], Eerappa R.[2], Giri J.[3*]
[1]Center for Interdisciplinary Programs, Indian Institute of Technology, Hyderabad, Kandi; [2]Dept. of Biotechnology, Indian Institute of Technology, Hyderabad, Kandi; [3]Dept. of Biomedical Engineering, Indian Institute of Technology, Hyderabad, Kandi, Telangana, India

Introduction

Protein therapeutics, including antibodies, vaccines, enzymes, and hormones, represent a rapidly growing market. However, their clinical use is limited by challenges such as short half-life, instability, immunogenicity, degradation, and dependence on cold-chain storage. Protein-based vaccines, in particular, require strict temperature control to maintain stability. Although nano/micro delivery systems can enhance immunogenicity through co-delivery of adjuvants, current strategies typically address stability and delivery separately. To address these limitations, we propose a Hybrid-Matrix Nanoparticle (HMnP) platform, a nanoencapsulation system that stabilizes proteins during storage and processing while enabling high encapsulation efficiency, controlled release, and targeted delivery through a multifunctional core-shell design.

Aim

To design and optimize HMnPs capable of encapsulating and stabilizing sensitive protein biomolecules, preserving their structural integrity and bioactivity under non-refrigerated conditions, and to evaluate their potential as a versatile platform for vaccine and therapeutic protein delivery.

Materials and Methods

We have developed HMnP system- Sugar glass nanoparticles (SGnPs)-the matrix is composed of sugar and Modified Silk Polymer. Silk fibroin was chemically modified using maleic anhydride to form a stabilizing polymer matrix. For nanoparticle fabrication, a model protein was mixed with trehalose and the modified silk polymer to form a homogeneous suspension. This mixture was introduced into a surfactant-organic solvent system to generate a reverse micelle emulsion, followed by flash freezing, solvent removal, and lyophilization to form sugar glass nanoparticles encapsulating the protein. The nanoparticles were then purified to remove residual surfactants and stored for further use.

Results

Sugar glass nanoparticles showed an average size of 169.8 ± 9.91 nm, increasing to 195.3 ± 7.47 nm after protein (Horsh Radish Peroxidase (HRP)) loading, with low PDI and spherical morphology. The formulation achieved 82% encapsulation efficiency and 96% retained enzymatic activity. High encapsulation efficiency (EE) and activity retention (AR) were also observed for Catalase (81.54% EE; 85.6% AR), LDH (Lactate dehydrogenase) (76.75% EE; 91.57% AR), ALP (Alkaline Phosphtase) (81.71% EE; 99.6% AR), and Papain (72% EE; 84.68% AR) (Fig 1). Spectroscopic and cell studies confirmed structural preservation and excellent biocompatibility (Fig 2). The nanoparticles also showed strong stability, retaining ~100% enzyme activity at 4°C and room temperature and >85% activity at 37- 45°C in dried form.

Conclusion

Sugar Glass Nanoparticles (SGnPs) enable efficient protein encapsulation, high activity retention, and strong thermal stability. This platform offers a promising strategy for stabilizing protein therapeutics and reducing cold-chain dependence.

Acknowledgements

I sincerely thank Dr. J. Giri and Dr. R. Eerappa for their guidance, and the Ministry of Education, Government of India, for supporting my doctoral research through the PMRF Scheme.




Fig. 1 A) SEM micrograph of Blank SGnPs and Protein loaded SGnPs. B) Encapsulation efficiency and residual enzymatic activity for multiple model proteins (i: Catalase, ii: Lactate Dehydrogenase (LDH), iii: Alkaline Phosphatase (ALP), vi: Papain) in SGnPs




Fig 2. Live/dead staining of HADF cells treated with various SGnPs Concentrations for 24 and 48 hours, Scale bar: 100 µm

D2 – P036

Development and characterization of tetracycline-loaded dual crosslinked carboxymethyl cellulose-based hydrogels for wound healing applications

Okur Aksu T.[1], Birer A.E. [1,2], Torman Kayalar M.[2], Anaç Şakır İ.[2], Ülker Turan C.[1]

[1]Gebze Technical University, Dept. of Bioengineering, Gebze; [2]Gebze Technical University, Dept. of Materials Science and Engineering, Gebze, Kocaeli, Turkey

Introduction

Skin is the largest organ of the human body and serves as the first protective barrier against environmental threats such as microorganisms, dehydration, and physical trauma. When the skin is injured, a wound healing process begins to repair the damaged tissue. Since ancient times, wound care has been important for supporting skin regeneration. Over time, wound care products have evolved into various wound dressings designed to accelerate healing, protect the wound from external factors, and increase patient comfort. Wound dressings also play an important role in preventing microbial contamination and reducing the need for systemic antimicrobial therapy, especially in chronic wounds. These dressings can be produced in different forms, including fibers, films, and hydrogels.

Hydrogel wound dressings are widely used as advanced wound healing materials because of their ability maintain three-dimensional structures in water and biological fluids. Their hydrophilic nature provides a moist environment that supports healing while enabling the delivery and controlled release of active agents at the wound site [1]. Biopolymer-based wound dressings are particularly advantageous due to their cost-effectiveness, biocompatibility, non-toxicity, and biodegradability. Carboxymethyl cellulose (CMC), a polysaccharide derivative, has been widely reported in the literature for wound dressing applications [2].

Aim

In the present work, CMC-based hydrogels were developed and characterized as a potential drug delivery system for wound healing applications.

Materials and Methods

Based on the study, an experimental design was implemented to identify the optimal hydrogel matrix through mechanical testing. The selected formulation was subsequently used to prepare physically, chemically, and dual-crosslinked hydrogels using citric acid and $CuCl_2$ to enhance structural stability and provide antimicrobial properties. In addition, tetracycline hydrochloride (TCH) was incorporated into the hydrogel matrix as an antibacterial agent. The resulting hydrogels were characterized using mechanical testing, FTIR, TGA, SEM, and EDS analyses. Furthermore, swelling behavior, drug release, and antibacterial activity were evaluated to confirm their structure, composition, and functional performance.

Results

The best formulation was used for further crosslinking experiments. Single- and dual-crosslinked blank and drug-loaded hydrogels were characterized using the previously mentioned methods, and the results confirmed the formation of the hydrogel network and the presence of citric acid, copper, and TCH within the structure. Additionally, antibacterial activity of the hydrogel networks and sustained release behavior of the TCH were verified.

Conclusion

Overall, the developed hydrogels exhibited suitable characteristics for further investigation in potential biomedical applications such as wound dressings and controlled drug delivery systems.

References

[1]Cometa S., Bonifacio M. A., Licini C., Bellissimo A., Pinto L., Baruzzi F., Mattioli-Belmonte M., De Giglio, E. (2021). Innovative eco friendly hydrogel film for berberine delivery in skin applications†. *Molecules* 2021; 26; 16. https://doi.org/10.3390/molecules26164901

[2]Kanikireddy V., Varaprasad K., Jayaramudu T., Karthikeyan C., Sadiku, R. Carboxymethyl cellulose-based materials for infection control and wound healing: A review. *International Journal of Biological Macromolecules* 2020; 164; 963–975. https://doi.org/10.1016/**j.ijbiomac.2020.07.160**

Acknowledgments

The authors gratefully acknowledge TUBITAK for supporting scientific mobility through the 2224-A Grant Program.

D2 – P037

Synergistic antimicrobial delivery from hydrogel-grafted endotracheal tubes to prevent ventilator-associated pneumonia

Wylie M.P., Ayasreh R., McCoy C.P
School of Pharmacy, Queen's University Belfast, Belfast, UK

Introduction

Ventilator-associated pneumonia (VAP) is among the most prevalent nosocomial infections in intensive care, with mortality rates of 20–76%[1]. Endotracheal tubes (ETTs), typically made of polyvinyl chloride (PVC), are prone to microbial biofilm formation, thereby facilitating VAP development[2]. Hydrogel-based coatings offer promise for sustained antimicrobial delivery; however, poor adhesion to PVC results in coating delamination under mechanical stress [3]. This study reports a multilayer coating strategy that enables covalent grafting of poly(2-hydroxyethyl methacrylate-co-methyl methacrylate) (p(HEMA-co-MMA)) hydrogels onto silver-thiol-functionalised PVC, combined with the co-delivery of the synergistic antimicrobials levofloxacin (LEV) and benzalkonium chloride (BAK), for long-term prevention of VAP.

Materials and Methods

A metallic silver layer was deposited on PVC substrates (Ag-PVC), followed by allyl mercaptan (AM) functionalisation to generate polymerisable surface groups (AM-Ag-PVC). Three p(HEMA-co-MMA) hydrogel formulations (HEMA:MMA ratios of 100:0, 90:10, and 75:25) were photopolymerised onto AM-Ag-PVC surfaces. Surfaces were characterised by SEM, contact angle goniometry, and ATR-FTIR. Coating adhesion was evaluated under mild (14-day immersion at 37 °C, 100 rpm) and extreme (30 min sonication) conditions. LEV and BAK were post-loaded into grafted p(HEMA-co-MMA) coatings and *in vitro* release monitored over 14 days in PBS (pH 7.4). Synergistic interactions were assessed via checkerboard microdilution assay. Bacterial adherence of *Staphylococcus aureus* (ATCC 29213) and *Pseudomonas aeruginosa* (ATCC 27318) was assessed over 14 days with daily re-challenge, and cytotoxicity was evaluated by MTT assay.

Results

Covalently grafted hydrogels retained >85% coating mass over 14 days under mild conditions, compared to <15% for non-grafted controls and all hydrogel-grafted surfaces exceeded the 70% cell viability threshold (ISO 10993-5), confirming biocompatibility. Dual-loaded hydrogels exhibited sustained co-release of LEV and BAK over 14 days, with intermolecular interactions moderating burst release and prolonging drug availability. Checkerboard assays confirmed strong antibacterial synergy against *S. aureus* and *P. aeruginosa*. Dual-loaded hydrogel-grafted surfaces completely inhibited viable adherence of both species across all time points over 14 days of repeated daily challenge, outperforming mono-loaded systems (Figure 1).




Figure 1. Viable adherence of *S. aureus* (a-c) and *P. aeruginosa* (d-f) to different surface-modified PVC materials after incubation at 37 °C for 4 h, 24 h, 7 days, and 14 days. (a, d) Bacterial adhesion to PVC, Ag-PVC, AM-Ag-PVC, and unloaded polymer-coated AM-Ag-PVC: p[HEMA]-AM-Ag-PVC, p[HEMA-co-MMA, 90:10]-AM-Ag-PVC, and p[HEMA-co-MMA, 75:25]-AM-Ag-PVC. (b, e) Adhesion on the same polymer-coated AM-Ag-PVC surfaces loaded with either LEV or BAK. (c, f) Bacterial adhesion on polymer-coated AM-Ag-PVC surfaces loaded with a combination of Levo and BAK. Compared to unmodified PVC, data are presented as mean log (CFU/mL) ± SD (n = 5).

Conclusion

A covalently grafted hydrogel coating strategy for PVC-based ETTs was developed, enabling sustained co-delivery of synergistic antimicrobials and complete prevention of bacterial colonisation for up to 14 days, matching typical intubation durations. This approach addresses key limitations of current ETT coatings, including coating delamination and limited antimicrobial longevity, and has translational potential to reduce VAP incidence in mechanically ventilated patients.

References

[1]Howroyd F., Chacko C., MacDuff A., et al. Ventilator-associated pneumonia: pathobiological heterogeneity and diagnostic challenges. *Nature Communications* 2024; 15; 6447.

[2]Diaconu O., Siriopol I., Poloșanu L.I., Grigoraș I. Endotracheal Tube Biofilm and its Impact on the Pathogenesis of Ventilator-Associated Pneumonia. *J Crit Care Med* 2018; 4(2); 50–55.

[3]Wylie M.P., Li J., Murphy G., et al. Development of antibacterial coatings for endotracheal tubes with enhanced antibacterial release properties through combined antibiotic loading. *J Pharm Pharmacol* 2025; 78(1).

D2 – P038

Electrospun biodegradable glaucoma stents for controlled local delivery of tacrolimus and Y-27632

He B.[3], Forouharshad M.[1], Parikh K.S.[1,2]
[1]Center for Nanomedicine, Wilmer Eye Institute, Dept. of Ophthalmology, Johns Hopkins University School of Medicine; [2]Center for Bioengineering Innovation & Design, Dept. of Biomedical Engineering, Johns Hopkins University; [3]Dept. of Neuroscience, Johns Hopkins University, Baltimore, USA

Introduction

Long-term success of glaucoma drainage devices is limited by postoperative inflammation and fibrotic encapsulation that compromise aqueous outflow. We aimed to develop electrospun biodegradable glaucoma stents as local drug-delivery platforms and determine how polymer choice, coating, and layered architecture govern delivery of anti-inflammatory tacrolimus and the Rho-associated protein kinase (ROCK) inhibitor Y-27632.

Materials and Methods

Poly(lactic acid) (PLA)- and polydioxanone (PDO)-based drug-eluting stents were fabricated by electrospinning. Morphology was assessed by scanning electron microscopy. Drug loading and in vitro release were quantified by high-performance liquid chromatography. Because uncoated Y-27632 constructs showed marked burst release, additional poly(caprolactone-co-glycolide) (PGC)-coated variants (3–12 coating cycles) and layered PLA stents were engineered to modulate early release and increase payload. Release profiles were compared using two-way and repeated-measures analyses of variance (ANOVA).

Results

Tacrolimus screening supported PLA as the more favorable base polymer, with slower and more stable release than PDO. For Y-27632, uncoated PLA and PDO stents released 85.7 ± 1.4% and 99.2 ± 0.3%, respectively, within 1 h. PGC coating markedly attenuated this burst release in both polymers (two-way ANOVA, interaction $p < 0.0001$ for both); 9–12 coating cycles reduced 1 h release to 1.8–2.7% in PLA and 2.5–3.6% in PDO. PLA also retained Y-27632 better at 24 h, with 9- and 12-cycle coatings releasing 17.8 ± 3.4% and 17.8 ± 4.4%, versus 37.0 ± 6.5% and 30.6 ± 16.8% for similarly coated PDO stents. Coating had limited effect on total loading, although higher coat numbers increased construct variability. To further enhance payload, multi-structure PLA stents were compared with single-structure designs. Multi-structure stents yielded greater cumulative Y-27632 release, consistent with higher loading, while preserving similar overall release kinetics (repeated-measures ANOVA, no time × configuration interaction, $p = 0.1509$; main effect of configuration $p < 0.0001$), albeit with larger diameter.

Conclusion

PLA emerged as the most favorable base material for biodegradable electrospun glaucoma stents. PGC coating substantially reduced, but did not eliminate, burst release of hydrophilic cargo, and layered architectures increased payload while preserving release behavior. These findings support electrospun glaucoma stents as a tunable biomaterials platform for local anti-inflammatory and anti-fibrotic therapy after glaucoma surgery and justify next-stage studies of mechanical performance, bioactivity, and glaucoma-relevant function.

D2 – P039

A versatile mesoporous silica nanoparticle platform for pro-regenerative protein delivery

Schimmel J.S.[1], Zhang X.[1], Dijkgraaf I.[2], van Herck S.[1], van Rijt S.[1]
[1]IBE, MERLN; [2]CARIM, Maastricht university, Maastricht, The Netherlands

Introduction

Growth factors and other bioactive proteins play key roles during the various phases of tissue regeneration by regulating cell recruitment, proliferation, and differentiation. However, the therapeutic use of proteins is hampered by their low stability, short half-life, and loss of bioactivity after delivery. Therefore, developing delivery strategies that preserve protein activity and enable sustained presentation at the target site remains a major challenge. Nanomaterial-based platforms offer promising opportunities to overcome challenges with traditional protein delivery methods. Among these materials, mesoporous silica nanoparticles (MSNs) are promising due to their high surface area, tunable pore structure, and versatile surface chemistry, which enable efficient surface functionalization and cargo loading. These features make MSNs an ideal platform for the controlled attachment and presentation of bioactive proteins.

In this project, MSNs are functionalized with a linker that enables site-specific binding of native proteins via their N-terminus, allowing stable immobilization while preserving biological activity. Combined with the intrinsic bioactivity of MSNs, this strategy enables the development of bifunctional nanomaterials that provide both instructive material cues and controlled protein delivery.

Aim

This project aims to develop an MSN platform for the site-specific attachment and sustained delivery of native bioactive proteins to create bifunctional biomaterials for tissue regeneration.

Materials and Methods

MSNs are synthesized via a sol-gel condensation reaction and functionalized on the surface with thiol groups. Thiol-functionalized MSNs are modified by attaching a linker that allows N-terminal conjugation of proteins. By using a model bioactive protein such as the growth factor bone morphogenetic protein 2 (BMP-2), osteogenesis could be enhanced. The resulting protein-functionalized nanoparticles are characterized in vitro to assess the short-term and long-term osteogenic bioactivity and, therefore protein stability of the modified MSNs platform.

Results

Results show successful MSN synthesis, which contains thiol groups at the surface level. We show the ability of the protein binding linker to successfully functionalize onto thiol groups of the MSNs. We show protein binding to the linker, opening up the potential to enable the binding of any bioactive protein. To prolong shelf life, we show that bound protein remains stable during lyophilization.

Conclusion

This MSN platform shows potential in promoting osteogenesis over prolonged periods of time.

Acknowledgements

This study was funded by the European Research Council (ERC CoG Nano4Bone).

D2 – P040

Leveraging the mucoadhesive characteristics of microparticles to improve drug delivery systems for pseudomonas keratitis management

Gallagher A.G.[1], Englisch C.N.[2], Wadood N.A.[2,3], Pätzold, L.[2], Rillo-Albert A.[1], Krasteva-Christ G.[3], Bischoff M.[2], Pandit A[1]

[1]CÚRAM Research Ireland Centre for Medical Devices, University of Galway, Galway, Ireland; [2]Institute for Medical Microbiology and Hygiene, Saarland University, Homburg, Germany; [3]Institute of Anatomy and Cell Biology, Saarland University, Homburg, Germany

Introduction

Antibiotic eye drops are the current standard of care for treating eye infections; however, they are highly inefficient with up to 95% of therapeutic lost in seconds due to ocular clearance mechanisms. Treatment requires highly concentrated formulations and frequent dosing regimens which can lead to hospitalisations if not adhered to. Frequent administration is inconvenient, uncomfortable and can result in issues such as eye irritation, making adherence to the treatment regimen difficult with non-compliance ultimately threatening vision. Furthermore, there is potential for antimicrobial resistance (AMR) developing from overuse of antibiotics. This study investigated a thiolated γ-polyglutamic acid-co-ε-polylysine (pγE-co-pεK) microparticle drug delivery system as a means of reducing the amount of antibiotics administered to the cornea whilst improving the overall treatment efficacy.

Materials and Methods

The pγE-co-pεK microparticle systems physicochemical properties were investigated utilising microscopy and SEM, size, zeta potential and polydispersity via DLS, antibiotic loading and release, in vitro antimicrobial efficacy against *E. coli* (ATCC 8739), *B. subtilis* (ATCC 6051) and *S. epidermidis* (ATCC 12228) and in vitro cytotoxicity towards human corneal epithelial cells. Therapeutic efficacy was investigated in a murine (C57BL/6N) *Pseudomonas* PA54 keratitis model with antibiotic application every 8 h for 3 days.

Results

The microparticle (MPs c 2) properties were optimised to produce a spherical (2.47 µm ± 0.40), monodispersed mucoadhesive particle system (Figure 1) that delivers therapeutic doses of antibiotics over 48 h. The particle system was cytocompatible with human primary corneal epithelial cells after 96 h of incubation, while maintaining antimicrobial efficacy in vitro. Mucoadhesion was 6-fold greater than non-thiolated particles (MPs) after incubation with mucin over 24 h. Thiolated pγE-co-pεK microparticles with a meropenem cargo achieved a sterile cornea and nearly complete resolution of *Pseudomonas* keratitis in a murine model after 72 h compared to the outcomes achieved with conventional antibiotic therapy (Figure 2).

Conclusion

These results demonstrate that thiolated pγE-co-pεK microparticles loaded with meropenem can provide a mucoadhesive drug delivery system with greater efficacy in treating *Pseudomonas* keratitis compared to the antibiotic alone.

Acknowledgements

This research was funded by the European Union's Horizon 2020-The EU Framework Programme for Research and Innovation under grant agreement No. 713654 and an Enterprise Ireland Commercialisation Fund (CF-2021-1837). N.A.-W, M.B. and G.K.-C. acknowledge financial support by the UdS-HIPS Tandem Initiative. G.K.-C. also acknowledges financial support by DFG KR 4338/1-2.




Figure 1: Light microscopic image of pγE-co-pεK microparticles in aqueous solution, *Scale bar = 10 µm* **(a)**. SEM image of a single pγE-co-pεK microparticle, *Scale bar = 3 µm* **(b)**. Particles attached to mucin at 15 min, 2 h, and 24 h following incubation at 35 °C **(c)**.




Figure 2: Keratitis clinical scores were observed over 3 days **(b)**. *Pseudomonas* CFU data were obtained from infected eyes **(c)**. Leukocyte counts in tissue homogenates at three days post-infection **(d)**.

References

[1]Dos Santos G. A., et al. Besifloxacin liposomes with positively charged additives for an improved topical ocular delivery. *Scientific Reports* 2019; 10(1); *19285*. doi: 10.1038/s41598-020-76381-y

D2 – P041

Drug-eluting stents coated with electrospun nanofibers for the treatment of calcified arteries

Boisseuil-Nissen N.[1], Roisin S.[2], Delplanque L.[1], Staelens J-N.[1], Maton M.[2], Hildebrand F.[2], Sobocinski J.[2,3], Blanchemain N.[2], Martel B.[1], Tabary N.[1]
[1]University of Lille, CNRS, INRAE, Centrale Lille, UMR 8207 – UMET – Unité Matériaux et transformations; [2]University of Lille, INSERM, U1365 - Advanced Drug Delivery Systems, Lille, France; [3]University of Lille, Institut Coeur Poumon, Hospital Center University of Lille, Lille, France

Introduction

Calcified arterial disease is a cardiovascular disorder characterized by calcium deposits on the arterial wall. This reduces the internal diameter of the blood vessel, compromising or even obstructing blood flow, a condition known as stenosis. Peripheral Arterial Disease (PAD) leads to limb amputation in up to 30% of cases within the year. Extensive calcification in below-the knees arteries is associated with a much higher risk of stent placement failure. All-trans-retinoic acid (ATRA) emerged as a promising drug to decrease calcium deposition and limit restenosis[1]. To enhance its efficacy, local delivery is crucial. ATRA will be incorporated into electrospun silk fibroin (SF) mats designed to cover the stent. Electrospun mats exhibit a highly porous structure, offering advantages for controlled drug release. SF, being biocompatible and flexible, is particularly well-suited for stent coatings.

Materials and Methods

SF was prepared from *Bombyx mori* cocoons via degumming treatment, dissolution in LiBr then dialysis. Fibroin solutions for electrospinning were prepared either in formic acid or water, and their viscosity was measured. The morphology of the electrospun mats and fibers diameters were analyzed using scanning electron microscopy (SEM). Mechanical properties, particularly the flexibility required for stent crimping and deployment, was also evaluated. Cyclodextrin was used for enhancing ATRA solubility in water thanks to host-guest complexation that was investigated by UV spectrophotometry.

Results

Complexation with HPbCD (hydroxypropyl-b-cyclodextrin) enhances ATRA solubility in PBS by more than three orders of magnitude, reaching milligrams-per-liter range. Electrospinning of 14% w/v SF solution in formic acid with 0.5% PEO produced uniform mats with fibers around 500 nm in diameter. When PEO was omitted, thinner fibers (~230 nm) were obtained but the mat presented more defects. An aqueous SF solution (14% w/v) adjusted to pH 10 using NaOH was successfully electrospun, highlighting water as a potential greener and safer solvent alternative (Fig.1). After electrospinning, ethanol treatment converted SF's structure from α-helix to β-sheet, evidenced by FTIR analysis, enhancing its stability in aqueous environments such as blood.

Conclusion

This study provided promising outcomes for electrospinning SF in a biocompatible solvent followed by a reduction of its aqueous solubility for future use on a stent. The effectiveness of complexation has shown great interest in further incorporating ATRA into the mat.

The authors would like to thank ANR for funding this work through ATRASTENT project. (Projet-ANR-25-CE17-7408).




Figure 1 : SEM image of electrospun mats. a) Fibroin + 0.5% PEO in formic acid b) Fibroin in formic acid c) Fibroin in water pH 10.

References

[1] Rosa, M., et al. *Circulation* 2025; 151 (18); 1329–1341.

D2 – P042

Enzyme-responsive mPEG-*b*-polyester vesicles as a drug delivery platform

Schandl S., Cusick N., Schönherr H.
[1]Physical Chemistry I & Research Center of Micro- and Nanochemistry and (Bio)Technology (Cμ), Dept. of Chemistry and Biology, School of Science and Technology, University of Siegen, Siegen, Germany

Introduction

Skin wounds are highly vulnerable to bacterial invasion, which can cause chronic infection and impair tissue regeneration. Standard treatment involves washing and physically removing bacteria, while dissolved antibiotics often lose effectiveness due to dilution in wound fluid or systemic distribution. Because antibiotic efficacy depends on maintaining a high local concentration, issues with stability, delivery, and systemic spread can reduce their impact. Polymersomes offer protection of encapsulated drugs and reduce unwanted diffusion. Especially, polyester-based amphiphilic block copolymers can be engineered to respond to specific stimuli, offering a more targeted approach.

Aim

This study aims to investigate the potential of amphiphilic block copolymers comprising FDA-approved polymer blocks for the self-assembly of stimulus-responsive vesicles for triggered drug release. Monomethoxy-terminated poly(ethyleneglycol) (mPEG-OH) was used as the hydrophilic headgroup with poly(lactic acid), and poly(ε-caprolactone) at various chain lengths as hydrophobic tails.

Materials and Methods

Amphiphilic block copolymers were produced by coordinative ring-opening polymerization using mPEG-OH as macroinitiator, the corresponding lactone for the targeted polyester and $Sn(Oct)_2$ as catalyst. Vesicles were produced by the solvent shift method manually and using a micromixer microfluidic chip design. The polymers were dissolved in THF, and the solvent quality for the hydrophobic block was reduced by the addition of an equal volume of phosphate-buffered saline (PBS). Nile red and fluorescein were chosen as model compounds for hydrophobic and hydrophilic drugs, respectively, due to their fluorescent properties. DLS, FESEM and zeta potential of these self-assemblies were measured. Enzymatic digestion was investigated using model lipase and proteases.

Results

All tested polymer compositions showed the ability to self-assemble upon solvent shift. Vesicle size increased with increasing hydrophobic block length for all tested polymers. PLA as the hydrophobic block showed slightly lower solubility and broader distribution in vesicle size with multimodal size distribution, while PCL showed narrower size distributions around hydrodynamic radii of ~150 nm. Enzymatic digestion revealed enzyme-specific degradation, where PLA was digested by Proteinase K, while PCL was digested by Lipase.

Conclusion

mPEG-*b*-polyester amphiphilic block copolymer assemblies show enzyme-specific degradation, due to high selectivities of the investigated enzymes. For future applications, self-assemblies of different composition could be combined for targeted and stimuli-responsive treatment of bacterial infections in wound environments. Vesicles could be delivered in suspension or immobilised within a support matrix to reduce systemic drug concentration and unwanted side effects on the patient.

Acknowledgements

This project is funded by the European Union, through the Horizon Europe research and innovation programme under the Grant Agreement no. 101177924 (INJECTHEAL).

D2 – P043

Targeting glioma-neuron synaptic communication: A gene therapy perspective

Al-Hajaj N.[1], Hannan H.[2], Reem K.[3] ,Ghaleb H.[4]
[1]Dept. of Biosciences and Bioengineering, American University of Sharjah; [2]Dept. of Biosciences and Bioengineering, American University of Sharjah; [3]Dept. of Biology, Chemistry and Environmental Sciences, American University of Sharjah; [3]Dept. of Chemical and Biological Engineering, American University of Sharjah, Sharjah, U.A.E

Introduction

Glioblastoma multiforme (GBM) remains the most aggressive primary brain malignancy, characterized by extensive invasion, therapeutic resistance, and poor patient survival despite standard treatment with surgical resection, radiotherapy, and temozolomide chemotherapy. Recent advances in cancer neuroscience have transformed our understanding of glioblastoma biology by demonstrating that neurons actively contribute to tumor progression through both synaptic and non-synaptic communication pathways. These interactions create a tumor-supportive microenvironment that promotes proliferation, invasion, neural network remodeling, and treatment resistance. Consequently, neuron–glioma communication has emerged as a promising therapeutic target for the development of innovative treatment strategies.

Aim

This review aims to examine the mechanisms underlying neuron–glioma communication in glioblastoma progression and to evaluate emerging therapeutic approaches designed to disrupt tumor-promoting neural signaling. An emphasis is placed on identifying molecular targets and exploring the potential of gene-silencing technologies as future therapeutic interventions.

Materials and Methods

A comprehensive literature review was conducted to evaluate current evidence regarding neuron–glioma interactions within the glioblastoma tumor microenvironment. Studies investigating neurogliomal synapses, neurotransmitter-mediated signaling, gap junction communication, tumor microtubes, neuronal activity modulation, and emerging therapeutic strategies were critically assessed. Experimental findings derived from electrophysiological studies, electron microscopy, optogenetics, co-culture models, molecular biology techniques, and pharmacological interventions were analyzed to identify key mechanisms driving tumor progression.

Results

Current evidence demonstrates that glioblastoma cells establish functional communication networks with neurons through both direct synaptic connections and indirect signaling pathways. Neurotransmitters including glutamate, gamma-aminobutyric acid (GABA), serotonin, and dopamine regulate tumor proliferation, migration, invasion, and survival. Neurogliomal synapses, gap junctions, and tumor microtubes facilitate electrical and molecular communication that promotes tumor growth and therapeutic resistance. Several therapeutic strategies targeting these pathways have demonstrated promising preclinical outcomes, including AMPA receptor antagonists, neuroligin-3 inhibition, gap junction blockade, and neuromodulation approaches. Among emerging strategies, targeting calcium-dependent signaling pathways represents a particularly attractive approach due to their central role in neuron–glioma communication. Gene-silencing platforms, including calcium-siRNA nanocomplexes, offer a novel opportunity to selectively inhibit signaling pathways involved in tumor-promoting neural interactions and may overcome limitations associated with conventional therapies.

Conclusion

Neuron–glioma communication represents a critical driver of glioblastoma progression and an underexplored therapeutic vulnerability. Disrupting synaptic transmission and calcium-mediated signaling pathways may provide new opportunities to overcome treatment resistance and improve clinical outcomes. Future research should focus on translating gene-delivery and gene-silencing strategies into clinically relevant therapies capable of targeting tumor-promoting neural signaling within the glioblastoma microenvironment.

D2 – P044
Degradable HSN as intracellular protein delivery system

Xu J., Zhong L., van Rijt S.
Dept. of Instructive Biomaterials Engineering, MERLN Institute for Technology-Inspired Regenerative Medicine, Maastricht University, Maastricht, The Netherlands

Introduction

Efficient intracellular delivery of biomacromolecules such as proteins and nucleic acids remains a major challenge in nanomedicine due to membrane barriers, cargo instability, and limited control over loading and release. Mesoporous silica nanoparticles (MSN) have been widely investigated as nanocarriers because of their high surface area, tunable pore structures, and versatile surface functionalization capabilities. These properties allow adsorption of diverse therapeutic molecules and have supported numerous applications in drug, protein, and gene delivery systems. However, the pore-confined loading mechanism of MSN restricts the encapsulation of large biomacromolecules and may leave cargos partially exposed to the external environment, resulting in limited loading capacity and insufficient protection against degradation. Hollow silica nanoparticles (HSN), featuring an internal cavity enclosed by a permeable silica shell, enable volume-driven encapsulation with increased loading capacity and improved cargo protection. This study aims to develop degradable hollow silica nanoparticles as intracellular protein delivery platforms and to explore ion doping to create multifunctional silica matrices.

Materials and Methods

Hollow silica nanoparticles (HSN) were synthesized via an adapted reverse microemulsion method. Metal ions were incorporated into the silica matrix to modulate degradation and cargo release. FITC-labelled HSN loaded with Texas Red–labelled bovine serum albumin (BSA) were incubated with human mesenchymal stem cells (hMSCs), and fluorescence microscopy was used to assess cellular uptake and intracellular localization.

Results

HSN with a well-defined core–shell structure were successfully synthesized, providing a large internal cavity for the encapsulation of biomacromolecules (Fig. 1a–e). Compared with conventional MSNs, this hollow architecture significantly improved protein loading capacity (Fig. 1f). Furthermore, incorporation of metal ions into the silica framework introduced structural defects within the matrix increasing degradation rate. To evaluate intracellular delivery performance, FITC-labelled HSN loaded with Texas Red–labelled albumin were incubated with hMSCs. Fluorescence microscopy revealed efficient cellular uptake of the nanoparticles and the protein cargo (Fig. 2). The co-localization of fluorescence signals with cytoskeletal staining confirmed that the nanoparticles were internalized and distributed within the cellular environment, indicating successful intracellular transport and release of the protein cargo. Together, these results demonstrate that HSN provide an efficient platform for intracellular delivery of biomacromolecules.

Conclusion

In this work, degradable FITC-labelled HSN were developed as an intracellular protein delivery platform. Ion doping enabled modification of the silica matrix, providing opportunities to tune nanoparticle degradation and cargo release behavior. These results highlight the potential of HSN as versatile carriers for intracellular protein delivery.




Figure 1 Characterization of HSN family. (a): HSN; (b): FITC-labelled HSN loading Texas red-labelled BSA; (c-e): HSNs doped by Ca^{2+}, Zn^{2+} and Sr^{2+}; (e): fluorescence intensity of FITC and Texas red from sample b




Figure 2 Cell uptake of FITC-labelled HSN (loading Texas red BSA) by co-localization using fluorescent microscopy. HSN at 200µg/mL were incubated with hMSC for 24 h. a Representative fluorescence microscopy images of hMSC stained with DAPI, phalloidin 647 and localization of HSN (green) and BSA (red) is shown in merged images. Scale bars are 20 µm.

D2 – P045

Process optimization of flash nanoprecipitation for lignin nanoparticle synthesis

Oliveira B., Calvo-Chica L.E., Miguel S.P., Ribeiro M., Coutinho P., Moreira A.F.
BRIDGES—Biotechnology Research Innovation Design of Health Products, Polytechnic Institute of Guarda, Guarda, Portugal

Introduction

Lignin, the main by-product of the pulp and paper industry, is the second most abundant renewable biopolymer worldwide. Developing value-added applications for lignin recovered from pulping waste streams is of growing economic and environmental relevance. The fabrication of uniform lignin nanoparticles has recently gained attention due to their antioxidant properties, structural versatility, and biodegradability. This work investigates the production of lignin-based nanoparticles for drug delivery, aiming to support the development of sustainable systems capable of controlled release and improved therapeutic efficacy.

Aim. Optimize the flash precipitation technique for the production of lignin-based nanoparticles based on solvent and anti-solvent influence on physicochemical properties and drug loading performance.

Materials and Methods

Lignin was recovered from black liquor through controlled acidification with hydrochloric or sulfuric acid, followed by centrifugation, washing, and drying. Nanoparticles were produced via flash nanoprecipitation, testing different solvents and anti-solvents, and evaluated by dynamic light scattering (DLS) to determine particle size, polydispersity index (PDI), colloidal stability, and drug loading capacity.

Results

Lignin recovery was achieved by the acidification from pH 9 to 3, with higher recovery yields at lower pH values, due to decreased solubility and stronger hydrophobic interactions. The resulting material was obtained as a fine dark-brown powder. UV–Vis spectra displayed a characteristic absorption band near 210 nm and a secondary feature around 280 nm, consistent with aromatic π–π* transitions. FTIR analysis confirmed preservation of the aromatic lignin structure, with only minor variations in hydroxyl and carbonyl regions, particularly in sulfuric-acid-treated samples.

Flash nanoprecipitation revealed clear influences of both solvent (e.g., ethanol, methanol, and acetone) and anti-solvent (water, phosphate-buffered saline, citrate buffer) on nanoparticle size and PDI. Particle sizes ranged from 11–620 nm, and PDI values from 0.048–0.349. Drug loading showed higher potential for hydrophobic small molecules (e.g., IR820). In vitro assays using normal human dermal fibroblasts confirmed high cytocompatibility of all formulations, maintaining viability above 85%.

Conclusion

Recovered Kraft lignin is a promising and sustainable precursor for nanoparticle fabrication through flash nanoprecipitation. The method enables rapid supersaturation and controlled nucleation, producing homogeneous lignin nanoparticles with tunable size and low polydispersity, supporting their potential use in drug delivery applications.

Acknowledgements

The authors gratefully acknowledge Biotek S.A. for supplying raw material samples. This work was supported by national funds from FCT—Foundation for Science and Technology (Project 2023.13669.PEX., UID/06407/2025, and UID/PRR/06407/2025, and 2025.09299.EI).

D2 – P046

Nanocarrier for peptide-based cervical cancer therapeutics: Cytotoxicity evaluation of nisin towards lignin nanoparticle delivery

Swekcha S.[1], Kirthanashri S.V.[1], Pati N.B.[1], Nayak U.Y.[2], Joshi A.S.[1]
[1]Dept. of Biotherapeutics Research, Manipal Academy of Higher Education, Manipal; [2]Dept. of Pharmaceutics, Manipal College of Pharmaceutical Sciences, Manipal Academy of Higher Education, Manipal, Karnataka, India

Introduction

Peptide-based therapeutics are increasingly recognized as promising agents for cancer treatment due to their high specificity and biological activity. However, their therapeutic application is often limited by poor stability, rapid enzymatic degradation, and reduced bioavailability in physiological environments. Natural biomaterial-based nanocarriers offer an effective strategy to improve peptide stability, enhance cellular delivery, and enable controlled therapeutic release. Lignin, an abundant aromatic natural biopolymer derived from plant biomass, has recently emerged as a sustainable material for nanoparticle fabrication because of its biodegradability, antioxidant properties, and ability to form stable nanostructures. Nisin A, a lantibiotic antimicrobial peptide produced by *Lactococcus lactis*, has demonstrated emerging anticancer activity. However, its potential as an anticancer therapeutic and its integration into biomaterial-based delivery systems remain underexplored.

Aim

This study aims to investigate the cytotoxic and mechanistic effects of nisin A in cervical cancer cell lines as a foundation for the development of lignin-based nanoparticle delivery systems.

Materials and Methods

The anticancer activity of nisin was evaluated in cervical cancer cell lines (HeLa and SiHa). Cell viability following peptide treatment was assessed using the MTT assay after 24-hour incubation. Cellular viability and membrane integrity were further examined using Live/Dead assay. To explore the mechanism underlying the observed cytotoxic effects, cell cycle distribution was analyzed following peptide treatment.

Results

Nisin treatment resulted in a dose-dependent reduction in cervical cancer cell viability, as determined by the MTT assay, with cell viability decreasing to below 50% at 75 µg/ml after 24 hours of exposure. As shown in Figure 1, Live/Dead staining confirmed increased cellular death following peptide treatment. Figure 2 demonstrated analysis revealing alterations in cell cycle progression, suggesting that nisin A may influence cellular proliferation pathways.

Conclusion

The present study demonstrates the anticancer potential of nisin in cervical cancer cell lines and provides a biological basis for its further development as a peptide therapeutic. Ongoing work focuses on the development and optimization of lignin-based nanoparticles for efficient encapsulation and controlled delivery of nisin. These findings provide a rationale for incorporating nisin into lignin nanocarriers to enhance peptide stability and therapeutic delivery.





Figure 1. Live-Dead assay using calcein-AM and ethidium homdimer-1 on SiHa cell line after 24H treatn i s.




ESB
2026

D2 – P047

Production of next-generation polymeric nanoparticles with thiosemicarbazone metal complex derivatives and investigation of their anticancer properties

Ozker P.[1], Ocal S.[1], Karaca Balta D.[1], Temel B.A.[2], Temel G.[3]
[1]Dept. of Chemistry, Yildiz Technical University, Istanbul; [2]Dept. of Pharmaceutical Chemistry, Faculty of Pharmacy, Bezmialem Vakif University, Istanbul; [3]Dept. of Polymer Material Engineering, Faculty of Engineering, Yalova University, Yalova, Türkiye

Introduction

Cancer remains a significant global health challenge characterized by uncontrolled cell proliferation and high mortality rates. Although conventional chemotherapy is widely used, its efficacy is often limited by systemic toxicity and the emergence of drug resistance. Metal-based drugs, particularly thiosemicarbazone derivatives, have emerged as promising anticancer agents due to their structural stability and potent biological activities. Additionally, curcumin, a natural polyphenol, exhibits remarkable antioxidant and antitumor properties but suffers from poor aqueous solubility and low bioavailability. Single-chain polymeric nanoparticles (SCNPs) offer a unique platform to overcome these limitations by mimicking protein-like architectures and providing high surface areas for targeted delivery. The aim of this study was to synthesize novel curcumin-based thiosemicarbazone ligand and its transition metal complexes (Cu(II), Ni(II), and Pt(II)) to produce next-generation SCNPs with enhanced anticancer and antioxidant activities.

Materials and Methods

A curcumin-based thiosemicarbazone ligand (KT-L) was synthesized via a Schiff base condensation reaction and structurally characterized. Metal complexes were subsequently prepared through coordination of KT-L with Cu(II), Ni(II), and Pt(II) salts. Amphiphilic block copolymers, poly(ethylene glycol)-*b*-poly(styrene-*co*-chloromethylstyrene) (PEG-*b*-P(St-*co*-CMS)), were synthesized *via* RAFT polymerization. First-generation SCNPs (SCNP1) were obtained by employing KT-L as an intramolecular crosslinker under highly dilute conditions (c= 0.5 mg mL^{-1}) to promote single-chain folding. Second-generation SCNPs (SCNP2) were produced through metal coordination of the folded polymer structures. The resulting nanostructures were characterized using GPC, DSC, DLS, UV–Vis spectroscopy, and TEM. Their biological activity was evaluated using DPPH radical scavenging assays to assess antioxidant capacity and MTT cytotoxicity assays on A549 and MCF-7 cancer cell lines.

Results

The formation of SCNPs was confirmed by a noticeable decrease in hydrodynamic volume observed in both DLS and SEC analyses, indicating efficient intramolecular folding of the polymer chains. UV–Vis spectroscopy further supported the successful coordination of metal ions to the thiosemicarbazone ligand. TEM analysis revealed the formation of well-defined nanoscale structures. Antioxidant assays demonstrated enhanced radical scavenging activity for the curcumin-containing systems, while cytotoxicity studies indicated promising anticancer activity against both tested cell lines.

Conclusion

Curcumin-based thiosemicarbazone ligands and their metal complexes were successfully integrated into SCNP architectures to develop multifunctional nanoplatforms. The obtained nanostructures combine the antioxidant properties of curcumin with the therapeutic potential of metal–thiosemicarbazone complexes, offering a promising strategy for the design of next-generation anticancer nanotherapeutics.

Acknowledgements

This work was financially supported by the Scientific and Technological Research Council of Türkiye (Project No: 124Z665).

D2 – P048

Polyphenol-loaded nanocarriers for inhibition of γD-crystallin aggregation: A non-surgical therapeutic approach to cataract

Das Sony M., Deep S.
Dept. of Chemistry, Indian Institute of Technology Delhi, New Delhi, India

Introduction

Cataract is the leading cause of vision impairment worldwide and is characterized by the progressive loss of lens transparency. Aggregation of γD-crystallin, a major structural protein of the human lens, is one of the key molecular events associated with age-related cataract formation. Oxidative stress promotes misfolding and aggregation of γD-crystallin into fibrillar structures. Naturally occurring polyphenols such as quercetin and resveratrol have shown promise as aggregation inhibitors; however, their poor aqueous solubility and limited ocular bioavailability restrict therapeutic application. This study investigates nanocarrier-based delivery systems to improve the effectiveness of these polyphenols against γD-crystallin aggregation.

Materials and Methods

Aggregation of human γD-crystallin was induced under oxidative stress conditions and characterized using turbidity measurements, thioflavin-T fluorescence assays, circular dichroism spectroscopy, and transmission electron microscopy. Quercetin and resveratrol were encapsulated in two nanocarrier systems: chitosan-coated poly (lactic-co-glycolic acid) (CS-PLGA) nanoparticles and niosomes composed of non-ionic surfactants and cholesterol. The nanoformulations were characterized using TEM, DLS, NTA, FTIR, TGA, and XRD. In vitro drug release studies were performed to evaluate release behaviour and sustained delivery.

Results

Both CS-PLGA nanoparticles and niosomal formulations were successfully prepared and demonstrated suitable physicochemical characteristics for ocular drug delivery. Characterization confirmed efficient encapsulation of the polyphenols and the formation of stable nanoscale carriers. In vitro release studies indicated sustained release profiles for the encapsulated compounds. Treatment with polyphenol-loaded nanocarriers significantly reduced γD-crystallin aggregation compared with untreated controls, as evidenced by biophysical and microscopic analyses.

Conclusion

Polyphenol-loaded CS-PLGA nanoparticles and niosomes represent promising nanotechnological approaches for the prevention of γD-crystallin aggregation associated with cataract formation. By improving polyphenol solubility, stability, and delivery, these nanoformulations may provide a potential non-surgical therapeutic strategy for cataract management.

Acknowledgements

The authors acknowledge the Department of Chemistry, IIT Delhi, for research facilities and support. Also acknowledge PMRF for funding.

References

[1]Rivillas-Acevedo L., Fernández-Silva A., Amero C. Function, Structure and Stability of Human Gamma D Crystallins: A Review. *Physical Biology of Proteins and Peptides* 2015; 1; 81–98.
[2]Fernández-Silva A., French-Pacheco L., Rivillas-Acevedo L., Amero C. Aggregation Pathways of Human γD Crystallin Induced by Metal Ions Revealed by Time Dependent Methods. *PeerJ* 2020; 8; e9178–e9178.
[3]Goswami V., Das S.M., Deep S. Quercetin-Loaded Nanocarriers as Effective Inhibitors for Copper Metal Ion-Induced γD-Crystallin Aggregation. *Langmuir* 2024; 40; 16093–16102.
[4]Das S.M., Gaur A., Deep S. Polyphenol-Loaded Niosomes as Efficient Nanocarriers for Inhibition of γD-Crystallin Aggregation and Sustained Drug Delivery. *Langmuir* 2025; 41; 15828–15840.

D2 – P049

Design and synthesis of crosslinking ionizable lipids for the formulation of DNA therapeutics in multifunctional lipid nanoparticles

Skigin P.[1], Kavand A.[1], Kuzucu E. Ü.[2], Cavegn A.[2], Detampel P.[2], Gerber-Lemaire S.[1], Huwyler J.[2]
[1]Group for Functionalized Biomaterials, Institute of Chemical Sciences and Engineering, École Polytechnique Fédérale de Lausanne, Lausanne; [2]Pharmazentrum, Division of Pharmaceutical Technology, University of Basel, Basel, Switzerland

Introduction

Gene therapy offers a promising approach for addressing genetic disorders, particularly conditions such as Citrullinemia type 1, caused by a deficiency in the argininosuccinate synthase 1 (ASS1) enzyme within the urea cycle. Current treatment options, including dietary management, dialysis, nitrogen scavengers, and liver transplantation in the most severe cases, are often limited and inconvenient. This study investigates the development of multifunctional lipid nanoparticles (LNPs) designed for liver targeted delivery of plasmid DNA (pDNA) as a therapeutic strategy. Collaboratively conducted by EPFL and the University of Basel, this interdisciplinary research focuses on designing and synthesizing novel ionizable lipid mimics with inherent crosslinking capabilities to overcome limitations of existing LNP-mediated gene delivery technologies, such as inefficient endosomal escape and inconsistent pDNA encapsulation within stable, sub-100 nm LNPs. pDNA offers longer transgene expression and improved storage stability compared to mRNA, but requires specific considerations for the development of optimal delivery vehicles.

Materials and Methods

To achieve this, an ionizable lipid design based on a functionalized peptidic backbone was developed and synthesized using solid-phase peptide synthesis (SPPS). The core structure is an azido-modified short peptide including one or several ionizable headgroups, and lipid tails. SPPS offers precise control over structure, streamlines synthesis, and facilitates purification. Click chemistry was integrated to introduce crosslinking subunits, specifically free thiols, enabling reversible disulfide bridge formation during LNP formulation for pDNA stabilization. Subsequent disassembly of reversible crosslinking bonds allows cargo unpacking and release during endosomal escape. A small library of lipopeptides was synthesized and incorporated into DNA-LNPs at an optimized N/P ratio of 6 for characterization of colloidal properties, including size, polydispersity index, zeta potential, and assessment of encapsulation efficiency.

Results

A small lipopeptide library with varying building blocks was successfully synthesized and characterized, demonstrating successful covalent conjugation of the intended crosslinking units. These lipids were formulated into DNA-LNPs with physico-chemical properties suitable for further evaluation. Further investigations will involve in vitro studies in human embryonic kidney cells (HEK293-T) to assess cellular uptake, transgene expression, and cell viability. In parallel, conjugation of nuclear localization signal (NLS) peptides to the cargo is being studied to address inefficient passage of pDNA through the nuclear pore complex.

Conclusion

The presented methodologies provide a basis for developing LNPs using reversibly crosslinked ionizable lipids, enabling flexible design of more biocompatible structures with adaptable building blocks. Future studies will fine-tune lipid structures based on biochemical and biological data to optimize therapeutic efficacy and safety.

Acknowledgements

This project was funded by the Swiss National Science Foundation (Sinergia Grant CRSII--222794).

D2 – P050

Chain length-tailored fusogenic lipid nanovesicles as efficient delivery systems

Pakhira M.[1,2], Sizovs A.[1,2]
[1]Laboratory of Pharmaceutical Pharmacology, Latvian Institute of Organic Synthesis; [2]Baltic Biomaterials Centre of Excellence, Headquarter at Riga Technical University, Riga, Latvia

Introduction

Vesicles are widely used in nanomedicine to deliver small-molecule drugs, proteins, and nucleic acids, but their cellular uptake is often dominated by endocytosis. In contrast, fusogenic vesicles may enable direct cytosolic delivery by promoting membrane fusion.

Aim

The aim of this study was to develop fusogenic lipids that can be incorporated into nanovesicles to confer membrane-fusion capability. We designed and synthesised a series of novel lipids with varied hydrophobic chain lengths and a shared polar motif to promote membrane fusion.

Materials and Methods

A series of novel lipids with varied hydrophobic chain lengths was synthesised from appropriate starting materials and characterised by ^{1}H NMR and high-resolution mass spectrometry. Lipid nanoparticles (LNPs) were prepared using jet injection, and particle size distribution was characterized by dynamic light scattering (DLS). The critical micelle concentrations (CMC) were determined using pyrene fluorescence emission spectroscopy method. Cytotoxicity of the lipids was evaluated using an MTT assay. Plasmid DNA (pDNA) binding was assessed by electrophoresis in 2% agarose gel in TAE (Tris/Acetic/EDTA) buffer. Fusion experiments were performed in HeLa cells using confocal microscopy, with the DiI-labelled vesicles and Calcein-AM counterstain. All measurements were done in triplicate.

Results

CMC values showed that the lipids exhibited chain-length-dependent self-assembly behavior, decreasing with increasing hydrophobic chain length and indicating enhanced hydrophobic stabilization. Cytocompatibility also showed a chain-length-dependent trend. No free pDNA migration was observed for the medium- to long- (C10–C20) lipid series in the gel retardation assay; however, shot-chain analogues (C6–C8) showed reduced binding affinity towards pDNA. In fusion experiments, lipids with intermediate to long hydrophobic chains (C16–C18) exhibited enhanced membrane fusion activity compared with the other formulations.

Conclusion

Overall, progressive elongation of the hydrophobic chain decreased CMC values, reflecting stronger hydrophobic interactions and more favourable self-assembly. Gel retardation analysis indicated that medium- to long-chain lipids achieved strong complexation with pDNA, whereas shorter-chain analogues showed reduced nucleic acid binding affinity. Notably, fusion studies demonstrated that lipids with intermediate to long hydrophobic chains provided the most favourable membrane fusion activity. These findings identify a chain-length window that supports further development of these nanovesicles as intracellular delivery systems.

Acknowledgements

Author acknowledge the financial support of this work by BioPhot program grant No. OSI_PIP_BioPhoT-2025/2-0062.

D2 – P051

Reprogramming brain tissue using CRISPR-based nanoformulation

Anjo A.[1,2], Brito J.[2,3], Simões S.[2,3], Tomatis F.[2], Francisco V.[2], Rodrigues A.F.[2,3], Estronca L.[2,4], Truong T.T.[5], Chintalagiri N.[5], Stricker S.[5], Ferreira L.[2,3,4]

[1]University of Coimbra, Institute for Interdisciplinary Research, Doctoral Programme in Experimental Biology and Biomedicine (PDBEB), Coimbra, Portugal; [2]CiBB - Centre for Innovative Biomedicine and Biotechnology, University of Coimbra, Coimbra, Portugal; [3]Faculty of Medicine, University of Coimbra, Coimbra, Portugal; [4]CoLAB4Ageing, Biocant Park, Coimbra, Portugal; [5]Institute of Structural Biology, Helmholtz Centre Munich, German Research Center for Environmental Health, Neuherberg, Germany.

Introduction

The limited regenerative capacity of the central nervous system represents a major challenge in treating neurodegenerative diseases and stroke, as neuronal loss is largely irreversible. Direct reprogramming of glial cells into functional neurons has emerged as a promising strategy to replace lost neuronal population. However, most current approaches rely mainly on viral vectors, raising concerns related to safety, immunogenicity and clinical translatability.

Aim

This work aims to develop a non-viral CRISPR-based formulation for gene activation and direct glial-to-neuron reprogramming, offering a safer and more versatile therapeutic alternative.

Materials and Methods

Polymeric nanoparticles (NPs) were formed as polyplexes through the interaction between the polymers developed in our group and CRISPR ribonucleoprotein complexes (Cas9:sgRNA, RNP or dCas9-VPR:sgRNA, dRNP). The physicochemical properties of NPs were evaluated by Zetasizer and by SDS-PAGE. As proof of concept, NP uptake and bioactivity were evaluated via GFP knockout in d2eGFP-HeLa cells and loxP excision in astrocytes isolated from Ai9 transgenic mice. CRISPR/dCas9-VPR–mediated gene activation was assessed in astrocytes and hippocampal organotypic 3D cultures by Ngn2 expression, and neuronal conversion was confirmed by β-tubulin III immunofluorescence, supporting glial-to-neuron reprogramming.

Results

To identify the best polymeric NP formulation, a library of 60 polymers was screened using CRISPR/Cas9 in d2eGFP-HeLa cells, using CRISPRMAX lipofectamine as control. The highest efficiency (~80% GFP knockout) was achieved with hit NP (300 nm, PDI 0.4, ζ-potential –10 mV). The Ai9 astrocytes were transfected with RNP-NPs to induce the knockout of loxP cassette resulting in tdTomato+ cells. The formulation demonstrated 40% efficiency against 20% with CRISPRMAX. Having demonstrated the feasibility of our CRISPR/Cas9 delivery platform, we performed gene activation assays using dRNPs (using dCas9-VPR) targeting Ngn2, a transcription factor that activates neuronal gene programs and drives cells toward a neuronal fate. Here, we achieved a 600-fold increase in expression vs. ~300-fold with CRISPRMAX in astrocytes. Consecutive administrations for 4 days led to 20% astrocytes to become neuronal-like cells as evaluated by the expression of β-Tubulin III$^+$ on day 10. In hippocampal organotypic 3D cultures, dRNP-NPs increased Ngn2 copies 3-fold by digital droplet PCR, demonstrating the platform's feasibility for gene activation and neuronal reprogramming.

Conclusion

With this work, we developed a novel platform for the delivery of CRISPR/Cas system, which demonstrated effective gene activation. When administered multiple times, NPs proved to be able to induce the direct reprogramming of primary astrocytes into neurons, representing a promising tool to counteract the neuronal loss that characterizes neurodegenerative diseases and stroke.

Acknowledgements

The authors acknowledge the COMPETE2020, the EIC Project REGENERAR (Ref. 101129812) and FCT program RETORNA (project no 15977). AA acknowledge for FCT fellowship (2025.02697.BDANA) and JB acknowledge for FCT fellowship (2024.05920.BDANA) and SS acknowledge for FCT for the funding (2024.11680.CEECIN).

D2 – P052

Gelatin-dextran hydrogels: Toward spatiotemporally controlled release of multiple bioactive molecules in wound healing

Vincent C., Hachem E., Buwalda S.J.,
MINES Paris, PSL Research University, Center for Materials Forming (CEMEF), UMR CNRS 7635, Sophia Antipolis, France

Introduction

Composite hydrogels, structured as polymeric networks incorporating drug-loaded particles, represent a promising strategy for spatiotemporally controlled release of bioactive molecules, making them attractive platforms for wound management. Controlled delivery of a small drug molecule may provide e.g. anti-inflammatory activity while a growth factor may promote tissue regeneration (Figure 1). As a first step toward composites development, this study focuses on designing gelatin-dextran hydrogels and evaluating how formulation parameters influence their properties.

Materials and Methods

Single-crosslinked hydrogels were prepared by reacting gelatin with aldehyde-functionalized dextran via Schiff base formation in aqueous solution and were characterized in terms of gelation time, crosslinking degree, and other structural properties. A second crosslinking step was applied by immersing the hydrogels in sodium citrate solutions at concentrations ranging from 10% to 30% w/w. Single- and double-crosslinked hydrogels were compared for structural properties as well as protein loading and release using FITC-labeled bovine serum albumin (BSA-FITC).

Results

Increasing gelatin and dextran concentrations reduced hydrogel swelling and increased the crosslinking degree from 34% to 60%. A formulation with optimized polymer concentrations (10% w/w gelatin, 5% w/w dextran) in terms of crosslink density and gelation time was selected for double-crosslinking. Secondary crosslinking with sodium citrate reduced the network mesh size from 11 nm to 4–6 nm, demonstrating that a kosmotropic salt effectively limits water uptake by increasing the crosslink density. FT-IR analysis confirmed additional interactions between gelatin chains and ionic interactions between gelatin and citrate ions, which contribute to network stabilization.

BSA-FITC was released in a sustained manner, with approximately 20% release over one month. Double-crosslinking did not significantly alter the release profile compared to single-crosslinked hydrogels, indicating that secondary crosslinking can modulate structural properties without compromising sustained protein delivery.

Conclusion

Gelatin-dextran hydrogels were successfully designed and characterized. Their structural properties were tuned via control of polymer concentration and a second crosslinking step with citrate ions. The resulting additional interactions, confirmed by FT-IR, suggest robust structural stability. Both single- and double-crosslinked hydrogels provided a sustained release of a model protein for more than one month. Overall, this study demonstrates the potential of gelatin-dextran hydrogels for controlled protein delivery in wound healing, supporting future development of multifunctional composites delivering therapeutic proteins and small-molecule agents to enhance tissue regeneration.

Acknowledgements

MINES Paris is acknowledged for funding (doctoral contract C. Vincent). We also thank IPMC (Sophia Antipolis) for help with release experiments.




Figure 1: Composite hydrogels for dual drug delivery in wound healing and pain management.

D2 – P053

Sodium alginate mucoadhesive films: A promising platform for drug delivery in the treatment of oral mucositis

Abe dos Santos C., Gava Mazzola P.
FCF-UNICAMP, Faculty of Pharmaceutical Sciences, State University of Campinas, Sao Paulo, Brazil

Introduction

Oral mucositis is a debilitating and frequent complication of cancer treatment, particularly associated with chemotherapy and radiotherapy in the head and neck region. Despite its prevalence and severity, current therapeutics for oral mucositis are limited. In this context, the development of new drug delivery systems that ensure prolonged and targeted action at the lesion site represents a promising strategy. Mucoadhesive films emerge as a prominent pharmaceutical technology, being produced from water-soluble polymers that dissolve rapidly when placed in the oral cavity, offering advantages such as easy application and prolonged permanence in the oral mucosa due their adhesion capacity.

Aim

To develop and characterize mucoadhesive films for the treatment of oral mucositis, using a polymeric matrix composed of alginate and glycerin. Sodium alginate is a natural polysaccharide widely recognized for its mucoadhesive properties and biocompatibility, and glycerin will be incorporated as and plasticizer aiming to optimize the mechanical properties.

Materials and Methods

The films were developed using the Solvent Casting method and based on experimental design, different concentrations of polymer (2 to 3,2%) and plasticizer (10,75 to 19,24% in relation to the polymer) were evaluated in an experimental design CCP (central composite planning). The dependent variable analyzed was the disintegration time of the films, using phosphate buffer at pH 7, and the film burst strength using the Texture Analysis XTPlus Connect. The experimental design was analyzed using Statistica v.7 software, with a significant level of 95% ($p<0.05$).

Results

According to Figure 1, only the linear term from the polymer concentration is significant for the force required to break the film did not have any statistically significant parameters. Similarly, the disintegration time (Figure 2). So, to obtain a higher disintegration time and also a mechanical resistance, the concentration of Polymer must increase linearly with the concentration of plasticizer not being signnificant. Between the analyzed formulations, the chosen formulation was with 3% of polymer and 12% of glycerin.

Figure 1:





Figure 2:



Conclusion

The formulation presented satisfactory physicochemical results and had characteristics suitable for the proposed pharmaceutical form, showing promise for incorporation of natural extracts or drugs for the treatment of oral mucositis.

Acknowledgements
Funding: FAPESP, grant number: 2024/15703-1

D2 – P054

AlgMA–fibrin hydrogel for controlled delivery of SDF-1–loaded nanoparticles in dental pulp regeneration

Ivković U.[1], Claeys R.[1], Zhang F.[2,3], Van Meerbeek B.[2], Deschaume O.[4], Beretta F.[5], Proost P.[5], Mignon A.[6], Jacobs R.[1,7,8], EzEldeen M.[1,2]

[1]OMFS-IMPATH, Dept. of Imaging and Pathology, KU Leuven, Belgium; [2]Dept. of Oral Health Sciences, KU Leuven, Belgium; [3]Dept. of Materials Engineering, KU Leuven, Belgium; [4]Dept. of Physics and Astronomy, KU Leuven, Belgium; [5]Rega Institute, KU Leuven, Belgium; [6]Campus Group T, KU Leuven, Belgium; [7]Dept. of Oral and Maxillofacial Surgery, UZ Leuven, Belgium; [8]Dept. of Dental Medicine, Karolinska Institutet, Sweden

Introduction

Regenerative endodontics aims to restore the dentin–pulp complex by recruiting and differentiating endogenous progenitor cells. Stromal cell-derived factor-1 (SDF-1) promotes dental pulp stem cell homing and is a key signaling molecule for pulp regeneration, but effective systems for its localized, sustained delivery are needed.
In this study, we developed an injectable alginate methacrylate (AlgMA)–fibrin hydrogel scaffold incorporating SDF-1–loaded nanoparticles for potential dental pulp regeneration.

Materials and Methods

Chitosan nanoparticles encapsulating SDF-1 were synthesized for controlled chemokine delivery. Loading effectiveness was studied with immunosorbent tandem mass spectrometry proteoform analysis (ISTAMPA). These nanoparticles were incorporated into an AlgMA–fibrin hydrogel, which involved covalent crosslinking via photopolymerization of AlgMA, preceded by ionic fibrin gelation. Hydrogel stiffness was assessed through nanoindentation, and its microstructure through scanning electron microscopy (SEM) and atomic force microscopy (AFM). Moreover, crosslinking of AlgMA was confirmed using Fourier transform infrared (FTIR) spectroscopy. In addition, the release profile of SDF-1 from the nanoparticle-loaded hydrogel was evaluated over 10 days. The cellular behaviour of dental pulp stem cells (DPSCs) cultured in contact with the hydrogels was also examined to assess biocompatibility.

Results

The SDF-1-loaded nanoparticles were synthesised successfully, with ISTAMPA confirming effective loading. AlgMA–fibrin hydrogel synthesis resulted in a robust scaffold integrating SDF-1-loaded nanoparticles. Nanoindentation quantified hydrogel's stiffness, confirming mechanical characteristics appropriate for soft tissue engineering. SEM and AFM demonstrated a honeycomb structure conducive to cellular infiltration, while FTIR confirmed AlgMA crosslinking. Sustained release of SDF-1 from loaded nanoparticles was observed up to 10 days. Cell viability assays confirmed the cytocompatibility with DPSCs.

Conclusion

The developed AlgMA–fibrin hydrogel represents a promising platform for regenerative endodontics. Its architecture and suitable mechanical properties support its potential as a scaffold for pulp regeneration. Incorporation of SDF-1-loaded nanoparticles may enable localized chemokine delivery to promote recruitment of DPSCs.

D2 – P055

Development of a NIR-activated, Au-$AgTiO_2$-SnO_2 implantable chip for deep-tissue UTI treatment

Chakraborty D.[1], Hazra S.[2], Upadhyay A.[1], Sahu C.R.[3], Agrawal A.[3], Pal B.N.[2], Mukherjee S.[1]
[1]School of Biomedical Engineering, Indian Institute of Technology (BHU); [2]School of Materials Science & Technology, Indian Institute of Technology (BHU); [3]Dept. of Pharmaceutical Engineering & Technology, Indian Institute of Technology (BHU), Varanasi, India

Introduction

Urinary tract infections (UTIs), predominantly caused by uropathogenic *Escherichia coli* (UPEC), represent one of the most common bacterial infections worldwide, affecting more than 150 million individuals annually. Despite antibiotic therapy, relapse occurs in 30–50% of cases, and the growing resistance of UPEC to last-resort antibiotics, including carbapenems and colistin, poses an immediate challenge clinically. Recent advances in nanoparticle-mediated photoactivated therapies (aPTT and aPDT) have emerged as a promising strategy due to their ease of application, potent antibacterial activity, and reduced risk of resistance development. However, the injectable versions often come with challenges including poor degradability or long-term biocompatibility, due to risk of inducing systemic toxicity and microbial dysbiosis.

Aim

To develop an implantable, NIR-responsive chip, which upon activation will generate sufficient heat within a very short time to achieve photothermal killing of bacterial communities. Since NIR light can effectively reach deeper tissues of the human body such as urinary tract, wherein generating localized hyperthermia and ROS would create a targeted antibacterial zone, leading to effective destruction of biofilm-encased bacteria. This ensures our chip is retrievable once therapy is given, paving the way for personalized healthcare.

Materials and Methods

The fabrication of the Au-$AgTiO_2$-SnO_2 chip was done using a low temperature, solution-processed technique to achieve a stable and robust thin film deposition on polyethylene substrates. Characterization by XRD, UV-Vis absorption, FE-SEM, HR-TEM, 3D AFM and photothermal performance was confirmed using a thermal camera (Fig.1). Herein, a NIR-source with a dominant wavelength of 1100 nm was used for photoactivation. All animals were studied after approval from the institutional animal ethical committee, IIT(BHU). GFP-*E. coli* was used for *in vivo* investigations. Briefly, an acute UTI model was generated by transurethral inoculation of bacteria followed by implanting the NIR-activated nanocoated chip within a subcutaneous pocket above the urethra of a female Wistar rat under anesthesia (Fig. 2). After 48 hrs, each animal was euthanized appropriately to collect various organs and body fluids. Further analysis was achieved by IVIS imaging of homogenized tissues to detect bacterial load of treated vs untreated rats and fixation of tissues for histopathological examination.

Results




Figure 1: Results of characterization of the Au-AgTiO$_2$-SnO$_2$ chip by (b) XRD analysis, which shows successful deposition of all three layers, (c) UV-Vis absorption spanning the optical spectral region of 300–1800 nm show a broadening effect from UV-Vis to NIR range, with a bi-metallic Au-Ag plasmonic peak at around 750 nm (d) FE-SEM images reveal a percolated nanoporous structure, (d) HR-TEM images shows the uniform distribution of Au-Ag NPs within the TiO$_2$-SnO$_2$ NP matrix, and (e) 3D-AFM image show a porous metallic network due to the preferential nucleation of metal atoms around the oxide NPs, g) and (h) shows the optical image and photothermal performance of the chip.




Figure 2: (a) Thermal images of rat skin with coated and uncoated chip (b) Dermal infection control efficacy of the chip upon NIR exposure after 24 hrs **(c)** A female Wistar rat model for targeted treatment of acute UTI by implanting the NIR-triggered chip for localized antibacterial action after 6 hrs of transurethral inoculation of 0.6 O.D. (A_{600}) GFP-*E. coli*. **(d)** GFP- *E. coli* detection to quantify bacterial load in isolated organs and body fluids by In vivo Imaging system after 48 hrs of treatment by exposure to NIR-light.

Conclusion

In this study, the fabrication of an NIR-responsive, Au-$AgTiO_2$-SnO_2 implantable chip with efficient *in vitro* and in vivo antibacterial and antibiofilm efficacy under very short exposure time was achieved. By leveraging the advantages of photothermal and photodynamic therapy, this synergistic bio-compatible nanoplatform, is one-of-a-kind device that, leads to bacterial inactivation within deep tissues, without damaging the surrounding tissues.

D2 – P056

Blueberry EV-loaded rehydratable films for colorimetric sensing and wound healing

Havlíčková Š.[1], Sedlář A.[2], Pratiwi F.[3], Slepičková Kasálková N.[1]
[1]Dept. of Solid State Engineering, UCT Prague, Prague, Czech Republic; [2]Institute of Physiology, Czech Academy of Sciences, Prague, Czech Republic; [3]Developmental Biology Laboratory, Oulu, Oulu University, Finland

Introduction

Plant-derived extracellular vesicles (EVs) are emerging as natural nanocarriers capable of delivering bioactive compounds directly to cells[1]. However, their broader application is limited by stability issues and demanding storage conditions. For topical therapies, particularly wound care, suitable biomaterial carriers are required to enable rapid and effective delivery of bioactive compounds. Blueberry-derived EVs are rich in anthocyanins and exhibit antioxidant and wound healing potential, while also providing pH-dependent colorimetric sensing of inflammation.

Materials and Methods

Aqueous solutions of poly(vinyl alcohol) (PVA) and sodium alginate were mixed and glycerol was added as a plasticizer. The mixture was cast into plastic moulds to form thin films and subjected to five freeze-thaw cycles to achieve physical crosslinking without toxic additives. Blueberry EVs were isolated by homogenization in extraction buffer with protease inhibitors followed by filtration and sequential centrifugation. EVs were incorporated into the hydrogel matrix at concentrations of 6×10^{10}, 6×10^{9} and 6×10^{8} particles/ml prior to film casting.

Results

The EV-loaded freeze-thaw films maintained structural integrity after rehydration and demonstrated rapid vesicle release. The release is likely driven by electrostatic repulsion between negatively charged alginate chains and EV membranes. Due to the presence of anthocyanins, the films exhibited pH-dependent color changes, enabling visual monitoring of the wound environment. Film eluates showed antioxidant and ROS-scavenging activity, and in vitro assays confirmed high cell viability (>90 %) with skin-relevant cells.

Conclusion

We developed rehydratable PVA/alginate films loaded with blueberry EVs as a multifunctional platform. They provide rapid EV delivery, antioxidant activity and pH-responsive colorimetric sensing, demonstrating potential for advanced wound healing.

Acknowledgements

This work was supported from the grant of Specific university research – grant No A2_FCHT_2026_009.

This work was also supported by the Project OP JAK EXRegmed, No CZ.02.01.01/00/22_008/0004562, of the Ministry of Education, Youth and Sports, which is co-funded by the European Union.

References

[1]Zhao B., et al. Exosome-like nanoparticles derived from fruits, vegetables, and herbs: innovative strategies of therapeutic and drug delivery. *Theranostics* 2024; 14(12); 4598-4621.
[2]Li, Y., et al. Engineering Strategies of Plant-Derived Exosome-Like Nanovesicles: Current Knowledge and Future Perspectives. *Int J Nanomedicine* 2024; 19; 12793-12815.

D2 – P057

Oral β-glucan supplementation enhances PD-1 immunotherapy and alleviates cancer cachexia through a microbiota–gut–brain axis

Lin P.H., Nguyen L.D.H., Lin Y.C., Chung Y.C., Sung H.W.*
Dept. of Chemical Engineering, National Tsing Hua University, Hsinchu, Taiwan (ROC)

Introduction

Immune checkpoint blockade (ICB) targeting the PD-1/PD-L1 axis has transformed cancer therapy; however, durable responses remain limited due to insufficient dendritic cell (DC) priming, poor $CD8^+$ T-cell infiltration, and inflammation-driven immunosuppression [1]. Emerging evidence indicates that the gut microbiota regulates antitumor immunity through microbial metabolites, including short-chain fatty acids (SCFAs) [2,3]. Meanwhile, tumor-associated inflammation contributes to cancer cachexia and disrupts striatal dopaminergic signaling via gut–brain interactions [4]. Strategies that simultaneously enhance immunotherapy efficacy while alleviating cachexia-associated neuroimmune dysfunction remain limited.

Aim

We investigated whether oral β-glucan supplementation could remodel gut microbial metabolism to enhance anti-PD-1 immunotherapy while mitigating cachexia-associated neuroimmune dysfunction.

Materials and Methods

BALB/c mice bearing CT26 tumors received oral β-glucan supplementation, anti-PD-1 antibody, or their combination. Tumors were established either subcutaneously or orthotopically in the cecum. Gut microbiota composition, SCFA levels, tumor immune responses, and neurobehavioral parameters were evaluated using sequencing, HPLC, flow cytometry, and behavioral assays.

Results

In the subcutaneous CT26 model, oral β-glucan supplementation significantly enhanced the therapeutic efficacy of anti-PD-1 treatment, resulting in reduced tumor growth and prolonged survival compared with monotherapy. Immune profiling revealed increased DC activation, enhanced $CD8^+$ T-cell infiltration, reduced $PD\text{-}1^+$ exhausted $CD8^+$ T cells, and decreased immunosuppressive macrophages within tumors. Microbiota analysis showed enrichment of SCFA-producing taxa accompanied by elevated systemic SCFA levels. Pharmacological blockade of the SCFA receptor GPR43 partially reversed these immunological effects and reduced intratumoral $CD8^+$ T-cell accumulation. In addition, β-glucan supplementation alleviated cancer-associated cachexia, preserving muscle mass and improving behavioral performance. These effects were associated with reduced brain IL-6 levels, decreased microglial activation, and restoration of striatal dopamine signaling. Similar therapeutic benefits were observed in the orthotopic tumor model.

Conclusion

Oral β-glucan supplementation potentiates PD-1 checkpoint blockade by reprogramming microbiota-derived metabolism. This strategy links SCFA-mediated immune activation with protection against cancer cachexia through a microbiota–gut–brain neuroimmune axis.

Acknowledgements

This research was supported by the National Science and Technology Council (NSTC 114-2639-E-007-001-ASP).

References

[1]Martins F., et al. Adverse effects of immune-checkpoint inhibitors: epidemiology, management and surveillance. *Nat Rev Clin Oncol* 2019; 16; 563–580.
[2]Simpson R.C., et al. Towards modulating the gut microbiota to enhance the efficacy of immune-checkpoint inhibitors. *Nat Rev Clin Oncol* 2023; 20; 697–715.
[3] Han K., et al. Generation of systemic antitumour immunity via in situ modulation of the gut microbiome by an orally administered inulin gel. *Nat Biomed Eng* 2021; 5; 1377–1388.
[4]Zhu X.A., et al. A neuroimmune circuit mediates cancer cachexia-associated apathy. *Science* 2025; 388; eadm8857.

D2 – P058

Solid lipid nanoparticles for miRNA delivery for anti-inflammatory therapy in ARDS in vitro models

Aihui G.[1,2], Preeti S.[1,2], Abigail W.[1,2], John L.[1,2,3]
[1]CÚRAM Research Ireland Centre for Medical Devices, School of Medicine Nursing and Health Sciences, University of Galway; [2]Discipline of Anaesthesia, School of Medicine, Nursing and Health Sciences, University of Galway; [3]Dept. of Anaesthesia and Intensive Care Medicine, Galway University Hospitals, Saolta University Healthcare System, Galway, Ireland

Introduction

Acute respiratory distress syndrome (ARDS) remains a major cause of morbidity and mortality in critically ill patients. Despite advanced supportive care, effective pharmacological interventions capable of modulating inflammatory and immune dysregulation associated with ARDS remain limited. However, clinical application of current immunologic therapeutic candidates is hindered by poor pulmonary targeting and limited structural stability, highlighting the potential of nanotechnology-based delivery systems in ARDS immunologic therapy. Among them, solid lipid nanoparticles (SLNs) offer several advantages, including improved drug stability, efficient tissue targeting, controlled release, and relatively high drug-loading capacity, supporting their translational potential for nucleic acid delivery.

Aim

To address current limitations in ARDS immunotherapy, we constructed a miRNA-loaded SLN (miRNA-SLN) delivery system and evaluated its anti-inflammatory effects in the *in vitro* ARDS model.

Materials and Methods

Briefly, we constructed the SLN platform consisting of 1,2-dioleoyl-3-trimethylammonium-propane chloride (DOTAP), glyceryl monostearate (GMS) and poloxamer 188 aiming at miRNA delivery(miRNA-SLN). Particle size and ζ-potential were measured by dynamic light scattering (DLS), while morphology was examined using scanning electron microscopy (SEM). Based on DLS and SEM results, proper SLNs platform were selected for further miRNA characterization, of which formulation transmission electron microscopy (TEM) was used for structure examination. Encapsulation efficiency (EE%), dialysis bag release assay, and differential scanning calorimetry (DSC) were performed to evaluate stability and release characteristics. Cytotoxicity was assessed by MTT assay in A549 and BEAS-2B cells. Anti-inflammatory effect was evaluated through Enzyme-Linked Immunosorbnent Assay (ELISA) in ARDS model induced by lipopolysaccharide (LPS) in both cell lines.

Results

DLS, SEM, and TEM analyses confirmed that the selected miRNA-SLN formulations exhibited diameter ranging from 110-200nm and suitable ζ-potential for *in vitro* delivery. Encapsulation efficiency, dialysis assays, and DSC demonstrated favorable stability and release characteristics. MTT assays indicated limited cytotoxicity in both A549 and BEAS-2B cells. Furthermore, miRNA-SLN treatment significantly modulated inflammatory responses in ARDS *in vitro* model, reducing levels of inflammatory cytokines, including Interleukin-6(IL-6).

Conclusion

The miRNA-SLN delivery system demonstrated effective anti-inflammatory activity with minimal cytotoxicity in vitro, highlighting its potential as a promising nanotherapeutic strategy for future ARDS treatment.

D2 – P059
Antiseptic thread based on hyaluronic acid for periodontitis treatment

Kralova M.[1], Chmelar J.[1], Kubickova J.[1], Pitucha T.[1], Matonohova J.[1], Nesporova K.[1], Suchanek J.[2]
[1]Contipro a.s., Dolni Dobrouc; [2]Dept. of Dentistry, Faculty of Medicine in Hradec Kralove, Charles University, Hradec Kralove, Czech Republic

Introduction
Periodontitis is one of the leading causes of tooth loss in adults, affecting the supportive tissues surrounding the teeth. It is associated with inflammation, microbial colonization and loss of bone tissue. Current therapies control infection and reduce inflammation; however, effective regeneration of periodontal tissues remains a challenge. To address this, we have developed braided threads composed of hyaluronan and its lauroyl derivative, specifically designed for application in the periodontal pocket. The threads are loaded with antiseptic octenidine to reduce infection.

Materials and Methods
Sodium hyaluronate (HA) and lauroyl hyaluronate (LAU-HA) were used as main materials for preparation of fibers by wet spinning method. Followed by braiding into threads and subsequent deposition of octenidine.
Degradation, antimicrobial activity and biocompatibility were evaluated *in vitro*. *In vivo* safety was assessed in rabbit jaws.

Results
Fibers composed of HA and LAU-HA were prepared by wet spinning and braided into the thread containing 16 filaments at an HA:LAU-HA ratio of 1:1. Octenidine was applied using a dispensing nozzle. The structure can be observed in Figure 1. The resulting threads exhibited suitable mechanical properties for dental application.
Owing to its composition, the thread gradually dissolves and swells in a moist environment. The degradation rate depends on the content of LAU-HA, reflecting its lower susceptibility to enzymatic degradation. Threads with lower LAU-HA content degrade faster and are therefore suitable for deeper placement in the periodontal pocket, where they facilitate tissue ingrowth. In contrast, threads with higher lauroyl content provide prolonged protection against bacterial infiltration.

Safety and antimicrobial properties were confirmed through *in vitro* testing, followed by a two-phase *in vivo* study in rabbits, which demonstrated safety and characterized resorption times.

Conclusion
The hyaluronan-based braided thread was developed with the potential to improve the treatment of periodontitis. The medicinal product prototype provides mechanical stability, controlled biodegradability and antimicrobial activity, thereby helping to prevent bacterial recolonization and support tissue regeneration. HA fibers promote healing, while LAU-HA fibers ensure prolonged therapeutic activity and modulate properties such as swelling and degradation rate, enabling optimization of the treatment.




Figure 5: SEM image of the hyaluronan-based braided thread

D2 – P060

Handheld electrospinning-assisted point-of-care fabrication of aloe vera–silk fibroin fibrous wound dressings for emergency burn care: Evaluation on CAM-based preclinical burn model

Bilginer-Kartal R.[1,2], Torkay-Çay G.[2], Öztürk B.[3], Bal-Öztürk A.[1,2,4]
[1]AdBioInk Biosystem Technology, Kocaeli; [2]Stem Cell and Tissue Engineering Application and Research Center (ISUKOK), Istinye University, Istanbul; [3]Dept. of Stem Cell and Tissue Engineering, Institute of Graduate Education, Istinye University, Istanbul; [4]Faculty of Pharmacy, Dept. of Analytical Chemistry, Istinye University, Istanbul, Turkey

Introduction

Burn wounds represent a critical clinical challenge that need urgent clinical intervention due to rapid progression of the burn, high risk of infection, and impaired tissue regeneration, thereby necessitating advanced wound dressing capable of maintaining a balanced healing microenvironment. In situ electrospinning has emerged as a promising approach, enabling direct deposition and effective coverage of wound sites, thereby providing a favorable microenvironment with electrospun fibrous matrices appropriately formulated. Natural biomaterials have gained significant attention in wound dressing applications owing to their bioactive functionalities. Among these, silk fibroin (SF) and Aloe vera (AV) are particularly promising; silk fibroin offers remarkable wound healing owing to enhancing collagen production, cell proliferation and activating cell migration, while AV provides anti-inflammatory and antibacterial effects. In this study, a handheld electrospinning device was utilized for *in situ* deposition of polyvinyl alcohol (PVA) wound dressing functionalized with AV-SF (AV-SF_{WD}) and their potential for burn wound healing was investigated.

Materials and Methods

AV-SF_{WD} formulations with varying AV concentrations were prepared and electrospinning was performed using a handheld device (AdBioInk Biosystem Technology) at 17 kV, 1 mL/h flow rate, and 10 cm working distance. The conformal deposition ability of the handheld electrospinning device for AV-SF_{WD} was demonstrated on different 3D-printed structures coated with gelatin. Effect of AV concentration on fiber morphology and diameter was analyzed by SEM and ImageJ, while chemical structure was evaluated by FTIR. Surface wettability and moisture permeability were assessed via water contact angle (WCA) and water vapor transmission rate (WVTR) measurements, respectively. Mechanical properties and injectability were evaluated. Antioxidant activity was determined using DPPH assay and antibacterial activity was evaluated using zone inhibition test. Cytocompatibility was assessed using MTT assay with human dermal fibroblasts, while cell migration was evaluated via scratch test. Hemocompatibility was determined by hemolysis assay. Collagen production of dermal fibroblast cells was investigated by Sirius red assay. The burn wound model was established on CAM by inducing localized injury using a preheated metal stamp**.**

Results

Handheld electrospinning device enabled *in situ* deposition of AV-SF_{WD}, achieving uniform fibrous coverage over curved and irregular surfaces and resulting in homogenous fibers, confirmed by SEM. FTIR spectra verified the successful incorporation of AV-SF within the PVA fibers. Contact angle measurements demonstrated appropriate hydrophilicity of the wound dressings, which is favorable for maintaining a moist wound environment, while WVTR values were within the optimal range for burn wound healing. Tensile strength of AV-SF_{WD} decreased upon AV concentration increased and AV-SF_{WD} formulations demonstrated acceptable injectability. Antibacterial test confirmed inhibition of bacterial growth, significantly with increasing AV concentration. Cytocompatibility assays demonstrated high cell viability (>90%), confirming the biocompatible nature of the developed wound dressings. Furthermore, scratch assay results revealed accelerated fibroblast migration and wound closure compared to control groups. In addition, AV-SF_{WD} supported collagen deposition, whereas hemocompatibility analysis indicated negligible hemolysis (<5%). CAM burn model was successfully established, demonstrating effective burn healing by AV-SF_{WD}.

Conclusion

The developed AV-SF_{WD} enabled conformal deposition on irregular surfaces, supporting its potential for point-of-care burn treatment, while CAM evaluation confirmed enhanced burn wound healing.

Acknowledgements

This work is supported by TUBA through Young Scientist Award Program (TUBAGEBIP/2024).

D2 – P061

Prebiotic-loaded mucoadhesive films for vaginal microbiota rebalancing: Development and biological evaluation

Sousa Fonseca M.E.[1], Jiang K.[2], Bernuz M.[2], Sedlacek Campagnoli G.[1], Crouzier T.[2], Agostini de Moraes M.[1]
[1]Dept. of Materials and Bioprocess Engineering, School of Chemical Engineering, University of Campinas (UNICAMP), Campinas, São Paulo, Brazil; [2]Dept. of Health Technology, Technical University of Denmark (DTU), Kongens Lyngby, Denmark

Introduction

Vaginal infections, such as candidiasis and bacterial vaginosis, significantly impair women's quality of life worldwide. While conventional vaginal films focus primarily on pathogen eradication, they fail to restore the local microbiome. Prebiotics offer a promising alternative to address this gap by selectively promoting a healthy microbiota. In this context, combining chitosan, valued for its mucoadhesive and microbicide properties, with mucin, an underexplored biocompatible material, provides a suitable platform for vaginal microbiota applications.

Aim

This study aims to develop prebiotic-loaded mucoadhesive films, focusing primarily on evaluating both their microbicide activity against pathogens and their microbiota support activity for beneficial microorganisms.

Materials and Methods

Mucoadhesive films were prepared using the solvent casting method by combining chitosan (dissolved in lactic acid) and mucin, loaded with the prebiotic α-glucan oligosaccharide (BioEcolia®). The films were characterized regarding their macroscopic appearance, surface pH, and chemical interactions by Fourier-transform infrared spectroscopy (FTIR). To evaluate biological performance, the microbicide activity was tested using agar diffusion and optical density (OD) measurements against *Candida albicans*, *Gardnerella vaginalis*, and *Escherichia coli*. Concurrently, the microbiota support activity was evaluated through proliferation assays with *Lactobacillus spp.*

Results

The films were homogeneous, flexible, and easy to handle (Figure 1), presenting a surface pH compatible with the vaginal environment (4.2–4.4). FTIR indicated interactions between chitosan and mucin within the film matrix (Figure 2), while preliminary microbiological assays suggested greater inhibitory activity against pathogens for mucin-containing formulations. The incorporation of BioEcolia® holds promising potential to selectively stimulate the proliferation of vaginal *Lactobacillus* spp.

Conclusion

The indications of synergy between chitosan and mucins could lead to more effective microbicide activity. Moreover, the innovative integration of prebiotics, combined with the formulation's ability to inhibit key pathogens, highlights the platform's potential as a therapeutic strategy. By combining the matrix's intrinsic microbicide activity with selective prebiotic microbiota support, this system represents a breakthrough alternative to conventional antimicrobial treatments for vaginal microbiota restoration.

Acknowledgements

São Paulo Research Foundation (FAPESP), grant numbers 2025/01868-1 and 2025/23105-0; Conselho Nacional de Desenvolvimento Científico e Tecnológico (CNPq), grant numbers 307960/2023-4 and 186491/2025-5 and Coordenação de Aperfeiçoamento de Pessoal de Nível Superior - Brasil (CAPES) - Finance Code 001. The authors also acknowledge the School of Chemical Engineering, University of Campinas (FEQ-UNICAMP), and the Department of Health Technology, Technical University of Denmark (DTU Health Tech), for institutional support.

Figure 1. Visual aspects of the mucoadhesive vaginal films based on pure chitosan (C100M0) and chitosan-mucin blends (C90M10 and C80M20), with and without the prebiotic BioEcolia®.





Figure 2. FTIR spectra of raw materials (pure chitosan and mucin) and the developed mucoadhesive film matrices (C100M0, C90M10, and C80M20).



D2 – P062

Engineering NIR-responsive theranostic gutta-percha for real-time detection and disinfection of endodontic bacteria during root canal treatment

Vincy A.[1], Yadav J.[2], Agarwal H.[1], Jain N.[1], Vankayala R.[1,2]
[1]Dept. of Bioscience and Bioengineering, Indian Institute of Technology Jodhpur, Karwar; [2]Medical Technologies Center, Indian Institute of Technology Jodhpur, Rajasthan, India

Introduction

Root canal treatment (RCT) is a widely performed endodontic procedure to eliminate infection and preserve the natural teeth. During RCT, infected pulp tissue is removed, the canal is disinfected through irrigation and subsequently sealed using gutta-percha (GP). Despite its clinical success, treatment failure can occur due to incomplete elimination of residual bacteria prior to sealing, as current irrigation strategies lack real-time confirmation of bacterial clearance within the root canal.

Aim

We report the development of SteriGP, an engineered GP-based smart theranostic platform that enables simultaneous bacterial detection as well as stimuli-responsive localized disinfection during root canal treatment.

Materials and Methods

SteriGP is fabricated through commercially available GP. Typically, the GP are coated with thin layer of sodium alginate crosslinked with $FeCl_3$. In the RCT model, potassium ferricyanide should be added first followed by dipping of the SteriGP, in case of infection, Prussian blue (PB) will be produced as a visible indicator. SteriGP utilizes a ferricyanide-mediated bioreaction to rapidly detect metabolically active bacteria through respiration-driven electron transfer, resulting in the in-situ formation of PB (Figure 1).

Results

SteriGP demonstrates concentration-dependent bacterial sensing and potent antibacterial activity in both planktonic and biofilm models of Gram-positive and Gram-negative bacteria. Furthermore, a root canal infection model using Escherichia coli biofilms confirm real-time visualization of bacterial presence within the canal and effective biofilm disinfection upon NIR activation reaching up to ~65°C.

.

Conclusion

To the best of our knowledge, this represents the first NIR-responsive theranostic endodontic obturation material integrating real-time bacterial sensing with on-demand localized disinfection. Overall, this work establishes a clinically translatable theranostic biomaterial platform for precision-guided root canal treatment and improved endodontic outcomes

Acknowledgements

We acknowledge the funding of this project though MSME 4.0 grant by Government of India.




Figure 1. Schematic representation of the mechanism of detection and disinfection of SteriGP during RCT.

D2 – P064

Real-time single-cell insights into antibacterial interactions of silver-loaded PEGDA/gelatin hydrogels

Şener Raman T.[1], Claus C.[2], Daikos O.[1], Scherzer T.[1], Prager A.[1], Lotnyk A.[1], Stieler L.[1], Konieczny R.[1], Abel B.[3,4], Schulze A.[1]
[1]Leibniz Institute of Surface Engineering (IOM), Leipzig, Germany; [2]Institute of Medical Microbiology and Virology, Medical Faculty, Leipzig University, Leipzig, Germany; [3]Institute of Chemical Technology, Faculty of Chemistry, Leipzig University, Leipzig, Germany; [4]Dept. Space Chemistry and Technology, J. Heyrovsky Institute of Physical Chemistry, Czech Academy of Sciences, Praha, Czech Republic

Introduction

The rising threat of bacterial infections and antibiotic resistance has intensified the demand for advanced biomaterials that prevent infection while supporting tissue regeneration. Hydrogels are promising wound care materials due to their high-water content, biocompatibility, and tissue-like properties; however, their limited intrinsic antibacterial activity remains a key challenge.[1] Silver nanoparticles (AgNPs) offer broad-spectrum antimicrobial activity, yet their integration into hydrogels requires precise control to balance efficacy and cytocompatibility. While their antibacterial effects are well known, real-time insights into their interaction with bacterial cells at the single-cell level remain limited. Electron beam irradiation provides an initiator-free method enabling simultaneous hydrogel formation, nanoparticle generation, and sterilization.[2] In this study, we aim to directly investigate how AgNP-loaded PEGDA/gelatin hydrogels influence bacterial behavior at the single-cell level and to relate these effects to hydrogel structure and nanoparticle distribution.

Materials and Methods

PEGDA/gelatin hydrogels containing 0–200 ppm $AgNO_3$ were synthesized via electron beam irradiation, enabling simultaneous crosslinking and *in situ* formation of AgNPs. Structural characterization was performed using infrared microspectroscopy, SEM–EDX, TEM, and XPS. Antibacterial mechanisms were investigated using real-time single-cell imaging of *Escherichia coli* based on Min protein oscillations. Cytotoxicity was evaluated using A549 cells.

Results

Infrared microspectroscopy revealed increased heterogeneity within the hydrogel matrix at higher Ag concentrations, attributed to interactions between silver ions and polymer components. Morphological and elemental analyses confirmed successful incorporation and distribution of AgNPs, with increasing particle size at higher precursor concentrations. Real-time single-cell imaging showed that AgNP-loaded hydrogels disrupt Min protein oscillations, a key regulator of bacterial division, leading to rapid cessation of oscillatory behavior within minutes. This effect was strongly concentration-dependent, with higher Ag levels inducing faster bactericidal responses. Cytotoxicity studies demonstrated a concentration-dependent effect, where lower Ag content maintained high cell viability while preserving antibacterial activity, indicating a favorable balance between biocompatibility and function.

Conclusion

This study reveals, in real time, how AgNP-loaded hydrogels disrupt bacterial behavior at the single-cell level. By relating hydrogel structure to antibacterial activity and cytocompatibility, it provides clear guidance for designing effective antibacterial biomaterials.

Acknowledgements

Financial support from the Federal State of Germany, the Free State of Saxony, and the Republic of Türkiye Ministry of National Education is gratefully acknowledged. The authors thank colleagues at IOM, Prof. Cristina Flors (IMDEA Nanociencia, Madrid) and Ingrid V. Ortega for support, and Prof. Piet A. J. de Boer for providing plasmid pDR122.

References

[1]Li J., Mooney D.J. Designing hydrogels for controlled drug delivery. *Nat Rev Mater* 2016; 1; 16071.
[2]Şener Raman T. et. al. Tailoring PEGDA/gelatin hydrogels with silver nanoparticles: Mechanical characterization and bacterial inhibition studies. *Int J Biol Macromol* 2026; 340; 149996.

D2 – P065

Biotinylated nanoparticle-conjugated streptavidin-associated Salmonella enhances photodynamic therapy and systemic antitumor immunity

Park J.H.[1,3], Lee D.H.[2], Suh S.B.[1,2,*], Kim S.H.[1,3,*]
[1]Chemical and Biological integrative Research Center, Korea Institute of Science and Technology (KIST); [2]Bionics Research Center, Korea Institute of Science and Technology (KIST); [3]Medical Convergence Engineering, KU-KIST Graduate School of Converging Science and Technology, Seoul, Republic of Korea

Introduction

Photodynamic therapy (PDT) is a promising non-invasive cancer treatment, but its clinical efficacy is often limited by poor intratumoral accumulation, rapid clearance of photosensitizers, and insufficient systemic immune activation. To overcome these limitations, we developed a Streptavidin-Associated Salmonella-enabled PDT (SAS-enabled PDT) platform, in which secreted streptavidin binds biotinylated nanoparticles, enabling their deeper penetration and retention within tumors.

Materials and Methods

An attenuated *Salmonella typhimurium* strain was genetically engineered to secrete streptavidin through the flagellar type III secretion system under arabinose induction. Biotinylated nanoparticles (biotinylated NPs) were synthesized and characterized by dynamic light scattering and transmission electron microscopy to confirm their size distribution and morphology. In vitro, CT26 murine colon carcinoma cells were treated with biotinylated NPs and exposed to laser irradiation to evaluate phototoxicity and immunogenic cell death (ICD)-related responses, including HMGB1 release. In vivo, therapeutic efficacy was assessed in CT26 tumor-bearing mouse models by examining intratumoral nanoparticle retention, primary tumor suppression, and abscopal effects on distant untreated tumors. Systemic immune responses were further evaluated by monitoring survival, body weight, and the activation of CD4 and CD8 T cells, together with the production of cytokines and cytotoxic mediators associated with antitumor immunity.

Results

Biotinylated NPs formed uniform nanoparticles with an average diameter of approximately 19.3 nm in water (fig. 1a). Under light irradiation, biotinylated NPs induced dose-dependent cytotoxicity, reaching a maximum cell death rate of 93.7% (fig. 1b), and also elicited hallmark features of immunogenic cell death, accompanied by a gradual increase in released HMGB1 levels (fig. 1c). To determine whether streptavidin-secreting SAS(+) bacteria could transport biotinylated NPs deep into tumors, Cy5.5-labeled bacteria were intravenously injected, followed by arabinose induction and peritumoral administration of the nanoparticles. At 24 h after treatment, tumor sections were analyzed by fluorescence imaging, and colocalization of the Cy5.5 bacterial signal with the photosensitizer fluorescence confirmed that SAS(+) bacteria facilitated the intratumoral penetration and delivery of biotinylated NPs (fig. 1d). In the primary tumor model, unlike conventional repeated PDT (G6), which showed only temporary tumor growth inhibition and regrowth after discontinuation of photosensitizer administration, the SAS-enabled PDT group (G7) achieved durable tumor control after a single nanoparticle injection followed by repeated light irradiation (fig. 1 f). In the secondary tumor model, treatment of the primary tumor also significantly suppressed the growth of untreated distant tumors, demonstrating a pronounced abscopal effect. Notably, distant tumors in the SAS-enabled PDT group (G7) were completely eradicated after repeated irradiation, whereas bacterial monotherapy (G3, G4) showed progression similar to the control group, and repeated PDT (G6) alone showed only transient inhibition (fig. 1 g). Throughout treatment, mice maintained stable body weight in all groups (fig. 1h)

Conclusion

SAS-enabled PDT effectively overcomes key limitations of conventional PDT by improving intratumoral photosensitizer retention and amplifying systemic antitumor immunity. This biohybrid strategy induces potent local tumor ablation together with abscopal immune responses, highlighting its potential as a next-generation platform for cancer photodynamic immunotherapy.




Figure 1. Streptavidin-associated Salmonella-based photodynamic therapy induces immunogenic cell death and systemic antitumor immunity suppressing distant tumor growth (a) Dynamic size distribution of biotinylated NPs and TEM image (scale bar, 100 nm). (b) Cell viability measured by MTT assay 24 h after treatment with biotinylated NPs. (c) To assess HMGB1 release after PDT, CT26 cells were treated with biotinylated NPs (0–250 ng/mL), and cell-free supernatants were collected after 24 hour for HMGB1 quantification by ELISA. (d) Tumor fluorescence images showing bacteria (red) and BioPpIX-F127 (purple). Scale bar: 500 μm. (e) Schematic timeline of the abscopal experiment (f) Tumor size of the 7 groups (n=5). (g) Secondary tumor size of the 5 groups (n=5). (h) Relative body weight profile during treatment. Groups were assigned as follows: G1, PBS; G2, biotinylated NPs; G3, SAS(–); G4, SAS(+); G5, biotinylated NPs@SAS(–); G6, biotinylated NPs (4×); and G7, biotinylated NPs@SAS(+). SAS(+) indicates arabinose-induced streptavidin secretion, whereas SAS(–) indicates the non-induced condition without arabinose treatment. All groups (G1–G7) were subjected to laser irradiation (Laser on).

D2 - P066

Multi-modal hyaluronic acid-derived hydrogels for therapeutic EVs delivery in tendinopathy

Stiliyanov-Atanasov K.[1], Torres Pérez M.D.[2], Carballal-Novoa R.[2], Martínez-Conesa E.[3], Calvo-Benito J.[3], Gómez-Florit M.[1]
[1]Health Research Institute of the Balearic Islands (IdISBa), Palma; [2]CINBIO - University of Vigo (UVigo), Vigo; [3]Blood and Tissue Bank of the Balearic Islands (FBSTIB), Palma, Spain

Introduction

Tendinopathy is a group of chronic and acute diseases affecting tendons, the treatment of which is limited to non-steroidal anti-inflammatory drugs or surgical intervention in acute cases. The causes for tendinopathy range from genetic and systemic factors to traumatic or overuse injuries, and the histological consequences include increased inflammatory cell migration, neo-angiogenesis, fibrous scar formation and chondrogenic switch, leading to tissue dysfunction. In previous works, extracellular vesicles (EVs) derived from platelet lysate improved tenogenic differentiation of tendon-derived stem cells (TDCs) in healthy and inflammatory conditions. The objective of this work was to develop a hydrogel for the sustained and localised delivery of platelet EVs in injured tissues.

Materials and Methods / Results

Chemically modified hyaluronic acid was used as base macromolecule, a bicomponent approach for the synthesis of a bulk hydrogel from hyaluronic acid. Hydroxy groups were oxidised to aldehyde (aHA), alternatively, amino groups were functionalised with an adipic acid dihydrazide molecule (adhHA), obtaining two HA molecules with compatible chemistry (Azido-aldehyde) and reversible bond dynamics (reflected on the shear thinning properties of the hydrogels). Confirmative hyaluronidase-mediated degradation assay was performed. EVs were isolated from platelet concentrates (platelet lysate and activated platelets supernatant) using qEV size-exclusion chromatography. EV characterisation of size, surface markers and concentration was performed following MISEV guidelines. EVs were loaded onto the bulk hydrogel (adh-aHA) or the microgels (norHA) following staining with lipophilic tracer dye (DiI) and cisteine-containing fluorescent peptides. The release of the EVs was quantified through fluorescence present in the supernatant of hydrogels incubated in PBS at 37ºC at different timepoints. Tendon-derived cells were cultured in indirect contact with the hydrogels for 4 timepoints (12, 24, 48 and 72 h) and flow cytometry was used to measure uptake kinetics by DAPI counterstaining for cells. COMSOL-based simulation of EVs diffusion through the extrinsic and intrinsic tendon compartments by mesh simplification of confocal image reconstruction of tissue-cleared samples and biphasic modelling of an anisotropic complex body. Tendon explants will be used to confirm the kinetics of EVs penetration.

Conclusion

The formulation offers a controlled release of EVs for the minimally invasive treatment of tendinopathy while maintaining biocompatibility and degradability.

Acknowledgements

Funding for KSA and MGF for the PhD Fellowship in Health Research Personnel (P-FIS) (KSA) and Consolidation (Miguel Servet / AES-LEIS) (MGF) from the Health Research Institute Carlos III (ISCIII), AES.

D2 – P067

Skeletal muscle regeneration following volumetric muscle loss using bioactive glass-biopolymer composite

Magyari K.[1,2], Feraru A.[1,3], Tóth Z.-R.[1], Bobu E.[1,3], Zăvoi A.[4], Ablassmaier T.[4], Mureșan S.[4], Purdoiu R.[4], Bel L.[4], Taulescu M.[4], Dreancă A.[4], Baia L.[1,5]

[1]Interdisciplinary Research Institute on Bio-Nano-Sciences, Babes-Bolyai University; [2]INSPIRE Research Platform InfoBioNano4Health & Biomedical Imaging, Babeș Bolyai University; [3]Doctoral School in Physics, Faculty of Physics, Babes-Bolyai University; [4]Faculty of Veterinary Medicine, University of Agricultural Science and Veterinary Medicine; [5]Faculty of Physics, Babes-Bolyai University, Cluj-Napoca, Romania

Introduction

Injuries with volumetric muscle loss (VML) lead to significant impairment in functional abilities. Biomaterials that provide structural support and deliver cells or growth factors are promising for muscle regeneration. Alginate (Alg) is a biocompatible water-soluble linear polysaccharide with the capability to retain a large amount of fluid, usable in regenerative medicine. Cellulose (MCC) is a linear polysaccharide with high specific mechanical properties, biocompatibility, and non-toxicity, usable in multifunctional scaffolds. Bioactive glasses doped with gold nanoparticles (BGAuSP) can stimulate the tissue regeneration process by promoting angiogenesis, offering a cost-effective alternative to growth factors for neovascularization.

Aim

In our previous study[1], an in vivo evaluation of spherical gold nanoparticles doped bioactive glass-alginate-cellulose (BGAuSP-Alg-MCC) composite using the murine VML model of the tibialis was performed. It was demonstrated that the composite material integrated well into the surrounding tissue and supported the formation of new myofibers. Based on these results, the composite beside the commercial hydrogels was introduced into the canine model to assess its translational potential in larger, multi-muscle defects (Fig.1).




Fig. 1 Muscle regeneration with BGAuSP-Alg-MCC and Hydrosorb® Gel

Materials and Methods

The BGAuSP was prepared via the sol-gel method, inducing the spherical gold nanoparticles in the sol. The BGAuSP-Alg-MCC composite was synthesized via ionic cross-linking using calcium carbonate ($CaCO_3$). MTT assay was used for cytotoxicity evaluation. A 3-year-old, previously healthy, spayed mixed-breed dog (30 kg) was severely injured by a weed trimmer. Written informed consent was obtained from the owner for the participation of their animal in this study. Under general anesthesia, the dead space was filled with BGAuSP-Alg-MCC composite, followed by the application of Hydrosorb® Gel to maintain wound hydration and support early granulation. This provided additional support to the regenerative function of the implanted biomaterial, with a skin transposition flap ultimately used to cover the defect. Computed tomography (CT) evaluations immediately after the surgical transposition flap, one month, and three months postoperatively. For histology and immunohistochemistry evaluation, at 3 months post-implantation, tissue samples were obtained using a punch biopsy technique.

Results

FT-IR and Raman spectra demonstrated cross-linking between biopolymers, and between BGAuSP and biopolymer composites. The TEM micrographs reveal that the pore size of the composite increases with MCC addition. The viability of keratinocyte and cardiomyocyte cells after 24 h interaction with samples indicates good in vitro tolerance. CT and histological evaluation confirmed adequate vascularization and tissue remodelling, suggesting the composite can provide structural support even in large.

Conclusion

In conclusion, the canine model with complex volumetric muscle loss showed functional recovery after reconstructive surgery using a BGAuSP-Alg-MCC composite paired with Hydrosorb® Gel.

Acknowledgements

This work was supported by a grant of the Ministry of Research, Innovation and Digitization, CNCS - UEFISCDI, project number PN-IV-P1-PCE-2023-1377, within PNCDI IV.

References

[1]Feraru A., Zavoi A., Magyari K., Toth Zs.R., Bobu E., Pall E., Dreanca A., Negoescu A., Taulescu M., Cenariu M., et al, Skeletal muscle regeneration using bioactive glass-alginate-cellulose composites, *I J Biol Macromol* 2025; 330; 148032.

D2 – P068

Oxidized pullulan – Alginate biomaterials as hemostatic agents

Bobu E.[1,2], Todea M.[2], Toth Z[2]., Dreanca A[3], Muresan S.[3], Sarpataki O[3], Magyari K.[2,4], Baia M.[4,5]
[1]Doctoral School of Physics, Faculty of Physics, Babeș-Bolyai University; [2]Interdisciplinary Research Institute in Bio-Nano-Sciences; [3]Faculty of Veterinary Medicine, University of Agricultural Science and Veterinary Medicine; [4]INSPIRE Research Platform, Babes Bolyai University; [5]Faculty of Physics, Babeș-Bolyai University, Cluj-Napoca, Romania

Introduction

Biomaterials in hemostasis should possess characteristics such as biocompatibility, good porosity, controllable degradability, rapid blood stoppage and a common approach to acquire them involves combining multiple biopolymers. Alginate and pullulan are bacterial polysaccharides used in tissue engineering. Alginate has good porosity but doesn't promote cells proliferation, whereas pullulan dissolves rapidly in water but is biocompatible.

Aim

This study aims to analyze the effect of oxidizing pullulan—which is subsequently crosslinked with alginate—on the structure and hemostatic properties of the resulting biomaterials.

Materials and Methods

Pullulan was oxidized with sodium periodate. Different quantities of alginate were then added, and the two biopolymers were crosslinked in a 4% $CaCl_2$ solution. The samples were lyophilized to become porous sponges.

XPS measurements and cell viability assays were performed to confirm the oxidation and biocompatibility of the oxidized polysaccharide.

FT-IR and SEM measurements were conducted to assess the biopolymers crosslinking and the samples morphology in terms of porosity. Water up-take was also evaluated. *In vitro* hemocompatibility assay was performed by respecting ISO10993-4 and clotting times were determined as described by Herliana et al, 2024.

Results

XPS data confirmed the oxidation of pullulan. In the FT-IR spectrum of pullulan the band around 1730 cm^{-1} demonstrated the oxidation of pullulan. Moreover, the small modifications in the vibrational bands of polymers proved their successful crosslinking. Cell viability assays shown that oxidation doesn't introduce toxicity to samples but improve the cell proliferation and the samples swell up to 2100% in first 20 minutes. All tested biomaterials exhibited favorable hemolysis percentage (2-4%). However, the Alg-0.75Pll-1ox sample demonstrated potent pro-coagulant activity, with a clotting induction time of 2.45 min, compared to 6.30 min for Alg one. This rapid thrombus formation is attributed to the electrostatic interaction between the pullulan cationic surface and negatively charged blood components, thereby facilitating the activation of the intrinsic clotting cascade.

Conclusion

Our results indicate that the interplay between swelling-induced viscosity and the intrinsic porosity of alginate-oxidized pullulan scaffolds optimizes their performance as wound-dressing materials. These composites not only sequester exudate through superior absorption but also serve as a structural template for cell-material interactions.

Acknowledgements

This work was supported by a grant of the Ministry of Research, Innovation and Digitization, CNCS -UEFISCDI, project number PN-IV-P1-PCE-2023-1377, within PNCDI IV.

References

[1]Herliana H., Yusuf H.Y., Laviana A., Wandawa G., Abbas B. In Vitro Hemostatic Activity of Novel Fish Gelatin–Alginate Sponge (FGAS) Prototype. *Polymers* 2024; 16(14); 2047.

D2 – P069

Mesenchymal stem cell-derived extracellular matrix sponge promotes regenerative healing and prevents scarring in burn wounds

Kwon JW[1], Ahn BH[1,2], Park K[1,2]
[1]Center for Biomaterials, Korea Institute of Science and Technology (KIST); [2]Division of Bio-Medical Science and Technology, KIST School, University of Science and Technology (UST), Seoul, Republic of Korea

Introduction

Burn injuries cause severe skin damages. Particularly, third-degree burn results in excessive scar formation, leading to functional impairment. Scar development is largely associated with persistent activation of myofibroblasts, which drive wound contraction and excessive extracellular matrix (ECM) deposition. Such burn wounds are still hard to handle. Here, we report an ECM sponge composed entirely of mesenchymal stem cell-derived ECM that enables a scar-free regenerative healing in deep burn wounds.

Materials and Methods

Umbilical cord-derived mesenchymal stem cells (UCMSCs) were cultured in vitro to yield cell-derived ECM, followed by decellularization to obtain UCMSC-derived decellularized matrix (UMDM). The matrix was subsequently lyophilized to fabricate a porous ECM sponge (UMDM sponge; US), which was later transplanted into murine deep burn wound model for up to 45 days. Its therapeutic efficacy was directly compared with PELNAC™ (PN), a commercial collagen sponge. The regenerated wound tissues were extensively evaluated via histological staining, immunofluorescence and mechanical measurement. In addition, mechanistic study of myofibroblast activation was carried out in vitro with human skin fibroblasts by analyzing ACTA2 mRNA and myofibroblast-associated proteins, while the same experiments were conducted with the cells grown on tissue culture plastic (TCP) and collagen-coated plates (CCP), respectively.

Results

The US significantly enhanced wound healing compared with the commercial PN. On day 45 as an end point of experiment, the US-treated group showed regenerative skin architecture without scar characteristics: hair follicles formation, regular ECM organization and significantly enhanced tensile strength (Fig. 1). Under TGF-β stimulated fibroblast–myofibroblast transition (FMT) in vitro, while TGF-β initially upregulated ACTA2 gene and SMAD2 phosphorylation in all groups, fibroblasts on UMDM disclosed significantly lower ACTA2 level and a rapid decline of p-SMAD2 within 24 h (Fig 2A, B). In addition, typical markers of myofibroblasts, α-SMA and collagen I were significantly downregulated at 72 h, indicating a strong attenuation of profibrotic signaling of myofibroblasts on UMDM (Fig 2C).




Figure 1. Evaluation of scar formation by tensile testing and histological analysis on day 45. (A) Representative H&E-stained scar tissue. (B) Herovici's stained images. (C) High-magnification PSR stained dermis showing collagen arrangements. (D) EVG stained images showing elastic fibers (black) and collagen (red-pink). (E) Stress–strain curves (MPa–%) of scar tissues. (F–H) Quantitative mechanical properties: (F) Young's modulus (MPa), (G) tensile strength at break (MPa), and (H) strain at break (%).Statistical significance: *p < 0.05, **p < 0.01, ***p < 0.001, ****p < 0.0001.




Fig 2. Third-degree burn wound model and observation of transplanted sponges. (A) Immunofluorescence images showing α-SMA (Green) expression in fibroblasts at 0, 24, and 72 h after TGF-β treatment. Counterstained with DAPI (Blue) and F-actin (Red). Yellow triangle indicates activated myofibroblasts. (B) Relative *ACTA2* mRNA expression in myofibroblast cultured on TCP, CCP, and UMDM following TGF-β-induced activation over time (0, 2, 4, 12, 24, 48, and 72 h). (C) Western blot images showing α-SMA, Collagen I, p-SMAD2, and total SMAD2 protein expression at later time points (0, 24, and 72 h) after TGF-β treatment in myofibroblast cultured on TCP, CCP, and UMDM.

Conclusion

We found that MSC-derived ECM sponge could promote scar-free healing in deep burn wounds by suppressing myofibroblast activation. Our finding suggest that the UMDM sponge is a promising regenerative biomaterial for burn wound therapy.

Acknowledgements: This research was supported by the Korean Fund for Regenerative Medicine (KFRM) grant (KFRM25A0206L1) funded by the Ministry of Science and ICT, Republic of Korea.

D2 – P070

Tannic acid loaded collagen and elastin conduits for paediatric right ventricular outflow tract reconstruction

Basu P.[1,2,3], O'Brien F.J.[3], Brougham C.M.[1,2,3]
[1]CÚRAM, Research Ireland Centre for Medical Devices, University of Galway; [2]tPOT, School of Mechanical Engineering, Technological University Dublin, Ireland; [3]Tissue Engineering Research Group, Royal College of Surgeons Ireland, Ireland

Introduction

Congenital heart disease can affect the functionality of the right ventricular outflow tract (RVOT) and when left untreated triggers further complications. The current treatment gold standard is to use a homograft as a replacement RVOT; however, homografts have inherent challenges such as low availability and structural degeneration. This work focuses on the development of a 'bioactive shunt' for RVOT treatment, through the development of a collagen-elastin conduit with an aligned fibre structure, loaded with a plant polyphenol, tannic acid (TA). A key requirement of this RVOT is an antithrombotic coating which we wish to create through recruitment of endothelial progenitor cells in situ. The aim of this study was materials development for this application.

Materials and Methods

Collagen and elastin [Collagen: Elastin (w/w%) = 1:1.5] were mixed in 0.05M aqueous acetic acid solution, stirred (15000 rpm) at 4ºC for 60 minutes and then degassed. Aqueous Tannic acid (TA, 1mg) was added prior to extrusion into tubular moulds, followed by freezing with liquid nitrogen, before freeze drying for 36h. Subsequently conduits were UV-crosslinked (45000µJ /cm^2 for 30 min) and then stored for physico-mechanical analysis: scanning electron microscopy (SEM), Energy Dispersive X-ray Spectroscopy (EDS), Fourier Transform Infrared spectroscopy (FTIR), uniaxial and biaxial tensile properties. Initial degradation and cellular experiments were also conducted.

Result

The morphological analysis with SEM indicated that the collagen elastin fibres have longitudinal orientations within the conduits. Images of the conduits' cross-section show porosity suitable for this application. Additionally, FTIR showed that suitable levels of TA remained in the conduits post processing. The tensile, degradation and cellular experiments indicated that the conduit has suitable properties to function as an RVOT.

Conclusion

The physico-mechanical properties of the conduits exhibited suitable surface properties, pore architecture and elasticity for the application. Initial cellular experiments show potential for in situ endothelial recruitment. Taken together, the results indicate that this conduit warrants further investigation as a promising next generation of RVOT treatment in CHD patients.

Acknowledgements

Marie Skłodowska-Curie Actions Grant Agreement [Grant Agreement No. 101081457] and in part from CÚRAM, Research Ireland Centre for Medical Devices [under Grant Reference 13/RC/2073_P2].

D2 – P071

Hybrid polyphosphoester–carboxymethylchitosan scaffolds based on emulsion templating for tissue engineering

Seronvalle L.[1], des Rieux A.[2], Jérôme C.[1], Debuigne A.[1]
[1]Center for Education and Research on Macromolecules, University of Liège, Liège; [2]Louvain Drug Research Institute, Université Catholique de Louvain, Bruxelles, Belgium

Introduction

Porous polymer scaffolds play a key role in tissue engineering (TE) by facilitating cell growth and contributing to the restoration of tissue and organ function. Key features of these scaffolds include biocompatibility, tunable degradation rates, mechanical properties compared to native tissue, cell adhesion and controlled porosity to facilitate implant colonisation and nutrient transport. Polyphosphoesters (PPEs) emerge as promising candidates for TE given their biocompatibility, tunable hydrophilicity, and degradation rate by varying their side groups. Previous work structured hydrophilic PPE into porous scaffolds via high internal phase emulsion (HIPE)-templated polymerisation, in which biological assays showed good cytocompatibility and high cell viability, but limited cell adhesion.[1]

Aim

This project aims to incorporate carboxymethylchitosan (CMCh) or methacrylated CMCh (CMCh-MA) into emulsion-templated PPE-based polyHIPEs to benefit from the cell-adhesive and antibacterial properties of CMCh.

Materials and Methods

PPE, bearing methoxy pendent groups and methacrylate as the chain ends, were synthesised by ROP, while CMCh was modified with glycidyl methacrylate to form CMCh-MA. The PPE-based polyHIPEs were formulated with CMCh or CMCh-MA by the emulsion-templated method and photo-crosslinking at 365 nm. The incorporation of CMCh into the polyHIPE was evaluated by solid-state NMR and its impact on the porous morphology and mechanical properties of scaffolds. Antibacterial properties of the CMCh/PPE scaffolds are currently under investigation. Biological tests using stem cells of the apical papilla (SCAP Luc+) were conducted to characterise the scaffolds' cell adhesion properties.

Results

Hybrid polyHIPEs were formulated using reactive PPE precursors and CMCh or CMCh-MA, yielding semi-interpenetrating networks (SIPNs) and co-networks, respectively. The resulting scaffolds exhibited porous structures (30-65 µm) that increased with CMCh content, while mechanical properties remained comparable to those of pristine PPE scaffolds (Table 1). Solid-state NMR revealed CMCh diffusion out of the matrix. This observation is consistent with biological assays, which showed limited cell adhesion for {PPE/CMCh} scaffolds compared to {PPE/CMCh-MA} scaffolds (Figure 1).

Conclusion

The present study demonstrates that incorporating CMCh in the polyHIPE influences its porosity but has no impact on cell adhesion. In contrast, chemical anchoring of CMCh-MA into the PPE scaffolds improves cell adhesion. Bioluminescence assays will be conducted to confirm the promising character of those CMCh/PPE hybrid materials for tissue engineering applications.

Acknowledgements

The authors acknowledge FRS-FNRS (FRIA grant) for funding.

Table 1: Formulation of PPE-based polyHIPEs and characterisation.

Sample name [a]	CMCh additives (wt%) [b]	Type of interaction/ network with CMCh	D (µm) [c]	d (µm) [d]	E (kPa) [e]
A	/	/	40.1 ± 8.2	14.0 ± 2.9	11.0 ± 4.5
B	CMCh (8.3)	Semi-interpenetrated network	32.8 ± 10.5	10.5 ± 3.3	7.1 ± 1.9
C	CMCh (12.5)	Semi-interpenetrated network	65.2 ± 14.2	22.6 ± 6.8	11.9 ± 2. 8
D	CMCh-MA (4.2)	Co-network	48.8 ± 14.8	18.4 ± 6.2	5.9 ± 1.1

[a] Conditions: external phase: PM-DMA (30 wt% compared to aqueous phase), F-68 surfactant, LAP photoinitator. Internal phase: mineral oil. O/W v/v = 85/15, photocuring at 365 nm for 15 min. [b] CMCh-based additives (wt% compared to PPE). [c] Mean pore diameter. [d] Mean window diameter. [e] Young's Modulus measured by compression tests.




Figure 1: CLSM images of cell morphology after day 1, 4, and 7 of culture on the unmodified PPE scaffold (A), the {CMCh/PPE} scaffold (B), and the {CMCh-MA/PPE} scaffold (C) (DAPI: nuclei are in blue, CellMask: plasma membrane in red, Alexa Fluor: actin filament in green).

References

[1]Boucq P., Ucakar B., Debuisson F., Riva R., des Rieux A., Jérôme C., Debuigne A. High Internal Phase Emulsion-Templated Hydrophilic Polyphosphoester Scaffolds: Tailoring the Porosity and Degradation for Soft Tissue Engineering. *Biomacromolecules* 2025; *26*(3); 1935–1947.

D2 – P072

Stem cells and vascular fragments as a cell component for soft tissue replacements

Musilkova J.[1], Sedlar A. [1], Beran M.[2], Wu YC.[1], Slepička P.[3], Molitor M.[4], Bacakova L.[1]
[1]Laboratory of Biomaterials and Tissue Engineering, Institute of Physiology of the Czech Academy of Sciences; [2] Czech Agrifood Research Centre; [3]Dept. of Solid State Engineering, University of Chemistry and Technology in Prague; [4]Dept. of Plastic Surgery, First Faculty of Medicine, Charles University and Na Bulovce Hospital, Prague, Czech Republic

Introduction

Modern tissue engineering combines a biodegradable polymeric scaffold with a cellular component to enable tissue self-regeneration and the prolonged lifespan of tissue replacements. The biodegradable scaffold provides temporary mechanical support for cell adhesion, proliferation, and differentiation. Prevascularization of the tissue substitutes is essential for their survival after implantation.

Aim

Our focus was on the colonization of scaffolds with cells and the development of a vascular system within them. We also examined the feasibility of using vascular fragments (VFs) isolated from lipoaspirates after liposuction using methods similar to those used for adipose-derived stem cells (ADSCs).

Materials and Methods

We tested several bioresorbable polymer scaffolds, including 3D-printed polylactide (PLA) and polycaprolactone (PCL) scaffolds and foams with a hierarchically organized porous structure prepared by lyophilization with the addition of water-soluble porogens (NaCl and Klucel). For the cellular component, we used a combination of adipose-derived stem cells (ADSCs) and human umbilical vein endothelial cells (HUVECs). We monitored cell colonization of the construct and vascular system formation over ten days in static and dynamic systems. We followed cell penetration inside the scaffold using fluorescence staining with phalloidin, DAPI, and the specific endothelial marker VE-cadherin with a Dragonfly 503 confocal microscope. So far, the survival and development of VF have been tested only at the level of collagen hydrogel.

Results

We have found that the pores in all the scaffolds were interconnected and well-colonized by both cell types. Dynamic cultivation also enhanced the formation of pre-vascular structures in the scaffolds when ADSCs were co-cultured with HUVECs (Fig.1). VFs were detected in large amounts in the collagen gel after 3, 7, and 14 days; the addition of ADSCs supported their growth (Fig.2).

Conclusion

Co-culturing ADSCs and HUVECs on the tested scaffolds provides a foundation for vascular structure. These cells can be used to pre-vascularize tissue substitutes. Using VFs for pre-vascularization is also promising.

Acknowledgements

Supported by the OP JAC Project „EXREGMED“ No. CZ.02.01.01/00/22_008/0004562 of the Ministry of Education, Youth and Sports of the Czech Republic, co-funded by the European Union, and by the *Praemium Academiae* grant No. AP2202 of the Czech Academy of Sciences.




Fig. 1: Co-cultivation of ADSCs with HUVECs on a 3D-printed PLA scaffold. The pre-vascular structure is visualized by immunofluorescence staining of an endothelial marker VE-cadherin (green). The F-actin cytoskeleton in the cells was stained with Alexa Fluor 568-conjugated phalloidin (orange), cell nuclei are counterstained by DAPI (blue). Dragonfly 503 confocal microscope (Obj. 20x).




Fig. 2: VFs after 7 days of cultivation on collagen hydrogel. The VF structure is visualized by immunofluorescence staining of an endothelial marker VE-cadherin (green). Cell nuclei are counterstained by DAPI (blue). Dragonfly 503 confocal microscope (Obj. 20x)

D2 – P073

Serum-Free generation of cell-derived extracellular matrix from human dermal fibroblasts and adipose-derived stem cells

Nellinger, S.[1], Ruggieri, S.[1], Kluger P.J.[2]
[1]Institute of Interfacial Process Engineering and Plasma Technology, University of Stuttgart; [2]Institute for Interfacial Engineering and Biotechnology IGB, Fraunhofer Society, Stuttgart, Germany

Introduction

The extracellular matrix (ECM) is a fundamental component of the cellular microenvironment and plays a critical role in regulating cell behavior, tissue organization, and regeneration. Cell-derived extracellular matrices have gained increasing attention in tissue engineering and regenerative medicine because they more closely mimic the structural and biochemical complexity of native tissues compared to synthetic biomaterials. However, most established protocols for the generation of cell-derived ECM (cdECM) rely on serum-containing culture conditions. The presence of serum introduces significant batch-to-batch variability, undefined components, and potential safety concerns, which collectively limit the reproducibility and translational applicability of cdECM-based biomaterials. Developing reliable strategies for cdECM production under fully defined, serum-free conditions therefore represents an important step toward improving standardization and clinical relevance.
In this study, we investigated the feasibility of generating robust cdECM under serum-free culture conditions using two human cell sources commonly employed in regenerative medicine: human dermal fibroblasts and adipose-derived stem cells (ADSCs).

Materials and Methods

Cells were cultured in defined, serum-free media optimized to support cell viability, proliferation, and matrix deposition. CdECM produced in serum-containing medium served as a control. Following matrix deposition, decellularization procedures were applied to remove cellular components while preserving the structural integrity of the deposited ECM. For characterization of the generated cdECM, histological and immunohistological stainings were performed. The collagen content was determined by hydroxyproline assay and the amount of sulfated glycosaminoglycans (sGAGs) was quantified by DMMB assay.

Results

Microscopic analysis revealed the formation of dense and interconnected fibrillar networks. To further characterize the generated matrices, histological and immunohistological analyses were performed to assess cdECM composition and organization. Histological staining confirmed the presence of extensive extracellular matrix deposition and revealed well-structured fibrous networks throughout the decellularized matrices. Immunohistochemical staining demonstrated the presence of key ECM proteins typically associated with connective tissue matrices, including major structural components such as collagen and fibronectin. The distribution patterns of these proteins indicated a well-developed matrix architecture with organized fibrillar structures supporting the overall scaffold integrity. The differences in matrix morphology and immunohistological staining patterns indicate potential variations in ECM composition and organization, which may influence downstream cell–matrix interactions.

Conclusion

Overall, our results establish a reproducible approach for producing cdECM from human dermal fibroblasts and ADSCs under fully serum-free conditions. The resulting matrices provide a biologically relevant platform for investigating matrix-driven regulation of cell. Future work will focus on detailed compositional analyses of the generated matrices and on evaluating their functional properties in supporting cell adhesion, proliferation, and differentiation. The establishment of standardized serum-free cdECM systems may ultimately contribute to more reliable in vitro models and improved translational strategies in regenerative medicine.


D2 – P074

Design and development of a biphasic scaffold mimicking the native architecture of the intervertebral disc

Bedmuthan T., Srivastava A.*
Dept. of Medical Devices, National Institute of Pharmaceutical Education and Research-Ahmedabad (NIPER-A), Dept. of Pharmaceuticals, Ministry of Chemicals and Fertilizers, Palaj, Opp. Air force station, Gandhinagar, Gujarat, India

Introduction

Intervertebral disc (IVD) degeneration is a major cause of chronic low back pain, yet current clinical interventions remain limited in restoring the native structure and function of the disc. The intrinsic biphasic architecture of the IVD—comprising the lamellar annulus fibrosus (AF) and the hydrated nucleus pulposus (NP)—poses a significant challenge for tissue engineering strategies. In this study, we report the design and development of a biomimetic biphasic scaffold that integrates electrospun nanofibers with a cryogel matrix to recapitulate the structural, mechanical, and biological characteristics of the native IVD. The electrospun nanofibrous layer is engineered to mimic the lamellar architecture of the AF, providing directional mechanical reinforcement and promoting cellular alignment. In parallel, the cryogel component reproduces the highly hydrated and viscoelastic nature of the NP, enabling effective load-bearing under compressive stress while supporting a favorable cellular microenvironment. The resulting composite scaffold exhibits region-specific mechanical behavior and structural integrity essential for functional disc regeneration. Furthermore, the biomimetic interface between the two phases facilitates cell–matrix interactions, extracellular matrix deposition, and tissue integration. Collectively, this electrospun nanofiber–cryogel platform demonstrates strong potential as a next-generation scaffold for intervertebral disc tissue engineering. This work establishes a versatile and translational strategy toward the development of advanced regenerative therapies for IVD degeneration, with future studies aimed at comprehensive in vitro and in vivo validation.





Materials and Methods


Poly (vinyl alcohol) (Mw 146,000; 87–89% hydrolyzed), glutaraldehyde, and polycaprolactone (Mw 80,000) were procured from Sigma-Aldrich and used in this study. Acetone, dimethylformamide (DMF), and chloroform were obtained from Qualigens, Thermo Fisher Scientific, Mumbai, India, while ethanol was supplied by Baroda Chemical Industries. Graphene oxide was also utilized as received. Unless otherwise specified, all chemicals were used without further purification.


Results

MTT Assay













Biphasic Scaffold **Hemocompatible**









Conclusion

The biomimetic biphasic scaffold successfully replicates the structural and functional characteristics of the native intervertebral disc by integrating electrospun nanofibers and a cryogel matrix. It demonstrates region-specific mechanical performance and supports cellular activity essential for tissue regeneration. This platform offers a promising and translational approach for advancing regenerative therapies for intervertebral disc degeneration.

Acknowledgements

Mrs. Mounika Seervi for Scanning Electron Microscopy & Confocal Imaging experiments.

Funding

Department of Pharmaceuticals, Ministry of Chemistry and Fertilizers

References

[1]Agarwal G., Roy A., Singh A.A., Kumar H., Mandoli A., Srivastava A. BM-MSCs-loaded-Graphene-Collagen Cryogels Ameliorates Neuroinflammation in Rat Spinal Cord Injury Model. *ACS Applied Bio Materials* 2024; 7(3); 1478-1489.

D2 – P075

Enhanced osteogenic differentiation and cell adhesion on exosome-coated polydopamine-modified nanofibrous scaffolds

Mahmoudifard M., Andrade J.C., Boccaccini A.R.
[1]Institute of Biomaterials, Dept. of Materials Science and Engineering, Friedrich-Alexander-Universität Erlangen-Nürnberg (FAU), Erlangen, Germany

Introduction

Bone tissue engineering requires biomimetic scaffolds capable of enhancing cell adhesion and osteogenic differentiation. Exosomes have emerged as a promising cell-free alternative to stem cell therapies due to their ability to transfer bioactive molecules without associated risks [1,2]. In this study, we investigate exosome-coated nanofibrous scaffolds functionalized with polydopamine (PDA) to improve exosome immobilization and biological performance.

Materials and Methods

Electrospun polyvinyl alcohol (PVA)/chitosan nanofibrous scaffolds were fabricated and crosslinked using glutaraldehyde. Surface modification was achieved via PDA coating to enhance exosome adhesion. Exosomes were isolated from osteogenically induced human adipose-derived stem cells and characterized by NTA and SEM (~115 nm). MC3T3-E1 pre-osteoblasts were seeded on four scaffold groups. Cell viability was assessed by WST-8 and Calcein-AM staining, while morphology and adhesion were evaluated by SEM (Fig. 1). Osteogenic differentiation was analyzed via ALP activity and immunocytochemistry (Fig. 2).

Results

PDA coating significantly improved exosome immobilization, resulting in more homogeneous distribution on nanofibers (Fig. 1). Biological assays demonstrated enhanced cell viability, adhesion, and spreading on exosome-coated scaffolds, particularly in PDA+Exo samples. Calcein-AM staining revealed higher cell density and distribution on modified scaffolds. ALP activity showed an approximately two-fold increase in exosome-treated groups compared to controls (Fig. 2), indicating enhanced osteogenic differentiation. Furthermore, collagen type I and osteopontin expression were markedly upregulated, confirming improved osteogenic maturation [3–5].

Conclusion

The combination of PDA functionalization and exosome incorporation provides a synergistic effect that enhances cell adhesion, proliferation, and osteogenic differentiation. This approach represents a promising cell-free strategy for bone regeneration and highlights the potential of exosome-functionalized nanofibrous scaffolds in advanced tissue engineering applications.




Figure 1. SEM image of exosome-coated nanofibrous scaffolds showing enhanced exosome immobilization.




Figure 2. Cell viability (WST8 and Calcein-AM) and ALP activity and osteogenesis markers staining of MC3T3-E1 cells cultured on scaffolds.

Acknowledgments
This work was granted by the Alexander von Humboldt Foundation (fellowship to Dr. Matin Mahmoudifard).

References

[1]Bose S., Roy M., Bandyopadhyay A. Recent advances in bone tissue engineering scaffolds. *Trends in Biotechnology* 2012; 30(10); 546–554.
[2]Liu Y., Ma Y., Zhang J., Yuan Y., Wang J. Exosomes: a novel therapeutic agent for cartilage and bone tissue regeneration. *Dose-Response* 2019; 17(4); 1559325819892702.
[3]Kang M., Lee C.S., Lee M. Bioactive scaffolds integrated with liposomal or extracellular vesicles for bone regeneration. *Bioengineering* 2021; 8(10); 137.
[4]Chen Y., Dong X., Shafiq M., Myles G., Radacsi N., Mo X. Recent advancements on three-dimensional electrospun nanofiber scaffolds for tissue engineering. *Advanced Fiber Materials* 2022; 4(5); 959–986.
[5]Saraf M., Prateek R., Ranjan R., Balasubramaniam B., Thakur V.K., Gupta R.K. Polydopamine-enabled biomimetic surface engineering of materials: New insights and promising applications. *Advanced Materials Interfaces* 2024; 11(6); 2300670.

D2 – P076

A dermal decellularized extracellular matrix (d-ECM) scaffold developed for cardiac tissue engineering (CTE) is actively remodeled in vitro by resident human cardiac progenitor cells (hCPCs)

Menini A.[1], Romano V.[1], Izzo G.[1], Sacco A.M.[1], Ricci G.[2], Nurzynska D.[3], Sorrentino C.[1], Schonauer F.[1], Castaldo C.[1], Di Meglio F.[1]

[1]Dept. of Public Health, University of Naples Federico II, Naples; [2]Dept. of Experimental Medicine, Università della Campania, Napoli; [3]Dept. of Medicine, Pharmacy and Dentistry, University of Salerno, Baronissi, Italy

Introduction

Cardiac tissue engineering (CTE) underscores the pivotal role of the extracellular matrix (ECM) in maintaining the myocardium structural stability and functional capacity. Beyond acting as a physical scaffold, the cardiac ECM delivers a wide range of signals that influence the behavior of cardiomyocytes and supporting cells. In this framework, decellularized ECM (d-ECM) has gained recognition as a valuable biomaterial for CTE. Unlike synthetic constructs, d-ECM preserves the natural ability to be remodeled by cells, allowing it to respond and adapt to changing physiological conditions. Previous research has shown that decellularized human dermis can effectively support the engraftment and differentiation of human cardiac progenitor cells (hCPCs). Based on these findings, this study aimed to explore how dermal d-ECM is remodeled by differentiating hCPCs.

Materials and Methods

Human abdominal skin samples (n=20) from patients undergoing abdominoplasty were decellularized in a solution containing SDS, Triton X-100, and antibiotics. The effectiveness of cell removal was verified through hematoxylin and eosin (H&E) and DAPI staining, as well as quantification of residual double-stranded DNA (dsDNA). The resulting d-ECM was cryosectioned into 600-µm-thick three-dimensional scaffolds. hCPCs, isolated from explanted hearts (n=15), were seeded onto these scaffolds and cultured for two weeks. Myogenic differentiation was then induced using ascorbic acid and VEGF, followed by an additional two weeks of culture. Differentiation was assessed by real-time PCR. Matrix remodeling was evaluated through biochemical assays measuring glycosaminoglycans, collagen, and elastin, along with immunofluorescence analysis of laminin, fibronectin, and tenascin. Structural changes were further examined by scanning electron microscopy.

Results

Effective decellularization was confirmed by the absence of nuclei and low dsDNA levels (9.138±1.009 ng/mg). Gene expression analysis indicated successful myogenic differentiation, with increased expression of cardiomyocyte markers such as connexin-43, ACTC1, and MYH7B, alongside markers of other cardiac lineages. Recellularized scaffolds exhibited increased GAG content (2.434±0.533 vs 1.246±0.175 µg/mg) and reduced collagen (16.49±1.496 vs 29.42±2.298 µg/mg) and elastin (26.74±1.241 vs 33.94±1.973 µg/mg) levels compared to controls. Immunofluorescence revealed higher fibronectin and tenascin expression (6969±177.4 vs 5172±292.3 intensity/pixel² and 1210±66.82 vs 820.6±36.64 intensity/pixel², respectively), while laminin remained unchanged. SEM analysis showed a denser network of fine elastic-like fibers and fewer thick collagen bundles.

Conclusion

Overall, these results demonstrate that dermal d-ECM actively interacts with seeded cardiac cells and undergoes significant remodeling, supporting its potential as a biologically relevant, possibly autologous scaffold for cardiac tissue engineering.

D2 – P077

Identifying optimal matrix properties for expansion and differentiation of liver organoids

Carpentier N.[1*], van der Laan L.J.W.[2], Schneeberger K.[3], Spee B.[3], Van Vlierberghe S.[1]
[1]Polymer Chemistry & Biomaterials Group, Centre of Macromolecular Chemistry, Ghent University, Ghent, Belgium; [2]Dept. of Surgery, Erasmus MC-University Medical Center, Rotterdam, The Netherlands; [3]Dept. Clinical Sciences, Faculty of Veterinary Medicine, Utrecht University, Utrecht, The Netherlands

Introduction

Intrahepatic cholangiocyte organoids (ICOs) have great potential as cell source in liver tissue engineering for the development of bioengineered liver constructs. After being isolated, the culture of these ICOs consist of 2 phases. The proliferation phase and the differentiation phase towards mature hepatocyte-like cells, both requiring culture in materials with different properties. Proper culture matrices are currently still lacking. In this work, the optimal material stiffness is determined for each of the phases. The developed materials are optimized for volumetric bioprinting towards vascular constructs.

Materials and method

ICOs were initiated and cultured from liver tissue biopsies obtained during liver transplantation. GelSH was developed by the reaction of gelatin with N-acetyl homocysteine thiolactone according to a protocol described earlier. DexNB was developed via a conventional DCC/DMAP coupling chemistry between the hydroxyl groups of dextran and the carboxylic acid groups of 5- norbornene-2carboxylic acid. The ICOs were encapsulated in DexNB-GelSH with different concentrations of 5, 10 and 15 w/v% in the presence of LAP and irradiated for 15 minutes with UV-A light. To investigate the proliferation and maturation phase, the organoids are cultured in respectively expansion and differentiation medium.

Results and Discussion

The varying concentration of the hydrogel (i.e. 5, 10 and 15w/v%) corresponds to a stiffness of respectively 3, 6 and 12 kPa. A live/dead and cell proliferation assay revealed an increased proliferation of the ICOs in softer materials. In soft gels, the ICOs become larger and have a higher cell number. Immunofluorescence was performed using the mature hepatocyte markers CYP3A4, K18, ALB and MDR1. With increasing hydrogel stiffness, these markers are more upregulated indicating a high degree of organoid maturation towards hepatocyte-like cells. Using a VAM system of Readily3D, DexNB-GelSH could be printed into tubular constructs within seconds as a proof-of-concept towards the development of the liver sinusoid.

Conclusion

DexNB-GelSH enables to develop a hydrogel that both support the proliferation and the differentiation towards hepatocyte-like cells depending on the material stiffness and the material can be printed using VAM towards vascular liver constructs.

D2 – P078

In situ electrospinning of recombinant type V collagen fibers promotes craniofacial scarless wound healing via the PI3K-AKT pathway

Gao S.[1,2,3,#], Lin J.[1,2,3,#], Liu C.[3], Kai Zheng[2,3,*], Pan Y.[2,3,*], Wang L.[1,2,3,*]
[1]Dept. of Orthodontics, The Affiliated Stomatological Hospital of Nanjing Medical University, Nanjing, China; [2]State Key Laboratory Cultivation Base of research, Prevention and Treatment for Oral Diseases, Nanjing Medical University, Nanjing, China; [3]Jiangsu Province Engineering Research Center of Stomatological Translational Medicine, Nanjing Medical University, Nanjing, China；

Introduction


Craniofacial scarless wound healing remains challenging due to complex anatomy and high aesthetic demands. Current therapies often fail to restore native skin architecture without fibrosis. Recombinant human type V collagen (rHTVC) offers high biocompatibility and low immunogenicity, yet its therapeutic potential in wound healing is underexplored. In situ electrospinning enables direct deposition of nanofibrous scaffolds onto wound beds, providing both physical support and biochemical cues. This study aimed to investigate whether in situ electrospinning of rHTVC fibers promotes craniofacial scarless wound healing and to elucidate the underlying molecular mechanisms.


Materials and Methods

Recombinant human type V collagen was biosynthesized and purified. In situ electrospinning was performed using a portable handheld device (10-20 kV, 10-20 cm nozzle-to-collector distance), depositing rHTVC nanofibers directly onto wound beds. In vitro assays evaluated proliferation (CCK-8, EdU), apoptosis (flow cytometry), migration (scratch/Transwell), and angiogenesis (tube formation) in L929 fibroblasts, MAECs, and HOKs. RNA-seq and Western blot were performed to identify pathway activation. In vivo efficacy was assessed in zebrafish tail fin (n=8) and murine full-thickness craniofacial wound models (n=5 per group, 6 mm defect), with rHTVC applied on days 0, 3, 5, and 7 post-surgery. Histological analyses (H&E, Masson, Sirius Red) and immunofluorescence (VEGF, PDGF, CD31, Ki67, TUNEL) were conducted on day 10.

Results

rHTVC electrospun fibers (12.5% w/v) exhibited uniform, bead-free nanofibrous morphology with preserved collagen structure (FTIR, XPS). In vitro, rHTVC significantly enhanced proliferation, migration, and anti-apoptosis across all three cell lines, and promoted MAEC tube formation (nodes increased from ~700 to ~1000, $P<0.01$). RNA-seq revealed PI3K-AKT pathway enrichment, confirmed by elevated p-PI3K/PI3K and p-AKT/AKT ratios ($P<0.01$). In vivo, rHTVC accelerated wound closure (96.7% vs. 78.1% in controls by day 10, $P<0.001$), reduced collagen I/III ratio (Figure 1), increased angiogenesis (VEGF/PDGF/CD31 upregulation, Figure 2), and promoted hair follicle regeneration with minimal scarring.


A
Full-skin wound
On craniofacial
In situ electrospinning
(rHTVC)
In situ electrospinning treatment
Tissue collection
Day0
Day3
Day5
Day7
Day10
B
Control
rHTVC
Day 0
Day 3
Day 5
Day 7
Day 10
(Distance/mm)
C
Control
rHTVC
Relative healing area
Time(days)
D
Weight(g)
Time(days)
E
H&E
Normal
Control
rHTVC
F
Masson
G
Sirius Red
H
Hair follicles per section
I
Epidermal-dermal thickness
J
Collegen deposition(%)
K
Ration of type I/III collagen



Conclusion

In situ electrospun rHTVC fibers promote craniofacial scarless wound healing by activating the PI3K-AKT pathway, coupling enhanced angiogenesis with anti-fibrotic ECM remodeling. This portable, synthetic biology-driven platform offers a clinically translatable strategy for emergency and reconstructive wound management.

Acknowledgements

This work was supported by the National Natural Science Foundation of China (Grant No. 82270900). The authors acknowledge the Jiangsu Key Laboratory of Oral Diseases for animal facility support.

D2 – P079

Gelatin-microgels as basis of a novel volumetric additive manufacturing bioink in neural tissue engineering

Shamieva S.[1], Reichert T.[2], Romahn G.[3], Mork M.[3], De Laporte L.[3], Van Vlierberghe S.[1]
[1]Polymer Chemistry and Biomaterials Group, Dept. of Organic and Macromolecular Chemistry, Ghent University, Ghent, Belgium; [2]Centre for Microsystems Technology, Imec and Ghent University, Ghent-Zwijnaarde, Belgium; [3]DWI - Leibniz Institute for Interactive Materials e.V., RWTH Aachen University, Aachen, Germany

Introduction

In 2021, ~15.4 million people worldwide were affected by spinal cord injury (SCI), caused by trauma or non-traumatic conditions such as tumors or infections[1]. Because neurons cannot self-repair, SCI often leads to temporary or permanent loss of function. Volumetric additive manufacturing (VAM) is a promising tissue engineering approach for SCI repair due to its gentle processing, suitable for shear-sensitive neural cells[2]. However, few photo-crosslinkable bioinks are available for VAM. Microgels, water-swollen, crosslinked polymer particles are promising building blocks for 3D scaffolds. This project discribes a novel gelatin microgel-based resin for VAM printing of neural scaffolds.

Materials and Methods

In this research project, a bifunctional methacrylated and norbornene-functionalized gelatin (gelMANB) was produced according to previously described protocols and their degree of substitution (DS) determined through an ortho-phtalic aldehyde assay[3]. Various gelatin concentrations were characterized in terms of their viscosity and crosslinking kinetics. Since the gelMANB-microgels are produced using microfluidics (Figure 1), the solution's viscosity needs to be lower than 10 mPa.s to allow efficient flow. Furthermore, the crosslinking time is required to be lower than 2 min, approximate of UV-illumination time in the setup. Both gel fractions and swelling ratios were assessed. Additionally, thiolated gelatin (gelSH) and norbornene-functionalized gelatin (gelNB), used in thiol-ene crosslinking during VAM, were developed[4]. Since neural cells are known to thrive in hyaluronic acid (HA) rich environments, norbornene-functionalized HA (HANB) was incorporated and its effect on physico-chemical properties of the resin assessed. The crosslinking kinetics of the gelMANB microgels – gelNB-gelSH(-HANB) resin were evaluated int he context of VAM. Additionally, cubes with dimensions 5 x 5 x 5mm3 were printed and post-cured under a UV-lamp with 405nm light with intensity of 70 mW cm-2. The print was visualized using scanning electron microscopy (SEM).

Results

The substitution degree of gelMANB was determined to be 90% (MA) and 10% (NB). Viscosities of all gelMANB solutions with concentrations of 7.5, 10 and 15 w/V% were determined to be lower than 10 mPa.s. The crosslinking time, determined through in situ photo-rheology, was under 2 min, ensuring efficient crosslinking in the microfluidics setup. Gel fraction analysis indicated an additional post-curing step (15 min at 405nm with intensity 70 mW cm-2) to be necessary to improve crosslinking efficiency. In situ photo-rheology of gelNB-gelSH(-HANB) mixed with microgels enabled determination of an optimal light dose for VAM printing of this resin. Finally, the resin was successfully used in a first print at the corresponding light dose.

Conclusion

This work describes gelMANB-microgel production through microfluidics along with microgel-characterization. Additionally, these microgels were successfully incorporated into a gelNB-gelSH(-HANB) resin, resulting in a novel resin for VAM printing.




Figure 1 Microfluidic chip setup for gelMANB microgel production. A gelMANB solution and oil are injected in a controlled manner (using syringe pumps) through the microfluidic chip using their respective inlets. At the interface of oil and polymer solution, droplets are formed that flow further to the outlet which is connected to a tube guiding the microgels under UV-light to allow photo-crosslinking. After crosslinking the tube runs to a collection tube where the produced microgels are collected.

References

[1]Spinal cord injury https://www.who.int/news-room/fact-sheets/detail/spinal-cord-injury.

[2]Gaub B.M., et al. Neurons differentiate magnitude and location of mechanical stimuli. *Proceedings of the National Academy of Sciences* 2020; 117; 848-856.

[3]Van Den Bulcke A.I., et al. Structural and Rheological Properties of Methacrylamide Modified Gelatin Hydrogels. *Biomacromolecules* 2000; 1; 31-38.

[4]Vlierberghe S. V., Schacht E., Dubruel P. Reversible gelatin-based hydrogels: Finetuning of material properties. *European Polymer Journal* 2011; 5; 1039-1047.

D2 – P080

Photocrosslinked polymeric network based on methacrylated gelatin-xanthan gum as potential ink for wound healing

Nicolae M.C., Stavarache C.E., Vlăsceanu G.M., Gârea S.A., Iovu H.
Advanced Polymer Materials Group, National University of Science and Technology POLITEHNICA Bucharest, Bucharest, Romania

Introduction

The skin, the largest organ of the body, play multiple roles, includig acting as a barrier against external pathogens, thermoregulation and sensory perception. When the skin suffers sever injury, a complex healing mechanism is activated. However, in the case of deep or large wound, the skin presents a limited regenerative capacity, which require the use of external support to promote wound healing without the appearance of complications. Methacrylated gelatin (GelMA) represents a very broad biomaterial used for skin tissue due to its similarity with extracellular matrix, its capacities to maintain wound hydratation and aid hemostasis. In order to obtain personalized dressing 3D bioprinting was employed. However, at the body temperature GelMA exhibits inadequate viscosity for extrusion bioprinting. Consequently, methacrylated xanthan gum (XG-MA) was incorporatd due to its double helix structure, which give the pseudoplastic behavior. Allantoin was used as active ingredient duet o their antioxidant, anti-inflammatory and antibacterial activity.

Aim

Different concentration of GelMA were proposed in order to identify the optimal formulation that ensure adequate strucural stability and a suitable environment for skin regeneration.

Materials and Methods

Gelatin and xanthan gum were modified with methacrylic anhidride and glycidil methacrilate, respectively. In the proposed ink, XG-MA was maintained at a constant concentratio,while GelMA was used in different mass ratios. After UV exposure, stable photocrosslinked scaffolds were obtained. Structural investigations were performed to confirm the modification of both biopolymers. Rheological experiments were carried out to asses if the inks exhibit suitable properties for extrusion 3D bioprinting, The obtaind scaffold were evaluaded in terms of structural, morphological and mechanical properties, as well behavior in the moinst enviroinment.

Results

The ^{1}H NMR spectra showed the modifications occurring in the both biopolymers structure after methacrylation. Rheological experiments revealed that all compositions exhibit suitable features for 3D bioprinting, including pseudoplastic behavior and advantageous viscosity recovery. The mass ratio higly influence morphology, mechanical and sweeling degree.

Conclusion

The results indicate that tuning GelMA ratio enable the development of stable and printabele scaffolds with tunable properties with potential in wound healing applicatiation.

Acknowledgements

This work was supported by a grant of the Ministry of Research, Innovation and Digitization, CNCS/CCCDI-UEFISCDI, project number PN-IV-P8-8.1-PRE-HE-ORG-2023-0054 (contract no. 17PHE/2023) within PNCDI IV.

D2 – P081

A collagen fibrillation inducing support bath for embedded 3D printing of collagen-based inks

Gonnella G.[1,2,3], Madden L.[1,2], Rory G.[1,2,3], Kelly D. J.[1,2,3,4]
[1]Trinity Centre for Biomedical Engineering, Trinity Biomedical Sciences Institute, Trinity College Dublin, Dublin, Ireland; [2]Dept. of Mechanical, Manufacturing and Biomedical Engineering, School of Engineering, Trinity College Dublin, Dublin, Ireland. [3]Advanced Materials and Bioengineering Research Centre (AMBER), Royal College of Surgeons in Ireland and Trinity College Dublin, Dublin, Ireland. [4]Dept. of Anatomy & Regenerative Medicine, Royal College of Surgeons in Ireland, Dublin, Ireland. [5]School of Veterinary Medicine, University College Dublin, Ireland

Introduction

Collagen fibre organisation is critical to the mechanical and biological function of many tissues. Although collagen-based bioinks are widely used in 3D bioprinting, their low viscosity and poor shape retention make high-fidelity printing challenging. Existing support baths can improve print stability, but often do not promote collagen fibril formation, allow clear visual monitoring during printing, and support straightforward recovery of fragile constructs after post-processing. The aim of this study was to develop a transparent fibrillation-inducing support bath for embedded printing of collagen-rich inks.

Materials and Methods

A fibrillation-inducing support bath was developed using a phosphate buffer-polyethylene glycol formulation in water, with yield stress and thixotropy tuned using either microfibrillated cellulose (MFC) or nanofibrillated cellulose (NFC). Three bath formulations (2% MFC, 10% NFC and 15% NFC) were evaluated for optical clarity and rheological properties at 37°C. Solubilised articular cartilage extracellular matrix, a type II collagen-rich ink, was used as a model ink at 10 and 50 mg/mL. Embedded printing performance was assessed through filament deposition studies and large-scale fabrication of multilayer sheets (15 × 15 mm, ~1.5 mm thick) and porous scaffolds (6 × 6 mm) with programmed filament spacing. Constructs were freeze-dried, dehydrothermal treated, and recovered by washing in water. Print morphology and collagen organisation were assessed by scanning electron microscopy.

Results

Rheological and optical screening identified 15% NFC as the most suitable support bath, providing the highest viscosity and greatest stability at 37°C while maintaining improved clarity relative to MFC-based baths (Figure 1). In embedded printing experiments, only the 15% NFC bath consistently supported filament deposition and post-print stability across both ink concentrations, and enabled recovery of morphologically intact constructs after freeze-drying and dehydrothermal treatment (Figure 2). Large-scale printing of multilayer sheets and porous scaffolds was achieved, with overall construct dimensions retained after processing. Scanning electron microscopy showed enhanced collagen fibre alignment in constructs printed within the 15% NFC bath and revealed fibrillar features consistent with collagen D-band periodicity. However, finer pore gradation in more complex scaffold designs was not fully maintained after processing.

Conclusion

These findings demonstrate that a 15% NFC-based fibrillation-inducing support bath provides a transparent and mechanically supportive environment for embedded printing of unmodified collagen-rich inks, while also enabling directional collagen organisation and straightforward post-processing retrieval. By combining print support, fibrillation induction, optical accessibility, and simple recovery within one system, this platform offers a practical strategy for fabricating aligned collagen-based constructs for tissue engineering and other advanced biofabrication applications.




Figure 1: Development and characterisation of NFC- and MFC-based support baths. Schematic illustration of the support bath formulation, comprising phosphate buffer, polyethylene glycol, and cellulose reinforcement in the form of MFC or NFC (a). Shear-thinning behaviour of the bath formulations, shown as viscosity as a function of shear rate (b). Thixotropic recovery of the formulations during cyclic step-shear testing, shown by changes in storage modulus (G′) and loss modulus (G″) over time (c). Amplitude sweep analysis showing viscoelastic behaviour of the support baths across increasing strain (d). Representative images of the different bath formulations demonstrating differences in optical appearance (e). Transmittance spectra of the bath formulations across the visible wavelength range (f). Data are presented as mean ± standard deviation, with statistical significance indicated in the figure. N = 4 samples per group. *p < 0.05, **p < 0.005, ***p < 0.001, ****p < 0.0001. Scale bar = 1 cm.




Figure 2: Embedded printing supports continuous filament deposition and directional fibrillar organisation of AC-ECM inks. Schematic of printing and post-processing workflow (a). Filament width immediately after printing in FIB and cellulose-only baths (b). Filament width after freeze-drying and construct retrieval from FIB bath (c). Filament length after construct retrieval from FIB bath (the dotted line indicates the expected filament length of 25 mm) (d). Percentage of collagen fibres with local orientations lying within ±10° of the printing direction, quantified from SEM images using OrientationJ (e). Representative SEM images of processed AC-ECM filaments showing collagen fibril morphology and D-banding (f). Data are presented as mean ± standard deviation, with statistical significance indicated in the figure. n = 27 points (3 printed samples per group, 3 lines printed, 3 images analysed per line). *p < 0.05, **p < 0.005, ***p < 0.001, ****p < 0.0001. Scale bar = 200 nm.

D2 – P082

Amyloid/PCL nanofibrous composites: An electrospun scaffold for wound dressing applications

Entzmann L.[1,2], Pignon F.[1], Bossard F.[1]
[1]Laboratoir Rhéologie et Procédés, Grenoble INP, Université Grenoble Alpes, CNRS; [2]CERMAV, Université Grenoble Alpes, CNRS, Grenoble, France

Introduction

Burns and chronic wounds are related to many complications during healing. Conventional dressings show limited efficacy for this type of open-injury: they do not support skin reconstruction and require frequent dressing changes. While being very painful for patients, this also exposes the wound to exterior pathogens and potential infections. To tackle these issues, tissue engineering increasingly focuses on the development of bioresorbable scaffolds as advanced alternatives to standard dressings. Proteins are an attractive component for such applications due to their biocompatibility and inherent bioactivity. However, their incorporation often results in mechanically weak constructs. Amyloid fibrils, formed through the structured aggregation of proteins, offer several advantages: their high rigidity makes them effective mechanical reinforcements, while their cell affinity is particularly relevant to skin regeneration.

Materials and Methods

Electrospun mats composed of polycaprolactone (PCL) and amyloid fibrils (AF) from α-lactalbumin were produced using a non-fluorinated solvent with AF to PCL ratio ranging from 1wt% to 25wt% (figure 1). Fibril release upon incubation in PBS was monitored by UV spectroscopy, and mechanical properties were evaluated by tensile testing prior and following incubation. Investigation of the internal organization of the material during elongation was performed by in situ SAXS/WAXS in ESRF facility. Hydrophilicity and absorption capacity were assessed by water contact angle and vertical wicking. Fibroblast proliferation was estimated through optical density, while antibacterial activity was measured through live/dead assay.

Results

Despite the affinity of AF with aqueous environment, the mats maintained their structural integrity upon incubation in PBS: a slow and steady dispersion of fibrils was observed, with a 50% release over a period of a month. Though AF release caused a decrease in mechanical performances, PCL-AF hybrids exhibited superior mechanical performances compared to pristine PCL, both prior to and following incubation. In particular, the elastic modulus and deformation at break of the composites were consistently higher than those of neat PCL. The influence of fibrils on material performances was correlated to its internal structure by SAXS/WAXS analysis. On another hand, AF incorporation significantly enhanced mats hydrophilicity, as evidenced by reduced water contact angles and increased absorption rates. Their positive effect on cell proliferation and antibacterial activity was investigated.

Conclusion

Amyloid fibrils could therefore become a key component for biomaterials: a mechanical reinforcement at low content, a support for cell growth at high content. Overall, these results highlight the many benefits that AF can bring to biomedical applications as a protein-based additive.




Figure 1 - Schematic representation of the elaboration process

D2 – P083

Fiber-hydrogel composites with covalently reinforced interface for tendon and ligament repair

Bondarenko D.[1,2], Kolouchova K.[3], Van Vlierberghe S.[3], Graulus G.-J.[1,2], Ethirajan A.[1,2]
[1]UHasselt, Institute for Materials Research (IUMAT), Hasselt; [2]imec, IUMAT, Diepenbeek; [3]Polymer Chemistry and Biomaterials Group, Centre of Macromolecular Chemistry (CMaC), Dept. of Organic and Macromolecular Chemistry, Ghent University, Ghent, Belgium

Introduction

Tendons and ligaments transmit and withstand high forces between muscles and bones thanks to a hierarchical, aligned collagen architecture. However, this structure is also characterized by low cellularity and vascularity, which impedes the healing of ruptures. Fibrous and printed scaffolds typically fail due to insufficient porosity, bioabsorption, or bioinstructability. Hydrogel-based approaches fail due to a lack of strength. Attempts to address both with reinforced hydrogels don't meet the tensile requirements and underperform expected values due to interfacial failure.

In this work, we design a composite scaffold: aligned fibers encased in a hydrogel, with a covalently reinforced interface. The fiber surface is functionalized to guide cells through attachment-mediated surface curvature sensing.

Methods

Centrifugal spinning (CFS) is used for fiber production due to its high throughput, leveraging a home-built setup[1]. PLLA is chosen due to its biocompatibility, strength, and long bioabsorption timelines. Molecular weight engineering and rotary collection are introduced to achieve the desired diameter and alignment. Different microscopic techniques were used to assess fiber morphology; tensile testing was used to evaluate the mechanical properties.

Two strategies were pursued for surface functionalization. First utilizes surface-limited reactions, followed by coupling reactive handles with peptides synthesized by solid-phase synthesis. Second leverages the inclusion of smaller reactive handle-functionalized polymers in the spinning mix, which react with functional peptides. Functionalization was confirmed with FTIR. Degree of functionalization was quantified via fluorescent labeling followed by spectroscopic measurement.

Results

PLLA fibers with an average diameter of 1.5 um with low-to-zero bead content were produced using the modified homemade CFS setup by varying polymer compositions, spinning, and setup parameters. During optimization, we discovered that the feed rate was the key factor determining polymer output, and not the commonly assumed interaction between nozzle size and solution viscosity.

Both chemical strategies were optimized and compared, achieving target grafting density. Notably, up to 50 wt.% Inclusion of functional polymer chains has shown no adverse effects on fiber morphology.

Conclusions and outlook

In this study, fiber spinning conditions were optimized to achieve the desired diameter, morphological quality, and alignment by modifying the molecular weight distribution, spinning conditions, and implementing setup improvements.

Surface functionalization success was confirmed using fluorescent dyes for two separate routes. Next steps include the assembly of the scaffold using peptide linkers, mechanical and biological assessment of its performance. These results are promising for the envisaged composite scaffold for tissue repair.

References:

[1]Merchiers J., et al. *Polymers* 12; 575.

D2 – P084

Rheological and electrical optimization of eutectic gels for conductive wound dressings application

Shakibania S.[1,2], Akbarinejad A.[3], Hui Y.[3], Du P.[4], Travas-Sejdic J.[3,5], Krukiewicz K.[1,6]
[1]Dept. of Physical Chemistry and Technology of Polymers, Silesian University of Technology, Gliwice, Poland; [2]Joint Doctoral School, Silesian University of Technology, Gliwice, Poland; [3]Centre for Innovative Materials for Health, School of Chemical Sciences, The University of Auckland, Auckland, New Zealand; [4]Auckland Bioengineering Institute, The University of Auckland, Auckland, New Zealand; [5]MacDiarmid Institute for Advanced Materials and Nanotechnology, Wellington, New Zealand; [6]Centre for Organic and Nanohybrid Electronics, Silesian University of Technology, Gliwice, Poland

Introduction

Chronic and complex wounds represent a major clinical challenge, significantly reducing patients' quality of life and increasing healthcare costs. Conventional wound dressings primarily provide protection and maintain a moist environment, but often fail to actively support the biological signaling required for efficient tissue repair. Electrical stimulation has been shown to enhance key healing processes, including cell migration, proliferation, and alignment, thereby accelerating tissue regeneration.

Aim

This project aims to develop a novel wound dressing capable of safely conducting electrical signals directly through the wound to support natural healing. The approach addresses key limitations of current conductive dressings, which often rely on potentially harmful metal ions or rigid materials that do not conform well to deep or irregular wound geometries.

Materials and Methods

Eutectic gels were synthesized by mixing PEDOT:PSS (PH 1000, Ossila) with a deep eutectic solvent (DES) at different weight ratios (40%, 50%, 60%, and 70%). The DES was synthesized by mixing Choline Chloride and Lactic Acid (ChCl:LAC 1:2 molar ratio) at 60 °C until a clear homogeneous liquid was obtained. The rheological behavior and printability of the gels were evaluated using a modular compact rheometer at room temperature. Electrical and ionic conductivity were characterized using cyclic voltammetry (CV), electrochemical impedance spectroscopy (EIS), and four-point probe measurements.

Results

The rheological study showed that the sample with 40% PEDOT:PSS has the highest resistance to flow, while the one with 70% PEDOT:PSS is the least viscous. All samples show high initial viscosity at low shear rates, followed by a sharp drop and then a constant at higher shear rates. Electronic conductivity was evaluated using the four-point probe measurement, showing that electrical conductivity reaches the highest value at 50 wt% PEDOT:PSS. Moreover, in EIS measurement in all frequencies sample containing 50% of PEDOT:PSS showed the lowest |Z| value, while the sample containing 70% PEDOT:PSS had the highest value for |Z|.

Conclusion

The developed PEDOT:PSS–DES gel demonstrates suitable rheological and electrical properties for use as a flexible, conductive wound dressing. Among the tested compositions, 50% PEDOT:PSS provides the optimal balance of conductivity and performance, making it the most promising candidate for further studies.

Acknowledgements

The authors would like to acknowledge Silesian University of Technology (32/014/SDU/10-27-30) and National Science Center (2021/42/E/ST5/00165) for financial support.

D2 – P085
Design of tunable UV-curable polyphosphate hydrogels as 3D printable inks for tissue engineering

Lombardi M.[1], Rabaux O.[2], Jérôme C.[1]
[1]Center for Education and Research on Macromolecules, University of Liège, Liège, Belgium; [2]DWI Leibniz Institut für Interaktive Materialien, RWTH University, Aachen, Germany

Introduction
Polyphosphoesters (PPEs) are emerging polymers for biomaterials thanks to their structural tunability, hydrolytically degradable profiles and excellent biocompatibility. These specific properties are sought out for hydrogels as scaffolds in the field of tissue engineering. PPEs end-capped with unsaturated groups have previously been used as hydrolysable crosslinkers for polyacrylic acid hydrogels, or combined with polysaccharides, or polyethylene glycol (PEG) to generate networks containing degradable moieties. Although PPEs have also been used to form PPE-only hydrogels, their mechanical properties have not met the requirements for hydrogel scaffolding applications. In addition, the previously reported gelation times following the UV irradiation of the macromonomers were around 15 minutes, which limits their suitability for 3D printing technologies.


The aim of this study is to develop self-standing, PPE-only hydrogels with mechanical properties comparable to that of established PEG hydrogels, with the added value of intrinsic degradability and enhanced crosslinking kinetics.

Materials and Methods
Hydrophilic PPEs were prepared by organo-catalyzed ring opening polymerization of the corresponding cyclic phosphate monomers, using different initiators (mono, bi, tetra-functional). The polymers were characterized by ^{1}H, ^{31}P NMR and gel permeation chromatography in dichloromethane. Hydrogels were prepared by irradiating aqueous solutions of polymer with a photo initiator at a wavelength of 365nm. Rheological and swelling measurements were performed to characterize the mechanical properties of the materials.

Results
We report the synthesis of reactive linear and star poly(methyl ethylene) phosphate exhibiting fast curing into networks with excellent and tunable mechanical properties, both in the dry state and in the water-swollen hydrogel form (Fig. 1). By modifying the polymer structure, molar mass and crosslinking strategy, the resulting hydrogels exhibit elastic moduli ranging from 1 to 30 kPa matching the mechanical properties of typical PEG hydrogels used as soft tissue scaffolds. These materials crosslink in a few seconds upon brief UV irradiation, making them particularly suitable for light-based additive manufacturing techniques. Therefore, the hydrogels were successfully processed via 3D printing using digital light processing.

Conclusion
The first functional PPE hydrogels were obtained, in just seconds after a brief UV exposure and processed with an innovative additive manufacturing method. These results open the way for future developments using PPE hydrogel inks combined with cells for further advanced bioprinting.

Figure 1. General Strategy for the design of 3D-printable PPE hydrogels



Acknowledgements
M. Lombardi is a FRIA grantee of the Fonds de la Recherche Scientifique - FNRS

D2 – P086
Evaluation of a new angiogenic dermal scaffold for better integration of dermal substitutes

Barbut C.[1], Teo P.[2], Tsigkou O.[1]
[1]Dept. of Materials, University of Manchester, Manchester, UK; [2]A*star, Singapore

Introduction
The management of extensive skin trauma and burns remains a clinical challenge. Conventional skin grafts and skin substitutes exhibit significant limitations, as successful integration depends on oxygen diffusion from adjacent vasculature and the patient's cells. This project developed an acellular dermal substitute to promote angiogenesis, enhancing the integration of skin substitutes for treating large skin defects.

Materials and Methods
A bioactive angiogenic dermal graft was fabricated using a novel 3D-printed brush polymer functionalized with angiogenic peptides. The material was evaluated *in vitro with* biocompatibility assessment using human dermal fibroblasts (HDFs) and Human Umbilical Vein Endothelial Cells (HUVECs), and the development of a wound bed vascularisation model incorporating Mesenchymal stem cells (MSCs)- Human Umbilical Vein Endothelial Cells co-culture, *ex vivo* angiogenic potential evaluation using the Chorioallantoic Membrane assay (CAM), and *in vivo* validation in a porcine full-thickness wound model.

Results
In vitro studies demonstrated excellent cell viability and proliferation on the scaffold material. The co-culture model successfully generated capillary-like networks, establishing a platform for future scaffold assessment. Ex vivo assays revealed significantly enhanced vessel formation and branching compared to controls. In vivo studies demonstrated accelerated granulation tissue formation and increased vascularisation, though initial design limitations were identified.

Conclusion
This work establishes a novel bench-to-bed bioactive dermal substitute with angiogenic properties, offering promising potential for advancing the treatment of large skin defects and burn injuries. In addition, the development of a new in vitro wound vascularisation model provides a valuable tool for future biomaterial screening.

Acknowledgements
We acknowledge support from the Henry Royce Institute, Manchester, UK. This project is funded by the Dean’s Doctoral Scholarship to CB, Faculty of Science and Engineering, University of Manchester, UK.

D2 – P087

In vivo evaluation of persistence and integration of two mammary prosthesis models derived from human placental tissue in rats

Martin L., Garcia P., Barnouin L.
R&D Dept., TBF - Tissue Engineering, Mions, France

Introduction

Breast reconstruction following mastectomy remains a major clinical challenge, with current options presenting limitations including foreign body reactions and long-term complications. The development of absorbable mammary prostheses derived from human placental tissue offers a promising biocompatible alternative, combining regenerative potential and gradual integration into host tissue. Placental tissue, rich in collagen, has demonstrated favorable properties for tissue engineering, including low immunogenicity and support for cellular infiltration. The aim is to evaluate if an engineered matrix derived from human placental tissue can serve as a scaffold for cell growth while being safely absorbed at a moderate rate. This study compares *in vivo* persistence and cellular colonisation of two mammary prosthesis prototypes made from this matrix in a rat model.

Materials and Methods

A collagen gel devoid of proteoglycans was first produced from human umbilical cord walls. Two prosthesis prototypes were then made from this gel:

No.1: A mix of the gel that was gamma-irradiated, umbilical cord powder and alginate, altogether cross-linked in a calcium chloride solution.
No.2: A mix of the non-irradiated gel and umbilical cord powder. Both products were molded, lyophilized and sterilized.

Nine-week-old rats were subcutaneously implanted at hip and shoulder level with either prosthesis prototype. Rats were sacrificed four and eight weeks after implantation. Macroscopic examination, including verification of the prosthesis presence, was realised during necropsy and implanted sites were carefully harvested and placed in formalin for fixation. Prosthesis integration and cellular colonization were evaluated by histology and histopathological analyses.

Results

Clinical and macroscopic examinations revealed no abnormalities in any of the animals, except for one rat - implanted with the second prosthesis - that developed a major splenomegaly.

In all animals, biomaterial No.1 was recovered at the implantation site at 4 and 8 weeks, with a slight decrease in thickness at 8 weeks. HES staining showed that prosthesis No.1 seems integrated, encased in a fibrous capsule and colonized by cells (Figure 1), contrary to the prosthesis No.2 (Figure 2).

Conclusion

The assay validated that one of the prosthesis prototypes is a promising matrix for the design of long-time resorbable biomaterial that could promote cellular growth.




Figure 1. HES staining of prosthesis No.1 at implantation site after 4 weeks




Figure 2. HES staining of prosthesis No.2 at implantation site after 4 weeks

Acknowledgements
Thanks to Atlantic Bone Screen for the realization of the animal study and HES images.

D2 – P088

In vivo Performance of Extracellular Vesicle–laden Injectable Hydrogel for Testicular Torsion Repair

Ozturk S.[1], Gultekinoglu M.[2], Conger-Onder E.[1,3], Tatar B.S.[4], Esentur Y.[5], Shirinli K.[6], Simsek D.[1], Mangir N.[6], Zeybek N.D.[4,5], Ulubayram K.[1,3]

[1]Dept. of Basic Pharmaceutical Sciences; [2]Dept. of Nanotechnology and Nanomedicine; [3]Dept. of Bioengineering; [4]Dept. of Histology and Embryology; [5]Dept. of Stem Cell Sciences; [6]Dept. of Urology, Hacettepe University, Ankara, Turkey

Introduction

Testicular torsion (TT) is a urological emergency caused by rotation of the spermatic cord, leading to ischemia and subsequent ischemia–reperfusion (I/R) injury after surgical detorsion. Although early detorsion restores blood flow, patients develop testicular atrophy or infertility. Pharmacological and cell-based therapies have been explored to mitigate TT-induced I/R injury, but rapid loss of transplanted cells and safety concerns limit their use. In TT models, Extracellular vesicles (EVs) improve testicular structure and function, yet free EVs exhibit limited local retention, highlighting the need for biomaterial-based delivery systems. This study aimed to investigate the therapeutic potential of injectable hydrogels loaded with stem cell–derived EVs (EXOGEL) in a rat torsion–detorsion model.

Materials and Methods

The therapeutic efficacy of EXOGEL was evaluated in a rat torsion–detorsion model. Rats were subjected to 720° testicular torsion for 3 h followed by detorsion, and animals received either EV solution or EXOGEL (10^{10} EVs). Treatment outcomes were assessed at 1 and 9 weeks through analyses of histopathological evaluation of spermatogenesis and seminiferous tubule structure, epididymal sperm count and morphology, as well as CD206 and αSMA immunohistochemistry, apoptosis (TUNEL assay), MDA levels, and Testosterone, LH, and FSH concentrations.

Results

Histological results showed improved seminiferous tubule morphology in the EXOGEL group, while apoptosis analysis revealed significantly higher apoptotic cell numbers in all TD groups than in control. At week 1, the EXOGEL group showed the lowest apoptotic cell counts, whereas the sham group exhibited the highest. Apoptotic cells decreased over time in the sham and EXOGEL groups ($p<0.05$), while the EV group showed the highest apoptosis at week 9 without reduction. Spermatogenic activity was significantly reduced in all TD groups at week 1 ($p<0.05$). The EXOGEL group showed the highest Johnsen score (5.31), although it significantly decreased by week 9 ($p<0.05$). The EXOGEL group also showed the highest sperm count (107.70×10^{6} sperm/g epididymis). Normal sperm increased from 13.40% to 18.90% in EXOGEL but decreased from 12.88% to 8.63% in EV. MDA levels were highest in sham at week 1 (5.045 nmol/mg tissue) and in EV at week 9 (4.14 nmol/mg tissue), while EXOGEL maintained lower levels (3.06 nmol/mg tissue). Testosterone was higher in EXOGEL than EV at week 1 ($p<0.05$). By week 9, LH decreased to baseline in EXOGEL, while FSH differences were not observed.

Conclusion

EXOGEL offers a promising biomaterial-assisted strategy for improving structural and functional recovery following testicular torsion–induced injury.

Acknowledgements

This work was supported by the TÜBİTAK (Project No: 120S910).

D2 – P089

Optimizing melt electrowriting parameters to predict and control fibre diameter: A design of experiments approach

Gennart I.[1,2,3,5], Kerckhofs G.[1,2,4,5], Bloemen V.[3, 4, 5]
[1]Institute of Mechanics, Materials and Civil Engineering (iMMC), UCLouvain; [2]Institut de recherche expérimentale et clinique (IREC), UCLouvain; [3]Skeletal Biology and Engineering Research Center (SBE), KU Leuven, Leuven; [4]Prometheus, Division of Skeletal Tissue Engineering, KU Leuven, Leuven, [5]Dept. Materials Engineering, KU Leuven, Leuven, Belgium

Introduction

Melt electrowriting (MEW) is an additive manufacturing technique used to produce well-defined fibrous scaffolds for tissue engineering (TE) applications (*i.e.* cartilage, skin, nerves, cardiac tissue, or blood vessel regeneration) [1]. It enables printing fibres with diameters between 0.1 and 50 µm and allows the fabrication of scaffolds with various architectures by controlling their microstructural properties, such as waviness and fibre orientation, through a computer using a motion controller [1,2]. Controlling fibre diameter is crucial when conceiving fibrous scaffolds for TE applications because it affects their mechanical properties, which in turn govern cell-matrix interactions through mechanotransduction [1,3]. Fibre diameter can be tuned through printing parameters, *i.e.* polymer temperature, nozzle inner diameter, applied voltage, pressure, collector speed, and tip-to-collector distance. However, achieving optimal printing parameters to obtain desired fibre diameter still strongly depends on extensive experimentation or the knowledge of experienced practitioners. Here, a design of experiment (DOE) was used to predict the diameter of MEW printed fibres with Poly(ε-caprolactone (PCL) and the critical translation speed (CTS).

Materials and Methods

A DOE approach was used to predict the diameter of MEW-printed PCL fibres and the CTS. A full factorial design with three levels per factor was implemented, varying the needle inner diameter (0.2mm-0.4mm), applied voltage (4-6kV) and polymer temperature (70-90°C), while keeping the tip-to-collector distance (3 mm) and pressure (1 bar) constant, and fixing the collector speed at CTS for all prints (*i.e.* squared grid scaffolds with one layer). Pressure and collector speed were fixed because their influence on fibre diameter can be computed from physical relations [4]. Fibre diameter was measured by optical microscope (40x, Leica), by averaging six points per print. Regression coefficients were determined using JMP software.

Results

Multiple experimental runs enabled the estimation of polynomial regression models predicting the fibre diameter and the CTS. It enables prediction and control of fibre diameter and highlights the contributions of printing parameters. For instance, printing smaller diameters requires a smaller nozzle inner diameter and a higher applied voltage, which in turn results in higher CTS.

Conclusion

This study demonstrates that DOE is an effective strategy to identify the most important (combination of) parameters influencing PCL fibre diameter and CTS in MEW, at fixed pressure. The models currently enable prediction of fibre diameter and CTS. This predictive capability will facilitate the fabrication of MEW scaffolds with tailored fibre diameters and controlled macro-architectural properties, such as waviness and fibre orientation.

Acknowledgements

I. Gennart acknowledges the Flanders Community of Belgium in the framework FWO-SB Mandate grant (1S09325N).

References

[1]Blum C. et al., Controlling Topography and Crystallinity of Melt Electrowritten Poly(ε-Caprolactone) Fibers. *3D Printing and Additive Manufacturing* 2021; vol. 8, no. 5; 315–321. doi: 10.1089/3dp.2020.0290.
[2]O'Neill K.L., Dalton P.D. A Decade of Melt Electrowriting. *Small Methods* 2023; vol. 7, no. 7; 2201589. doi: 10.1002/smtd.202201589.
[3]Goswami A.K., Giduturi V.K., Yerramilli S.N., Chauhan V.S., Yadav N. Tissue engineering: Hydrogel scaffolds and mechanical properties as key design parameters. *Advances in Colloid and Interface Science* 2026; vol. 347; 103691. doi: 10.1016/j.cis.2025.103691.
[4]Hrynevich A., et al. Dimension-Based Design of Melt Electrowritten Scaffolds'. *Small* 2018; vol. 14, no. 22; 1800232. doi: 10.1002/smll.201800232.

D2 – P090
Development of an implantable PLLA scaffold for isthmocele prevention

Inzerillo E., Carfì Pavia F., Brucato V., Burriesci G., Ingrassia T.
Dept. of Engineering, University of Palermo, Viale delle Scienze, Palermo, Italy

Introduction
The uterus undergoes continuous morphological and functional remodelling. The increasing rate of caesarean sections (~21%) has raised the incidence of uterine scar defects that may compromise uterine wall integrity. Incomplete uterine healing can result in isthmocele, a niche-like defect associated with abnormal bleeding, pain and infertility[1]. Since current treatments do not represent a gold standard for complete myometrial regeneration, tissue engineering may offer biomaterials-based strategies for uterine regeneration.

Aim
This study aims to produce, via thermally induced phase separation (TIPS), a biodegradable scaffold with a pore-size gradient designed to mimic the structural heterogeneity of uterine wall, promoting regeneration and potentially preventing isthmocele after caesarean section.

Materials and Methods
To obtain a pore-size gradient scaffold, a configuration designed to impose unidirectional heat transfer during TIPS freezing step was developed using a parallelepipedal sample holder covered on three sides with an insulating layer, leaving one face exposed. Heat transfer was simulated using MATLAB to evaluate temperature distribution over time. Scaffolds were then fabricated using a ternary PLLA/1,4-dioxane/water solution (4% w/w PLLA; 87/13 w/w solvent-antisolvent ratio) cast into the designed sample holder, and TIPS was carried out using a modified protocol[2]: phase separation was induced by immersion in a thermostatic bath at 30°C for 45min, followed by freezing at -20°C for 30min. Scaffold morphology and pore architecture were analysed by scanning electron microscopy (SEM).

Results
Thermal simulations showed the cooling front propagation from the non-insulated side toward the insulated region during freezing, generating a temperature gradient within the polymer solution. Temperature maps at 30s, 45s and 60s (Fig.1) confirmed the efficacy of this directional cooling configuration. SEM analysis (Fig.2) revealed a pore-size gradient across the scaffold thickness, with smaller pores near the exposed side and larger pores toward the insulated side.

Conclusion
Directional cooling during TIPS enabled the fabrication of a PLLA scaffold with a controlled pore-size gradient. This structure may represent a promising strategy to mimic the structural heterogeneity of uterine tissues and support regenerative approaches to prevent isthmocele formation after caesarean section.




Figure 1: Temperature distribution during TIPS freezing step at t = 30s, t = 45s, t = 60s




Figure 2: a) SEM image of scaffold with a pore size gradient, b) smaller pores region, c) larger pores region

References

[1]Baldini G.M., Lot D., Malvasi A., Di Nanni D., Laganà A.S., Angelucci C., Tinelli A., Baldini D., Trojano G. Isthmocele and Infertility. Jou*rnal of Clinical Medicine* 2024; no.8; 2192.

[2]Carfì Pavia F., La Carrubba V., Piccarolo S., Brucato V. Polymeric scaffolds prepared via thermally induced phase separation: Tuning of structure and morphology. *J Biomedical Materials Res* 2008; no.2; 459–466.

D2 – P091
Design of innovative shape-memory polyurethanes for tendon tissue repair

Bona B.L., Compostella F., Ricci C., Spitaleri A., Vaghi S., Del Favero E.
Dept. of Medical Biotechnology and Translational Medicine, University of Milan, Milano, Italy

Introduction
Tendinopathies represent a heterogeneous group of debilitating musculoskeletal disorders affecting hundreds of millions of individuals worldwide, leading to chronic pain, reduced functional capacity, diminished quality of life, and substantial socioeconomic burden. Their multifactorial aetiology, encompassing mechanical overload, degenerative changes, metabolic dysregulation, and limited intrinsic healing capacity, makes the development of universally effective therapeutic solutions particularly challenging. Moreover, even when surgical intervention is required, tendon healing frequently results in the formation of fibrovascular scar tissue. This tissue exhibits inferior mechanical strength, disorganized extracellular matrix architecture, and reduced elasticity compared to native tendon, ultimately predisposing patients to chronic symptoms, re-injury, and long-term functional impairment.

In response to these clinical limitations, significant research efforts in recent years have focused on regenerative medicine strategies, with scaffold-based approaches emerging as particularly promising. Engineered scaffolds can provide not only structural support but also biological cues that guide cellular behavior, promote extracellular matrix deposition, and encourage the formation of more physiologically aligned tendon tissue. By carefully tailoring scaffold composition, microstructure, and bioactive components, it is possible to enhance tissue integration and modulate the healing cascade toward more regenerative outcomes.

Aim
Within the framework of the TEN4CARE Horizon project, our work aims to design and synthesize a new class of shape-memory polyurethane-based biomaterials to serve as the bulk component of next-generation scaffolds for tendon repair. These materials offer the possibility of finely tuning both mechanical behavior and biological performance.

Material and Methos
By adjusting the ratios of the polymeric constituents and introducing chemical functionalization with selected biomolecules, we can modulate the interactions of the material with the biological environment, and program the shape-memory response to meet the unique mechanical and surgical requirements of tendon healing.

Results
Herein, we will present our first insights into the rational design and synthesis of advanced thermoplastic shape-memory materials, with particular emphasis on the tailored methodologies developed for their characterization.

Conclusions
This integrated approach will enable the development of innovative, clinically effective medical devices capable of improving tendon regeneration and ultimately enhancing patient outcomes.

Acknowledgements
We thank the TEN4CARE project (Grant agreement ID: 101178590) for funding.

D2 – P092

Anodized titanium surfaces modified with flavonoids to improve soft-tissue integration

Abenia-Artigas L.[1], Arias-Mainer C.[1], Romero-Gavilán F.[1], Martínez C.[2], Elortza F.[3], Azkargota M.[3], Gurruchaga M.[4], Goñi I.[4], Suay J.[1]

[1]Dept. of Industrial Systems Engineering and Design, University Jaume I, Castellón de la Plana; [2]Dept. Pathology, University of Valencia, Valencia; [3]Proteomics platform, CIC bioGUNE, Derio; [4]Dept. of Polymers and Advanced Materials: Physics, Chemistry and Technology, Universidad del País Vasco, San Sebastián, Spain

Introduction

Peri-implantitis, a condition characterized by gingival inflammation and bone loss, has increased in incidence over the years and represents a significant challenge in oral health. Titanium (Ti) and its alloys, widely used in dental implants, exhibit excellent mechanical properties and biocompatibility. However, their biological inertness leads to the formation of a different tissue structure around the implant, resulting in weaker adhesion between human gingival fibroblasts (HGFs) and implant abutments. This compromises the gingival seal and facilitates bacterial infiltration. To enhance biological performance, this study explores the functionalization of anodized Ti surfaces with flavonoids (Quercetin (QR), Rutin (RU), Naringenin (NE), and Naringin (NI)) to improve HGFs affinity and modulate immune response and inflammation without increasing bacterial viability.

Materials and Methods

Machined Ti6Al4V discs were anodized and subsequently treated with (3-aminopropyl)triethoxysilane (APS), followed by immersion in flavonoid solutions, heat treatment, and washing. Surface characterization was performed using SEM/EDX, contact angle measurements, XPS, and confocal fluorescence microscopy to confirm flavonoid presence and evaluate their release. In vitro assays with HGFs were conducted to evaluate cell adhesion, proliferation, and collagen secretion, while immunoassays assessed the expression of immune-related genes by analyzing the response of THP-1 macrophages. Proteomic analyses were performed to identify adsorbed proteins, and antimicrobial tests were carried out using *Streptococcus gordonii*, an early colonizer model for peri-implantitis.

Results

Results indicated that all flavonoids increased HGF proliferation. In addition, all flavonoids demonstrated the ability to reduce the secretion of cytokines such as TNF-α, reducing their levels. QR and NI stood out, reducing IL-1β secretion to M2 reference levels by day 3. Flavonoid-treated surfaces also exhibited reduced immunoglobulin adsorption, indicating a potential decrease in immune responses and related inflammation. An increase in the adsorption of proteins associated with fibrinolysis was also observed, suggesting a potential role in the modulation of regenerative processes. On the other hand, bacterial viability analysis showed that the treated surfaces did not improve *Streptococcus gordonii* proliferation.

Conclusion

In conclusion, the modification of Ti surfaces with flavonoids significantly improved the affinity of human gingival fibroblasts (HGFs) for the surface. In addition, an enhanced effect on the control of inflammation was observed, particularly on surfaces modified with QR and NI. Finally, these modifications did not promote the proliferation of S. gordonii, indicating that the improved biological response is mainly associated with enhanced HGF affinity and modulation of the inflammatory response.

Acknowledgements

Ministerio de Ciencia, Innovación y Universidades [PID2023-150429OB-I00/MCIU/AEI/10.13039/501100011033/FEDER,UE]; Generalitat Valenciana [CIPROM/2023/62]

D2 – P093

Improving soft tissue integration of titanium dental abutments through collagen and quercetin surface functionalization

Arias-Mainer C.[1], Romero-Gavilán F.[1], Abenia-Artigas L.[1], Elortza F.[2], Azkargorta M.[2], C. Martinez-Ramos[3] Gurruchaga M.[4], Goñi I.[4], Suay J.[1]
[1]Dept. of Industrial Systems Engineering and Design, Universitat Jaume I, Castellón de la Plana; [2]Proteomics Platform, CIC bioGUNE, Derio; [3]Center for Biomaterials and Tissue Engineering, Universitat Politècnica de València, Valencia; [4]Dept. of Polymers and Advanced Materials, Universidad del País Vasco, San Sebastián, Spain

Introduction

Peri-implantitis is a multifactorial inflammatory disease that can arise from an inadequate soft tissue seal at the implant-abutment interface. Improving the seal between titanium (Ti) abutment and connective tissues while reducing inflammation requires advanced surface modifications that stimulate tissue growth and modulate the immune response.

Aim

This study aimed to examine the effect of functionalising titanium alloys grade V, used in dental abutments, with collagen (COL) and quercetin (QUE) through APTES on the cellular response and protein adsorption patterns.

Materials and Methods

Machined Ti grade V discs were divided into three groups based on surface treatment: an untreated machined control (MC05), and two groups silanized using APTES as an anchor molecule for collagen functionalisation (COL) or dual functionalisation with collagen and quercetin (COL-QUE). Physicochemical properties were analysed by SEM/EDX, Raman spectroscopy, and contact angle measurements. *In vitro* biological responses were evaluated using human gingival fibroblasts (HGF) and THP-1 macrophages. HGF cell adhesion, spreading, proliferation, and oxidative stress were analysed, while macrophage cytokine secretion and gene expression were measured by ELISA and RT-PCR. The adsorption of proteins onto the surfaces was assessed employing nLC-MS/MS.

Results

Physicochemical characterisation confirmed the successful integration of COL and QUE, which altered the chemical composition and increased the surface hydrophobicity. The functionalised surfaces, particularly COL, enhanced HGF cell adhesion, spreading, and proliferation compared to MC05. Additionally, COL-QUE demonstrated a superior reduction in oxidative stress. THP-1 cells cultured on the functionalised surfaces, especially COL-QUE, showed an attenuated inflammatory response with reduced expression of pro-inflammatory genes (TNF-α, IL-1β, iNOS, NF-κB) and lower cytokine secretion. Proteomic data correlated with these results, revealing a global reduction in proteins associated with thromboinflammation and a favourable modulation of proteins linked to cell adhesion and tissue regeneration (Figure 1).

Conclusion

Functionalising Ti surfaces with collagen and quercetin improves biological responses for dental abutments. Collagen promotes cell proliferation and tissue regeneration, while the addition of quercetin effectively reduces inflammation and oxidative stress, providing an environment highly conducive to tissue integration.

Acknowledgements

Ministerio de Ciencia, Innovación y Universidades [PID2023-150429OB-I00/MCIU/AEI/10.13039/501100011033/FEDER,UE]; Generalitat Valenciana [CIPROM/2023/62]




Figure 1. Results included in the experimental work

D2 – P094

EV-embedded collagen scaffolds for wound healing – A physiochemical model with EV-mimetic liposomes

Nicolson K., Nair M., Ye H.
Institute of Biomedical Engineering, Dept. of Engineering Science, University of Oxford, Oxford, UK

Introduction

Non-healing wounds are a growing concern worldwide. Extracellular vesicles (EVs) have emerged as promising solutions to such wounds, by delivering nucleic and protein cargos that can influence biological healing processes. However, translational barriers include sustained EV delivery and long-term stability. Bioactive scaffolds provide a 3-dimensional framework for tissue regeneration while incorporating biological components that enhance therapeutic effects. We aim to develop an EV-embedded collagen scaffold as a stable and sustained delivery vehicle to encourage cellular activity through gradual EV release. Here we investigate liposomes as a physiochemical analogue of EVs, to probe their impact on scaffold mechanics and stability.

Materials and Methods

Fluorescently labelled liposomes (DOPC/Cholesterol 60:40 mol/mol) were produced through thin-film hydration. The liposomes were mixed into collagen slurry (1% w/v in 0.05 M acetic acid) with and without 25 mM trehalose cryoprotectant, prior to freeze-drying (-20°C overnight, dry at 0°C, 0.600 mbar, 26h). Bulk mechanical properties were assessed through tensile and compression testing. Scanning electron microscopy, confocal microscopy, and x-ray tomography (micro-CT) were used to analyze liposome distribution and porosity.

Results

Dye-loaded liposomes of an EV-mimetic range (135nm modal diameter, –11 mV surface charge) were homogeneously embedded within scaffold pore walls, with Manders' M1/M2 colocalization coefficients 0.691/0.707 and 0.594/0.702 for liposomes and liposomes-trehalose scaffolds, respectively (Fig 1.). Micro-CT analysis revealed liposome-containing scaffolds possessed a lower average pore size compared to collagen controls (Fig 2.). Inclusion of cryoprotectant or liposomes resulted in no statistically significant change in bulk mechanical properties of scaffolds.

Conclusion

EV-mimetic liposomes were successfully fabricated, characterized and embedded into collagen scaffolds. Liposomes were well-distributed within the scaffold, with pore sizes aligned with optimal values for cellular activity. Inclusion of liposomes and cryoprotectant presented no significant impact on bulk mechanical properties. Current and future work is focused on analyzing release profiles, degradation, and EV characterization to delineate biochemical effects of EVs from physical effects arising from incorporation into scaffolds.

Acknowledgements

KN acknowledges the Natural Sciences and Engineering Research Council of Canada – Postgraduate Scholarships Doctoral program.




Figure 1: Confocal images of liposome embedded scaffolds. A – Collagen autofluorescence B - Dye-loaded liposomes. C – Channels overlapped.




Figure 2: A - 3D pore sizes. B – Compression test. C, D – Uniaxial tensile data. Data presented as mean ± SD.

D2 – P095

VECOLLAN® - A promising, recombinant, collagen-like protein for biomedical applications

Krauss, C.[1,2], Montero Mirabet, M.[2], Mäder, K.[1]
[1]Institute of Pharmacy, Martin Luther University Halle-Wittenberg, Halle (Saale); [2]Evonik Operations GmbH, Research Development & Innovation, Darmstadt, Germany

Introduction

The market size for biomaterials and green chemicals produced via synthetic biology was estimated at 743.2 million USD in 2025, with an annual growth rate (CAGR) of 20.4% until 2029, reaching a market size of 1883.2 million USD.

VECOLLAN®, a recombinant, non-animal-derived collagen-like protein, has great potential for use in biomedical and drug delivery fields. Animal-derived collagen, widely used in these sectors, presents several challenges, including immunogenicity, variability, contamination risks, and ethical concerns. VECOLLAN®, produced biotechnologically, offers a promising alternative due to its consistent molecular properties, non-immunogenicity, non-allergenicity, and the ability to promote cell proliferation and wound healing. In comprehensive *in vitro* and *in vivo* assays, VECOLLAN® showed no cytotoxicity, irritation, or sensitization, supporting its potential as a safe biomaterial for long-term medical applications.

Electrospinning is a versatile and efficient technique for producing nanofibers from a variety of synthetic and natural materials, gaining traction in the biomedical field. Typical for electrospun products is their high surface-to-volume ratio.

Aim

The study aims to (1) explore the potential and limitations of the non-animal-derived protein VECOLLAN® for electrospinning. Suitable parameters of the electrospinning formulation and processing should be identified. In addition, (2) the impact of crosslinking on the dissolution and disintegration behavior of the fibers should be investigated. Furthermore, (3) a material-scientific examination is conducted.

Materials and Methods

VECOLLAN® was provided by Evonik Industries AG, Germany. Polyethylene oxide (PEO) with a molecular weight of 400 kDa was purchased from Merck KGaA, Germany. Hyaluronic acid (610 kDa) was purchased from Matexcel, USA. Elastin (10 kDa) was purchased from Matrihealth GmbH, Germany. 4-(4,6-Dimethoxy-1,3,5-triazin-2-yl)-4-methylmorpholinium Chloride (DMTMM) was purchased from TCI Deutschland GmbH, Germany. 4-Arm-polyethylene glycol-succinimidyl-glutarate-ester with a molecular weight of 10 kDa (PEG 4-Arm CL) was purchased from JenKem Technology USA Inc. 5 nm Silver nanoparticle suspension 2200 ppm was purchased from NanographeneX, United Kingdom. Acetone EMSURE® was purchased from Merck KGaA, Germany.

Electrospinning was conducted using a FLUIDNATEK LE-50 electrospinning equipment (BIOINICIA FLUIDNATEK SLU, Spain). The electrospun fibers were made from VECOLLAN® and PEO. The composition of the final formulation is 120 mg/mL VECOLLAN® and 18.6 mg/mL PEO. In one experiment, hyaluronic acid was added, and in another, elastin. The solvent mixture for all electrospinning formulations consisted of double-distilled water/acetone [9:1 (v/v)]. The fibers were produced with or without crosslinkers, depending on the experiment. The applied voltage to generate the fibers was 14-22 kV. The negative voltage on the flat collector was always -5 kV. The temperature in the climate chamber of the Fluidnatek LE-50 was set to 25 °C, and the relative humidity was set to 40% for all experiments. The spinneret to collector distance was 22.5 cm, and the fibers were collected on aluminum foil or baking paper on the collector. Each formulation was loaded into a 5 mL polypropylene syringe purchased from B.Braun SE, Germany. For monoaxial electrospinning, the formulations were pumped through a VIEWEG GmbH (Germany) dosing needle with an inner diameter of 0.41 mm and a capillary length of 12.7 mm. For coaxial electrospinning, the formulations were pumped through a VIEWEG GmbH (Germany) dosing needle with an inner diameter of 1.19 mm. The inner needle of the coaxial electrospinning head (BIOINICIA FLUIDNATEK SLU, Spain) had an inner diameter of 0.6 mm and an outer diameter of 0.9 mm. The flow rate for the integrated syringe pump was between 600 µL/h and 1200 µL/h in the case of monoaxial electrospinning. For the coaxial electrospinning, the flow rate of the core phase was 600 µL/h, and for the shell phase, 110 µL/h.

Results

VECOLLAN® was processed via electrospinning. The electrospinning parameters were optimized while examining the effects of a novel coaxial crosslinking approach on fiber properties, including dissolution and mechanical behavior. The crosslinker concentration and type significantly influenced VECOLLAN® dissolution and swelling behavior of the electrospun fibers. Incorporating hyaluronic acid enhanced water absorption capacity (Figure 19), while silver nanoparticles were homogeneously distributed within the fibers during coaxial electrospinning. This provided indications of the uniformity of the coaxial electrospinning process. Mechanical testing revealed that higher crosslinker concentrations improved fiber rigidity and stability, whereas elastin incorporation enhanced elongation at break.




Figure 1: SEM pictures and fiber size distribution of VECOLLAN®/PEO + 0.4% (w/w) HA and 4-(4,6-Dimethoxy-1,3,5-triazin-2-yl)-4-methylmorpholinium Chloride (DMTMM) (Molar ratio 1:0.1). (a) Dry state, (b) Wet state, (c) dry state overview, (d) wet state overview, (e) Average diameter: 291.1 nm, Standard deviation: 55.9 nm, Median: 293.4 nm, (f) Average diameter: 655.1 nm, Standard deviation: 257.3 nm, Median: 590.2 nm.

Conclusion

The findings highlight VECOLLAN®'s suitability for producing electrospun fibers that mimic the extracellular matrix, offering scalability and versatility for biomedical applications. These fibers show promising properties for use in the medical device and drug delivery sector. Future research should focus on biocompatibility assessments of these potential product candidates to further explore their therapeutic potential.

Acknowledgements

The authors acknowledge financial support provided by Evonik Operations GmbH. Christoph Krauss and Maria Montero Mirabet report a relationship with Evonik Operations GmbH that includes employment and equity or stocks.

Additionally, Christoph Krauss and Maria Montero Mirabet have patents pending to Evonik. Karsten Mäder declares no known competing financial interests or personal relationships that could have influenced the work reported in this abstract.

D2 – P096

3D mold optimization for mycelium biocomposites: Pathways toward sustainable industrial scaling

Hernández-Carpio C., Sánchez F., Calabuig L.
Research Institute of Design, Innovation and Technology, University CEU Cardenal Herrera, CEUUniversities, Valencia, Spain

Introduction

The current resource scarcity crisis, driven by production systems based on intensive raw material extraction and limited reuse strategies, highlights the urgent need to rethink contemporary material culture, still dominated by waste and linear industrial models. In this context, biofabricated materials emerge as a promising alternative capable of challenging conventional material practices and fostering generative production systems aligned with circular logics. Following a review of relevant theoretical frameworks, this research focuses on mycelium-based biocomposites, widely recognized for their environmental potential and increasing relevance within design and material innovation. Specifically, the study addresses a scarcely explored aspect: the role of the mold in which these materials are cultivated. Within this research, the mold is understood not merely as a passive container but as an active mediating device through which the designer negotiates between the living organism and the final product.

Materials and Methods

The research adopts a Material Driven Design approach, combined with principles from Growing Design, structuring the investigation through iterative experimentation and direct engagement with the living material. Biofabrication experiments were conducted using molds produced through additive manufacturing, identified as a technology aligned with the philosophy of biofabricated materials, supporting non-extractive practices while enabling geometric optimization, waste reduction, and circular strategies. Two printing technologies, FDM (Fused Deposition Modeling) and FGF (Fused Granulate Fabrication), were explored and compared using materials such as PLA, PHA and ABS. Experimental prototypes were developed [1] to investigate the interaction between mycelium growth and 3D-printed molds, focusing on how geometry, surface quality, ventilation, and printing resolution influence the cultivation process. Iterations examined substrate filling, compaction, mold assembly, and demolding, allowing design parameters to emerge progressively from observed material behavior.

Results



[1]: Final 3D printed mold



[2]: mycelium lampshade final prototype

Conclusion

The results demonstrate that mycelium-based composites' performance is not determined solely by biological variables but is strongly conditioned by mold design and fabrication processes. The mold emerges as a key operative element, influencing substrate compaction, aeration, growth dynamics, demolding, and final material quality. Shell-type geometries, layered filling strategies, controlled ventilation, and appropriate surface finishing were shown to be critical for reproducibility. Overall, the research establishes preliminary design criteria positioning mold design as a strategic factor for reproducibility, scalability, and circular integration of mycelium-based materials in sustainable production systems. As a tangible outcome, a mycelium-based lampshade was produced as a functional prototype [2], demonstrating the feasibility of translating experimental findings into an industrially relevant, usable product.

D2 – P097

Control of oxygen levels in vitro to mimic the tumor microenvironment using an engineered cell culture device

Rosalia M.[1,2], Malferrari M.[2], Grassilli E.[1], Rapino S.[2]
[1]InSimili srl, Bologna; [2]Dept. of Chemistry "Giacomo Ciamician", University of Bologna, Bologna, Italy

Introduction

Hypoxia is recognized as a hallmark of cancer, since 90% of solid tumors thrive in hypoxic microenvironments. Cellular responses to low oxygen are mediated by hypoxia-inducible factors (HIFs). The HIF pathway controls metabolic and transcriptional adaptation in tumors, favoring cancer cell proliferation, migration and invasion, ultimately affecting therapeutic outcomes. Nevertheless, *in vitro* anticancer drug screenings are often performed in standard cell culture settings, due to the technical challenges and high costs associated with hypoxia workstations and incubators. Standard cell culture conditions expose cancer cells to hyperoxia (in standard incubators, it is around 19% O_2), altering gene expression and methabolic behavior, which can confound the relevance of the results and delay the development of new therapies.

Aim

This work showcases the application of an innovative, multiwell-cell culture device (O*xygenControl plate*), that exploits a functional biomaterial to regulate oxygen concentration in vitro, without the need for hypoxia workstations, chambers, or special incubators.

Materials and Methods

The OxygenControl plate was manufactured by depositing a functional matrix on the bottom of a standard multiwell-cell culture plate. Oxygen levels and their spatial distribution in the cell culture medium were monitored by scanning electrochemical microscopy (SECM) by recording the oxygen reduction current, which is proportional to the local oxygen concentration. A three-electrode configuration was used, consisting of a 10 µm platinum microelectrode as the working electrode, a platinum wire counter electrode, and a silver wire acting as a quasi-reference electrode. MCF-7 and A549 cells were cultured in the *OxygenControl plate* at different O_2 levels (*i.e.* 1%, 3%, 5%) and the HIF stabilization was analyzed using fluorescence microscopy, ELISA assay and Western-blotting.

Results

The OxygenControl plate successfully controls the oxygen concentration in the cell culture medium, and the target oxygen level is reached within few minutes. Different oxygen levels were achieved in the cell culture, including 1%, 3%, 5%. Homogeneous oxygen concentration is achieved throughout the well, independently form its size (96-, 24-, 12-, 6-multiwell plates were tested). The oxygen concentration is stable for up to 5 days. Cell growth curves demonstrated compatibility of the device with MCF-7 and A549 cell cultures, while fluorescence imaging Western-blotting and ELISA assays highlighted HIF stabilisation at controlled oxygen levels, in a time-dependent fashion.

Conclusion

The OxygenControl plate was demonstrated to be an effective and user-friendly device for the control of oxygen levels *in vitro*, providing a pathophysiological relevant microenvironment for cancer research.

D2 – P098

Biocompatibility challenges of biomaterials in mechanical circulatory support: Limitations of in vitro models in predicting in vivo performance

Cholewa K[1,2], Kurtyka P[2], Szuber-Dynia A[1,2], Kapis A[2], Gawlikowski M[1,2]
[1]Faculty of Biomedical Engineering, Silesian University of Technology; [2]Institute of Heart Prostheses, Foundation of Cardiac Surgery Development, Zabrze, Poland

Introduction

Mechanical circulatory support (MCS) systems involve prolonged interactions between biomaterials and biological environment, making biocompatibility a critical determinant of device performance and patient safety. Despite advances in biomaterials design and surface engineering, complications such as thrombosis, hemolysis, inflammatory responses, complement activation, and device-associated infections remain prevalent. These complications highlight that biocompatibility in MCS represents both a material challenge and a significant clinical problem. In particular, the translation of in vitro findings into reliable in vivo performance is still not fully established.

Aim

This work aims to evaluate limitations in the biocompatibility assessment of biomaterials in MCS systems, focusing on the translational gap between in vitro testing and in vivo preclinical outcomes.

Materials and Methods

In vitro biocompatibility assessment of biomaterials utilized in MCS was performed using assays targeting clinically important endpoints, including hemocompatibility and thrombogenicity under flow conditions. Thrombogenic potential was evaluated using models reflecting shear-dependent platelet activation and coagulation processes associated with MCS implantation. In vivo preclinical studies were conducted on large animal model to evaluate biological responses under physiologically relevant conditions. These studies enabled the assessment of device-related complications, including thrombosis, coagulation system activation, and inflammatory and infectious responses during MCS support. The in vitro findings were analyzed in relation to in vivo outcomes, with emphasis on their predictive value and ability to reflect physiological conditions, including flow dynamics, shear stress gradients, and patient-specific variability.

Results

In vitro models provide controlled and reproducible conditions for biomaterials screening. However, they do not fully capture the complexity of in vivo conditions. Factors such as device-specific hemodynamics, immune activation, and systemic biological responses are insufficiently represented. Consequently, some inconsistencies between in vitro and in vivo findings are frequently observed. Biomaterials demonstrating favorable hemocompatibility under in vitro conditions may exhibit increased thrombogenicity, coagulation system activation, or susceptibility to infection in vivo. These discrepancies limit the predictive value of in vitro testing and complicate translation to preclinical safety assessment.

Conclusion

Biocompatibility of biomaterials in MCS remains a multifactorial challenge at both the material and clinical levels. The limited translational relevance of current in vitro models, particularly for hemocompatibility, highlights a critical gap in evaluation strategies. Preclinical studies remain essential for assessing device safety, as they integrate systemic responses and clinically relevant complications such as pump thrombosis and device-associated infections. Bridging the gap between in vitro and in vivo assessment is essential for improving the safety, reliability, and clinical translation of MCS technologies.

Acknowledgements

The work was prepared as part of the “Implementation Doctorate 2024” program, financed by the Ministry of Science and Higher Education (DWD/8/0117/2024 and DWD/8/0118/2024). Research was also supported by the National Centre for Research and Development (NCBR) under the LIDER program (LIDER14/0239/2023). The work was also partially prepared as part of the project co-financed by the NCBR (POIR.04.01.02-00-0073/17-00) and the statutory research project (07/010/BK_26/1058).

D2 – P099

Optimizing cryo-preservation methods for long-term storage of 3D bioprinted constructs

Pitton M.[1], Lazzaro A.[1], Madè A.[2], Renna L.V.[2], Delgrosso E.[3], Scocozza F.[3], Conti M.[1,3], Cardani R.[2]
[1]C3D Laboratory, Bioprinting Unit, IRCCS Policlinico San Donato, San Donato, Milano; [2]BioBank BioCor, IRCCS Policlinico San Donato, San Donato, Milano; [3]CompMech DICar, University of Pavia, Pavia, Italy

Introduction

3D bioprinting is an emerging Additive Manufacturing technique which consists in precisely bioprinting biomaterials combined with living cells (bioinks). Even though solutions for personalized medicine have been implemented, the long-term storage of bioprinted constructs is challenging.

Aim

We aimed to define a standardized and reproducible protocol to cryo-preserve bioprinted constructs by investigating the influence of the freezing/thawing process parameters on samples' stability-stiffness-biocompatibility.

Materials and Methods

Bioinks concentration was set by combining alginate (15-25cP, 2-4-6-8%w/V) with gelatin (4%w/V). To screen the optimal bioink composition, printing accuracy (PA%) was evaluated with INKredible+ (CELLINK, Sweden) by 3D printing grid-like structures (n=3 per each; 1x2cm, with 8 adjacent squares 0.5x0.5cm; G=0.410 μm; v=2.5-5 mm s^{-1}) (*Ribezzi et al., 2023*). Three freezing protocols were tested from 4°C: up to -196°C (A); up to -80°C (B); up to -20°C, 1h rest, and up to -80°C (C). For each protocol, four freezing media were evaluated: on air (FM1); a commercially available one (*Miltenyi Biotec*, FM2); FBS90+DMSO10 (FM3); DMEM75+FBS20+DMSO5 (FM4) (Figure 1). Cell-free samples (n=3 per each, d=5 mm, h=1.5 mm) were printed, cryo-preserved and thawed. Thawing process was monitored by measuring samples' temperature after 10, 60, 120, 180 s of immersion in thermostatic bath (37°C), whereas their *in vitro* stability was evaluated at subsequent time points (t=0,1,2,3,24,48,168,336 h). The influence of cryo-preservation on cell viability was assessed by 3D bioprinting ALG4-GEL4 with AG01522 fibroblasts ($10x10^6$ cells mL^{-1}). Once thawed, cell viability was qualitatively investigated with Live&Dead staining.

Results

ALG4-GEL4 resulted the most promising bioink (PA>80%, v=5 mm s^{-1}) and selected for further experiments. To optimize the thawing process, we monitored the samples' temperature kinetic, which seemed to reach a *plateau* after 120 s of immersion in a thermostatic bath (37°C). Once thawed, samples were incubated in culture medium and weighted at subsequent time points: all the formulations remained stable up to 14 days. FM4 (DMEM75+FBS20+DMSO5) seemed to guarantee a weight variation comparable to the kinetic of fresh samples, probably due to the larger amount of DMEM which cryo-protected the samples, whereas FM1 (on air) exposed the models to a higher thermal shock. Cell-laden samples showed their ability in maintaining cell viability once cryo-preserved constructs have been thawed and cultured.

Conclusion

We aimed to optimize a reproducible cryo-preservation protocol for long-term storage of bioprinted constructs. Further perspective will be directed to evaluate the impact of this protocol on cell viability, morphology and functionality of more sensible cells, by combining also different bioinks.

References

[1]Ribezzi D. et al. Design of a novel bioink suitable for the 3D printing of lymphoid cells. *Frontiers in Biomaterials Science* 2023; 1081065.



Figure 1. Freezing protocols optimization. Samples were bioprinted (n = 3 per each condition) and immersed in different freezing media (FM1, FM2, FM3, FM4), as reported. After maintaining the samples in ice (4°C), they were frozen with three different protocols (A, B, C), as explained, and subsequently stored for 5 days.




Figure 2. Live&Dead staining. Cell-laden samples (with AG01522 fibroblasts) were bioprinted, immersed in FM2, FM3, FM4, and cryo-preserved (A, B, C) for 5 days. After thawing (< 120 s), constructs were thawed, immersed in DMEM, and cultured up to 7 days. Bioprinted fibroblasts remained viable up to 7 days of cell culture (magnification 4X).

D2 – P100

Hybrid 3D cryo-bioprinting and electrospun nanofiber integration for mechanically enhanced biomimetic cartilage scaffolds

Carrasco Montesdeoca C.Y.[1,2], Finzi Corat M.A.[1], Khayet M.[2], Roberta Marciano F.[3], Oliveira Lobo A.[3]
[1]Faculty of Medical Science, University of Campinas, Campinas SP, Brazil, [2]Dept. of Structure of Matter, Thermal Physics and Electronics, Faculty of Physics, University Complutense of Madrid, Avda. Complutense, Madrid, Spain, [3]BioMatLab, PPGCM, Federal University of Piauí, Brazil

Hyaline cartilage presents a highly organized hierarchical architecture and sustains considerable mechanical loading, making its faithful biomimetic reproduction particularly challenging[1-2]. In this work, we developed a modified integrated with 3D cryo-bioprinting and random ultrathin electrospun fibrous reinforcement to enhance scaffold mechanical performance while enabling controlled oxygen release to mitigate the severe hypoxic microenvironment associated with osteoarthritis. Mats of ultrathin fibers were developed with polyvinyl alcohol (PVA) and polyvinyl alcohol–calcium peroxide composites (PVA/CPO), the bioink was engineered to act as an intrinsic cryoprotective matrix, preserving cell viability during low-temperature processing. Scanning electron microscopy (SEM), Fourier transform infrared spectroscopy (FTIR) were utilized for morphological and compositional analyses. Others test as contact angle, porosity and degradability were utilized to determined characteristic specific, and in-vitro test were done to evaluated the biological properties of biomimetic cartilage structures. The results shown that synergistic effect of bioink, low-temperature, fibrous reinforcement, and CPO nanoparticle incorporation significantly improved the mechanical properties of gelatin methacryloyl (GelMA) hydrogels. Besides, cryo-bioprinting eliminated the need for sacrificial or support materials during GelMA deposition, due to GelMA supplementation with DMEM/F12 increased bioink viscosity at room temperature, thereby enhancing print fidelity and structural stability. Constructs incorporating randomly interposed ultrathin fibers containing CPO exhibited superior cell viability over three days compared with PVA ultrathin fiber. Overall, this integrated strategy enables the fabrication of mechanically reinforced constructs with properties approaching those of native hyaline cartilage using biocompatible and environmentally sustainable components.




Figure 1: Graphical abstract.

References

[1]Ying H., Shen C., Pan R., Li X., Chen Y. Strategy insight: Mechanical properties of biomaterials' influence on hydrogel-mesenchymal stromal cell combination for osteoarthritis therapy. *Front. Pharmacol* 2023; vol. 14, no. April; 1–7. doi: 10.3389/fphar.2023.1152612.
[2]Correia C.R., Reis R. L., Mano J. F. Multiphasic, multistructured and hierarchical strategies for cartilage regeneration. *Adv. Exp. Med. Biol* 2015; vol. 881; 143–160. doi: 10.1007/978-3-319-22345-2_9.

D2 – P101

X-TRUDE: A process-informed framework for high-fidelity analysis of hydrogel extrusion

Sanaei F.[1], Bertsch P.[1,2], Lafosse J.[1], Leeuwenburgh S.C.G.[1], Diba M.[1]
[1]Dept. of Dentistry-Regenerative Biomaterials, Radboud Institute for Medical Innovation, Radboud University Medical Center, Nijmegen, The Netherlands; [2]Current address: Dept. of Chemistry, University of Fribourg, Fribourg, Switzerland

Introduction

Reliable extrusion of viscoelastic hydrogels is crucial for technologies ranging from 3D (bio)printing to injectable therapeutics, yet current methods to characterize extrusion performance fail to mimic key processing conditions. Hydrogel extrusion is commonly assessed by rotational rheology (RR), which does not capture the flow profile of extrusion process, resulting in poor reliability and predictability, while visual assessment of morphological features is commonly performed post-extrusion. Consequently, extrusion performance cannot be precisely predicted or controlled, particularly for thermosensitive, shear-thinning, or heterogeneous hydrogels. This methodological gap limits the translatability of RR results to real-life extrusion of these materials.

Aim

To address this gap, we introduce X-TRUDE (Extrusion Rheology for Understanding and Defining Extrudability), a capillary rheology-based platform that recapitulates the spatiotemporal conditions of extrusion to characterize and quantify material behavior under process-relevant environments.

Materials and Methods

X-TRUDE consists of a temperature-controlled extrusion unit with in situ pressure and temperature monitoring, coupled with visual extrudate assessment. Three formulations representing distinct material classes were evaluated: Pluronic F-127 as a synthetic shear-thinning hydrogel, monolithic gelatin methacryloyl (mGelMA) as a homogeneous natural polymer hydrogel, and granular GelMA (gGelMA) as a jammed microgel system.

Results

X-TRUDE revealed substantial discrepancies relative to RR across all formulations. Flow curves for 5 wt% mGelMA yielded viscosity values approximately threefold higher than RR across comparable shear-rate ranges, while 10 wt% mGelMA formulation predicted by RR to extrude smoothly failed to extrude at all (Figure 1). X-TRUDE captured extrusion-specific phenomena inaccessible to conventional methods, including transient evolution of apparent rheological response, heterogeneity-induced extrudate morphology variations, and filter-pressing phase separation in granular systems (Figure 2). Across material classes, formulations exhibited distinct extrusion failure modes, with granular hydrogels being particularly prone to phase-separation phenomena. Integrated temperature sensing further revealed dramatic thermal gradients (up to 10 °C) from syringe to capillary exit, significantly influencing extrusion behavior. Analysis of temporal pressure fluctuations, quantified through local pressure fluctuation (LPF), mechanistically linked these transient flow instabilities to the resulting filament morphology, establishing LPF as a generalizable sensory metric for predicting extrusion performance across diverse material systems.

Conclusion

Our findings demonstrate that RR cannot faithfully predict material flow behavior under capillary extrusion conditions. By probing intrinsic material properties within extrinsic processing conditions, X-TRUDE bridges the gap between standard rheological analysis and actual extrusion performance. This integrated, mechanistic framework enables more reliable formulation development, reduces failure during process translation, and provides a generalizable benchmarking tool for extrusion-based technologies in biofabrication, therapeutic delivery, and soft material manufacturing.




Figure 1. Rheological behavior of mGelMA formulations characterized using rotational rheology (RR) and the X-TRUDE system. (a–c) Flow behavior assessed (a) using RR shown as flow curves, (b) using X-TRUDE shown as pressure-time plots (mGelMA-10 stopped at syringe pressure tolerance), and (c) representative images of the nozzle tip/extruded filament. X-TRUDE measurements (b-c) were performed using an 18G nozzle at 10 mm s^{-1}. (d–f) Flow behavior inconsistencies shown as (d) comparative RR and X-TRUDE flow curves, (e) shear-thinning index n from RR (ascending: 0.1–100 s^{-1}; descending: 100–0.1 s^{-1}) and X-TRUDE (~1–100 s^{-1} for mGelMA-10; ~1–130 s^{-1} for mGelMA-5), and (f) material expulsion from geometry-plate gap (indicated with yellow arrows) during flow sweep characterization. Data in panel (e) are presented as mean ± standard deviation (n = 2 for RR, n = 3 for X-TRUDE). All experiments were carried out at room temperature (21 °C).




Figure 2. Extrusion phenomena captured using X-TRUDE across three hydrogel systems. (a-d) Pressure curves paired with corresponding microscopic images for each formulation. (a) Pluronic-25 exhibits stable, homogeneous extrusion with minimal temporal variation. (b) mGelMA-2.5 displays a pronounced shoulder feature and fragmented extrudate. gGelMA reveals (c) a filter-pressing regime, characterized by an initial low-pressure aqueous phase followed by a rapid pressure increase, as well as (d) intermittent nozzle clogging, reflected by rapid pressure spikes and transient pressure drops. All experiments were carried out at room temperature (21 °C). AU indicates arbitrary units.

D2 – P102

Microstructure evolution at selective laser melting of a biodegradable Mg-alloy

Raducanu D.[1], Cojocaru V.D.[1], Hendea R.E.[2], Stanciu D.[2], Nocivin A.[3], Zarnescu-Ivan N.[1], Cojocaru M.E.[1]
[1]National University of Science and Technology Politehnica of Bucharest - Bucharest; [2]ZIRCON DENT SRL - Cluj Napoca; [3]OVIDIUS University of Constanta – Constanta, Romania

Introduction

Biodegradable magnesium alloys have attracted attention for implantology due to their important advantages: high biocompatibility-magnesium ions can promote the bone healing [1], the mechanical properties close to natural bone (a Young's modulus of 41–45 GPa).
Additive manufacturing (AM) is suitable to obtain porous implants and bioactive scaffolds for tissue regeneration; for magnesium alloys is adequate the Selective Laser Melting (SLM) technique [2].

Aim

The goal of this work was to study the SLM-processability of a Mg-alloy and the structural of the 3D-printed samples by the variation of the SLM process parameters (laser power, scanning speed, layer thickness).

Materials and Methods

The feedstock for the SLM process (MYSINT 100-3D) is a powder-alloy prepared by mechanical alloying (MA) with a new composition: Mg-10Zn-0.8Ca-0.5Zr (%wt.) Various combinations of processing parameters for SLM were experimented with especial focus on laser energy density – E [J/mm^3]. SEM-SE investigations were performed using a Tescan VEGA II-XMU SEM microscope to examine the characteristics of the feed stock powders and SLM-ed samples. XRD analysis- using a Panalytical X'Pert PRO MRD diffractometer was also done.

Results


The laser energy density (E) represents an important and influential processing parameter, cumulating all others. E values were between 450-110 J/mm^3. Apparently, there are not major differences between samples: all show a porous morphology. However, the samples with higher E show a more irregular morphology of the pores. Most importantly, none of the selected samples show the unwanted balling effect. The initial chemical composition of the MA powder-alloy is preserved after SLM processing (Figure 1).

Conclusion

The experiments for 3D-printing of Mg-10Zn-0.8Ca-0.5Zr (%wt.) revealed that the best samples consistency, with no cracks and with good characteristics were obtained at the lowest energy density (E), – a low laser power associated with a moderate scanning speed allows layers adherence with no smog and balling, phenomena which occur at high laser power.

Acknowledgements

This work was supported by a grant of the Ministry of Research, Innovation and Digitization, CCCDI - UEFISCDI, project number PN-IV-P7-7.1-PTE-2024-0557, contract no. 4PTE / 08.01.2025, within PNCDI IV.



Element	At. No.	Mass Norm. [%]	Atom [%]	abs. error [%]	rel. error [%]
Magnesium	12	83,99288	86,34041	4,451057	5,493148
Zinc	30	9,145844	3,618125	0,277866	2,964172
Calcium	20	0,769007	0,494365	0,047869	6,143124
Zirconium	40	0,198489	0,05606	0,033798	16,80403
Oxygen	8	5,893779	9,49104	0,652001	10,91737
		100	100		

Figure 1. Chemical composition of the MA powder-alloy and SEM images after SLM processing

References

[1]Dong J., Lin T., Shao H., Wang H., Wang X., Song K., et al. Advances in degradation behavior of biomedical magnesium alloys: A review. *J. Alloys Compd*. 2022; 908; 164600. https://doi.org/10.1016/j.jallcom.2022.164600.
[2]Manic M., Vitković N., Mitic J. Design and Manufacturing of the Personalized Plate Implants. *In: Canciglieri Junior, O., Trajanovic, M.D. (eds) Personalized Orthopedics* 2022; Springer, Cham. https://doi.org/10.1007/978-3-030-98279-9_6.

D2 – P103

Freezing of high concentrations of cells for bioprinting applications in space

Kirbas E., Windisch J., von Witzleben M., Lode A., Gelinsky M.
Centre for Translational Bone, Joint and Soft Tissue Research, Faculty of Medicine & University Hospital, TU Dresden, Dresden, Germany

Introduction

With further space exploration, space expeditions will become longer and travel distances will increase. To become more independent from Earth, bioprinting is seen as one key technology. However, bioprinting applications in space require simplification of the process due to strong limitations of material transport capacity as well as resources and space on board of space stations.

Aim

In this study, instant preparation of bioinks by direct mixing of cryopreserved cells with the hydrogel immediately after thawing and before printing was explored. Initially, the possibility of cryopreserving cells in high concentrations and the effect of prolonged exposure to DMSO was evaluated. Finally, the concept was proven by examining the cell viability in constructs bioprinted from bioinks directly prepared from cryopreserved cells.

Materials and Methods

Fibroblasts (NHDF) were frozen with 10% DMSO in standard or high concentration (1 vs. 25 million/ml) and stored at -80°C for 1 month. Immediately after thawing and after 3 days cultivation in dilutions of 1:5-1:20, viable/dead cells were quantified following trypan blue staining. For instant bioink preparation, 25 million NHDF were frozen in either 1 mL or 500 µL of freezing medium. Following 1 month of storage, they were thawed, mixed into the hydrogel (Alginate/Methylcellulose dissolved in blood plasma) and bioprinted. As control, samples were bioprinted with bioinks prepared conventionally with freshly expanded and detached cells. Scaffolds were cultured for 35 days and cell viability and proliferation were analysed.

Results

NHDF can be frozen in high concentration without loss in post-thawing viability. Cell recovery during 3 days cultivation was significantly reduced at a 1:5 dilution of DMSO (as in the bioink immediately after preparation) and only slightly reduced at a 1:10 dilution (corresponding to the continuous loss of DMSO during cultivation after bioprinting) compared to a 1:20 dilution (control). In bioprinted constructs, cell viability and density was higher (unitl day 14) or comparable (afterwards) to the control, if bioinks were prepared from 25 million cells frozen in 1 ml. Lowering the freezing medium volume to 500 µl affected cell viability and density significantly.

Conclusion

This study showed that on-site expansion of cells for bioink preparation can be circumvented as they can be frozen at high concentrations on Earth; on the space station, bioinks for bioprinting can be quickly, easily and reproducibly prepared directly after thawing the cells.

Acknowledgements

This work was funded by the German Space Agency at DLR (grant number 50WB2332).

D2 – P104

Digital light processing-based 3D printing of GelMA–PEGDA-CNF scaffolds: Quantitative analysis of printability, shape fidelity and scaffold properties

Shruthi G, Basu B
Laboratory for biomaterials science and translational research, Materials Research Centre, Indian Institute of Science, Bengaluru, India

Introduction

Peripheral nerve injuries often result in significant functional impairment and require strategies that guide axonal regeneration across defect sites. Nerve guidance conduits (NGCs) have emerged as promising alternatives to autografts due to their ability to provide structural support for directed nerve regeneration. Hydrogels such as gelatin methacryloyl (GelMA) are widely used in neural tissue engineering owing to their biocompatibility and photocrosslinkable nature. However, GelMA-based constructs often exhibit limited mechanical strength and lack electrical conductivity, which are important for neural signalling. Digital light processing (DLP) based 3D printing enables the fabrication of hydrogel scaffolds with high resolution. Incorporation of conductive nanomaterials such as carbon nanofibers (CNFs) into GelMA–PEGDA hydrogel systems enhances both mechanical stability and electrical functionality of the printed constructs.

Aim

To fabricate GelMA–PEGDA–CNF hydrogels via DLP and evaluate scaffold properties.

Materials and Methods

GelMA–PEGDA photocrosslinkable hydrogels containing LAP photoinitiator, tartrazine photoabsorber, and carbon nanofibers (CNFs) were prepared for DLP printing of nerve guidance conduits. Nerve guidance conduit geometries with defined lumen structures were fabricated using a DLP-based printing system.

Results


The GelMA–PEGDA–CNF hydrogel formulations were successfully processed using DLP printing, producing scaffolds with high geometric fidelity and well-defined pore architectures. Printability analysis showed minimal deviation between the CAD design and printed constructs, indicating good shape fidelity. Micro-computed tomography (micro-CT) confirmed an interconnected porous architecture with uniform pore distribution and an overall porosity of approximately 40%. FTIR spectra revealed characteristic amide and C–O functional group vibrations corresponding to GelMA and PEGDA, confirming successful hydrogel network formation. Thermogravimetric analysis (TGA) demonstrated improved thermal stability with increasing CNF concentration, with degradation temperatures increasing from ~305 °C for pristine hydrogels to ~320 °C for CNF-reinforced composites. Swelling studies indicated enhanced water uptake with CNF incorporation, while degradation kinetics showed slightly increased degradation rates. Compression testing showed that CNF addition influenced mechanical properties, with pristine GelMA–PEGDA exhibiting the highest Young's modulus (~68 kPa). Contact angle measurements indicated favorable surface wettability of the scaffolds.

Conclusion

DLP bioprinted GelMA–PEGDA hydrogels reinforced with carbon nanofibers provide a promising platform for fabrication of conductive nerve guidance conduits. The developed composite system combines printability, mechanical reinforcement, and electrical functionality for peripheral nerve regeneration.

Scaffold Composition




Analysing Shape Fidelity Compliance
CAD Model
HEIGHT
DIAMETER
STRANDS
PORES
200µm
200µm
100µm
100% macroscopic dimensional compliance

D2 – P105
Optimization of orodispersible personalized medicines by 3D printing

Cabral C.[1], Eusébio D.[2], Gomes P.[2], Valente J.[2], Alves N.[2], Novo P.[2], Alves G.[1], Santos A., Sousa A.[1]
[1]Rise-Health, Faculdade de Ciências da Saúde, Universidade da Beira Interior, Covilhã, Portugal; [2]CDRSP – Centre for Rapid and Sustainable Product Development, Instituto Politécnico de Leiria, Marinha Grande, Portugal

Introduction
Standardized “one-size-fits-all” medicines often fail to address interindividual heterogeneity in therapeutic requirements, particularly in pediatric and geriatric patients who require precise dose adaptation, acceptable dosage forms, or personalized drug combinations. Consequently, extemporaneous compounding is frequently employed but is associated with instability, suboptimal palatability, and dosing imprecision [1]. To address these limitations, the M3D.Printer project proposes an integrated 3D printing system for the fabrication of personalized, patient-friendly orodispersible dosage forms, to enhance therapeutic efficacy and safety.

Aim
This work focuses on two main components of ongoing research: i) a structured analysis of regulatory and quality control frameworks for decentralized production in healthcare settings; ii) formulation and preliminary development of 3D-printed orodispersible films incorporating antibiotics, using trimethoprim as a model active pharmaceutical ingredient (API), comprising: a) definition of printable excipient mixtures, b) selection of printing method and parameters, and c) design-of-experiments-based (DoE) optimization of the formulation and process parameters to achieve rapid disintegration.

Materials and Methods
A structured review is being conducted covering international and European guidance on point-of-care manufacturing, focusing on appropriate legislation for the implementation of decentralized 3D printing production. In parallel, formulation development employs semi-solid extrusion (SSE) 3D printing of orodispersible films. A DoE approach explores the effects of ratio of polymers, plasticisers and disintegrants used, and process parameters (nozzle diameter, extrusion rate, and deposition pattern), as well as dose-driven targets for film dimensions and thickness to deliver the intended API per unit. Through the DoE, we aim to elucidate the effects of formulation and process variables on printability, such disintegration time and mechanical integrity, thickness and mass uniformity, and content uniformity of trimethoprim.

Results
The preliminary findings of this work shows that initial trimethoprim formulations were printable and enabled the fabrication of structurally stable films, with current compositions exhibiting disintegration times above and below 3 min. Further studies based on DoE-guided optimization will determine the formulation and process adjustments required to achieve disintegration <3 min, while preserving mechanical integrity, dose strength/content uniformity, and dose-driven film dimensions and thickness, in accordance with European Pharmacopoeia requirements. Simultaneously, the regulatory review highlights that legislation on decentralized manufacturing remain undeveloped, with the United Kingdom leading recent advancements, highlighting the need for clearer quality control frameworks.

Conclusion
The work conducted to date provides essential regulatory insight and formulation/printing optimization required for a future point-of-care 3D printing system for personalized orodispersible medicines. These advances support the development of safe, compliant, and clinically viable decentralized manufacturing and highlights the potential of this project.

Acknowledgements
The authors acknowledge the project M3D.printer (ref: COMPETE2030-FEDER-02093600) supported by the Centro Regional Programme (Centro 2030), funded by the European Fund of Regional Development (FEDER), under Portugal 2030.

References
[1]Amekyeh H., Tarlochan F., Billa N. Practicality of 3D printed personalized medicines in therapeutics. *Frontiers in pharmacology* 2021; 12; 646836.

D2 – P106

A printable crosslinking system for liquid-free hydrogel stabilization for extrusion-based bioprinting in microgravity

Windisch J., Von Witzleben M., Busam N., Lode A., Gelinsky M.
Centre for Translational Bone, Joint and Soft Tissue Research, TU Dresden, Dresden, Germany

Introduction

With space missions aiming for Moon, Mars or even deep space, crews have to rely a lot more on independent medical care. 3D bioprinting could address this by enabling the fabrication of tissues for wound treatment or regenerative medical care directly on board. One known bottleneck for extrusion-based bioprinting in microgravity is the use of ion or enzyme-containing crosslinking solutions, as those are difficult to handle or contain, making highly viscous alternatives more or less mandatory.

Materials and Methods

To replace conventional crosslinking solutions in space missions, we developed and characterized a printable crosslinker ink. The ink is not a pure crosslinking tool, but more of an active yet sacrificial support component. Co-deposited within or alongside the bioink construct, it crosslinks the bioink through controlled diffusion of ions and/or enzymes. Building on a concept originally introduced during the Bioprint FirstAid Mission on the International Space Station and in parabolic flight campaigns, we now investigate this crosslinker ink systematically with a 3 wt% alginate 6 wt% gelatin bioink laden with normal human dermal fibroblasts (NHDF). The crosslinker ink, whose viscosity and dissolution can be controlled through different methylcellulose concentrations, delivers calcium ions for ionic alginate crosslinking and microbial transglutaminase for enzymatic gelatin crosslinking. We characterize different ink compositions and ion concentrations regarding crosslinking functionality, cell viability of NHDF, and dissolution of the ink during sacrificial use.

Results

The study shows that NHDF-laden bioinks crosslinked with the system maintain high cell viability over extended cultivation time and allowed fibroblast spreading across the constructs. The optimized system thereby allows dual crosslinking of a co-printed bioink, replacing the original liquid handling step. The gradual release of ions through diffusion avoids the cytotoxic effects associated with exposure to excessive calcium-ion concentrations.

Conclusion

The crosslinker ink system allows the replacement of liquid-based crosslinking steps, enabling ionic or enzymatic crosslinking in microgravity environments. The cell-friendly behavior and sacrificial support capabilities also promise high potential for terrestrial biofabrication applications. The sacrificial nature of the ink also opens further possibilities, such as core-shell bioprinting where dissolving the crosslinking core could allow the creation of tubular channels.

Acknowledgements

This work was funded by the German Space Agency at DLR (grant number 50WB2032).

D2 – P107

Biofabrication of a co-culture system for bone tissue engineering from nanocomposite bioinks incorporating Ga-doped mesoporous bioactive glass nanoparticles

Kurtuldu F.[1], Detsch R.[2], Mutlu N.[1,2], Michalek M.[1], Galusek D.[1,3], Boccaccini A.R.[2]
[1]FunGlass, Alexander Dubcek University of Trenčín, Trenčín, Slovakia; [2]Institute of Biomaterials, University of Erlangen-Nuremberg, Erlangen, Germany; [3]Joint Glass Centre of the IIC SAS, TnUAD and FChFT STU, FunGlass, Trenčín, Slovakia

Introduction

Bone tissue is composed of three primary components: an organic phase mainly composed of collagen; an inorganic phase consisting of calcium phosphates; and osteoblasts and osteoclast cells. Biofabrication has seen significant progress in recent years in the development of heterogeneous inorganic/organic materials to mimic bone composition. Nevertheless, the development of cell-laden bioinks for observing the early stages of bone formation remains a challenge.

Materials and Methods

A nanocomposite ink was developed using gallium-doped mesoporous bioactive glass nanoparticles (MBGNPs) functionalized with amine groups, combined with a hydrogel system composed of alginate dialdehyde (ADA) and gelatin (GEL). ADA was synthesized by oxidizing alginate with sodium (meta)periodate according to an established protocol[1]. MBGNPs were produced using a microemulsion-assisted sol-gel method[2]. Their physicochemical properties were characterized using SEM, XRD, XPS, and gas adsorption analyses. The nanocomposite hydrogel ink was employed to encapsulate osteoblast (MC3T3-E1) and osteoclast (RAW 264.7) progenitor cells. Extrusion-based 3D printing was used to fabricate the scaffolds, which were subsequently crosslinked with transglutaminase and calcium chloride solutions. 3D-printed scaffolds were then cultured under both normal and osteogenic medium conditions. Morphological assessments using fluorescence microscopy and SEM were performed to examine structural and phenotypic changes over time. The interaction and crosstalk between the two cell lines were examined by RT-qPCR, and osteoblast- and osteoclast-related gene expression levels were evaluated at days 7 and 14.

Results

3D-bioprinting of the bioink enabled high cell survival and rapid cell spreading within the co-culture system. Cell viability and live/dead assays demonstrated steady proliferation throughout the 14-day culture period. Morphological assessment revealed interactions between both cell types within the co-culture environment; macrophage cells began to proliferate colonially and form spheroids inside the scaffolds after 3-days of culture. Gene expression analysis revealed that gallium-containing samples enhanced osteogenesis while suppressing osteoclast differentiation within the co-culture system.

Conclusion

The findings of this study demonstrate that the MC3T3-E1/RAW 264.7 co-culture system within an ADA-GEL-MBGNPs osteoid-like construct provides a beneficial platform for investigating cell responses. The effect of gallium doping was systematically observed within the three-dimensional culture environment. The interactions between osteoblasts and macrophages were highlighted during the initial stages of bone formation.

Acknowledgements

This project has received funding from the Slovak Research and Development Agency under grant agreement VV-MVP-24-0409.

References

[1]Karakaya E., Schöbel L., Zhong Y., Hazur J., Heid S., Forster L., Teßmar J., Boccaccini A.R. Detsch R. *Biomacromolecules*, 2023; 24; 2982–2997.
[2]Kurtuldu F., Mutlu N., Friedrich R.P., Beltrán A.M., Liverani L., Detsch R., Alexiou C., Galusek D. Boccaccini A.R. *Biomater Adv*., 2024; 162; 213922.

D2 – P108

Fabrication of hollow microneedles for intradermal delivery by two-photon polymerization of a biocompatible photocrosslinkable polyester

Cleyman A.[1,2], Van Durme B.[1], Bijleveld B.[1], Pien N.[1], Jaén Ortega A.[1], Van Daele L.[1], Brancart J.[3], Van Rompaey V.[4], Blondeel P.[2], Van Vlierberghe S.[1]

[1]Polymer Chemistry and Biomaterials Group, Centre of Macromolecular Chemistry (CMaC), Dept. of Organic and Macromolecular Chemistry, Ghent University, Ghent; [2]Tissue Regeneration and Organ Printing (TROP) Research Center, Dept. of Human Structure and Repair, Ghent University, Ghent; [3]Sustainable Materials Engineering (SUME), Dept. of Materials and Chemistry (MACH), Vrije Universiteit Brussel (VUB), Brussels; [4]Dept. of Otorhinolaryngology and Head & Neck Surgery, Antwerp University Hospital, Dept. of Translational Neurosciences, University of Antwerp, Antwerp, Belgium

Introduction

Microneedles (MNs) have emerged as a promising platform for transdermal delivery because they enable minimally invasive and nearly painless administration of therapeutic agents. Hollow microneedles are particularly interesting for the delivery of biologics, including vaccines and proteins, as they allow the controlled injection of liquid formulations at relevant doses. However, the development of suitable materials for hollow microneedle fabrication remains challenging. Only a limited number of photocrosslinkable polyesters combine the biocompatibility, mechanical strength, and printability required for high-resolution fabrication by two-photon polymerization (2PP).

Materials and Methods

In this study, a star-shaped, acrylate-endcapped urethane-based poly(ε-caprolactone-co-δ-valerolactone-co-D,L-lactide) was investigated as a photocrosslinkable polyester platform for hollow MN fabrication. The polymer was characterized in terms of gel fraction, swelling behavior in phosphate-buffered saline, thermal stability, and thermomechanical performance. Biocompatibility was assessed using human fibroblasts, hemolysis testing, and OECD TG 439 EpiDerm skin irritation assays. For microfabrication, a 40 wt% resin formulation was processed by 2PP to produce hollow MN arrays. Functional performance was evaluated by injecting Texas Red-labeled dextran (10 kDa) into GelMA hydrogels.

Results

The developed material formed dense and stable crosslinked networks with a gel fraction of 94.4 ± 0.1% and a low swelling ratio of 1.07 ± 0.02 in phosphate-buffered saline, indicating efficient crosslinking and good dimensional stability. Thermal analysis showed stability up to 255 °C. Dynamic mechanical analysis revealed a Young's modulus of 1.83 MPa at ambient temperature and a glass transition temperature of 33.5 °C, close to physiological temperature. This enabled excellent shape-fixity at -20 °C and shape recovery above 85%. Biological evaluation demonstrated favorable cytocompatibility, with human fibroblast viability exceeding 80% after 7 days. In addition, hemolysis remained below 0.3%, while EpiDerm testing confirmed a non-irritant profile with a tissue viability of 97.8 ± 2.9%. Processing of the 40 wt% resin by 2PP resulted in freestanding hollow MN arrays with dimensions of 600 µm in height, 300 µm base width, and 60 µm tip opening (Figure 1A). Successful injection of Texas Red-labeled dextran into GelMA hydrogels confirmed the presence of open lumens (Figure 1B).




Figure 6: (A) SEM image of 2PP-printed constructs fabricated from a 40 wt/v% PCL-co-VL-co-DLLA AUP resin in the presence of 2 wt/wt% M2CMK. (B) Confocal microscopy images of the autofluorescent 2PP-printed MNs (405 nm) after 48 h soaking in Texas Red-labeled dextran (top right), followed by 24 h insertion into 7.5 wt% crosslinked GelMA. This resulted in depletion of the dye from the MNs and its homogeneous diffusion throughout the hydrogel (594 nm), with residual channel imprints remaining visible (white arrow).

Conclusion

Overall, this work demonstrates that this biocompatible photocrosslinkable polyester is a promising material platform for the fabrication of hollow MNs by 2PP. The combination of favorable mechanical properties, excellent biological performance, and precise microfabrication highlights its strong potential for intradermal delivery applications.

Acknowledgements

Van Durme B. and Van Daele L. would like to acknowledge the Research Foundation – Flanders for a PhD (FWO-SB) and Junior Post-Doc with grant numbers 1SH3W24N and 12A7B26N, respectively. Bijleveld B., Brancart J. and Van Vlierberghe S. gratefully acknowledge support from the ICON PHOTO-AUP project funded by VLAIO (Flanders Innovation & Entrepreneurship) with project number HBC.2023.0736. Jaén Ortega A. acknowledges the support by the Instituto para la Formación y Aprovechamiento de Recursos Humanos (IFARHU) and the Secretaría Nacional de Ciencia, Tecnología e Innovación (SENACYT) of the Republic of Panama through the scholarship program IFARHUSENACYT (270-2023-010). The authors acknowledge the NMR expertise centre from Ghent University for providing support and access to its NMR infrastructure. The 400 MHz NMR spectrometer used in this work was funded by a grant of the FWO (grant number I006920N) and the “Bijzonder Onderzoeksfonds” (BOF) of Ghent University (grant code BOF.BAS.2022.0023.01).

D2 – P109

Expanding melt electrowriting toward hydrophilic polymer systems: Material design and processing

Ebrahimi M.[1], Satarova S.[1], Taurino I.[2], Van de Poel B.[3], Bloemen V.[1], Mignon A.[1]
[1]Dept. of Materials Engineering, Surface and Interface Engineered Materials (SIEM), KU Leuven; [2]Dept. of Physics and Astronomy, Laboratory for Semiconductor Physics, KU Leuven; [3]KU Leuven Plant Institute (LPI), KU Leuven, Leuven, Belgium

Melt electrowriting (MEW) enables the fabrication of high-resolution, solvent-free 3D porous structures by controlled extrusion of molten polymers through a nozzle, forming continuous micrometric fibers upon solidification. Poly(ε-caprolactone) (PCL) is the gold-standard material for MEW due to its low melting temperature, rapid crystallization, and high fiber fidelity. However, its intrinsic hydrophobicity limits applications that require interaction with moisture or biological environments, such as humidity sensing and tissue engineering applications. In this work, we aim to expand the material scope of MEW toward hydrophilic polymer systems. To address the inherent challenge between hydrophilicity and melt processability, complementary material strategies are explored. First, blends of PCL with PEG-based photocrosslinkable polymers (PEGDA/PEGDMA, 20 and 35 kg/mol) are developed in combination with 1 wt% TPO-L as a photoinitiator. The blend composition and PEG molecular weight are systematically varied to balance hydrophilicity with the rheological and thermal requirements for stable fiber deposition, followed by post-printing crosslinking to stabilize the structure. Second, methacrylated poly(vinyl alcohol) (PVA) systems with varying degrees of methacrylation (5–15%) and different molecular weights are investigated to tune thermal behavior, printability, and swelling characteristics. Finally, PCL-PEG-PCL triblock copolymers are synthesized, in which the molecular weight of the PEG mid-block is systematically varied (8, 10, 12, 20, and 35 kg/mol) to create a library of materials with different PCL-to-PEG block ratios. In these systems, the PCL end blocks ensure melt stability and crystallization behavior required for MEW, while the PEG mid-block introduces controlled hydrophilicity and moisture uptake. All materials are evaluated in terms of thermal properties (melting temperature, crystallization temperature, and Tg), viscosity, and printing stability. The resulting fibrous meshes are further characterized for swelling behavior, surface wettability, and structural integrity. Overall, this work demonstrates that hydrophilic, moisture-responsive polymer systems can be successfully processed via MEW. More broadly, these findings expand the material design space of MEW toward functional, water-interactive systems for sensing, biomedical, and tissue engineering applications.

D2 – P110

Engineering 3D chitosan dressings crosslinked with genipin (from *Genipa americana* L.) for enhanced chronic wound healing

Lima R.R.S.[1], Souza J.S.N.[1], Viana E.R.C.[1], Silva-Filho E.C.S. [1], de Almeida E.A. [2], Muniz, E.C.[1,2,3]
[1]Dept. of Chemistry, Federal University of Piauí (UFPI), Teresina, PI; [2]Dept. of Chemistry, State University of Maringá (UEM), Maringá, PR; [3]Postgraduate Program in Materials Science and Engineering, Federal University of Technology - Paraná - Campus UTFPR, Londrina, PR, Brazil

Introduction

Chronic wounds, such as diabetic ulcers, represent a significant clinical challenge, requiring advanced biomaterials that promote an adequate healing environment. 3D printing technology allows the fabrication of personalized dressings with precise structural control. This study focuses on developing bio-printed dressings using chitosan, gelatin, and poly(vinyl alcohol) (PVA), utilizing natural crosslinking to enhance stability and biocompatibility.

Aim

To develop and characterize 3D-printed hydrogel dressings crosslinked with natural genipin for potential application in tissue engineering.

Materials and Methods

Polymeric blends of chitosan, gelatin, and PVA were prepared and crosslinked with genipin, extracted in a previous study. The dressings were fabricated using a 3D printing system adapted with a syringe extruder (Figure 1), following a process that ranged from blend preparation to final printing (Figure 2).

Results

The bio-ink exhibited pseudoplastic and viscoelastic behavior, ensuring shape fidelity after printing (Fig. 1). FTIR analysis confirmed the interaction between the blend components and the effectiveness of the crosslinking, evidenced by the appearance of new vibrational bands and the shift or change in intensity of characteristic bands of amine and hydroxyl groups. XRD patterns revealed a reduction in the crystallinity of the isolated polymers, confirming the formation of an amorphous matrix and good compatibility between the components. SEM images showed a porous and interconnected morphology. Swelling tests demonstrated a high fluid absorption capacity (over 400%), essential for exudate management and maintaining a moist environment. Mechanical tests showed flexibility and resistance, while tests with *Artemia salina* confirmed the biocompatibility.

Conclusion

The use of genipin as a natural crosslinker provided superior structural stability compared to non-crosslinked matrices. The 3D printing strategy proved efficient for producing customized dressings that align with Green Chemistry principles and Sustainable Development Goals. The results suggest that these biocomposites are promising candidates for the treatment of chronic wounds and regenerative medicine.

Acknowledgements

Infrastructure support from: UFPI, LIMAV, IFPI, IFAL, UFRN, UNIFSA, Brazil. Financial support from: CAPES (Capes Cofecub-Program), CNPq (INCT-Polysaccharides, Brazil).




Figure1: Fabrication and structural characterization of genipin-crosslinked hydrogel system. Overview of the hydrogel fabrication and characterization. (A) Platform configuration and syringe-based deposition system; (B) SEM images showing microstructural morphology at different magnifications; (C) FTIR spectra indicating functional groups and crosslinking interactions; (D) XRD patterns comparing crystallinity before and after genipin crosslinking.




Figure 2: Schematic overview of the HG-CHGE 20-C hydrogel synthesis and 3D bioprinting process. (A) Chemical structures of Chitosan (CH), Gelatin (GE), Poly(vinyl alcohol) (PVA), Glycerol, and Genipin. (B) Bioink preparation workflow including polymer dissolution, crosslinker incorporation, and stabilization. (C) 3D extrusion-based bioprinting and the resulting crosslinked scaffold.

References

[1]Hafezi F., et al. 3D printed chitosan dressing crosslinked with genipin for potential healing of chronic wounds. *International Journal of Pharmaceutics* 2019; v. 560, n. January; 406–415.
[2]Guo W., et al. Recent Advances of Chitosan-Based Hydrogels for Skin-Wound Dressings. *Gels* 2024; v. 10 n. 3; 175.
[3]Boateng J.S., et al. 3D printed composite dressings loaded with human epidermal growth factor for potential chronic wound healing applications. *Journal of Drug Delivery Science and Technology* 2023; 86.

D2 – P111

Engineering a temperature-controlled handheld bioprinter for urethral tissue regeneration using thermosensitive bioinks

Bilginer-Kartal R.[1], Aydın H.[1], Kuru B.[1], İzbudak B.[1], Pien N.[2], Eeckman N.[3], Van Vlierberghe S.[2], Pennisi P.[4], Bal-Öztürk A.[1]

[1]AdBioInk Biosystem Technology, Kocaeli, Turkey; [2]Polymer Chemistry and Biomaterials Group, Centre of Macromolecular Chemistry (CMaC), Ghent University, Ghent, Belgium; [3]4Tissue, Zwijnaarde, Belgium; [4]Dept. of Health Science and Technology, Aalborg University, Aalborg, Danmark

Introduction

Three-dimensional (3D) bioprinting is an innovative biofabrication technology widely used in advanced tissue engineering. It enables the fabrication of 3D structures through the layer-by-layer deposition of biomaterials, biochemical factors, and living cells. Although patient-specific scaffolds can be fabricated using conventional 3D bioprinting, geometric changes occurring at the surgical site following debridement may hinder anatomical adaptation and lead to graft–host mismatch. To overcome these limitations, *in-situ* bioprinting has emerged as a cutting-edge technology that allows direct deposition of cells and biomaterials onto the defect site. One of the key advances improving its clinical applicability is the development of handheld bioprinting devices (Biopen), which enable *in-situ* tissue fabrication. However, thermo-responsive bioinks used in Biopen can affected by ambient temperature during 3D bioprinting. Therefore, maintaining bioink printability and cell viability remains challenging due to the temperature-dependent rheological behavior of some bioinks. In this study, a temperature-controlled Biopen was engineered from the conventional Biopen previously developed by AdBioInk, enabling stable extrusion of thermosensitive bioinks and minimizing the effects of environmental temperature fluctuations during the 3D bioprinting for urethral tissue engineering applications.

Materials and Methods

The Biopen generated by AdBioInk was integrated with temperature-controlled system. Two peltiers that provide bidirectional heating and cooling were symmetrically positioned around the barrel house to ensure homogeneous temperature distribution. To enhance thermal stability, aluminum components, PLA-based elements, a copper heat transfer, and an aluminum fin-based heatsink were integrated to the peltier module, while incorporating a cooling compartment onto the aluminum heatsink. An OLED display module that allows real-time monitoring of key operational parameters was included into the Biopen. In addition, Biopen includes a 405 nm LED curing module for *in-situ* photocrosslinking of extruded gelatin-based bioinks. Performance characterization tests of the temperature controlled Biopen were conducted to evaluate temperature response, steady-state thermal stability test heat/cooling asymmetry, temperature deviation, while *in-situ* 3D printed gelatin-based structure were evaluated by printability index (Pr), filament collapse test and live-dead assay for cell survival.

Results

Precise temperature regulation within a 19–40 °C operational range was maintained by developed temperature-controlled Biopen, maintaining deviations below ±0.5 °C for up to 60 minutes. The extrusion consistency and printability of gelatin-based bioinks was significantly improved by controlled temperature regulation, resulting in Pr value close to 1 at certain temperature. Adjustable exposure times of up to 60 seconds and activation of photoinitiator were provided by curing module, allowing simultaneous deposition and stabilization of the printed structure. Preliminary *in-vitro* assessments confirmed that cell viability was preserved and enabled uniform filament formation was enabled owing to temperature-controlled extrusion.

Conclusion

The temperature-controlled Biopen offers improved operational reliability, which offers a promising platform for *in-situ* bioprinting applications in urethral tissue engineering.

Acknowledgements

STRONG-UR is a project funded by the European Union and has received funding from the Horizon Europe programme under grant agreement No 101191695. Views and opinions expressed are however those of the author(s) only and do not necessarily reflect those of the European Union or HaDEA. Neither the European Union nor the granting authority can be held responsible for them.

D2 – P112

Red-Light tomographic volumetric 3D printing in seconds for fabrication of colorless structures

Eftekhari[1,2], Zhang[2], Radmehr[3], Santala[3], Kellomäki[4], Laaksonen[1,5], Moser[2]
[1]Faculty of engineering and natural science, Tampere University, Tampere, Finland; [2]Laboratory of Applied Photonics Devices École Polytechnique Fédéral Lausanne (EPFL), Lausanne, Switzerland; [3]Bio- and Circular Economy Unit, Faculty of Engineering and Natural Sciences, Tampere University, Tampere, Finland; [4]Biomaterials and Tissue Engineering Group, Faculty of Medicine and Health Technology, Tampere University, Tampere, Finland; [5]Drug Research Program, Division of Pharmaceutical Bio-sciences, Faculty of Pharmacy, University of Helsinki, Helsinki, Finland

Introduction

Light-triggered polymerization is widely used in 3D printing because it enables on-demand curing of reactive materials. Conventional bioprinting and additive manufacturing methods, including extrusion-based, lithographic, laser-based, and melt electrowriting techniques, fabricate structures layer by layer. However, this approach limits structural complexity, often requires support materials, and is time-consuming, particularly for large constructs. In contrast, Tomographic Volumetric Additive Manufacturing (TVAM) enables the rapid fabrication of entire 3D objects in a single step. Yet, most volumetric printing methods rely on UV light, which suffers from high scattering, low penetration, and limited compatibility with light-sensitive materials. To address these challenges, lower-energy light such as red (or near-infrared) light offers a promising alternative. Here, for the first time, we present a red-light-based TVAM system for fabricating colorless 3D structures.

Materials and Methods

To investigate the reaction kinetics and mechanical properties during ambient photopolymerization, in situ photorheology was performed using a rotational rheometer (Discovery HR-2, TA Instruments, USA) with a 12 mm parallel-plate geometry. In addition, the emission of the photoinitiator methylene blue was monitored using a Vlinder Newton 7 imaging system.

Results

In this study, methylene blue (MB^+), an FDA-approved water-soluble dye, was used as a sacrificial photosensitizer and triethanolamine (TEA) as a one-electron/one-proton donor for red-light-driven traceless photopolymerization. In the presence of TEA, excited methylene blue is converted to its colorless leuco form while generating radicals that initiate polymerization. Under ambient conditions, reactive oxygen species are also formed, and continued irradiation degrades MB^+, producing a permanently transparent crosslinked hydrogel. Figure 1A shows the effect of initial viscosity on polymerization kinetics under ambient conditions. Based on these results, polyethylene glycol diacrylate (PEGDA) was used for red-light 3D printing of vascular and three-branched (Figure 1B and C) models under ambient conditions.



Figure 1. In situ photorheology measurements of PEGDA at different concentrations to evaluate gelation time. (B) Vascular model and (C) three-branched model fabricated by TVAM under red-light irradiation within 30 s.

Conclusion

We developed for the first time a red-light-based TVAM approach for the fabrication of colorless 3D structures under ambient conditions. The reduced scattering and enhanced penetration of red light make this strategy particularly promising for highly scattering materials and systems.

Acknowledgements
The authors gratefully ac-knowledge financial support from the European Research Council (ERC Consolidator Grant Project PADRE, No 101001016) and Tampere Institute for Advanced Study.

D2 – P113

Two-dimensional printing of functional wrinkled films by drop-on-demand technology: Assessment of cytocompatibility, antibacterial, and virucidal properties

Gonzalez-Henriquez C.M.[1,2], Rodriguez-Umanzor F.E.[1], Cohn-Inostroza N.A.[2], Sarabia-Vallejos M.A.[3]
[1]Dept. de Química, Universidad Tecnológica Metropolitana, Santiago, Chile; [2]Instituto Universitario de Investigación y Desarrollo Tecnológico, Santiago, Chile; [3]Facultad de Ingeniería, Universidad San Sebastián, Santiago, Chile

Introduction

This work explains the creation of multifunctional wrinkled polymeric films for biomedical applications using Drop-on-Demand (DOD) inkjet printing. This study addresses the difficulty of creating surfaces that both avoid microbial contamination and preserve cytocompatibility. The authors hope to develop materials with antibacterial, antiviral, and cell-supportive properties by combining chemical functionalization with regulated surface topography.

Materials and Methods

Functional monomers such as 2-hydroxyethyl methacrylate (HEMA), acrylic acid (AAc), and 2-(dimethylamino)ethyl methacrylate (DMAEMA) are among the functional monomers utilized, along with poly(ethylene glycol) diacrylate (PEGDA) as a crosslinker, and LAP as photoinitiator. To improve wettability, these inks were printed on UV-ozonized polycarbonate substrates. Controlled wrinkled microstructures were created by vacuum treatment, argon plasma exposure, and UV curing. In addition to biological tests using different bacterial strains, a coronavirus model (HCoV-229E) and preosteoblastic cells were used in this study, leading to thorough characterisation using spectroscopic (ATR-FTIR, Raman), rheological, and morphological (SEM, AFM) methods.

Results

Uniform wrinkled patterns with adjustable morphology and good printability were corroborated via AFM and SEM analysis. The films demonstrated notable antiviral effectiveness, including total inactivation of the virus in DMAEMA-based samples, and substantial antibacterial action, lowering bacterial viability by more than 90%. Crucially, every material promoted cell adhesion and growth, especially on wrinkled surfaces, and maintained good cytocompatibility (>70% cell viability).

Conclusion

These results demonstrate a scalable and economical method for creating multifunctional polymeric coatings. These materials have great potential for biomedical devices because they provide a balance between tissue compatibility and antibacterial activity, which is essential for tissue engineering and infection control.

Acknowledgements

The authors acknowledge financial support from FONDECYT (grant numbers 1260671 and 1260875).

D2 – P114

Development of conductive ink for extrusion 3D printing based on graphene derivates incorporation in GelMA polymer

Teixeira J.V.U.*; Bronze-Uhle E.S.; Lisboa Filho P.N.
School of Science /São Paulo State University “Julio de Mesquita Filho-Bauru, Brazil

Introduction

Conductive hydrogels have garnered significant attention in biomedicine due to their potential applications in tissue engineering, particularly for cardiac, neural, and spinal surgeries [1-2]. For successful biomedical applications, these inks must combine three key properties: conductivity, biocompatibility, and printability. In this study, we explore the combination of gelatin methacrylate (GelMA) and graphene oxide (GO) in various proportions to create a conductive and biocompatible ink suitable for extrusion-based 3D printing

Materials and Methods

GelMA was synthesized by modifying gelatin with methacrylic anhydride. The final ink formulation included 1 gram of GelMA dispersed in 5 milliliters of phosphate-buffered saline (PBS) and 5 milliliters of a 0.1% solution of lithium phenyl-2,4,6-trimethylbenzoylphosphinate (LAP), containing 7.5 micrograms. We evaluated the percentage of graphene oxide at concentrations ranging from 0.1% to 1.5% by weight. To assess the printability of the proposed inks, we conducted experiments on four different structures using 22G and 25G needles and then used microscopy to evaluate scaffold stability. Additionally, we constructed printed electrodes to analyze the ink's electrochemical properties through cyclic voltammetry and electrochemical impedance spectroscopy.

Results

Microscopy results indicate a strong correlation between structural data and the final scaffold conformation, up to a GO concentration of 1.5%. In terms of electrochemical properties, the incorporation of GO enhanced the conductivity of the ink in a simulated body medium, while charge transfer resistance decreased as the GO content increased.

Conclusion

The results demonstrated the suitability of the proposed GelMA/GO system to use as a conductive ink for future biomedical applications.

Acknowledgements

The authors acknowledge the Instituto de Estudos Avançados do Mar (IEMAR) for allowing the use of the electrochemical equipment. This study was financed, in part, by the São Paulo Research Foundation (FAPESP), Brasil. Process Number 25/07982-0 and 24/01132-2.

References

[1]Shin Y., Lee H.S., Jeong H., Kim D.H. Recent Advances in Conductive Hydrogels for Soft Biointegrated Electronics: Materials, Properties, and Device Applications. *Wearable Electronics* 2024.
[2]Zhang X., Zhang H., Zhang Y., Huangfu H., Yang Y., Qin Q., ... Zhou Y. 3D printed reduced graphene oxide-GelMA hybrid hydrogel scaffolds for potential neuralized bone regeneration. *Journal of Materials Chemistry B* 2023; 11(6); 1288-1301.

D2 – P115

Using 3D bioprinted hiPSC-derived engineered-heart-tissues as a human model to study variants associated with arrhythmia development

Singh S., Babini H., Tibbits G., Prondzynski M.

Atrial fibrillation (AF) is typically triggered by ectopic activity, causing disorganized cardiac rhythm and contributing to substantial morbidity and mortality. Recent studies have identified a KCNN3 variant that alters the small-conductance Ca^{2+}-activated K^+ (SK3) channel, a key regulator of cardiac rhythm. The variant is predicted to remodel action potential duration (APD), calcium handling, conduction, and various electrophysiological properties, but its tissue-level effects remain poorly understood. Current models, including 2D monolayers and animal models, lack human atrial architecture, physiological mechanical loading, and scalability, limiting mechanistic genotype-to-phenotype inference and translational drug testing. This study will engineer patient-relevant atrial engineered-heart-tissues (EHTs) using human induced pluripotent stem cells (hiPSCs) to provide a platform to evaluate how this variant may contribute to the development of AF. We will generate atrial EHTs using a standardized 3D bioprinting workflow that anchors tissues between flexible posts to impose defined geometry and mechanical preload. This architecture is expected to improve electrophysiological fidelity by promoting cardiomyocyte alignment, cell–cell coupling, and reproducible wave propagation, enabling robust measures of the disturbed electrical properties. Concurrently, EHT post deflection enables non-destructive quantification of contractile function, which is important because SK3-associated electrophysiological remodeling may impair excitation-contraction coupling in ways not captured by electrical indices alone. By applying high-speed optical mapping with voltage and calcium imaging, alongside contractile assessment, we aim to establish a validated, reproducible platform linking genotype to tissue-scale phenotype to help identify intervention strategies.

References

[1]Ellinor P.T., Lunetta K.L., Glazer N.L., Pfeufer A., Alonso A., Chung M.K., et al. Common variants in KCNN3 are associated with lone atrial fibrillation. *Nature Genetics* 2010; 42(3); 240-244.
[2]Zhang X.D., Lieu D.K., Chiamvimonvat N. Small-conductance Ca^{2+}-activated K^+ channels and cardiac arrhythmias. *Heart Rhythm* 2015; 12(8); 1845-1851.
[3]Gunawan M.G., Sangha S.S., Shafaattalab S., Lin E., Heims-Waldron D.A., Bezzerides VJ.., et al. Drug screening platform using human induced pluripotent stem cell-derived atrial cardiomyocytes and optical mapping. *Stem Cells Translational Medicine* 2021; 10(1); 68-82.
[4]Mannhardt I., Breckwoldt K., Letuffe-Brenière D., Schaaf S., Schulz H., Neuber C., et al. Human engineered heart tissue: analysis of contractile force. *Stem Cell Reports* 2016; 7(1); 29-42.
[5]Prondzynski M., Krämer E., Laufer S.D., Shibamiya A., Pless O., Müller O.J., et al. Efficient and reproducible generation of human iPSC-derived cardiomyocytes in suspension culture. *Nature Communications* 2024.

D2 – P116

Multifunctional piezoresistive MWCNT-reinforced nanocomposites for self-sensing applications

Anbu Anandhan J.[1], Krishnapillai S.[1], Ramachandran V.[2]
[1]Dept. of Mechanical Engineering, Indian Institute of Technology Madras; [2]Dept. of Aerospace Engineering, Indian Institute of Technology Madras, Chennai, India

Introduction

Additive manufacturing has revolutionized the fabrication of ceramic-polymer composites by enabling lightweight structures with improved toughness and enhanced thermal performance. Compared to fused deposition modeling (FDM), digital light processing (DLP) provides superior printing speed and dimensional accuracy. This study investigates and compares the mechanical and piezoresistive properties of hydroxyapatite (HA)/multi-walled carbon nanotube (MWCNT)/polymer composites fabricated through DLP for biomedical applications. The incorporation of HA improves biocompatibility, while MWCNT enhances hardness, piezo-resistivity, and wear resistance.

Aim


To develop self-sensing implants for continuous monitoring of implants.

Materials and Methods

A homogeneous photocurable nanocomposite resin was formulated by dispersing MWCNT (0.3 phr) and HA (5 phr) into a surgical guide resin matrix. The viscosity and UV-curing parameters of the developed resin were optimized to ensure printability in suspension-based DLP printing. Rheological characterization was performed using a rheometer, and the viscosity was found to be within the acceptable processing range. Solid coupons were fabricated using a 405 nm DLP 3D printer, followed by post-curing to complete cross-linking. Scanning electron microscopy (SEM) was employed to evaluate filler dispersion and interfacial bonding within the polymer matrix.

Results

SEM analysis confirmed homogeneous dispersion of HA and conductive fillers within the clear surgical guide resin matrix, along with strong interfacial bonding between the fillers and polymer matrix. The piezoresistive responses of SG-0.3MWCNT-5HA solid specimens were evaluated under strain and depicted in the following figure. It exhibited a highest gauge factor of 8, indicating excellent self-sensing capability. The developed composites also demonstrated enhanced mechanical and thermal performance, as well as biocompatibility, suitable for biomedical applications.



Conclusion

The developed HA/MWCNT/polymer nanocomposite resin demonstrated excellent printability, structural integrity, and multifunctional performance when fabricated using DLP technology. The incorporation of HA and conductive nanofillers significantly improved biocompatibility and piezoresistive behavior. It demonstrated superior self-sensing performance, underscoring the potential of these DLP-fabricated composites for advanced biomedical and smart-sensing applications.

D2 – P117

Bioprinting strategies for small-diameter tubular constructs: From vascular grafts to Wirsung duct training phantoms

F.P.[1], S.F.[2], S. M[1], A.C.[1,3], P.O.[1], F.D.G.[1,3]
[1]IRCCS Humanitas Research Hospital, Rozzano, 20089 Milan, Lombardy; [2]Dept. of Biomedical Sciences, Humanitas University, Milan; [3]Dept. of Chemistry, Materials and Chemical Engineering “Giulio Natta”, Politecnico di Milano, Milan, Lombardy, Italy

Introduction

3D bioprinting represents a promising strategy for fabricating biocompatible tubular constructs that mimic small-diameter biological tissues. In this study, a single rotating-mandrel bioprinting platform, Electrospider, was used to address two different clinical needs involving tubular structures.

Aim

The first objective was to develop a cellularized multilayer vascular graft designed to reproduce the mechanical and biological properties of native small-diameter vessels (<6 mm), for which synthetic alternatives still show high failure rates due to thrombosis and compliance mismatch. The second objective was to fabricate an acellular monolayer Wirsung duct phantom for mechanical replication and surgical training in pancreatic anastomosis, with the potential to reduce the risk of postoperative pancreatic fistula after pancreatoduodenectomy.

Materials and Methods

Both constructs were fabricated on a 5 mm rotating mandrel using a dual-crosslinked alginate–gelatin bioink. Printability, viscoelastic behavior, and mechanical properties were evaluated over 21 days through rheological analysis, tensile ring tests, and stress relaxation tests. Cell viability in the cellularized constructs was assessed using L929 fibroblasts and iPSC-derived endothelial cells by means of Live/Dead assays.

Results

Stress–strain curves and stress relaxation profiles showed mechanical behavior highly consistent with that of native vessels. The vascular constructs also maintained excellent cell viability up to day 21, supporting the suitability of the bioink and fabrication strategy for the production of cellularized tubular grafts.

Conclusion

These findings demonstrate that a single rotating-mandrel bioprinting strategy can generate multipurpose small-diameter tubular constructs for different biomedical applications. The multilayer vascular graft shows potential for preclinical drug screening, device testing, and future vascular implantation, while the Wirsung duct phantom represents a realistic tool for pancreaticojejunostomy training and may contribute to improving surgical outcomes.

D2 – P118

Melt electrowriting Integration into hybrid manufactured scaffolds for multiscale architectural control

S.M.[1], L.B.[1], F.P.[1], F.D.G.[1,2], M.C.[1,3], E.D'I.[1,3], and P.O.[1]
[1]IRCCS Humanitas Research Hospital, Via Alessandro Manzoni, 56, 20089 Rozzano MI; [2]Dept. of Chemistry, Materials and Chemical Engineering "Giulio Natta", Politecnico di Milano, Milan; [3]Correlative Light and Electron Microscopy Core, Humanitas University, Via Rita Levi Montalcini, Pieve Emanuele, Italy

Introduction

Engineering scaffolds capable of reproducing the hierarchical organization of native tissues remains a major challenge in tissue engineering. Conventional fabrication approaches often reproduce only specific aspects of extracellular matrix complexity, limiting the simultaneous control of structural features across multiple length scales. The integration of complementary biofabrication technologies represents a promising strategy to develop advanced scaffold platforms with improved control over nano-, micro-, and macroscale architectures.

Aim

This study aimed to develop a multimodal hierarchical scaffold through the integration of melt electrowriting (MEW) into a previously established electrospinning/extrusion-based manufacturing approach. The objective was to introduce an additional level of microscale architectural control while evaluating the effect of MEW integration on scaffold mechanical response and investigating cell–scaffold interactions within the resulting multiscale construct.

Materials and Methods

Polycaprolactone (PCL) graded scaffolds were fabricated through the sequential combination of electrospinning (ES), MEW, and extrusion-based (EB) 3D printing. The resulting constructs consisted of a central electrospun region containing MEW-deposited sinusoidal microstructures, two lateral electrospun/extruded transition regions, and two terminal extrusion-printed regions. The planar scaffolds were subsequently converted into cylindrical constructs while preserving their spatial architectural organization. The effect of MEW integration on scaffold mechanical response was evaluated through uniaxial tensile testing and compared with a previously developed electrospinning/extrusion-based platform. Geometrically scaled constructs were used for biological evaluation with L929 fibroblasts. Cell distribution and cell-scaffold interactions were assessed using scanning electron microscopy (SEM), while changes in mechanical behavior following cell culture were evaluated after different culture periods.

Results

The hybrid manufacturing approach enabled the fabrication of continuous multiscale graded constructs integrating electrospun fibers, MEW sinusoidal microstructures, and extrusion-printed architectures within a single scaffold. SEM analysis confirmed the successful integration of the different architectural regions and highlighted the interaction between cells and the hierarchical fibrous environment. Mechanical characterization demonstrated the influence of MEW-derived microscale features on the response of the hybrid scaffold platform. Furthermore, cell-seeded constructs showed time-dependent changes in mechanical behavior during in vitro culture, suggesting an active interaction between cells and the multiscale scaffold architecture.

Conclusion

The proposed multimodal manufacturing strategy enables the development of hierarchical graded scaffolds by combining complementary fabrication technologies across different length scales. The integration of MEW provides an additional level of architectural control within hybrid scaffold platforms, representing a promising approach for the engineering of complex tissue interfaces requiring spatially organized structural and mechanical properties.

D2 – P119

Towards rational design of microalgae-laden bioinks for reproducible manufacturing of engineered living materials

Dawiec-Liśniewska A.[1], Nizioł M.[2], Szyszka M.[2], Podstawczyk D.[2], Bastrzyk A.[2], Kolinko A.[2], Jakubcewicz A.[2], Jurga A.[3], Miller U.[3], Brandić Lipińska M.[4]
[1]Dept. of Advanced Materials Technologies, Faculty of Chemistry, Wroclaw University of Science and Technology, Wroclaw, Poland; [2]BioSS lab, Dept. of Process Engineering and Technology of Polymer and Carbon Materials, Faculty of Chemistry, Wroclaw University of Science and Technology, Wroclaw, Poland; [3]Dept. of Environmental Biology and Air Protection, Faculty of Environmental Engineering, Wroclaw University of Science and Technology, Wroclaw, Poland; [4]Integrative Design | Extremes, Dept. of Experimental Architecture, Innsbruck University, Innsbruck, Austria

Introduction

3D printed engineered living materials (ELMs) incorporating photosynthetic microorganisms are emerging as promising platforms for environmental, biomedical, and space-related applications. However, the development of reproducible fabrication strategies remains challenging due to the complex interplay between bioink composition, printability, cell viability, and post-printing material performance.

Aim

The aim of this study is to investigate how bioink composition and rheological modifiers influence the fabrication process, physicochemical characteristics, and biological performance of microalgae-based engineered living materials, providing guidelines for their rational and reproducible design.

Materials and Methods

Alginate- and GelMA-based bioinks containing *Chlamydomonas reinhardtii* were formulated with selected rheological modifiers. A range of formulations was investigated to determine how material composition affects bioink preparation, printing performance, physicochemical characteristics, microalgal viability and cytotoxicity. Rheological properties were evaluated together with printability and structural stability of printed constructs. Biological performance was assessed through fluorescence-based viability assays, photosynthetic activity measurements, oxygen production, and spectrophotometric analysis.

Results

The investigated bioink formulations enabled the fabrication of microalgae-laden ELMs with good printing fidelity and structural stability. The incorporation of rheological modifiers affected bioink processability, shape retention, and the physicochemical characteristics of the printed constructs. Rheological modifiers, including Laponite and Pluronic, played a multifunctional role beyond improving extrusion behavior by affecting hydrogel organization, and cell–material interactions, ultimately contributing to the fabrication and performance of microalgae-based ELMs (Fig.1.). Fluorescence-based analyses confirmed the viability of immobilized *Chlamydomonas reinhardtii*, with noticeable differences observed between formulations. The obtained results highlight the importance of material composition in balancing printability, construct stability, and biological performance, providing insights into the development of microalgae-based ELMs.




Fig.1 Influence of bioink composition on the structural and biological performance of microalgae-laden 3D printed objects.

Conclusion

The study highlights the importance of bioink design for the successful fabrication of microalgae-based ELMs. The obtained findings provide guidance for developing reproducible constructs with tailored properties while maintaining the viability and functionality of immobilized microalgae. Improved understanding of the interactions between biomaterials, rheological modifiers, and living cells will support the future development of engineered living materials for environmental, biotechnological, and biofabrication applications.

Acknowledgements
This research was funded by the National Science Centre, Poland, under grant no. 2023/49/B/ST8/03834.

D2 – P120

Inclusion of rete ridges in a human skin model for a novel dermopathological functionality

Weroniczak-Ballod M., Fischer H.
Dental Materials and Biomaterials Research (ZWBF), RWTH Aachen University Hospital, Aachen, Germany

Introduction

Rete ridges play a crucial role in human skin, as well as in the development of certain mechanically mediated skin diseases. However, due to the challenging geometry of these microstructures, in vitro models containing them are currently unavailable.

Aim

In this study, we present a method for biofabricating an improved dermis tissue model containing rete ridges.

Materials and Methods

Gelatin moulds were fabricated using microextrusion bioprinting with high printing resolution. Collagen hydrogels containing fibroblasts were then cast in these moulds, which were subsequently dissolved, leaving the crosslinked collagen structure intact. This procedure aimed to eliminate the drawbacks of the already established methods that were tried before that: the time-consuming process of applying changes to dermal geometry, using typical solid-state moulds, the limited robustness of stamping cast hydrogel in well plates, and the adverse trade-off between printing resolution and cell viability in direct microextrusion of the cell-laden collagen.

Results

The goal of eliminating the above-mentioned shortcomings of simple casting and direct bioprinting was achieved by comparing the time and quality of the results for these three methods. The biofabricated rete ridges are as small as 500 µm in depth. Optimising the procedure to produce ridges of 200 µm reliably is underway. Overall, the spatial resolution was deemed satisfactory; however, the shape fidelity between single ridges is yet to be improved.

Conclusion

The proposed biofabrication process for creating an in vitro dermis model containing rete ridges has the potential to produce skin models that are more physiologically relevant than existing models, with the assumption that the spatial resolution of the cast collagen will be further improved. This yields a positive outlook towards developing a functional model of a disease such as pemphigus.

Acknowledgements

This work is part of the project funded by DFG, Deutsche Forschungsgemeinschaft (German Research Foundation) -- 363055819/GRK2415

D2 – P121

Development of an alginate–keratin bioink for 3D bioprinting of living wound-healing constructs

Gąbka M.[1]*, Wrześniewska-Tosik K.[2], Stodolak-Zych E.[1]*
[1]Faculty of Material Science and Ceramics, AGH University of Krakow; [2]Łukasiewicz Research Network – Lodz Institute of Technology, Lodz, Poland

Introduction

Three-dimensional (3D) bioprinting has emerged as a powerful technology for the fabrication of complex biological constructs for tissue engineering, regenerative medicine, and wound healing applications. Among the available approaches, extrusion-based bioprinting is particularly attractive due to its versatility and ability to process cell-laden bioinks. Successful bioprinting requires bioinks with suitable rheological properties that ensure both printability and structural stability after deposition.

Aim

The aim of this study was to develop and characterize an alginate–keratin bioink containing bacterial cells and chemical crosslinkers, intended as a platform for the immobilization of microorganisms capable of producing bioactive compounds for wound healing applications.

Materials and Methods

An alginate-based bioink supplemented with keratin (4.5%/0.5%, w/v) and chemically crosslinked using EDC/NHS (3.15%/0.45%, w/v) was prepared. A suspension of Escherichia coli cells was incorporated into the bioink formulation. The resulting mixture was homogenized using a three-roll mill and subsequently characterized in terms of its rheological properties. Bioprinting was performed using a Biocloner Desktop Pro bioprinter equipped with a 22G nozzle. The printed constructs were subjected to microbiological analyses to assess bacterial viability. For in vitro evaluation, the printed samples were incubated in nutrient broth, followed by Live/Dead staining performed in 24-well culture plates.

Results

The incorporation of keratin significantly increased the viscosity of the alginate-based formulations compared with alginate alone, improving their suitability for extrusion bioprinting. The developed bioink enabled the fabrication of well-defined grid structures with a printability index close to 1, indicating excellent shape fidelity and accurate reproduction of the designed geometry. Live/Dead staining confirmed high bacterial viability after printing, demonstrating that the extrusion process did not adversely affect bacterial survival. Moreover, bacterial proliferation was observed during subsequent incubation, confirming that the hydrogel environment supported microbial growth and activity.

Conclusion

The incorporation of keratin significantly increased the viscosity of the alginate-based formulations compared with alginate alone, improving their suitability for extrusion bioprinting. The developed bioink enabled the fabrication of well-defined grid structures with a printability index close to 1, indicating excellent shape fidelity and accurate reproduction of the designed geometry. Live/Dead staining confirmed high bacterial viability after printing, demonstrating that the extrusion process did not adversely affect bacterial survival. Moreover, bacterial proliferation was observed during subsequent incubation, confirming that the hydrogel environment supported microbial growth and activity.

D2 – P122

Seed-assisted hydrothermal growth of ZnO nanoarrays on 3D-printed scaffolds for enhanced bone tissue engineering applications

Kim D., Lee J., Jung J-Y., Lee J., Park S.A.*
Nano-Convergence Manufacturing Research Division, Korea Institute of Machinery and Materials (KIMM), Daejeon, South Korea

Introduction

Large bone defects remain a major challenge in regenerative medicine. 3D printing enables patient-specific scaffolds, but common polymers such as polycaprolactone (PCL) are bioinert, limiting osteoblast adhesion, proliferation, and differentiation. Bioactive zinc oxide (ZnO) nanostructures can promote osteogenesis, yet blending them into polymers traps the particles and lowers cell performance, while conventional surface-deposition routes require harsh conditions unsuitable for low-melting polymers. We developed a seed-assisted, low-temperature hydrothermal method to grow ZnO nanoarrays directly on the surface of 3D-printed PCL scaffolds.

Aim

To surface-functionalize 3D-printed PCL scaffolds with hydrothermally grown ZnO nanoarrays at low temperature and to evaluate their physicochemical properties and osteogenic performance.

Materials and Methods

PCL scaffolds (20×20×2 mm) were 3D-printed by fused deposition modeling. ZnO nanoparticles (NPs) were thermally anchored as seeds at 55 °C, after which ZnO nanoarrays (NAs) were grown in a zinc nitrate hexahydrate/HMTA solution for 3 or 18 h at 55 °C. Surfaces were characterized by SEM, AFM, XRD, Raman, and XPS, and Zn ion release was quantified by ICP-MS over 10 days. Osteoblast-like MG63 cells were used to assess viability (live/dead), proliferation (WST-1), and differentiation (ALP activity and Alizarin Red S staining).

Results

SEM and AFM confirmed rodlike ZnO NAs whose density, length, and surface roughness increased with growth time (R_a ~0.16 μm at 18 h). XRD and Raman verified a hexagonal wurtzite ZnO structure, and XPS revealed chemical bonding between PCL carboxylate groups and Zn(OH)2 in addition to physical anchoring of the seeds. Zn ions were released within a non-cytotoxic range (1-10 μM), with the 18 h group showing the most stable, lowest release. MG63 proliferation and ALP activity were significantly higher on ZnO-coated scaffolds, greatest for NAs grown 18 h, accompanied by enhanced calcium mineralization in ARS staining.

Conclusion

The seed-assisted hydrothermal route functionalizes thermally degradable PCL scaffolds with ZnO nanoarrays under mild conditions, enhancing osteoblast proliferation and early differentiation. This strategy offers a versatile platform for depositing bioactive metals onto polymer scaffolds for bone tissue engineering.

Acknowledgements

This research was supported by the National Research Council of Science & Technology (No. CRC22021-200).

D2 – P123

Fast transport of soluble antimicrobials by porous meshes enables bacterial eradication in distal locations

Mohammadi S.[1,2], Pereira A.L.[1], Maranesi A.[1], Spasiano C.[1], Ferrari A.[1]
[1]Hylomorph AG, Zurich, Switzerland; [2]Dept. Pediatrics, Sophia Children's Hospital, Erasmus MC, Rotterdam, The Netherlands

Introduction

Implantable polymeric meshes provide structural support, reinforce soft tissue, and promote regeneration in patients with abdominal wall damage, pelvic prolapse, or undergoing breast reconstruction after mastectomy. In addition, meshes are used in combination with soluble drugs to ensure therapeutic protection and mechanical reinforcement.


Cardiac implantable electronic devices (CIEDs) are susceptible to potential complications, including post-implantation infections (1.7-5.6%) and device migration. Absorbable protective envelopes made from polymeric meshes and including a drug-eluting component, sustain the local elution of antimicrobial agents and significantly reduce the risk of CIED infection and biofilm formation. In this context, uniform antimicrobial distribution and homogenous elution in the CIED surgical pocket are vital for infection prevention.

Materials and Methods

Herein, we highlight the importance of understanding the interaction mechanisms between soluble molecules and polymeric meshes. In silico experiments were performed in COMSOL Multiphysics 6.3 by which we developed a two-phase transport model. Next, a custom-made 3D printed set-up was used to experimentally measure the solution transport in polymeric mesh. The obtained results were validated by assessing the antimicrobial activity in vitro and in vivo, using bioluminescence *E. coli* and New Zealand white rabbit models, respectively.

Results

We proposed a Multiphysics model that captures the interplay between material microstructure, local tissue environment, and drug transport phenomena. In vitro transport experiments validated the simulation results, demonstrated by fluorescence videos in conditions of diffusion, capillary pull and cohesion-tension. Furthermore, the antimicrobial activity of the transported soluble molecule against bioluminescent *E. Coli* and infected rabbit was in line with the developed model.



Conclusion

Through combined simulations and experiments, we show that transport dynamics are strongly modulated by boundary conditions: capillary wicking reinforced by evaporation driven cohesion-tension dominates in dry meshes under low humidity, whereas transport is reduced under high humidity and becomes diffusion limited in fully saturated meshes. While diffusion is present in all cases, it plays a secondary role compared to capillary and evaporation driven mechanisms in determining the extent and rate of transport.

D2 – P124

Digital light processing of PCL/calcium phosphate scaffolds for bone regeneration

Arslan A.[1], Van Hoorick J.[1], Lasgorceix M.[2], Jean F.[2], Hocquet S.[3]
[1]BIO INX BV, Ghent, Belgium; [2]Université Polytechnique Hauts-de-France, Valenciennes, France; [3]Belgian Ceramic Research Center (BCRC), Mons, Belgium

Introduction

Bone tissue engineering requires scaffolds that combine mechanical support with bioactivity to promote osteogenesis. Polycaprolactone (PCL)-based resins are widely used in digital light processing (DLP) 3D printing due to their tunable properties and processability. Incorporating hydroxyapatite (HA) into PCL matrices can enhance scaffold bioactivity and mimic the mineral phase of bone and supporting cell adhesion and differentiation.

Materials and Methods

Calcium phosphate powders, namely hydroxyapatite (HA) and β-tricalcium phosphate (β-TCP), were synthesized via aqueous precipitation using calcium nitrate tetrahydrate ($Ca(NO_3)_2 \cdot 4H_2O$) and diammonium hydrogen phosphate ($(NH_4)_2HPO_4$) as precursors. Phase composition was verified by X-ray diffraction and particle size distribution was measured by laser diffraction. The synthesized powders were incorporated into a commercially available PCL-based DLP photo-resin (DEGRES INX X100, BIO INX) through a two-step process. First, powders were pre-treated with 0.5% dispersant in ethanol, mixed overnight with 2 mm zirconia beads in a Turbula mixer, and recovered via rotary evaporation. Next, the treated powders (10%) were loaded into the photo-resin using a progressive mixing protocol in a Speed Mixer. The resulting composite bioink was characterized via rheology. Composite scaffolds were 3D printed using DLP (ADMAFLEX 130) and analyzed by mechanical testing, scanning electron microscopy (SEM, JEOL), and 3D optical microscopy (Keyence VR 3200).

Results

The Ca/P molar ratios of HA and β-TCP were 1.667 and 1.50, respectively, with median particle sizes of 1–2 µm. XRD analysis confirmed high-purity powders, with secondary phases below 5%. Composite scaffolds were successfully printed via DLP with a 4s/layer curing time (Figure 1a). SEM images of the composite scaffolds revealed a dense and continuous polymer matrix with homogeneously dispersed HA and β-TCP particles, demonstrating good interfacial adhesion (Figure 1b). The Young's modulus of the composite scaffolds was significantly higher than that of the structures without calcium phosphate powders (9.5 MPa vs. 0.4 MPa). A roughness (Ra) of 40 µm was measured via 3D optical microscopy (Figure 1c), partly due to the stacking of layers during 3D printing—layers with dimensions on the order of 50 to 60 µm.

Conclusion

The incorporation of hydroxyapatite (HA) and β-tricalcium phosphate (β-TCP) into PCL-based DLP resins successfully yielded composite scaffolds with enhanced mechanical strength and improved surface characteristics. Future studies will focus on assessing the biological performance of these scaffolds in bone tissue engineering applications.

Acknowledgements

This project is supported by the Interreg microprojects program (RAPIDOS, project no: 0400393)




Figure 1 (a) Gyroid scaffold printed via DLP using composite photo-resin, (b) SEM image of the printed structure and (c) 3D optical microscopy of the printed structure showcasing the surface roughness

D2 – P125

AI-assisted MRI segmentation and 3D reconstruction for patient-specific proximal tibial growth plate scaffold design

Tsumura W.G.[1,2], Ribeiro A.C.[1], Stocco T.D.[2]
[1]Dept. of Internal Medicine, Faculty of Medical Sciences, State University of Campinas, Campinas; [2]BioRegenera.Lab, Bioengineering Program, Scientific and Technological Institute, Brasil University, São Paulo, Brazil

Introduction

Growth plate injuries in skeletally immature patients remain a major clinical challenge due to the risk of bone bridge formation, growth disturbance, and angular deformities[1]. The development of patient-specific regenerative scaffolds for growth plate repair requires accurate reconstruction of the native anatomy from medical images [2]. However, segmentation of the proximal tibial growth plate from magnetic resonance imaging (MRI) is challenging because of its thin geometry, low contrast boundaries, and anatomical variability.

Aim

To develop and preliminarily evaluate an AI-assisted workflow for MRI-based segmentation and 3D reconstruction of the proximal tibial growth plate, enabling the fabrication of a patient-specific scaffold prototype for future growth plate regeneration strategies.

Materials and Methods

Anonymized MRI datasets of immature knees were collected from public databases. A custom segmentation workflow was developed using MONAI Label integrated with 3D Slicer to specifically identify and reconstruct the proximal tibial growth plate. A pilot training set was iteratively annotated to train the model in a human-in-the-loop approach, followed by preliminary testing on 5 independent examinations. Segmentation performance was assessed using the Dice similarity coefficient. After segmentation, a representative 3D model of the complete proximal tibial growth plate was reconstructed and exported as an STL file. The model was then sliced and fabricated in polylactic acid (PLA) using a fused deposition modeling 3D printer. The printed scaffold prototype was subsequently 3D scanned and compared with the original digital model to assess overall morphological correspondence.

Results

The proposed workflow enabled successful AI-assisted segmentation of the proximal tibial growth plate from MRI data and generation of printable patient-specific 3D models. Preliminary testing indicated satisfactory segmentation performance according to the Dice similarity coefficient. In addition, the segmented model was successfully converted into an STL file, processed for printing, and manufactured as a physical scaffold prototype. Qualitative comparison between the printed construct and the original digital model indicated preservation of the main anatomical morphology of the growth plate.

Conclusion

This pilot study demonstrates the feasibility of an AI-assisted MRI-to-print workflow for generating patient-specific proximal tibial growth plate scaffold prototypes. Although regenerative biofabrication has not yet been implemented at this stage, this approach provides a relevant enabling step toward the future development of patient-specific scaffolds for growth plate regeneration.

Acknowledgements

FAPESP (2024/00414–4)
CNPq (444141/2023–5)

References

[1]Sananta P., Lesmana A., Alwy Sugiarto M. Growth plate injury in children: Review of literature on PubMed. *J Public Health Res* 2022; 11; 227990362211041.
[2]da Silva F.T., Tsumura W.G., Sousa e Silva M. de C., et al. Establishing a framework for the design and fabrication of patient-specific scaffolds targeting partial meniscal defects. *Int J Bioprint* 2025; 1; 556–572.

D2 – P126

Mechanical optimization of infill architecture in a patient-specific anterior cruciate ligament scaffold

Silva S.G.C.P., da Silva A.M.H., Stocco T.D.
BioRegenera.Lab, Bioengineering Program, Scientific and Technological Institute, Brasil University, São Paulo, Brazil


Introduction

Anterior cruciate ligament (ACL) injuries remain a major clinical challenge due to the limited intrinsic healing capacity of the ligament and the shortcomings of current reconstruction approaches. In ligament tissue engineering, the development of patient-specific scaffolds that combine anatomical fidelity with suitable mechanical performance is essential[1]. Although 3D printing enables the fabrication of customized structures, the influence of internal scaffold architecture on the mechanical behavior of anatomically reconstructed ACL scaffolds remains insufficiently explored.

Aim

To develop and evaluate a patient-specific and mechanically optimized ACL scaffold prototype by integrating MRI-based 3D reconstruction, computational structural analysis, and 3D printing (Figure 1).

Figure 1. Graphical abstract



Materials and Methods

An anonymized public-domain knee MRI dataset was used to reconstruct a patient-specific ACL model. Anatomical segmentation and 3D reconstruction were performed in InVesalius, followed by STL generation. Polycaprolactone (PCL) filament was mechanically characterized by uniaxial tensile testing and used as the base material for scaffold fabrication. Different scaffold architectures were generated by varying infill patterns within the patient-specific ACL geometry. The corresponding G-code files were reconverted into STL models using a custom Python script developed by our group, which fused the deposited layers to simulate the post-print scaffold geometry. These reconstructed models were then subjected to finite element analysis under tensile loading to compare structural behavior and identify the mechanically optimized configuration. The best-performing design was printed in PCL by fused deposition modeling as a proof of concept.

Results

The proposed workflow enabled successful patient-specific ACL reconstruction from MRI data and generation of scaffold models with distinct internal architectures. Comparative structural analysis demonstrated that infill pattern strongly influenced scaffold performance. Although the hexagonal design showed the highest resistance under tensile loading, the rectilinear pattern provided the best overall mechanical efficiency, offering a more favorable balance between structural performance and material usage. The selected scaffold design was successfully fabricated in PCL by FDM 3D printing, preserving the overall anatomical geometry and the intended internal configuration.

Conclusion

This study demonstrates the feasibility of an integrated workflow for developing patient-specific ACL scaffold prototypes combining medical image-based reconstruction, custom G-code-to-STL geometric rebuilding, computational optimization, and 3D printing. The findings support the relevance of infill design as a key parameter in ligament scaffold development and contribute to the advancement of patient-specific strategies for future ACL tissue engineering applications.

Acknowledgements
FAPESP (2024/00414–4)
CNPq (444141/2023–5)

References
[1]Romano F., Lopresti F., Gesù R.D., et al. Tissue engineering for tendon and ligament repair: Insights and advances. *View* 2025; 6; 20250063.

D2 – P127

From droplets to microtissues: The droplet microarray for high-throughput 3D cell assembly

Schliephake M.[1], Quaschning C.[2], Popova A.[1], Schepers U.[2], Levkin P.[1,3]
[1]Institute of Biological and Chemical Systems – Functional Molecular Systems (IBCS-FMS), Karlsruhe Institute of Technology (KIT); [2]Institute of Functional Interfaces (IFG), Karlsruhe Institute of Technology (KIT); [3]Institute of Organic Chemistry (IOC), Karlsruhe Institute of Technology (KIT), Karlsruhe, Germany

Introduction

Assembloids are engineered 3D constructs formed by fusing spheroids or organoids and represent a rapidly growing frontier in tissue modeling. By assembling distinct spheroids, assembloids enable the recreation of multi-tissue interfaces, cellular heterogeneity, and spatial organization that are difficult to achieve within single spheroids or conventional organoids. This approach offers opportunities for advanced tissue modeling, drug screening, and regenerative medicine applications.

Aim

The aim of this study is to develop a scalable strategy for the controlled fabrication of modular multicellular assembloids using droplet microarray technology. This high-throughput platform enables the parallel generation of hundreds of 3D assembloids per array with defined cellular composition and spatial organization.

Materials and Methods

The droplet microarray is a miniaturized, high-throughput technology that enables the parallel formation and handling of hundreds of isolated nanoliter-scale droplets, each confined to a hydrophilic spot surrounded by superhydrophobic barriers. Spheroid formation via the scaffold-free hanging drop method allows control over spheroid size through defined seeding densities. By sandwiching two or more microarray slides, pre-formed spheroids can be brought into contact, enabling controlled fusion and the parallel fabrication of diverse assembloid architectures (Figure 1). Automated image analysis based on a trained model was integrated to evaluate spheroid diameter and circularity.

Results

As shown in Figure 2, evaluation of spheroid diameter and circularity indicates scalable and reproducible spheroid generation of HEK293 cells. Live/dead staining confirmed high viability after 24 h and 72 h of culture for spheroids generated from 100 cells and 500 cells. Heterotypic and multi-spheroid assembloids demonstrate the spatial co-assembly of distinct cell populations. In addition, core-shell assembloids demonstrate controlled radial organization with a central core surrounded by outer cell layers.

Conclusion

This study establishes a scalable and versatile strategy for the rapid generation of modular multicellular assembloids on droplet microarray. The platform enables reproducible spheroid formation with high viability and allows controlled assembly of heterotypic spheroids into defined architectures such as
core-shell structures. By enabling the parallel fabrication of hundreds of assembloids with tunable cellular composition and spatial organization, this approach provides a powerful tool for bottom-up tissue engineering. The presented method offers promising potential for applications in complex tissue modeling, drug screening, and the study of multicellular interactions.

Acknowledgements

The authors acknowledge funding from the Deutsche Forschungsgemeinschaft (DFG, German Research Foundation) through the Excellence Cluster “3D Matter Made to Order” (EXC 2082/1–390761711) and the Carl Zeiss Foundation through the “Carl-Zeiss-Foundation-Focus@HEiKA”.




Figure 7 Overview of the droplet microarray-based approach for scalable assembloid fabrication. (1) Modular assembly of pre-formed spheroids via sandwiching. (2) Assembled spheroids demonstrating diverse architectures. (3) Bottom-up tissue assembly from modular assembloids as building blocks.




Figure 2 Spheroid characterization. (1) Growth kinetics and circularity of HEK293 cell spheroids with 100-500 cell seeding density after 24 h, 48 h and 72 h. (2) Viability assay of 100 cells and 500 cells per spheroid after 24 h and 72 h.

D2 – P128

Iodixanol enhances type II photoinitiation enabling Xolographic printing of cell-dense living matter

Anspach A.[1], Wolfel A.[1], Cano-Jorge M.[1], Custódio C.[2], König N.[3], Rolfes S.[1], Mano J.[4], Passier R.[1], Leijten J.[1]
[1]Dept. Bioengineering Technologies, University of Twente, Enschede, The Netherlands; [2]Metatissue, Aveiro, Portugal; [3]xolo, Berlin, Germany; [4]CICECO, Dept. Chemistry, University of Aveiro, Aveiro, Portugal

Introduction

The engineering of functional living tissues with multiscale and hierarchical features has remained a largely unsolved key challenge. Conventional bioprinting approaches have shown promise in their ability to realize such features, but are unable to achieve this at a clinically relevant time scale.[1] Rapid volumetric bioprinting has recently been invented to overcome this technical hurdle. Xolography is a recently developed volumetric printing technique that indeed can print plastic resins at both high speed and resolution.[2] However, xolographic printing currently demands the use of high concentrations of the cytotoxic co-initiator such as triethanol amine (TEA) to achieve fast high-resolution printing. This essential reliance on cytotoxic compounds forces current xolographic bioprinting approaches to choose between fast print speeds or cytocompatibility. Here, we report that iodixanol improves xolographic print reactivity allowing for the near-elimination of cytotoxic co-initiators thereby allowing for rapid yet cytocompatible xolographic bioprinting. As an additional benefit, iodixanol reduces cell-mediated light scattering by matching the refractive index of the print bath and the cells contained within cells, which effectively improves bioprint resolution. Together, we demonstrate that the use of iodixanol allows for rapid, cytocompatible, and high-resolution xolographic bioprinting of living matter.

Materials and Methods

To identify the optimal IDX concentration for high-resolution printing, we prepared GelMA-based bioinks, and incorporated 3T3 fibroblasts at a concentration of 10 M/mL. Visible light transmission was measured for various IDX concentrations to determine the lowest scattering inks. The cell-gel RI-matching was then verified by holotomography. To determine resolution, these cell-containing inks were then printed. Dual-color photorheology was used to determine Xolographic print reactivities. Cell viability was analyzed using various fluorescent and biochemical assays. Print resolutions were investigated using holotomography, confocal microscopy, and Schlieren photography as well as by printing various complex shaped prints within minutes.

Results

Optimal bioink transmission was achieved at 24% iodixanol. Holotomography verified that increased light transmission resulted from the matching of print bath RI to cytoplasm RI. Dual-color photorheology revealed that print reactivity increased with iodixanol in a dose-dependent manner. Notably, the reactivity even increased at lower amounts of TEA, which allowed low-TEA inks to surpass the reactivity of high-TEA inks while increasing print speeds by four-fold. This also improved cell viability increased from negligible to >85% cell survival in all printed constructs. In addition, cell viability in printed constructs with was vastly improved when using high-transmission IDX concentrations. Together, this enabled accurate xolographic printing of highly cell-dense bioresins, which facilitated the biofabrication of engineered living matter with at least 50 M cells mL^{-1}. Human induced pluripotent stem cell-derived cardiomyocytes were printed into contractile cardiac-like engineered living matter, which exhibited enhanced cell-cell contact and synchronous contractions, showing tissue level function.

Conclusion

Iodixanol addition was identified as a highly effective strategy to address a key challenge of realizing the promise of bioxolography. Specifically, the use of iodixanol allows rapid xolographic printing of voluminous living matter at high viability, high cell density, and high resolution in seamless, shear stress-free, and cytocompatible manner. These advances enabled the first demonstration of tissue function in xolographically-printed living materials.

Acknowledgements

J.L. acknowledges financial support from the European Innovation Council (210803707: BioRobot-MiniHeart).

References

[1]Zandrini T., et al, *Trends in biotechnology* 2023; 41; 604.
[2]Regehly M. et al, *Nature* 2020; 588; 620.

D2 – P129

Design and optimization of a coaxial set-up for 3D bioprinting cardiac fiber-like *in vitro* models

Lazzaro A.[1], Pitton M.[1], Conti M.[1,2]
[1]C3D Laboratory, Bioprinting Unit, IRCCS Policlinico San Donato, San Donato, Milano, Italy; [2]CompMech DICar, University of Pavia, Pavia, Italy

Introduction

Cardiac diseases nowadays represent the first cause of death in the Western World. Although myocardium is usually considered a permanent cellular population, the possibility to stimulate the proliferation and differentiation of cardiac stem cells has recently gained huge interest. However, recapitulating the hierarchical myocardial organization is challenging due to its complexity.

Aim

Herein, we designed 3D fiber-like *in vitro* models for cardiac tissue engineering. For this purpose, we optimized and developed a coaxial set-up for our 3D bioprinter to allow the deposition and the orientation of core-shell structures by bioprinting cardiomyocytes in the internal bioink, sustained by the external supportive shell.

Materials and Methods

The coaxial set-up was properly designed, by carefully adapting its dimensions to our 3D bioprinter INKredible+ (CELLINK, Sweden), and 3D printed in resin with Elegoo Mars 2Pro. Alginate (*shell*) was dissolved in DPBS (4% w/V) and internally pre-crosslinked with $CaCO_3$ (20 mM) and GDL (40 mM) overnight at 4°C (*Hazur et al., 2020*). Methacrylate gelatin (GelMA, *core*) was synthesized (*Pitton&Urzì et al., 2024*) and enriched with riboflavin (RF, 0.4 mM) and sodium persulfate (SPS, 10 mM) as photo-initiator. Prior to the 3D bioprinting, AC16 cardiomyocytes were embedded in GelMA solution ($3x10^6$ cells mL^{-1}). 3D fiber-like *in vitro* models were bioprinted and dually crosslinked with $CaCl_2$ and visible light (5 min). The morphology and distribution of the cells were observed with calcein/phalloidin/DAPI staining, after fixation in 4% PFA (10X magnification).

Results

The coaxial set-up was realized with an internal diameter equal to 1 mm and an external diameter equal to 2 mm (Figure 1). Alginate was internally crosslinked to guarantee a shear-thinning behaviour and proper printability to the shell biomaterial, whereas GelMA (DOF = 60%) was selected as core bioink to allow cells to adhere and proliferate in a favourable matrix. 3D fiber-like *in vitro* models were realized by bioprinting snake-like structures (3 cm x 3 cm, v = 2.5 mm s^{-1}) which were then cultured in DMEM F/12 up to 10 days. Calcein/phalloidin/DAPI staining qualitatively showed that AC16 cardiomyocytes adhered and proliferated along the internal fiber-like structure (Figure 2), forming an intricate network which maintained the fiber-like conformation during cell culture.

Conclusion

The optimized coaxial set-up paved the way for successfully designing and realizing fiber-like and well-oriented *in vitro* models to recapitulate the musculature of native heart. Future perspectives will be focused on increasing the complexity of the model by co-culturing endothelial cells, fibroblasts and cardiomyocytes.




Figure 1. Design, optimization and use of coaxial set-up for 3D bioprinting core-shell structures.




Figure 2. Calcein (green) / phalloidin (red) / DAPI (blue) staining on 3D fiber-like *in vitro* models. AC16 cardiomyocytes were bioprinted in GelMA bioinks (core) and cultured up to 10 days (10X magnification).

References

[1]Hazur J., et al. Improving alginate printability for biofabrication: establishment of a universal and homogeneous pre-crosslinking technique. *Biofabrication* 2020; 12; 1758-5090.
[2]Pitton M., Urzì C., et al. Visible light photo-crosslinking of biomimetic gelatin-hyaluronic acid hydrogels for adipose tissue engineering. *Journal of the mechanical behavior of biomedical materials* 2024; 158; 1751-6161.

D2 – P130

Post-printing tunability of printed nitroxide hydrogels for tissue engineering applications

Gusev J.[1], Parmentier L.[1], Tran H. B. D.[2], Blasco E.[2], Thijssen Q.[1], Van Vlierberghe S.[1]
[1]Polymer Chemistry and Biomaterials Group (PBM), Centre of Macromolecular Chemistry (CMaC), Ghent University, Ghent, Belgium; [2]Institute for Molecular Systems Engineering and Advanced Materials (IMSEAM), Heidelberg University, Heidelberg, Germany

Introduction

Tissue engineered implants offer a promising alternative to conventional grafts, particularly when combined with volumetric 3D-printing, a technique characterized by its short fabrication times and absence of shear forces. In volumetric printing, a 3D light-dose distribution is delivered throughout the resin, enabling selective crosslinking of in-part voxels while out-of-part regions remain liquid. However, achieving suitable mechanical properties in printed hydrogels while providing a cell compatible environment remains a major challenge. Post-printing strategies provide a route to tailor material properties without compromising printability. Nitroxide-mediated polymerization (NMP), through the incorporation of nitroxide moieties, offers a controlled approach to tune the structure of the printed construct post-fabrication, thereby enabling adjustment of mechanical properties and crosslinking density.

Aim

This study aims to develop post-modifiable gelatin-methacryloyl (GelMA)-based hydrogels using NMP to enable tunable mechanical properties for tissue engineering applications.

Materials and Methods

Hydrogels were developed using 20 w/V% GelMA (DS 95%) and TMA (0.044 w/V%), with Li-TPO-L (0.44 w/V%) as photoinitiator. 3D structures were fabricated through volumetric 3D-printing. Following fabrication, NMP was initiated through the incorporated alkoxyamine functionalities to introduce polystyrene chains onto the printed constructs using bulk polymerization at 125 °C for 1 to 4 hours. Rheological characterization was performed to assess mechanical property changes after post-modification over time.

Results

Upon moisture removal, no decrease in G′ was observed at elevated temperatures in dimethylformamide, while an increase in G″ was observed, indicating enhanced viscous dissipation. Rheological analysis demonstrated an increase in the storage modulus (G') following polymer grafting, with an increase of G' from 2 kPa in unmodified samples to 11.5 kPa after polystyrene incorporation. From cel viability assays, it can be concluded that no measurable cytotoxicity was observed within the material processed post-printing. Additional material characterization is currently ongoing and will be presented at the conference.

Conclusion

This study presents a versatile platform for the fabrication of GelMA-based hydrogels with post-modifiable properties using polymerization techniques such as NMP. The ability to tailor mechanical properties after printing while providing a cell-compatible environment provides a promising strategy for developing functional, patient specific implants.

Acknowledgements

Q.T. acknowledge the Research Foundation – Flanders for a junior postdoctoral fellowship with grant number 1201125N. J.G. and S.V.V. acknowledge support from the BSMARTT! project funded by the Interreg Flanders-Netherlands programme and co-funded by VLAIO.

D2 – P131

Lumen X-enabled DLP bioprinting of GelMA hydrogels with tunable mechanics and high cell viability

Pernevik E., Godoy P., Silva C., Erikçi N., Kuzmenko V.
CELLINK Bioprinting AB, Gothenburg, Sweden

Introduction

Digital light processing (DLP) bioprinting of gelatin methacrylate (GelMA) hydrogels offers precise spatial control for engineering biomimetic constructs, yet optimizing cytocompatibility alongside mechanical performance remains a key biomaterials challenge. This study integrates biological and mechanical evaluations of GelMA 95% degree of substitution (DS) photoinks processed using a DLP platform to define a practical and tunable materials-processing window.

Materials and Methods

GelMA photoinks (7.5–12.5% w/v) were prepared and printed using a DLP bioprinter under varying layer thicknesses (20–100 µm) and exposure conditions. Human mesenchymal stromal cells (MSCs) were encapsulated in selected formulations (7.5–10% w/v) to evaluate cytocompatibility. Cell viability and morphology were assessed at days 1 and 7 using live/dead staining and fluorescence imaging. Mechanical performance was characterized via compressive modulus measurements of acellular constructs across the full parameter space.

Results

High cytocompatibility was observed across all tested cell-laden conditions, with MSC viability exceeding 75% at day 1 and 85% at day 7, indicating minimal photopolymerization-induced damage. Cells exhibited progressive spreading, consistent with favorable cell–matrix interactions and matrix remodeling within the GelMA network. Variations in printing layer thickness (50–100 µm) and polymer concentration (7.5–10% w/v) did not significantly impact viability, supporting a robust biological processing window.

Mechanical characterization revealed that compressive stiffness is primarily governed by polymer concentration, increasing from approximately 3–8 kPa at 7.5% to 42–88 kPa at 12.5% GelMA. Print resolution provided a secondary tuning parameter, with thinner layers yielding stiffer constructs, attributed to increased cumulative light exposure. However, the finest resolution (20 µm) was associated with reduced cell viability under the applied exposure conditions, indicating a trade-off between mechanical enhancement, resolution, and biological performance.

Conclusion

This study demonstrates that GelMA-based photoinks processed via DLP bioprinting enable independent tuning of cytocompatibility and mechanical properties within a defined parameter space. High cell viability and active cell spreading can be maintained while spanning a broad stiffness range relevant to soft tissue models. These findings establish a practical biomaterials design framework for balancing structure, mechanics, and biological function in engineered hydrogel systems, supporting applications in tissue engineering and advanced in vitro models.

D2 – P132

Development of a tunable 3D bioprinted alginate-gelatin platform for breast tumor microenvironment modeling

Lo Bello G.[1], Elahi A.[1], Rosalia M.[2], Visai L.[1], Bloise N.[1]
[1]Molecular Medicine Dept. (DMM), Centre for Health Technologies (CHT), Unità di Ricerca (UdR) INSTM, Operative Unit (OU) of the Interuniversity Center for the Promotion of the 3Rs Principles in Teaching and Research (Centro 3R), University of Pavia; [2]Dept. of Drug Sciences, University of Pavia; [3]UOR6 Nanotechnology Laboratory, Dept. of Prevention and Rehabilitation in Occupational Medicine and Specialty Medicine, Istituti Clinici Scientifici Maugeri IRCCS, Pavia, Italy

Introduction

Breast cancer research heavily traditionally relies on l two-dimensional (2D) cell cultures, which fail to accurately reproduce the complex three-dimensional (3D) architecture, mechanical stiffness, and extracellular matrix (ECM) interactions of native tumors. To overcome these limitations, 3D bioprinting has emerged as a highly promising approach. This study aims to develop and comprehensively characterize a tunable alginate-gelatin (Alg-Gel) bioink to engineer a biomimetic 3D breast tumor microenvironment.

Materials and Methods

Four Alg-Gel formulations with varying polymer concentrations were prepared and ionically crosslinked using calcium chloride. The hydrogels underwent thorough morphological (SEM), chemical (FTIR), swelling, and rheological (amplitude and frequency sweeps) characterizations. The optimal formulation was then selected for extrusion-based 3D bioprinting. Triple-negative breast cancer cell lines (MDA-MB-231 and HCC-1937) were encapsulated within the matrix. Cellular responses, including viability (Trypan Blue, Live/Dead staining via confocal microscopy) and metabolic activity (CCK-8 assay), were evaluated over long period. Furthermore, Real-Time qPCR was performed to assess the dynamic expression of proliferation (Ki67) and matrix remodeling/invasion (MMP2) genes.

Results

SEM and FTIR analyses confirmed a homogeneous, structurally stable polymeric network with complete preservation of the native chemical functional groups. Rheological testing revealed a predominantly elastic, shear-thinning behavior, achieving stiffness values (~10 kPa) that closely mirror those of native breast tumor tissue. Based on superior mechanical stability and printability, one formulation was selected as the optimal bioink. The bioprinted constructs maintained structural fidelity and exhibited a sustained gelatin release profile, retaining 70-80% of cell-adhesive motifs after three weeks. Encapsulated breast cancer cells demonstrated high viability, uniform 3D spatial distribution, and a progressive increase in metabolic activity throughout the culture period. Molecular analysis revealed a significant time-dependent upregulation of Ki67, confirming sustained tumor proliferation. Moreover, a marked peak in MMP2 expression at day 7 indicated an active phase of matrix remodeling by the invasive cancer cells, followed by a subsequent stabilization phase at later time points of cell culture.

Conclusion

The engineered alginate-gelatin hydrogel represents a robust, physiologically relevant 3D platform for breast cancer modeling. By effectively recapitulating the mechanical and biological cues of the native tumor microenvironment, this bioprinted system offers a highly predictive in vitro tool for advanced cancer research and targeted drug screening, while actively implementing the 3Rs principles for the replacement of animal models.

Acknowledgements

Support from the Interuniversity Center for the Promotion of the 3Rs Principles, the Nanotechnology Lab at Istituti Clinici Scientifici Maugeri IRCCS, and the PNRR program is gratefully acknowledged.

D2 – P133

Rational design of cell viability-improved bioinks based upon rheological parameters.

de Castro Hernández D.F.[1], Flores-Cedillo M.L.[2], Rodríguez-Lorenzo L.M:[1]
[1]Bio2, Biomateriales y Bioimpresión, ICTP-CSIC, Madrid, Spain; [2]Ing. Industrial, Tecnológico Nacional de México/ITS de San Luis Potosí Capital, Mexico

Introduction

Shear stress during extrusion is critical for cell viability in bioprinted constructs and depends directly on bioink pseudoplastic behavior and selected printing noozle. This work aims to determine how the composition of a bioink influences shear stress in the nozzle. A rheological model is used to describe their behavior and generate stress maps as a function of the pseudoplasticity index *n* and consistency index *K* from the power-law model. These maps act as tuning charts for classification and design. By linking composition, rheology, and predicted shear stress, designing inks that maintain maximum shear stress within a viable range becomes possible, improving cell survival.

Materials and Methods

Sodium alginate from brown algae (SA), Sigma, methylcellulose (MC), Sigma, Poloxamer 188 PRO P4894, Sigma, home made hydroxyapatite particles[1] and PANC-1 from ATCC (frozen, CRL-1469, tissue: Pancreas; Duct) were used as bioinks components. Several have been prepared and rheological behaviour test include shear stress ramps, recovery tests, LVR tests, frequency sweeps and gelation tests. A pneumatic extrusion Inkredible 3D printer (Cellink) was used. Index n and consistency K have been obtained[2] and fed into a rheological physical model to calculate the maximum shear stress of the inks in different printing nozzles. The model has also been used to generate maps of the shear stress dependence with n and K.

Results and discussion

Stress maps produced (Fig. 1) show that minimizing K and n is critical for reducing tip shear stress and improving cell survival through extrusion. In inks without cells, poloxamer (I2c[5%Al-10%MC]) reduces K by 52.1% but raises n by 10.55%; in contrast, with particles (I4c[5%Al-5%HA-10%MC]), K drops 64.59% while n barely changes (+1.99%). When cells are added to particle-free ink (I2b[5%Al-10%MC-PANC-1]), K and n are minimally altered compared to I2c, whereas bioink I4b[5%Al-5%HA-10%MC-PANC-1] further reduces K by 8.62% beyond I4c. Shear stress calculations (Fig. 2) show I2b performs better in larger-gauge needles due to lower pseudoplasticity, while I4b performs better in smaller-gauge needles due to lower K. Per Lemarie et al., fibroblast viability requires $n \in [0–0.4]$ and $K \in [0–400]$; although these limits are cell-type specific and should be investigated, PANC-1 cells tested here fall within these ranges.

Conclusion

Two cell-viable bioinks for a 20G nozzle were designed. Consistency K can be modulated with power law index n remaining stable by introduction of hydroxyapatite particles in the bioink composition. This work shows that a rational approach can be adopted in bioink designing without the need for trial and error-based optimization.

Acknowledgments

Associate unit Bio2-Aries from CSIC-U. Nebrija is acknowledged.

This research was funded by MCIN/AEI/10.13039/501100011033/FEDER. Una manera de hacer Europa, grant number PID2021-128985OB-I00




Figure 1. Stress maps for three different printing nozzles 25G-0.260mm, 22G-0.413mm and 20G-0.900mm.




Figure 2. Shear stress, viscosity and shear rate profiles for the inks with (I4b) and without (I2b) hydroxyapatite particles along the three nozzles.

References

[1]Serrano-Belmonte et al. *Applied Sciences* 2025 ; 15 ; 7540. doi:10.3390/app15137540
[2] Banda Sánchez et al. *Polymers* 2023; 15 ; 3196. doi:10.3390/polym15153196
[3]Lemarié L., et al. *Bioprinting* 2021; 21; e00119. doi: 10.1016/j.bprint.2020.e00119

D2 – P134

Bio-ink from bio-waste: A dual crosslinking strategy to develop 3D-printed patch for the treatment of tympanic membrane perforation

Karmakar S., Raichur A.M.*
Dept. of Materials Engineering, Indian Institute of Science, Bangalore, India

Introduction

According to the WHO and UNICEF, developing nations like India generate a large amount of pathological and childbirth-associated bio-waste, in which placenta and umbilical cord contribute significantly due to the high fertility rate. Although a bio-waste, the placenta is also known as a major repository of biomolecules required for organ development and an excellent, readily accessible source of bioactive molecules.

The tympanic membrane (TM), situated between the middle and external ear, converts sound waves into mechanical vibrations to initiate hearing. Hence, perforation(s) in TM lead to several complications, such as infection, trauma, and conductive hearing loss, and require tympanoplasty, a surgical grafting procedure whose shortcomings include mechanobiological mismatch, microbial growth, rejection, and repeated surgery. Hence, this research aims to develop the bio-ink for a 3D-bioprinted personalised bio-adhesive patch that regenerates and repairs damaged TM.

Materials and Methods

HPMC-MA was synthesised via a nucleophilic substitution reaction; the placenta extract (PE) was prepared after decellularization, homogenisation, and lyophilization. Ink was formulated by mixing HPMC-MA (1-3%w/v) and SA (2-5%w/v) at different concentrations, along with PE; further rheological studies were conducted. 3D printing parameters were optimised for both the extrusion-based (Cellink+) and DLP-based (Bionova X) 3D bioprinters. 3D-printed hydrogels were prepared via dual crosslinking strategies: photo- and ionic. Scanning electron microscopy (SEM) was performed to assess the surface morphology. An *in vitro* cytocompatibility study and a wound-healing assay were performed.

Results

The modified polymer was characterised by FTIR and proton NMR study. Decellularisation of the placenta (DP) was confirmed by DNA staining and by DNA quantification relative to the control. Protein estimation in DP was significantly high, and a growth-promotion test confirmed sterilisation. Dual crosslinking was confirmed by exposing the printed patches to 405nm light and subsequently immersing them in an ionic solution. Rheological studies showcased viscoelastic and shear-thinning properties. The *in vitro* cell viability study showed relatively higher growth than the control group using NIH-3T3 and L929 cell lines. SEM images confirmed the high porosity and interconnectivity for cell migration and vascularisation.

Conclusion

Such a 3D-printed bio-adhesive patch encourages local cell migration and stimulates proliferation, thereby promoting rapid healing and tissue regeneration (e.g., perforated tympanic membrane) to restore hearing. Hence, the research has the potential to replace the current line of treatment protocol (surgical repairment, tympanoplasty) with a simpler solution at a significantly lower treatment cost (~€50) than the existing one (~€5000-7000).

Acknowledgements

PMRF, MoE, India
CSIR, MoS&T, India
IISc, Bangalore, India

D2 – P135
Sustainable manufacturing of pectin-based granular hydrogels for regenerative medicine

Hosseini M., Tirella A., Zanella C.
Dept. of Industrial Engineering. University of Trento, Trento (Italia), Italy

Introduction
Recent advancements in technological processes enabled implementation of circular-economy and sustainable approaches in regenerative therapies. Natural-derived polysaccharides, such as pectin, possess properties that make them suitable for controlled manufacturing strategies for tissue repair, including technologies such as 3D printing and microfluidics.

Aim
The aim of this work is to exploit sustainable manufacturing methods to fabricate pectin hydrogels products for wound management applications.

Materials and Methods
Pectin, derived from agricultural byproducts (apple pomace), was obtained using different protocols based on ultrasonic extraction, a more sustainable process than the traditional acidic extractions.

Physicochemical and thermal properties of the pectins extracted with different procedures were characterized using a commercially available pectin as a control. The optimal extraction conditions were identified by considering both the physicochemical characteristics of the pectin and its ability to form stable hydrogels.

Pectin hydrogel microbeads were fabricated using microfluidics, an advanced and sustainable manufacturing strategy enabling the controlled, precise, reproducible and environmental-friendly process. Microfluidics parameters were optimised to fabricate pectin microbeads with target size in the range of 100-150 μm and with monodispersed distribution. Pectin microbeads were formulated into a granular pectin-based biomaterial ink compatible with extrusion-based bioprinting (EBB). Rheological properties of pectin granular hydrogel and pectin solution biomaterial inks were tested to assess compatibility with EBB. The printability and structural stability of the resulting three-dimensional hydrogels were investigated, comparing bulk pectin hydrogel with granular pectin hydrogel geometries.

Results
A protocol for the extraction of pectin from apple pomace was selected, and obtained pectin was successfully used to produce tailored granular hydrogels for EBB. The pectin granular hydrogel used as biomaterial inks exhibit favorable flowability, improved printability, and enhanced injectability compared with conventional pectin hydrogels. Further, printed pectin granular hydrogel showed gelation and stability for the precise manufacturing of technologies supporting tissue repair and regenerative medicine strategies.

Conclusion
This study highlights a sustainable pathway for transforming agro-industrial waste into high-value biomaterials for regenerative medicine applications and demonstrates the potential of combining microfluidics and EBB as manufacturing technologies to develop next-generation technologies for wound management, and in general for biomedical applications.

D2 – P136

Towards stereolithography-based breast phantoms: Evaluation of photopolymer resins for phase contrast x-ray imaging

Trandas A.N., Serafim A., Ghitman J., Biru E.I., Horia I.
Advanced Polymer Materials Group, National University of Science and Technology Politehnica Bucharest, Bucharest, Romania

Introduction

Physical breast phantoms are essential tools in medical imaging for quality control, system calibration, and technique development. In phase contrast X-ray imaging (PCI), conventional phantoms often fail to replicate the complex, heterogeneous architecture of soft tissues, limiting the relevance of current results. Additive manufacturing, particularly stereolithography (SLA), offers the ability to fabricate anthropomorphic structures. Designing phantoms for PCI requires materials with homogeneity, low intrinsic X-ray scattering, and controlled, reproducible refractive index variations. This study investigates the correlation between the properties of commercial SLA photopolymer resins and their suitability for PCI breast phantom fabrication.

Materials and Methods

Test geometries and anatomically inspired models were fabricated using fused deposition modelling (FDM) and SLA. Evaluated parameters included material and structure homogeneity, and the influence of object thickness and additives on imaging quality. Each technique was assessed for PCI compatibility. Further material screening considered printability, structural fidelity, and multi-material assembly potential. Radio-optical properties were characterized primarily by X-ray microtomography (μCT), while PCI performance was assessed through contrast-to-noise ratio and edge enhancement. Mechanical properties were measured via tensile and compression testing, along with nanoindentation to capture local behaviour. Material stability under relevant conditions, including solvent exposure and UV irradiation, was also evaluated. Thermal analysis provided insight into polymer network stability and processing performance.

Results

Both SLA and FDM structures showed high geometric fidelity and reproducibility; however, only SLA-fabricated objects were compatible with PCI. μCT imaging highlighted the suitability of each resin for different phantom regions, the quality of printed structures, and internal assembly integrity, corroborated by PCI analysis. Multi-material assemblies demonstrated the feasibility of combining resins with complementary properties, enhancing phase contrast at interfaces. Mechanical testing revealed a wide range of stiffness and local behavior, supporting the potential to mimic heterogeneous soft tissue environments. Stability assessments indicated that selected materials maintained functional integrity under relevant conditions, with resin-specific variations observed under prolonged exposures.

Conclusion

Commercial SLA resins show strong potential for the fabrication of breast-mimicking phantoms optimized for PCI. Integrating imaging, mechanical, and stability evaluations provides a practical framework for material selection and design optimization. This approach enables the development of multi-material, structurally complex phantoms for imaging system calibration, supporting future advancements in phase-sensitive breast imaging.

Acknowledgements

The authors acknowledge the support of the “Medical applications of high-power lasers - Dr. LASER” project (SMIS Code: 326475), co-funded by the European Union, the Romanian Government and the Health Program.

D2 – P137
Tailoring the properties of Mg - LPSO alloys during powder bed fusion – Laser beam (PBF-LB)

Dobkowska A.[1], Ciftci J.[2], Kawamura Y.[3], Święszkowski W.[1]
[1]Faculty of Materials Science and Enginnering, Warsaw University of Technology, Poland; [2]Amazemet Ltd., Poland; [3]Magnesium Research Centre, Kumamoto University, Japan

This study aims to develop a new generation of Mg-based alloys containing long-period stacking ordered (LPSO) phases and to elucidate the relationship between their microstructure and corrosion behavior after processing using powder bed fusion – laser beam (PBF-LB). The Mg–LPSO alloy with the nominal composition Mg–0.9Zn–2.05Y–0.15Al–0.1Yb (at.%) was supplied as cast material by the Magnesium Research Centre at Kumamoto University, Japan and subsequently converted into spherical powder via inductive atomization. Atomization parameters were optimized to obtain powder with morphology and particle size distribution suitable for PBF-LB.

PBF-LB processing parameters were systematically tailored to produce materials with low porosity in the form of cylinders and TMPS structures. The porosity assessment was conducted using micro-computed tomography (µCT). The resulting microstructure was characterized using scanning electron microscopy (SEM/EDX) and electron backscatter diffraction (EBSD), while phase composition was characterized using X-ray diffraction (XRD). Corrosion performance was evaluated through electrochemical techniques, including linear polarization and potentiodynamic measurements, while corrosion rate was quantified using immersion tests. Additionally, tensile tests were performed.

During next steps, we optimized surface of the scaffolds through chemical polishing, proposing the optimal combination of the process to ensure the reliable properties of the TPMS structure.
The outcomes of this work provide fundamental insights into the design of LPSO-containing Mg alloys processed by PBF-LB, supporting the development of microstructure-controlled biodegradable materials.




Figure 1. TMPS printed using PBF-LB with their corresponding STEM microstructure.

D2 – P138

Additive manufacturing of biodegradable magnesium Alloy WE43: Effect of process parameters on microstructure and tesulting key properties

Larsson L.[1], Nilsson-Åhman H.[1,2], De Berardinis N.[1], Hulsart Billström G.[3], Mellin P.[2], D'Elia F.[1], Persson C.[1]
[1]Dept. of Materials Science and Engineering, Uppsala University, Uppsala; [2]Swerim AB, Stockholm; [3]Dept. of Medical Cell Biology, Uppsala University, Uppsala, Sweden

Introduction

Additive manufacturing through powder bed fusion with laser beam (PBF-LB) of magnesium alloy WE43 (Mg–4 wt% Y–3 wt% RE–0.5 wt% Zr) offers the potential for patient-specific biodegradable implants. However, no additively manufactured Mg implants are currently available for clinical use, largely due to knowledge gaps regarding the connection between microstructure, corrosion and mechanical performance. This study consolidates a broad range of findings that addresses these gaps by linking the aforementioned microstructure and properties to critical PBF-LB parameters.

Aim

Clarify the link between PBF-LB process parameters and the resulting microstructure (e.g. texture) and mechanical and corrosion properties of Mg alloy WE43.

Materials and Methods

Laser power, hatch distance, build orientation, and scan rotation were systematically varied (Fig. 1). Microstructure was analysed by SEM/BSE and XRD; texture by EBSD and neutron diffraction; and mechanical properties by tensile, compression, and hardness testing. Selected conditions were also evaluated for corrosion rate and *in vitro* biocompatibility.

Results

Higher laser power promoted equiaxed-dendritic grains, increasing tensile strength but reducing corrosion resistance. By tuning the hatch distance, the corrosion resistance was maintained while simultaneously preserving strength. Build direction was shown to be a valuable tool for tuning the mechanical strength. In fact, horizontal builds showed ~40% higher tensile strength and ~20% higher elastic modulus than vertical builds due to basal texture alignment. Laser scan rotation enabled texture control; segmented chessboard strategies improved compressive strength, while unidirectional scans led to poor densification. An optimized process parameter set enabled a higher pre-osteoblastic proliferation rate of the printed material as compared to extruded WE43.

Conclusion

The results demonstrate how coordinated selection of PBF-LB parameters enables tailoring of microstructure, texture, and performance of WE43, supporting its future application in biodegradable implants. Promising *in vitro* biocompatibility results supports this application, whilst additional work is required to enhance the corrosion resistance.

Acknowledgements

The Swedish Foundation for Strategic Research (SSF) within the Swedish national graduate school in neutron scattering (SwedNess), and VINNOVA's Competence Centre in Additive Manufacturing for the Life Sciences AM4Life (2019-00029), are gratefully acknowledged for financial support.




Figure 1. Schematic describing key process parameters investigated throughout the work.

D2 – P139

Design and characterization of bio-based hydrogels for light-based 3D-printing

Gunawan J.[1], Meyer J.[1], Biermann M.[2], Kara S.[1,3]
[1]Institute of Technical Chemistry, Leibniz University Hannover, Germany; [2]Anton Paar OptoTec GmbH, Seelze-Letter, Germany; [3]Biocatalysis and Bioprocessing Group, Dept. of Biological and Chemical Engineering, Aarhus University, Denmark

Introduction

Hydrogels are hydrophilic polymer networks that are continuously being developed for a wide range of applications, including biomedical applications, waste management and additive manufacturing. However, many of the materials currently in use are derived from non-renewable fossil fuels, which raises sustainability concerns. Materials based on poly(aspartic acid) and poly(aspartamide) are particularly attractive due to their biocompatibility, biodegradability and potential to be derived from renewable resources.[1] Comprehensive material characterization is essential to evaluate polymer structure and polymerization behavior.[2] The aim of this work is to develop sustainable, 3D-printable hydrogels based on poly(aspartamide) and to characterize them for application in digital light processing (DLP). In the long term, these materials are intended to enable covalent protein immobilization for applications such as antibody immobilization and biocatalysis.

Materials and Methods

Polysuccinimide (PSI) was synthesized through polycondensation of L-aspartic acid in mesitylene/sulfolane solvent mixture. PHEA or poly(hydroxyethyl aspartamide) was synthesized through aminolysis of PSI with 2-Aminoethanol, methacrylation of PHEA with methacrylic anhydride (MA). Material was characterized by NMR, FTIR, *in situ* photorheology and rheology-Raman spectroscopy.

Results


The synthetic pathway (Scheme 1) yielded methacrylated PHEA suitable for photopolymerizable hydrogel formulation. This strategy is based on previously reported poly(aspartamide) systems with modifications to the solvent system to improve the sustainability aspects.[3] Photopolymerization was initiated using lithium phenyl-2,4,6-trimethylbenzoylphosphinate (LAP) as a photoinitiator (Figure 1A). Hydrogel formation was observed upon UV irradiation during photorheological measurements.
To improve the printing resolution, tartrazine was incorporated as a photoblocker in the hydrogel formulation. As shown in Figure 1B, increasing irradiation time resulted in more transparent and clearer hydrogels, attributed to the degradation of tartrazine. These results confirm the feasibility of methacrylated poly(aspartamide) hydrogels as sustainable materials for light-based additive manufacturing.

Conclusion

Bio-based methacrylated poly(aspartamide) hydrogels were successfully synthesized and characterized, demonstrating photopolymerizable behavior suitable for light-based 3D-printing. The resulting materials provide a promising platform for the fabrication of functional hydrogel structures that can be further surface modified for covalent protein immobilization. Such materials offer potential for applications in biomaterials, antibody immobilization and biocatalysis.[4]

Acknowledgements

The project is funded by the Deutsche Forschungsgemeinschaft (DFG, German Research Foundation) – Project number 568637738.



Scheme 1 Synthesis pathway from polycondensation of L-aspartic acid to obtain polysuccinimide (PSI) followed by aminolysis with 2-aminoethanol resulting in poly(hydroxyethylaspartamide) or PHEA with subsequent methacrylation with methacrylic anhydride (MA) to obtain PHEA-MA.




Figure 8 A: Photopolymerization of PHEA-MA with LAP as photoinitiator results in a photocrosslinked PHEA-MA network. B: Hydrogel disks containing LAP as photoinitiator and tartrazine as photoblocker 3 min (left) and 10 min (right) post-UV exposure obtained after photorheological measurements.

References

[1]De Grave L., Di Meo C., Gréant C., Van Durme B., Gérard M., La Gatta A., Schiraldi C., Thorrez L., Bernaerts K.V., Van Vlierberghe S. Photo-crosslinkable Poly(aspartic acid) for Light-based Additive Manufacturing: Chain-growth versus Step-growth Crosslinking. *European Polymer Journa*l 2023; 190; 112017.

[2]Lambrecht S., Biermann M., Kara S., Jopp S., Meyer J. A Novel Characterization Technique for Hydrogels – in situ Rheology-Raman Spectroscopy for Gelation and Polymerization Tracking. *Materials Advances* 2024; 5; 6957-6966.

[3]Pitarresi G., Saiano F., Cavallaro G., Mandracchia D., Palumbo F.S. A New Biodegradable and Biocompatible Hydrogel with Polyaminoacid structure. *International Journal of Pharmaceutics* 2007; 335(1-2); 130-137

[4]Meyer J., Meyer L.-E., Borg H., Dorfs D., Kara S. Functionalized Poly(aspartic acid) Hydrogel Particles as Carriers for Covalent Enzyme Immobilization. *RSC Sustainability* 2025; 3; 3554-3566.

Isodimorphic copolyesters enabling non-linear tuning of physico-chemical properties towards light-based additive manufacturing

Bijleveld B., Quaak A., Parmentier L., Thijssen Q., Van Vlierberghe S.
Polymer Chemistry and Biomaterials Group, Centre of Macromolecular Chemistry, Dept. of Organic and Macromolecular Chemistry, Ghent University, Ghent, Belgium

Introduction

The development of polyester-based materials with tunable properties remains essential for biomedical applications, particularly given the limited flexibility of homopolymers such as poly(ε-caprolactone), which exhibit slow degradation and a limited range of physico-chemical properties.[1] Copolymerization provides a route to overcome these limitations by introducing compositional control. In particular, isodimorphic copolyesters result in a non-linear, typically parabolic dependence of physico-chemical properties on composition. Such behavior offers a framework to systematically tailor material performance. Here, ε-caprolactone-*co*-δ-valerolactone copolyesters are investigated to establish composition-structure-property relationships, with emphasis on tuning physico-chemical properties and their implications for degradation behavior.

Materials and Methods

ε-Caprolactone-*co*-δ-valerolactone copolyesters with varying comonomer ratios were synthesized via ring-opening polymerization. Alkene functionalization yielded degrees of substitution exceeding 95%, enabling the formulation of thiol-ene resins. Thermal properties were characterized using differential scanning calorimetry, with emphasis on melting temperature and enthalpy of fusion. Photopolymerization behavior was evaluated through photo-rheology under 405 nm irradiation (9.65 $mW.cm^{-2}$). Resin formulations were processed using volumetric additive manufacturing (VAM) and two-photon polymerization (2PP).

Results

The materials exhibited clear isodimorphic behavior, reflected in a parabolic dependence of melting enthalpy on copolymer composition (Table 1), decreasing from ~39-43 $J.g^{-1}$ for the homopolymers to ~18-26 $J.g^{-1}$ for the copolymers, with a minimum at equimolar composition. This corresponds to a reduction in crystallinity from ~30% for the homopolymers to ~13% at equimolar co-monomer ratio. In addition, the melting temperature decreased from ~40 °C to ~3.3 °C at equimolar composition. Transmittance (at 405 nm) increased from 3-12% for homopolymers to 91% at equimolar composition. The composition range was also tested for cell viability in an in vitro cytotoxicity assay, showing sustained viability above 80% throughout the 7-day testing period. Finally, these compositions were evaluated in light-based additive manufacturing via VAM and 2PP, demonstrating their processability into three-dimensional constructs.

Conclusion

These results demonstrate that isodimorphic copolymerization enables systematic tuning of polyester physico-chemical properties through compositional control, establishing a versatile strategy for the rational design of functional polyester materials that maintain cell viability across the composition range and have potential for light-based additive manufacturing.

Acknowledgements

B.B. and S.V.V. acknowledge support from the ICON PHOTO-AUP project funded by VLAIO (Flanders Innovation & Entrepreneurship) with project number HBC.2023.0736. A.Q. and Q.T. acknowledge the Research Foundation Flanders for a PhD (FWO-SB) and Junior postdoctoral fellowship with grant numbers 1SHDP24N and 1201125N, respectively. B.B., L.P., and S.V.V. acknowledge the Flemish Government, Department of Work, Economy, Science, Innovation, and Social Economy under the RegmedXB Covenant.




Figure 9: Schematic overview of the design rationale and structure-property-processing relationship governing isodimorphic copolyesters.

Table 1: Physico-chemical and photoreactive properties of 3-armed 8000 g.mol^{-1} alkene-functionalized ε-caprolactone-co-δ-valerolactone copolyesters.

Ratio ε-CL:δ-VL	Mn_{exp} (g.mol^{-1}, ^{1}H-NMR)	Alkene content (mmol.g^{-1})	T_d (°C)	T_g (°C)	T_m (°C)	ΔH_m (J.g^{-1})
1:0	7450	0.393	315	-65	41	39
3:1	7600	0.398	322	-62	16	38
1:1	7350	0.420	289	-64	3.3	17
1:3	6400	0.462	283	-63	14	26
0:1	7450	0.410	282	-61	42	43

References

[1]Thijssen Q., Quaak A., Bijleveld B., et al. Light-Based 3D Printing of Polyesters: From Synthesis to Fabrication. *Chemical Reviews* 2025; 126, 2; 1258-1293.

D2 – P141

Design of photo-curable biodegradable lactide- and ε-caprolactone based resins for 3D-printing and bioprinting

Sedush N.G.[1], Kalinin K.T.[1], Starikova A.A.[2], Chvalun S.N.[1,2]
[1]Laboratory of polymeric and composite materials for biomedical applications, Enikolopov Institute of Synthetic Polymeric Materials RAS; [2]Lomonosov Institute of Fine Chemical Technologies, Russian Technological University, Moscow, Russia

Introduction

Biodegradable and biocompatible aliphatic polyesters such as PLA, PLGA, PCL and PLCL are widely used for the manufacture of medical devices, drug delivery systems and scaffolds for tissue engineering. Depending on composition and molecular structure the properties and degradation profile of the aliphatic polyesters vary widely. Such polymers, mostly in the form of 1.75 mm filaments, are already used for fabrication of personalized implants for craniomaxillofacial surgery, neurosurgery and regenerative medicine by FDM printing. However, for more precise fabrication of implants and scaffolds photopolymerization-based 3D printing techniques are more favorable, since they enable the production of even micron- and submicron-scale structures. Therefore, development of lactide- and ε-caprolactone based biodegradable photo-curable resins is of great interest.

Aim

Development of novel photo-curable biodegradable linear and star-shaped lactide- and ε-caprolactone oligomers for 3D-printing and bioprinting of products with controlled properties and degradation profile.

Materials and Methods

Linear and star-shaped (3- and 6-arm) oligomers of D,L-lactide- and ε-caprolactone with arm lengths from 5 to 50 monomeric units were synthesized by ring-opening polymerization and comprehensively characterized by SEC, NMR, MALDI, DSC and rheological analysis. At the next step the end-groups of the oligomers were modified with a methacrylic acid derivative to get UV-curable resins. Oligomers were UV-cured in the presence of a photoinitiator at different temperature in molds to get the samples for mechanical tests. Allevi 3 bioprinter and Ember Autodesk DLP 3D printers were used for printing.

Results

Linear and star-shaped lactide and ε-caprolactone methacrylated oligomers with predetermined number and length of the arms were synthesized. Rheological tests at different temperatures were conducted in order to identify the resins with properties favorable for different techniques of 3D printing (SLA, DLP, VAM, bioprinting). Depending on the molecular structure of the original oligomers, the cross-linked materials were characterized by different crystallinity and mechanical properties: modulus varied from 5 to 1850 MPa, strength from 2 to 35 MPa, and deformability from 1 to 300%. Demonstration of printing using the developed resins was demonstrated by fabrication of porous gyroid scaffolds.

Conclusion

Composition and characteristics of developed photo-curable biodegradable lactide- and ε-caprolactone based resins can be tuned to meet the requirements of different light-based 3D printing techniques and to adjust the mechanical properties and degradation profile of the printed product. The developed materials can be considered as promising and flexible platform for fabrication of personalized medical devices, implants and scaffolds by photopolymerization-based 3D printing and bioprinting.

D2 – P142

Stimuli-responsive polymeric fiber scaffolds with thermally switchable liquid crystal elastomers fabricated by melt electrowriting

Iamsamang J.[1], Yue L. [2], Cedillo-Servin G.[1], Debije M. G. [2], Castilho M.[1]
[1]Dept. Biomedical Engineering, Eindhoven University of Technology; [2]Dept. Chemical Engineering and Chemistry, Eindhoven University of Technology, Eindhoven, The Netherlands

Introduction

Liquid crystal elastomers (LCE) are stimuli-responsive materials with promising applications in tissue engineering, including scaffolds that adapt to context-dependent conditions. However, current LCE processing techniques often lack the ability to tune mesogen alignment and filament stiffness in a localized and controllable way. Here, we hypothesized that melt electrowriting (MEW) can align LCE mesogens (Fig. 1A), activating the thermoresponsive shape change and enhancing fiber stiffness.

Aim

We leveraged process-induced alignment to produce mechanically robust, responsive LCE fibers using MEW.

Materials and Methods

A thermoplastic polyurethane-based LCE was synthesized containing liquid crystalline soft segments (66 wt%) and thio-urethane hard segments (34 wt%), with a nematic-isotropic transition temperature of 31 °C. Melt-electrowritten LCE fibers were fabricated using a custom-built setup (printing speed: 200–300 mm/min; reservoir temperature 185°C; 24G needle; nitrogen atmosphere 0.07 bar; voltage: 1.9–3.7 kV). Collector temperature was modulated at either room temperature or 60°C to produce fiber with high or low liquid-crystalline alignment (+align, –align), which was examined by polarized microscopy (Leica DMi8). The effect on mechanical performance was characterized using uniaxial tensile testing (CellScale Biotester5000).

Results

The deposited fibers showed printing-speed-dependent jet morphology: coiled, meandered, or straight (Fig. 1B). Polarized imaging suggested that the MEW process induced LCE alignment (Fig. 1C), likely due to shear forces from extrusion and stretching from electrodynamic forces and printing speed. Uniaxial tensile testing confirmed anisotropic mesogen alignment within LCE fibers. Aligned fibers were significantly stiffer than unaligned fibers (2.0 ± 0.5 vs 1.0 ± 0.3 MPa), as the energy is first spent rotating those unaligned mesogens to face the tensile direction, leading to a lower tensile strength (Fig. 1D).




Figure 1: A) Schematic diagram of LCE fiber deposition via MEW. B) LCE jet behavior and C) mesogen alignment. D) Representative uniaxial tensile curves of LCE fibers.

Conclusion

MEW is an effective method for inducing LCE molecular alignment without complex post-processing. By leveraging shear and electrodynamic forces, we fabricated micro-fibers with tunable mechanical stiffness. The ability to manipulate mesogen orientation via MEW provides a promising way for developing dynamic, responsive scaffolds for biomedical applications, e.g. drug-delivery and vascular grafts.

D2 – P143

3D-printed amphiphilic polymer conetworks (APCNs) as advanced functional biomaterial for biomedical application

Santamaria C.[1,2], Wolschner M.[3], Frascella F.[1], Boesel L.F.[3] , Roppolo I.[1]
[1]Dept. of Applied Science and Technology, Politecnico di Torino, Turin, Italy Institution; [2]Dept. of Chemistry, Biology and Biotechnology, University of Perugia, Perugia, Italy; [3]Laboratory for Biomimetic Membranes and Textiles, EMPA, St. Gallen, Switzerland

Introduction

Amphiphilic polymer conetworks (APCNs) represent a promising class of materials composed of hydrophobic and hydrophilic polymer phases, resulting in unique combinations of optical, mechanical and swelling properties. In this work, APCN chemistry is combined with Digital Light Processing (DLP) 3D-Printing to enable fabrication of structures with desired geometry and enhanced functionality. The presence of silicone-based components provides optical transparency, biocompatibility and good mechanical properties. In addition, the possible functionalization with responsive and functional moieties thanks to the hydrophilic phase make these materials attractive for the biomedical field.

Materials and Methods

The materials used include polydimethylsiloxane methacryloxypropyl-terminated poly(dimethyl siloxane) (MA-PDMS-MA) and a solution of trimethylsilyl-protected 2-hydroxyethyl acrylate (TMS-HEA). The TMS group acts as a hydrophobic masking agent, improving the miscibility of the polymers. After the polymerization, the TMS protection is removed, resulting in an amphiphilic structure where PDMS constitutes the hydrophobic phase and HEA the hydrophilic phase.

For functionalization, two solutions were employed: (i) 0.7wt% LR305 in Toluene (ii) a 1:1: H2O:EtOH solution containing 0.3 wt% fluorescein salt. In addition, pentafluorophenyl acrylate (PFPA) was used to achieve a more efficient and long-term stable functionalization. Samples were fabricated using a DLP 3D printer (Asiga MAX UVx27). The resulting materials were characterized by FTIR, DSC, DMTA, swelling tests in two different solvents, fluorescence spectroscopy and SAXS.

Results

As first, FTIR analysis was performed to confirm the successfull deprotection of HEA-groups. This was evidenced by the presence of a characteristic peak around 3500 cm^{-1} and the absence of a peak around 750 cm^{-1} in the spectrum of post-prcessed samples to remove the TMS. Once verified the TMS removal, further characterization was carried out to evaluate mechanical, thermical and optical properties of the 3D-Printed Samples. For each analysis, a direct comparison between deprotected and non-deprotected samples was perfomed, highlighting the differences between single-phase and biphasic systems. In addition, fluorescence measurements confirmed the successful functionalization of the APCNs with fluorescent dyes, demonstrating the effective incorporation of the fluorophores within the network.

Conclusion

The development of APCNs represents a versatile platform for the fabrication of advanced functional biomaterials. Their biphasic structure enables efficient and stable functionalization, allowing the incorporation of responsive moieties, fluorescent probes and biomolecules. These features make APCNs particularly promising for biomedical applications, including drug delivery systems, selective membranes and biointerfaces. In this context, this work aims to develop photoluminescent sensing systems by integrating DLP 3D-Prinitng with APCN chemistry for real-time environmental monitoring.

D2 – P145

On-chip microfluidic strategies for tunable microgel filament assembly

van der Ben B.V.[1], Zafeiropoulos S.[1], Wlodarczyk-Biegun M.K.[1, 2]
[1]Zernike Institute for Advanced Materials, University of Groningen, Groningen, The Netherlands; [2]Biotechnology Centre, The Silesian University of Technology, Gliwice, Poland

Introduction

Microgels are promising building blocks in biofabrication due to their shear thinning behaviour, tunable properties, and ability to encapsulate cells or biomolecules. Their modular nature enables the assembly of scaffolds with varied internal structures. Using microfluidics, microgel organization can be precisely controlled, enabling the production of filaments with heterogeneous composition, gradients, or distinct domains.

Aim

The aim of this study is to explore on-chip microfluidic mixing strategies to guide microgel assembly and generate structured filaments for biofabrication applications.

Materials and Methods

Microgels were generated from gelatin methacryloyl using microfluidic droplet formation. Fluorescent labeling with Rhodamine isothiocyanate and fluorescein isothiocyanate was incorporated to visualize microgel distribution. Microfluidic devices for controlled microgel mixing were fabricated from polydimethylsiloxane (PDMS) using CAD-designed moulds produced by high-resolution resin printing. Various Devices included microchannels with mixing regions and junctions to facilitate interaction of multiple microgel streams. PDMS chips were plasma bonded to glass substrates to seal the microchannels. Following plasma treatment, channel surfaces were rendered hydrophobic to ensure stable flow. Microgel suspensions were introduced through multiple inlets and combined within the microfluidic channels to investigate mixing and filament formation. Flow conditions were precisely controlled to tune microgel interactions and mixing within the channels. The mixing behaviour was visualized directly on-chip using optical microscopy, and filament structure was assessed post-printing.

Results

Initial observations indicate that microfluidic mixing strategies enable control over the spatial distribution of microgels within continuously formed filaments. Flow conditions and device design can be tuned to guide the arrangement of microgels within filaments. These findings indicate how microfluidic control can be used to alter filament composition and internal architecture.

Conclusion

On-chip microfluidic control allows tuning of microgel organization within filaments, enabling the fabrication of materials with tailored spatial properties. Such strategies have the potential to aid the production of complex tissues and engineered biomaterials.

Acknowledgements

Funded by the European Union (ERC-2024-Stg #101161716 JAM2PRINT). Views and opinions expressed are however those of the author(s) only and do not necessarily reflect those of the European Union or the European Research Council. Neither the European Union nor the granting authority can be held responsible for them

D2 – P146

Cerium-oxide nanoparticles´ interactions with cells depends significantly on their surface chemistry (fluorescent tagging)

Hubalek Kalbacova M.[1], Jolous Jamshidi P.[1], Dulta K.[2], Ju X.[2]
[1]Institute of Pathological Physiology, 1st Faculty of Medicine, Charles University, Prague; [2]Dept. of Chemistry and Biochemistry, Mendel University in Brno, Brno, Czech Republic

Introduction

Colloidally stable cerium oxide nanoparticles (CeNPs) coated with polymers have been extensively developed for antioxidant therapeutic applications since they possess multi-enzyme mimicking activities such as peroxidase, catalase, and superoxidase, targeting inflammation and oxidative stress related diseases. The surface chemistry of CeNPs governs their catalytic behaviours, yet the role of various surface functionalization of nanoparticles in modulating their cellular interactions remains poorly understood. For biological applications, CeNPs are mostly modified with fluorescent tags to better visualize their cellular fate as well as *in vitro/in vivo* quantification. However, how this staining procedure alters the surface chemistry and nanoparticle-cell interaction remains unexplored.

Aim

We investigated how grafting the lipophilic dye DiI onto poly(acrylic acid)-coated cerium oxide nanoparticles (DiI@CeNPs) and onto those enriched of platinum (DiI@Pt/CeNPs) alters their physicochemical properties, colloidal stability, catalytic activity and interaction with cells compared to unlabelled CeNPs.

Materials and Methods

Physicochemical properties, colloidal stability and catalytic activity were determined (evaluation of UV-Vis adsorption spectra, TEM micrographs, XPS core-lever spectra, XRD patterns and DLS and zeta potential measurement). Cytotoxicity and cellular internalization of CeNPs in human fibroblasts were evaluated by fluorescence microscopy, TEM and STEM after FIB-SEM lamella preparation.

Results

While both systems retained redox-mimetic enzyme activities (catalase, peroxidase, SOD, oxidase) corelated to their Ce^{3+}/Ce^{4+} ratio, DiI conjugation dramatically reshapes nanoparticle-cell interactions. The DiI tagged CeNPs exhibited the colloidal stability and physiochemical properties very similar to those without dye, with the only variation being their surface oxidation state (Ce^{3+} percentage) due to the dye incorporation. There was no cytotoxic effect observed on the human cells after 24 h of co-incubation at selected NPs dosage. TEM analysis confirmed the cellular internalization of both types of nanoparticles, although more agglomerates of NPs inside the cells were observed in the case of fluorescent stained NPs compared with NPs without dye.

Conclusion

These findings provide insight into the role of surface functionalization of dye-labelled CeNPs on their cellular uptake. They would not only replace the existing molecular and nanoparticle tools but also stimulate new applications.

D2 – P147

Biofunctionalized electrospun fibers for controlled cell-material interaction in 3D bioprintable systems

Schütz J.[1], Neuhäusler A.[2], Stadler J.[3], Weber M.[4], Daum R.[1], Schmolz M.[4], Blaeser A.[2], Hartmann H.[1]
[1]NMI Natural and Medical Sciences Institute at the University of Tübingen, Reutlingen; [2]IDD Institut für Druckmaschinen und Druckverfahren, Technical University of Darmstadt, Darmstadt; [3]Black Drop Biodrucker GmbH, Darmstadt; [4]HOT Screen GmbH, Reutlingen, Germany

Introduction

Bioprinted, organ-like tissues have become of great interest in recent years for in-vitro test systems. However, the controlled cell-material interaction, allowing spatial orientation and functionality of cells within such 3D-systems, remains challenging. We aim to solve this by integration of fragmented and biofunctionalized electrospun polymer fibers into bioinks for 3D bioprinting.

Materials and Methods

Fiber mats were electrospun, characterized by scanning electron microscopy, and tested for undesired immune cell activation. Fiber fragments were produced by cutting with a rotor-driven razorblade, subsequent filtration and lyophilization. The fragments were plasma-activated, biofunctionalized by fibronectin coating and dispersed in a hydrogel. The orientation of endothelial cells along the fibers was confirmed by CD31/Hoechst staining. In addition, the fibers' potential to function as carrier material was evaluated by analyzing the immobilization of a representative bioactive molecule and its ability to elict a cellullar response. Viscosity measurement of the fiber-hydrogel formulation was performed with a rheometer, followed by extrusion-based 3D bioprinting. To adjust the fragment concentration dynamically during printing, a coaxial system was developed and evaluated. Suitable print parameters were analyzed to ensure a controlled extrusion and the fiber orientation was evaluated based on brightfield microscopy using a dedicated software.

Results

Bead-free fibers were successfully electrospun with an average diameter of 2.7 µm and extracts showed no immune cell activation in whole blood cultures. Fiber fragmentation resulted in fragments shorter than 300 µm. Fibers could be homogeneously coated with fibronectin and successfully mixed at final concentrations between 5 mg/mL and 10 mg/mL with endothelial cells and hydrogel. Immunofluorescence staining revealed 3D orientation of endothelial cells along the fibers, showing elongated morphology, compared to the fiber-free control, where cells showed a round morphology within the bioinert hydrogel. Viscosity of the hydrogel increased after fiber-addition. Applying the coaxial printing approach allowed precisely controlled fiber addition and local concentration adjustment during the printing process. In addition, alignment of the fibers relative to the printing direction was achieved, allowing the 3D bioprinting of tissue analogues with anisotropic fiber orientation. Furthermore, immobilization of the representative biomolecule to the fibers and its release were successfully analyzed.

Conclusion

Defined electrospun fiber fragments can be biofunctionalized and homogeneously distributed in a bioinert hydrogel, providing 3D orientation for cells. Bioprintability of the composite material with fiber alignment and additional fiber functionalization with bioactive compounds offers wide potential for in-vitro test systems.

Acknowledgements

We thank all project partners and the BMFTR for financial support (13XP5203).

D2 – P148

Undiscovered antibacterial properties of nanostructured aluminium alloys: The bacterium-substrate interface study

Krawczynska A.T.[1], Michalicha A.[2], Belcarz-Romaniuk A.[2]
[1]Warsaw University of Technology, Faculty of Materials Science and Engineering, Warsaw; [2]Chair and Dept. of Biochemistry and Biotechnology, Medical University of Lublin, Lublin, Poland

Introduction

Antibacterial properties of materials can be attributed to multiple factors, including chemical composition, surface roughness, and microstructure. It has been shown that microstructural refinement via severe plastic deformation, e.g., high-pressure torsion, can significantly enhance the antibacterial properties of copper and brass.

Aim

The enhancement of antibacterial properties of aluminium alloys via severe plastic deformation.

Materials and Methods

The antibacterial properties of annealed and high-pressure torsion-processed aluminum alloys have been investigated in biofilm formation tests. Afterward, the fluorescence microscopy (Olympus BX41 microscope equipped with UC 12 Soft Imaging System camera), as well as focused ion beam (NB5000 Hitachi) and scanning transmission electron microscopy (STEM Spectra 200 Thermo Fisher Scientific) observations and analysis were performed.

Results

High-pressure torsion led to the microstructure refinement to the nanoscale. More advanced biofilm was created on annealed samples than on high-pressure torsion processed, which was revealed on the plane-view as well as on cross-sections of the bacterium-substrate interface in the nanoscale.

Conclusion

High-pressure torsion-processed aluminium alloy samples show enhanced antibacterial properties in comparison with annealed ones.

Acknowledgements

The work was funded by the National Science Centre in Poland under the project “Sonata bis 11”, UMO-2021/42/E/ST5/00118.

D2 – P149

Elastin-like polypeptide multilayers as biointerfaces for rapid tumor cell adhesion

Paglia E.B.[1], de Freitas G.P.[1], Baldin K.K.E.[1], Bataglioli A.R.[2], de Carvalho H.F.[3], Beppu M.M.[1]
[1]School of Chemical Engineering, Universidade Estadual de Campinas (UNICAMP), Campinas, Brazil; [2]Dept. of Biological Science, Virginia Tech, Blacksburg, USA; [3]Instituto Nacional de Ciência e Tecnologia de Fotônica Aplicada à Biologia Celular – INFABIC, Universidade Estadual de Campinas (UNICAMP), Campinas, Brazil

Introduction

Engineering biointerfaces that regulate tumor cell adhesion is important for biomaterial design and for the development of cell-interactive sensing platforms. Elastin-like polypeptides (ELPs) are biomimetic polymers inspired by the repetitive elastin-derived pentapeptide motif (VPGXG) and have emerged as promising materials for surface engineering due to their tunable physicochemical properties and protein-like character. In multilayer systems assembled by the layer-by-layer (LbL) technique, bioactive ligands such as the integrin-binding motif RGD are commonly incorporated to promote cell adhesion. However, the contribution of such ligands during the early stages of tumor cell attachment remains unclear. In this study, we investigated the rapid adhesion of PC3 prostate cancer cells on ELP multilayer biointerfaces and evaluated the influence of RGD incorporation. Alginate multilayers were included as a non-adhesive polysaccharide control to assess the influence of polymer chemistry on early tumor cell–surface interactions.

Materials and Methods

LbL films assembled on plasma-treated glass: polyethylenimine (PEI, 0.1% w/v, pH 4) primer, then 3.5 bilayers of polyanions (0.1% w/v, 10 mM Tris pH 5: alginate, ELP, or ELP-RGD) alternated with chitosan (CHI, 0.1% w/v, pH 5). PC3 cells seeded (200 µL, 6.25 × 10^4 cells/mL), incubated 1 h at 37°C/5% CO_2, fixed (4% PFA), stained (DAPI/phalloidin), and quantified by ImageJ nuclear counts (3 films/condition). Nanotopography by AFM (FlexAxiom SLD, Nanosurf) in tapping mode; Sa (ISO 25178) via Gwyddion.

Results

ELP multilayers supported rapid PC3 adhesion (299 ± 48 cells mm^{-2}), comparable to ELP-RGD (231 ± 45 cells mm^{-2}; $p > 0.05$), while alginate remained non-adhesive (~2.5 cells mm^{-2}). AFM analysis revealed smooth surfaces for both ELP (Ra = 0.69 ± 0.15 nm) and ELP-RGD (Ra = 0.71 ± 0.12 nm) coatings, alginate multilayers were substantially rougher (Ra = 13.72 ± 8.14 nm). Surface roughness alone did not explain adhesion difference. A plausible explanation is that adsorption of serum proteins from the culture medium onto the biomimetic ELP coatings provides adhesion ligands that enable integrin-mediated cell attachment during the early stages of cell–surface interaction.

Conclusion

ELP multilayer coatings support rapid tumor cell adhesion without additional ligand functionalization. These findings suggest that biomimetic ELP biointerfaces may enable simple surface designs for applications where fast tumor cell attachment is desirable, such as label-free cell capture and sensing platforms, with potential to explore underlying molecular mechanisms. Moreover, the versatility of the LbL approach may allow future tuning of surface topography and ligand presentation to investigate the specificity of tumor cell adhesion.

Acknowledgements

To FAPESP for the financial support (Grant n. 2020/12980-3).

D2 – P150

Silk fibroin coatings for intravascular sensors: Cytocompatibility and hemocompatibility assessment

Russo L.[1], Babboni S.[1], Vurro D.[2], D'Onofrio I.[3], D'angelo P.[2], Basta G.[1], Ottomaniello A.[4], Mattoli V.[4], Tarabella G.[2], Del Turco S.[1]

[1]Institute of Clinical Physiology, CNR, Pisa; [2]Institute of Materials for Electronics and Magnetism, CNR, Parma; [3]Dept. of Chemistry Life Sciences and Environmental Sustainability, University of Parma, Parma; [4]Center for Materials Interfaces, Istituto Italiano di Tecnologia, Pontedera, Italy

Introduction

Implantable intravascular devices offer a tool for improved cardiovascular disease management. These devices interact with vascular tissues and blood, triggering biological responses, such as inflammation and thrombosis. Biocompatible coatings are essential to overcome these biological challenges, preserving device long-term functionality. Silk fibroin, a natural protein, has gained attention as a biomaterial due to its good cytocompatibility and ability to form stable thin films. A key advantage of silk fibroin is that its β-sheet content can be tuned to control degradation in biological fluids, enabling time-programmed coating protection of implantable sensors.

Aim

This study aimed to evaluate the cyto- and hemocompatibility of thin silk fibroin films by in vitro assessment.

Materials and Methods

Ultrathin silk fibroin films (7.5% wt fibroin in water) were fabricated by spin-coating. ilm thickness was measured using a surface profilometry (500 ± 20 nm). Film morphology was characterised by SEM. Film degradation in PBS (at 0, 7 and 14 days) was assessed by profilometry and FIB/SEM.

Direct cytocompatibility was assessed using human umbilical vein endothelial cells (HUVECs) cultured on silk fibroin films to investigate cell adhesion, viability, and proliferation (4-24-48 hours) by immunofluorescence staining, Presto Blue and wound-healing assays. Indirect cytotoxicity (MTT) and oxidative stress (DCF assay) were evaluated by exposing HUVECs for 24 h to fibroin-conditioned media collected at different time points (1-7-14-21 days). Hemocompatibility was evaluated in porcine blood by measuring haemolysis, blood cell counts, and coagulation times.

Results

SEM revealed clear fibroin degradation over time with increasing surface roughness and thickness reduction. FIB cross section showed a reduction of thickness, in agreement with profilometry, quantified as 35±5 nm/day from days 0 to 7, and 15±5 nm/day from days 7 to 14.

HUVECs cultured on fibroin films showed good adhesion, with well-organized cytoskeletal structure. A significant increase in cell proliferation on fibroin films was evidenced after 48h of culture ($p=0.039$). Fibroin films applied directly on HUVECs supported cell migration and adhesion in the scratched area, demonstrating that ultrathin coatings are non-toxic and promote tissue regeneration.

HUVECs exposed to fibroin film-conditioned media maintained high viability and did not increase intracellular ROS production. Hemocompatibility testing demonstrated that fibroin coatings did not induce haemolysis, platelet adhesion and clot formation, highlighting their blood compatibility.

Conclusion

Silk fibroin ultrathin coatings demonstrate excellent cyto- and hemocompatibility and time-programmed degradation, thereby preserving device function in the vascular environment.

Acknowledgements

This work was supported by the EIC Pathfinder Challenger project IV-Lab (ID: 101115545).

D2 – P151

Electroactive biomaterials for mechanoelectrical modulation of breast cancer cell behaviour

Ribeiro S.[1,2], Brito-Pereira R.[1,3,4], Lanceros-Mendez S.[4,5], Martins P.[1,2], Ribeiro C.[1,2]
[1]CF-UM-UP - Physics Centre of Minho and Porto Universities, University of Minho, Braga, Portugal; [2]LaPMET - Laboratory of Physics for Materials and Emergent Technologies, University of Minho, Braga, Portugal; [3]IB-S - Institute of Science and Innovation for Sustainability, University of Minho, Braga, Portugal; [4]BCMaterials, Basque Center for Materials, Applications and Nanostructures, UPV/EHU Science Park, Leioa, Spain; [5]IKERBASQUE, Basque Foundation for Science, Bilbao, Spain

Introduction

Breast cancer remains one of the leading causes of cancer-related mortality worldwide, with tumour progression strongly influenced by the physical and biochemical characteristics of the cellular microenvironment. Electroactive biomaterials capable of converting mechanical stimuli into electrical signals have recently emerged as promising platforms to modulate cellular behaviour through mechanoelectrical stimulation. Such materials may provide new strategies to influence tumour cell activity while preserving healthy tissue function. In this context, this work investigates the interaction between electroactive biomaterials and breast cancer cells under static and mechanically stimulated conditions.

Materials and Methods

Magnetoactive polymer films based on P(VDF-TrFE) were developed by incorporating different types and concentrations of magnetic fillers, including cobalt ferrite (CFO) and magnetite (Fe_3O_4). Composite films containing 10–50 wt% CFO as well as films containing 20 wt% Fe_3O_4 were fabricated and used as cell culture platforms.

The biological response of the materials was evaluated using two breast cancer cell lines with distinct phenotypes, MDA-MB-231 (triple-negative breast cancer) and SK-BR-3 (HER2-positive), together with a reference epithelial breast cell line (MCF-10A). Experiments were conducted under static conditions and under dynamic stimulation to generate a magneto-mechanical microenvironment in the composite films. Cellular behaviour was assessed through proliferation assays, cell cycle analysis, apoptosis quantification and reactive oxygen species (ROS) evaluation.

Results

All developed films supported cell adhesion and growth under static conditions. However, distinct cellular responses were observed depending on the composition of the magnetoactive films and the stimulation conditions. Dynamic stimulation influenced proliferation rates and altered cell cycle distribution in breast cancer cells compared to static culture conditions.

In addition, variations in apoptotic activity and intracellular ROS levels were detected, indicating that the magnetoactive microenvironment generated by the composite films can modulate oxidative stress and programmed cell death pathways. The magnitude of these effects depended on the type and concentration of magnetic particles incorporated in the polymer matrix.

Conclusion

These results demonstrate that magnetoactive P(VDF-TrFE) composite films can generate dynamic microenvironments capable of modulating key biological processes in breast cancer cells. These platforms provide a promising approach to investigate the role of physical stimuli in tumour mechanobiology and support the development of biomaterial-based strategies for cancer modulation and therapy.

Acknowledgements

This work was supported by Fundação para a Ciência e a Tecnologia (FCT) through the strategic funding of CF-UM-UP (UID/04650/2025) and the project BreastInTreat (COMPETE2030-FEDER-00772000). C.R. and S.R. acknowledge FCT for individual research contracts (2020.04163.CEECIND/CP1600/CT0019 and 2022.02722.CEECIND/CP1718/CT0015). R.B.P. acknowledges the Juan de la Cierva research contract (JDC2023-052829-I).

D2 – P152

Impact of surface coatings on biocompatibility of PEDOT:GABA neural delivery systems

Shakibania S.[1,2], Smolka S.[1,2], Tomasiak A.[1], Maryam S.[1,2], Krukiewicz K.[1,3]
[1]Dept. of Physical Chemistry and Technology of Polymers, Silesian University of Technology; [2]Joint Doctoral School, Silesian University of Technology; [3]Centre for Organic and Nanohybrid Electronics, Silesian University of Technology, Gliwice, Poland

Introduction

The growth of the aging population has led to a rising prevalence of neurological disorders. A wide range of conditions, including epilepsy, Parkinson's disease, Alzheimer's disease, chronic pain, and depression, require varied therapeutic strategies, among which electrical stimulation has emerged as a particularly effective approach. Gamma-aminobutyric acid (GABA) is the primary inhibitory neurotransmitter in the central, peripheral, and enteric nervous systems, and it plays a role in numerous physiological processes within the nervous system and throughout the body. Conducting polymer-coated electrodes that allow electrically controlled release of neurotransmitters offer significant potential for treating neurological disorders.

Aim

This study explores the modification of neural electrodes using electroactive materials to store and release GABA in a controlled, electrically triggered manner. Moreover, different strategies to improve the cell-material interaction are particularly studied to not only improve the release but also enhance the cell-material interaction.

Materials and Methods

A poly (3,4-ethylene-1,4-dioxithiophene) (PEDOT) layer containing GABA was created through an electrochemical polymerization method in a three-electrode configuration, at different pHs. Then, for further investigations, samples were modified by a top layer of either PEDOT:PSS or PEDOT:PSS+Alginate conducting hydrogel. To study the biological behaviour of the coatings, a cell viability assay was conducted using the SH-SY5Y neuroblastoma cell line. Moreover, the morphology of the cells was visualized using Scanning Electron Microscopy 48 hours post-seeding.

Results

The results of this study indicate that the presence of GABA increased cell viability from 96.63 ± 2.07% to 103.7 ± 1.62% compared to the PEDOT:PBS sample. However, the formation of an additional layer on top of the PEDOT:GABA surface led to a reduction in cell viability. Specifically, cell viability decreased to 55.63 ± 1.69% for PEDOT:GABA:Hydrogel and 73.53 ± 2.12% for PEDOT:GABA:PEDOT:PSS. Furthermore, cell morphology analysis revealed distinct differences between the sample types. On PEDOT:PBS and PEDOT:GABA surfaces, cells exhibited a well-spread morphology. Meanwhile, on the surface of the PEDOT:GABA:Hydrogel and PEDOT:GABA:PEDOT:PSS, they showed a round shape with a few filopodia.

Conclusion

PEDOT:GABA coated with either PEDOT:PSS or PEDOT:PSS+Alginate conducting hydrogel reduced viability and altered cell morphology, highlighting the impact of surface properties on cell–material interactions. These results suggest that while PEDOT:GABA is a promising platform for neural interfaces, further optimization of protective layers is needed to maintain biocompatibility.

Acknowledgements

The authors would like to acknowledge NCN Sonata Bis 2021/42/E/ST5/00165 for financial support.

D2 – P153

A changing world: Matrix viscoelasticity and degradability synergize to govern stem cell mechanobiology differentially in 3D vs 2D

Luo Z., Pringle E.W., Gourdon D., Gonzalez-Garcia C., Cantini M.
Centre for the Cellular Microenvironment, University of Glasgow, Glasgow, UK

Introduction

Native extracellular matrices (ECMs) are viscoelastic and degradable environments. Cells sense and respond to these biophysical and biochemical cues through mechanotransductive and matrix remodelling processes: an interplay that regulates not only key cellular functions, such as migration and differentiation, but also tissue homeostasis and pathology. While significant progress has been made in understanding these mechanobiological phenomena, several key questions remain unresolved, hindering progress in biomaterial design for regenerative medicine and tissue models. Indeed, the contributions of viscoelasticity and degradability to the modulation of cell mechanobiological behaviours remain unresolved; this is also exacerbated by the complexity of current hydrogel systems. This work aims to engineer a simple polyethylene-glycol (PEG)-based hydrogel platform with tuneable viscoelasticity and degradability, where the interplay between mechanotransduction and ECM remodelling in the mechanobiology of human mesenchymal stem cells (hMSCs) can be comprehensively studied.

Materials and Methods

We engineered and characterised pairs of soft (~1kPa) and rigid (~10 kPa) 2D and 3D PEG-Maleimide hydrogels, each containing an elastic ($\tan\delta \approx 0.1$) and a more viscous counterpart ($\tan\delta \approx 0.15$), functionalised with fibronectin-derived adhesive ligand RGD and crosslinked with matrix metalloproteinases-cleavable peptide VPM or a scrambled counterpart. We then examined hMSCs behaviour through immunofluorescence.

Results

We found that the mechanoresponse of hMSCs to viscoelasticity depends on hydrogel stiffness, dimensionality, and degradability. In 2D environments, viscoelasticity dominated cellular responses, promoting adhesion on soft hydrogels but not inducing YAP nuclear translocation, while hindering mechanotransduction on rigid substrates. Degradability, although promoting spreading on softer surfaces, did not significantly affect YAP mechanoactivation. When cells were encapsulated in 3D matrices, both viscoelasticity and degradability influenced the mechanoresponse. In stiffer environments, degradability was essential for cells to overcome mechanical confinement and enable YAP translocation, whereas viscous cues alone were sufficient to rescue YAP mechanoactivation in softer niches (Fig.1).

Furthermore, we observed a correlation between these mechanotransductive responses and ECM remodelling, as evidenced by deposition and reorganisation of fibronectin and collagen I. Indeed, on 2D substrates early fibronectin remodelling was mainly regulated by viscoelasticity, with fibrils associating with cell spreading and focal adhesion formation. Instead, degradability was essential for fibronectin remodelling within 3D matrices (Fig.2). These early responses governed later ECM remodelling, including collagen I.

Conclusion

We engineered a robust, yet simple, hydrogel platform with tuneable viscoelasticity and degradability, dissecting the roles of these cues in stem cell mechanobiology. These mechanobiological platform will also inform the design of advanced biomaterials and tissue models.




Figure 1: Fluorescent Microscopy Images of hMSCs YAP Localisation on Non-degradable & Degradable PEG-MAL Hydrogels with Different Extents of Viscoelasticity 3 Days After Seeding. Hydrogels were functionalised with RGD. Cell seeding density: 5,000 cells/cm^2 (2D) and 2,000,000 cells/mL (3D). White dotted line indicates the area of nucleus. Scale bar = 50 µm (n = 30).




Figure 2: Fluorescent Microscopy Images of hMSCs Focal Adhesion Formation (Yellow) and ECM Deposition (Magenta) on Non-degradable & Degradable PEG-MAL Hydrogels with Different Extents of Viscoelasticity 3 Days After Seeding. Hydrogels were functionalised with RGD. Cell seeding density: 5,000 cells/cm^2 (2D) and 2,000,000 cells/mL (3D). Scale bar = 50 µm (n = 30).

D2 – P154

Impact of cold atmospheric plasma on cells/bacteria surface interaction for dental abutments using additively manufactured 3Y-TZP

Damghani H.[1], Vettorel A.[1,2], Zayed N.[3], Zhang F.[1,2], Braem A, Teughels W.[3], Van Meerbeek B.[1], Čokić S.M.[1]
[1]Dept. of Oral Health Sciences, BIOMAT & UZ Leuven, KU Leuven; [2]Dept. of Materials Engineering, Surface, and Interface Engineered Materials (SIEM), KU Leuven; [3]Dept. of Oral Health Sciences, Research unit Periodontology and Oral microbiology, KU Leuven, Leuven, Belgium

Introduction

Additive manufacturing of zirconia ceramics shows strong potential in implantology, but its application for dental abutments and its impact on surface properties remain unclear. As abutment surface physicochemical properties are critical for soft-tissue sealing and peri-implant health, cold atmospheric plasma (CAP) has emerged as a promising strategy to enhance wettability and bioactivity of chemically inert zirconia.

Aim

To evaluate the microstructure, surface characteristics, primary human gingival fibroblast (HGF) behaviour, and initial multispecies biofilm attachment of/to 3D-printed and pressed/polished 3Y-TZP before and after CAP treatment.

Materials and Methods

Disks of 3Y-TZP containing 0.25 wt% Al_2O_3 were prepared by (i) UV curing assisted direct ink writing (UVDIW), debinding, and sintering (1450 °C/2 h) and (ii) cold isostatically pressing powder, sintering (1350 °C/2 h), and mirrorpolishing. Subsequently, both groups were treated with argon CAP (80SLM flow rate, 100W). Material characterization included density by Archimedes' method, phase analysis by XRD, elemental composition by XRF, and grain size distribution by SEM. Surface roughness (Sa) was measured by 3D optical profilometry, hydrophilicity by sessile drop method, protein adsorption by bovine serum albumin (BSA) adsorption assay, before and after CAP treatment. HGF viability and morphology were evaluated over 72h using Alamar Blue, live/dead assay, and SEM. Bioreactor-derived multispecies oral biofilms on all groups were quantified after 24h by viability-qPCR.

Results

3D-printed and pressed 3Y-TZP achieved optimal density (6.02±0.16 g/cm3 and 6.07±0.15 g/cm3, respectively), similar chemical composition and grain size (≈0.3 µm). 3D-printed 3Y-TZP showed lower Y_2O_3 content in the tetragonal phase (≈2.6 mol%) and, consequently, lower cubic phase content (≈7.2 wt%) than pressed zirconia (≈2.8 mol% and ≈11.8 wt%, respectively). 3D-printed surfaces exhibited a hierarchical micro/nanotopography with higher roughness (0.39±0.13 µm and 10±0.5 nm, respectively) compared with polished zirconia (2±0.4 nm). CAP treatment did not affect surface roughness in either group but significantly increased hydrophilicity (<12°), resulting in higher BSA adsorption on treated surfaces in both groups. Cell viability exceeded 70% in both non-CAP-treated zirconia groups after 24 and 72h. Fluorescent microscopy and SEM revealed well-spread, strongly adhered HGF with elongated, flattened bodies and long pseudopodia, but no specific orientation on either 3D-printed or pressed/polished 3Y-TZP surfaces was observed. Bacterial attachment did not differ significantly between 3D-printed and polished 3Y-TZP.

Conclusion

3D-printed 3Y-TZP demonstrated suitable physicochemical properties, supported high HGF viability and adhesion, and showed initial bacterial attachment comparable to pressed/polished 3Y-TZP, supporting its potential for dental abutments. CAP treatment further improved surface wettability and BSA adsorption without altering surface roughness.

D2 – P155

Experimental bioactive glass derived from rice husk silica and doped with strontium enhances osteogenic differentiation on titanium

Faria L.V.[1], Lopes M.E.S.[1], Caminaga R.M.S.[2], Fernandes L.[3], Cirelli J.A.[1]
[1]Dept. of Diagnosis and Surgery, School of Dentistry at Araraquara, São Paulo State University (UNESP), Araraquara, São Paulo; [2]Dept. of Pediatric Morphology and Clinical Dentistry, School of Dentistry at Araraquara, São Paulo State University (UNESP), Araraquara; [3]Dept. of Chemistry, Federal University of São Carlos (UFSCar), São Carlos, Brazil

Introduction

Bioactivation of titanium (Ti) surfaces represents a promising strategy to enhance peri-implant bone response, particularly under conditions of compromised bone quality. Bioactive glasses (BG), especially when doped with strontium (Sr), may modulate the cellular microenvironment through ionic release, stimulating osteogenesis while reducing osteoclastic activity, thereby emerging as relevant candidates for bioactive implant coatings. In this context, the present study evaluated the physicochemical modifications and the in vitro osteogenic behavior of Ti surfaces coated with experimental 4S5S bioactive glasses synthesized using silica extracted from rice husk (*Oryza sativa),* with or without Sr doping.

Materials and Methods

Polished Ti discs (G1) and commercially treated discs with double acid-etching (G2; SIN Implant System, Brazil) were used as controls. BG 4S5S (G3) and BG+Sr (G4) coatings were synthesized via a sol–gel process, in which silica derived from rice husk biomass was used as the SiO_2 precursor following controlled thermal treatment and purification steps. The obtained sols were aged, dried, and thermally stabilized before being deposited onto the commercial substrate by ultrasonic spray coating, followed by final heat treatment. Surface characterization included scanning electron microscopy (SEM), energy-dispersive spectroscopy (EDS), and contact angle wettability analysis. The biological response was investigated using MC3T3-E1 pre-osteoblasts through cell viability assays (3, 6, and 9 days), fluorescence-based morphological analysis (24 h), alkaline phosphatase (ALP) activity, and matrix mineralization (21 days). Statistical significance was set at 5%.

Results

SEM demonstrated homogeneous and continuous coating coverage on the treated surfaces. EDS confirmed the incorporation of Si, Ca, Na, and P in the BG groups, with Sr detected exclusively in the BG+Sr group. The coatings significantly reduced the contact angle (~17°) compared to controls (>67°), indicating markedly increased hydrophilicity. No cytotoxic effects were observed in the experimental groups, although metabolic activity was slightly higher in controls at day 9, likely due to greater cellular proliferation. At 21 days, however, the BG and BG+Sr groups exhibited increased ALP activity and enhanced mineral deposition, suggesting an earlier transition from a proliferative phenotype to a more differentiated osteogenic profile.

Conclusion

Ultrasonic spray deposition enabled stable incorporation of experimental bioactive glass coatings onto Ti surfaces, promoting chemical surface modulation and enhanced hydrophilicity. Despite reduced initial proliferation, the bioactive coatings favored greater late-stage osteoblastic differentiation, indicating potential to accelerate bone maturation events at the implant–tissue interface.

Acknowledgements

This research was supported by grant # 2024/16854-3, São Paulo Research Foundation (FAPESP).

D2 – P156

Atmospheric pressure plasma jet polymerized octadiene coatings for infection-resistant biomaterial surfaces

Masood A.[1,2], Borzouyan Dastjerdi M.[1,2], Raghavendra Rao G.[1,2], and Akhavan B.[1,2*]
[1]School of Engineering, College of Engineering, Science and Environment, University of Newcastle, Callaghan; [2]Hunter Medical Research Institute (HMRI), New Lambton Heights, Australia

Introduction

Bacterial colonization of biomaterial surfaces is a major cause of implant-associated infections. These infections often lead to biofilm formation, chronic inflammation, and eventual device failure. Therefore, preventing bacterial adhesion on biomaterial surfaces is essential for improving the safety and longevity of biomedical devices. Antibacterial surface coatings have emerged as an effective strategy to control microbial colonization. Among these approaches, plasma polymerization is particularly attractive because it enables solvent-free deposition of thin films with tunable surface properties.

Materials and Methods

In this study, antibacterial nano-thin coatings were fabricated using atmospheric pressure plasma jet (APPJ) plasma polymerization of octadiene. The APPJ technique enables coating deposition under atmospheric conditions while providing precise control over plasma processing parameters. Therefore, plasma power and treatment time were systematically varied in order to optimize coating properties.

The chemical composition of the coatings was analyzed using Fourier Transform Infrared Spectroscopy (FTIR) and X-ray Photoelectron Spectroscopy (XPS). These analyses confirmed successful plasma polymerization of octadiene on the substrate surface. Subsequently, surface wettability was evaluated using water contact angle (WCA) measurements. Surface free energy (SFE) was also calculated to better understand changes in surface energetics.

Surface morphology and roughness were further investigated using Atomic Force Microscopy (AFM). In addition, coating stability was evaluated by immersing samples in phosphate-buffered saline (PBS) for 1 day, 1 week, and 1 month. After soaking, XPS analysis was performed to examine possible chemical changes in the coating. Finally, antibacterial performance was evaluated against *Escherichia coli* (*E. coli*).

Results

The plasma polymerized surfaces exhibited hydrophobic behavior with water contact angles approaching 90°. Optimization of plasma power and deposition time resulted in the maximum WCA under specific processing conditions. AFM analysis revealed an ultra-smooth and homogeneous coating surface with an average roughness of 0.23 ± 0.02 nm. Furthermore, the deposition process showed stable film growth with a deposition rate of approximately 45 nm/min.

After immersion in PBS for 1 day, 1 week, and 1 month, XPS analysis confirmed that the plasma polymerized octadiene film remained chemically stable. These results demonstrate the durability of the coating under physiologically relevant conditions.

Antibacterial testing showed strong activity against *E. coli*, achieving more than 90% bacterial reduction compared with untreated surfaces. FESEM imaging further revealed severe structural damage and rupture of bacterial cell membranes on the coated surfaces.

Conclusion

APPJ plasma polymerization of octadiene produces smooth, stable, and antibacterial nano-thin coatings with tunable surface properties. Therefore, this approach provides a promising strategy for developing infection-resistant biomaterial surfaces and next-generation antibacterial biomedical devices.

D2 – P157

A tunable 3D polyisocyanide hydrogel model to study matrix-dependent T cell infiltration and tumor killing

A.N.[1], G.S.F[1], C.E.N.[2], I.E.[2], S.R.[1]
[1]Molecular Imaging and Photonics, Dept. of Chemistry, KU Leuven; [2]Laboratory of Metabolic Regulation of Cell Function, Dept. of Cellular and Molecular Medicine, KU Leuven, Belgium

Introduction

Cancer immunotherapy has improved patient outcomes, yet many patients still fail to respond due to suppressive conditions within the tumor microenvironment. Metabolic constraints together with the physical and biochemical properties of the extracellular matrix can limit T cell infiltration, migration, and effector function, reducing therapeutic efficacy. Conventional two-dimensional cultures provide limited physiological relevance, while animal models may not fully capture human tumor–immune interactions and raise ethical concerns. Three-dimensional in vitro systems offer a valuable intermediate; however, widely used natural matrices such as Matrigel show variability and restricted experimental control. Synthetic fibrillar polyisocyanide-based (PIC) hydrogels provide tunable mechanics, defined composition, and reversible gelation, making them attractive for modeling tumor-immune interactions in a controlled and reproducible manner.

Aim

To establish a tunable 3D tumor-immune model to study how matrix mechanics and metabolic conditions shape $CD8^+$ T cell infiltration and activity.

Materials and Methods

PIC hydrogels with different mechanical properties were used to establish a 3D culture system and compared with Matrigel identifying conditions supporting $CD8^+$ T cell motility. Uniform tumor spheroids were generated in agarose micro-molds and embedded in PIC matrices to evaluate spheroid growth, extracellular matrix deposition, and degradation. Antigen-expressing and antigen-negative spheroids were co-cultured with antigen-specific $CD8^+$ T cells to investigate tumor recognition, infiltration, and killing in different matrices. Owing to the thermo-reversible nature of PIC hydrogels, immune cells will be retrieved enzyme-free for downstream metabolic analyses.

Results

Matrix composition influenced $CD8^+$ T cell behavior, with stiffness and pore size determining T-cell motility (Fig.1A). These findings identified mechanical conditions that enable efficient immune cell migration in synthetic fibrillar environments. Tumor spheroids embedded in PIC actively interacted with the surrounding matrix by depositing extracellular matrix proteins, unlike spheroids maintained in suspension (Fig.2A). In co-culture, antigen-specific T cells selectively accumulated around and infiltrated antigen-expressing spheroids, leading to localized tumor cell killing (Fig.2B). This response was absent in antigen-negative spheroids, where T cells remained dispersed and showed no cytotoxic activity. Activated T cells appeared to promote recruitment of neighboring T cells, resulting in a coordinated collective attack. Ongoing analyses examine how these conditions shape the metabolic state of infiltrating T cells.

Conclusion

This work establishes a controllable and retrievable 3D tumor-immune model that captures key physical and biochemical features of the tumor microenvironment. The platform enables investigation of how matrix mechanics and tumor recognition jointly regulate T cell behavior and metabolism, providing a versatile tool for mechanistic studies and immunotherapy development.




Figure 1. Matrix properties regulate T cell motility, recovery, and viability in PIC hydrogels. A. CD8⁺ T cell motility in PIC hydrogels with varying polymer length (1K, 2K) and concentration (1 or 2 mg/mL). Migration distances were normalized to Matrigel (MG), which was set to 100% as the reference condition. B. Retrieval efficiency of T cells from PIC hydrogels compared to cells maintained in solution. C. Viability of T cells following culture in PIC hydrogels. Data are presented as mean ± SD.




Figure 2. Tumor spheroids remodel PIC matrices and are selectively targeted by antigen-specific T cells A. MC38 colorectal cancer spheroids cultured in suspension or embedded in PIC hydrogels and stained for DAPI (nuclei), fibronectin-1, and laminin-β1, demonstrating extracellular matrix deposition in 3D culture. B. Co-culture of CMT93 colorectal tumor spheroids with antigen-specific CD8⁺ T cells in PIC hydrogels. Cancer cells are shown in red and all nuclei in white. Scale bars: white, 100 µm; red, 50 µm.

D2 – P158

Interplay between magnesium and nickel modulates cellular stress and ion accumulation during implant-associated metal exposure

Navrátilová P.[1], Stráníková M.[2], Tesárová, L.[2], Wojtas, D.[1], Válková, L.[1], Vaculovič, T.[2], Pávková Goldbergová, M[1]
[1]Dept. of Pathophysiology, Masaryk University; [2]Dept. of Chemistry, Masaryk University, Brno, Czechia

Introduction

The release of metallic ions from orthopaedic implants represents a persistent source of biologically active degradation products that influence both implant longevity and tissue responses. Nickel (Ni), a minor constituent of cobalt–chromium alloys, can be liberated through tribocorrosion processes and subsequently accumulate in periprosthetic environments[1]. Elevated intracellular Ni^{2+} levels have been associated with oxidative imbalance, impaired cellular function, and adverse tissue reactions[2,3]. Nevertheless, cellular mechanisms capable of modulating Ni^{2+} uptake and limiting its intracellular accumulation remain poorly understood.

This study examined the cellular interaction between nickel and magnesium, testing the hypothesis that magnesium can mitigate Ni-induced cytotoxic effects.

Materials and Methods

Primary human chondrocytes isolated from osteoarthritic cartilage were used as a clinically relevant model of cells potentially exposed to implant-derived metals. Cells were loaded with Ni^{2+} in the presence or absence of magnesium, including pre-exposure conditions. Cellular responses were assessed using viability (MTT) and oxidative stress assays (DCFDA, CellROX™), while particular emphasis was placed on characterising Ni^{2+} uptake dynamics. Intracellular nickel accumulation and spatial distribution were analysed using LA-ICP-MS.

Results

Nickel exposure induced pronounced cellular stress and reduced chondrocyte viability. In contrast, magnesium supplementation attenuated these effects and was consistently associated with lower intracellular Ni^{2+} levels. Elemental imaging revealed distinct differences in Ni^{2+} distribution patterns depending on magnesium availability, indicating that magnesium significantly influences cellular handling and uptake of nickel ions.

Conclusion

These findings demonstrate that magnesium can modulate Ni^{2+} internalisation and mitigate its cytotoxic impact in human chondrocytes. The results point to an underexplored biological mechanism that may contribute to reducing metal ion burden in tissues surrounding orthopaedic implants and may drive future strategies aimed at improving implant biocompatibility and long-term performance.

References

[1]Maceška J., Navrátilová P., Pávková Goldbergová M. Periprosthetic inflammation: from the cellular level to clinical implications. *JBMR Plus* 2025; 9(11).
[2]Navrátilová P., Emmer J., et al. Plastic response of macrophages to metal ions and nanoparticles in time mimicking metal implant body environment. *Environ Sci. Pollut. Res.* 2024; 31; 4111-4129.
[3]Mlinaric M.R., Durgo K., et al. Cytotoxicity and oxidative stress induced by nickel and titanium ions from dental alloys on cells of gastrointestinal tract. *Toxicol. Appl. Pharmacol.* 2019; 383; 114784.

D2 – P159

Effects of HEMA on protein S-glutathionylation in human monocytic cells

Uvsløkk S.[1], Decoster W.[1,2], Brysse P.-J. [1,2], Uhlig S.[1], Jakaviciute R. [1], Samuelsen J.T. [1]
[1]Nordic Institute of Dental Materials, Oslo, Norway; [2]Dept. of Bioanalysis, Faculty of Pharmaceutical Sciences, Ghent University, Ghent, Belgium

Introduction

The methacrylate monomer 2-hydroxyethyl methacrylate (HEMA) is a main component of most dental adhesive systems. Due to incomplete polymerization of such resin-based materials, both dental personnel and patients are exposed to methacrylate monomers. HEMA is known to have toxic effects *in vitro*, but the underlying mechanisms are not fully described. HEMA is shown to spontaneously form an adduct with glutathione (GSH), by reacting with the thiol (-SH) site of cysteine. Since most proteins contain cysteine, it is suggested that HEMA can also interfere with these thiol groups. Specific cysteine residues are also subject to a post-translational modification by GSH (protein S-glutathionylation; PSSG), in which GSH attaches to protein thiol sites and may alter protein conformation. Actin dynamics is known to be partly regulated by PSSG.

Aim

The study aimed to investigate the impact of HEMA on protein S-glutathionylation in the human monocytic cell line (THP-1).

Materials and Methods

The THP-1 cell line was used as a model system to investigate the effects of 2 mM HEMA after short-term (1, 2 and 4 h), and long-term (24 h) exposure. Cells were grown in RPMI-1640 base medium with 1 mM sodium pyruvate, 10 mM HEPES buffer, 55 ug/mL gentamicin, and 5% fetal bovine serum. Cell viability was measured using the MTT assay. Levels of GSH and PSSG were measured using a spectrofluorometric GSH assay and western blotting.

Results

No reduction in cell viability was seen in cells exposed to 2 mM HEMA when compared to control. Levels of GSH and PSSG declined similarly after short-term exposure to HEMA. This may indicate that GSH availability affects glutathionylation levels in the HEMA-exposed cells. After long-term exposure, GSH levels recovered. However, PSSG levels remained low. This may indicate that HEMA reacts with thiol sites in proteins, thereby preventing re-glutathionylation. The most evident protein that was detected by the specific antibody towards glutathionylated proteins showed an SDS-molecular weight of approximately 42 kDa, which aligns with the weight of actin. This indicates that actin glutathionylation, and thereby cytoskeletal dynamics, is affected in HEMA-exposed cells.

Conclusion

This study shows that HEMA-exposure reduces protein S-glutathionylation and indicates that both GSH depletion and competitive binding of HEMA to protein glutathionylation sites are responsible for this effect.

D2 – P160

A biomimetic tissue-engineered 3D model to study osteogenic cell-implant interactions

Liu J.[1], Ioannidis K.[2], Jacobs W.[1], Papantoniou I.[2], Van Meerbeek B.[1], Čokić, S.[1]
[1]Dept. of Oral Health Sciences, BIOMAT & UZ Leuven, KU Leuven; [2]Dept. of Development and Regeneration, Skeletal Biology and Engineering Research Center, KU Leuven, Leuven, Belgium

Introduction

Conventional two-dimensional (2D) cell-culture models fail to reproduce the cell-material interface, critical for successful implant osseointegration. Although 3D *in-vitro* models have emerged as promising alternatives, biomimetic models that recapitulate the osteogenic microenvironment at the implant interface remain limited and urgently needed.

Aim

To develop a biomimetic 3D *in-vitro* model that simulates early phases of osseointegration and enables investigation of skeletal cells-implant surface interactions in 3D context.

Materials and Methods

3Y-TZP powder was uniaxially pressed into discs, sintered (1450°C, 2h), and mirror-polished. Discs were used for 2D-monolayer cell culture or sectioned into sticks for 3D-cell culture. In the 3D model, sticks (1×1×3 mm) were positioned vertically in cylindrical 2% agarose chambers, and human periosteum-derived cells (hPDCs) encapsulated in rat tail type I collagen were cast around the sticks. In the 2D-model, hPDCs were directly seeded on 3Y-TZP discs. Surface roughness was characterized by 3D optical profilometry, wettability by sessile drop method. Cell viability was evaluated by Live/Dead staining and PrestoBlue after 1d of cell proliferation and 21d of osteogenic differentiation. Osteogenic differentiation was assessed by RT-qPCR, while cytoskeletal organization, extracellular matrix (ECM) organization and mineral distribution were analyzed by CLSM, nanoSEM-EDS, and nano-CT.

Results

Both zirconia sticks and discs showed uniform low surface roughness (Sa: 6.6±1.1 nm and 2.2±0.01nm, respectively), and high wettability (≈ 40°). After one day, a robust 3D cellular network in the collagen scaffold with interconnected round-to-elongated cells was observed, while hPDCs on zirconia discs showed typical 2D morphology with well-spread, flattened cells and pseudopodia. High cell viability was observed in both models after 1d and after 21d of osteogenic induction, while metabolic activity was higher in 3D-model at both time points (175% and 164%, respectively). Osteogenic markers (RUNX2, Osterix, ALP, COL1, BSP, and OPN) were upregulated in the 3D model. CLSM demonstrated a more complex and organized cytoskeleton in the 3D-model. Unlike 2D model, nanoSEM-EDX revealed a bone microtissue-like architecture on the zirconia-organoid interface, with hPDCs and ECM organized into clustered mineralized collagen fibrillar networks rich in calcium and phosphorus. Presence of granular mineralized nodules were confirmed by nano-CT.

Conclusion

The 3D peri-implant bone organoid model maintained high cell viability and promoted formation of a mineralized bone microtissue-like interface on zirconia. Compared to 2D-model, it better reproduced early structural and functional features of the bone-implant interface. This biomimetic *in-vitro* platform shows strong potential for advanced analysis of cell-implant interactions from the microtopographic to the whole-implant scale.

D2 – P161

Surface functionalization of mesoporous bioactive glass nanoparticles: modulating protein adsorption and tailoring cell interactions for intracellular ion delivery

Damian-Buda A.-I.[1], Biba S.[1,2], Detsch R.[1], Boccaccini A.R.[1]
[1]Institute of Biomaterials, University of Erlangen-Nuremberg, Erlangen, Germany; [2]Dept. of Information Engineering (DEI), University of Padova, Italy

Introduction

Mesoporous bioactive glass nanoparticles (MBGNs) and biomolecules have emerged as promising solutions for intracellular therapy, owing to their ability to deliver therapeutic ions. However, their intrinsically negative surface charge can reduce the interactions with proteins and the cell membrane, resulting in less efficient cellular uptake. To enhance the intracellular uptake of MBGNs, their surface can be modified with poly(ethyleneimine) (PEI), known for its high density of surface amines and positive charge. Even if PEI is associated with nonspecific protein adsorption and cytotoxicity, these effects may be modulated by controlled acetylation.

Aim

In this context, the aim of this work is to modify the surface of MBGNs with PEI, followed by controlled acetylation with acetic anhydride (AA) and to evaluate the effect of surface chemistry on physicochemical properties, cytocompatibility, and nanoparticle-cell interactions.

Materials and Methods

MBGNs (70%SiO_2-30%CaO (mol%)) were functionalized with PEI (MBGNs+PEI), and AA (MBGNs+PEI+AA). The morphology of the particles was assessed by scanning electron microscopy (SEM), while the particle surface was characterized by Fourier transform infrared spectroscopy (FTIR) and ζ-potential measurements. Protein adsorption was quantified using bovine serum albumin (BSA), and the amide I band in the FTIR spectra was deconvoluted to evaluate secondary structure changes of the adsorbed BSA. Cytocompatibility and nanoparticle–cell interactions were investigated in normal human dermal fibroblasts (NHDFs), using a WST-8 assay, SEM and confocal laser scanning microscopy (CLSM) by staining the cell membrane, nuclei and F-actin.

Results

SEM confirmed that the particles maintained their characteristic spherical and open mesoporous morphology after PEI and PEI+AA modification (Figure 1a). FTIR demonstrated successful PEI coupling and subsequent acetylation, which was supported by the positive ζ-potential for MBGNs+PEI, and the nearly neutral values for MBGNs+PEI+AA. PEI-functionalized MBGNs showed increased BSA adsorption and altered protein secondary structure. More precisely, the content of β-sheet and turn structures increased, while the α-helix content decreased, indicating structural rearrangement of the protein after adsorption on the particles. Cytocompatibility tests revealed a surface-chemistry dependent response: MBGNs were not cytotoxic up to 250 µg/mL, MBGNs+PEI exhibited tenfold higher cytotoxicity (20 µg/mL) and MBGNs+PEI+AA were in the cytocompatibility range even at 1 mg/mL. SEM images of cells exposed to MBGNs revealed particles attached to the cell membrane, interacting with it and partially covered by the plasma membrane (Figure 1b). Among the tested samples, MBGNs+PEI showed stronger membrane attachment and a rougher surface. Further simultaneous staining of the cell nuclei and plasma membrane demonstrated that the particles were present inside the cells, with a tendency to accumulate in the perinuclear region. The F-actin cytoskeleton was not affected by the presence of the particles.




Figure 10. SEM images of the simple and surface-modified MBGNs, together with the SEM images of the cells exposed to 20 µg/mL MBGNs+PEI for 24 h.

Conclusion

The modification of the surface of the MBGNs with PEI and AA did not change the morphology of the particles, but it influenced protein attachment and cell growth. While PEI grafting promotes intracellular delivery, the controlled acetylation mitigates the cytotoxicity associated with PEI and its nonspecific protein interactions, without compromising the cellular internalization. The results of this study are relevant for the design of MBGNs functionalized strategies for target intracellular ion delivery.

D2 – P162

Modulation of glial responses using piezoelectric scaffolds under mechanoelectrical stimulation

Claudino J.[1], Brito-Pereira R.[2,3], Lanceros-Mendez S.[1,3,4], Ribeiro C.[1], Ribeiro S.[1]
[1]CF-UM-UP - Physics Centre of Minho and Porto Universities and LaPMET - Laboratory of Physics for Materials and Emergent Technologies, University of Minho, Braga, Portugal; [2]IB-S – Institute for Research and Innovation on Bio-Sustainability, University of Minho, Campus de Gualtar, Braga, Portugal; [3]BCMaterials, Basque Center for Materials, Applications and Nanostructures, UPV/EHU Science Park, Leioa, Spain; [4]IKERBASQUE, Basque Foundation for Science, Bilbao, Spain

Introduction

Regeneration of the central nervous system remains a major challenge due to the limited regenerative capacity of neural tissues and the complex cellular interactions involved in repair processes[1]. Astrocytes play a key role in regulating neuronal survival, neurite extension and tissue homeostasis, making them important targets for biomaterial-based regenerative strategies[2]. Electroactive biomaterials, particularly piezoelectric polymers, can provide localized bioelectrical cues in response to mechanical stimuli, offering a promising approach to modulate glial cell behavior[3].

Aim

This study investigates how scaffold morphology, surface polarization and biochemical functionalization influence astrocyte behavior under mechanoelectrical stimulation using piezoelectric PVDF substrates.

Materials and Methods

PVDF films and electrospun fibers with different polarization states (non-poled, positively poled and negatively poled) and architectures (aligned and randomly oriented fibers) were produced and characterized by SEM, AFM, FTIR and piezoelectric measurements. Samples were evaluated with and without poly-D-lysine (PDL) coating. Human astrocytes were cultured on the substrates under static and dynamic conditions using a mechanical bioreactor operating at 1 Hz. Cellular responses were assessed through proliferation assays, immunofluorescence analysis of GFAP expression, intracellular calcium measurements, cell cycle analysis by flow cytometry, and gene expression analysis of mechanosensitive pathways (PIEZO1 and CACNA2D1).

Results

Mechanoelectrical stimulation significantly enhanced astrocyte proliferation across most PVDF substrates. Positively poled PVDF under dynamic conditions promoted the highest proliferation and activation levels. Fibrous scaffolds, particularly aligned fibers, supported enhanced cell adhesion and cytoskeletal organization. Intracellular calcium imaging revealed stronger Ca^{2+} responses under dynamic stimulation, especially in polarized substrates. Gene expression analysis further demonstrated modulation of mechanosensitive pathways, with CACNA2D1 upregulation observed in stimulated polarized scaffolds.

Conclusion

These results demonstrate that the combined effects of scaffold morphology, surface polarization and mechanoelectrical stimulation regulate astrocyte activity. Understanding how electroactive biomaterial properties influence glial responses provides important insights for the development of advanced platforms for neural tissue engineering and spinal cord regeneration.

Acknowledgements

This work was supported by Fundação para a Ciência e Tecnologia (FCT, Portugal) through the strategic funding of CF-UM-UP (UID/04650/2025), the Individual Scientific Employment Stimulus programme (2022.02722.CEECIND/CP1718/CT0015 (SR) and 2020.04163.CEECIND/CP1600/CT0019 (CR)), and the FCT project RECONNECT (2024.16188.PEX).

References

[1]Vanni, S., et al. Brain aging: A Ianus-faced player between health and neurodegeneration. *Journal of Neuroscience Research* 2020; 98(2); 299-311.
[2]Couselo, F.L., et al. The Essential Role of Astrocytes in Neurodegeneration and Neuroprotection. *CNS Neurol Disord Drug Targets* 2024; 23(9); 1101-1119.
[3]Pinho, T.S., et al. Enhanced neuronal differentiation by dynamic piezoelectric stimulation. *Journal of Biomedical Materials Research - Part A 2023*; 111(1); 35-44.

D2 – P163

When aligned nanofibers meet thiol plasma polymerization and gelatin immobilization: A synergistic strategy for enhanced endothelial cell function

Zahedifar P.[1], Narimisa M.[1], Morent R.[1], Ghobeira R.[1], Fernández-Colino A.[2], De Geyter N.[1]
[1]Research Unit Plasma Technology (RUPT), Dept. of Applied Physics, Ghent University, Ghent, Belgium; [2]Dept. of Biohybrid & Medical Textiles (BioTex), AME-Institute of Applied Medical Engineering, Helmholtz Institute, RWTH Aachen University, Aachen, Germany

Introduction

Bioengineered vascular grafts are increasingly recognized as viable substitutes for autologous vessels in treating vascular pathologies. Their clinical success, however, hinges on the scaffold's ability to foster a continuous, junctionally connected endothelial cell (EC) monolayer that aligns with the vessel's longitudinal axis, an essential feature for replicating native vascular function. To achieve this, a dual-modality strategy integrating topographical and biochemical cues was employed to engineer a biomimetic scaffold.

Materials and Methods

Electrospun poly(ε-caprolactone) (PCL) nanofibers (NFs) were fabricated in both random and aligned configurations to emulate the extracellular matrix architecture and promote contact-guided cell orientation. The NFs were subsequently functionalized with a thiol-rich coating via plasma polymerization using a dielectric barrier discharge system operating at medium pressure, with 1-propanethiol as the monomer precursor. Although thiol groups are well known for their dual role in facilitating biomolecule immobilization and supporting direct cellular attachment, their introduction via plasma-driven surface modification has been only sparsely investigated in tissue engineering (TE) contexts. To further enhance bioactivity, gelatin was adsorbed post-thiolation, leveraging electrostatic interactions between positively charged gelatin residues ($–NH_3^+$) and surface thiolate. Surface chemical composition and morphology were characterized using X-ray photoelectron spectroscopy and scanning electron microscopy, respectively. For endothelialization studies, primary human umbilical vein endothelial cells (HUVECs) were cultured on the different NF variants, and a series of *in vitro* assays was performed.

Results

Results confirmed the successful deposition of a bioactive thiol-rich layer on the NFs without compromising their structural integrity or porosity, with sulfur content exceeding 10% and C–S bond prevalence above 17%. The coatings exhibited excellent aqueous stability, remaining chemically and structurally stable for over 40 days. Plasma-mediated thiolation markedly improved gelatin adsorption, as evidenced by elevated nitrogen content on treated fibers. Across both random and aligned configurations, thiol-modified surfaces enhanced HUVEC adhesion, viability, and proliferation, with further improvements observed after gelatin adsorption. Microscopic analysis revealed that unmodified NFs supported only limited cell attachment, with cells remaining rounded and poorly spread. In contrast, thiolated NFs facilitated extensive cell spreading, resulting in multidirectional organization on random scaffolds and uniaxial elongation on aligned scaffolds, demonstrating effective contact guidance. Immunostaining for CD31 confirmed the maintenance of endothelial identity, showing continuous intercellular junctions on thiolated NFs. Additional gelatin immobilization led to confluent EC monolayers characterized by cobblestone-like morphology on random NFs and aligned arrangements on oriented NFs, closely replicating native endothelium architecture.

Conclusion

Overall, this study demonstrates that the combined use of fiber alignment, plasma-induced thiol functionalization, and gelatin adsorption synergistically enhances endothelialization, offering a versatile and biomimetic platform for next-generation vascular TE.

Acknowledgements

The authors are thankful to the Research Foundation Flanders (FWO, Belgium) for funding this research (junior research project, G029920N). A.F.C. acknowledges the financial support of the NanoMatFutur Program of the German Ministry of Education and Research (BMBF, grant number 13XP5136).

D2 – P164

Plasma-assisted polymerization and activation route for high-density primary amine functionalization of PCL/PLGA nanofibers in nerve tissue engineering

Aliakbarshirazi S.[1], Ghobeira R.[1], Egghe T.[1], Declercq H.[2], De Geyter N.[1], Morent R.[1]
[1]Research Unit Plasma Technology (RUPT), Dept. of Applied Physics, Faculty of Engineering and Architecture, Ghent University, Ghent; [2]Tissue Engineering Lab, Dept. of Development and Regeneration, Faculty of Medicine, KU Leuven Campus Kulak, Kortrijk, Belgium

Introduction

Surface modification of hydrophobic electrospun nanofibers to introduce stable specific cell-interactive functional groups remains challenging in tissue engineering. This study presents a novel three-step plasma-based approach to create stable, high-density primary amine coatings on PCL/PLGA nanofibers with improved chemical selectivity compared to conventional plasma polymerization.

Materials and Methods

PCL/PLGA nanofibers were fabricated via electrospinning and subsequently functionalized using a three-step surface modification process: (1) hexamethyldisiloxane (HMDSO) plasma polymerization in a medium-pressure dielectric barrier discharge (DBD), (2) helium plasma activation of the deposited coating in a medium-pressure DBD, and (3) grafting of (3-aminopropyl)triethoxysilane (APTES) in ethanol.The resulting scaffolds were characterized in terms of surface chemistry, wettability, morphology, and mechanical properties using X-ray photoelectron spectroscopy (XPS), water contact angle (WCA) measurements, scanning electron microscopy (SEM), and tensile testing.Schwann cells (RT4-D6P2T) were seeded onto the scaffolds, and their viability, proliferation, adhesion, and morphology were assessed after 1, 3, and 5 days using MTT assay, live/dead staining, S100 immunostaining, and SEM.

Results

The optimized process (90 s HMDSO plasma polymerization, 90 s He plasma activation, and 1 h APTES grafting) produced a stable aminated layer with high primary amine density (≈8 % N before washing, stabilizing at 2–3 % N after aqueous incubation). The treatment did not damage the nanofibrous morphology. Schwann cells showed significantly higher metabolic activity and proliferation on the aminated nanofibers (up to 136 % relative to tissue culture plate at day 5) compared to untreated and HMDSO-coated controls. Cells exhibited excellent spreading, bipolar morphology, and formation of a near-confluent layer by day 5, indicating strong bioactivity.

Conclusion

The proposed plasma-assisted polymerization/activation route enables substrate-independent deposition of high-density primary amine coatings on delicate nanofibers while preserving their structure. The resulting scaffolds markedly enhance Schwann cell responses, making them highly promising for peripheral nerve tissue engineering applications.

D2 – P165

Synergistic effect of surfaces functionalized with sulfated chitosan and hyaluronic acid on tumor cell capture and platelet inhibition

Freitas G.P.[1], Baldin E.K.K.[1], Gomes S.D.L.[1], Paglia E.B.[1], Carvalho H.F.[2], Beppu M.M.[1]
[1]School of Chemical Engineering, Universidade Estadual de Campinas (UNICAMP); [2]Instituto Nacional de Ciência e Tecnologia de Fotônica Aplicada à Biologia Celular – INFABIC, Universidade Estadual de Campinas (UNICAMP), Campinas, Brazil

Introduction

Efficient capture of circulating tumor cells (CTCs) can transform cancer detection, diagnosis, and treatment. CTCs, originating from primary or metastatic tumors and present in the bloods, are biomarkers for the diagnosis and monitoring of the disease. However, the selective and specific capture of these rare cells remains technically challenging, limiting the performance of current CTC detection platforms. In blood-interfacing biomaterials, one strategy to preserve functional efficiency involves the incorporation of sulfonated polysaccharides, which reduce nonspecific protein adsorption and platelet adhesion[1]. In this context, we investigated the use of sulfated chitosan (CHI-S)—produced via chitosan (CHI) sulfation—and hyaluronic acid (HA), the principal ligand for the CD44 receptor that is expressed in various tumor cell lines[2]. The combination of these two biopolymers was explored to harness their synergistic physicochemical and biological properties, aiming to develop interfacial coatings capable of promoting selective CTC adhesion while minimizing undesired interactions with blood components.

Materials and Methods

Titanium alloy (Ti6Al4V) substrates were polished using #1200 grit sandpaper, cleaned, and treated with cold plasma. Polyelectrolyte multilayer films composed of chitosan (CHI), sulfated chitosan (CHI-S), and hyaluronic acid (HA) were then deposited by the layer-by-layer assembly, forming 3.5 bilayers with HA as the outermost layer. Sulfated chitosan was synthesized following the method described by Moraes et al. [3]. PC-3 prostate tumor cell adhesion and platelet-poor plasma interactions were assessed by optical microscopy, with quantitative analysis performed using ImageJ software.

Results

Uniform multilayer polyelectrolyte films were successfully deposited on the metallic substrates. As anticipated, PC-3 cell adhesion was markedly higher on coated surfaces compared to uncoated controls, consistent with the known affinity between HA and the CD44 receptor widely expressed in tumor cells. Among the tested coatings, those containing CHI-S exhibited the greatest PC-3 adhesion. Platelet adhesion was significantly reduced on CHI-S-coated substrates, highlighting the contribution of sulfate groups in suppressing interactions with blood components.

Conclusion

The sulfation reaction of chitosan is capable of providing properties relevant for the application of this material with blood components. Multilayer films composed of HA and CHI-S effectively promoted selective tumor cell adhesion while minimizing platelet attachment, demonstrating the synergistic potential of these biopolymers for developing advanced interfaces aimed at circulating tumor cell capture.

Acknowledgements

To the National Institute of Science and Technology on Photonics Applied to Cell Biology (INFABIC). This study was financed by the São Paulo Research Foundation (FAPESP), Brazil. Process Number 2020/12980-3, 2023/01660-6.

References

[1]Lima P.H., et al. Blood protein adsorption on sulfonated chitosan and κ-carrageenan films. *Colloids Surf B Biointerfaces* 2013; 111; 719-725.
[2]Rocha Neto J., et al. Engineering the surface of prostate tumor cells and hyaluronan/chitosan multilayer films to modulate cell-substrate adhesion properties. *Int. J. Biol. Macromol.* 2020; 158; 197-207.
[3]Moraes A.F., et al. Hemocompatibility of 2-N-3, 6-O-sulfated chitosan films. *J. Appl. Polym. Sci.* 2019; 136(9); 47128.

D2 – P166

Simple fabrication method for cancer cell migration studies on biomimetic substrates with tunable stiffness

Portone A.[1,2], Sercia L.[1,2,3], Leporatti S.[1,2], Belli S.[4], Franco P.[4], Stoppelli M.P.[4,5], Gigli G.[1,2,6], Polini A.[1,2], Gervaso F.[1,2]

[1]Institute of Nanotechnology, National Research Council (CNR-NANOTEC), Lecce; [2]Tecnomed Puglia, Technopole for Precision Medicine (Biotech Lecce Hub), Lecce; [3]Dept. di Ingegneria dell'Innovazione, University of Salento, Lecce, Italy; [4]Institute of Genetics and Biophysics "A. Buzzati Traverso" (CNR-IGB), National Research Council, Naples; [5]Dept. Faculty of Medicine and Surgery, UniCamillus-Saint Camillus International University of Health Sciences, Rome; [6]Dept. di Medicina Sperimentale, University of Salento, Lecce, Italy

Introduction

Glioblastoma (GBM) is the most aggressive primary brain tumor, characterized by a highly invasive phenotype that limits the efficacy of current therapies. Tumor recurrence is largely driven by the remarkable ability of GBM cells to migrate and infiltrate surrounding brain tissue. The development of anti-migratory therapies therefore requires reliable in vitro models capable of reproducing key physical cues of the tumor microenvironment. However, many currently available strategies present significant limitations. Traditional two-dimensional cell cultures are widely used but fail to recapitulate the complexity of in vivo tissue architecture, while more advanced systems provide more physiological conditions, but are often technologically complex, limiting their widespread use in high-throughput studies.

Aim

Here we present a simple and reproducible biofabrication strategy for realizing hydrogel-based soft substrates with tunable mechanical properties, i.e., with either controlled uniform stiffness or a stiffness gradient. These substrates are designed to investigate cancer cell migration and to test the performance of anti-migratory drugs.

Materials and Methods

Flat gelatin methacrylate (GelMA) hydrogel substrates were fabricated through a simple and rapid process using different polymer concentrations (5–20% w/v) to obtain tunable stiffness. Hydrogel mechanical properties were characterized by compression tests and atomic force microscopy. Human glioblastoma cells (U87-MG) and astrocytes (SVG-A) were cultured on these substrates. Live-cell imaging and automated tracking protocols were developed and used to quantify cell migration parameters. To demonstrate the potential of the platform for drug screening, a new anti-migratory drug, the cyclopeptide Ala-2/5, was tested.

Results

The developed method enables the production of highly flat, transparent hydrogel substrates with tunable stiffness that span the typical mechanical range of brain tissue. Migration assay revealed that GBM cells migrate faster on stiffer substrates, confirming the key role of matrix mechanical properties in tumor cell motility. When treated with the cyclopeptide Ala-2/5, GBM cells exhibited a significant reduction in migration velocity and travelled distance, whereas non-tumoral astrocytes were less affected. On gradient substrates, both cell types confirmed the anti-migratory effect of Ala-2/5 and exhibited directional migration toward stiffer regions, demonstrating the ability of the platform to reproduce durotactic responses and its suitability for drug testing.

Conclusion

The proposed platform enables quantitative cell migration studies and provides a practical tool for mechanobiology investigations and rapid screening of anti-migratory compounds. This approach offers a versatile strategy for studying invasive cancers and accelerating the discovery of novel therapies.

Acknowledgements

The authors acknowledge the NRRP "Fit4MedRob - Fit for Medical Robotics" Grant (#PNC0000007), and "D34 Health" Grant (#PNC0000001). The study was supported also by the "Tecnopolo per la medicina di precisione" (TecnoMed Puglia) - Regione Puglia DGRn.2117 of 21/11/2018, CUP:B84I18000540002.

D2 – P167

Evaluation of immersion period and current-dependent changes in shear bond strength and fracture surface characteristics of resin-modified glass-ionomer-cement

Kubota M.[1], Wada R.[1], Takegawa E.[2], Horiuchi S.[1], Sekine K.[2], Tanaka E.[1], Hamada K.[2]
[1]Dept. of Orthodontics and Dentofacial Orthopedics, Tokushima Univ.; [2]Dept. of Biomaterials and Bioengineering, Tokushima Univ., Tokushima, Japan

Introduction

Advanced dental cements offer durable bonding, but this strength makes device removal difficult. “Smart” cements are therefore needed that retain clinical strength yet weaken on demand. A resin-modified glass-ionomer cement (RMGIC) with an ionic liquid (IL) has shown reduced bond strength under current application (CA). However, because dental devices remain in the mouth long term, electrolyte exchange with saliva may affect the cement’s conductivity and bonding behavior[1].

Aim

The objective of this research is to evaluate the effect of immersion of RMGIC containing IL in a sodium chloride (NaCl) solution that simulates saliva, on its electric conductivity and bond strength.

Materials and Methods

RMGIC (RelyX™ Luting Plus) was prepared with or without 10 mass% IL (RX10, RX0). Cement was applied to sandblasted titanium plates and pressed at 20 g/mm² for 5 min. Specimens were immersed at 37 °C in 18 µM NaCl solution for up to 6 months. Voltage levels of 0, 2, 6, or 10 V were applied for 300 s, and charge density (Cd) was calculated from the recorded current. Shear bond strength (σ_s) was then measured. Statistical analysis was performed using the Steel–Dwass test ($p < 0.05$) and Weibull analysis. Fracture surfaces were photographed and evaluated following σ_s measurement.

Results

Cd increased with increasing voltage. RX10 maintained stable Cd from 1 to 180 days at 10 V, whereas both RX0 and RX10 showed an initial decrease at 6 V up to 30 days, followed by stabilization (Fig.1). These findings indicate that conductivity can be preserved long term at both 6 V and 10 V. RX0 exhibited significant σ_s reduction at 7 and 180 days under 10 V, while RX10 demonstrated consistent CA-dependent σ_s reduction across all immersion periods (Fig.2). Fracture surfaces showed predominantly anode-side failure, suggesting that electrochemical reactions influenced the debonding mode.

Conclusion

Immersion in a low-concentration NaCl solution preserved the electrical conductivity of IL-containing RMGIC for up to 180 days, enabling stable electro-responsive reductions in shear bond strength. These findings support the long-term potential of IL-modified RMGICs as smart dental cements capable of on-demand debonding in clinically relevant environments.

Acknowledgements

This study was partially supported by JSPS KAKENHI Grant Numbers JP 25K13067.




Fig.1 Effect of immersion period on Cd




Fig.2 Effect of Cd the σ_s of the specimen immersed

References

[1]Matsuki Y., et al. *Dent Mater J* 2022; 41(3) ; 487–494.

D2 – P168

Artificial enamel demineralization assessed by spectroscopic and microscopic methods

Buchwald Z.[1], Ratajczak M.[2], Sandomierski M.[1], Buchwald T.[3]
[1]Institute of Chemical Technology and Engineering, Poznan University of Technology; [2]Institute of Building Engineering, Poznan University of Technology; [3]Institute of Material Research and Quantum Engineering, Poznan University of Technology, Poznań, Poland

Introduction

Artificial enamel provides a standardized and reproducible experimental model, allowing controlled investigation of demineralization processes, material interactions, and physicochemical changes. Unlike natural dental tissues, which vary significantly between donors in terms of composition, structure, and susceptibility to demineralization, artificial enamel enables to systematically study the effects of specific factors under well-defined conditions, facilitating reliable and comparable results. Such models are particularly valuable for testing new restorative materials, protective agents, or analytical techniques without the ethical and logistical limitations associated with human teeth. In studies on novel dental restorative materials with potential remineralizing effects, the heterogeneity of enamel and dentin structure poses an additional challenge in comparing the remineralization potential of individual restoratives. Moreover, there is a lack of literature defining the minimum concentrations and conditions necessary to achieve effective remineralization of these tissues. Raman spectroscopy has been successfully applied in studies of natural dental tissues, including healthy enamel[1], early-stage caries[2], artificial caries[3], as well as in evaluating the effectiveness of products for caries prevention[4].

Aim

The aim of this study is to produce artificial enamel pellets in a reproducible manner and to investigate their demineralization under various conditions, as well as to evaluate the effectiveness of the process using spectroscopic methods, including Raman spectroscopy, and microscopic techniques.

Materials and Methods

Artificial enamel pellets were prepared from commercially available hydroxyapatite with a particle size below 200 nm. A total of 0.4 g of powder was weighed and pressed for 60 seconds under reduced pressure in 13 mm diameter molds. The pellets were then sintered in a furnace at 1250 °C and subjected to demineralization in a solution with pH 4.4, both in the presence and absence of calcium and phosphate ions. After each incubation interval (4 days and repeated cycles), mass loss was measured, and spectroscopic and microscopic analyses were performed.

Results and Conclusions

The applied methodology allows for the production of reproducible artificial enamel pellets, and the obtained results enable tracking the degree of demineralization over successive measurement cycles, providing a valuable model for further research on active dental restorative materials..

Acknowledgements

This work was produced with financial support from the National Science Centre, Poland (Sonata grant no. 2021/43/D/ST5/00888).

References

[1]Buchwald T., Buchwald Z., Daktera-Micker A. The fluorescence background in Raman spectra of sound enamel. *Vibrational Spectroscopy* 2021; 115; 103275.
[2]Buchwald T., Okulus Z., Szybowicz M. Raman spectroscopy as a tool of early dental caries detection – new insights. *Journal of Raman Spectroscopy* 2017; 48; 1–9.
[3]Buchwald T., Buchwald Z. Assessment of the Raman spectroscopy effectiveness in determining the early changes in human enamel caused by artificial caries. *Analyst* 2019; 144; 1409–1419.
[4]Daktera-Micker A., Rzeczkowski M., Buchwald Z., Buchwald T. Raman spectroscopic evaluation of silver diamine fluoride in preventing acid-induced caries progression. *Vibrational Spectroscopy* 2025; 141; 103856.

D2 – P169

Biobased composite microrobots for microplastics removal from aquatic environments

Resina L.[1,2], Fernández A.[1], Sans J.[1,2], Alemán C.[1,2,3], Peréz-Madrigal M.M.[1,2]
[1]IMEM-BRT Group, Dept. d'Enginyeria Química, EEBE, Universitat Politècnica de Catalunya - BarcelonaTech (UPC); [2]Barcelona Research Center in Multiscale Science and Engineering (CCEM), Universitat Politècnica de Catalunya - BarcelonaTech (UPC); [3]Institute For Bioengineering of Catalonia (IBEC), The Barcelona Institute of Science and Technology, Barcelona, Spain

Introduction

The relatively low-cost production of polymers and plastic materials and their features have made them essential elements in our daily activities. However, they have been accumulating in the environment for decades, with being aquatic environments the most polluted. Furthermore, when exposed to weather conditions, natural aging, photo-oxidation, mechanical abrasion, or microbial decomposition, plastic waste breaks down into microplastics (MPs), which are plastic debris smaller than 5 mm, with worldwide impact. Such situation is now regarded as severe and life-threatening. Although currently no single European law covers this issue, efforts are being made by the European Commission since 2019 (i.e. European Green Deal) to address it by including measures to increase the capture of MPs. Hence, the growing concerns about their presence and their potential negative impact on human health urges the need to further explore advanced strategies for the capture, removal and degradation of MPs.

Aim

Engineer 3D-structured and bio-based multilayered composite microrobots designed specifically for MPs mitigation. The envisioned advanced strategy is focused on permanently removing MPs from the environment by degrading MPs efficiently into non-toxic products by merging photocatalysis and electromagnetic properties.

Materials and Methods

A biocompatible ceramic, synthetic hydroxyapatite (HAp), was used to prepare mesoporous microparticles to efficiently anchor magnetic nanoparticles. Moreover, permanently polarized HAp (p-HAp), which exhibits enormous catalytic activity, promoted the photocatalytic activity of MNPs. A biodegradable polymer, polylactic acid (PLA) was used as the microrobots storage.

Results

p-HAp/Fe_3O_4 microrobots were synthesized by sintering and polarization steps, and characterized by Raman spectroscopy, SEM, and other techniques. Photocatalytic degradation assays were performed in MPs commonly found in water (e.g. polypropylene) and the degradation products were analyzed by NMR, confirming the presence of alcohol-based products. Successful incorporation of p-Hap within PLA fiber-scaffold was verified.

Conclusion

A biocompatible ceramic with magnetic nanoparticles microrobot was successfully synthesized and the photocatalytic degradation of MPs was achieved. Therefore, paving the way for the development of microrobots capable of capturing and degrading MPs from aquatic environments.

Acknowledgements

This publication is part of the I+D+i project CNS2023-144422, funded by MICIU/AEI /10.13039/501100011033, and the Maria de Maeztu Units of Excellence Programme CEX2023-001300-M, funded by MCIN/AEI/10.13039/501100011033, and, as appropriate, by “ERDF A way of making Europe” and European Union Next Generation EU. Support for the research of C.A. was also received through the prize “ICREA Academia” for excellence in research funded by the Generalitat de Catalunya.

D2 – P170

Development of fluorapatite-based glass ceramics for bone block grafting

Sharma P.[1,2], Elsharkawy S.[1], Murab S.[2]
[1]Faculty of Dentistry, Oral & Craniofacial Sciences, King's College London, London, UK; [2]School of Biosciences and Bioengineering, Indian Institute of Technology Mandi, Himachal Pradesh, India

Introduction

Dental implants have emerged as the preferred restorative option for tooth loss problems due to their excellent retention, preservation of adjacent teeth, and high masticatory efficiency. Long-term success of dental implants is highly dependent on the availability of adequate bone volume and quality at the implant site. Severe alveolar bone resorption can lead to significant bone thinning and deterioration of the jawbone, compromising the ability of the jawbone to provide sufficient mechanical support and stability for implant placement. Therefore, to enhance jawbone quality and promote bone regeneration in deficient areas, bone block grafts are often employed. After an appropriate healing period that allows graft integration and new bone formation, dental implants can subsequently be placed [1]. Autografts, allografts, and xenografts are widely employed in bone grafting procedures. Among these, autogenous bone grafts are regarded as the gold standard owing to their superior biocompatibility and osteoconductive potential. However, their clinical application is limited by several drawbacks, including donor-site morbidity, limited availability, and significant graft resorption. Furthermore, alternative graft materials such as allografts, xenografts, and synthetic materials present certain limitations, including the risk of immunogenic reactions, limited osteoinductive potential, and mismatched degradation-osteogenesis rates [2]. Apatite-containing glass-ceramics, such as hydroxyapatite and fluorapatite, have been developed for restorative dentistry applications due to their excellent biocompatibility and their ability to promote bone formation *in vivo*. Fluorapatite forms a chemical bond with bone unlike bioinert ceramics, promoting bone formation, enhances compressive strength, and offers tunable properties through controlled crystallization. The present study focuses on the design and development of fluorapatite based glass-ceramics for bone block grafting applications.

Materials and Methods

Fluorapatite-based glass-ceramics were synthesized by casting molten glass into a graphite mould to produce glasses with three distinct Ca/F ratios (FAF3, FAF12, and NF). The synthesized glasses were characterized using DSC to determine T_g and T_p. Subsequently, the glass samples were subjected to controlled heat treatment at predetermined temperatures and durations to transform to glass-ceramic. The phase composition and crystallinity of the glass-ceramic systems were analysed using XRD, while FE-SEM was employed to examine the microstructure. The glass blocks were then milled and sieved to obtain particles within the desired size range of 300–500 µm.

Results

DSC analysis revealed the T_g and T_p of FAF3 (684°C, 978°C), FAF12 (723°C, 990°C), and NF (770°C, 1162°C), respectively, indicating that an increase in fluoride content resulted in a reduction in both T_g and T_p (Fig. 1A). FESEM micrographs of FAF3 revealed a dense structure comprising numerous branched, well-organized elongated nanocrystals. FAF12 exhibited well-developed spherulitic crystals arranged in radial patterns, whereas NF displayed a heterogeneous distribution of fine crystallites (Fig. 1B). XRD spectra of FAF3, FAF12 displayed characteristic peaks of fluorapatite crystals at 25.8° (002) and 32° (211), along with peaks of aluminium phosphate crystals in the cristobalite form at 21.3° (101) and 28.2° (111). Whereas, XRD spectra of NF demonstrated peaks corresponding to aluminium phosphate crystals only. Milling of the glass-ceramic blocks for 45 s and 120 s yielded particles with mean sizes 350.60±11.33µm and 150.41± 2.77µm, respectively (Fig. 1C). Further, these glass-ceramic particles will be evaluated for their antibacterial properties and osteogenic potential.




Figure 1(A). DSC spectra showing the T_g and T_p of FAF3 (684°C, 978°C), FAF12 (723°C, 990°C), and NF (770°C, 1162°C), respectively. (B). FE-SEM micrographs of FAF3 and FAF12 exhibiting dendritic branching patterns characteristic of spherulitic structures, whereas NF showed a heterogeneous distribution of fine crystallites. (C). Digital microscope images and particle size analysis of milled FAF3 particles showing mean particle sizes of 350.60 ± 11.33 µm and 150.41 ± 2.77 µm after milling for 45 s and 120 s, respectively.

References:

[1]Ghodpage P., Suroshe A. Mandibular Block Graft for Localised Ridge Augmentation Followed by Delayed Implant Placement: A Case Report. *Cureus* 2023; Feb 11, 15(2); e34881.

[2]Ferraz M.P. Bone Grafts in Dental Medicine: An Overview of Autografts, Allografts and Synthetic Materials. *Materials (Basel)* 2023; May 31, 16(11); 4117.

D2 – P171

Additive manufacturing and crystallization behavior of nepheline glass-ceramics for dental applications

Alzahrani A.[1], Elsayed H.[2], Colombo P.[2]
[1]Dept. of Basic Medical, Oral and Allied Dental Sciences, College of Dentistry, Taif University, Taif, Saudi Arabia; [2]Dept. di Ingegneria Industriale Università di Padova, Padova, Italy

Introduction

The fabrication of dental glass-ceramics using additive manufacturing remains a significant challenge due to the limited availability of printable glass compositions and the difficulty in controlling crystallization during post-processing. Nepheline-based glass-ceramics are attractive candidates for dental applications because of their favorable thermal expansion, mechanical strength, and chemical durability. However, their use in additive manufacturing has been largely unexplored.

This study introduces a novel approach for the additive manufacturing of nepheline glass-ceramics, enabling the fabrication of complex dental components with controlled microstructure and properties. By developing a printable glass formulation and optimizing the printing and heat-treatment processes, this work aims to bridge the gap between conventional glass-ceramic processing and modern digital dentistry manufacturing techniques. The results are expected to provide new insights into the processing–structure–property relationships of additively manufactured nepheline glass-ceramics and demonstrate their potential as a new class of materials for advanced dental restorations.

Materials and Methods

Novel glass composition based on the Na_2O-CaO-Al_2O_3-SiO_2 system were synthesized using the melt-quench method. Experimental glass were ground into fine powders (D_{50} <25 μm) and then sinter-crystallized to monolithic glass-ceramics using two different methods; a) conversional method and b) Additive Manufacturing method. The developed glass and glass-ceramics were characterized using DSC, Dilatometry, X-ray diffraction, and scanning electron microscopy. This study shows how the nepheline glass-ceramics can be produced in different methods which allow tailoring of the chemical, physical and thermal properties of both the starting glasses and the end glass-ceramics, including their thermal expansions coefficients, glass transition temperatures, softening points, sintering and melting temperatures.

Results

Preliminary results will be presented and discussed in this poster, highlighting the thermal behavior, crystallization characteristics, and microstructural evolution of nepheline-based glass-ceramics produced via conventional processing and additive manufacturing.

Conclusion

The results demonstrate the feasibility of producing nepheline glass-ceramics using different manufacturing routes. The developed glass compositions exhibit suitable thermal and crystallization behavior for controlled sinter-crystallization. Additive manufacturing offers the potential to fabricate complex dental components with tailored microstructures and properties. This approach may provide a promising pathway for the development of next-generation dental glass-ceramic materials compatible with digital dentistry technologies.

D2 – P172

Bioactive characterization of Nb_2O_5 powders obtained at different temperatures

de Almeida E.A.[1], Santo D.E.[2], dos Santos A. R.[3], Peron A.P.[3], Gonzalez R. S.[3], Muniz E.C.[1,4]
[1]Postgraduate Program in Chemistry, State University of Maringá, Maringá; [2]Postgraduate Program in Biological Sciences, State University of Londrina, Londrina; [3]Postgraduate Program in Food Technology, Federal Technological University of Paraná, Campo Mourão; [4]Dept. of Chemical, Federal University of Piauí, Teresina, Brazil.

Introduction

Niobium pentoxide (Nb_2O_5) stands out as a promising material for technological innovation due to its properties that enable applications in different areas. Although there are still few studies investigating its use as a biomaterial, evidence suggests that Nb_2O_5 powders exhibit bioactive and biocompatible characteristics, suggesting potential for applications as a biomaterial.

Aim

Thus, this study aimed to analyze the bioactive properties of Nb_2O_5 particles obtained at different calcination temperatures, with emphasis on antimicrobial activity and toxicity.

Materials and Methods

The particles were synthesized by the Pechini method and calcined at 800, 900, and 1000 °C. For the tests, an aqueous dispersion containing 0.5% Nb_2O_5 powder was prepared and subjected to an ultrasonic bath. Antimicrobial activity was evaluated by determining the Minimum Inhibitory Concentration (MIC) against Escherichia coli (Gram-negative) and Staphylococcus aureus (Gram-positive) bacteria.

Cytogenotoxicity analysis was conducted using the Allium cepa test, employing five bulbs per treatment. After scarification and washing, the bulbs were subjected to Nb_2O_5 dispersion to induce rooting and remained in contact with this solution for five days. For the protective effect assay, the bulbs (already rooted in distilled water) were initially exposed to methylmethanesulfonate (MMS) solutions (10 µg/L) for 24 hours, then transferred to an Nb_2O_5 dispersion for another 24 hours.

The collected roots were fixed in Carnoy's solution for 24 hours, and slides of the meristematic regions were analyzed by optical microscopy at 400× magnification. For the determination of the Mitotic Index (MI), 2.000 cells per bulb were examined, totaling 10.000 cells per treatment. For the evaluation of the Cellular Alteration Index (CAI), 200 cells per bulb were examined, totaling 2.000 cells per treatment. Toxicity data were evaluated using the non-parametric Kruskal-Wallis test ($p \leq 0.05$).

Results

The results demonstrated that the Nb_2O_5 particles did not exhibit antimicrobial activity against the tested bacteria. The MI and CAI values (Table 1) were statistically similar to the control, indicating an absence of cytotoxic and genotoxic effects. In the protective effect assay, a reduction in the frequency of chromosomal alterations was observed, indicating a protective effect of the Nb_2O_5 particles.

Conclusion

The Nb_2O_5 powders show potential for use as a biomaterial, regardless of the calcination temperature. Although they do not exhibit antimicrobial activity, it became clear that these powders do not cause cytotoxic or genotoxic effects and are effective in reducing damaged cells.

Acknowledgements

The authors are grateful to Companhia Brasileira de Metalúrgica e Mineração (CBMM), Brazil, for niobium samples; to COMCAP/UEM, Brazil, for using several characterizing equipment; and to CAPES (Capes-Cofecub program); and to CNPq, Brazil, for financial support.

Table 2. Analysis of the cytotoxic and genotoxic potential of Nb_2O_5 powder in 0.5% aqueous dispersion at temperatures of 800, 900 and 1000 °C.

Nb_2O_5	MI*/SD*** (%)	CAI**/SD* (%)
Control	100	0.20 ± 0.9
Nb_2O_5-800°C	92.6 ± 0.12	0.30 ± 0.9
Nb_2O_5-900°C	79.3 ± 0.9	0.50 ± 0.8
Nb_2O_5-1000°C	85.4 ± 1.1	0.10 ± 0.9

* Mitotic Index
** Cellular Alteration Index
*** Standard deviation (SD)

D2 – P173

Smart implants: Development of bioactive bioglasses with dual antitumor and osteogenic functionality

Mayorga Moreno L.D., Buchner S
LAPMA (Laboratório de Alta Pressão e Materiais Avançados), IF/UFRGS (Institute of Physics/Federal University of Rio Grande do Sul); Porto Alegre-RS, Brazil

Introduction

Cancer with bone metastasis causes pain and fractures. Bioactive glasses doped with therapeutic ions have emerged as promising biomaterials with antitumoral and osteogenic potential[1,2].

Materials and Methods

Ga-doped 45S5 bioglasses were synthesized by melt-quenching (1500 °C) and characterized by DTA, XRD, Raman spectroscopy and Vickers microhardness.

Results

Amorphous bioglasses were obtained. Ga incorporation showed preliminary structural changes in the glass network[3].

Conclusion

Initial results suggest that Ga can modify the properties of bioglass, indicating its potential for bone regeneration and anticancer therapy applications.

Acknowledgements

The authors acknowledge the financial support provided by the CAPES (Funding Code 001), CNPq (grant #404967/2023-0) and FAPERGS (grant #24/2551-0002341-0).

Reference

[1]Kargozar S., Moghanian A., Rashvand A., et al. Nanostructured bioactive glasses: A bird's eye view on cancer therapy. *WIREs Nanomedicine Nanobiotechnology* 2023; 15; e1905.
[2]Souza L., Ferreira F.V., Lopes J.H., et al. Cancer Inhibition and In Vivo Osteointegration and Compatibility of Gallium-Doped Bioactive Glasses for Osteosarcoma Applications. *ACS Appl Mater Interfaces* 2022; 14; 45156–45166.
[3]Xie W., Allioux F.-M., Ou J.Z., et al. Gallium-Based Liquid Metal Particles for Therapeutics. *Trends Biotechnol* 2021; 39; 624–640.

D2 – P174

Structural and biological investigations of manganese-copper/zinc co-doped ternary 58S bioactive glass

Tabia Z.[1], Barroug A.[1,2], Ben Youce H.[3], Noukrati H.[1]
[1]Faculty of Medical Sciences, UM6P Hospitals, University Mohammed VI Polytechnic, Ben Guerir, Morocco; [2]Cadi Ayyad University, Faculty of Sciences Semlalia, Marrakech, Morocco; [3]High Throughput Multidisciplinary Research Laboratory, University Mohammed VI Polytechnic, Ben Guerir, Morocco

Introduction

Implant-associated infections remain a major challenge in bone tissue engineering. Bioactive glasses can address this through their apatite-forming ability and compositional flexibility for incorporating therapeutic ions. While single-ion doping with Mn, Cu, or Zn has shown promising effects, the multifactorial nature of bone healing requires multi-ion strategies exploiting synergistic interactions.

Aim

This work examines whether co-incorporating Mn with Cu or Zn in 58S bioactive glasses yields synergistic antibacterial and antioxidant effects, and how these combinations differ structurally and biologically.

Materials and Methods

Six glass compositions based on the 58S system (SiO_2-CaO-P_2O_5 mol%) containing 5 mol% MnO with 1, 3, or 5 mol% ZnO (MZ series) or CuO (MC series) were synthesized via the sol-gel route. Calcined powders (600 °C) were characterized by XRD, FTIR and Raman spectroscopy. Bioactivity was assessed in SBF over 14 days, with the structural and morphological properties of samples were monitored by XRD, FTIR and SEM. Antioxidant capacity was evaluated through H_2O_2 scavenging over 7 days, and antibacterial activity against *E. coli* and *S. aureus* was tested by plate counting (5-80 $mg \cdot mL^{-1}$).

Results

XRD confirmed a predominantly amorphous structure for all compositions, with minor apatite and calcite peaks particularly in the Cu series. Raman and FTIR spectroscopies revealed surface calcite on all compositions, including MZ1 and MZ3 which appeared fully amorphous by XRD. The Cu series showed calcite intensifying from MC1 to MC5, suggesting minor bulk crystallization. XRD, FTIR and SEM analysis confirmed apatite formation in all compositions after SBF test, with Cu-doped glasses showing enhanced crystallization. The H_2O_2 scavenging assay revealed that Cu co-doping enhanced peroxide decomposition relative to Mn alone, while Zn co-doping slightly reduced it, which is attributed to the concurrent participation of Mn and Cu in Fenton-like redox cycles. Antibacterial testing confirmed that MC glasses were markedly more effective. For *S. aureus*, Cu-containing glasses achieved 78-94% inhibition at 40 $mg.mL^{-1}$, versus 47-69% for MZ glasses at 80 $mg.mL^{-1}$.

Conclusion

These findings demonstrate that Mn-Cu co-doping produces a synergistic enhancement of both antioxidant and antibacterial activity in 58S bioactive glasses, driven by dual Fenton-like redox chemistry. The Mn-Zn combination yields more modest outcomes probably owing to Zn's network-stabilizing effect. This work provides a rational basis for designing multifunctional co-doped bioactive glasses for bone tissue engineering where infection prevention and treatment are critical.

Acknowledgements

This work was supported by the OCP Foundation within the framework of the AS100 project.

D2 – P175

Cobalt-substituted tricalcium phosphate nanostructured coatings for pro-angiogenic and osteointegrative orthopedic applications

Montesissa M.[1], Perut F.[1], Boi M.[1], Rubini K.[2], Boanini E.[2], Baldini N.[1,3]
[1]IRCCS Istituto Ortopedico Rizzoli, Biomedical Science and Technologies and NanoBiotechnologies Lab; [2]University of Bologna, Dept. of Chemistry "Giacomo Ciamician"; [3]University of Bologna, Dept. of Biomedical and Neuromotor Sciences, Bologna, Italy

Introduction

Calcium phosphates-based nanocoatings are used in orthopedics and dentistry, due to their similar chemical composition with the human bone mineral phase. Indeed, CaP nanocoating can improve the osseointegration by fostering host cells colonization, proliferation and differentiation. However, a bone substitute needs to support and favor also vascularization. To this aim the use of trace elements, such as cobalt ions, has been explored as cobalt ions are able to induce hypoxia and stimulate mesenchymal stem cells to produce proangiogenic factors.

Aim

To develop new coatings with angiogenic and osteointegrative properties.

Materials and Methods

Cobalt substituted beta-tricalcium phosphate (Co-TCP) coatings, with different amounts of cobalt ions (0, 2, 5, 10 and 15 wt%), were obtained by Ionized Jet Deposition (IJD).

Morphological (SEM) and physical chemical (XRD, EDS and FT-IR) analyses, wettability and dissolution profile of the realized coatings were analyzed. The influence of different amount of Co ions on film properties was investigated and optimized. Murine fibroblast cells (L929) were challenged in short-term cultures (24-48 hours) with material extracts to test the cytotoxic effects of Co ions released from the coating. Then, adhesion and proliferation of MSC directly seeded on the coatings were analyzed. Moreover, the ability of MSC to secrete VEGF, as a representative pro-angiogenic factor, was evaluated. As VEGF secretion is influenced by HIF-1α factor, its activation in MSC was analyzed by Western blotting.

Results

All the different Co-TCPs materials were deposited with a good level of fidelity in composition transfer from the targets to the coatings, as observed by FT-IR and EDS analyses. All coatings were formed by globular aggregates (diameter around 200nm), with homogeneous and uniform coverage of the substrate surface, without uncoated areas. The films were hydrophilic, with a contact angle around 60° and were stable when soaked in medium up to 7 days. No significant cytotoxic effect was noticed on L929 cells, that proliferated and were metabolically active in the presence of coating extracts. MSC adhered and were able to proliferate from 24h up to 7d, on all coatings. The lower amount of attached cells was observed on 15% Co-TCP coatings, possibly due to the higher amount of Co ions in the coating. VEGF secretion was increased for MSC grown on 5 and 10% Co-TCP coatings, corresponding to HIF-1α factor activation when compared to b-TCP coatings.

Conclusion

Based on these results, the fabrication of Co-TCPs coatings is a solution to improve the vascularization of metallic orthopaedic scaffold through VEGF production for applications in orthopedics and dentistry.

D2 – P176

Interventions to reduce catheter-associated urinary tract infections in primary care settings: A systematic review

Rabi A.[1,2], Ayasreh R.[2], Rabeh M.[2], Alqudah A.[3], McCoy C.P.[2], Parsons C.[2]
[1]School of Pharmacy, Jerash University, Jerash, Jordan; [2]School of Pharmacy, Queen's University Belfast, Belfast, UK; [3]School of Pharmacy, Hashemite University, Zarqa, Jordan

Introduction

Catheter-associated urinary tract infection (CAUTI) is the most common adverse event from urinary catheter use, leading to various clinical complications. Despite being largely preventable, CAUTI significantly impacts patient outcomes, extends hospital stays, and increases morbidity and mortality rates[1]. In the United States (USA), the estimated annual additional costs for treating CAUTI amount to approximately $36 billion[2]. This systematic review aimed to identify interventions specifically designed to reduce CAUTIs within primary care settings and evaluate their effectiveness.

Materials and Methods

Three trial registry and seven electronic databases were systematically searched to identify eligible English language studies from inception until December 2023. To be eligible for inclusion, studies had to be randomised controlled trials (RCTs) or non-randomised studies (NRS), including controlled before-and-after studies and interrupted time-series studies, of interventions reduce CAUTIs in primary care. All outcomes were to be considered. Two reviewers independently screened studies, extracted data, and assessed risk of bias using the Cochrane Risk of Bias tool for RCTs and ROBINS-I tool for NRS. The review adhered to PRISMA guidelines and was registered with PROSPERO (CRD42023474674).

Results

A total of 6027 articles were retrieved through the selected databases and trial registries. After removing duplicates, 5176 articles were screened by titles and abstracts Twenty articles underwent full-text screening, with five RCTs meeting inclusion criteria. Interventions included clean vs. sterile catheterisation techniques, sterile water vs. 0.05% chlorhexidine gluconate solution for periurethral cleansing, targeted infection prevention programs (TIP), self-management education programs, and continuous low-dose antibiotic prophylaxis. Clean technique was as effective as sterile technique while being more cost-effective. TIP significantly reduced CAUTI rates (adjusted hazard ratio 0.54, 95% CI 0.30-0.97) and antibiotic prophylaxis showed a 48% reduction in UTI incidence (incidence rate ratio 0.52, 95% CI 0.44-0.61). However, self-management education showed limited long-term effectiveness. Quality of included studies varied with two low risk of bias, two having some concerns, and one high risk of bias. The heterogeneity of interventions and outcomes precluded meta-analysis.

Conclusion

While some interventions show promise in reducing CAUTI rates, particularly targeted infection prevention programs and antibiotic prophylaxis, the heterogeneity of interventions and limited evidence base highlight the need for further high-quality research. Future studies should prioritize long-term effectiveness and sustainable non-antibiotic strategies for CAUTI prevention in primary care.

References

[1]Hollenbeak C.S., Schilling A.L. The attributable cost of catheter-associated urinary tract infections in the United States: a systematic review. *Am J Infect Contro* 2018; 46(7); 751-757.
[2]Feneley R.C., Hopley I.B., Wells P.N. Urinary catheters: history, current status, adverse events and research agenda. *J Med Eng Technol* 2015; 39(8); 459-470.

D2 – P177

Designing PVA – self-assembling peptide (SAP) composite hydrogels for wound healing applications

Ayimuhan A.[1,2], Miller A.F.[2,3], Saiani A.[1,2]
[1]Division of Pharmacy and Optometry; [2] Manchester Institute of Biotechnology; [3] Dept. of Chemical Engineering, The University of Manchester, UK

Introduction

Chronic wounds are highly susceptible to bacterial infection and mechanical disruption, necessitating dressings that provide antimicrobial protection, structural stability, and therapeutic functionality. In this study we investigate the potential of poly (vinyl alcohol) (PVA) – self-assembling peptide (SAP) composite hydrogels as multifunctional wound dressings. The incorporation of SAPs aimed at providing biological activity and cytocompatibility, while PVA provided mechanical strength and dimensional stability. Through this work we demonstrate that the hydrogels mechanical properties can be tuned through modulation of the polymer and peptide concentrations allowing to tailor the novel hydrogel dressings to diverse wound environments. We also investigate the composite hydrogels potential as a drug delivery platform, allowing controlled release of bioactive agents such as antibiotics[1-2]. These novel biomaterials integrate infection control, physical barrier protection, adjustable mechanics, and therapeutic delivery for advanced wound care applications.

Materials and Methods

The polymer and peptides used in this work were purchased from Biomatik (95% purity; HCL salt) and Tokyo Chemical Industry UK Ltd (M_n ~ 1700; M_W ~ 75 kDa) respectively. The composites were prepared by mixing pre-made PVA and SAP solutions, followed by physical cross-linking via freeze-thawing. PVA was first dissolved in water at 80 – 100 °C and cooled. Peptide solutions were then added at varying ratios. Samples were homogenised through vigorous mixing. The mixture then underwent 3 freezes (–20 °C)-thawing (37 °C/Room temperature) cycles to form the composite hydrogels.

Results

The PVA – SAP samples formed stable and homogeneous composite hydrogels. Transmission electron microscopy (TEM) showed the formation of dense fibrillar networks with uniform morphology. Rheological analysis demonstrated concentration-dependent mechanical properties, indicating tunable stiffness and viscoelastic behavior. Spectroscopic characterization confirmed interactions between PVA chains and SAP fibres. Preliminary evaluations also suggested that the composite hydrogels have antimicrobial properties and can be used for the delivery of therapeutic agents. Overall, the composite system exhibits adaptable mechanical properties and structural stability suitable for wound dressing, providing a versatile platform for further functional development.

Conclusion

PVA - SAP composite hydrogels were developed with tunable mechanical properties and stable, homogeneous network structures. The novel composites are thought to have potential as wound dressing materials and therapeutic delivery. These results highlight the composite hydrogels' adaptability and multifunctionality, providing a promising foundation for advanced wound care applications.

References

[1]Dong S., Chapman S.L., Pluen A., Richardson S.M., Miller A.F., Saiani A. Effect of Peptide–Polymer Host–Guest Electrostatic Interactions on Self-Assembling Peptide Hydrogels Structural and Mechanical Properties and Polymer Diffusivity. *Biomacromolecules* 2024; 25; 3628-3642.
[2]Elsawy M.A., Wychowaniec J.K., Castillo-Diaz L.A., Smith A.M., Miller A.F. A Saiani Controllingdoxorubicin release from peptide hydrogel through fine-tuning drug-peptide fibre interactions. *Biomacromolecules* 2022; 23; 2624-2634.
[3]Hou Y., Tian Y., Tian J., Shi J., Zhao H., Hu J., Zhang Y. Peptide-Based Double-Network Hydrogels for Melanoma Treatment and Wound Healing Promotion. *ACS Applied Materials & Interfaces* 2023; 15; 29927-29938.

D2 – P178

Trimethyl chitosan hydrogels strengthened by multifunctional bimetallic Au/Ag–decorated core-shell polymer particles

Sunintaboon Panya
Dept. of Chemistry, Faculty of Science, Mahidol University, Bangkok, Thailand

Introduction

Polysaccharide-based hydrogels are promising materials for wound healing and cosmetic applications due to their excellent biocompatibility and tunable antioxidant properties[1]. A major challenge in chronic wounds is the excessive accumulation of reactive oxygen species (ROS), which leads to oxidative stress, cellular damage, and prolonged inflammation that impairs tissue regeneration. Trimethyl chitosan (TMC), a quaternized derivative of chitosan, offers important advantages over native chitosan, including improved solubility across a wider pH range and enhanced mucoadhesive properties[2]. These features make TMC particularly suitable for managing ROS-rich wound environments. However, pure TMC hydrogels typically suffer from poor mechanical stability, resulting in premature degradation and inadequate structural support during application. To address this limitation, we developed a reinforced TMC hydrogel system incorporating multifunctional bimetallic Au/Ag–decorated polymer particles as hybrid fillers. These hybrid particles are designed to strengthen the hydrogel network while simultaneously providing radical-scavenging activity to mitigate ROS-induced oxidative stress in dermatological and wound-healing applications.

Materials and Methods

TMC-functionalized core–shell colloidal particles were first synthesized via emulsifier-free emulsion polymerization using a photo-initiating system, as previously reported by our group. The particles, bearing a TMC shell, were subsequently decorated with bimetallic Au/Ag nanoparticles to produce hybrid fillers with different structures, including Au/Ag alloy, Ag-core/Au-shell, and Au-core/Ag-shell nanoparticles. These hybrid fillers were incorporated into a TMC matrix to form hydrogels using a small amount of glutaraldehyde as crosslinker. The presence of Au/Ag nanoparticles was confirmed by UV–Vis spectroscopy, XRD, TEM, and FESEM-EDX analyses. The resulting hydrogels were characterized for porosity, swelling behavior, gel fraction, compressive strength, and antioxidant activity.

Results

The formation of Au/Ag nanoparticles was confirmed using multiple techniques. TEM revealed electron-dense nanoparticles within the hybrid particles, XRD showed characteristic crystalline peaks of metallic Au/Ag, UV–Vis displayed surface plasmon resonance bands, and FESEM–EDX confirmed the elemental presence of Au and Ag. The resulting hydrogels exhibited disconnected porous structures, high gel fractions (90–95%), and substantial swelling capacity (~1600%), indicating stable crosslinked networks. Incorporation of Au/Ag hybrid particles improved compressive strength and provided strong antioxidant activity, with radical-scavenging efficiency reaching approximately 95%, demonstrating enhanced mechanical stability and therapeutic functionality.

Conclusion

Incorporation of the hybrid fillers significantly improves both the mechanical strength and antioxidant activity of the hydrogels, highlighting their potential for wound-healing and cosmetic applications. Future work will focus on improving pore interconnectivity through directional ice-templating and optimized lyophilization techniques to refine the internal architecture**.**

Acknowledgements

his research project has been supported by Mahidol University (Fundamental Fund: fiscal year 2025 by National Science Research and Innovation Fund (NSRF), Grant Number FF-077/2568).

References

[1]Cui R., Zhang Y., Li Y., Li Y., Yang X., Feng R., Bai X., Han J. Polysaccharide-based hydrogels for wound dressing: Design considerations and clinical applications. *Frontiers in Bioengineering and Biotechnology* 2022; 10; 845735.
[2]Thanou M., Verhoef J.C., Junginger H.E. Trimethyl chitosan and its applications in drug delivery. *Journal of Materials Science: Materials in Medicine* 2009**;** 20; 1057–1079.
[3]Lekjinda K., Sunintaboon P. Green synthesis of quaternized chitosan nanogel using emulsion-photopolymerization as redox-responsive drug carrier. *Carbohydrate Polymers* 2023; 304; 120495.

D2 – P179
Composite power: The uniqueness of hydrotalcite and biodegradable polymers

Soyhan I., Lei Li L., van Rijn P.
The Personalized Medicine Research Institute (PRECISION) for Biomaterials and Biomedical Technology, University of Groningen/University Medical Center Groningen, Groningen, The Netherlands

Introduction

Biomaterials are essential in medical applications, and biodegradable polymers including PLA are widely used in various fields due to their strength, biocompatibility, and biodegradability, along with the ease of processing it as a thermoplastic [1].

PLA degrades primarily through hydrolysis of its ester bonds, producing lactic acid (LA) which further accelerates polymer degradation via autocatalysis caused by acidosis [2]. Resulting acidic environment, can compromise bone regeneration, and lead to mechanical failure of the implant.

This study explores the use of carbonated and sodium stearate (SS) coated layered double hydroxide (LDH) fillers to mitigate these effects. LDHs, with their exchangeable anions, have acid-scavenging properties that can neutralize the acidic environment, while, the SS coating can help the homogenous particle distribution in polymer matrix. Their layered structure can also enhance the mechanical properties of PLA [3]. LDHs have already been successfully used as fillers in other polymers, making them promising candidates for improving PLA-based implants by preventing acidosis, and maintain the implant's mechanical stability throughout healing.

Materials and Method

To investigate the project's objective, we utilized poly(D,L-lactide-co-glycolide) (PLGA), an amorphous PLA-based copolymer that offers greater control over its properties. The degradation of PDLG-LDH composites with three different fillers concentration (3, 6, and 9% LDH), studied in physiologically relevant conditions using a phosphate-buffered saline (PBS) system at pH 7.4 at 37°C over the course of 6 weeks.

Results

The addition of LDH showed effective retention of mass decrease, pH control and preserving structural integrity during polymer degradation. Moreover, presence of LDH helps composites to maintain the mechanical properties as acidosis increase polymer hydrolysis speed.




Figure 1. Mass change of PDLG-LDH composites in the course of 6 weeks.

Conclusion

This approach proves that addition of LDH to PLA matrix can be possible solution for implant failures caused by acidosis without drastically affecting the mechanical properties.

Keywords: Polylactic acid (PLA), Biodegradation, Layered-Double Hydroxide (LDH) , Acid Scavenging

Reference

[1]Ebrahimi F., Ramezani D.H. *International Journal of Polymeric Materials and Polymeric Biomaterials* 2022; 71(15); 1117-1130.
[2]Lyu S., Untereker D. *International journal of molecular sciences* 2009; 10(9); 4033-4065.
[3]Tichit D., Álvarez M.G. *ChemEngineering* 2022; 6(4); 45.

D2 – P180

Fluorinated MOF-801: An active additive for dental resin-based composites

Buchwald Z.[1], Domke A.[1], Jakubowski M.[1,2], Orłowska A.[3], Sandomierski M.[1]
[1]Institute of Chemical Technology and Engineering, Poznan University of Technology, Poznań; [2]Institute of Mechanical Technology, Poznan University of Technology, Poznań; [3]Dept. of Biomaterials and Medical Device Engineering, Silesian University of Technology, Zabrze, Poland

Introduction

MOF-801 is a zirconium-based metal-organic framework built from Zr6 clusters bridged by fumarate linkers, forming a robust three-dimensional microporous network[1]. This structure exhibits high surface area and stability in aqueous environments, which has made it a model material in adsorption and separation research[2]. In particular, MOF-801 has been investigated for its ability to interact with fluoride ions via anion exchange with hydroxyl groups on the zirconium nodes, resulting in efficient fluoride uptake from aqueous solutions, and underscoring its potential as a functional additive in materials that release or capture biologically relevant anions[1,2]. Recent advances in dental materials research have begun to explore the potential of metal–organic frameworks (MOFs) as functional components in restorative and adhesive dentistry. For example, a nano-structured zirconium-based MOF, post-functionalized with methacrylate groups, was incorporated into an experimental resin-based dental composite and shown to improve key physical and mechanical properties such as flexural strength and elastic modulus, while reducing water sorption and solubility compared with traditional fillers. This suggests that MOF-based additives may act as innovative, coupling-agent-free fillers in dental composites[3]. In addition to composite fillers, strontium-based MOFs (Sr-MOFs) with fumarate ligands have been investigated as bioactive nanofillers in dental adhesive systems. Incorporation of a small fraction of these Sr-MOFs into adhesive formulations significantly enhanced micro-tensile bond strength to dentin and promoted mineral deposition at the adhesive interface, indicating their potential to support durable bonding and remineralization in restorative applications[4].

Aim

The aim of this study was to use fluorinated MOF-801 as an active additive to a silica filler in dental composites and to compare the basic physicochemical properties of the resulting materials.

Materials and Methods

MOF-801 was first synthesized and subsequently subjected to fluorination. The fluorinated powder was characterized and used as an active additive, partially replacing the silica filler in a light-curable resin-based composite. The basic physicochemical properties of the obtained composites were then evaluated.

Results and Conclusions

Fluorinated MOF-801 exhibited an active influence on composite performance, as demonstrated by fluoride ion release and by the dependence of selected physicochemical properties on the content of this active component.

Acknowledgements

This work was produced with financial support from the National Science Centre, Poland (Sonata grant no. 2021/43/D/ST5/00888).

References

[1]Tan T.L., Krusnamurthy P.A., Nakajima H., Rashid S.A. Adsorptive, kinetics and regeneration studies of fluoride removal from water using zirconium-based metal organic frameworks. *RSC Advances* 2020; 10; 18740–18752.
[2]Li Y., Wang X., Metal-organic framework-801 for efficient removal of fluoride from water. *Microporous and Mesoporous Materials* 2018; 259; 163–170.
[3]Shekofteh K., Jafarzadeh Kashi T., Behroozibakhsh M., Sadr A., Najafi F., Bagheri H. Evaluation of physical/mechanical properties of an experimental dental composite modified with a zirconium-based metal-organic framework (MOF) as an innovative dental filler. *Dental Materials* 2023; 39; 790–799.
[4]Matphang S., Aueboonprasert N., Rattanakam R., Teanchai C., Sinthuvanich C., Attarataya J., Sonthisathaporn M., Akkarachaneeyakorn K. Multifunctional strontium-MOFs-based dental adhesive: Innovation for enhanced bonding performance and bioactivity. *International Journal of Adhesion and Adhesives* 2026; 144; 104189.

D2 – P181

Multi-functional biocomposite thin film based on CO_2-derived and natural biopolymers for wound healing applications

Morris E., Tran T.N.
School of Biological and Chemical Sciences, University of Galway, Galway, Ireland

Introduction

Biodegradable poly(propylene carbonate) (PPC) is an ideal material for biomedical applications, degrading to non-toxic compounds such as water and CO_2.[1] However, PPC films are known for having poor mechanical strength and poor miscibility with other polymers. To subdue these drawbacks and synthesize a homogenous film, we combined the PPC with natural biopolymers such as gelatin and alginate. Gelatin, a biocompatible biopolymer has applications in the biomedical and pharmaceutical industries.[2] Alginates also show biocompatibility and are used to treat highly exudative wounds.[3] Propyl gallate, a synthetic antioxidant, was added to produce active biocomposites with antioxidant features to accelerate wound healing. Propyl gallate can promote wound healing through collagen fibre formation and reduction of oxidative stress.[4]

Materials and Methods


Novel PPC/Gelatin, and PPC/Alginate biocomposite films were prepared by combining pre-dissolved solutions of PPC, gelatin and alginate. These mixtures were then cast into Teflon molds and placed in a fume hood for solvent evaporation. The free-standing films were analysed using FTIR, SEM and mechanical testing. The mechanical testing was carried out by using Zwick Uniaxial using a 10kN load cell in a dog-bone shape with crosshead speed of 50 mm min^{-1}. Release studies of the propyl gallate films were carried out using UV-Vis at 275 nm. The antioxidant capacity was conducted using a $DPPH^{\bullet}$ free radical assay on UV-Vis. The active biocomposites biocompatibility was examined using the cell viability assay Alamar Blue.

Results

The resulting biocomposites found on SEM, produce flat homogeneous films with low biopolymer content, although, it shows some unevenness increasing the biopolymer content. FTIR shows evidence of bond formation between PPC and the biopolymer showing shifts in certain bands. Mechanical properties show addition of biopolymer offers reinforcement effects for the robust biocomposites. Biocomposites were shown to have better water vapour permeability than human skin which would allow exudate to escape. The developed materials are highly biocompatible. Propyl gallate showed sustained release over 72 hours, with highest release being found with increased biopolymer content. The antioxidant capacity shows high free radical scavenging.

Conclusion

In this study, homogeneous and free-standing PPC/gelatin and PPC/alginate biocomposites were successfully developed. The developed biocomposite featured good homogeneity, high antioxidant activity and biocompatibility which is advantageous for wound healing applications.



References

[1]Pasini C., Pandini S., Milocco F., Chen J., Tang Z., Pescarmona P.P., Sartore L. CO2-Based Polypropylene Carbonates with High-Stretch and Self-Healing Properties. *International Journal of Molecular Sciences* 2025; *26* (8); 3878.
[2]Xu X., Xi Y., Weng Y. Gelatin-based materials: fabrication, properties and applications in the food packaging system. *RSC advances* 2025; *15* (37); 30605-30621.
[3]Dong S., Li Y., Zhu K., Wang C., Zhai S. Advances in structure designing and function tailoring strategy toward alginate-based hydrogels for efficient water remediation: A review. *International Journal of Biological Macromolecules* 2025; 304; 140801. DOI: https://doi.org/10.1016/j.ijbiomac.2025.140801.
[4]Zhang X., Cui J., Liu L., Sun J., Fan B., Wang F., Lu C. Propyl Gallate Attenuates Cognitive Deficits Induced by Chronic Sleep Deprivation Through Nrf2 Activation and NF-κB Inhibition. *Antioxidants* 2026; *15* (1); 79.

D2 – P183

Study of mechanical properties of nanocellulose-CNT-metal sulfide (CuS, CoS, NiS) composites

Mrityunjoy M.[1,*], Senapati S.[1], Aunggat S.[1], Singh Parihar V.[2], Kanta Layek R.[3]
[1]Dept. of Basic and Social Sciences, School of Technology, North-Eastern Hill University, Shillong, India; [2]Biomaterials and Tissue Engineering Group, Faculty of Medicine and Health Technology, Tampere University, Tampere, Finland; [3]Dept. of Separation Science, School of Engineering Science, LUT University, Lahti, Finland

Introduction

Nanostructured hybrid composites based on nanofibrillated cellulose (NFC) and carbon nanotubes (CNTs) have emerged as promising materials for various applications such as packaging, flexible electronics, supercapacitor etc. due to their advantages of sustainability, high mechanical strength, and electrical conductivity.

Aim

The aim of this study is to evaluate the mechanical performance of NFC and different metal sulfide based CNT hybride fillers i.e. CNT-MS (NiS, CuS, CoS) and their dispersion, interfacial bonding, and structure–property relationships.

Materials and Methods

The NFC is derived from pulp and paper industry waste, which is purchased one. CNT is prepared using NiO catalyst and using plastic waste as carbon source using lab developed pyrolysis reactor. The metal sulfides (NiS, CuS, CoS) have been directly grown on the CNTs. The obtained CNT-MS hybride filler have been dispersed in the NFC matrix using probe sonication for 30 min. The composite films are prepared by vaccum filtration technique and hot pressed. The mechanical properties of the composite films were measured by Universal testing machine (UTM).

Results

The study reveals that NFC–CNT-MS composites show improved mechanical performance at 10 wt% loading of the filler. The synergistic effect of NFC and CNTs and proper dispersion, may be responsible for effective stress transfer and achieving higher tensile strength.




Fig. 1. Tensile strength of NFC-CNT-MS (NiS, CuS, CoS) composites.

Conclusion

NFC–CNT-MS (NiS, CuS, CoS) composites hold significant potential as sustainable, high-performance materials for mechanical, electrical and thermal applications. The future research should focus on ideveloping scalable fabrication methods to enable their use in real-world engineering applications.

Acknowledgments

Authors thank their respective Institutes for basic resources.

References

[1]Senapati S., Shah A., Patra P.K., Mahato M.* Measurement of elastic modulus of CNT composites: a nondestructive study. *Fullerenes, Nanotubes and Carbon Nanostructures* 2022; 3(2); 290-296.

[2]Senapati S., Anwar S., Singh Parihar V., Patra P.K., Mahato M.* Sustainable carbon-metal oxide composites from waste sources: synthesis, characterization, and mechanical properties. *RSC Applied Interfaces* 2025.

D2 – P184

Green synthesis of covalently bonded polypyrrole/cellulose nanofiber composites

Muchová M.[1*], Vícha J.[1], Martínková M.[1], Plachý T.[1], Hanulíková B.[1], Humpolíček P.[1,2]
[1]Centre of Polymer Systems, Tomas Bata University in Zlin; [2]Faculty of Technology, Tomas Bata University in Zlin, Zlin, Czech Republic

Introduction

Polypyrrole (PPy) is a widely studied conductive polymer for biomedical applications due to its conductivity and biocompatibility[1,2]. However, conventional conductive PPy composites often suffer from poor matrix adhesion and gradual delamination. Electrostatic strategies used to improve adhesion may weaken in polar environments with high ionic strength, such as biological systems, whereas covalent bonding is typically achieved through complex procedures, toxic chemicals, or specialized linkers, which limit environmental compatibility and biomedical applicability[3]. Here, we present a green, aqueous-phase route to prepare covalently bonded PPy/cellulose nanofiber composites (CNF-DAC-PPy) with good biocompatibility. This approach is based on the spontaneous aldol condensation between pyrrole and aldehyde groups of periodate-oxidized cellulose nanofibers (CNF-DAC), enabling direct pyrrole anchoring without toxic linkers. During subsequent *in situ* polymerization, these anchored pyrrole units are incorporated into growing PPy chains. Final composites showed improved durability and improved stability through covalent anchoring, making them promising for biomedical applications and wearable electronics.

Materials and Methods

The composites were prepared by oxidation of cellulose nanofibers (CNF) to dialdehyde cellulose nanofibers (CNF-DAC), followed by spontaneous aldol condensation with pyrrole and subsequent *in situ* $FeCl_3$-initiated polymerization. Morphology was characterized by scanning electron microscopy (SEM). Bulk electrical conductivity was determined using the van der Pauw method. The effect of modification on fatigue limit was studied using dynamic mechanical analysis (DMA). Cytocompatibility was assessed by direct contact with HaCaT keratinocytes according to ISO 10993-5.

Results

SEM revealed that the CNF nanofibrous structure was preserved after the oxidation (DO =10%). After *in situ* PPy polymerization, PPy grains were formed on the surface of the nanofibers, with higher pyrrole loading resulting in a thicker and more continuous coating. The composites exhibited bulk electrical conductivities ranging from 0.046 to 1.155 S/cm depending on pyrrole loading and composite composition. Covalent anchoring enhances mechanical durability under mechanical stress and improves electrical stability. Cytotoxicity testing confirmed full cytocompatibility of all PPy-containing composites, while the cytotoxicity associated with reactive aldehyde groups in the CNF-DAC intermediate was eliminated after PPy deposition.

Conclusion

The presented green PPy/cellulose nanofiber composites prepared via an aldol condensation strategy exhibit good electrical conductivity and cytocompatibility, while covalent anchoring improves mechanical durability and electrical stability. These properties make CNF-DAC-PPy composites promising candidates for wearable electronics, biosensors, and tissue engineering.

Acknowledgements

The work was supported within the Czech Science Foundation GAČR 24-11534S

References

[1]Káčerová S., Víchová Z., Valášková K., Vícha J., Münster L., Kašpárková V., Vašíček O., Humpolíček P., *Colloids Surf. B Biointerfaces*, 2023; 232; 113605.
[2]Huang Z.-B., Yin G.-F., Liao X.-M., Gu J.-W. *Front. Mater. Sci.* 2014; 8; 39–45.
[3]Park Y., Jung J., Chang M., *Appl. Sci.* 2019; 9; 1070.

D2 – P185

Incorporation of metal nanoparticles in polymers: Surface wettability and biocompatibility

Schultz S.[1], Markhoff J.[1], Emmert S.[2], Bader R.[3], Grabow N.[1], Eickner T.[1]
[1]Institute for Biomedical Engineering, Rostock University Medical Center; [2]Dept. of Dermatology and Venereology, Rostock University Medical Center; [3]Dept. of Orthopedics, Rostock University Medical Center, Rostock, Germany

Introduction

Silver and copper represent important metals for biomedicial application. Their antibacterial and antimicrobial properties can be broadly exploited, particularly in dermatology and gynaecology.[1] Incorporating metal nanoparticles into a polymer matrix allows for a continuous release of the metal ions, largely avoiding a so-called 'burst release'.

Aim

Incorporating metal nanoparticles into a polymer matrix using a solvent-based process, investigating contact angle before and after UV irradiation and biocompatibility.

Materials and Methods

Poly(L-lactic acid) (PLLA) films containing 5 wt% silver or copper nanoparticles (AgNPs/CuNPs) were produced by dip coating. Contact angle measurements were performed on pure PLLA and AgNP/CuNP-loaded PLLA films using the sessile drop method with a DSA 25 Drop Shape Analyzer (KRÜSS GmbH, Hamburg, Germany), using ultrapure water and diiodomethane as test liquids. For each material, n = 8 measurements were performed. Half of the samples were previously irradiated with UV light for 2 x 15 minutes. Biocompatibility tests were performed in direct contact (samples Ø = 6 mm) with the murine L929 fibroblast cell line according to DIN EN ISO 10993-5 for n = 1 with 4 replicates, respectively.

Results

Incorporation of AgNP (87.5° ± 6.2°/ 45.7° ± 3.8°) or CuNP (86.0° ± 4.0°/ 43.0° ± 1.9°) led to a reduction in contact angle compared to pure PLLA (96.5° ± 3.3°/ 57.9° ± 3.4°) for both test liquids (water/ diiodomethane). UV irradiation caused a further reduction in contact angle in AgNP-loaded samples (77.9° ± 2.6°/ 42.5° ± 3.0°) and pure PLLA (91.4° ± 5.3°/ 52.7° ± 3.0°) samples. For CuNP-loaded samples (80.7° ± 4.9°/47.6° ± 1.7°), UV irradiation led to a slight increase in contact angle for diiodomethane. In biocompatibility tests, incorporating AgNP (68.0% ± 6.0%) or CuNP (78.7% ± 11.4%) shows a decreasing trend in relative metabolic cell activity when compared to pure PLLA (97.4% ± 6.5%) samples.

Conclusion

Incorporation of AgNPs and CuNPs tends to increase the surface wettability of dip-coated PLLA samples. This effect is enhanced by UV irradiation. Controlled release behaviour of AgNPs and CuNPs from dip-coated PLLA samples will subsequently be analyzed.

Acknowledgements

Financial support by the German Research Foundation (DFG) within the RTG 2901/1 SYLOBIO (project number: 501988175) is gratefully acknowledged.

References

[1]Ghazzy A., Naik R.R., Shakya A.K. Metal–Polymer Nanocomposites: A Promising Approach to Antibacterial Materials. *Polymers* 2023; 15 (9); 2167.

D2 – P186

Engineering superior bioimplant coatings by electrophoretic deposition of $Eu_2O_3/CeO_2/TiO_2$ composites: Fabrication and characterization

Korothum Kandiyil A.[1], Uthirapathy V.[2]
[1]Dept. of Chemistry, Vellore Institute of Technology; [2]Dept. of Chemistry, Vellore Institute of Technology, Vellore, India

Introduction

Rutile TiO_2 has emerged as a preferable material in biomedical domain due to its bioinertness, biocompatibility and cytocompatibility. CeO_2 and Eu_2O_3 were reinforced into TiO_2 to confer favourable biological responses. CeO_2 has dual functionality of both antibacterial and antioxidant benefits, due to the unique redox couple. Eu_2O_3 has osteogenic, angiogenic and bioimaging characteristics. In addition, we incorporate chitosan, a bioactive polymer to improve the osseointegration behaviour. Therefore, a single composite coating system combining these constituents are fabricated by electrophoretic deposition over Ti-6Al-4V alloy and anticipated to deliver exceptional multifunctional benefits and to be a potent orthopedic implant coating.

Aim

We fabricate a composite coating of $Eu_2O_3/CeO_2/TiO_2$ over Ti-6Al-4V substrate to yield a potent orthopedic implant coating with beneficial antibacterial and antioxidant responses, with efficient cytocompatibility, angiogenesis and bioimaging benefits.

Materials and Methods

Rutile TiO_2 is prepared by sol-gel method using titanium tetraisopropoxide, glacial acetic acid, ethanol and distilled water in a molar ratio of 1: 15: 4: 150 respectively. Stoichiometric amount of Ceric Ammonium nitrate is added to the sol to obtain CeO_2/TiO_2. Eu_2O_3 is further incorporated using wet impregnation method. The obtained composite is suspended in isopropanol with a bath concentration of 3g/100ml and 0.5wt% chitosan added as a binder. The anode is stainless steel electrode and the Ti-6Al-4V is in the cathode, placed 1cm apart to undergo cathodic deposition at applied voltage and time parameters.

Results

The applied voltage and process time are optimized to be 40V and 3.5 minutes to achieve coatings of desirable thickness and surface roughness. SEM, AFM and digital microscopy confirm the formation of suitable morphology, with a consistent peak-to-valley topography, contributing to enhanced mechanical anchorage with early protein adhesion and subsequent osseointegration. Vickers Hardness test and scratch test were employed to evaluate the mechanical behaviour and the results signified the coating integrity and adhesion strength, with adequate coating-substrate bonding, ensuring least delamination and reduced debris formation. The coatings are also studied for biological responses including antibacterial activity displaying activity slightly higher against S. aureus than E. coli. The cytocompatibility upto 200µg/ml along with AO/EB fluorescence staining assay portrays the fair ability of the coating to enact as a potent bioimplant coating.

Conclusion

$Eu_2O_3/CeO_2/TiO_2$ coating is fabricated over Ti-6Al-4V using cathodic electrophoretic deposition. The fabricated coatings deliver potent antioxidant and cytocompatible materials with fair structural integrity demonstrating the relevance and potential of composite coatings offering a valuable advancement in orthopedics.

Acknowledgements

The authors thank the facility of Vellore Institute of Technology, Vellore, India for providing adequate research facility and financial help for our study.

References

[1]Anavadya K.K., Vijayalakshmi U. Insights Into the Microstructure and Coating Integrity of TiO2 Coatings on Conventional and Laser Shock Peened Ti-6Al-4V Alloy. *Journal of Materials Research and Technology* 2026; 42; 5121-5138.
[2]Han X., Ma J., Tian A., Wang Y., Li Y., Dong B., Tong X., Ma, X. Surface modification techniques of titanium and titanium alloys for biomedical orthopaedics applications: A review. Colloids and Surfaces B: *Biointerfaces* 2023; 227; 113339.
[3]Wennerberg A., Albrektsson T. Effects of titanium surface topography on bone integration: a systematic review. *Clinical oral implants research* 2009; 20; 172-184.

D2 – P187

Mechanical properties and antibacterial activity of novel bioactive dental restoratives

Peltola T.[1], Loimaranta V.[2], Vähäsalo L.[3], Kontturi E.[4], Lassila L.[5], Säilynoja E.[1,5]
[1]Research Development and Production Dept., Stick Tech Ltd – a GC Europe AG Company, Turku; [2]Institute of Dentistry, University of Turku, Turku; [3]CH-Bioforce Oy, Raisio, Finland; [4]Aalto-University, Espoo; [5]Dept. of Biomaterials Science and Turku Clinical Biomaterial Center (TCBC), Institute of Dentistry, University of Turku, Turku, Finland

Introduction

Antibacterial properties and capacity for biomineralization play an important role in novel restorative materials in dentistry. Recently, lot of attention has been paid on antibacterial properties of lignin or chitin in the food, cosmetics, and health industry because of the possible biocompatibility of natural lignin and chitin [1]. However, organic antibacterial agents or ion releasing materials can have negative effects on restorative materials' mechanical properties. The aim of this study was to evaluate the flexural strength, modulus, and antibacterial effects of experimental fiber-reinforced bioactive flowable composite resin (Bio-SFRC [2]).

Materials and Methods

Studied experimental dental materials were Bio-SFRC and Bio-SFRC containing 2% antibacterial agents: lignin (CH-Bioforce Ltd), chitin (Aalto-University), bioactive glass (BAG, <45 µm) (Bonalive Ltd) and chlorhexidine (CHX) (Sigma-Aldrich).

The flexural strength and modulus were measured using universal testing machine Lloyd LRX Plus (Lloyd Instruments Ltd, UK). Antibacterial effects were tested in direct contact test using cariogenic *Streptococcus mutans* as a model bacterium. Pre-made bacterial suspension was dispensed on top of the materials. The suspension was covered with an inert polyester membrane (Mylar™) to prevent evaporation and to increase the contact surface between bacteria and materials. As a negative control, bacteria were incubated between two polystyrene membranes while Bio-SFRC dipped in 2% CHX served as a positive control. After four hours of contact the bacteria were recovered from the surface and cultured on agar plates. Six separate samples were analyzed from each material.

Results

The flexural strength and modulus (figure 1) were almost the same for all Bio-SFRC materials. In the antibacterial test significantly less bacteria were recovered from Bio-SFRC supplemented with 2% chitin, 2% lignin and 2% CHX than from Bio-SFRC control (table 1). However, the difference between Bio-SFRC and Bio-SFRC supplemented with 2% chitin was only marginal, and no significant difference was found between inert Mylar™ control and Bio-SFRC supplemented with 2% chitin.

Conclusion

Experimental Bio-SFRC material supplemented with 2% lignin suggests the potential antibacterial activity. However, optimization is still needed to find the most effective concentration of the antibacterial agent, so that the mechanical properties do not decrease, and the color shade of the final material is acceptable for dental use.

Acknowledgements

This work is a part of the Business Finland project (Co-innovation project IMD1 11/31/2023).




Figure 1. Flexural strength and modulus of experimental Bio-SFRC materials containing antibacterial agents.

Table 1. Recovered bacteria after four-hour contact with materials.

Sample	Mean (logCFU/ml)	SD	t-test sample vs Bio-SFRC
Bio-SFRC	6.72	0.09	
+2% chitin	6.61	0.06	0.035
+2% lignin	6.16	0.18	0.000
+2% BAG	6.71	0.25	0.921
+2% CHX	5.57	0.32	0.000
Mylar control	6.59	0.11	0.063
CHX (control)	0.00	0.00	0.000

References

[1]Benhabiles M.S., Salah R., Lounici H., Drouiche N., Goosen M.F.A., Mameri N. Antibacterial activity of chitin, chitosan and its oligomers prepared from shrimp shell waste. *Food Hydrocolloids* 2012; 29; 48-56.
[2]Garoushi S., Peltola T., Siekkinen M., Hupa L., Vallittu P.K., Lassila L., Säilynoja E. Retention of strength and ion release of some restorative materials. *Odontology* 2025; 113(2); 714-723.

D2 – P188

Computationally driven design of electroactive electrospun fibers for wound healing: from *in silico* modeling to experimental validation

Tommasini A.[1,2], Gallucci S.[1], Pollini M.[3], Ruggeri M[3], Giberti H.[4], Sandri G.[3], Ravazzani P.[1], Parazzini M.[1], Suarato G.[1]

[1]Cnr-Istituto di Elettronica e di Ingegneria dell'Informazione e delle Telecomunicazioni, Milano; [2]Politecnico di Milano, Milano; [3]Dept. of Drug Sciences, University of Pavia, Pavia; [4]Dept. of Electrical, Computer and Biomedical Engineering, University of Pavia, Pavia, Italy

Introduction

Chronic skin wound has been considered a serious worldwide health concern affecting millions globally. These types of lesions impair epithelium integrity and compromise the physiological tissue electric field, forming endogenous electrical currents produced by the potential difference between the wound center and its edges. The healing process can be greatly influenced by this electric potential. Electric fields (EF) can influence cell responses, directing collagen deposition and vascularization. Moreover, smart conductive wound patches have been developed to promote synergistic effects with EF, providing support for cell growth, and accelerating the healing [1]. Herein, the behavior of conductive biodegradable electrospun fibers composed of poly-caprolactone and zein (PCLZ) and coated with polypyrrole (PPy-PCLZ) have been investigated, when electrically stimulated, using a finite element simulation platform.

Materials and Methods

The software Sim4Life (https://sim4life.swiss/) was employed to computationally solve the bioelectromagnetic problem. The Small Male Rat V1.0 from the VirtualZoo Phantom Library was imported in the simulation platform, and 3 circular wounds (r=2mm) were created in different positions of the animal's back from the skin and connective tissue domains by means of Boolean operations, to recapitulate *in silico* the skin lesion, exposing the muscle tissue (Figure1). ECG-type electrodes were designed and properly curved to adhere to the back of the model animal and set at +/- 0.5 V. Simulations considering scaffold-based treatments and saline solution as control were carried out using the Low Frequency electro-quasi-static approximation. Wounds treated with electrospun scaffolds were compared to the use of saline solution as control. The electrical conductivities of the scaffolds were experimentally measured, while tissue electrical properties were assigned using the materials database integrated in Sim4Life for the low-frequency regime [2] (Figure1). Simulation outputs were processed via MATLAB (R2024b) and analyzed with OriginPro2023.





Figure 1: In-silico modelling and voxelization workflow: (i) Configuration of the animal model (Small Male Rat V1.0), including a multilayer wound, and positioning of the electroconductive scaffold, which is stimulated by a potential difference of ±0.5 V. (ii) Voxelization of the model for computational analysis, including an anatomical cross-section and a table of electrical conductivities (σ) assigned to biological tissues and polymeric materials (PCLZ and PCLZ-PPy).

Results

The model surface projection of Figure 2a shows the correct activation of the electrodes: each pair consists of dark blue (anode, -0.5V) and bright yellow (cathode, +0.5V) electrodes. For all the three wound locations and scaffolds application, the PCLZ-PPy current density distributions are shifted towards higher values than PCLZ ones, confirming that charges can move more easily in the more conductive material (Figure 2b). An analysis of the current density propagation in the biological surrounding of interest was conducted (Figure 2c), highlighting how the resulting distributions are dependent from the electrical properties of each tissue.



(b)

PCLZ	Mean	Median	95th perc	99th perc
bottom scaffold	0,62	0,55	1,15	1,57
middle scaffold	0,68	0,64	1,20	1,57
top scaffold	0,56	0,50	0,97	1,39
PCLZ-PPy				
bottom scaffold	1,32	1,20	2,32	3,03
middle scaffold	1,51	1,45	2,53	3,14
top scaffold	1,26	1,17	2,00	2,89




Figure 2: (a) Small Male Rat V1.0 from the Sim4Life ViZoo library used for the simulations: 3 wounds were created and electrodes were placed near each wound, which were covered with either PCLZ scaffold, PCLZ-PPy scaffold or saline solution as control; (b) Current Density statistical values of median, mean, 99th percentiles and 95th developed within the entire scaffolds volumes; (c) box plots and the values of median, mean, 1st – 99th percentiles, and 5th– 95th developed in the tissues of interest within a volume of 6x6x1.5 mm3 around the wounds.

Conclusion

The enhancement of current density and a directional tissue remodeling in support of a physiological skin wound healing have been experimentally demonstrated via electrical stimulation. Increasing electric field values and endogenous currents trigger cellular signalling pathways which act as a 'kick-start' for the healing process. Our *in-silico* assessment revealed that conductive, biocompatible scaffolds modulate current density distribution, enabling controlled electrical cues at the scaffold–tissue interface. Such digital twin-based strategy is essential to predict a new material behavior and to define safe operational ranges, to reduce animal use.

Acknowledgement

The authors wish to thank ZMT Zurich MedTech AG (www.zmt.swiss) for providing the simulation software Sim4Life.

References

[1]Pollini M., Ruggeri M., Bianchi E., Vigani B., Boselli C., Icaro Cornaglia A., Giulietti N., Giberti H., Rossi S., Sandri G. Smart conductive nanofibers integrating electrical stimulation for enhanced fibroblast alignment and collagen deposition in chronic wound repair. *Results in Engineering* 2026.
[2]Gabriel C. Compilation of the dielectric properties of body tissues at rf and microwave frequencies. 1996.

D2 – P189

Wall shear stress-constrained multiphysics design optimization of poroelastic bone scaffolds: A coupled darcy–solid mechanics approach

Sahin, M.[1], Tabak, A.F.[2], Kiziltas Sendur, G.[3,4]
[1]Biomedical Engineering, TOBB University of Economics and Technology, Ankara; [2]Mechatronics Engineering, Istanbul Ticaret Üniversitesi, Istanbul; [3]Faculty of Engineering, Mechatronics Engineering, Sabancı University, Istanbul; [4]Sabancı University Nanotechnology Research and Application Center, Istanbul, Turkey

Introduction

Bone scaffolds have been emerged as pivotal biomaterial candidates for the treatment of critical-sized bone defects. A central challenge in scaffold engineering is determining an optimal geometry that promotes robust tissue regeneration while balancing competing mechanical, biological, and transport functionalities. To manage this complexity, computational modeling has emerged as a key tool for optimizing scaffold architectures. However, maintaining a balance between fluid-induced stimuli and structural stability continues to require sophisticated multiphysics design frameworks.

Aim

This study introduces an integrated framework for pore-size optimization in bone scaffold design, bridging the gap between mechanobiology-driven tissue differentiation and MSC diffusion. Moving beyond conventional optimization strategies that rely on mechanobiological stimuli, our approach incorporates a multiphysics poroelastic model that explicitly accounts for the influence of wall shear stress (WSS) on cellular behavior, treating it as a critical design constraint.

Materials and Methods

To simulate the mechanical environment of bone fracture healing, scaffolds were subjected to fully coupled compressive loading and fluid flow governed by Darcy's law. The resulting fluid–solid interactions were modeled using poroelastic theory, where differentiated tissues (fibrous tissue, cartilage, and bone) were represented as poroelastic materials. The optimization framework was developed by coupling COMSOL Multiphysics with MATLAB to determine optimal pore sizes. The objective was to maximize bone formation under pore volume constraints, while simultaneously maintaining WSS values—calculated following the formulation by Guyot et al. (2016)—within physiological safety limits. Tissue differentiation was predicted via a mechanobiological stimulus defined as a linear function of octahedral shear strain and local fluid velocity.

Results

Obtaining the mechanobiology maps and spatial tissue distributions in the scaffold pore domain (Figure 1) for different cases, computational simulations demonstrate the critical influence of pore size on tissue differentiation, emphasizing the inherent trade-offs between mechanobiological stimuli, cellular diffusion, and WSS constraints. To evaluate manufacturability and validate the proposed framework, polylactic acid (PLA) scaffolds were fabricated via fused deposition modeling (FDM). Subsequent compression tests demonstrated that the experimental mechanical response was in high correspondence with the predicted displacement profiles, thereby supporting the reliability of the multiphysics model.

Conclusion

The developed optimization framework underscores the pivotal role of pore size in modulating mechanobiological stimuli and guiding tissue differentiation. By integrating the diffusion of MSCs and WSS constraints with mechanobiology, the model provides a promising computational tool for the rational design of bone scaffolds. With further calibration of biological parameters, the framework has a potential to be extended to guide the design of scaffold architectures for complex bone defects.




Figure 1. Predicted spatial distribution of differentiated tissues within the porous bone scaffold (left). The mechanobiology map (right) illustrates the classification of each mesh node in the porous domain according to the mechanobiological stimulus defined by local fluid velocity magnitude and octahedral shear strain.

References

[1]Guyot Y., Papantoniou I., Luyten F.P., Geris, L. Coupling curvature-dependent and shear stress-stimulated neotissue growth in dynamic bioreactor cultures: a 3D computational model of a complete scaffold. *Biomechanics and modeling in mechanobiology* 2016; 15(1); 169-180.

D2 – P190

Asymmetric crack opening: A COP-based method to estimate local mode I stress intensity factors

Allahdiniyan A.[1], Maggie L.[2], Taylor D.[2], Hoey D.[2], Vergani L.[1], Buccino F.[1]
[1]Dept. of Mechanical Engineering, Politecnico di Milano, Milan, Italy; [2]Dept. of Mechanical, Manufacturing and Biomedical Engineering, Trinity College Dublin, Dublin, Ireland

Introduction

Cracks interacting with free edges, other cracks or material interfaces are common in biomaterial devices and tissues such as trabecular bone. In such asymmetric configurations, the two crack tips experience different loading conditions, making classical stress-based approaches difficult to apply without detailed finite element modelling and precise knowledge of boundary conditions. Here we propose an alternative based on our novel approach which uses the crack opening profile (COP).

Aim

Develop COP-based formulation to independently determine mode I stress intensity factors (K_A and K_B) at each tip in asymmetric crack configurations.

Materials and Methods

2D plane-stress finite element models (ABAQUS) simulated three asymmetric cases: crack–edge, crack–crack and crack–interface geometries, spanning wide ranges of geometric and stiffness ratios. A new COP expression (Fig 1b) was derived by generalising Westergaard's centre-crack solution to include independent K_A and K_B while preserving the correct square-root behaviour near each tip (Fig. 1b). The proposed formulation was calibrated by least-squares fitting to numerical crack opening profiles and validated against J-integral stress intensity factors and, where available, handbook solutions. Practical use was demonstrated using PMMA plates in which the COP was determined by stereo digital image correlation (DIC).

Results

In a parametric FE study, COP-derived K_A and K_B reproduced J-integral and handbook values with errors of 2–5% for most crack–edge and crack–crack configurations, with higher deviations only in strongly interacting configurations. The two-parameter formulation captured the increasing skewness of the COP as cracks approached free edges, neighbouring cracks or compliant–stiff interfaces (R^2>0.96).In PMMA experiments, COP-based SIFs scaled linearly with nominal stress and aligned with theoretical trends within a few percent, despite measurement noise and slot-root blunting.




Figure 11-(a) Asymmetric crack opening profile with different SIF at each tip. (b) COP formulation δT(x). (c) DIC-measured COPs for a crack near a free edge in a PMMA by DIC with fits for various a/b ratios.

Conclusion

This asymmetric COP framework provides a straightforward, displacement-based approach to estimate local mode I SIFs at individual crack tips, bypassing complex stress analysis. It holds strong potential, for example, for bone toughness assessment, where heterogeneous material properties, intricate geometries, and uncertain *in vivo* loads hinder conventional methods.

Acknowledgements
Supported by the European Commission under Marie Skłodowska-Curie grant No 101120290 (GAP project).

References
[1]Westergaard H.M. *J Appl Mech* 1939; 6; 49–53.
[2]Allahdiniyan A., Taylor D. *Theor Appl Fract Mech* 2025; 138; 104940.

D2 – P191

Biomechanical high-fidelity framework for assessing slip risk in polyurethane-based footwear treads

Gupta S.[1], Chanda A.[2]
[1]School of Engineering and Materials Science, Queen Mary University of London, London, UK; [2]Centre for Biomedical Engineering, Indian Institute of Technology Delhi, India

Introduction

Traumatic injuries such as fractures, ligament tears, dislocations, and muscle strains are common outcomes of slip and fall incidents. These accidents frequently occur in workplaces, recreational areas, industrial settings, and during everyday activities. Previous studies indicate that a sudden reduction in friction at the shoe floor interface is a major cause of unintended slips. Additional contributing factors include the presence of surface contaminants such as water or oil, smooth flooring materials, and the gradual wear of footwear tread patterns. Therefore, evaluating the frictional performance of footwear along with other influencing factors is essential to ensure adequate shoe floor traction and reduce slip related injuries.

Aim

To evaluate the slip risk of different footwear tread patterns using a combined computational and biofidelic robotic testing framework under realistic loading conditions.

Materials and Methods

In this study, an explicit dynamics based computational model was combined with a custom developed biofidelic robotic device designed to measure slip risk. Five different footwear tread patterns, developed using liquid Polyurethane, were evaluated. The lower limb of the Toyota's Total Human Model for Safety (THUMS) was used to generate realistic loading conditions on the tread patterns during slipping on a rough flooring surface. The same Polyurethane-based tread patterns were also experimentally tested using the robotic device to measure their frictional performance under controlled conditions.

Results

The computational simulations and experimental tests provided comparable insights into the slip performance of the tread patterns. The results demonstrated that the computational model was capable of predicting slip risk under water contaminated flooring conditions.

Conclusion

The cost effective methodology and findings of this study contribute to improving the understanding of traction behavior across different tread designs. The combined computational and experimental approach provides a useful framework for evaluating footwear traction and supports future efforts aimed at reducing slip and fall incidents.

Acknowledgements

This work received no external funding.

D2 – P192

Morphology-dependent stiffness–density scaling in healthy, osteoporotic and post-COVID trabecular bone: An image-based finite element study

Ateeq M., Allahdiniyan A., Buccino F.,Vergani L.M.
Dept. of Mechanical Engineering, Politecnico di Milano, Milan, Italy

Introduction

Bone fragility reflects changes in both bone mass and trabecular architecture, with stiffness scaling with bone volume fraction and structural organization. Osteoporosis reduces transverse trabeculae and promotes bending of slender struts, while SARS-CoV-2 infection may also affect bone remodelling and microarchitecture [1]. Here, we compared healthy, osteoporotic, and post-COVID femoral head trabecular bone using image-based finite element analysis and a stiffness–density power law.

Materials and Methods

Trabecular cores were extracted from human femoral heads and assigned to healthy, osteoporotic, and post-COVID groups according to clinical records and DXA diagnosis. Each core was tested in stepwise displacement controlled micro-compression device installed at the Elettra synchrotron [2], with intermittent µCT scans at selected displacement levels. Reconstructed scans were Gaussian filtered, thresholder and morphologically processed, then segmented in 3D Slicer to obtain trabecular regions of interest (ROIs); representative ROIs for each group are shown in Fig. 1 (a). ROIs were meshed with C3D8 elements and analysed in Abaqus under boundary conditions matching the experiments, providing apparent stiffness at reaction forces comparable to the experimental results. Bone volume fraction (BV/TV) was computed for each ROI, and normalized stiffness values were related to BV/TV by group wise power law fits; Fig. 1(b) displays the obtained relationship curves between young's modulus and BV/TV for the healthy bone samples.

Results

Fig. 1 (a) illustrates distinct architectures: healthy bone with thick, well-connected plates; osteoporotic bone with perforated, slender trabeculae and loss of cross links; post-COVID bone with irregular, disorganized structure. Finite element apparent stiffness agreed with experimental values in the elastic regime, enabling robust stiffness with BV/TV relations for healthy bone samples (Fig. 1(b)). Osteoporotic specimens showed the highest exponent and largest scaling factor, consistent with a bending-dominated network that stiffens rapidly only at higher BV/TV. Healthy specimens exhibited a lower exponent and smaller scaling factor, indicating a more stretch-dominated, plate-like architecture that uses bone volume efficiently. Post-COVID specimens had lowest exponent and an almost linear stiffness–BV/TV trend, suggesting reduced mechanical benefit per unit bone volume and a distinct, mechanically inefficient regime compared with both healthy and osteoporotic bone.




Fig.1. (a) Comparative trabecular architecture of healthy, osteoporotic, and COVID-19 bone samples, (b) Relationship between the BV/TV and young's modulus for the healthy samples.

Conclusion

The stiffness–density exponent links BV/TV to deformation mode across healthy, osteoporotic, and post-COVID trabecular bone. Healthy bone is more stretch-dominated, osteoporotic bone more bending-dominated, and post-COVID bone shows intermediate, less efficient scaling due to architectural disorder. These findings suggest that stiffness–density metrics and trabecular orientation, together with BV/TV, may improve fracture risk assessment.

Acknowledgements
This research was conducted as part of the GAP Project and was supported by European Commission under the Marie Skłodowska-Curie grant agreement No 101120290 (GAP). The authors are grateful for the financial support and resources that have enabled the progress of this research.

References
[1]Adami G., Saag K.G. Osteoporosis and COVID-19: Detected similarities in bone involvement and potential long-term consequences. *J Clin Med* 2023; 12.
[2]Clementini L., Buccino F., Palazzetti R., Longo E., Kudrna Prasek M., Banfi G., Qin Z., Vergani L.M. Multifunctional in situ imaging of biological materials under load: a synchrotron-based platform for large-scale image-guided failure analysis. *Mater-Des* 2025.

D2 – P193

Comparative assessment of failure modeling approaches for trabecular structures

Piacentini M.[1], Skallerud B.[2], Gao C.[1]
[1]Dept. of Mechanical and Industrial Engineering, Norwegian University of Science and Technology; [2]Dept. of Structural Engineering, Norwegian University of Science and Technology, Trondheim, Norway

Introduction

Trabecular bone failure plays a central role in osteoporotic fractures. High-resolution micro-computed tomography (micro-CT) enables detailed characterization of trabecular microarchitecture and has motivated microstructural finite element simulations. Nevertheless, failure in trabecular networks is a complex process in which individual trabeculae undergo localized deformation, damage accumulation, and eventually rupture at multiple locations within the network. Predicting this behavior numerically remains challenging due to the geometric complexity of trabecular structures and the computational cost associated with high-resolution three-dimensional (3D) models. In addition, the suitability of different failure modeling approaches for trabecular microstructures remains unclear. Although some studies have applied specific failure formulations, systematic comparisons within a common benchmark are lacking.

Aim

This study aims to identify suitable failure modeling approaches and meshing strategies for 3D finite element simulations of representative trabecular structures and to compare their performance in terms of mechanical response and computational cost.

Materials and Methods

Four failure modeling paradigms are briefly reviewed and compared: cohesive zone models (CZM), continuum damage mechanics (CDM), the extended finite element method (XFEM), and phase-field fracture (PFF). These approaches are discussed with respect to their compatibility with complex trabecular geometries, their ability to represent crack initiation and propagation, computational efficiency, and practical implementation. In parallel, meshing strategies for trabecular-like structures are investigated. Voxel-based discretizations are compared with alternative geometry-processing approaches aimed at reducing model complexity while preserving key structural features. Finally, selected failure formulations are calibrated to be comparable and quantitatively evaluated on identical representative structures and meshes, to the extent permitted by their respective formulations.

Results

Literature observations suggest trade-offs between modeling flexibility and computational cost. PFF models allow general crack initiation and propagation but can be computationally demanding. In XFEM, the treatment of multiple crack nucleation events in complex networks requires careful implementation, and the admissible crack morphologies are restricted. CZM impose stronger constraints because potential crack surfaces must typically be defined in advance. CDM offers comparatively efficient implementations but requires appropriate regularization to avoid mesh-dependent localization. Numerical comparisons on the same representative trabecular structures—a systematic comparison largely absent from recent literature on bone failure—illustrate differences in damage patterns, numerical stability, and computational cost between modeling approaches.

Conclusion

This work provides a systematic assessment of failure modeling and meshing strategies for simulations of trabecular structures, with the aim of identifying approaches that enable computationally feasible 3D simulations while preserving the key structural characteristics of trabecular microarchitectures.

Acknowledgements

The authors acknowledge the support from MSCA DN GAP project (No. 101120290).

D2 – P194

In-silico informed design of a high-throughput microfludic platform through hydraulic resistance equalization

De Giorgi A.[1], Corallo G.[1], Corbezzolo N.[1], Gigli G.[1 2], Polini A.[1], Gervaso F.[1]
[1]Institute of Nanotechnology, National Research Council (CNR-NANOTEC), c/o Campus Ecotekne; [2]University of Salento, Dipartimento di Medicina Sperimentale, c/o Campus Ecotekne, Lecce, Italy

Introduction

Microfluidic platforms enable precise control of fluid transport at the microscale and are widely used in chemical analysis, biosensing, and biological experimentation. In high-throughput microfluidic systems, however, ensuring uniform flow distribution across multiple parallel channels remains a major challenge. Even minor fabrication imperfections introduced during rapid prototyping processes—such as channel narrowing, partial occlusions, or vertical deformation—can alter hydraulic resistance and generate significant flow imbalances. Computational modeling provides a powerful tool to address this issue by enabling the rational design and optimization of microfluidic architectures prior to fabrication. In this work, an in-silico design strategy is applied to develop a multi-channel microfluidic platform capable of maintaining uniform flow distribution despite fabrication-induced defects.

Materials and Methods

Two microfluidic configurations were designed using Rhinoceros 3D: a baseline network without equalization elements and an optimized architecture incorporating serpentine channels to homogenize hydraulic resistance across eight parallel branches. Representative fabrication defects were introduced in both designs, including partial channel occlusions, lateral dimensional variations, and vertical deformation caused by roof sagging (Figure1a,b and c). The geometries were imported into COMSOL Multiphysics where steady-state laminar flow simulations were performed using finite element methods (Figure 1d and e). An inlet flow rate of 800 µL h^{-1} was imposed to ideally obtain 100 µL h^{-1} per outlet while all outlets were set to zero-gauge pressure. Flow uniformity was evaluated by comparing outlet flow rates across the eight branches.

Results

The baseline configuration exhibited pronounced heterogeneity in outlet flow distribution, with deviations exceeding ±30% from the expected flow rate in certain branches (Figure 2a). The largest imbalance occurred in branches affected by vertical geometric deformation, confirming that variations in channel height strongly influence hydraulic resistance due to its cubic dependence on channel dimensions in rectangular microchannels. The introduction of serpentine channels significantly improved flow uniformity by introducing distributed hydraulic resistance that balanced pressure across the network (Figure 2b). As a result, outlet flow rates became substantially more homogeneous across the eight wells. Experimental validation was performed by fabricating the optimized device via DLP 3D printing and perfusing a dyed aqueous solution through the chip, qualitatively confirming uniform perfusion across all wells (Figure 2c).

Conclusion

This study demonstrates that computational modeling can effectively guide the design of high-throughput microfluidic OoC platforms by anticipating fabrication-induced variability and introducing hydraulic resistance elements to equalize flow distribution. The integration of in-silico design with additive manufacturing enables the development of robust microfluidic devices capable of delivering uniform perfusion across multiple parallel compartments. Such approaches are essential for scalable OoC systems used in drug screening, disease modeling, and precision medicine.




Figure 1. design of the microfluidic device and computational setup. a, Baseline microfluidic design featuring a multi-branch distribution network without flow equalization elements. b, Optimized design incorporating serpentine channels to homogenize hydraulic resistance and improve flow uniformity across parallel outlets. c, Schematic representation of fabrication-induced defects introduced in both configurations, including partial channel occlusions (clogging), lateral dimensional variations (channel shrinkage), and vertical deformation (roof sagging). Colored rectangles indicate corresponding spatial regions used for defect implementation in both designs. Dimensions are in mm. d–e, Computational domains and mesh skewness for the baseline (d) and serpentine-enhanced (e) configurations.




Figure 2. Flow distribution and experimental validation of the microfluidic device. a, Pressure distribution in the baseline configuration without serpentine equalization, showing non-uniform flow partitioning across the eight branches due to uneven hydraulic resistance. b, Pressure distribution in the optimized configuration with serpentine channels, demonstrating improved pressure balancing and more uniform flow distribution across all outlets. c, Experimental validation of the optimized design obtained by perfusing a dyed aqueous solution, confirming homogeneous flow distribution across the eight wells.

Acknowledgements
The authors acknowledge the Italian Ministry of Research (MUR) under the complementary actions to the NRRP “D34 Health” Grant (# PNC0000001). The study was supported also by the “Tecnopolo per la medicina di precisione” (TecnoMed Puglia) - Regione Puglia DGR n.2117 of 21/11/2018, CUP: B84I18000540002, and by the “National Center for Gene Therapy and Drug based on RNA Technology” (CN00000041 CN3 RNA), funded by the European Union - Next Generation EU- NRRP M4.C2- Investment 1.4. Finally, the authors acknowledge the ZEISS labs@location partnership between ZEISS Italy and the CNR NANOTEC for providing application and technical support.

D2 – P195

Left ventricular assist device outflow graft area and its influence on systematic vascular resistance

Lopez-Santana G.[1,2], De Rosis A.[1], Venkateswaran R.[3], Keshmiri A.[1,2]
[1]Faculty of Science and Engineering, The University of Manchester; [2]Manchester University NHS Foundation Trust, Wythenshawe Hospital, Southmoor Road; [3]Faculty of Biology, Medicine and Health, The University of Manchester, Manchester, UK

Introduction

The HeartMate III (HMIII) LVAD has extended the life expectancy of patients with heart pumps, but cardiovascular complications such as aortic regurgitation (AR) remain prevalent. Although the internal diameter of the HMIII outflow graft (OG) is fixed at 21mm, the length is determined by the clinical practitioner during LVAD implantation and the nature of the material of the OG allows for internal deformations to adapt the OG to the anatomy of each patient. We considered whether HMIII OG inlet area may influence the development of AR.

Materials and Methods


We reconstructed three-dimensional aortic models using CT data of 20 LVAD patients. Along the centrelines, we measured the area of a cross-section of the HMIII OG near to the site of anastomosis and retrospectively analysed the relationship between OG dimensions and AR development. Computational fluid dynamics (CFD) simulations were performed to observe the effect of aortic flow patterns produced by the OG on AR development.

Results

The incidence of AR rose in line with the area of the OG and abnormal shaping such as twisting or kinking significantly increased the risk of AR development. The irregular lumen area of the OG has a concave up, decreasing fourth-degree trendline (R^2=0.998) to the systematic vascular resistance of the turbulent flow, which means that the pressure and resistance in non-circular outlets are heavily influenced by the cross-sectional area and the wetted perimeter. The CFD results show the area of the OG affects eddy formation, retrograde flow, and wall shear stress in the aortic wall. They also depict the high concentration of stresses along the OG which may lead to elongation.

Conclusion

OG irregular area after LVAD implantation may contribute to AR development, along with other factors such as aortic morphology and the aortic wall's response to the pump flows. Given the influence of OG placement on aortic flows, this research demonstrates the potential of using patient-specific data as part of surgical planning to determine the optimal OG positioning in each patient and improve the accuracy of the intervention.



D2 – P196

Practical stress intensity factor estimation from crack opening profiles: Beyond sharp 2D cracks

Maggi L.[1,2], Allahdiniyan A.[3], Hoey D.A. [1,2], Taylor D. [1,2]
[1]Dept. Mechanical, Manufacturing and Biomedical Engineering, Trinity College, Dublin, Ireland; [2]Trinity Centre for Biomedical Engineering, Trinity Biomedical Sciences Institute, Trinity College, Dublin, Ireland; [3]Dept. Mechanical Engineering, Politecnico di Milano, Milan, Italy

Introduction

Cracks and notch-like defects frequently occur in biological tissues like bone or in medical implants. Estimating damage severity and propagation risk is essential to improve both prevention and treatment strategies. Classical fracture mechanics provides a well-established framework to study crack propagation in different materials, but it often requires complex stress analysis or simulations, not always straightforward and easy to apply. Allahdiniyan and Taylor[1] proposed an alternative approach: estimating the stress intensity factor (*K*) from direct measurements of Crack Opening Profile (COP), that is the opening of the crack faces along the entire crack front (Figure 1A). This method is based on Westergaard's equation[2] linking displacement to *K*. However, this is limited to sharp 2D cracks. Therefore, we are working to extend this to more realistic cases such as blunt notches, anisotropic materials and 3D effects in biological structures.

Aim

Extend the COP-based method to estimate *K* in realistic defect scenarios, including notches relevant to biological tissues and devices.




Figure 12. A. Schematic of the Crack Opening Profile (COP, δT) for an edge-notched component under tension. B. Experimental COP ($\delta T^{Experimental}$) of PMMA plates with double-edge notches, compared to Westergaard ($\delta T^{Westergaard}$) and corrected notch formula (δT^{Notch}) at three stages of tensile loading.

Materials and Methods

For each model extension, we combine Finite Element Analysis (FEA) simulations with experiments. FEA explores COP shapes, refining Westergaard's equation for better displacement prediction, and provides stress-based reference *K* values. Experiments demonstrate method applicability and practical aspects. For finite-root notches, FEA models included U-shaped and elliptical notches in three 2D configurations: central, edge and double-edge. Experiments involved tensile tests on PMMA samples with machined notches and displacements were measured via 2D Digital Image Correlation with a simple USB microscope to prove easy applicability.

Results

FEA showed that crack-based equations model COP and estimate *K* reasonably well for small notches in large plates (independent of radius) and for larger notches relative to plate dimensions only if sharp; for blunter ones, we propose corrected formulas. This approach models COP with errors <5% for sharper notches and <10% for blunter notches. COP-derived *K* closely matches equivalent *K* from J-integral method in most cases. Practical applicability was demonstrated on notched PMMA specimens (Figure 1B), proving the equations effectively predict COP and local *K* values.

Conclusion

This study shows that the COP method enables prediction of fracture risk via direct displacement measurements, without needing stress analysis. It is potentially broadly applicable to bone and other biological materials as well as medical devices made from biomaterials based on polymers and ceramics.

Acknowledgements

This research is conducted as part of the GAP Project and is supported by the European Commission under the Marie Skłodowska-Curie grant agreement No 101120290 (GAP). The authors are grateful for the financial support and resources that have enabled the progress of this research.

References

[1]Allahdiniyan A., Taylor D. Using crack face displacement to measure stress intensity: A practical approach. *Theor. Appl. Fract* 2025; 138; 104940.
[2]Westergaard H.M. Bearing pressures and cracks. *J. Appl. Mech* 1939; 6; A49-A53.

D2 – P197

Biomimetic hypoxic microenvironment for glioblastoma using organ-on-chip

Sercia L.[1,2,3], Corallo G.[2,3], De Giorgi A.[2,3], Scalera F.[2,3], Portone A.[2,3], Franco P.[4], Stoppelli M.P.[4,5], Gigli G.[2,3,6], Polini A.[2,3], Gervaso F.[2,3]

[1]Dept. di Ingegneria dell'Innovazione, University of Salento, Lecce; [2]Institute of Nanotechnology, National Research Council (CNR-NANOTEC), Lecce; [3]Tecnomed Puglia – Technopole for Precision Medicine (Biotech Lecce Hub), Lecce; [4]Institute of Genetics and Biophysics "A. Buzzati Traverso" (CNR-IGB), National Research Council, Naples; [5]UniCamillus-Saint Camillus International University of Health Sciences, Dept. Faculty of Medicine and Surgery, Rome; [6]Dept. di Medicina Sperimentale, University of Salento, Lecce, Italy

Introduction

Glioblastoma (GBM) is the most aggressive primary brain tumor, characterized by rapid progression, therapeutic resistance, and poor prognosis. A hallmark of GBM is severe intratumoral hypoxia, which drives tumor growth, invasion, and resistance to therapy. Conventional two-dimensional cultures and many animal models fail to reproduce the spatial and temporal oxygen heterogeneity of the tumor microenvironment, limiting their predictive value. Organ-on-chip technologies enable the recreation of physiologically relevant microenvironments through controlled fluid dynamics and mass transport. The aim of this study was to develop a microfluidic GBM-on-Chip platform capable of generating controllable, pathophysiologically relevant hypoxic conditions in vitro.

Materials and Methods

A custom microfluidic device was fabricated using digital light processing (DLP) to support dynamic cell culture under controlled perfusion. GBM cells and astrocytes were cultured within a chitosan-based matrix inside the device. A computational model was developed to simulate fluid dynamics and oxygen transport coupled to cellular consumption, incorporating flow velocity, diffusion coefficients, and oxygen uptake rates. This model was used to predict spatiotemporal oxygen distributions and guide optimization of perfusion protocols and device geometry. Experimental measurements of the hypoxia marker HIF-1α were performed to validate model predictions.

Results

Two culture strategies were investigated to engineer controllable hypoxia: 4 days of static culture followed by 4 days of perfusion (4S+4D) and 8 days of continuous perfusion from seeding (8D), both at 100 µL/h. Simulations revealed markedly different oxygen dynamics between protocols. In the 4S+4D condition, the device remained open during the static phase, maintaining near-atmospheric oxygen (~21%), followed by a progressive decline after sealing and initiating perfusion, reaching 1.09% pO_2 at day 8. In contrast, the 8D protocol induced immediate oxygen depletion, resulting in a lower final pO_2 of 0.65% and prolonged hypoxic exposure. Thus, hypoxia severity could be tuned by protocol without modifying device architecture. HIF-1α immunostaining confirmed significantly higher hypoxia under continuous perfusion, supporting model predictions. These results demonstrate a reproducible system capable of generating controlled hypoxic microenvironments relevant to GBM pathology.

Conclusion

This microfluidic GBM-on-Chip platform reliably reproduces key hypoxia-driven features of the tumor microenvironment in vitro. Integration of computational modeling with experimental validation enabled rational optimization of operating conditions to achieve physiologically relevant oxygen levels. The ability to modulate hypoxia through perfusion protocols alone provides a powerful tool for studying tumor biology and may enhance the predictive value of preclinical models for drug testing and therapeutic development.

Acknowledgements

The authors acknowledge the Italian Ministry of Research (MUR) under the complementary actions to the NRRP "D34 Health" Grant (# PNC0000001). The study was supported also by the "Tecnopolo per la medicina di precisione" (TecnoMed Puglia) - Regione Puglia DGR n.2117 of 21/11/2018, CUP: B84I18000540002.

D2 – P198
Lignin-based hydrogel for indoor cultivation

Cimino V., Pepi S., Leone G., Magnani A.
Dept. of Biotechnology, Chemistry and Pharmacy, University of Siena, Siena, Italy

Introduction
Currently the world is facing unprecedented global challenges such as rising temperatures, water scarcity, and the loss of fertile soil. These factors directly threaten food security.

Aim
This work focuses on the development of sustainable growth substrates, specifically advanced materials designed for indoor cultivation that can reduce environmental impact while maximizing productivity.

Materials and Method
The approach for choosing the components of the supports was the identification and valorization of biomass waste: the focus was on the main components of wood. Thanks to the presence of hydroxyl and metoxyl groups lignin can do covalent bond with other substrates. Choosing the proper crosslinker it allows to create a tunable porous structure capable of water retention. The chosen approach is to integrate lignin with two specific polysaccharides and an organic acid using an inorganic crosslinker. This hydrogel is a physical support, and it acts as a reservoir, holding water and nutrients exactly where the plants need. Developing these materials involves many variables: to handle this, it was used a Design of Experiment (DoE) approach (Fig.1).

Results
A pre-screening step was first performed: a Plackett-Burman with 5 variables and 8 experiments was performed, doing this it was possible to identify the most significant synthetic factors influencing the final product properties, but not detecting the variables interactions. The produced substrates have been characterized using two analytical techniques: rheology (for mechanical proprieties) and Differential Scanning Calorimetry (for thermal and morphological proprieties). The analyses show that all selected variables were indeed significant. Then, it was performed a D-Optimal Design statistical analysis. This approach allows to examine multiple factors efficiently and it is crucial to identify the most relevant factors and detecting the hidden interactions within them. This design lets to find the optimal synthetic parameters values to maximize or minimize the examinated hydrogel property.

Conclusion
A D-Optimal design was performed on the produced leaves using the hydrogels supports and then compared with commercial ones: it was tested the secondary metabolites profile, and so the produced plant quality. On selected supports were also performed a surface analysis to evaluate the components distribution.




Figure 1. Design of Experiment approach

D2 – P199

α-Alkylidene bis-cyclic carbonates: Building safer and greener polyurethane hydrogels

Delvaux A., Riva R., Grignard B., Detrembleur C., Jérôme C.
CERM, ULiège, Belgium

Introduction

Thanks to their remarkable mechanical properties, polyurethanes (PUs) are widely used in biomedical applications. Especially, PUs hydrogels are found in both scaffold engineering and drug delivery systems. However, PUs conventional synthesis involves di-isocyanates (Fig. 1A), compounds increasingly subject to regulatory restrictions because they are irritants and pose flammability and explosivity hazards.

To overcome these limitations, non-isocyanate polyurethanes (NIPUs) have attracted increasing attention. Among the various synthetic approaches, the reaction between polyamines and α-alkylidene bis-cyclic carbonates (BisαCC) has been selected here to prepare NIPU hydrogel scaffolds with tuneable mechanical and drug-delivery properties.

Materials and Methods

NIPU networks were synthesized from Jeffamine® ED-2003, BisαCC, and a crosslinker bearing a central tertiary amine, using a 1:1 stoichiometric ratio between primary amine and cyclic carbonate groups (Fig. 1B). These networks were loaded by impregnation with acetylsalicylic acid, used as a model active pharmaceutical ingredient (API). High-performance liquid chromatography was used to monitor both the loading and the release profile of the API under neutral conditions. The compression moduli of hydrogels immersed in water at 37 °C were measured using an Instron tester equipped with a dedicated thermostated bath.

Results

By varying the nature of the spacer in the BisαCC, three distinct NIPU networks were obtained leading to mechanically robust elastic hydrogels when swollen in water. These materials exhibit a high affinity for the API, resulting in high loading (relative to the quantity of API in the loading solution) and slow release kinetics (Fig. 2). This behavior is attributed to the tertiary amine group in the crosslinker, which promotes acid–base interactions with the acidic API. Furthermore, the structure of the BisαCC modulates the release profile and minimizes the initial burst release.

Conclusion

We successfully developed a robust synthesis process enabling the safe production of NIPU hydrogels with strong mechanical properties and high affinity for acidic APIs resulting in sustained release. Variation of the BisαCC structure within these covalent networks influenced the release profile allowing its tuning according to specific needs. These materials thus represent promising candidates as scaffolds with drug-delivery capabilities.





Figure 1: Schematic representation of the conventional synthesis of polyurethane (A) and the stepwise synthesis of non-isocyanate polyurethane networks developed in this work (B)



	Loading	Water swelling
	%	%
BisαCC1	0.24	409
BisαCC2	0.27	380
BisαCC3	0.36	332

$$Loading\ (\%) = \left(\frac{m_{API}}{m_{dry\ network}}\right) * 100$$

Figure 2 : Cumulative release profiles of the acidic model API from NIPU hydrogels in water, illustrating the influence of the BisαCC structure. API loading and water swelling values are reported in the table.

D2 – P200

Low-concentration formaldehyde fixation enables prolonged sample storage for space-based cell culture experiments

Sharma N., Grzempczyńska K., Duin S., Windisch J., von Witzleben M., Lode A., Gelinsky M.
Centre for Translational Bone, Joint and Soft Tissue Research, Faculty of Medicine & University Hospital, TU Dresden, Dresden, Germany

Introduction

Cell culture experiments in microgravity offer unique opportunities to study cellular behaviour under conditions unattainable on Earth. However, performing such experiments aboard the International Space Station (ISS) imposes stringent safety and logistical constraints. All materials must comply with European Space Agency (ESA) regulations restricting hazardous substances, precluding the use of standard 4% formaldehyde (FA) fixation solutions. Crew time and payload volume are severely limited, and shifting transport priorities may necessitate prolonged sample storage. Consequently, adaptation of fixation protocols is required to allow safe but efficient fixation in one step.

Aim

This study aimed to identify minimal FA concentrations that ensure complete cell fixation while preserving fluorescence microscopy imaging quality after prolonged storage in the fixation solution for up to six months.

Materials and Methods

Normal human dermal fibroblasts (NHDF) were cultured in 2D monolayers and, together with human umbilical vein endothelial cells (HUVEC), in 3D fibrin-gel co-cultures. Two parameters were systematically varied: FA concentration (0.2%, 0.5%, and 0.95%; control: 4%) and storage duration in the fixative solution (up to six months). 2D NHDF samples were stained with DAPI (nuclei), phalloidin (actin) and anti-collagen III; 3D NHDF/HUVEC samples were stained with DAPI, phalloidin and anti-CD31. Fluorescence imaging was performed using both fixed exposure times matching the control and individually optimized exposure settings. Additionally, the effect of storage temperature (4°C to 37°C) on fixation quality was assessed for reduced FA concentrations (0.2% and 0.95%).

Results

Concentrations of FA below 1% proved sufficient for complete cell fixation in 2D and 3D cultures: even after three and six months of storage, the samples retained detectable fluorescence signals in all three channels, although signal intensity was reduced compared to freshly fixed controls. This reduction could be compensated by increasing microscope exposure times. All cellular structures were visible without loss of information. Based on the balance between reduced concentration and preserved imaging quality, 0.95% FA was selected as the optimal concentration. Fixation quality remained consistent across a temperature range of 4°C to 37°C, accommodating variable thermal conditions during ISS transport and operations.

Conclusion

A 0.95% formaldehyde fixation protocol provides reliable cell fixation compatible with ESA safety regulations while maintaining acceptable fluorescence imaging quality after extended storage periods in the fixative of up to six months. This protocol minimizes crew handling time and represents a practical solution for spaceflight cell biology experiments subject to unpredictable sample return timelines.

Acknowledgements

This work was funded by the German Space Agency at DLR (grant number 50WB2332).

D2 – P201

Ontology-driven literature integration for a minimal information standard in antimicrobial biomaterials research

Qaisar M., Sierka M.
Otto Schott Institute of Materials Research, Friedrich Schiller University, Jena, Germany

Introduction

Research on antimicrobial biomaterials for biomaterial-associated infections (BAI) is expanding rapidly, yet a comparison of studies remains challenging due to the inconsistent and diffuse reporting of essential descriptors across heterogeneous publications. This limitation impedes the interoperability, reproducibility, and reuse of literature-derived evidence. In the context of the BioMat project, we present the implementation of the ontology-centered literature component of a minimal information standard for antimicrobial biomaterials data.

Materials and Methods

A domain ontology was developed and extended to represent key descriptors necessary for the structured organization of literature, including biomaterial, biomaterial type, study type, research technique, bacterial target, and cell type. The retrieval of literature metadata was executed through an automated pipeline, and the publication title, abstract, and keyword fields were semantically matched to ontology classes using embedding-based similarity. The classified records were written into a knowledge graph serialized in RDF/Turtle (Resource Description Framework) as ontology-linked paper entities with DOI-based provenance. This representation was designed to support SPARQL (SPARQL Protocol and RDF Query Language) querying, ontology-aware filtering, and extensible integration with broader semantic resources in BioMat.

Results

The pipeline generated a machine-readable literature layer for antimicrobial biomaterials research, processing 5,000 records and transforming them into an enriched, DOI-traceable knowledge graph linked to ontology-defined descriptors across six dimensions. The resulting graph enabled consistent filtering and retrieval by material, study context, microbial target, technique, cell type, and publication date, while preserving traceability to the source literature. The ontology-based representation also enhanced the comparability across heterogeneous studies and established a reusable structure for integrating literature evidence with future experimental and simulation-derived datasets. Unlike manually curated databases, this ontology-driven approach scales consistently across heterogeneous sources and does not rely on domain-expert curation for each new record added.

Conclusion

This work provides a practical semantic foundation for a minimal information standard in antimicrobial biomaterials research. By converting heterogeneous literature metadata into a queryable ontology-linked graph, it supports reproducible literature triage, transparent source traceability, and interoperable evidence organization, while preparing the basis for future integration of in vitro, in vivo, and clinically relevant BAI data.

Acknowledgements

This research was supported by the Deutsche Forschungsgemeinschaft (DFG) Research Training Group RTG 2723, entitled "Materials-Microbes-Microenvironments (M-M-M)," which is hosted at Friedrich Schiller University Jena.

D2 – P202

Identification of specific scFv fragments against a cancer-associated cytokine for potential diagnostic applications

Porsuk M.H.[1,2], Akkoc Y.[3,4], Kutlu O.[1,2], Gozuacik D. [3,4], Cetinel S.[1,2]
[1]Faculty of Engineering and Natural Sciences, Sabancı University; [2]Sabancı University Nanotechnology Research and Application Center (SUNUM); [3]Dept. of Medical Biology, School of Medicine, Koç University; [4]Koç University Research Center for Translational Medicine (KUTTAM), Istanbul, Turkey

Introduction

Hepatocellular carcinoma (HCC) has high mortality rates worldwide, mainly due to the lack of effective early diagnostic strategies. A specific cytokine belonging to the IL-6 family has been associated with tumor progression and could serve as a potential biomarker for HCC. In this context, this study aimed to select specific single-chain variable fragments (scFv) targeting cancer-associated cytokine. To the best of our knowledge, phage display-based scFv selection against this specific cytokine has not been reported previously.

Materials and Methods

An antibody phage display-based biopanning was performed using a naive murine scFv library. Four rounds of selection were conducted to enrich target-binding clones. A negative selection step against serum proteins was included to improve specificity. Selected clones were subjected to Sanger sequencing for analysis of the complementarity-determining region (CDR). Binding properties were evaluated by phage ELISA. Clones that showed enrichment across biopanning rounds were analyzed further for CDR motifs and amino acid composition.

Results

After four rounds of biopanning, 22 specific phage clones were identified. ELISA showed that five clones (Ab.p5, Ab.p9, Ab.p11, Ab.p12, and Ab.p20) exhibited binding signals above the negative control, indicating specific interaction with the target. Sequence analysis demonstrated reduced variety across selection rounds and revealed common CDR motifs, suggesting enrichment of target-specific clones rather than random amplification. Amino acid analysis indicated that ELISA-positive clones shared structural features. Optimal CDR3 length and the presence of aromatic residues were observed, which are likely associated with binding function. Motif analysis showed that enrichment of certain motifs during biopanning does not always correlate with functional binding. A single amino acid substitution in the CDR3 region significantly affected the binding efficiency. These findings indicate that functional binding is strongly associated with specific structural properties of CDR3.

Conclusion

This study successfully identified cancer-associated cytokine-specific scFv candidates using an antibody phage display strategy. Results demonstrated the binding potential of the candidate clones through ELISA and sequence analysis. The selected clones represent promising candidates for further characterization. These scFvs may contribute to the development of biosensor-based platforms and biomaterial surface functionalization for early diagnostic strategies of HCC.

D2 – P203

Investigation of nanostructured surface effect on hemocompatibility and HUVECs viability for stent application

Erdogan Y.K.[1,2], Adali M.A.[2]
[1]Dept.of Biomedical Engineering, Isparta University of Applied Sciences, Isparta, Turkey; [2]Dept. of Thoracic and Cardiovascular Surgery, University Hospital Tübingen, Germany

Introduction

Hemocompatibility, stent restenosis and poor endothelization are still major problems in stent application. Drug-releasing or bioabsorbable stent surfaces have limited improvement in bare stent problems. One of the potential remedies to address some of these issues can be modified nanophase stent surface modification. Creating nanostructured morphology and changing surface chemistry and zeta potential on stent surface can affect biocompatibility and minimize these issues.

Aim

The aim of study to fabricate nanostructures on stent surface, characterized surface properties and evaluate comprehensively hemocompatibility behaviour and HUVECs viability on bare and nanostructured stent surface.

Materials and Methods

The nanostructured surface was obtained by applied anodization, which performed 7,5% perchloric acid in ethylene glycol butyl ether solution. Surface morphologies and topographies were examined by SEM and AFM. The viability of HUVECs (ATCC®, Manassas, USA) on surfaces was examined by Calcein Am staining. Human whole blood was collected from the antecubital vein of healthy volunteers (n:4). ELISA kits were employed to assess changes in coagulation (TAT), the complement system (sC5b-9), polymorphonuclear (PMN), and activation of platelets (β-TG) and neutrophils. After the incubation of bare and nanostructured surfaces with blood, imaging surface was performed by SEM.

Results

We obtained uniform nanostructured, which had 220 nm feature size, on the surface. AFM analysis confirmed that nanostructured surface ten times rougher value compared to bare surface. Also, increased surface area was obtained. Moreover, nanostructured surface performed more negatively charged. After incubation of blood with surfaces, significantly increased levels of TAT complex, an indicator of coagulation activation, was detected on bare surface. Regarding the activation of inflammation (PMN elastase) and complement system (sC5b-9), no significant changes were measured between surfaces. In addition, SEM analyses showed reduced amounts of fibrin formation and platelet adhesion was observed on nanostructured surface. Moreover, nanostructured surface performed better HUVECs viability and migration compared to bare surface.

Conclusion

In this study, novel and uniform nanostructured stent surface was created. Modified nanostructured surface performed improved endothelization and hemocompatibility, while limiting coagulation activation, which is desired in successful stent application.

Acknowledgements

The authors would like to thank the TUBITAK (2219 Programme).

D2 – P204

Diazirine-enabled biofunctionalization of inert polymers for stable and functional protein interfaces

Bhaila Z.[1], Li J.[1], Scott S.[4], Wong C.[2], Virk S.[3], Wulff J.[3], Chan A.K.C.[5], Sask K.N.[1,2]
[1]School of Biomedical Engineering, McMaster University, Hamilton; [2]Dept. of Materials Science & Engineering, McMaster University, Hamilton; [3]Dept. of Chemistry, University of Victoria, Victoria; [4]Dept. of Engineering Physics, McMaster University, Hamilton; [5]Dept. of Pediatrics, McMaster University, Hamilton, Canada

Introduction

Polymer substrates such as thermoplastic polyurethane (TPU) and polydimethylsiloxane (PDMS) are widely used in biomedical applications including catheters, vascular grafts, and biosensors. However, their inherent chemical inertness limits surface functionalization, resulting in heterogeneous protein coverage and poor immobilization stability.

Aim

To develop a simple and versatile diazirine-based surface modification strategy enabling stable, covalent protein immobilization and spatially controlled photopatterning on inert polymer substrates.

Materials and Methods

Four diazirine derivatives (carbamate, bromide, NHS-ester, and phenyl) were synthesized and deposited onto TPU and PDMS substrates. Activation was performed either thermally (100°C) or via 360 nm UV irradiation, triggering carbene formation and covalent C–H/N–H insertion into the substrate. Surface characterization was conducted by high-resolution XPS to confirm diazirine deposition and covalent bond formation. Protein immobilization was quantified using iodine-125 radiolabeled IgG on TPU and antithrombin heparin (ATH) on PDMS, with stability assessed by incubation in human plasma and SDS elution. Photopatterning capability was evaluated by UV-activating masked TPU discs followed by incubation with fluorescently labeled proteins and fluorescence microscopy imaging.

Results

XPS confirmed the presence of diazirine-derived functional groups and a significant increase in C–C bonds post-activation, suggesting covalent surface conjugation. Thermally activated carbamate- and bromide-functionalized TPU surfaces exhibited approximately two-fold higher IgG immobilization versus unmodified controls. ATH immobilization on diazirine-modified PDMS increased by 25–35% (Fig 1). In all cases, diazirine-modified surfaces showed markedly enhanced resistance to protein elution, indicating stable covalent attachment. UV-activated surfaces enabled spatially controlled IgG photopatterning corresponding to applied photomasks (Fig 2).

Conclusion

Diazirine-based surface modification provides a robust and versatile platform for stable covalent protein immobilization and photopatterning on inert polymer substrates. Ongoing work includes evaluation of post-immobilization protein bioactivity via lysozyme activity and radioimmunoassays, and assessment of ATH anticoagulant performance through plasma clotting and anti-factor Xa assays. This strategy holds strong potential for advancing functional polymer interfaces in biosensing, blood-contacting devices, and tissue engineering.




Figure 1: ATH adsorption and immobilization from PBS buffer (0.1 mg/mL) to various modified PDMS surfaces and the amount of protein remaining after elution in human plasma for 24 hours and subsequently 2% SDS elution for another 24 hours. Data are mean ± SD, n=3. D1 – Imidazole Carbamate Diazirine, D3 – Benzyl Bromide Diazirine, D7 – NHS Ester Diazirine.




Figure 2: Fluorescence and brightfield imaging of imidazole carbamate diazirine-functionalized TPU discs following UV activation through a maple leaf photomask. TRITC-tagged protein immobilization was spatially confined to UV-exposed regions and persisted following IgG incubation and 24 h SDS elution, indicating covalent attachment. Minimal signal was observed in non-irradiated regions or prior to activation. DAPI and GFP images showcase diazirine presence and activation, not protein immobilization.

D2 – P205

Chitosan-hyaluronic acid hydrogel: Elaboration of a physical hydrogel for tissue engineering application

Demilly L.[1], Maillard M.[1], Pardessus J.[1,3], Drucbert A.S.[1], Martel B.[4], Marchetti P.[2], Guerreschi P.[1,3], Blanchemain N.[1]

[1]Inserm U1365-Advanced Drug Delivery Systems (ADDS), University of Lille, Lille; [2]ONCOLILLE Cancer Institute - CANTHER Laboratory "Cancer Heterogeneity, Plasticity and Resistance to Therapies", Lille, France; [3]Hôpital Salengro –Service de Chirurgie Plastique, CHU, Lille, France; [4]UMR 8207 – Unité Matériaux et Transformations (UMET), University of Lille, Lille, France

Introduction

Breast cancer affects 1 in 8 women in the world. Once the disease has been treated, some option of breast reconstruction can be proposed: a synthetic implant, tissue taken from another part of the body, or by fat injection. These methods may require several surgeries and the results can vary from one person to another. There is a need for natural reconstruction methods that are simpler and more reliable. In this context, the project is based on tissue engineering principles. The objective is to design an injectable cell-loaden hydrogel which could be shaped by 3D printing, providing a personalized reconstruction solution. This hydrogel is made from two naturally sourced substances, chitosan (CHT) and hyaluronic acid (HA). It will serve as a scaffold to maintain living cells, organize their growth, and allow them to develop in optimal conditions.

Materials and Methods

The hydrogel was formulated using the method developed in the laboratory using two interconnected syringes (Fig 1). CHT and HA powders were mixed together in different ratios (5:1, 4:1, and 3:1) to obtain a homogeneous mixture in a first syringe. The second syringe contain physiological medium and lactic acid. The rheological properties of the hydrogel with rheometer AresG2, stability and swelling in PBS or DMEM at 37°C (80 rpm) were evaluated. Cytotoxicity assays (Blue Alamar® with 3T3-L1 P8) was performed according to ISO10993-5 standard and cell printing tests (BioX6 Cellink) were also performed.




Fig 1 : Mixing process of physical hydrogel between chitosan and hyaluronic acid

Results
Rheological analyses confirmed that the hydrogel forms a three-dimensional network according to a storage modulus greater (G') than the loss (G'') modulus. Hydrogels show shear-thinning properties while formulations containing a higher proportion of CHT show a higher modulus (1130.20 Pa, 423.21 Pa and 169.52 Pa for formulation 5:1, 4:1 and 3:1). These hydrogels are stable in PBS and culture medium for 7 days and swelling of up to 30% to 70% can be achieved. Biological tests show no cytotoxicity (more than 90% of viability). A single 400-micron layer can be printed for all three formulations.

Conclusion
This study confirms that this hydrogel can be used as a hydrogel suitable for tissue engineering applications. The hydrogel could then be used as a scaffold for adipocyte growth and enable breast reconstruction.

Acknowledgements
This research was funded by Institut pour la Recherche sur le Cancer de Lille (IRCL)
This project was supported by CPER TecSanté, within the framework of the Contrat Plan Etat Région Hauts-de-France 2021-2027.

D2 – P206

Tunable alginate composite hydrogels support formation and stability of liver organoids

Ahmed S.*, Alshehri E., Assiri A., Broering D., Mir Tanveer A.*
Transplant Research and Innovation, Organ Transplant center of Excellence, King Faisal Specialist Hospital and Research Center, Riyadh, Saudi Arabia

Introduction

Engineering suitable extracellular matrix environments is essential for the successful growth and maintenance of organoids in vitro. Unlike traditional scaffold-free culture systems, biomaterial-based hydrogels provide defined mechanical support and biochemical cues that regulate cellular organization, proliferation and differentiation. Alginate based hydrogels are widely used due to their compatibility, mild gelation conditions and tunable mechanical properties. However, pure alginate matrices often lack adhesion motifs and optimal structural stability required for long term organoid culture. Incorporating natural polymers such as gelatin and carboxymethyl cellulose (CMC) may enhance the biological functionality and mechanical properties of alginate hydrogels. In this study, we developed composite alginate-gelatin and Alginate CMC hydrogels to investigate their ability to support liver organoid formation and growth in the controlled 3 D microenvironment.

Materials and Methods

Composite hydrogels were prepared by blending sodium alginate with gelatin or carboxymethyl cellulose to generate two biomaterials formulations: Alg-Gel and Alg-CMC. Hydrogels were crosslinked under controlled conditions to obtain 3D matrices suitable for cell encapsulation and organoid culture. Liver derived cells were embedded within the hydrogel matrices. Suitable for cell encapsulation and organoid culture. Liver derived cells were embedded within the hydrogel matrices and cultured under organoid promoting conditions. Organoid formation and morphology and growth kinetics were monitored using phase contrast microscopy. Cell viability and structural organization within the hydrogel were evaluated using live/dead assays and fluorescence imaging. The mechanical stability and swelling behavior of the hydrogels were also characterized to assess their suitability as supportive matrices for organoid development.

Results

Both composite hydrogel systems supported the formation and growth of liver organoids. Organoid cultured within Alg-Gel hydrogels displayed enhance cellular aggregation and structural organization, likely due to the presence of gelatin derived cell adhesion motifs. In contrast, Alg-CMC hydrogels exhibited improved structural stability and maintained organoid morphology over extended culture periods. Viability assesses confirmed high survival within both hydrogel system, demonstrating good cytocompatibility of the composite matrices. The distinct physico-chemical properties of two hydrogels influences organoid size, morphology and spatial organization.




Figure 1. Live/Dead staining of liver organoids cultured in Matrigel, alginate, alginate–gelatin, and alginate–CMC hydrogels. Green indicates live cells and red indicates dead cells. Scale bar: 1000 µm

Conclusion

Alginate based composite hydrogels incorporating gelatin or CMC provide supportive microenvironment for liver organoid culture while Alg-Gel promoted cellular interactions and organoid formation. Alg-CMC offers improved structural stability for prolonged culture. These findings highlight the potential of tunable alginate-based biomaterial platforms for advanced organoid engineering and tissue modelling applications.

D2 – P207

Percutaneous injectable hydrogels for instant fracture healing

Sankaralingam P.[1], Ganesan S.M.[2], Balasubramanian M.[2], Thangavel V.C.[1]
[1]Dept. of Rubber and Plastics Technology, Madras Institute of Technology Campus, Anna University, Chromepet, Chennai; [2]Bone Substitutes, Madurai, Tamil Nadu, India

Introduction

Minimally invasive biomaterials capable of filling irregular bone defects and promoting rapid regeneration are increasingly sought in orthopedic applications. Injectable hydrogels offer several advantages, including defect conformability, in situ gelation, and localized therapeutic delivery. Incorporating bioactive glass nanoparticles within hydrogel matrices provides sustained release of osteogenic ions that stimulate bone regeneration. Fluorophosphate glass nanopowders doped with therapeutic metal ions such as silver and zinc are particularly attractive due to their osteogenic and antimicrobial properties. Combining these nanoparticles with biocompatible hydrogel networks can generate multifunctional biomaterials capable of enhancing fracture healing and bone formation.

Aim

This study aims to develop an injectable thermo responsive hydrogel composite incorporating metal oxide doped fluorophosphate glass nanopowders for enhanced osteogenesis and accelerated fracture healing.

Materials and Methods

Injectable hydrogel systems were fabricated using oxidized cellulose derivatives combined with gelatin network. Glutaraldehyde was used as a crosslinking agent to stabilize the polymeric network. Silver and zinc doped fluorophosphate glass nanopowders were incorporated into the hydrogel matrices to impart bioactivity. Physicochemical characterization was carried out using FTIR spectroscopy, SEM-EDX analysis, differential scanning calorimetry, thermogravimetric analysis, rheological viscosity measurements, and swelling studies in simulated body fluid (SBF). Ion release kinetics of Ag^{+} and Zn^{2+} were evaluated using atomic absorption spectroscopy under different immersion conditions. Biological performance was assessed through hemolysis assays, MTT cytocompatibility testing, alkaline phosphatase activity, chondroitin sulfate deposition, and osteogenic gene expression (RunX2, osteocalcin, and collagen II) in osteoblast like cell lines.

Results

The developed hydrogel composites exhibited rapid sol-gel transition near physiological temperature (~37 °C), enabling injectable delivery and in situ gel formation. SEM analysis revealed a porous interconnected network with homogeneous dispersion of fluorophosphate glass nano particles. Rheological measurements demonstrated improved viscosity and thermal stability upon nanoparticle incorporation. Swelling studies indicated water uptake between 200-300%, supporting efficient defect filling and sustained ion release. Atomic absorption spectroscopy confirmed controlled release of Ag^{+} and Zn^{2+} ions over prolonged immersion periods. Biological evaluation showed excellent hemocompatibility and high cell viability. Osteogenic assays demonstrated enhanced alkaline phosphatase activity and increased expression of bone marker genes including RunX2, osteocalcin, and collagen II, indicating strong stimulation of osteogenic differentiation.

Conclusion

The developed fluorophosphate glass nanopowder filled injectable hydrogel demonstrates excellent biocompatibility, controlled ion release, and significant osteogenic stimulation. Its ability to gel in situ and promote bone marker expression suggests strong potential as a non-invasive biomaterial for fracture repair and bone regeneration.

Acknowledgements

The research was fully supported by Bone Substitutes, Madurai 625014, India. The authors are much grateful to the PAMC Hospital, Madurai, and the Department of Rubber and Plastics Technology, MIT campus, Anna University, Chennai-600044.

D2 – P208

Hydrogels modified with active substances for the regeneration of mucous membranes

Świeczko-Żurek B.[1], Farrow J.[2], Nowak M.[3]
[1]Dept. of Biomaterials Technology, Institute of Manufacturing and Materials Technology, Faculty of Mechanical Engineering and Ship Technology, Gdansk University of Technology, Gdansk; [2]Student at Gdansk University of Technology, Gdansk; [3]Dept. of Trauma Surgery and Orthopaedics, Hospital in Inowrocław, Poznańska 97, 88-100 Inowrocław, Poland

Introduction

Soft tissue wounds after cancer resection pose a major problem for clinicians, because they delay the healing process. The demanding environment of the human body contains microorganisms, which also does not favor this process. Current solutions are short-acting and symptomatic. Therefore, new solutions are being sought in the field of tissue regeneration that would be biocompatible, have high adhesion to wet tissues, and also possess antibacterial and anti-inflammatory properties. One of the solutions is nanocellulose. It is a widely available and natural material that is biocompatible, biodegradable, non-toxic, durable, and flexible. An undeniable advantage of nanocellulose is the possibility of modifying it with various bioactive additives.[1-3]

Aim

The aim of the work is to develop materials intended for the regeneration of hard-to-heal mucosal wounds after tumor resection.

Materials and Methods

The research material was nanocellulose with active substances (snail mucus modified with additives). Unfortunately, at the current stage, the authors cannot provide details of the research methodology. It will be presented during the conference.

Results

The research will be conducted in collaboration with the University of Bordeaux. Studies conducted so far have shown high resistance to microbiological degradation, and on the other hand, they have shown very good adhesion of healthy cells, thus regeneration of damaged tissue.

Conclusion

The current studies will continue. Additionally, new substances are being prepared, which will also be incorporated into the samples.

References

[1]Cho Y.-D., Kim K.-H., Lee Y.-M., Ku Y., Seol Y.-J. Periodontal Wound Healing and Tissue Regeneration: A Narrative Review. *Pharmaceuticals* 2021; 14, 5; 456. doi:10.3390/ph14050456.
[2]Baker J.L., Mark Welch J.L., Kauffman K.M., McLean J.S., He X. The oral microbiome: diversity, biogeography and human health. *Nat Rev Microbiol* 2024; 22, 2, 47; 89–104. doi:10.1038/s41579-023-00963-6.
[3]Chmielewski M. et al. The Oral Cavity—Another Reservoir of Antimicrobial-Resistant Staphylococcus aureus? *Antibiotics* 2024; 13, 7; 649. doi:10.3390/antibiotics13070649.


D2 – P209

Real-time label-free monitoring of fibrosis-associated stiffness using a breathing lung-on-a-chip

Ha G.H, Lee G.H, Lee J.M
Dept. of Material Science and Engineering, POhang university of Science and TECHnology, Pohang, Republic of Korea

Introduction

Pulmonary fibrosis is characterized by abnormal extracellular matrix (ECM) remodeling, progressive tissue stiffening, disrupted mechano-transduction, and impaired respiratory function. Changes in tissue stiffness not only reflect disease progression but also strongly influence cellular responses to therapeutic agents. Therefore, continuous monitoring of mechanical properties is critical for understanding fibrosis progression and evaluating antifibrotic treatments. However, conventional in vitro models have limitations in simultaneously reproducing breathing-associated mechanical stimuli and enabling real-time measurement of stiffness changes. In this study, we present a lung-on-a-chip platform that integrates physiologically relevant cyclic mechanical stimulation with label-free stiffness sensing (Fig. 1a). The system mimics the alveolar microenvironment using a thin patterned polydimethylsiloxane (PDMS) membrane coated with a cell-laden collagen methacrylate (ColMA) hydrogel. Cyclic pressure modulation through an underlying air channel reproduces breathing dynamics, while image-based deformation analysis enables non-destructive quantification of mechanical properties.



Materials and Methods

ColMA was synthesized via methacrylation of type I collagen and purified through dialysis followed by lyophilization. Human lung microvascular endothelial cells (HULEC-5a), lung fibroblasts (MRC-5), and alveolar epithelial cells (NCI-H1703 and NCI-H441) were cultured under standard conditions. The lung-on-a-chip device was fabricated using a thin punctured PDMS membrane that mimics the ultrastructural features of the alveolar basement membrane. Surface modification enabled stable bonding between the PDMS membrane and the ColMA hydrogel layer. The hydrogel was deposited through repeated coating to achieve a stable and tunable thickness, followed by incubation-based stabilization. Cyclic pneumatic actuation applied breathing-like mechanical deformation to the membrane-hydrogel construct (Fig. 1b).

Results

The fabricated punctured PDMS membrane successfully reproduced the structural features of the alveolar basement membrane and allowed stable cyclic deformation under pneumatically driven breathing conditions. After surface modification, the membrane and hydrogel layer formed a chemically stable interface capable of withstanding repeated mechanical loading. Image-based analysis of membrane bulging profiles enabled quantitative estimation of stiffness changes without destructive mechanical testing. The stiffness values obtained from this method showed strong agreement with finite element simulations and nanoindentation measurements, confirming the reliability of the sensing strategy. Furthermore, the thickness and composition of the ColMA hydrogel could be tuned to modulate the mechanical microenvironment, enabling the modeling of fibrosis-associated stiffening. The platform enabled continuous monitoring of the transition from compliant healthy-like tissue to stiff fibrotic-like tissue under dynamic mechanical stimulation.

Conclusion

Overall, this dynamic lung-on-a-chip platform provides a physiologically relevant and non-invasive tool for longitudinal stiffness assessment in engineered lung tissue. The system enables real-time monitoring of fibrosis-associated mechanical changes and offers strong potential for studying mechanobiological responses, modeling fibrosis progression, and evaluating antifibrotic therapeutics in preclinical drug screening applications.

Acknowledgements

The authors gratefully acknowledge funding from the National Research Foundation of Korea (NRF) grant (RS-2023-00260454 and RS-2024-00403376) funded by the Korean government (MSIT)

D2 – P210

Incorporation of decellularized wharton's jelly into GelMA bioink improves fibroblast viability and migration in 3D bioprinted constructs

Amrutha H.K.[1], Dr. Sanatombi Devi E.[2], Dr. Shashikala Bhat K.[3], Dr. Kirthanashri S.V.[1]
[1]Dept. of Biotherapeutics Research (DBR), MAHE, Manipal; [2]Dept. of Medical Surgical Nursing, Kasturba Medical Collage, Manipal; [3]Dept. of Obstetrics and Gynaecology, Dr TMA Pai Hospital, MAHE, Udupi, India

Introduction

Decellularization is widely used in regenerative medicine to remove cellular and nuclear components while preserving extracellular matrix (ECM) architecture and biochemical cues. Wharton's Jelly (WJ), the mucoid connective tissue of the umbilical cord, is rich in ECM proteins and bioactive molecules and is therefore considered a promising biomaterial source for wound repair and tissue engineering applications.

Materials and Methods

Chemical, enzymatic, and mechanical decellularization approaches were compared to identify a method capable of effectively removing cellular content while preserving WJ-derived bioactivity. Among the tested approaches, homogenization provided the most favourable balance between decellularization efficiency and retention of functional biomolecules. The resulting decellularized WJ extract was incorporated into in-house developed gelatin methacryloyl (GelMA) to fabricate 3D bioprinted constructs.

Results




Fig 1: Quantitative analysis of cell viability (%) measured at Day 1, 3, 7, and 14.




Fig 2: Cell Migration Assay showing wound closure (0-24hrs) across different protein and condition media treatment on NHI3TS Cells Line

In vitro evaluation demonstrated that GelMA–WJ constructs supported an improved NIH3T3 fibroblast response, with approximately 25% higher cell viability in the MTT assay compared with control constructs, indicating that the incorporation of WJ-derived components provides a more favorable microenvironment for cell survival and proliferation. Additionally, scratch assay analysis revealed accelerated wound closure within 18 h in the presence of WJ-derived proteins, suggesting enhanced fibroblast migration and indicating the potential of these constructs to promote cellular activities associated with effective wound healing.

Conclusion

These findings suggest that incorporation of decellularized WJ into GelMA bioink enhances fibroblast viability and migration. The study highlights the potential of WJ-derived ECM components as bioactive additives in 3D bioprinted constructs for wound-healing applications.

D2 – P211

A multifunctional hydrogel orchestrating healing cascade via sequential immunomodulation and glucose metabolic regulation for diabetic wound repair

Li J.*, Li Y., Li Y.
Research Center for Nano-Biomaterials, Analytical and Testing Center, Sichuan University, Chengdu, China

Introduction

Diabetic wound healing remains a critical clinical challenge due to persistent infection, dysregulated inflammation, and hyperglycemic microenvironment.[1] Conventional treatments often target these factors in isolation, lacking temporal coordination to restore the natural healing cascade.[2] Herein, we designed a fully bio-based multifunctional hydrogel (LHL-OβCD) capable of sequentially modulating immune responses and regulating glucose metabolism. The hydrogel integrates high- and low-molecular-weight hyaluronic acid (HHA/LHA) with lysine-preassembled oxidized β-cyclodextrin (OβCD) via host-guest interaction and covalent crosslinking, enabling early release of LHA to initiate pro-inflammatory phase and sustained presentation of HHA to promote anti-inflammatory transition, while OβCD provides long-lasting antibacterial activity and lysine contributes to local glycemic control.

Materials and Methods

LHL-OβCD hydrogel was fabricated by first forming a host-guest complex between lysine and OβCD, then crosslinking with HHA via amide bonds, and finally incorporating LHA through physical entrapment. The hydrogel was characterized for structure, mechanical properties, degradation, and release kinetics. Antibacterial activity was assessed against S. aureus and E. coli. Immunomodulatory effects were evaluated in RAW264.7 macrophages by analyzing M1/M2 marker expression and cytokine secretion. Angiogenic potential was tested using HUVEC tube formation and migration assays. In vivo efficacy was examined in a full-thickness skin wound model in type 2 diabetic mice. Wound closure, histology, and immunofluorescence staining for macrophages and vascular markers were performed. Transcriptomic analysis (RNA-seq) was used to uncover underlying mechanisms.

Results

LHL-OβCD hydrogel exhibited sustained antibacterial efficacy (>90% for 7 days) and excellent biocompatibility. The sequential release profile led to early M1 polarization (increased TNF-α, iNOS, CD86) followed by M2 polarization (elevated IL-10, Arg-1, CD206) in macrophages, promoting angiogenesis and cell migration. In diabetic mice, LHL-OβCD significantly accelerated wound closure, enhanced granulation tissue formation, collagen deposition, and neovascularization. RNA-seq and validation revealed activation of hematopoietic lineage and calcium signaling pathways, with upregulation of P2RX2 and ATP2A, improving glucose metabolism and immune microenvironment.[3]

Discussion

The healing of diabetic wounds requires dynamic regulation of the pathological microenvironment.[4] Our LHL-OβCD hydrogel leverages the differential binding of LHA and HHA to achieve sequential immunomodulation, mimicking the natural inflammatory-to-proliferative transition.[5] The sustained release of OβCD ensures long-term antibacterial protection, while lysine-mediated calcium signaling enhances glucose uptake and insulin sensitivity.[6] This multi-targeted approach addresses the complex diabetic wound milieu more effectively than single-function dressings.

Conclusions

We developed a multifunctional hydrogel that integrates sequential immunomodulation, sustained antibacterial activity, and glucose metabolic regulation. By actively remodeling the diabetic wound microenvironment, LHL-OβCD promotes accelerated healing with improved tissue quality. This work provides a promising strategy for designing advanced wound dressings that orchestrate the healing cascade through coordinated biological pathways.




Figure illustration of the synthesis of multifunctional hydrogel dressing and the mechanisms for promoting diabetic wound healing.

References

[1]Maschalidi S., et al. 2022. 10.1038/s41586-022-04754-6.
[2]Deng M., et al. 2022. 10.1016/j.biomaterials.2022.121790.
[3]Zeng X., et al. 2023. 10.1016/j.bioactmat.2022.04.032.
[4]Jia D., et al. 2024. 10.1021/acsami.3c17667.
[5]Yin G.-Z., et al. 2021. 10.1016/j.ensm.2021.05.023.
[6]Ausri I.R. et al. 2024. 10.1002/adma.202402009.

D2 – P212

Photo-crosslinked carboxymethyl cellulose/collagen hydrogel-infused mesh for preventing postoperative pelvic adhesions in a rat model

Tsai W.B.[1,*], Chang W.C.[1], Chang C.C.[2], Chang R.J.[3]
[1]Dept. of Chemical Engineering, National Taiwan University, Taipei; [2]Dept. of Obstetrics and Gynecology, School of Medicine, Chung Shan Medical University and Chung Shan Medical University Hospital, Taichung; [3]Dept. of Chemical Engineering and Biotechnology, National Taipei University of Technology, Taipei, Taiwan

Introduction

Postoperative adhesions are common and clinically significant complications after abdominal and pelvic surgeries. They can cause chronic pain, bowel obstruction, infertility, and increased reoperation risk, significantly impairing patient outcomes and quality of life. Although synthetic meshes such as polypropylene (PP) provide durable mechanical support and reduce recurrence, their exposed surfaces often induce inflammation, fibrin deposition, and fibrotic encapsulation, promoting adhesions with surrounding tissues. Therefore, developing a surface modification strategy that maintains mechanical strength while offering an effective anti-adhesion barrier is clinically important.

Materials and Methods

In this study, we developed a surface-modified anti-adhesion mesh by coating commercial PP meshes with a photocrosslinkable hydrogel composed of methacrylated carboxymethyl cellulose (CMCMA) and maleated type I collagen (ColME). The precursor infiltrated the mesh pores and was rapidly photocrosslinked in situ, forming a conformal barrier layer while preserving structural integrity. Material properties were evaluated by morphological characterization, mechanical testing, rheological analysis, and in vitro degradation. Cytocompatibility was assessed using cell culture to determine the optimal formulation. Anti-adhesion efficacy was further examined in rat cecum injury and abdominal adhesion models (Fig. 1).

Results

The hydrogel-modified mesh maintained structural integrity and handling properties comparable to the unmodified PP mesh. Formulations containing ColME exhibited controlled in vitro degradability. In vitro studies demonstrated favorable cytocompatibility, high cell viability, and stable cell attachment without observable cytotoxic effects. In vivo results showed that the hydrogel alone effectively reduced adhesion formation in the cecum injury model. In the abdominal adhesion model, the composite mesh significantly decreased adhesion severity, adhesion area, and fibrotic tissue deposition compared with the unmodified control. Histological staining and quantitative analysis further confirmed reduced inflammatory infiltration and collagen accumulation.

Conclusion

This study presents a simple, scalable, and biocompatible hydrogel platform that can be directly applied to surgical meshes or wounded tissues to form a stable anti-adhesion barrier. By integrating mechanical reinforcement with controlled degradability and bioactive functionality, this strategy demonstrates strong translational potential for abdominal and pelvic surgeries and may improve postoperative safety and long-term clinical outcomes.

Acknowledgements

This work was financially supported by the Ministry of Science and Technology, Taiwan, and Department of Obstetrics and Gynecology, China Medical University Hospital. The authors acknowledge the members of Advanced Biomaterials Laboratory, Department of Chemical Engineering and Biotechnology, National Taipei University of Technology for assistance in the animal experiments.




Figure 1. Schematic overview of anti-adhesion hydrogel and hydrogel- infused mesh for preventing adhesion formation in surgical models.

D2 – P213

Towards functional scaffolds: Characterization of a conductive bioink for 3D bioprinting

Guner E., Arslan-Yildiz A.*
Dept. of Bioengineering, Izmir Institute of Technology (IZTECH), Izmir, Turkey

Introduction

Recapitulating the electrophysiological microenvironment of excitable tissues remains a central challenge in 3D bioprinting. Conductive bioinks that simultaneously offer tunable electrical properties, printability, and cytocompatibility are critically needed to advance functional tissue engineering of neural and cardiac constructs.

Materials and Methods

In this study, a novel electroconductive hybrid bioink was developed by integrating quince seed hydrogel (QSH); a naturally derived, biocompatible polysaccharide matrix with favorable gelation and rheological properties, with Poly(3,4-ethylenedioxythiophene) polystyrene sulfonate (PEDOT:PSS). Bioprinting parameters including formulation of bioink, extrusion pressure, and nozzle diameter were systematically optimized. Rheological behavior, electrochemical performance, and print fidelity were subsequently characterized. The optimized bioink was used to fabricate 3D cell-laden constructs incorporating neuroblastoma (SH-SY5Y) and cardiomyocyte (H9c2) cell lines.

Results

The QSH/PEDOT:PSS bioink exhibited pronounced shear-thinning behavior and viscosity profiles suitable for extrusion bioprinting, with high shape fidelity and structural stability post-printing. Incorporation of PEDOT:PSS significantly enhanced electrical conductivity through improved charge-transfer capacity [10^{-3} -10^{-4} S/cm]. Long-term culture demonstrated cell viability exceeding 70-80% on day 15, alongside sustained proliferation in both cell lines, confirming biocompatibility. Furthermore, enhanced neurite extension in SH-SY5Y cells and improved cellular organization in H9c2 cultures were observed in the conductive microenvironment compared to non-conductive controls.

Conclusion

The QSH/PEDOT:PSS bioink presents a tunable, naturally derived electroconductive platform that successfully bridges printability, mechanical integrity, and electrophysiological functionality. These properties position it as a promising material for fabricating electrically active tissue models and stimulation-responsive scaffolds, with direct relevance to neural and cardiac tissue engineering, and broader applicability across electroactive tissue systems.

Acknowledgements

This study is financially supported by Health Institutes of Türkiye (TÜSEB) under Project ID: 43984.

D2 – P214

Designing self-assembling peptide–chitosan composite hydrogel for wound healing applications

Ali Hosseinzadeh S.[1,2], Saiani A.[3,2], Miller A.[1,2]
[1]Dept. of Chemical Engineering, The University of Manchester; [2]Manchester Institute of Biotechnology, The University of Manchester; [3]Division of Pharmacy and Optometry, The University of Manchester, Manchester, UK

Introduction

Chronic wounds are characterized by persistent infection, prolonged inflammation, and delayed tissue repair, creating a need for wound-healing materials that combine antimicrobial efficacy with good cytocompatibility and suitable handling properties. Self-assembling peptides provide supramolecular assembly, nanofibre formation, and gel-forming capability, but their direct use is often limited by high cationic charge, cytotoxicity, and rapid depletion. Chitosan is an attractive partner because it is biocompatible, film-forming, intrinsically antibacterial, and relevant to wound repair, where it can support cell migration and wound closure while moderating peptide-associated charge effects. Here, we aimed to develop a peptide–polymer composite that preserves peptide self-assembly, antibacterial function while improving biological tolerance and allows topical wound application.

Materials and Methods

A composite hydrogel (2:1) was prepared by combining liquid chitosan (5 mg/ml) with the self-assembling cationic peptide $K(FEFK)_2K$ (10 mg/ml). Structural and physicochemical properties were characterized by Fourier transform infrared spectroscopy (FTIR), rheology, transmission electron microscopy (TEM), small-angle X-ray scattering (SAXS), zeta potential analysis, and HPLC-based peptide release measurements. Antibacterial activity was evaluated by minimum inhibitory concentration (MIC) testing against Gram-negative *Escherichia coli (E.Coli)* and Gram-positive *bacillus subtilis (B subtilus)*. Cytocompatibility was assessed using 3T3 fibroblasts in 2D culture after 24 hours and wound-healing potential was evaluated by via in vitro scratch assay.

Results

Composite hydrogels showed enhanced mechanics (storage modulus and yield stress) than either the peptide or chitosan alone. FTIR confirmed retention of peptide β-sheet secondary structure after composite formation, while TEM and SAXS showed preservation of the fibrillar nanostructure with only a modest increase in fibre diameter, indicating chitosan association without disruption of peptide self-assembly. The composite displayed an intermediate positive zeta potential (+34.22 mV) relative to $K(FEFK)_2K$ and chitosan, consistent with partial peptide charge screening through chitosan addition. HPLC demonstrated minimal peptide release, ~ 1.5 % peptide released after 24 hours and maximum of ~ 2.4 % after 150 hours onwards. The composite hydrogel also showed antibacterial activity with MIC_{90} values against *E. coli* of 0.16 mg/mL and against *B. subtilis* of 0.13 mg/mL as well preventing bacterial colonisation. Cytocompatibility studies showed that $K(FEFK)_2K$ added to cell culture media (1:1) affected 3T3 cell viability, ~ 60 % after 24 hours, while both chitosan and the peptide-chitosan composite addition to media resulted in high viability ~ 99 %. In the scratch assay, materials were applied using the same treatment approach, and the wound gap decreased from ~1050 µm to ~820 µm in untreated control, ~690 µm with chitosan, ~1000 µm with $K(FEFK)_2K$, and ~590 µm with the composite, indicating the greatest improvement in wound closure for the composite.

Conclusion

The $K(FEFK)_2K$ –chitosan composite hydrogel showed antibacterial properties and high cytocompatibility. Overall, this work demonstrate that self-assembling peptide-chitosan composite hydrogels have significant potential as wound-contact material.

References

[1]Liu Z., Saiani A., Miller A.F. Investigating the co-assembly of amphipathic peptides. *Faraday Discussions* 2025; 260; 179-91.
[2]Che X., Zhao T., Hu J., Yang K., Ma N., Li A., Sun Q., Ding C., Ding Q. Application of chitosan-based hydrogel in promoting wound healing: a review. *Polymers* 2024; Jan 26 16(3); 344.

D2 – P215

Gelatin & pectin composite hydrogels: When the circular economy reinforces regenerative medicine

Kleisoura T.[1], Dimopoulou M.[2], Bikiaris R.[3], Tsamesidis I.[4], Kontonasaki E.[4], Boccaccini A.R.[5], Chatzistavrou X.[1]
[1]Dept. of Chemical Engineering, School of Engineering, Aristotle University of Thessaloniki, Thessaloniki, Greece; [2]School of Health & Life Sciences, Teesside University, Middlesbrough, UK; [3]Dept. of Chemistry, Aristotle University of Thessaloniki, Thessaloniki, Greece; [4]School of Dentistry, Aristotle University of Thessaloniki, Thessaloniki, Greece; [5]Dept. of Materials Science and Engineering, Institute of Biomaterials, University of Erlangen-Nuremberg, Erlangen, Germany

Introduction

Tissue Engineering is an interdisciplinary field that integrates engineering, medicine, and materials science to develop innovative solutions for the regeneration of soft and hard tissues. In this context, gelatin-based hydrogels, such as pure methacrylate gelatin (GelMA) and a composite system formed by blending GelMA with silver-doped bioactive glass nanoparticles (Ag-BGNPs), have attracted considerable interest. These systems demonstrate high water content, tunable structure, printability, biocompatibility, biodegradability, and bioactivity. At the same time, the growing demand for sustainable biomaterials has encouraged research to explore alternatives to conventional pork gelatin-based systems. Applying the principles of circular economy, food waste, e.g., orange peel, can be utilized as a renewable source of functional biopolymers for pectin hydrogel production. This study aims to develop pectin-based hydrogels and composites with properties comparable to those of gelatin-based ones, and appropriate for their use in biomedical applications. Thus, expanding the potential of tissue engineering by linking biomaterials innovation with circular economy practices.

Materials and Methods

Type A gelatin from pork skin was used to synthesize GelMA through methacrylation with methacrylic anhydride (MAA). After lyophilization, GelMA was dissolved in PBS with LAP photoinitiator to form hydrogels. Ag-bioactive glass nanoparticles (Ag-BG NPs) were synthesized via a modified Stöber method and dispersed in GelMA to prepare a composite bioink. Moreover, pectin extracted from powdered orange peel waste via aqueous extraction (pH 2, 80 °C, 1 h) followed by ethanol precipitation was used to prepare pectin hydrogels in PBS, with $CaCl_2 \cdot 2H_2O$ as an ionic crosslinker. The structure, morphology, and rheological characteristics of the developed materials were characterized, and their printability, cellular, and antibacterial properties were assessed.

Results

The structural characterization of the developed systems confirmed the successful synthesis of all types of hydrogels, identifying the characteristic peaks. Scanning Electron Microscopy images showed a porous structure, which allows swelling. Rheological testing indicated that all hydrogels have an inverse relationship between viscosity and temperature / shear rate (shear thinning behavior), with the pectin hydrogel not being particularly affected by temperature changes. Degradation study revealed that GelMA degraded within 33 days, with major mass loss after 14 days. Pectin hydrogel appears competitive with a stability up to 15 days. Both gelatin-based and pectin hydrogels ensure 3D printability and stability. Cell viability studies showed 94% viability for GelMA, outperforming the composite (83%). The biological properties of pectin hydrogel are also comparable to those of GelMA, highlighting superior biocompatibility in cell culture studies and potential for 3D printing while displaying antibacterial activity.

Conclusion

GelMA-based hydrogels demonstrated significant potential for biomedical applications. The incorporation of Ag-BGNPs enhanced their antibacterial properties, while their controlled rheological behavior and favorable printability supported their suitability as bioinks. In addition, pectin-based hydrogels exhibited competitive functional properties, emerging as a sustainable alternative biomaterial that aligns with circular economy principles and supports environmentally responsible strategies in tissue engineering.

References

[1]Marsh A.C. et al. A new BioInk for improved 3D bioprinting of Bone-Like constructs, bioRxiv (Cold Spring Harbor Laboratory). 2021. https://doi.org/10.1101/2021.11.04.467312.
[2]Ashammakhi N. et al. Bioinks and Bioprinting Technologies to Make Heterogeneous and Biomimetic Tissue Constructs. *Materials Today Bio* 2019; 1 (January); 100008. https://doi.org/10.1016/j.mtbio.2019.100008.
[3]Hamed R. et al. Green Hydrogels Prepared from Pectin Extracted from Orange Peels as a Potential Carrier for Dermal Delivery Systems. *ACS Omega* 2025; 10 (17); 17182-17200. DOI: 10.1021/acsomega.4c08449.
[4]Dimopoulou M. et al. Pectin recovery and characterization from lemon juice waste streams. *Journal of the Science of Food and Agriculture* 2019; 99(14); 6191–6198. DOI: 10.1002/jsfa.9891.

D2 – P216

Diffusion and solute–hydrogel interactions in a gelatin-based stromal model for a cornea-on-a-chip

Lamouline L.[1], Destrée B.[1], Franco A.[1], Bazazordeh S.[2], Reichert T.[2], Van Durme B.[3], Delcorte A.[1], Dupont-Gillain C.[1]

[1]Institute of Condensed Matter and Nanoscience, UCLouvain, Louvain-la-Neuve; [2]Center for Microsystems Technology and IMEC, University of Ghent, Ghent; [3]Centre of Macromolecular Chemistry, Ghent University, Ghent, Belgium

Introduction

Poor translation from preclinical studies to clinical trials remains a major challenge. Organ-on-a-chip technology offers a promising approach by integrating living cells within microfluidic platforms that reproduce key physiological features of human tissues.

A cornea-on-a-chip has been developed to replicate the structural and functional complexity of the human cornea, including its three main layers (epithelium, stroma, endothelium) and physiological flows. Accurate reproduction of transport behavior in vitro is critical for validating such systems. This study focuses on the stromal compartment, represented by a gelatin-based hydrogel, to evaluate solute transport.

Materials and Methods

Gelatin hydrogels were polymerized inside a microfluidic chip to mimic the stromal extracellular matrix. Diffusion experiments employed fluorescent probes with distinct properties (e.g. Rhodamine B). Fluorescence microscopy enabled spatial and temporal monitoring of solute concentration profiles within the hydrogel under controlled microfluidic conditions (Figure 1).

Concentration profiles were analyzed to extract effective diffusion coefficients. Partition experiments assessed solute distribution between the surrounding solution and hydrogel, probing solute–polymer interactions. Comparative experiments were conducted with PEG-based hydrogels of controlled charge densities.

Results

Fluorescence imaging visualized solute profiles and their evolution over time, allowing extraction of effective diffusion coefficients. Rhodamine B profiles showed pronounced peaks inside the hydrogel, indicating significant solute accumulation due to both molecular diffusion and interaction-driven retention (Figure 1).

Partition measurements confirmed solute–matrix interactions. PEG-based hydrogels with defined charge densities highlighted the role of electrostatic interactions in modulating solute distribution, supporting the negatively charged nature of gelatin hydrogel and explaining observed accumulation (Figure 2).

Conclusion

These findings show that solute transport in stromal hydrogel models is governed not only by diffusion but also by solute–matrix interactions. Accounting for these interactions is essential when interpreting transport in hydrogel-based organ-on-chip systems. This work represents a step toward validating gelatin hydrogels as stromal mimics in cornea-on-a-chip platforms. Future work will integrate an epithelial layer to study trans-corneal transport under more physiologically relevant conditions.

Acknowledgements

This project (40007548-GOJ3322N) has received funding from the FWO and F.R.S-FNRS under the Excellence of Science (EOS) program.




Figure 13: (A) Experimental setup for diffusion measurement in a microfluidic hydrogel mimicking stroma. (B) Rhodamine B diffusion profile, showing fluorescent intensity as a function of distance.




Figure 14: Charge-dependent solute distribution in PEG-based and GelMA (type B) hydrogels. Fluorescein (negative) and Crystal Violet (positive) in hydrogels with low or high ionic strength demonstrate the role of electrostatic interactions.

D2 – P217

Laponite doped injectable dextran hydrogels for controlled delivery of dexamethasone

Khan S.[1], Shajahan A.B.[1], Alexandris S.[2], Jing R.[3], Nielsen T.T.[3], Larsen K.L.[3], Pennisi C.P.[1]
[1]Dept. of Health Science and Technology, Aalborg University; [2]Dept. of Materials and Production, Aalborg University, Denmark; [3]Dept. of Chemistry and Bioscience, Aalborg University, Denmark

Introduction

Bone defects remain a significant clinical challenge, motivating the development of biomaterial approaches that support regeneration and can incorporate localized, controlled delivery of osteogenic factors. In this study, we developed an injectable, dextran-based supramolecular hydrogel for bone tissue engineering applications, capable of controlled dexamethasone delivery. The system is based on dynamic host–guest interactions between cyclodextrin- and adamantane-modified dextran, forming a reversible network that allows minimally invasive administration. Such supramolecular hydrogels offer the advantage of localized, controlled, and sustained drug release, which is critical for enhancing osteogenic differentiation while minimizing systemic side effects. This study aimed to investigate the influence of laponite incorporation on the mechanical properties of the hydrogel and its drug release profile.

Materials and Methods

Laponite nanoclay was incorporated into the hydrogel system to modulate mechanical properties and injectability. Key parameters, including dextran molecular weight, degree of substitution, host-to-guest anchor-point ratio, and laponite concentration, were systematically modified to optimize performance. Rheological and mechanical properties were assessed, with particular emphasis on shear-thinning behavior and compressive stiffness. Higher anchor-point ratios were employed to generate vacant cyclodextrin host sites, enabling efficient drug loading and controlled release. Hydrogel formulations that met predefined criteria, specifically a shear-thinning ratio below 0.5 and compressive stiffness within the range of 1-20 kPa, were selected for further evaluation. Degradability studies were conducted, and dexamethasone was incorporated into the optimized formulations to evaluate drug release kinetics over time.

Results

The incorporation of laponite significantly enhanced the mechanical properties of the hydrogels in a concentration-dependent manner. Increasing laponite content (0–3%) resulted in a marked increase in compressive stiffness, accompanied by a reduction in mesh size. Additionally, the introduction of laponite imparted pronounced shear-thinning behavior, supporting injectability and post-injection structural recovery. The optimized hydrogels exhibited suitable mechanical characteristics for non-weight-bearing bone tissue engineering applications. Laponite-doped hydrogels exhibited altered release kinetics relative to base dextran hydrogels, indicating a more sustained and controlled delivery of dexamethasone

Conclusion

We present an injectable supramolecular dextran hydrogel system with tunable mechanical and rheological properties, achieved by incorporating laponite. The nanoclay not only enhanced stiffness and injectability via shear-thinning behavior but also improved the controlled delivery of dexamethasone. This platform shows strong potential for minimally invasive bone tissue engineering applications requiring localized and sustained therapeutic delivery.

Acknowledgements

This research was funded by the European Union’s Horizon Europe programme through a Marie Skłodowska-Curie Postdoctoral Fellowship (Grant agreement ID: 101207455) for the project “BONEGEL: Development of a novel bone-adapting injectable smart hydrogel for bone tissue engineering.”

D2 – P218
Hyaluronic acid/polynucleotide hydrogel patch for enhanced wound healing

Kim Y.W., Park J.S., Lee K.Y.
Dept. of Bioengineering, Hanyang University, Seoul, Republic of Korea

Introduction
Hyaluronic acid (HA)-based hydrogels have been widely used in wound healing for decades. However, HA-only hydrogels often exhibit limited mechanical stability and lack the ability to actively regulate biological responses in vivo. Polynucleotide (PN) is known to promote angiogenesis and collagen synthesis, thereby enhancing cellular and extracellular remodeling during wound repair. However, conventional PN systems typically lack structural stability and sustained delivery capability, which are essential for maximizing therapeutic efficacy. In this study, PN was integrated into HA-based hydrogels prepared from oxidize HA and hydrazide-modified HA. We hypothesized that integration of PN into HA-based hydrogels could facilitate intermolecular interactions to improve hydrogel stability. The controlled release of PN from the hydrogel was also expected to enhance wound healing. Various physicochemical properties of hydrogels were characterized, and their therapeutic efficacy was evaluated in vivo using a mouse wound model.

Materials and Methods
Hydrogels were prepared with oxidize HA and hydrazide-modified HA in the presence of PN via reversible hydrazone bond formation, and their viscoelastic properties were evaluated using a rotational viscometer through frequency and strain sweep tests. In vitro PN release was quantified using a spectrophotometer. Various 3D constructs were fabricated using extrusion-based 3D printing, and their printability and shape fidelity were evaluated. The expression levels of vascular endothelial growth factor (VEGF) and collagen-related genes in human dermal fibroblasts (HDFs) were analyzed using quantitative PCR. In vivo wound healing efficacy was evaluated using a full-thickness mouse wound model.

Results
PN-containing hydrogels had higher storage modulus (G ′) values and structural stability compared with HA-only hydrogels. Hydrogels were 3D-printable via extrusion-based printing, with good printability and structural stability. In addition, PN exhibited a sustained release profile without an initial burst. These hydrogels enhanced HDF proliferation and significantly upregulated VEGF and collagen-related gene expression in vitro. In vivo, compared with non-treated controls, HA/PN hydrogel patches significantly promoted wound healing and increased angiogenesis and collagen remodeling in the mouse model.

Conclusion
HA/PN hydrogels represent a mechanically reinforced and bioactive platform for effective wound healing. The dynamic hydrazone-bonded network provided mechanical stability and self-healing capability for 3D printing. PN, as a bioactive substance, not only promoted angiogenesis and collagen synthesis but also contributed to enhancing the mechanical stability of the network. The sustained release of PN provided continuous regenerative signals throughout the wound healing process, resulting in the enhanced therapeutic efficacy. Compared with HA-only hydrogels, this approach demonstrated synergistic mechanical and biological effects. In this system, PN acts both as a therapeutic agent and as a functional component of the polymer network, further enhancing collagen remodeling and overall wound healing efficacy compared with conventional HA-based system.

Keywords: Hydrogels / Polynucleotide / Bio(material)inks / 3D printing / Wound healing
Research Topic: Biomaterials for tissue regeneration

References
[1]Uchida D.T., Bruschi M.L. 3D printing as a technological strategy for the personalized treatment of wound healing. *AAPS PharmSciTech* 2023; 24 (1); 41.
[2]Kong M., Kim H.S., Hwang J., Park J.S., Lee I.Y., Lee K.Y. Hyaluronic acid-based self-healing hydrogels with enhanced hydrolytic stability for 3D bioprinting in tissue engineering. *International Journal of Bioprinting* 2025; 11 (6); 374.
[3]Heo T.-H., Gu B.K., Ohk K., Yoon J.-K., Son Y.H., Chun H.J., Yang D.-H., Jeong G.-J. Polynucleotide and hyaluronic acid mixture for skin wound dressing for accelerated wound healing. *Tissue Engineering and Regenerative Medicine* 2025; 22 (4); 515–526.

D2 – P219

Immunomodulatory double-network hydrogel for effective wound healing

Park J.S., Kwon M.J., Lee K.Y.
Dept. of Bioengineering, Hanyang University, Seoul, Republic of Korea

Introduction

Effective wound healing requires mechanical protection of the wound site and appropriate regulation of the inflammatory response. Hydrogels have been widely used as wound dressings due to their ability to maintain a hydrated and biocompatible environment. Hyaluronic acid (HA)-based hydrogels are particularly attractive for tissue repair because they regulate cellular behavior and inflammation. However, HA hydrogels typically have poor mechanical properties and rapid degradation, limiting their practical application in wound healing[2]. In this study, we proposed a double-network hydrogel composed of oxidized HA and hydrazide-modified HA, integrated with an alginate/strontium ion (ALG/Sr^{2+}) network to enhance both mechanical properties and immunomodulatory activity for improved wound healing.

Materials and Methods

Double-network hydrogels were prepared from oxidized HA and hydrazide modified HA, incorporating the ALG/ Sr^{2+} network. Their chemical composition and mechanical properties were characterized using FT-IR spectroscopy, rheological analysis, and tensile testing. In vitro studies were performed to evaluate macrophage polarization and cytocompatibility of hydrogels. In vivo wound healing efficacy was assessed in a full-thickness mouse wound model.

Results

Rheological analysis confirmed that the double-network hydrogel recovered its storage modulus (G′) after repeated high-strain deformation, reflecting its reversible network structure and self-healing capability required for 3D printing. Cell viability analysis showed high cytocompatibility with macrophages and keratinocytes. In vitro inflammation studies demonstrated that Sr^{2+} containing hydrogels promoted macrophage polarization toward an anti-inflammatory phenotype by downregulating M1 markers and upregulating M2 markers. These immunomodulatory effects depended on Sr^{2+} concentration in the hydrogel. In vivo, the Sr^{2+} containing double-network hydrogel significantly accelerated wound closure and enhanced skin tissue regeneration.

Conclusion

We developed a HA-based double-network hydrogel with enhanced mechanical stability and immunomodulatory activity by integrating a dynamic HA network with an ionically crosslinked ALG/Sr^{2+} network. The reversible hydrazone bonds enabled structural stability and self-healing behavior, while the ALG/Sr^{2+} network provided mechanical reinforcement. Sr^{2+} ions actively modulated the inflammatory response by promoting macrophage polarization toward an anti-inflammatory M2 phenotype, which supports progression to the proliferative phase of wound healing. These combined effects resulted in enhanced wound closure and improved tissue regeneration in vivo. Overall, this suggests that the proposed hydrogel system is a promising biomaterial for effective wound healing applications.

References

[1]Liang Y., He J., Guo B. Functional hydrogels as wound dressing to enhance wound healing. *ACS Nano* 2021; 15(8); 12687–12722.
[2]Kong M., Kim H.S., Hwang J., Park J.S., Lee I.Y., Lee K.Y. Hyaluronic acid-based self-healing hydrogels with enhanced hydrolytic stability for 3D bioprinting in tissue engineering. *International Journal of Bioprinting* 2025; 11 (6); 374.

D2 – P220

Engineering tunable granular hydrogels to model tumor–immune interactions: Effects of microstructure and mechanics on cancer cells and T cell infiltration

Feng S.[1,2], Cheng R.[1,2], Wang M.[1,2], Valle Delgado J.[3], Hirvonen S.-P.[4], Wang S.[1,2]
[1]Dept. Pharmacy, University of Helsinki; [2]Institute of Biotechnology, Helsinki Institute of Life Science (HiLIFE), University of Helsinki; [3]Dept. Bioproducts and Biosystems, Aalto University; [4]Dept. Chemistry, University of Helsinki, Helsinki, Finland

Introduction

The tumor microenvironment (TME) is characterized by complex physical and biological heterogeneity, where matrix mechanics and porosity critically influence both tumor progression and immune cell behavior. *In vitro* 3D models that can recapitulate these physical barriers are therefore essential for understanding tumor-immune interactions. Granular hydrogels offer a promising platform for engineering such biomimetic microenvironments. This study aims to develop tunable granular hydrogel models with controlled porosity and stiffness to investigate how microstructural and mechanical cues regulate immune cell infiltration and tumor cell dynamics.

Materials and Methods

The granular system was constructed from microspheres with tunable sizes and stiffness, with packing density controlled via centrifugation or vacuum-assisted assembly, followed by photo-initiated annealing to achieve precise regulation of porosity and mechanical properties. B16-OVA tumor spheroids were embedded within the granular hydrogel scaffold. Cytotoxic T cells were introduced into the surrounding culture medium to facilitate their infiltration and interaction with tumor cells.

Results

Microspheres with tunable sizes (100–300 μm) and stiffness (0.5–3 MPa) were successfully fabricated. Following UV-induced annealing, stable granular hydrogel scaffolds with well-defined pore structures were obtained. B16-OVA melanoma cells, introduced as multicellular spheroids, exhibited distinct morphological behaviors ranging from confined to more spread and elongated phenotypes, depending on the microstructural properties of the matrix. These variations further modulated tumor–immune interactions by influencing T cell infiltration and tumor killing.




Fig.1 (a) Schematic of granular hydrogel scaffold assembly; (b) Microspheres of varying sizes before and after assembly; (c) Distribution of microsphere size, stiffness, and resulting porosity; (d) 3D reconstruction of the scaffold with pore visualization.

Conclusion

Tunable GelMA-based granular hydrogels show promise as a controllable in vitro tumor immunotherapy model.

Acknowledgements

The authors are grateful for the Research Funding from the Sigrid Juselius Foundation.

D2 – P221

Evaluation of geometric confinement as driving tool for the fusion of hiPSC spheroids into complex tissues: Polarized intestinal tuboids

Lemarié L.[1,2] & Sohier J.[2]
[1]SEGULA Technologies France, Nanterre; [2]CNRS UMR 5305, LBTI (Tissue Biology and Therapeutic Engineering Laboratory), Lyon, France

Introduction

Human intestinal organoids derived from induced pluripotent stem cells (hiPSCs) are promising models for studying intestinal morphogenesis and developing future diagnostic or therapeutic platforms. However, conventional organoid cultures produce heterogeneous spherical structures with limited architectural control. While bioprinting enables spatial organization of cells, it requires complex materials and fabrication steps. Guiding tissue self-organization through geometric confinement represents an alternative strategy to promote controlled morphogenesis of intestinal microtissues. Here, we investigated how the diameter of confined tubular environments influences fusion, viability, and morphogenesis of hiPSC spheroids toward polarized intestinal tuboids.

Materials and Methods

hiPSCs (AG08C5 cell line, MMG, Marseille, France) were used to generate spheroids using a pellet-based aggregation method, enabling production of homogeneous multicellular aggregates. Spheroids were collected, pelleted, and combined with a small amount of Matrigel® (~80/20 spheroid–matrix ratio) to promote fusion. Cylindrical molds with internal diameters (400 µm and 800 µm) were fabricated by casting agarose around removable cylindrical templates, generating hollow microtubes. Agarose was selected as an inert, non-adhesive material to prevent cell–matrix interactions and ensure that tissue organization was driven by spheroid self-assembly and cell–cell interactions. The mixture was inserted into the molds, and constructs were stabilized at 37 °C and maintained for 48 hours in pluripotency medium before intestinal differentiation. Cultures were maintained up to 9–11 days with daily monitoring. Histological characterization was performed on paraffin sections (5 µm) using hematoxylin–phloxine–saffron, Masson's trichrome, and Alcian blue staining.

Results

Following injection into the confined tubular environment, hiPSC spheroids aggregated and fused into a continuous multicellular structure. Early compaction and partial fusion were observed during the first two days, followed by formation of a dense biomass between day 2 and day 7.

At day 10, constructs in 400 µm microtubes exhibited tubular morphology, with spheroid fusion, tissue polarization, and emergence of a continuous lumen, occasionally associated with epithelial outgrowths (Figure 1-A). In contrast, 800 µm constructs showed biomass accumulation but formed dense tissues with limited structural organization, suggesting impaired morphogenesis (Figure 1-B).




Figure 15 : Brightfield images after 10 days of hiPSC-derived constructs in (A) 400 µm and (B) 800 µm microtubes, showing tubular organization and polarization in 400 µm conditions versus dense, thick tissue formation in 800 µm constructs.

After differentiation, a morphogenetic transition toward a tubular intestinal structure was observed. Alcian blue staining at day 9 confirmed presence of a polarized epithelial layer with mucopolysaccharide secretion in 400 µm tuboids. Conversely, 800 µm constructs displayed a compact structure with a central necrotic core and no detectable mucus secretion, indicating loss of epithelial organization and function.




Figure 16 : Alcian blue staining of sections from intestinal constructs at D9 in (A) 400 µm and (B) 800 µm microtubes, showing epithelial polarization and mucus secretion in 400 µm versus dense tissue with necrotic core and no secretion in 800 µm.

These observations indicate that the fused spheroid assembly can reorganize into a tubular epithelial structure during differentiation under appropriate geometric confinement.

Conclusion

Geometric confinement of hiPSC spheroids enables rapid fusion and promotes morphogenesis of polarized intestinal tuboids within a short culture period. Our results identify a critical geometric threshold, as a confined diameter of 400 µm supports tissue viability and organization, whereas increasing diameter to 800 µm leads to necrosis and loss of structural coherence. This approach provides a simple strategy to generate organized digestive microtissues from hiPSCs and represents a foundation for scalable mini-gut production. Future developments will focus on integrating perfused culture systems and analyzing additional epithelial markers to enhance tissue maturation and functional relevance.

D2 – P222

Blue light–crosslinked thiol–ene fish gelatin hydrogel enables localized delivery and osteogenic differentiation of equine DP-MSCs

de Meij E.[1,2], Pien N.[1,2], Meeremans M.[1,2], Lim K.[3], De Schauwer C.[1] and Van Vlierberghe S.[2]
[1]Veterinary Stem Cell Research Unit, Dept. of Translational Physiology, Infectiology and Public Health, Faculty of Veterinary Medicine, Ghent University, Merelbeke, Belgium; [2]Polymer Chemistry and Biomaterials Group, Centre of Macromolecular Chemistry, Faculty of Sciences, Ghent University, Ghent, Belgium; [3]The University of Sydney School of Medical Sciences, Sydney, Australia

Introduction

Equine periodontitis is a major cause of tooth loss in horses, yet current treatments are limited to mechanical debridement, lavage, and temporary fillings that are often cytotoxic and lack long-term stability. Systemic therapies are largely ineffective due to poor drug penetration into periodontal pockets, highlighting the need for localized regenerative strategies. In this study, we developed a visible-light crosslinkable, norbornene-functionalized fish gelatin (GelNB) hydrogel platform for in situ periodontal tissue engineering. The effect of thiolated crosslinkers (DTT vs. GelSH) was evaluated when crosslinking using blue dental lamp light and a ruthenium/sodium persulfate (Ru/SPS) photo-initiator system. We also investigated the combination of equine dental pulp–derived mesenchymal stromal cells (DP-MSCs) with this injectable hydrogel for periodontal bone regeneration.

Materials and Methods

Cold-water fish gelatin was modified to yield gelatin-norbornene (Gel-NB) and thiolated gelatin (Gel-SH), enabling thiol–ene crosslinking. A precursor solution (10% w/v, equimolar NB/SH) containing 0.1 mM ruthenium and 2 mM sodium persulfate was crosslinked under blue light (460 nm, 1400 mW/cm²) for 60 s. In situ photorheology monitored gelation kinetics, and compressive modulus was assessed. Equine DP-MSCs were encapsulated at 2 × 10⁶ cells/mL to assess cytocompatibility and osteogenic potential within the 3D microenvironment. To assess osteogenic differentiation, alkaline phosphatase (ALP) activity and calcium deposition were measured as early and late markers, respectively.

Results

The obtained degrees of substitution (DS) were quantified using an OPA assay with results showing a DS of 93% for GelNB and 67% for GelSH, respectively. GelNB-GelSH hydrogels exhibited higher storage moduli (8.7 kPa), suggesting a denser and more interconnected network architecture compared to GelNB-DTT hydrogels (4 kPa). Osteogenic differentiation was evaluated within the GelNB-GelSH hydrogels using early and late markers. Alkaline phosphatase (ALP) activity was elevated between day 7 and day 14 but not significantly different between control and differentiated groups. In contrast, calcium deposition was significantly increased in the differentiation group at days 14 and 21, demonstrating progression toward matrix mineralization.

Conclusion

This study demonstrates the regenerative potential of equine DP-MSCs within a cytocompatible, injectable, and photo-crosslinkable Gel-NB/Gel-SH hydrogel. The platform supports osteogenic maturation and represents a promising strategy for localized periodontal bone regeneration in equine patients.

Acknowledgements

S. Van Vlierberghe and E. de Meij acknowledge the support from the Interreg FWVL programme VI (Healthy Teeth, 0100096), co-funded by the European Regional Development Fund.

D2 – P223

Biomimetic 3D hydrogels for prostate tissue modeling

Restivo E.[1], Cavarzan F.[2], Cremonesi M.[2], Guagliano G.[2], Briatico-Vangosa F.[2], Chiarugi P.[3], Giannoni E.[3], Iozzo M.[3], Gangarossa G.[3], Bloise N.[1], Petrini P.[2]
[1]Dept. of Molecular Medicine, University of Pavia, Pavia; [2]Dept. of Chemistry, Materials, and Chemical Engineering 'G. Natta', Politecnico di Milano, Milan; [3]Dept. of Experimental and Clinical Biomedical Sciences "Mario Serio," University of Florence, Florence, Italy

Introduction

Hydrogel-based three-dimensional (3D) models are useful for mimicking the biological and mechanical environments of tissues. It is important to study and understand the interplay between structure, composition and function to modulate hydrogel properties.

Aim

The objective of this study was to engineer an internally cross-linked alginate/gelatin-based hydrogel that could provide a physiologically relevant 3D microenvironment capable of supporting either healthy or cancerous prostate cells. The ultimate goal was to combine these cells together to study the microenvironment and progression from healthy to tumor status.

Materials and Methods

An internally cross-linked alginate-gelatine hydrogel with tunable viscoelastic properties was developed and produced by sequentially mixing solutions/suspensions of gelatin, alginate, $CaCO_3$, and GDL (glucono-delta-lactone), in prostate cell medium at a specific ratio.
Hydrogels were produced with and without prostate cells (either cancerous or healthy tissue). The samples without cells were studied in terms of their rheological properties, pH and stability. Hydrogels with embedded cells (either myofibroblast WPMY-1 or 22Rv1 cancerous cells), were studied in terms of cell viability, metabolic activity, and distribution over time.

Results

The results of the rheological analyses showed that the stiffness of the produced hydrogels is in the same range identified for prostate tissue. The produced hydrogels provided good support for the growth and homogeneous distribution of cells (both cancerous and healthy) along the hydrogel.

Conclusion

The produced hydrogel reproduces the micromechanical environment of prostate tissue, providing a reliable and adaptable in vitro platform for the rational design of advanced multicellular 3D models.

D2 – P224

A self-healing alginate hydrogel for vascularized tissue regeneration

Vilela de Sousa I.[1,2], Magalhães M.[1,2], Araújo M.[1], Calejo I.[3], Barrias C.C.[1,4]
[1]i3S- Institute for Research and Innovation in Health; [2]Faculty of Engineering - University of Porto, Porto, Portugal; [3]RISE-Health, Faculty of Medicine, University of Porto; [4]ICBAS-School of Medicine and Biomedical Sciences, Porto, Portugal

Introduction

Self-healing hydrogels are attractive biomaterials for minimally invasive tissue engineering owing to their ability to recover structural integrity following mechanical disruption. This behaviour, enabled by dynamic covalent bonds, confers injectability while allowing adaptation to irregular tissue defects. Alginate is widely used in regenerative medicine because of its biocompatibility and ease of processing; however, conventional ionically crosslinked alginate hydrogels lack self-healing capacity and exhibit limited mechanical adaptability. Incorporating reversible covalent crosslinks can impart self-healing behaviour, enabling injectable hydrogel formation and minimally invasive delivery. In addition, the dynamic nature of these networks may create a more permissive microenvironment for cell-mediated remodelling, migration, and organization. These properties are particularly relevant for vascular tissue engineering, where the hydrogel matrix must accommodate cell-mediated remodelling while supporting endothelial outgrowth and neovessel formation.

Aim

To engineer a self-healing alginate hydrogel as an injectable platform for minimally invasive vascular tissue engineering.

Materials and Methods

Oxidized alginate (ALG-OXI) was prepared by periodate oxidation method, while hydrazide-modified alginate (ALG-ADH) and RGD-functionalized oxidized alginate (ALG-OXI-RGD) were synthesized by EDC/NHS-chemistry. All derivatives were characterized by ^{1}H-NMR and size-exclusion chromatography (SEC). Hydrogels were generated by mixing the different alginate derivatives at varying concentrations and hydrazide-to-aldehyde ratios. Viscoelastic properties and self-healing behaviour were evaluated by oscillatory rheology. Human Dermal Neonatal Fibroblasts (HDNFs) were embedded within the hydrogels and cultured for 14 days. Cell viability, metabolic activity, and morphology were assessed using live/dead staining, resazurin assay, and IF. To evaluate endothelial sprouting, vascularized microtissues (vascular units, VUs) composed of endothelial colony-forming cells (ECFCs) and fibroblasts were embedded within the hydrogels and analysed by IF.

Results

^{1}H-NMR and SEC analyses confirmed the successful synthesis of the alginate derivatives. Rheological characterization demonstrated that hydrogel mechanical properties could be tuned by varying the hydrazide-to-aldehyde ratio. Following repeated high-strain deformation cycles (G'' > G'), the storage modulus (G') recovered to values close to those measured prior to disruption, confirming efficient self-healing behaviour. Embedded fibroblasts remained viable throughout culture and displayed a more elongated morphology in softer hydrogel formulations (Figure 1). The best hydrogel formulations also supported cell migration and endothelial sprouting from embedded VUs.

Conclusion

A self-healing alginate hydrogel was developed that combines injectability with support for cell migration and endothelial sprouting, highlighting its potential for minimally invasive vascular tissue engineering.

Acknowledgements

Vilela de Sousa I. acknowledges Fundação para a Ciência e a Tecnologia (FCT) for the PhD Grant (2023.01867.BD).




Figure 17. 3D network of spreading HDNF in the self-healing alginate hydrogel.

D2 – P225

Evaluation of macrophage-mediated immunomodulatory responses to bone extracellular matrix-derived hydrogels

Bidipto C., Yang-hee K.
Bone and Joint Research Group, Human Development and Health, Institute of Developmental Sciences, Southampton General Hospital, Southampton, UK

Introduction

Major non-union bone defects remain a major clinical challenge, necessitating biomaterials that actively promote osteogenesis. Hydrogels derived from demineralised and decellularised bone extracellular matrix (bECM) are highly promising due to their ability to retain native biochemical cues, which significantly enhances stem cell proliferation compared to synthetic polymers[1]. However, clinical success of these bioscaffolds also depends on the host immune response. Macrophages act as crucial regulators at the biomaterial interface, mediating transition from initial inflammation to tissue remodelling[2]. Therefore, this study aims to evaluate the immunomodulatory properties of bECM hydrogels by investigating the inflammatory, migratory, and phenytoic responses of RAW 264.7 macrophages cultured directly on the hydrogel.

Materials and Methods

bECM hydrogels were prepared via sequential demineralisation, decellularisation, and enzymatic digestion of bone tissue. RAW 264.7 macrophages were seeded onto three experimental substrates: tissue culture plastic (TCP; negative control), Collagen Type I hydrogels (positive control), and the bECM hydrogels. Constructs were maintained in vitro for 1 and 3 days. Cell migration dynamics and morphology were analysed quantitatively using time-lapse microscopy and immunocytochemical (ICC) staining. To evaluate macrophage polarisation, the expression of key pro- and anti-inflammatory genes was quantified via RT-qPCR. Concurrently, the secretion profiles of phenotypic cytokine markers were characterised using semi-quantitative enzyme-linked immunosorbent assays (ELISA).

Results

Staining following one- and three-day incubation periods revealed atrophy and a decrease in cells. Low persistence (ratio of mean displacement of cell and actual length travelled) and low mean velocity were seen across the substrates in the migration assay. Both pro- and anti-inflammatory genes (IL-6 and IL-10) were upregulated in bECM hydrogels compared with tissue culture plastic and collagen gels, indicating the simultaneous promotion of pro-inflammatory and pro-regenerative macrophage functions. Semi-quantitative ELISA analysis revealed similar trends, with significantly elevated IL-10 and TNF-α cytokine levels in the bECM gel.

Conclusion

The bECM hydrogel significantly modulates gene expression and cytokine profiles of macrophages, eliciting a complex, hybrid activation state. The high density of the current bECM gel limits optimal staining resolution and cellular migration; therefore, further studies optimising hydrogel crosslinking and density are required to fully evaluate the immunomodulatory potential for bone regeneration.




Fig. 1 Expression of Inflammatory and Immunomodulatory genes in macrophages cultured on bone-ECM derived hydrogels




Fig. 2 Relative cytokine secretion by macrophages cultures on different substrates

References

[1]Xu D. et al. *J. Biomed. Mater. Res. A* 2024; 112; 1104-1115.
[2]White L. et al. *Biomaterials* 2025; 312; 120760.

D2 – P226

Supercritical CO2–decellularized amniotic ECM hydrogel promotes immunomodulatory skin regeneration

Ye S.[1,2], Kim Y-J.[1,] Yoo J. [1], Choi I.C.[3], Lee K.[2], Park J.W.[3], Jung Y.[1]
[1]Center for Biomaterials, Biomedical Research Institute, Korea Institute of Science and Technology (KIST); [2]Dept. of Applied Bioengineering, Graduate School of Convergence Science and Technology, Seoul National University; [3]Dept. of Orthopedic Surgery, College of Medicine, Korea University, Seoul, South Korea

Introduction

Acute ultraviolet B (UVB) exposure triggers rapid skin inflammation marked by immune cell infiltration, extracellular matrix (ECM) degradation, and tissue dysfunction. Conventional treatments such as hydrating dressings, hyaluronic acid/collagen formulations, and exogenous growth factors offer only partial benefits, as they poorly modulate the inflammatory and regenerative microenvironment of damaged skin. Amniotic membrane-derived ECM is rich in growth factors and anti-inflammatory cytokines, yet conventional decellularization often destroys these bioactive cues. We therefore developed a single-component bioactive hydrogel from supercritical CO_2 ($scCO_2$)-decellularized porcine amniotic membrane (dPAM) that preserves native matrix-associated signals.

Aim

To fabricate and evaluate a scCO2-decellularized dPAM hydrogel that preserves bioactive ECM cues and provides combined anti-inflammatory and pro-regenerative effects for photodamaged skin.

Materials and Methods

Porcine amniotic membrane was decellularized with $scCO_2$ (37 °C, 300-350 bar) and processed into a 2% (w/v) thermoresponsive hydrogel. Decellularization and ECM preservation were assessed by DNA/collagen/GAG quantification, histology, cytokine arrays, and LC-MS/MS proteomics; rheology, swelling, and degradation characterized the hydrogel. In vitro assays evaluated HUVEC tube formation, THP-1 macrophage polarization, and human follicle dermal papilla cell (HFDPC) gene expression. In vivo efficacy was tested in a UVB-induced (500 mJ/cm^2) murine skin inflammation model against PBS and collagen hydrogel controls.

Results

$scCO_2$ treatment reduced residual DNA to 83.9 ng/mg while retaining ~90% of GAGs and key factors (Decorin, IL-28B, PDGF-BB, VEGF). The dPAM hydrogel showed stable elastic behavior (G′ 125-300 Pa), ~400% swelling, and structural integrity for up to 7 days. It enhanced endothelial tube formation, downregulated TNF-α and IL-1β in M1-like macrophages, and upregulated angiogenic (VEGF, ANGPT1), immunoregulatory (IL-10, TGF-β1, IDO-1), and hair follicle-related (Wnt3, β-catenin) genes in HFDPCs. In vivo, dPAM accelerated wound closure, reduced neutrophil (MPO) infiltration, increased CD206+ macrophages, elevated the COL1/COL3 ratio, and promoted hair follicle-like structures.

Conclusion

The $scCO_2$-decellularized dPAM hydrogel preserves bioactive ECM cues and delivers dual anti-inflammatory and pro-regenerative functions, offering a promising bioactive platform for photodamaged skin repair that goes beyond passive wound dressings.

Acknowledgements

This work was supported by the National Research Foundation of Korea (NRF) funded by the Korea government (MSIT) (RS-2025-00518691) and the Technology Innovation Program (RS-2024-00443495, RS-2025-03373015) funded by the Ministry of Trade, Industry & Energy (MOTIE, Korea).




Fig. 1. (A) Schematic of the scCO2-based decellularization process used to prepare the dPAM scaffold and hydrogel. (B) Proposed regenerative effects of the dPAM hydrogel in modulating UVB-induced inflammatory responses and supporting skin repair.

References

[1]Ye S., Kim Y-J., Yoo J., Choi I.C., Lee K., Park J.W., Jung Y. Supercritical CO_2-decellularized amniotic ECM hydrogel promotes immunomodulatory skin regeneration. *Materials Today Bio* 2026; 38; 103293.

D2 – P227

Establishing a lymphatics-on-a-chip model to study bone marrow mesenchymal-lymphatic endothelial cell interactions in non-union fractures

Ghyselen H.[1,2], Verbraeken T.[1,2], Comeliau L.[3], Bekisz S.[3], Tylzanowski P.[1,2,4], Geris L.[1,2,3,5]
[1]Skeletal Biology and Engineering Research Center, KU Leuven, Leuven, Belgium; [2]Prometheus, Division of Skeletal Tissue Engineering, KU Leuven, Leuven, Belgium; [3]Biomechanics Research Unit, GIGA In Silico Medicine, University of Liège, Liège, Belgium; [4]Laboratory of Molecular Genetics, Medical University of Lublin, Lublin, Poland; [5]Biomechanics Section, Dept. of Mechanical Engineering, KU Leuven, Leuven, Belgium

Introduction

Non-union fractures represent a major clinical challenge and are often associated with persistent inflammation that disrupts normal bone healing. Emerging evidence suggests that lymphatic vessels play a role in modulating inflammation and tissue regeneration, but their contribution to bone repair remains unclear. This study aimed to establish an organ-on-a chip model, enabling controlled investigation of cellular interactions influencing lymphangiogenesis in the context of non-union fractures.

Materials and Methods

In silico analysis of single-cell RNA sequencing and spatial transcriptomics datasets from murine and human bone defects was performed to identify potential cellular sources of lymphangiogenic factors. A microfluidic lymphatics-on-a-chip model was used to study lymphatic endothelial cell (LEC) sprouting. Paracrine interactions were assessed using conditioned medium from bone marrow mesenchymal cells (BMMCs). Direct co-culture of BMMCs and LECs was established on the chip, to evaluate cell–cell interactions in an isolated, yet physiologically relevant microenvironment. Inflammatory conditions characteristic of non-union were simulated using TNFα.

Results

Computational analysis identified $Cxcl12^{+}$ bone marrow stromal cells as a major source of VEGF-C, suggesting a role in lymphatic recruitment. Conditioned medium from BMMCs contained VEGF-C but did not induce LEC migration or sprouting, likely due to insufficient activation of the growth factor in the absence of proteolytic processing. Rescue experiments excluded inhibitory effects. Direct co-culture of BMMCs and LECs demonstrated the feasibility of modelling cellular interactions, although interpretation was limited by similar responses in controls. TNFα-induced inflammation significantly reduced LEC migration and sprouting, indicating impaired lymphangiogenic responses under inflammatory conditions.

Conclusion

This study presents a microengineered lymphatics-on-a-chip platform that enables investigation of potential BMMC-mediated lymphangiogenesis in the context of bone regeneration. The system provides an isolated yet physiologically relevant environment to elucidate the underlying mechanisms governing lymphatic behaviour.


D2 – P228

Tailoring the microenvironment: Microfiber-reinforced cryoprinted scaffolds for biomimetic cartilage repair

Silva M.[1], Leal A.[1], de Sousa Cunha M.H.[2], Menezes A.[3], Marciano F.R.[1], Lobo A.[1]
[1]BioMatLab, PPGCM, Federal University of Piauí, Medical Clinic, Piauí; [2]State University of Campinas, Campinas; [3]Physics Dept., Federal University of Maranhão, Maranhão, Brazil

The study focuses on fabricating and evaluating hybrid scaffolds of printed GelMA hydrogels reinforced with multilayers of Poly(Lactic Acid) (PLA)/Laponite (LAP) microfibers membranes. [1-2] PLA microfibers with varying amounts of LAP (0, 1.0, and 2.5) were synthesized using rotary-jet spinning and electrospinning after that were subjected to oxygen plasma treatment. Scanning electron microscopy (SEM), Fourier transform infrared spectroscopy (FTIR), and x-ray diffraction (XRD) were utilized for morphological and compositional analyses. Other tests were injectability, fiber diameters, and contact angle, to determine solution specifications. The membranes were subjected to plasma treatment and demonstrated through the contact angle that became more hydrophilic. Their mechanical properties were evaluated via uniaxial tensile testing, highlighting improved mechanical strength by incorporating LAP. The electrospinning synthesized group presented the smallest diameter of about 0.6µm and better results in tensile strength, while the microfibers synthesized using rotary-jet spinning have a diameter of about 3µm. The microfibers membranes were integrated into printed GelMA hydrogel layers, creating GelMA-PLA/LAP hybrid scaffolds, whose interaction and integrity were confirmed through SEM. Mechanical assessment via uniaxial compression tests demonstrated a significant enhancement in the mechanical properties of the hybrid scaffolds attributed to the inclusion of microfibers membranes, the groups of electrospinning presented better results tensile strength compression strength. These findings underscore the potential utility of the scaffolds in tissue engineering applications by capitalizing on the mechanical reinforcement imparted by PLA/LAP microfibers layers. After that, the scaffolds were printed at a cryogenic temperature of about -20°C with the inclusion of the best groups of microfibers by rotary-jet spinning and electrospinning, this temperature variation promotes the increase in the compressive strength result compared to the other group printed in room temperature. The results support the development of research in this area and the investigation of printing at low temperatures due to improved mechanical properties in soft tissues.

Figure 1: Graphical abstract.



References

[1]e Silva M. C.S., et al. Tailoring mechanical properties of printed GelMA scaffolds with multilayers of PLA/Laponite nanocomposite fibers. *Mater. Lett* 2024; 364; 136314.
[2]da Silva F.T., et al. Establishing a framework for the design and fabrication of patient-specific scaffolds targeting partial meniscal defects. *Int. J. Bioprinting* 2025; 8109.

D2 – P229

Suppression of pro-inflammatory genes by calcium doped mesoporous nanoparticles for pharmacological applications

Axypolitou S., Tsamesidis I., Pouroutzidou G.K., Kontonasaki E.
School of Dentistry, Aristotle University of Thessaloniki, Thessaloniki, Greece

Introduction

Chronic inflammation is a major contributor to the pathogenesis of numerous diseases, including autoimmune disorders, cardiovascular conditions, and cancer[1]. Targeted suppression of pro-inflammatory gene expression represents a promising pharmacological strategy to control excessive inflammatory responses. Calcium-doped mesoporous silica nanoparticles (Ca-MSNs) have emerged as versatile nanomaterials with tunable physicochemical properties that may enable modulation of cellular signaling pathways[2]. In this study, we evaluate the capacity of Ca-MSNs to knock down key pro-inflammatory genes in activated macrophages and explore their potential for pharmacological applications in inflammatory conditions.

Materials and Methods

Ca-MSNs were synthesized in basic environment using a modified sol–gel method. Their anti-inflammatory potential was evaluated in vitro using RAW 264.7 macrophages, which were seeded in 48-well plates and allowed to adhere for 24 h. Cells were stimulated with lipopolysaccharide (LPS, 10 ng/mL) to induce an inflammatory response and treated with Ca-MSNs at concentrations of 1 mg/mL, 0.5 mg/mL, and 0.125 mg/mL. At 6, 12, and 24 h post-treatment, total RNA was extracted for cDNA synthesis and gene expression analysis of TNF-α, IL-6, and iNOS using real-time quantitative PCR. Additionally, TNF-α protein levels were measured in the culture supernatants at 24 h using ELISA to evaluate the effect of Ca-MSNs on cytokine secretion.

Results

LPS stimulation induced a robust inflammatory response in RAW 264.7 macrophages, with marked upregulation of TNF-α, IL-6, and iNOS. Treatment with Ca-MSNs effectively reduced the expression of all markers, with the lowest concentration (0.125 mg/mL) producing the strongest knockdown. Higher concentrations also suppressed inflammatory gene expression, but to a lesser extent. ELISA analysis of TNF-α protein levels confirmed the PCR results. While LPS significantly increased TNF-α secretion compared to untreated controls, Ca-MSN treatment at 1 mg/mL and 0.5 mg/mL partially reduced cytokine release, whereas 0.125 mg/mL restored TNF-α levels close to baseline. These findings indicate that Ca-MSNs possess a dose-dependent anti-inflammatory effect, with the lowest tested concentration demonstrating the highest efficacy.

Conclusion

Calcium-doped mesoporous silica nanoparticles effectively reduced pro-inflammatory gene expression and TNF-α secretion in macrophages, with the lowest tested concentration (0.125 mg/mL) showing the strongest anti-inflammatory effect. These findings highlight the potential use of Ca-MSNs as a pharmacological tool for controlling macrophage-mediated inflammation.

References

[1]Chavda V. P., Feehan J., Apostolopoulos V. Inflammation: The Cause of All Diseases. *Cells* 2024; *13*(22). doi:10.3390/cells13221906
[2]Liu Y., Zhao M., Zhang M., Yang B., Qi Y.K., Fu Q. Mesoporous Silica Nanoparticle-Based Nanomedicine: Preparation, Functional Modification, and Theranostic Applications. *Mater. Today Bio* 2025; 34. doi:10.1016/j.mtbio.2025.102223.

D3 – P001

Artificial extracellular matrices based on biohybrid hydrogels for CAR-T cell culture

Merlina F.[1], Castellote-Borrell M.[1], Giménez M.[2], Juan M.[2], Guedan S.[2], Guasch J[1].
[1]Dynamic Biomaterials for Cancer Immunotherapy, Max Planck Partner Group, Institut de Ciència de Materials de Barcelona (ICMAB-CSIC), Campus UAB, Bellaterra; [2]Dept. of Hematology, Hospital Clinic, Institut d'Investigacions Biomèdiques August Pi i Sunyer (IDIBAPS), Barcelona, Spain

Introduction

Adoptive Cell Therapy (ACT) is a promising cancer treatment based on the ex vivo engineering and expansion of a patient's immune cells to enhance their anti-tumor activity after reinfusion. Up to date, the most successful clinical results have been obtained with the engineered chimeric antigen receptor (CAR) T cells. However, many challenges need to be overcome to obtain an effective and prolonged immune response against cancer cells. One of the problems that remains unsolved is to reproduce ex-vivo the lymph node microenvironment, in which T cells are activated in vivo. We have recently demonstrated that synthetic scaffolds based on hybrid PEG-heparin hydrogels are an interesting strategy to engineer such lymphoid microenvironment for primary CAR CD4+T cell culture by increasing the percentage of CAR+ T cells and their ability to proliferate (1).

Aim

This work aims to explore these artificial extracellular matrices for both CAR CD4+ and CAR CD8+T cell expression, differentiation and exhaustion when cells are cultured in our 3D hydrogels vs in suspension.

Materials and Methods

To produce PEG-heparin hydrogels, 4-arm thiolated PEG is mixed with heparin-maleimide and incubated overnight at 37 °C, resulting in a covalently cross-linked hydrogel. For inverse opal (IOPAL) hydrogel fabrication, an aqueous suspension of PMMA beads with diameters of either 80 or 120 µm is used as template precursor. The suspension is added into 5 mm wells and allowed to dry completely. Once the solvent has evaporated, the mixture of PEG and heparin-maleimide is applied onto the template and permitted to infiltrate the interstitial spaces. The system is then incubated at 37 °C for at least 48 h. The final IOPAL hydrogels are produced after opal removal with glacial acetic acid. Cellular behavior was assessed through flow cytometry and confocal microscopy.

Results

We observed differences in CAR-T cell phenotypes (differentiation and exhaustion) when cells are cultured on our hydrogels vs in suspension. We also observed an incremented % of CAR+ T cells in our hydrogels with consequences in tumor cytotoxicity.

Conclusion

We demonstrated that our hydrogels represent an interesting strategy to reproduce ex-vivo the lymph node microenvironment in order to explore their potential application in ACT.

References

[1]Castellote-Borrell M., Domingo M., Merlina F., Lu H., Colell S., Bachiller M., Juan M., Guedan S., Faraudo J., Guasch J. Lymph-Node Inspired Hydrogels Enhance CAR Expression and Proliferation of CAR T Cells. *ACS Appl Mater Interfaces* 2025; 17; 16548-16560.

D3 – P002

Novel yeast exopolysaccharides for 3D cell culture of cancer spheroids

Hamacek H.S. del Rio[1], Butelmann T.[2], Ostertag K.[1,3], Joasoon K.-L.[1], Tingajeva O.[1], Jõul P.[1], Lahtvee P.-J.[1], Shastri V.P.[2], Kumar R.[1]

[1]Dept. of Chemistry and Biotechnology, Tallinn University of Technology, Estonia; [2]Institute for Macromolecular Chemistry, University of Freiburg, Germany; [3]Dept. of Biotechnology, Institute of Bioprocess Science and Engineering, BOKU University, Vienna, Austria

Introduction

Natural polysaccharides such as alginate are widely used as biomaterial, particularly for 3D cell culture (CC) in applications like tissue engineering and cancer modeling. However, sourcing from natural resources introduces batch-to-batch variability. Microorganism-derived exopolysaccharides (EPS) offer a compelling alternative, providing tunable physicochemical properties through controlled biomanufacturing and genetic engineering. In our work, we aimed to characterize EPS properties and production parameters by *Rhodotorula toruloides*, to apply it as a biomaterial for 3D CC.

Materials and Methods

We cultured *R. toruloides* in bioreactors and extracted EPS from the supernatant. For a detailed analysis, several standard analytical methods for macromolecules were deployed, such as FTIR, GC-MS, GPC or rheology. Standard CC and novel 3D CC techniques were applied, and the constructs were analyzed by fluorescence microscopy.

Results

For this recently discovered EPS from *R. toruloides*, we determined that glucose as carbon source has the highest EPS conversion with an onset under acidic conditions, reaching 5.2% of the carbon balance (Figure 1). We further analyzed the polysaccharide composition and its glycosidic bonds with the backbone mainly consisting of 1→4-ljnked β-glucopyranose with possible side chains. We identified three distinct M_w fractions of which the most prominent was ~1000 kDa. Finally, we applied this EPS together with PEGDA to form a hydrogel network embedding cancer spheroids to overcome limitations of a single-component system in 3D CC (Figure 2).

Conclusion

We characterized the bioproduction and properties of EPS from *R. toruloides*, establishing a foundation for scalable production and future optimization for multi-product bioprocesses. Importantly, we demonstrate the utility of this EPS as a biomaterial component for 3D CC of cancer spheroids, achieving enhanced hydrogel properties through incorporation with PEGDA. This work positions *R. toruloides*-derived EPS as a compelling building block for advanced biomaterials in applications such as 3D cell culture and regenerative medicine.




Figure 1: Biomanufacturing of EPS in bioreactors.




Figure 2: Hydrogel engineering and fluorescence microscopy of embedded spheroids.

Acknowledgements
The authors acknowledge funding and support by the Estonian Research Council (grant PRG1101, TARISTU24-TK15), from the European Commission grant 101060066 co-funded by the Estonia state budget, funding and mobility grants from the Austrian government's public employment service (AMS), European Research Council's Erasmus+ program, the Baltic-German University Liaison Office Agreement NO. 2021/11, Wissenschaftliche Gesellschaft (Freiburg im Breisgau) and Dr. Leo-Ricker-Stiftung.

D3 – P003

Design of a dynamic dual crosslinkable hydrogel based on engineered hyaluronic acid and gelatin

Grillo Coppola P.[1,2], Sinnona F.[1,2], Boffito M.[1], Tonda-Turo C.[1], Mommer S.[3], Cassino C.[4], Ciardelli G.[1]
[1]Dept. of Mechanical and Aerospace Engineering, Politecnico di Torino, Turin, Italy; [2]Dept. of Surgical Sciences, Università degli Studi di Torino, Turin, Italy; [3]Dept. Of Mechanical and Process Engineering, ETH Zürich, Switzerland; [4]Dept. of Sciences and Technlogical Innovation, Università del Piemonte Orientale, Alessandria, Italy

Introduction

Dynamic hydrogels capable of adapting to cellular activity are crucial to support native tissues. Nevertheless, most natural hydrogels lack mechanical stability and shape retention, hindering their use in advanced biofabrication. To overcome these limitations, we designed a dual-crosslinkable hydrogel based on natural polysaccharides integrating supramolecular interactions with tunable covalent chemistry.

Materials and Methods

Hyaluronic acid (HA) was functionalized with adamantane (Ada) moieties (HA-Ada), via carbodiimide-mediated coupling with 1-adamantanemethylamine. β-Cyclodextrins (βCD) were functionalized with acrylate groups yielding Ac-βCD, that acts as a multifunctional cross-linker (i) enabling host-guest interactions with Ada groups and (ii) copolymerizing with methacryloyl gelatin (GelMA). Hydrogel formation occurred via βCD-Ada host-guest complexation, followed by photo-induced (λ=405 nm) acrylate-methacrylate crosslinking. The hydrogel composition was tuned by varying HA-Ada (0.5-1.5% w/v), GelMA (3-5% w/v), and Ac-βCD (1-5% w/v).

Results

The degree of functionalization of HA-Ada, GelMA and Ac-βCD was quantified by ^{1}H nuclear magnetic resonance (NMR) spectroscopy, being 10-30%, 60-90% and 60-80%, respectively. Fourier transform infrared spectroscopy (FTIR) confirmed chemical modification.

Host-guest interactions between Ac-βCD and HA-Ada were characterized by isothermal titration calorimetry (ITC). Consistent with a 1:1 host–guest complexation, the analysis yielded a stoichiometry of N=0.9, and a fit to a one site binding model revealed an apparent binding constant of $K_a=10^4$ M^{-1}, confirming stable yet reversible supramolecular complexes and the suitability of the βCD-Ada pair as a dynamic cross-linking mechanism, capable of promoting network rearrangement under mechanical stress.

Rheological analyses showed a sol-to-gel transition upon irradiation, with the system evolving from a viscous solution to a well-developed network, with storage modulus (G') exceeding loss modulus (G''), and both moduli were independent of frequency in frequency sweep tests. Strain sweep tests revealed G' and G'' values of approximately 3000 and 300 Pa, respectively, with network disruption at ~100% strain, suggesting mechanical robustness and shape retention. Cytocompatibility tests showed high cell viability (80–100%), indicating no cytotoxic effects from the functionalization or photopolymerization steps.

Conclusion

This dual-crosslinkable hydrogel merges printability, adaptability, and biocompatibility within a fully natural polymeric network. Its mechanical resilience enables stable filament formation and shape retention, while reversible network dynamics support cellular remodeling and migration, making the system promising for 3D bioprinting and vascularized tissue engineering. Ac-βCD domains further provide tunable crosslinking sites, for multifunctional, cell-responsive bioinks and support baths in regenerative medicine. Additionally, the βCD cavities may enable host-guest complexation with therapeutics, suggesting potential use of the system as a drug-delivery hydrogel platform.

D3 – P004

Best of both worlds: Grafting synthetic to natural polymers for burn wound healing applications

Deroose N., Bouzoukas T., Dubruel P.
Ghent University, Belgium

Introduction


Burn wounds constitute the fourth most frequent type of injury worldwide and are associated with approximately 180,000 deaths annually. Effective wound dressings are essential to reduce complications such as infection, pain, and scarring. Yet, materials that simultaneously combine biocompatibility, suitable mechanical properties, and high moisture absorbance remain limited. This work addresses this gap by developing hybrid biomaterials that integrate natural polymers (gelatin and silk sericin) with synthetic polyesters—poly(ε-caprolactone) (PCL) and poly(trimethylene carbonate) (PTMC)—to combine the advantageous properties of both material classes.

Materials and Methods

A library of PCL and PTMC homopolymers (2–9 g/mol) and copolymers (2.5–4 g/mol) with varying compositions and microstructures was synthesized and subsequently functionalized with thiol groups. Natural polymers were modified with norbornene functionalities. The components were coupled via photo-initiated thiol–ene chemistry to obtain amphiphilic grafted constructs (grafting density 21–40%) capable of physical gelation in aqueous media through hydrophobic associations. UV-induced crosslinking with DTT was subsequently applied to generate dual cross-linked hydrogels. Moreover, the physically cross-linked hydrogels were processed via electrospinning to obtain nanofibrous mats. The structure and mechanical properties of the synthesized materials were evaluated.

Results

The grafted materials exhibited pronounced gel-like behavior, while secondary UV crosslinking significantly enhanced mechanical performance, with the storage modulus G' increasing from 0.5 to 8 kPa and gel fractions exceeding 77%. All hydrogels displayed high swelling capacities (>190%), and swelling behavior was tunable through graft length, polymer composition, and copolymer microstructure. Morphological analysis revealed that graft length strongly governed porosity: shorter grafts produced porous hydrogel networks, whereas higher molar mass grafts yielded dense, non-porous films. In contrast, all copolymer-based grafts exhibited porous architectures not observed for homopolymer grafts of comparable molar mass, highlighting the crucial role of copolymer microstructure in pore formation. Proof-of-concept electrospinning produced homogeneous fibers with an average diameter of 1.04 ± 0.63 µm, demonstrating the feasibility of processing these materials into extracellular matrix-mimicking fibrous mats.



Conclusion

Within the explored graft-length and composition range, the developed porous hybrid materials exhibit tunable mechanical and swelling properties, controlled porosity, and compatibility with fibrous processing. These characteristics position them as promising candidates for soft tissue engineering and burn wound healing applications.

D3 – P005

Development of a vascularized 3D in vitro hepatic lobule model with dynamic perfusion system

Chiudaroli L.[1], Capotorto E.[1], Facchinetti G.[1], Facchi M.[1], Parodo N.[1], Farè S.[1,2]
[1]Dept. of Chemistry, Materials and Chemical Engineering G. Natta, University of Politecnico di Milano; [2]National Interuniversity Consortium of Materials Science and Technology (INSTM), Florence, Italy

Introduction

Liver damage from drugs, infections, or cancer can be irreversible despite its regenerative capacity. Because 2D cultures and animal models have limitations, 3D liver models are being developed to better mimic native structure and function. Recreating both tissue architecture and vascular networks is essential to simulate realistic cell behavior and blood flow.

Aim

Development of a GelMA hydrogel with PLA sacrificial structures to form internal vascular channels. The model is then characterized physically, mechanically, and biologically under static and dynamic perfusion conditions.

Materials and Methods

To mimic the typical geometry of the hepatic lobule hexagonal mold were realized through SLA-DLP printer in medical grade resin. In addition, a multi-lobule mold was realized to simulate liver pattern. 10% w/v GelMA was photocrosslinked with UV light using Irgacure 926 as photocrosslinker. PLA filaments were extruded through FDM printer. The sample realization process is shown in Figure 1. Perfusion tests were realized using food dye. Stability tests were performed over 4 weeks. Compression tests were performed on GelMA samples and, for a comparison, on cylindrical bovine liver samples.

To simulate blood flow within the hepatic network, a dynamic perfusion set up was built. Huh-7s epathoma cells were encapsulated in GelMA. Alamar Blue assay and DAPI staining was performed on models without channels (bulk samples) and samples with channels placed under static and dynamic conditions over 14 days.

Results

The dimensions of the resin mold and of the holes fabricted for the insertion of PLA filament into GelMA reflected the CAD dimensions, the same for the sacrificial filament. Dye perfusion tests showed excellent channel patency and diffusion into the scaffold. Samples were stable for over 4 weeks dimostrating their suitability for long-term experiments. Mechanical compression test showed a non significant difference between GelMA model and bovine liver elastic modulus (around 2,5 kPa). The Alamar Blue assay shows good viability until day 14. After the seventh day, DAPI assay shows cells organizing around the channels, demonstrating better diffusion of nutrients from the channels to the hydrogel.

Conclusion

This work developed a 3D model of the hepatic lobule mimicking properly geometry, vascularization and mechanical properties. The dynamic perfusion system could maintain flow rates comparable to that of blood in the vessels of the lobules. The results of this study are a promising starting point for the realization of a more complex liver model already ensuring adequate characteristics and promoting cell viability and proliferation, while properly mimicking the physiological environment.




Figure 1: a) Samples realization proccess, b) resin mold with PLA filaments, c) sample after perfusion dye




Figure 2: a) Dynamic perfusion system, b) schematic chamber sample design, c) AlamarBlue assay results, d) DAPI assay on cross-sections of sample with channels

D3 – P006
Mussel foot-inspired protein adhesives for soft tissue applications

Derkoningen K.[1], Derveaux E.[2], Graulus G-J.[1]
[1]UHasselt, Institute for Materials Research (IUMAT), Biomolecule Design Group (BDG); [2]UHasselt, Institute for Materials Research (IUMAT), Applied and Analytical Chemistry, NMR group, Diepenbeek, Belgium

Introduction
When tissues are damaged, the body's natural healing process aims to repair the injured site. However, in many cases, this process alone is insufficient to fully restore tissue integrity and function. Sutures or staples can be applied to join tissues together, but these methods sometimes suffer from drawbacks, e.g. tissue tearing. Tissue adhesives are more practical when considering applications such as minimally invasive surgery. The ideal tissue adhesive should be adhesive under physiological conditions, resemble the surrounding tissue as closely as possible and prevent bacterial colonization. Protein-based hydrogels would therefore be an interesting material to meet these requirements due to their adjustable properties and their biocompatibility. In this project, dynamically cross-linked hydrogels based on elastin-like proteins (ELPs) will be modified so that the proteins contain catechol-rich adhesive domains inspired by mussel foot protein-5 (Mefp-5). Additionally, the combination of catechol-based adhesive domains with dynamic covalent chemistry (DCC) is expected to provide an additional energy dissipation mechanism, thereby improving tissue adhesion under dynamic conditions.

Materials and Methods
Mefp-5-ELP_3 sequences were genetically engineered in *E. coli* using recombinant DNA technology. Protein expression was performed in the Rosetta strain using the pET28a plasmid. Freeze-thaw cycles and/or B-PER™ reagent were used for cell lysis. The Mefp-5-ELP_3 fusion protein was purified with inverse transition cycling (ITC) and characterized with SDS-PAGE and Western Blotting. Dynamic crosslinkers were synthesized based on a protocol found in literature.[1,2]

Results
The Mefp-5-ELP_3 protein is successfully expressed and purified using ITC as assessed by SDS-PAGE and Western Blotting. The expression efficiency and protein yield are under investigation for further optimization along with tyrosine conversion experiments to DOPA residues to introduce the catechol groups.

DCC crosslinkers have been successfully synthesized and confirmed by ^{1}H-NMR. They are being tested using commercially available reference materials containing primary amines.

Conclusion
Mefp-5-ELP_3 proteins were expressed in *E. coli* and successfully purified. The conversion of the encoded tyrosines to DOPA residues is under investigation to yield protein-based bioadhesives.

Acknowledgements
This research is supported by the special research fund of Hasselt University (BOF-UHasselt, R-15146).

References
[1]Schmitt E., A General Approach towards NH-pyrazoles That Bear Diverse Fluoroalkyl Groups by Means of Fluorinated Iminium Salts. *Eur. J Org. Chem.* 2015; number; 6052-6060.
[2]Di Giovanni., Determination of benzyl methyl ketone – a commonly used precursor in amphetamine manufacture. *Anal. Methods*, 2012, 4, 3558-3564.

D3 – P007

Dynamic coordination chemistry for tuning mechanical behaviour of catechol-based hydrogels

Ercan Polat H.[1,2], Es Sayed J.[1], Włodarczyk-Biegun M.K.*[1,3]
[1]Biotechnology Centre, Silesian University of Technology, Gliwice, Poland; [2]Dept. of Chemistry, Karamanoglu Mehmehbey University, Karaman, Turkey; [3]Polymer Science, Zernike Institute for Advanced Materials, University of Groningen, The Netherlands

Introduction

Dynamic metal-catechol coordination enables the formation of viscoelastic networks with tunable mechanical properties. Here, we investigate the rheological behavior of catechol-functionalized quaternized chitosan (QCC) hydrogels crosslinked via Fe^{3+}, focusing the effects of pH, polymer concentration, and Fe^{3+}:catechol ratio on gelation and stiffness to obtain printable scaffolds for tissue engineering.

Materials and Methods

Chitosan was quaternized to enhance solubility at physiological pH and functionalized with catechol. QCC solutions (1.5–5% w/v) were mixed with $FeCl_3$ at different Fe^{3+}:catechol ratios (1:3 and 1:5) followed by pH adjustment (5.4–7.3). Oscillatory rheology was performed to determine linear viscoelastic regions, time sweep evolution, and frequency dependence. To evaluate printability, a range of pressures (40-80kPa) and speeds (0.5-3mm/sec) were tested. Cytocompatibility was evaluated through live/dead assays.

Results

UV–vis analysis confirmed pH-driven transitions from mono- to bis- and tris-Fe^{3+}–catechol complexes. Frequency sweep measurements showed that increasing pH shifted the hydrogels from a dynamic viscoelastic response to a predominantly elastic behavior (G′>G″), indicating a more stable network (Fig.1). Across all QCC concentrations, increasing the Fe^{3+}:catechol at ratio led to higher moduli, reflecting stronger coordination and a more robust gel structure. Increasing QCC concentration further enhanced the moduli and stiffness due to higher crosslink density and polymer entanglement. Among the formulations, 1.5% QCC with a Fe^{3+}:Cat ratio of 1:5 was selected for 3D printing and cell culture due to its stability at physiological pH and favorable shear-thinning and self-healing behavior. Stable extrusion enabled multilayer printing without post-crosslinking, and pre-incubated scaffolds supported cell viability.

Conclusion

We developed a printable QCC hydrogel system based on dynamic Fe^{3+}–catechol coordination with tunable mechanical properties. The results demonstrate that pH, polymer concentration, and Fe^{3+}:catechol ratio play a key role in governing gelation behavior and stiffness. These findings highlight how coordination chemistry can be used to tailor the mechanical properties of catechol-based hydrogel networks and design biocompatible, printable material-platforms.




Figure 1. Frequency sweep measurements of (A) 1.5%, (B) 2.5% and (C) 5% w/v QCC-Fe^{3+} solutions at fixed Fe^{3+}:Cat (1:3) molar ratio.

Acknowledgements

This work was supported by the Polish National Agency for Academic Exchange (NAWA,Polish Returns) and the National Science Centre, Poland (NCN,OPUS 2020/37/B/ST5/00743).

D3 – P008
Mimicking Lymph Node 3D Architecture in a Microfluidic platform

Rodríguez A.R.[1,2], Marrero D.[3,4], Villa R[3,4]., Alvarez M[3]., Guasch J.[1]
[1]Institut de Ciència de Materials de Barcelona (ICMAB-CSIC), Campus UAB, Bellaterra 08193, Spain; [2]Universidad Autónoma de Barcelona (UAB), Bellaterra, 08193, Barcelona, Spain; [3]Instituto de Microelectrónica de Barcelona (IMB-CNM, CSIC), Campus UAB, Bellaterra, 08193, Barcelona, Spain.; [4]Centro de Investigación Biomédica en Red en Bioingeniería Biomateriales y Nanomedicina, Madrid, 50018, Spain

Introduction
In vitro models have contributed significantly to advances in cell biology and oncology. In recent years, tissue engineering has progressed considerably, enabling the development of complex systems that mimic the extracellular matrix and cell–matrix interactions, producing 3D models capable of reproducing many tissue characteristics. Meanwhile, microfluidic systems have introduced the component of flow into cell culture, resulting in models that more closely represent physiological conditions. Combining both approaches yield a system consisting of a 3D artificial extracellular matrix subjected to flow generated by a peristaltic pump. In our case, we harnessed this potential to create a system that is inspired by the lymph nodes due to their interest in immunotherapy.

Aim
Engineering a 3D lymph node-on-a-chip under flow conditions for investigating healthy and oncologic cell behavior in a physiologically relevant environment.

Materials and Methods
An IOPAL PEG-heparin hydrogel was synthesized, following a previous protocol (1), and characterized by rheology and environmental scanning electron microscopy (ESEM). A microfluidic chip was also designed according to a prior publication (2) and operated with a pulsatile flow.Cellular responses were studied by flow cytometry and confocal microscopy.

Results
The hydrogel allows immune cells to infiltrate the scaffold, preventing them from being displaced by fluid flow. Cells cultured in the chip exhibited high viability compared to controls (cells in suspension and in hydrogel under static culture). Additionally, morphological changes were observed, reflecting adaptation to the flow conditions.

Conclusion
Our 3D platform allows to investigate healthy and oncologic immune cell behavior in a physiologically relevant microfluidic environment.

References
(1) Santos, F., Valderas-Gutiérrez, J., Del Río, E. P., Castellote-Borrell, M., Rodriguez, X. R., Veciana, J., ... & Guasch, J. (2022). Enhanced human T cell expansion with inverse opal hydrogels. Biomaterials science, 10(14), 3730-3738.
(2) Marrero, D., Guimera, A., Maes, L., Villa, R., Alvarez, M., & Illa, X. (2023). Organ-on-a-chip with integrated semitransparent organic electrodes for barrier function monitoring. Lab on a Chip, 23(7), 1825-1834.

D3 – P010

2-Hydroxyethyl methacrylate binds to Cys-374 of *b*-actin in THP-1 monocytes

Uhlig S.[1], Decoster W.[1,2], Brysse P.-J.[1,2], Jakaviciute R.[1], Grutle L.[1], Samuelsen J.T.[1]
[1]Nordic Institute of Dental Materials, Oslo, Norway; [2]Dept. of Bioanalysis, Faculty of Pharmaceutical Sciences, Ghent University, Belgium

Introduction

Polymer-based dental materials frequently contain methacrylate monomers such as 2-hydroxyethyl methacrylate (HEMA), which can leach due to incomplete polymerization and material degradation, exposing both patients and dental professionals. HEMA is small, water-soluble, readily released, and known to react with thiol groups in glutathione (GSH) and proteins via thiol-Michael addition, depleting GSH and potentially disrupting protein function. Actin, a key cytoskeletal protein, has a surface-exposed Cys374 that is a known nucleophilic hotspot and regulatory site for post-translational modification, making it a plausible toxicological target.

Aim

This work investigated whether the dental monomer HEMA covalently binds to cysteine residue 374 (Cys374) of actin in human monocyte-like cells (THP-1) and explores this interaction as a potential mechanism of HEMA-induced cytotoxicity.

Materials and Methods

The study used a bottom-up peptide-mapping approach with LC–HRMS to detect HEMA adducts in actin. Method development started with synthetic C-terminal actin peptides (YDESGPSIVHRKF and YDESGPSIVHRKCF) to optimize chromatographic conditions and mass spectrometric identification. THP-1 cells were exposed to non-cytotoxic concentrations of HEMA (2 mM and 4 mM) for 2 h and 24 h, then actin-enriched bands (~42 kDa) were isolated by SDS-PAGE and subjected to in-gel trypsin digestion. The trypsin digest was subsequently analyzed by LC–HRMS.

Results

HEMA reacted with the cysteine-containing peptide (YDESGPSIVHRKCF), and LC–HRMS/MS confirmed formation of a HEMA–peptide adduct, with fragment ions consistent with HEMA bound to the cysteinyl-phenylalanine (CF) dipeptide. Trypsin digestion of the HEMA–peptide adduct still yielded expected fragments, including the HEMA–CF dipeptide, indicating that modification at Cys did not prevent proteolysis.

In unexposed THP-1 controls, numerous actin-derived peptides were detected, and Cys374 was identified as cysteinyl-phenylalanine acetamide after reduction and alkylation. In HEMA-exposed cells, single-ion monitoring at *m/z* 399.1583 revealed a peak at the same retention time and with the same MS/MS fragmentation pattern as the HEMA–CF standard, which was absent in controls and increased with HEMA concentration.

Conclusion

This work provides mass spectrometric evidence that HEMA covalently binds to Cys374 of actin in THP-1 cells after short-term exposure. This supports a mechanistic hypothesis that modification of Cys374, a residue important for actin polymerization dynamics, may contribute to HEMA-induced toxicity by disturbing actin-dependent cellular functions such as cytoskeletal organization, motility, and signaling.

D3 – P011

Time-resolved biodistribution of a three-layer human cardiac stem cell sheet–fibrin composite in a nude mouse wound model

Han S.[1], Draugelyte G.[2], Jung Y.[3], Park J.C.[1,2,3,*]
[1]Dept. of Medical Device Engineering and Management, Yonsei University College of Medicine; [2]Dept. of Medical Science, Yonsei University College of Medicine; [3]Dept. of Biomedical Engineering, Yonsei University, Seoul, Republic of Korea

Introduction

Biomaterial-based cell therapy constructs require rigorous evaluation of systemic biodistribution and potential off-target persistence to ensure safety and regulatory readiness. This study aims to characterize the time- and organ-dependent biodistribution of a three-layer human cardiac stem cell (CSC) sheet–fibrin gel construct implanted in a nude mouse dorsal wound model and to determine whether human DNA signals are detectable in distant organs.

Materials and Methods

Male and female nude mice received an 8-mm full-thickness dorsal wound followed by implantation of the CSC sheet–fibrin construct. The construct was generated by sequential stacking of human CSC sheets onto a pre-formed fibrin gel. Biodistribution was evaluated using Alu quantitative PCR to detect human DNA signals in mouse tissues. Samples include the implantation site and 13 major organs collected at D1, D3, D7, D14, D30, D60, and D90. Detected signals were interpreted relative to the assay limit of detection (LoD). A sustained pattern will be assessed based on time-dependent trends above LoD, and exploratory comparisons by sex will be performed. Detected human DNA signals were interpreted cautiously, as Alu qPCR detects human genetic material but does not directly indicate viable cells. Alu qPCR results will be used to describe biodistribution signals rather than infer viable cell presence.

Results

Biodistribution analysis is currently ongoing. The dataset will provide time-resolved profiles of human DNA signals across tissues from D1 to D90, enabling evaluation of signal persistence and clearance, organ-specific distribution patterns, and local retention at the implantation site with minimal systemic distribution.

Conclusion

This study aims to establish a biodistribution profile of a fibrin-based CSC sheet construct and provide a framework for interpreting organ-specific signals in biomaterial-based cell therapy evaluation. The extended observation period up to 90 days enables evaluation of long-term signal clearance and supports safety assessment of implantable cell–biomaterial constructs.

Acknowledgements

This research was supported by the Korean Fund for Regenerative Medicine (KFRM) grant funded by the Korea government (the Ministry of Science and ICT, the Ministry of Health & Welfare) (code: KFRM RS2023-00215084).

D3 – P012

Long-term biodistribution and tissue clearance of fibrin-encapsulated cardiac stem cell constructs

Draugelyte G.[1], Han S.[2], Jung Y.[3], Park J.C.[1,2,3*]
[1]Dept. of Medical Science, Graduate School of Medical Science, Brain Korea 21 Project, Yonsei University College of Medicine; [2]Dept. of Medical Device Engineering and Management, Yonsei University College of Medicine; [3]Dept. of Biomedical Engineering, Yonsei University, Seoul, Republic of Korea

Introduction

The long-term in vivo fate of cell-biomaterial constructs is critical for safety evaluation in regenerative medicine. In fibrin-based constructs, gradual degradation of the fibrin matrix after implantation may gradually release encapsulated cells, and unexpected persistence or distribution of these cells to non-target sites may raise safety concerns. Therefore, systematic assessment of biodistribution and clearance kinetics is necessary to determine whether these constructs exhibit controlled and predictable in vivo behavior.

Materials and Methods

In this study, fibrin-encapsulated cardiac stem cell (CSC) constructs were implanted into a full-thickness skin wound created using biopsy punch in a nude mouse model, and their biodistribution was monitored over a 90-day period. Tissues from the implantation site and major organs were collected at early and late post-implantation time points and analyzed using human-specific Alu quantitative PCR to detect human genomic DNA within host tissue. Signal levels were interpreted relative to the assay's defined limit of detection (LOD) to evaluate long-term persistence and clearance dynamics.

Results

Human-derived DNA was detectable at the implantation site at early post-implantation time points and showed a decreasing trend over time. By day 90, signals were below the assay's defined limit of detection. Preliminary analysis suggest a time-dependent reduction in detectable human genomic DNA, while detailed quantitative analysis of biodistribution and clearance kinetics is currently ongoing.

Conclusion

These results demonstrate a transient local presence following implantation of fibrin-encapsulated CSC constructs with gradual tissue clearance over time and no evidence of prolonged persistence. Importantly, the absence of sustained signal suggests limited long-term persistence of transplanted cells The observed kinetic profile supports predictable in vivo behavior of fibrin-based cell constructs. Integrating explicit LOD-based interpretation into biodistribution analysis provides a practical analytic framework for evaluating long-term persistence of biomaterial-integrated cell therapies and may contribute to more standardized safety assessment of advanced regenerative medicine products.

Acknowledgements

This research was supported by the Korean Fund for Regenerative Medicine (KFRM) grant funded by the Korea government (the Ministry of Science and ICT, the Ministry of Health & Welfare) (code: KFRM RS2023-00215084).

D3 – P013

A standardized ex vivo porcine skin wound infection model for evaluating antibacterial delivery in wound care

Defrançois S., Maton M., Blanchemain N., Chai F.
[1]Univ. Lille, INSERM, CHU Lille, U1365 - Advanced Drug Delivery Systems, Lille, France

Introduction

Wound infections are a major cause of morbidity in acute and chronic wounds. While standard *in vitro* models (like MIC tests) fail to mimic tissue complexity, *in vivo* models face ethical and throughput constraints. Within the DIAMOND (Interreg FWVL) project – focus on smart dressings for diabetic wounds with real-time sensing and on-demand drug delivery - we developed a standardized *ex vivo* porcine skin model. This platform simulates the biochemical environment of an infected diabetic wound to validate topical antimicrobial efficacy.

Materials and Methods

A schematic overview of the experimental workflow is presented in Figure 1. Porcine skin was collected from minipigs previously used in other experimental studies (3R compliant). The dorsal skin was shaved, cleaned, excised, disinfected and stored at -80°C until use. Cryopreserved skin samples were thawed and standardized partial-thickness wounds were induced via mechanical dermabrasion using a rotary tool (Dremel) to create reproducible wound beds. Tissue explants were then excised using a biopsy punch and transferred into 24-well plates and were stabilized in Mueller–Hinton agar-broth interface to simulate interstitial fluid supply.

Wounds were inoculated with two clinically relevant pathogens frequently found in infected wounds: *Staphylococcus aureus* ATCC 6538 or *Pseudomonas aeruginosa* ATCC 27853. Following a 2 h colonization phase at 37 °C, treatments were applied on the wounds: PBS (negative control) or Cadexomer iodine ointment (Iodosorb®, Smith & Nephew, UK), a reference treatment for infected diabetic foot wounds. After 24 h incubation, antimicrobial efficacy was quantified via plate viable bacterial counts.

Results

Figure 2 presents the results of the microbiological assays. The model successfully supported bacterial proliferation showed by PBS-treated wounds: with *S. aureus*, a slight increase in bacterial load and with *P. aeruginosa,* bacterial load increasing from ~10^3 to 6.5×10^9 CFU/explant in 24 h. Whereas treatment with Iodosorb® demonstrated superior antimicrobial flux, achieving a > 6log reduction for *S. aureus* and > 8log reduction for *P. aeruginosa*, brining bacterial counts below the limit of detection (LOD, < 7.10^1 CFU/explant). It confirms the model's sensitivity in distinguishing between uncontrolled colonization and therapeutic intervention.

Conclusion

This *ex vivo* wound infection model offers a high-fidelity, cost-effective bridge for the early-stage screening of "smart" antimicrobial biomaterials. It provides the necessary physiologically constraints to evaluate the on-demand drug delivery systems within the DIAMOND project.

Acknowledgements

The authors acknowledge the financial support of the Interreg FWVL DIAMOND project.




Figure 1. Graphic illustration demonstrating the experimental set-up and workflow of the *ex vivo* wound model.




Figure 2. Evaluation of Iodosorb®, a topical antimicrobial reference treatment in an infected e*x vivo* wound model. Infection was induced with either *S. aureus* or *P. aeruginosa.* Values were $\log_{10}$ transformed and are represented as the mean ± SEM (*n* = 4).

D3 – P014

The use of marine-derived collagen skin dressings in the treatment of skin wounds

de Souza A.[1], Hataka, A.[2], de Souza D.V.[1], Renno A.C.M.[1]
[1]Dept. of Biosciences, Federal University of São Paulo, Santos; [2]Dept. of Veterinary Clinical Sciences, São Paulo State University, Botucatu, Brazil

Introduction

Skin injuries represent a major clinical challenge, leading an impaired tissue regeneration. Advanced skin dressings have emerged as important therapeutic strategies by maintaining a favorable microenvironment and promoting cellular proliferation and tissue repair. Natural polymers such as collagen and alginate are widely used due to their biocompatibility and bioactivity. In particular, marine-derived collagen has gained attention as a promising alternative to mammalian sources because of its low zoonotic risk, structural similarity to vertebrate collagen, and ability to stimulate fibroblast and keratinocyte activity. In parallel, 3D printing technologies enable the fabrication of porous and customizable scaffolds that better mimic the extracellular matrix architecture.

Aim

This study evaluated the *in vivo* performance of marine-derived collagen in full-thickness wound model.

Materials and Methods

A 3D-printed skin dressing composed of marine-derived collagen and sodium alginate was fabricated and *in vivo* evaluated in a full-thickness wound model, where animals were allocated to either a control group (no treatment) or a skin dressing group. Tissue samples were collected at 7 and 14 days post-injury. Healing responses were evaluated through qualitative histological staining and immunohistochemistry for COX-2, PCNA, and type I collagen.

Results

Qualitative H&E analysis at 7 days showed crust formation, early neoepithelium migration, and granulation tissue composed of fibroblasts, inflammatory cells, and neovessels in both groups. The marine collagen group presented a more disorganized extracellular matrix at this stage. By day 14, complete re-epithelialization occurred in all wounds, while residual biomaterial fragments surrounded by foreign body-type granulomas suggested ongoing scaffold resorption and dermal remodeling. Immunohistochemistry demonstrated balanced COX-2 expression, persistent PCNA-positive fibroblasts, and increased COL-1 deposition over time, indicating sustained cell proliferation and progressive extracellular matrix maturation.

Conclusion

The marine-derived collagen skin dressing supported physiological wound healing, promoting fibroblast proliferation and extracellular matrix deposition without exacerbating inflammation. These findings highlight its potential as a bioactive scaffold for skin regeneration.

Acknowledgements

This work was supported by “Fundação de Amparo à Pesquisa do Estado de São Paulo - FAPESP” through the grants #2021/13056-0, #2025/13279-0 and #2019/10228-5. The authors also acknowledge “Coordenação de Aperfeiçoamento de Pessoal de Nível Superior – CAPES” and “Conselho Nacional de Desenvolvimento Científico e Tecnológico – CNPq” for financial support.

D3 – P015

COIN™: A modular cell culture insert enabling advanced in vitro models for biomaterial research

De Berardinis N.[1,2], Hulsart-Billström G.[2]
[1]Dept. of Materials Science and Engineering, Division of Biomedical Engineering; [2]Dept. of Medical Cell Biology, Uppsala University, Sweden.

Introduction

Cell-cell communication plays a fundamental role in biomaterial-driven tissue regeneration. In bone regeneration, osteoblasts, osteoclasts, and mesenchymal stromal cells interact through soluble signaling molecules that regulate bone formation and resorption. However, conventional in vitro models such as transwell systems allow only limited multicellular organization and restrict experimental flexibility. To address this limitation, we developed COIN™, a modular cell culture insert designed to enable multiplex paracrine co-culture while maintaining physical separation between different cell populations. The system is compatible with standard culture plates and analytical techniques commonly used in biomaterials research.

Materials and Methods

COIN™ inserts (figure1) were fabricated using high-resolution resin 3D printing and designed to fit standard culture plates. The material cytocompatibility was first evaluated by culturing mammalian cells within the insert and assessing cell viability and metabolic activity using fluorescence-based assays.

Following cytocompatibility validation, the functionality of the platform was tested in a proof-of-concept paracrine co-culture setup. Finally, the system was used to establish a tri-culture model relevant to bone remodeling. Osteoblastic cells, osteoclast precursors, and mesenchymal stromal cells were cultured in separate compartments within the same well, allowing communication through shared medium while preventing direct contact. Osteoclastogenesis was quantified using standard osteoclast differentiation assays to assess the effect of paracrine signaling between the three cell populations.




Figure 1. Graphical representation of how a COIN™ insert looks and its most important function, stackability. In this example, three COIN™s are placed on top of each other.




Figure 2. Normalised acid phosphatase (ACP) activity after seven and twenty-one days of culture for RAW 264.7 macrophages tri- and monoculture. ACP activity is to be considered a marker for osteoclastic differentiation.

Results

Cytocompatibility testing demonstrated that the printed material and device architecture did not induce detectable cytotoxic effects, with cells maintaining normal viability and metabolic activity within the system. The modular insert enabled stable compartmentalization of different cell populations while allowing soluble signaling factors to diffuse through the shared culture medium. In the tri-culture model, the system successfully supported simultaneous culture of osteoblasts, osteoclast precursors, and mesenchymal stromal cells. Quantification of osteoclast differentiation (figure 2) demonstrated that paracrine interactions between the three cell types could be monitored within the platform, confirming the ability of the system to reproduce biologically relevant multicellular signaling environments.

Conclusion

COIN provides a versatile in vitro platform for studying complex multicellular interactions relevant to biomaterial-mediated bone regeneration. By enabling multiplex co-culture while maintaining physical separation of cell populations, the system overcomes limitations of conventional co-culture methods and facilitates the investigation of paracrine signaling in bone remodeling models. This approach may support the development and evaluation of next-generation biomaterials by enabling more physiologically relevant in vitro testing.

D3 – P016

Cytocompatibility of biofunctionalized titanium surfaces for dental implant applications using SaOs-2 cells

Gaião W.D.C.[1], Andrade A.N.[1], Silva R.G.[1], Silva I.C.[1,2], Branco-Junior J.F.[1], Da Silva J.R.[1], Oliveira M.L.[1], Machado G.[1]

[1]Centro de Tecnologias Estratégicas do Nordeste (CETENE); [2]Universidade Federal Rural de Pernambuco, Recife, Brazil

Introduction

Titanium dental implants are surface-modified to improve early cell-material interactions to overcome the limited bioactivity of titanium. However, nanoengineered and bioactive coatings may also change surface chemistry and release leachable components, and therefore, cytocompatibility testing is an important initial step before more advanced biological evaluation. This work aimed to study how surface modifications with TiO_2 nanotubes, hydroxyapatite, and a chitosan-cinnamaldehyde coating affected the survival of osteoblast-like SaOs-2 cells under conditions from ISO 10993-5.

Materials and methods

TiO2 nanotubes were prepared by anodisation of grade II titanium sheets in a fluoride-containing electrolyte, either without hydroxyapatite (TiTNT) or with simultaneous electrodeposition of hydroxyapatite using two fluoride concentrations (TNTHA1 and TNTHA2). Chitosan films incorporated with cinnamaldehyde were spray-coated at 60°C (SC-60) on TNTHA1 and TNTHA2. Sterilised samples were extracted in culture medium at a surface-area to volume ratio of 3 cm2/mL for 72 h at 37°C. The cells were cultured in McCoy's 5A medium supplemented with 10% foetal bovine serum and treated with extracts for 24 h. Culture medium and 10% DMSO served as negative and positive controls, respectively. The cellular metabolic activity was assessed by MTT assay and the absorbance was measured at 570 nm.

Results

The cell viability of TiTNT, TNTHA1 and TNTHA2 extracts was >90% at all concentrations tested, indicating that the formation of nanotubes and the incorporation of hydroxyapatite did not induce cytotoxic effects under the experimental conditions. The SC-60 coating resulted in a concentration-dependent decrease in viability at the highest extract concentration (74.37 ± 10.02 %), but the values remained above the 70% cytotoxicity threshold recommended by ISO 10993-5. These findings suggest that the suggested multifunctional surface modification does not release leachable components at levels that might impair SaOs-2 viability in this screening model.

Conclusion

The titanium-based surfaces tested showed satisfactory in vitro cytocompatibility, including the more complex chitosan-cinnamaldehyde-coated system. This work demonstrates the ability of the surface-engineered titanium platform to provide a nanoarchitectured surface with TiO2 nanotubes, hydroxyapatite functionalisation and bioactive polymer coating without exceeding the ISO 10993-5 cytotoxicity limit, supporting the further development of the platform for dental implant applications. The results provide a safety-oriented foundation for the subsequent studies on osteogenic response, antimicrobial performance, wettability and corrosion behaviour.

Acknowledgements

CNPq, FACEPE and FINEP (Ref.: 0071/21).

D3 – P017

Mechanoadaptive extracellular matrix remodeling in a humanoid robotic bioreactor for physiologically relevant biomaterial testing

Nadhif M.H.[1], Lin J.[1], Choreno Machain T.[2], Snelling S.[3], Mouthuy P.-A.[1]
[1]Dept. of Materials, University of Oxford; [2]Dept. of Engineering Science, University of Oxford; [3]Botnar Research Center, Nuffield Dept. of Orthopaedics, Rheumatology, and Musculoskeletal Sciences (NDORMS), University of Oxford, UK

Introduction

Re-tear rates after rotator cuff augmentation remain high, reaching up to 91% in large tears. These failures may occur when augmentation materials do not provide adequate mechanical reinforcement, tendon healing support, or cellular organization. A limitation of conventional pre-clinical testing is the lack of physiologically relevant mechanical loading. Humanoid robotic arm bioreactors have therefore been developed to reproduce rehabilitation-like joint motion and mechanical stimulation. Previous studies showed that robotic bioreactors can promote cell alignment and activate mechanotransduction pathways, including PI3K–Akt signalling.

Aim

This study aims to evaluate a robotic bioreactor for tendon biomaterial testing device with the presence of cells by considering the cell distribution, extracellular matrix deposition, and related marker to tendon maturation.

Materials and Methods

Rehabilitation exercise motions were applied across three degrees of freedom using a humanoid robotic bioreactor to a synthetic non-degradable rotator cuff patch material (PolyTape). Green fluorescent protein-labelled mesenchymal stem cells (MSC-GFP) were cultured on the material for 30 days. From Day 9, samples were subjected to three weeks of cyclic loading with progressive weights from 0.5 to 2.5 kg. Comparative groups included matched uniaxial loading, static culture, and plate control conditions. Cell metabolic activity was monitored using PrestoBlue, and live cell distribution was assessed by confocal microscopy on Day 29. After culture, samples were fixed for scanning electron microscopy and immunofluorescence analysis. Paraffin sections were stained for collagen type I (COL1), tenomodulin (TNMD), tenascin-C (TNC), and matrix metalloproteinase-13 (MMP13).

Results

Cells were confluent across all groups by Day 29 (Figure 1a). Plate control samples showed the highest PrestoBlue signal, followed by static culture, while uniaxial and robotic bioreactor groups showed comparable metabolic activity (Figure 1b). Scanning electron microscopy revealed condition-dependent differences in cell distribution, with increasing mechanical complexity associated with altered cell sheet organization and more pronounced cellular clustering (Figure 1c). Immunofluorescence quantification showed broadly comparable mean fluorescence intensity for COL1 and TNMD across groups (Figure 2a). MMP13 signals were also comparable across groups (Figure 2b). In contrast, TNC signal was elevated in the robotic bioreactor group, indicating a selective response to robotic mechanical stimulation (Figure 2b).

Conclusion

Humanoid robotic bioreactor loading altered cell organization on the biomaterial surface and selectively increased TNC expression. These findings suggest that rehabilitation-like robotic motion promotes TNC-associated mechanoadaptive extracellular matrix remodelling without broadly increasing collagen deposition, tenogenic maturation, or MMP-13-associated matrix turnover. This platform may provide a more physiologically relevant approach for evaluating tendon augmentation biomaterials under dynamic loading conditions.

Acknowledgements

Engineering and Physical Sciences Research Council (EPSRC), United Kingdom (Grant No. EP/S003509/1); National Institute for Health Research (NIHR), Oxford Biomedical Research Centre (BRC); Indonesia Endowment Fund for Education (LPDP), Indonesia (Ref. No. S-983/LPDP.4/2022 & LOG-650/LPDP.3/2025)

References

[1]Liu, Z. et al. Humanoid Robotic Loading Enhances Mechanotransduction in Tendon Tissue Engineering. *Cyborg and Bionic Systems* 2026; 7; 0542.




Figure 1. Cell metabolic activity, live-cell distribution, and surface morphology across culture conditions. (A) PrestoBlue metabolic activity signal across groups during the culture period, normalized relative to Day 1. The red dashed inset shows an enlarged view of the mechanically tested groups. (B) Live MSC-GFP distribution on the materials at Day 29, imaged using spinning disc confocal microscopy. Scale bar = 200 μm. (C) Scanning electron microscopy (SEM) images showing cell/material surface morphology after mechanical loading and culture. Scale bar = 100 μm.




Figure 2. Immunofluorescence imaging and quantification of extracellular matrix, tendon maturation, and matrix-remodelling markers. (A) Representative images and mean fluorescence intensity quantification of COL1 and TNMD staining. (B) Representative images and mean fluorescence intensity quantification of TNC and MMP13 staining. Nuclei were counterstained with DAPI. Scale bar = 50 μm.

D3 – P018

Synergistic CO2 cryotherapy and EGF delivery for accelerated wound healing through anti-inflammatory and regenerative pathways

Pham Ngoc C.[1], Lee Yong H.[1], Heo Chan Y.[1,2]
[1]Dept.Plastic Surgery, Seoul National University Bundang Hospital, Seongnam; [2]Dept.Medical Device Development, Seoul National University, Seoul, Korea

Introduction

Wound healing remains a major clinical challenge, and improved strategies are needed to accelerate closure while limiting inflammation and oxidative stress[1-4]. This study assessed the therapeutic potential of the AcuCool™ system, a multifunctional device combining high-velocity CO_2 cryotherapy with intradermal delivery of epidermal growth factor (EGF), for enhancing cutaneous wound repair.

Materials and Methods

Full-thickness excisional skin wounds were created in Sprague Dawley rats. Animals were allocated to three groups: (1) AcuCool™ Device+EGF, (2) conventional microneedling-based EGF delivery, and (3) untreated controls. Wound healing was evaluated by macroscopic monitoring of closure. Tissue repair was further assessed by histological analysis of re-epithelialization, inflammatory cell infiltration, and collagen deposition. Molecular changes were examined by quantifying inflammatory mediators (TNF-α, IL-1β, MCP-1) and remodeling-related genes (TGF-β1, Collagen I, Vimentin). Local oxidative stress was estimated using nitrite assays as a surrogate for nitric oxide levels.

Results

The Device+EGF group showed significantly accelerated wound closure compared with microneedling-based EGF delivery and untreated controls. Histology demonstrated enhanced re-epithelialization, reduced inflammatory cell infiltration, and increased collagen deposition in Device+EGF–treated wounds. Molecular analyses revealed downregulation of pro-inflammatory markers (TNF-α, IL-1β, MCP-1) and upregulation of remodeling-associated genes (TGF-β1, Collagen I, Vimentin). Nitrite levels were also reduced, consistent with suppression of local nitric oxide linked oxidative stress.

Conclusion

AcuCool™ enables precise, non-invasive intradermal delivery of EGF while providing complementary cryotherapeutic effects, resulting in improved inflammation control and tissue regeneration in an acute rat wound model. Although validation in chronic wound settings is warranted, these findings support AcuCool™ as a promising translational platform for accelerating wound healing.

Acknowledgements

This work was supported by the Technology Innovation Program (or Industrial Strategic Technology Development Program Material Technology Development Project 2023 (heterogeneous technology convergence type Investment-linked type)) (20022874, Supersonic jet of cryogenic microparticles for non invasive transdermal drug delivery) funded by the Ministry of Trade, Industry &Energy (MOTIE, Republic of Korea).

References

[1]Nuutial K., Eriksson E. Moist Wound Healing with Commonly Available Dressings. *Adv. Wound Care* 2021; 10; 685-698.
[2]Ellis S., Lin E.J., Tarta. D. Immunology of Wound Healing. *Curr. Dermatol. Rep* 2018; 7; 350-358.
[3]Sinha A., Jain P., Ajazuddin.D. Recent advancement in molecular pathways and receptor targeting using natural products for wound healing activity. *Inflammopharmacology* 2025; 33; 4595-4613.
[4]Prazeres J., Lima A., Ribeiro G. Effects of Carbon Dioxide Therapy on Skin Wound Healing. *Biomedicine*s 2025; 13; 228-243.

D3 – P019

In vivo evaluation of 3D-printed titanium: From surface modification to healing

Válková L.[1], Krchová M.[2], De Felice A.[1], Chatzichristou K.[1], Pávková Goldbergová M.[1]
[1]Dept. of Pathophysiology, Faculty of Medicine, Masaryk University; [2]Dept. of Mechanical Engineering, University of Defence, Brno, Czech Republic

Introduction

Titanium and its alloys are widely used materials for biomedical implants due to their unique combination of high strength, corrosion resistance, and biocompatibility. Advances in 3D printing technologies have enabled the fabrication of patient-specific titanium implants, thereby improving treatment outcomes and reducing the risk of complications. However, degradation of metallic implants through corrosion or wear can result in the release of metal ions and particles, potentially triggering inflammatory responses, tissue irritation, and implant loosening. To overcome these limitations, various surface modifications are being developed to enhance biocompatibility, reduce inflammation, and extend implant lifespan.

Aim

The aim of this study was to modify the surface of titanium samples to minimize complications and maximize the benefits for the patient who will receive the implant.

Materials and Methods

The titanium samples were prepared using a Selective Laser Melting (SLM) 3D printer (3D Ti), and their surfaces were subsequently modified through a combination of methods: laser surface texturing (LST), laser-induced periodic surface structures (LIPSS), and finally deposition of TiN-based nanolayer coatings of defined composition with physical vapor deposition (PVD) technology. In vivo experiments were carried out on female Wistar rats. A titanium disc (with or without surface modification) was placed beneath the scapula on the dorsal side. After the monitoring periods (72 hours, 2 weeks, and 4 weeks), muscle samples from the implant-contact region were collected. Expression of inflammation-associated genes was quantified by RT-qPCR using the 2-ΔΔCT method.

Results

Surface modification significantly affected the inflammatory response to 3D-printed titanium. The unmodified samples induced acute reactions and signs of a later chronic inflammatory phase. In contrast, laser-treated and TiN-coated surfaces showed substantially lower expression of inflammatory markers, including IL1B and the adhesion molecule ICAM-1.

Conclusion

The combination of laser-based surface modification with TiN-based PVD coatings effectively reduces both acute and chronic inflammatory responses to 3D-printed titanium in vivo. The improved tissue reaction suggests better biocompatibility and supports the use of such surface engineering approaches for more stable long-term implant integration.

Acknowledgements

This research was supported by MUNI/LF-ACC/1129/2022 and the Czech Republic Ministry of Defence–University of Defence project for the Development of the Organization “DZRO Military autonomous and robotic systems”.

D3 – P020

TEER integration on a PMMA Organ-on-a-Chip for mimicking the blood-brain barrier

Valentino M.[1,2], Patella B.[1], La Rosa M.[1], Palumbo L.[3], Picone P.[3], Perricone U.[2], Inguanta R.[1], Lopresti F.[1], La Carrubba V.[1]

[1]Dept. of Engineering, University of Palermo; [2]Dept. of Molecular Informatics, Ri.MED Foundation; [3]Dept. of Neuroscience, Consiglio Nazionale delle Ricerche - Istituto per la Ricerca e l'Innovazione Biomedica (CNR-IRIB), Palermo, Italy

Introduction

The blood-brain barrier (BBB) is a highly selective cellular barrier that is crucial for drug development. Organ-on-a-Chip (OoC) technology is attracting increasing interest, although scaffold integration remains a challenge. A non-invasive technique for evaluating the BBB integrity *in-vitro* is by measuring the transepithelial/transendothelial electrical resistance (TEER), usually made by wire electrodes integrated into thermoelastic-based OoC[1].The aim of this work is to integrate the TEER system into a thermoplastic-based OoC device with an electrospun scaffold integrated for monitoring the BBB integrity (BBBoC).

Materials and Methods

To fabricate the chip, PMMA sheets were cutted using a CO_2 laser cutter. The electrodes for TEER were made by sputtering gold onto PMMA, oxidised by NaOH solution treatment to improve the gold adhesion and copper tapes were used to enable the electrical connection. The layers were then assembled using a hot press, coadiuvated by ethanol. An electrospun PLA membrane was produced and integrated into the BBBoC to define two chambers for the dynamic culture of endothelial cells and brain cells. Validation included computational fluid dynamics (CFD) simulation to optimize the inlet velocity values in order to produce a homogeneous wall shear stress (WSS) on the cell culture surface, water contact angle (WCA) to evaluate the effectiveness of the oxidation treatment on PMMA layers.

Results

The OoC was design on Fusion 360 (**Figure 1a**) and successfully assembled following the layer-by-layer procedure (**Figure 1b**). Through the CFD simulations, setting an inlet velocity of 0.001 m/s in the brain chamber (**Figure 1c**) and 0.1 m/s in the vascular chamber (**Figure 1d**), two homogeneous WSS maps were obtained, according to physiological values[2]. The reduction of WCA shown on PMMA untreated (**Figure 1e**) and after oxidation treatment (**Figure 1f**) proves its effectiveness.




Figure 1: (a) Design on Fusion 360 of the PMMA-based BBBoC with electrospun scaffold,TEER electrodes and copper tapes integrated; **(b)** BBBoC assembled the PMMA layers by placing ethanol between the layers and applying the hot press; **(c)** WSS map of the culture surface for the upper chamber (brain); **(d)** WSS map of the culture surface for the lower chamber (vascular); **(e)** WCA of PMMA surface before the oxidation treatment; **(f)** WCA of PMMA surface after the oxidation treatment.

Conclusion

A BBBoC was fabricated based on a layer-by-layer technique using CO_2 laser cutter and thermal press for a thermoplastic OoC. PLA electrospun membrane and gold sputtered electrodes were successfully integrated into the device.

References

[1]Malik M., Steele S.A., Mitra D. Trans-epithelial/endothelial electrical resistance (TEER): Current state of integrated TEER measurements in organ-on-a-chip devices. *Current Opinion in Biomedical Engineering* 2025; 34; 100588.
[2]Maoz B.M., Herland A., FitzGerald E.A. A linked organ-on-chip model of the human neurovascular unit reveals the metabolic coupling of endothelial and neuronal cells. *Nature Biotechnology* 2018; 36; 865-874.

D3 – P021

Osteoporosis-on-Chip: A PLA-based microfluidic platform for preclinical testing

Tornabene S.[1], Calambriso N.[2], Lopresti F.[1], Macaluso D.[1] Carmagnola I.[3], Annunziata M.[2], La Carruba V.[1]
[1]Dept. of Engineering, University of Palermo, Palermo, Italy; [2]Dept. of Experimental Medicine, University of Salento, Lecce, Italy; [3]Politecnico di Torino, Dept. of Mechanical and Aerospace Engineering, Torino, Italy

Introduction

Increasing ethical, regulatory, and environmental pressures to reduce animal testing have accelerated the development of Organ-on-Chip (OoC) systems as promising and relevant alternatives to animal models. In this work, we present an Osteoporosis-on-Chip device fabricated from poly(lactic acid) (PLA), a biodegradable thermoplastic derived from renewable resources. The OoC integrates an electrospun PLA membrane functionalized with gelatin to enhance cell compatibility. The aim of this study is to develop a sustainable osteoporosis-on-Chip platform using materials processed through rapid prototyping techniques, ensuring optimal mechanical and microfluidic performance.

Materials and Methods

The Osteoporosis-on-Chip was fabricated from PLA (NatureWorks 2003D) pellets via compression molding (200°C, 1200 psi, 6 min). Layers were patterned by a laser cutter (20% power, 15 mm/s) and bonded via cold plasma (200 W, 240 s) and thermal pressing (70°C, 1200 psi, 3 min). A bilayer electrospun PLA membrane (10wt% in chloroform:acetone 2:1 vol) was produced with random and aligned fibers, and APTES-functionalized (1 cm gap, 60 s, 1.5 L/min air) with gelatin. Validation included tests on human cell cultures of mesenchymal stem cells (MSCs) and endothelial cells, numerical simulations and microfluidic test.

Results

The chip was successfully assembled under the described process (fig.1 A, B). Electrospun membrane integration preserved structural integrity and APTES functionalization efficacy. Numerical simulations combined with experimental analyses allowed the identification of optimal wall shear stress conditions for both MSC and endothelial cell monocultures. Furthermore, MSC–endothelial cell co-cultures were successfully established within the device. Under these conditions, MSCs exhibited a pronounced differentiation toward the osteoblastic lineage, as confirmed by enhanced matrix mineralization (Fig.2).

Conclusion

This work standardizes PLA-based OoC production via compression molding, CO_2 laser cutting, and optimized plasma/APTES functionalization. The resulting device meets all mechanical and dimensional requirements while leveraging PLA's eco-friendly and biodegradable. Unlike conventional single-use microfluidic devices typically disposed of through incineration, and contributing to environmental pollution, this sustainable Osteoporosis-on-Chip platform significantly reduces the ecological footprint of preclinical testing systems. Overall, this OoC features as an innovative tool scalable for disease modeling and preclinical research.

Acknowledgements

This research was supported by PRIN-2022 Green Microfluidic platform for advanced tissue-on-a-Chip cultures (Green MID-PLACE), financed by the European (Next-GenerationEU-plan).




Fig. 1 Design of the osteoporosis-on-chip model A) Focus of the 3D model and functional separation of the electrospun membrane B) OoC after manufacturing processes




Fig. 2 Quantification of mineralization by ARS assay on BMSCs in monoculture or in co-culture with HMEC-1 on r-PLA or a-PLA scaffolds. *$p < 0.05$ versus BMSC monoculture.

D3 – P022

Comparative evaluation of crosslinking strategies for decellularised bovine pericardium for next-generation transcatheter aortic valve leaflets

Desai A.[1,3], Roe J.[1,2], Berry H.E.[1,2], Jennings L.M.[1,3]
[1]Institute of Medical and Biological Engineering, University of Leeds; [2]School of Biomedical Sciences, University of Leeds, UK; [3]School of Mechanical Engineering, University of Leeds, UK

Introduction

Improving long-term durability of transcatheter aortic valve (TAV) leaflets remains limited by calcification and structural degeneration associated with conventional glutaraldehyde (GA) fixed pericardium. Decellularisation can reduce calcification and immunogenicity, while alternative crosslinkers and matrix fillers offer additional ways to limit mineralisation and enhance stability. This study compares the biological, physicochemical and mechanical performance of several crosslinking strategies applied to decellularised bovine pericardium (DBP) and benchmarked against GA-crosslinked cellular control.

Aim

To compare how different crosslinking strategies influence the biological, physicochemical and mechanical performance of DBP for next-generation TAV leaflet materials.

Materials and Methods

Bovine pericardium was decellularised using a low-concentration sodium dodecyl sulphate protocol[1]. Decellularised samples were treated with various crosslinking strategies. All study groups, concentrations, abbreviations, and their scientific rationale and assessments are summarised in Table 1. Statistical analysis used non-parametric tests with Bonferroni correction or one-way ANOVA with suitable post-hoc tests.

Results

Biological analysis showed preserved extracellular matrix across all groups, with the greatest surface calcification in GA-treated DBP and reduced calcium deposition in PEG-NHS DBP. Enzymatic resistance for GA-treated DBP and EDC/NHS was comparable to GA-crosslinked cellular control. Water activity was significantly higher only in PEG-NHS 8-arm (1:1000) compared with DBP ($p<0.05$), whereas water content did not differ significantly between DBP and any crosslinked groups, though several PEG-NHS groups exhibited higher hydration than the GA-crosslinked cellular control. The peak onset temperatures (a measure of thermal stability) of all the GA groups and the EDC/NHS were not significantly different, the PEG groups were significantly lower than all the GA groups and EDC/NHS.

Conclusion

Decellularised bovine pericardium crosslinked with PEG-NHS or EDC/NHS demonstrated favourable biological and physicochemical properties, reduced surface calcification, and maintained mechanical properties, supporting their potential for TAV leaflets.

Acknowledgements

This research is supported by Engineering and Physical Sciences Research Council.

References

[1]Booth C., Korossis S.A., Wilcox H.E., Watterson K.G., Kearney J.N., Fisher J., Ingham E. Tissue engineering of cardiac valve prostheses I: Development and histological characterization of an acellular porcine scaffold. *Journal of Heart Valve Disease* 2002; 11; 457–462.

Table 1

Study groups, abbreviation, purpose and assessments			
Bovine pericardium group	**Concentration**	**Abbreviation**	**Rationale**
Control and Reference Groups			
Cellular	-	Cellular BP	Cellular baseline
Cellular crosslinked with glutaraldehyde	0.6 %	Cellular BP - 0.6%GA	GA-crosslinked cellular control
Decellularised	-	DBP	Effect of decellularisation alone
Crosslink groups			
Decellularised and crosslinked with glutaraldehyde	0.1%	DBP - 0.1% GA	Low concentration GA
	0.6%	DBP - 0.6% GA	High Concentration GA
Decellularised and crosslinked with Carbodimiide/NHS	0.1 %	DBP – EDC/NHS	Zero-length carbodiimide collagen crosslinking
Decellularised and crosslinked with 4 -arm PEG –NHS	1:1	DBP - 4-arm PEG-NHS (1:1)	Space-filling surface modification
	1:10	DBP - 4-arm PEG-NHS (1:10)	
	1:1000	DBP - 4-arm PEG-NHS (1:1000)	
Decellularised and crosslinked with 8 -arm PEG –NHS	1:1	DBP - 8-arm PEG-NHS (1:1)	
	1:10	DBP - 8-arm PEG-NHS (1:10)	
	1:1000	DBP - 8-arm PEG-NHS (1:1000)	
Assessments			
Biological assessments: histology, resistance to enzymatic digestion for all groups, and in vitro calcification over 10 days for only DBP, DBP–0.1% GA, DBP–0.6% GA, EDC/NHS, and both 4-arm and 8-arm PEG-NHS (1:1000). [3 hearts/group; specimen numbers = 18 (most groups) or 6 (PEG-NHS 1:10 and 1:1000)]			
Physicochemical assessments: water activity and water content; and thermal degradation [3 hearts/group; specimen numbers = 18 (most groups) or 6 (PEG-NHS 1:10 and 1:1000)			
Biomechanical performance :uniaxial tensile parameters [ultimate tensile stress (UTS), collagen-phase modulus, and failure strain] in circumferential and axial directions. [12–24 specimens per group from ≥3 hearts]			

D3 – P023

Biological impact on endothelial cells following stimulation by immobilized growth factors

Langner L. M.[1, 2], Loza K.[2], Hiepen C.[3], Epple M.[2], Veith M.[1]
[1]Molecular Biophysics, Faculty of Engineering and Applied Sciences, Westphalian University of Applied Sciences, Recklinghausen; [2]Inorganic Chemistry, Faculty of Chemistry, University of Duisburg-Essen; [3]Biomedicine and cellular biomechanics, Faculty of Engineering and Applied Sciences, Westphalian University of Applied Sciences, Recklinghausen, Germany

Introduction

Despite continuous technological progress, the long-term clinical performance of cardiovascular stents remains limited by insufficient and delayed endothelialization, contributing to in-stent restenosis and thrombotic complications. Impaired vascular healing following implantation can promote neointimal hyperplasia and luminal re-narrowing. Targeted biofunctionalization of implant surfaces has therefore emerged as a promising strategy to modulate early cell–material interactions, enhance endothelial coverage, and potentially mitigate restenosis-associated failure mechanisms.

Methods

The response of the immortalized human endothelial cell line HUVEC/TERT2 to biofunctionalized implant model surfaces was investigated using a comparative in vitro approach. Functionalized and non-functionalized substrates were analyzed to evaluate differences in cell adhesion, spatial distribution, and morphological organization. Fluorescence microscopy was used to visualize endothelial coverage patterns and cytoskeletal arrangement, enabling qualitative assessment of cellular organization. In parallel, scanning electron microscopy (SEM) provided high-resolution insights into cell morphology and surface contact behavior at the biomaterial interface.

Results

Qualitative imaging analyses revealed distinct differences in endothelial cell behavior between functionalized and non-functionalized surfaces. Fluorescence microscopy indicated altered cell distribution and cytoskeletal organization, suggesting enhanced spreading and more homogeneous surface coverage of HUVEC/TERT2 cells on biofunctionalized substrates (Fig. 1). Complementary SEM observations demonstrated variations in cellular morphology and adhesion-related features (Fig. 2A), including differences in cell density, cell flattening, formation of membrane protrusions, and the extent of surface interaction (Fig. 2B). These findings collectively point toward an improved early endothelial interaction profile on functionalized surfaces, a factor considered critical in limiting biological processes associated with in-stent restenosis.

Conclusion

The combined application of fluorescence microscopy and SEM enables an integrative evaluation of early endothelial responses to biofunctionalized implant model surfaces. Observed differences in adhesion behavior and morphological organization suggest that targeted surface biofunctionalization may support more favorable endothelialization. Such surface-driven strategies hold strong potential for improving vascular healing and reducing restenosis-related remodeling, thereby contributing to the development of next-generation cardiovascular stents with enhanced long-term performance.

Acknowledgements

I. Krützner is gratefully acknowledged for valuable support and guidance regarding cell culture techniques and experimental procedures. The Heinrich Böll Stiftung is gratefully acknowledged for financial support.




Fig. 1: Fluorescence microscopy images of HUVEC/TERT2 on glass surface (A) and biofunctionalized surface (B). Images were acquired using a magnification of 20x and 63x with oil immsersion. [Staining: DAPI (blue), Phalloidin (white), VE-Cadherin (green), PECAM-1 (red)]




Fig. 2: SEM images of HUVEC/TERT2. (A) Overview (250×) on glass surface (left) and biofunctionalized surface (right). (B) Cells showing filopodia formation (left, 8,000× and 6,500×), overlapping filopodia (middle, 60,000× and 50,000×), and scar-like junction between two cells (right, 10,000×). Upper row: glass surface; lower row: biofunctionalized surface.

D3 – P024

Transforming vaccine administration with dissolvable microneedles

Yavuz A.[1], Escaich S.[1], Alessio M.[1], Mourier V.[1], Navarro F.[1], Texier I.[1]
[1]Univ. Grenoble Alpes, CEA, Leti, Grenoble, France

Introduction

Infectious diseases remain a major global health challenge, requiring innovative and patient-friendly vaccination strategies. Conventional intramuscular or subcutaneous injections demand trained personnel, generate sharps waste, and often cause pain or needle anxiety, limiting compliance and complicating large-scale immunization. Transdermal delivery with dissolvable microneedles (MNs) offers a promising alternative by enabling painless administration, eliminating sharps, and directly targeting the skin's dense network of antigen-presenting cells.

Aim

Our goal was to develop a platform of biphasic microneedle arrays comprising soluble tips serving as antigen reservoirs and able to deliver rapidly and efficiently their payload into the skin.

Materials and Methods

MN arrays comprising polyvinylpyrrolidone (PVP) as a baseplate and soluble hyaluronic acid (HA) tips were fabricated by a two-step casting process. MN tips were loaded with two antigen models: Cy5-labelled albumin, mimicking sub-protein vaccines, and DiD-labelled lipid nanoparticles, mimicking mRNA vaccine nanocarriers. Structural, mechanical, and payload quantification were performed by optical and fluorescence microscopy, compression testing, and dissolution kinetics in culture medium. Skin perforation and payload delivery were assessed in human skin explants.

Results

Fluorescence imaging confirmed exclusive antigen localization in distal MN tips, ensuring targeted delivery into viable epidermal and dermal layers. Compression tests demonstrated sufficient strength for skin perforation, while dissolution studies showed complete solubilization of MN tips within one minute, enabling rapid cargo release. Human skin explants validated epidermal perforation, confirming delivery to immune-relevant layers (Figure 1). Antigen uptake by skin-resident immune cells and in vivo immunogenicity are demonstrated.

Conclusion

The HA/PVP biphasic MN arrays thus combine precise antigen localization, mechanical strength, rapid dissolution and cargo delivery, and proven skin penetration. MN arrays appear as transformative tools to strengthen vaccination coverage and preparedness against emerging threats.

Acknowledgements

This work has received funding from the European Defence Fund (EDF) under the grant agreement RESILIENCE-R-2023 no.101168024. Funded by the European Union. Views and opinions expressed are those of the author(s) and do not necessarily reflect those of the European Union or the European Commission. Neither the European Union nor the granting authority can be held responsible for them.




Figure 1. Photograph of biphasic MN loaded with Cy5-labelled albumin (left, scale bar 500 µm). Diffusion of Cy5-labelled albumin into human skin explants 30 minutes (middle panels) and 6 hours (right panels) after MN device application.

D3 – P025

Beyond decoration: Free-standing lace embroidery for 3D shaped surgical mesh implants

Tonndorf R.[1], Elschner C.[1], Osterberg A.[1], Mozer V.[1], Wink de Menezes E.A.[1], Römer L.[2], Kyosev Y.[2], Spickenheuer A.[1,3], Scheffler C.[1,4], Stommel M.[1,5]
[1]Division Polymer Materials Engineering, Leibniz Institute of Polymer Research Dresden; [2]Chair of Development and Assembly of Textile Products, Institute of Textile Machinery and High Performance Material Technology, Dresden University of Technology; [3]Faculty Design, University of Applied Sciences HTW Dresden, Germany; [4]Institute of Construction Materials, Dresden University of Technology; [5]Institute of Materials Science, Dresden University of Technology, Germany

Introduction

In contemporary breast reconstruction, autologous tissue remains standard, while implant-based approaches reinforced with Acellular Dermal Matrices (ADMs) or synthetic meshes are increasingly used to address limited autologous volume and reduce donor-site morbidity. ADMs and synthetic meshes are provided as planar constructs and must be shaped and secured during surgery to form a pocket; this prolongs operative time and often causes layer overlap, surface wrinkles and imperfect fit. Pocket stability and final geometry depend on the folding and fixation technique, producing variability between cases.

Aim

The aim of the study was to validate an embroidery-based route for producing near-net-shape mesh pockets that reduces intraoperative shaping and improves implant fit, and to demonstrate its feasibility on standard commercial embroidery equipment.

Materials and Methods

Parametric stitch geometries (stitch density and dome-forming segments) were defined in CAD and exported as embroidery files (Fig. 1a). Embroidery was performed on a commercial flat-bed Tajima machine using polypropylene monofilament on a polyvinyl-alcohol (PVA) soluble backing; after dissolution the free-standing lace pockets were rinsed, and draped over 3D-printed implant models (Fig. 1b). Mechanical characterisation included filament and pocket tensile testing, drop (impact-relevant) tests and 3D surface scanning for geometric fidelity (Fig. 1c); finite-element analyses (FEA) simulated deformation and stress distribution for comparison with experiments.




Figure 1. (a) Examples for mesh pocket designs; (b) Embroidered mesh pockets with inserted 3D-printed implant model; (c) Overlay of embroidered pocket and implant from 3D scanning; colour scale indicates distance to the reference surface (green = close, red = distant).

Results

Machine embroidery enabled fabrication of novel three-dimensional, free-standing mesh pockets suitable for implant coverage. Experimental evaluation—tensile and impact tests plus 3D surface analysis—confirmed good mechanical performance and close fit with minimal surface irregularities. Filament diameter was the primary factor controlling strength, with stitch geometry also important; simply increasing mesh density produced limited benefit. Failures consistently initiated at the lateral dome sides, while pocket size and back-reinforcement had little effect on peak load[1].

Conclusion

Embroidery-fabricated, near-net-shape mesh pockets provide a practical, scalable alternative to intraoperative pocket formation by producing implant covers that closely match implant geometry with fewer wrinkles, overlaps and seams, thereby reducing the need for manual shaping and intraoperative handling and shortening operative time. Further studies are required to evaluate long-term biocompatibility, performance and handling in the surgical setting.

Acknowledgements

Supported by the ZIM program of the BMWE (KK5129006SK3) and the GO-Bio initial program of the BMFTR (03LW0621). Thanks to Scheibner H. and Scheibe K. for mechanical testing and to BioCer Entwicklungs-GmbH for the silicone implant.

References

[1]Tonndorf R., Elschner C., Osterberg A. et al. Beyond decoration: free-standing lace embroidery for 3D shaped surgical mesh implants. *Scientific Reports* 2026; 16; 8270.

D3 – P026

Microwave processing and degradation of metallic biomaterial, Mg alloy AZ31B

Prajapati D.R.[1], Tarunpreet S.[2], Shankar S.[2]
[1]Mechanical Engineering Dept., Punjab Engineering College (Deemed to be University); [2]Mechanical Engineering, UIET, Panjab University, Chandigarh, India

Introduction

Magnesium (Mg) alloys have lately enticed substantial consideration as metallic owing to its favorable characteristics of biocompatibility, biodegradability and mechanical behavior analogous to a natural bone. These characteristics render Mg alloys a suitable candidate for biomedical implant, including orthopedic fixation, orthopedic bone screws, and biodegradable scaffolds. AZ31B is one of the many Mg alloys that have been researched widely since it maintains a constant strength to weight ratio, exhibits formability and microstructure stability. In addition, Mg alloys are denser and have the same elastic modulus with human cortical bone as compared to the conventional implantation materials. However, corrosion rate of Mg alloys is very high in physiological conditions which is a major limitation. Microwave hybrid heating in this relation has emerged as one of the sustainable and developed processing techniques that can offer a quick volumetric heating, which can be used in determining the microstructure and surface properties of metallic materials.

Materials and Methods

The present study analyzes the electrochemical characteristics of AZ31B alloy subjected to a microwave treatment in terms of its promising conversion into a metallic biomaterial. The joints were manufactured with 300 W of microwave power. The electrochemical and physical analysis of the processed specimens was done in a 3.5 wt% NaCl solution.

Results

A substantial reduction in corrosion rate was observed, from 36.62 mm/year for the base specimen to 15.243 mm/year for the joint formed at 300 W, as determined by LSV and validated through EIS. Further, physical characterization outcomes were evaluated to analyze the variation in the biomaterial behavior.

Conclusion

The results show that microwave processing can be used in the modification of the microstructure and enhances the corrosion strength of the microwave processed material compared to the base material rendering the technique suitable for processing of metallic biomaterial, AZ31B.

References

[1]Zhou K., Lu Q., Qin J., Shi H., Zhang P., Yan H., Shi H., Wang X. A view of magnesium alloy modification and its application in orthopedic implants. *Journal of Materials Research and Technology* 2025, 36; 1536-61.
[2]Singh T., Sehgal S. On the Recent Investigations on Computational Modeling, Simulation, and Experimental Analysis of AZ31B Joints Through Microwave Hybrid Heating. *Archives of Computational Methods in Engineering* 2025, 8; 1-59.

D3 – P027

AC vs DC micro-arc oxidation: Ca/P/Se-modified coatings on Ti-13Nb-13Zr alloy

Makurat-Kasprolewicz B.[1], Matykina E.[2,3]
[1]Dept. of Biomaterials Technology, Gdansk University of Technology, Poland; [2]Departamento de Ingeniería Química y de Materiales, Universidad Complutense, Madrid, Spain; [3]Unidad Asociada al ICTP-CSIC, Instituto de Química Médica (IQM-CSIC), Grupo de Síntesis Orgánica y Bioevaluación, Instituto Pluridisciplinar (UCM), Madrid, Spain

Introduction

Titanium alloys are widely used for biomedical implants due to their favourable mechanical properties, corrosion resistance, and biocompatibility. The Ti-13Nb-13Zr alloy is considered a promising alternative to Ti-6Al-4V because it does not contain potentially cytotoxic elements. However, its long-term performance may still be limited by insufficient bioactivity in physiological environments. Micro-arc oxidation (MAO) forms porous oxide coatings that improve corrosion resistance. Incorporation of Ca, P, and Se may further enhance coating functionality, while the influence of the current regime remains insufficiently explored.

Aim

This study compared Ca/P/Se-incorporated MAO coatings produced on Ti-13Nb-13Zr alloy using alternating current (AC) and direct current (DC) regimes.

Materials and Methods

Ti-13Nb-13Zr discs were modified by MAO in an electrolyte containing $Ca(CH_3COO)_2$, $C_3H_7Na_2O_6P{\cdot}5H_2O$, and SeO_2. Two current regimes were investigated: AC and DC. Surface morphology, composition, and phase structure were analysed by SEM/EDS and XRD. Surface topography, wettability, and coating thickness were determined using optical profilometry, contact angle measurements, and eddy-current testing, respectively. Corrosion behaviour was investigated in Hanks' balanced salt solution (HBSS; 37 °C, 7 days) using open circuit potential, potentiodynamic polarisation, and electrochemical impedance spectroscopy. Bioactivity after 7 days of immersion in HBSS was evaluated by SEM/EDS and XRD.

Results

MAO coatings produced under AC and DC regimes exhibited distinct structural and functional properties. AC processing resulted in higher surface roughness (Sa≈1.18 μm) than DC coatings (Sa≈0.42 μm) and much greater thickness (~16.5 μm vs ~5.1 μm). AC coatings were also more hydrophilic, with a water contact angle of ~25° compared with ~46° for DC. SEM confirmed the typical porous MAO morphology of both coatings. Electrochemical measurements in HBSS revealed different corrosion behaviour depending on immersion time. DC coatings showed higher resistance of the outer porous layer at early stages, whereas AC coatings exhibited improved mid-term corrosion resistance. Moreover, after 168 h of immersion, AC coatings were almost completely covered with a Ca–P-rich layer, indicating pronounced early bioactivity.

Conclusion

The MAO current regime significantly influences the structure and performance of Ca/P/Se-incorporated coatings on Ti-13Nb-13Zr alloy. AC processing produced thicker, rougher, and more hydrophilic coatings, resulting in improved mid-term corrosion resistance and enhanced early bioactivity through extensive Ca–P mineralisation. In contrast, DC coatings showed better short-term resistance to electrolyte penetration but slower mineralisation.

Acknowledgements

This research was funded by the Polish National Science Center (grant no. 2023/49/N/ST5/03551, PRELUDIUM program, B.M.-K.). The support of PID2024-158719OB-C33 (MICIU/AEI/10.13039/501100011033/FEDER, UE) and PLEC2023-010346 (MICIU/AEI/10.13039/501100011033, Spain) is acknowledged.

D3 – P028
Nanostructured Ti13Nb13Zr (TNZ) alloy for orthopedic applications

Ozonuk O. C.[1], Doğan M. Z.[3], Gültekinoğlu M.[3], Yakar E.[3,4], Bayram C.[3], Ercan B.[1,2]
[1]Dept. of Metallurgical and Materials Engineering, Middle East Technical University; [1]BIOMATEN, METU Center of Excellence in Biomaterials and Tissue Engineering; [3]Hacettepe University, Graduate School of Science and Engineering, Dept. of Nanotechnology and Nanomedicine; [4]OSTİM Technical University, Dept. of Nanotechnology Engineering, Ankara, Turkey

Introduction

Titanium and its alloys are widely used in orthopedic implants due to their excellent corrosion resistance, mechanical strength, and biocompatibility. However, their bioinert surface limits osseointegration after implantation [1]. Surface processing are therefore required to improve interaction of the implant surface with bone tissue. Electrochemical anodization is an effective method to fabricate nanostructured oxide layers on titanium alloys, which can enhance cellular interactions because of increased nanoscale surface roughness, altered surface chemistry, and surface hydrophilicity [2]. In this study, nanoporous oxide layer was fabricated on TNZ alloy which have lower elastic modulus than commercially used implant materials via anodization [3]. Surface properties, corrosion behavior, and cellular interactions of the anodized TNZ were systematically investigated for orthopedic implant applications.

Materials and Methods

TNZ samples were anodized in an electrolyte containing 0.2 M NH_4F, 10 vol% H_2O, and ethylene glycol at 40 V for 5 min, followed by heat treatment at 300 °C for 1 h. Anodized samples were characterized using SEM, AFM, XPS, and TEM. Corrosion behaviour was assessed using electrochemical polarization and EIS methods in 1X PBS. For cytotoxicity assessment, MC3T3-E1 cells were seeded onto sterilized samples and cultured in MEM-α supplemented with 10% FBS, 1% penicillin–streptomycin, and 1% L-glutamine at 37 °C, 5% CO_2. MC3T3-E1 viability experiments were performed using MTT assay. Cells were stained with rhodamine and DAPI to image f-actin filaments and nuclei, respectively. To evaluate the cellular functions, cells were seeded on the samples and cultured in osteogenic medium. ALP activity was determined using a commercial kit (ab83369, Abcam). Calcium deposition was assessed by Alizarin Red S staining. Total protein content was measured using the Bradford assay (Ozbiosciences). Statistical comparisons were performed via ANOVA approach.

Results

SEM images revealed the formation of a nanoporous oxide structure on the TNZ surface after anodization at 40 V, with an average pore diameter of 51 ± 14 nm. After anodization nanoscale roughness increased, with RMS values increasing from 1.4 ± 0.1 nm to 10.6 ± 0.8 nm. XPS analysis confirmed the formation of an oxide-rich surface layer containing Ti, Nb, Zr, and oxygen species. Also, anodization significantly improved the hydrophilicity of the TNZ surface. On the other hand, electrochemical measurements showed that the anodized sample current density of 19.4 nA/cm². Biological experiments demonstrated that cells adhered and spread well on the anodized surface, and the anodized sample showed higher cell viability after 5 days of culture *in vitro* compared to the non-anodized alloy. Importantly, TNZ surfaces upregulated alkaline phosphatase activity, and stimulated calcium mineral deposition in long-term in vitro functional assays.




Figure 1. SEM images of anodized sample at 40V a) lower, b) higher maginification.




Figure 2. MTT assay results of MC3T3-E1 cells cultured on the samples *in vitro*.

Conclusion

In this study, a uniform and crack-free nanoporous oxide layer was successfully fabricated on the TNZ via anodization. The nanostructured surface increased surface roughness and hydrophilicity and exhibited favorable corrosion behavior. In addition, anodized surfaces supported adhesion and viability of MC3T3-E1 cells, indicating the potential of anodized Ti13Nb13Zr for orthopedic implant applications.

Acknowledgements

We would like to acknowledge TUBITAK project no 22AG049 for funding.

References

[1]Abd-Elaziem W. et al. 2024; doi.org/10.1016/j.matdes.2024.112850.
[2]Webster T.J. et al. 2003; doi.org/10.1016/j.biomaterials.2003.12.002.
[3]Cvijovic-Alagic et al. 2014; doi.org/10.1016/j.corsci.2014.02.017.

D3 – P029

Optimization of nanostructured surfaces of the Ti-35Nb-5Ta alloy: Effect of electrochemical anodization on the functional performance of titanium dioxide nanotubes

Mesquita R.C.[1], Serra J.B.[2], Silva E.S.[2], Rodrigues S.F.[2], Batista B.S.[3], Alencar L.M.R.[3], Melo C.C.[1],Menezes A.S.[3], Lobo A.O.[1], Marciano F.R.[1]

[1]Federal University of Piauí, Teresina; [2]Federal Institute of Education, Science and Technology of Maranhão, São Luis; [3]Federal University of Maranhão, São Luís, Brazil.

This study investigates the optimization of nanostructured TiO_2 surfaces formed by electrochemical anodization on the Ti-35Nb-5Ta alloy and their influence on roughness, adhesion, and work function [1]. Techniques such as scanning electron microscopy (SEM), X-ray fluorescence (XRF) and X-ray diffraction (XRD), and energy-dispersive X-ray spectroscopy (EDS) confirmed the presence of equiaxed grains of the β phase (BCC) and amorphous TiO_2 nanotubes. Atomic Force Microscopy (AFM) indicated a 35% increase in the root-mean-square roughness (Rq) after anodization, which resulted in a 25% improvement in adhesion, attributed to the increased surface area with a smaller average diameter ($d < 80$ nm) and the nanometric morphology of the TiO_2 nanotubes [2]. Kelvin Probe Force Microscopy (KPFM) revealed an increase in the work function (φ) from 4.32 eV to 4.47 eV, related to vacancies (Ti; O) and greater Ti exposure inside the nanotubes, while a homogeneous mixture of oxides and other elements, such as Nb and Ta, occurs on the surface. The inner walls of the nanotubes present different degrees of crystallization and charge accumulation, making the work function (φ) sensitive to these variations, since amorphous and crystalline structures have distinct surface energies. These results indicate that electrochemical anodization improves roughness and cellular adhesion, suggesting the efficacy of the Ti-35Nb-5Ta alloy in osseointegration for biomedical applications.

References

[1]Nogueira R.P. et al. Characterization of Optimized TiO2 Nanotubes Morphology for Medical Implants: Biological Activity and Corrosion Resistance. *International Journal of Nanomedicine* 2021, v.16, 667-682.

[2]Dong Y., Ji X., Laaksonen A., Cao W., An R., Lu L., Lu X., Determination of the small amount of proteins interacting with TiO2 nanotubes by AFM-measurement, *Biomaterials 192* (2019) 368-376.

D3 – P030

Biocompatible MgTiCuZrNb high entropy alloy with superior tribo-corrosion properties under physiological conditions

Pal D.[1], Kumar D.[2], Kalyanasundaram D.[3]
[1]School of Interdisciplinary Research, Indian Institute of Technology Delhi; [2]Centre for Automotive Research and Tribology, Indian Institute of Technology Delhi, India; [3]Centre for Biomedical Engineering, Indian Institute of Technology Delhi, India

Introduction

The global phenomenon of population aging has heightened the need for biomedical implant materials. Stainless steel (SS), titanium alloys, and cobalt-chromium alloys have been pivotal in advancing implantable materials owing to their superior strength and exceptional corrosion resistance. Nevertheless, materials such as 316L stainless steel and Ti6Al4V, frequently used in clinical settings, contain hazardous compounds, such as nickel and vanadium, which may impede cell growth after implantation [1]. Moreover, the gradual release of aluminum from implant materials within the human body presents a possible risk for the onset of Alzheimer's disease [2]. Furthermore, with Young's modulus for stainless steel and cobalt-chromium alloys exceeding 200 GPa, this greatly surpasses the 4 GPa–30 GPa range reported in human bones, resulting in a stress-shielding effect that is deleterious to osteogenesis and organism repair [3]. Consequently, it is essential to develop innovative materials that exhibit enhanced strength and corrosion resistance while ensuring the exclusion of harmful substances to meet the increasing demand for biomedical implant materials [4]. In order to overcome this critical research gap, an equimolar high entropy alloy with a single crystal phase can be employed.

Aim

To address the density-corrosion trade-off and the evolution of tribo-corrosion characteristics in simulated bodily fluid.

Materials and Methods

Powders of Magnesium (Mg, Purity 99%, APS 40-50 µm, CAS 7439-95-4), Titanium (Ti, Purity 99%, APS 40-50 µm and CAS 7440-32-6), Copper (Cu, Purity 99%, APS 40-50 µm, CAS 7440-50-8), Zirconium (Zr, Purity 99%, APS 40-50 µm, CAS 7440-67-7), and Niobium (Nb, Purity 99%, APS 40-50 µm, CAS 7440-03-1) were purchased from Intelligent Materials Private Limited (Punjab, India). Toluene was purchased from Thermofisher Scientific (Massachusetts, U.S.). Equimolar MgTiCuZrNb HEA was developed by ball-milling followed by sintering method.

Results

The biocompatibility of the developed HEA was evaluated by MTT assay. Figure 6 is representing the cell viability of more than 94.5 % after 72 h is indicative of optimum cell viability required for biomedical applications. Figure 7 exhibiting the live-dead assay on MgTiCuZrNb HEA, which indicates optimum cell adhesion with the HEA surface.




Figure 2. MTT assay data to assess the biocompatibility of the developed MgTiCuZrNb HEA




Figure 3. Live and dead assay on MgTiCuZrNb

Conclusion

The developed HEA is biocompatible with the L929 fibroblast cell line. It can be suitable for biomedical applications.

Reference

[1]Adhikari J., Saha P., Mandal P., Sinha S. K. Seikh A., H. Mohammed J. A., Ghosh M. A Review on High Entropy Alloys as Metallic Biomaterials: Fabrication, Properties, Applications, Challenges, and Future Prospects. Biomedical Materials and Devices. *Springer* 2025. https://doi.org/10.1007/s44174-025-00314-4.

[2]Yu B., Chen J., Ding N., Yang X., Bao W., Cai Z., Xie G. Effect of Si Additions on Microstructure and Properties of TiZrHfNbSix High-Entropy Alloys as Potential Biomaterials. *Materials Science and Engineering* 2024, 915. https://doi.org/10.1016/j.msea.2024.147223.

[3]Rajabi M., Dehghani K., Shahmir H. Development of a Novel Ti35Nb25Zr15Mo15V10 High-Entropy Alloy for Metallic Biomaterials. *Physica B Condens* 2024, 691. https://doi.org/10.1016/j.physb.2024.416283.

[4]Li C., Ma Y., Yang X., Hou M. New TiTaNbZrMo High-Entropy Alloys for Metallic Biomaterials. *Mater. Res. Express* 2021, 8 (10). https://doi.org/10.1088/2053-1591/ac2f0b.

D3 - P031

Investigation of the effects of Mg degradation products on endothelial cells to evaluate the potential impact on blood vessel formation

Helmholz H.[1], Soetebeer L.[1], Voigt F.[2], Zeller-Plumhoff B.[2], Willumeit-Römer R.[1]
[1]Institute of Metallic Biomaterials, Helmholtz-Zentrum Hereon, Geesthacht; [2]Data-driven Analysis and Design of Materials, University Rostock, Germany

Introduction

The process of new blood vessel formation is essential for restoring oxygen and nutrient supply as well as recruitment of repair cells to ensure tissue regeneration in case of trauma and bone defects. This essential process can be modified by degradable Magnesium (Mg)-based materials. To characterize the biomaterial impact on angiogenesis not only cell migration but also tube formation are parameters to be studied at a cellular level. In addition, molecular-biological pathways influenced by the degradation process, and leading to a modified endothelial cell behaviour, have to be elucidated. A few observations indicate a positive impact of Mg on angiogenesis that was related to the induction of VEGF a growth promoter of endothelial cells, to the change of cytoskeleton network to increase mobility, to increase sensitivity against HIF and a general increase of cell proliferation (1).

Materials and Methods

Primary human endothelial cells obtained from umbilical cord vessels (HUVECs) will be utilized as in vitro model and exposed to Mg degradation products in a dose-dependent manner. Cell response will be determined at different level in form of proliferation, migration and gene expression. Live cell imaging has been applied to measure cell migration behaviour in a scratch assay. Cell viability was measured via CCK8 assay and gene expression utilizing qRT-PCR.

Results

Our results determined a Mg-concentration dependent inhibitory effect on primary endothelial cells. The migration kinetics showed an induction at a concentration of < 10 mM Mg accompanied with an increased wound closure. Finally the expressions of angiogenetic markers such as vascular endothelial growth factor receptor 1 (VEGFR-1/FLT1) and vascular endothelial growth factor receptor 2 (VEGFR-2/KDR) was influenced. It turned out that a donor dependent effect has to be considered. The data have been utilized to develop mathematical models to simulate and predict the cell behaviour under the impact of Mg.

Conclusion

Considering the fundamental role of vascularization for implant integration and tissue regeneration the potential effects of Mg-based biomaterials on endothelial cells is a valuable benefit. To understand the underlying mechanisms of Mg-related effects on angiogenesis, it is necessary to homogenize the multitude of applied methods. The establish mathematical tools will help to predict cellular behaviour with spatial and temporal resolution.

References

[1]Zhao N., Zhu D. Endothelial responses of magnesium and other alloying elements in magnesium-based stent materials. *Metallomics* 2015; 7; 118-128.

D3 – P033

Improvement in balance of strength and ductility of Ti alloys subjected to HPT processing for biomedical appliations

Kakiuchi K.[1], Akahori T.[2], Adachi N.[3], Todaka Y.[3], Niinomi M.[4]
[1]Graduate School of Science and Engineering, Meijo University, Nagoya; [2]Faculty of science and Technology, Meijo University, Nagoya; [3]Graduate School of Engineering, Toyohashi University of Technology; [4]Institute for Materials Research, Tohoku University, Sendai, Japan

Introduction

Titanium materials are extensively utilized in biomedical applications; in particular, commercially pure titanium containing controlled amounts of oxygen has historically been widely adopted. However, its relatively low mechanical strength has prompted a shift toward the utilization of α+β-type and β-type Ti alloys. Generally, α+β-type Ti alloys possess high specific strength but exhibit limited workability, whereas single-β-phase Ti alloys offer excellent workability but suffer from relatively low strength. Therefore, this study systematically investigates the modifications in the mechanical properties of both α+β-type Ti-6Al-7Nb (Ti-67) and β-type Ti-29Nb-13Ta-4.6Zr (TNTZ) alloys subjected to high-pressure torsion (HPT), a severe plastic deformation processing technique.

Materials and Methods

Ti-67 and TNTZ bars subjected to annealing and solution treatments in a vacuum, respectively, were mechanically machined and wet-polished into coin-shaped 0.8 mm-thick specimens. The HPT processing was performed at room temperature under a pressure of 1.25 GPa and a rotation speed of 0.2 rpm for various numbers of rotations (N = 0.25, 0.5, 0.75 and 1.0 for Ti-67. N = 1.0, 5.0 and 10 for TNTZ). Microstructural observations and mechanical property evaluations, including Vickers hardness and tensile tests, were subsequently performed on each specimen.

Results

As shown in Fig. 1, the HPT treatment of Ti-67 results in a significant increase in the mechanical strength (tensile strength), which increases from 1130 MPa at a rotation number of 0.25 to 1205 MPa at a rotation number of 0.5, as compared to that of the untreated Ti-67 specimen (876 MPa). However, the strength did not further increase at the rotation numbers of 0.75 and 1.0. These results suggest that the strain hardening of Ti-67 saturates at a relatively low rotation number of 0.5. Consequently, Ti-67 exhibits a narrow window of HPT conditions for strength enhancement, allowing the mechanical strength to be improved rapidly and efficiently within a single rotation (N = 1.0).




Fig.1 Tensile properties of Ti-67 before and after HPT processing.

Conclusion

The HPT processing of Ti-67 resulted in a high tensile strength exceeding 1200 MPa at a low rotation number of 0.5, at which point the strain hardening appeared to saturate. Therefore, the findings suggest that the mechanical strength of the α+β-type titanium alloy Ti-67can be improved rapidly and efficiently within a single rotation (N = 1.0) during HPT processing.

References

[1]Niinomi M. Development of Strengthening and Toughening of β-type Titanium Alloys Matrria Japan 58. 2019; 193-200.
[2]Edalati K., Horita Z. A review on high-pressure torsion(HPT) from 1935 to 1988, *Mater. Sci. Eng. A652*; 2016; 325-352.

D3 – P034

Improvement of mechanical properties of β-type Ti alloy through various strengthening mechanisms for biomedical applications

Kamada Y.[1], Akahori T.[2], Adachi N.[3], Todaka Y.[3], Niinomi M.[4]
[1]Graduate School of Science and Engineering, Meijo University, Nagoya; [2]Faculty of Science and Technology, Meijo University, Nagoya; [3]Graduate School of Engineering, Toyohashi University of Technology, Japan; [4]Institute for Materials Research, Tohoku University, Sendai, Japan

Introduction

In recent years, metallic biomaterials for in vitro applications have been required to exhibit higher biocompatibility and superior durability. A newly developed titanium alloy, Ti-29Nb-13Ta-4.6Zr (TNTZ), has attracted significant attention due to its low Young's modulus, which is approximately equal to that of cortical bone. However, as compared to other biomedical Ti alloys, TNTZ in the single β-phase condition exhibits a low tensile strength of less than approximately 600 MPa. Therefore, improving the mechanical strength of TNTZ is crucial for ensuring its reliability in clinical applications. In this study, various mechanical strengthening methods, including solid-solution strengthening via the addition of oxygen, work hardening via cold rolling and high-pressure torsion (HPT) processing, and precipitation hardening via solution and under-aging (STA) treatments, were applied to TNTZ to investigate their respective effects on the mechanical properties of the alloy.

Materials and Methods

The materials used in this study were TNTZ with 0.1 mass% O, which served as the base material (designated as TNTZB), and TNTZ with 0.7 mass% O for solid-solution strengthening. For the work hardening specimen, TNTZB was cold-worked into plates at a reduction ratio of approximately 80%. Furthermore, HPT processing, was also applied under a processing condition of one rotation (N = 1.0). Conversely, for precipitation hardening, a solution treatment (ST) was conducted on TNTZB followed by an STA treatment. Following these respective strengthening treatments, microstructural observations, and mechanical property evaluations, including Vickers hardness, tensile, and fatigue tests, were performed.

Results

Figure 1 shows the tensile properties of TNTZB and TNTZ subjected to each strengthening method. The highest tensile strength (σB) and 0.2% proof stress (σ0.2) were achieved in the TNTZ specimen subjected to HPT processing, which exhibited values 106% (σB:1090 MPa) and 132% (σ0.2:866 MPa) higher than those of the baseline TNTZB (σB, σ0.2:530 MPa, 451 MPa). Conversely, all elongation values followed an inverse trend across all conditions, although the TNTZ specimen with 0.7 mass% O and the TNTZ subjected to STA still maintained elongations exceeding 20%. Figure 2 shows the fatigue properties of TNTZB and TNTZ subjected to each strengthening method. The fatigue limits for all strengthened TNTZ conditions followed an increasing trend identical to that of the tensile strength. In particular, the TNTZ specimen with 0.7 mass% O exhibited the highest fatigue limit at 630 MPa. Overall, the TNTZ subjected to solid-solution strengthening provides a significantly better balance of tensile and fatigue properties.




Fig. 1. Tensile properties of $TNTZ_B$ and of the TNTZ specimens subjected to various strengthening methods.




Fig. 2. Fatigue properties of $TNTZ_B$ and of the TNTZ specimens subjected to various strengthening methods.

Conclusion

TNTZ subjected to solid-solution strengthening via the addition of 0.7 mass% O exhibited a significantly better balance of mechanical strength and ductility, as compared to the specimens subjected to the other strengthening methods.

References

[1]Masaaki N. et al. J. Japan Inst. Metals, *Vol. 72, No.12* 2008; 960-964.
[2]Edalati K., Horita Z. A review on high-pressure torsion(HPT) from 1935 to 1988, *Mater.Sci.Eng.A652* 2016; 325-352.

D3 – P035

Relationship between surface hardening layer and mechanical properties of α+β type titanium alloy subjected to atmospheric oxidation treatment for biomedical and dental applications

Morimoto H.[1], Akahori T.[2]
[1]Graduate School of Science and Engineering, Meijo University; [2]Faculty of science and Technology, Meijo University, Nagoya, Japan

Introduction

The surface of titanium materials readily reacts with ambient oxygen at elevated temperatures due to strong chemical affinity, forming a titanium dioxide (TiO_2) surface film alongside a subsurface, oxygen-enriched zone that significantly alters the overall mechanical strength of the material[1],[2]. In this study, atmospheric oxidation (OX) treatments were applied to the α+β-type Ti-6Al-7Nb alloy, a material widely utilized in biomedical and dental applications, under varied processing conditions to systematically investigate the resulting modifications to its, mechanical properties.

Materials and Methods

The starting material used in this study was a Ti67 hot-forged material with a diameter of 30 mm (referred to as "as-received Ti67"). Atmospheric OX treatments were conducted on the Ti67 specimens under various OX conditions: processing temperatures of 873, 973, 1073, and 1173 K were utilized for holding times of 3.6, 10.8, and 21.6 ks, with each treatment followed by air-cooling. Thereafter, the OX-treated Ti67 specimens were designated based on their specific oxidation temperature and holding time, for example, Ti67 OX_{873K} or Ti67 $OX_{873K/3.6ks}$. Microstructural observations and mechanical property evaluations, including Vickers microhardness profiles and tensile testing, were subsequently conducted on each OX-treated Ti67 specimen.

Results

Cross-sectional examination near the specimen surface revealed the formation of a thin oxide film across all OX-treated Ti67 specimens, reaching a maximum thickness value of approximately 4.0 μm in the Ti67 $OX_{1173K/21.6ks}$ specimen. Figure 1 shows the Vickers hardness profiles as a function of the depth from the specimen surface to the interior of the as-received Ti67 specimen and Ti67 $OX_{21.6ks}$ specimens oxidized at various OX temperatures. The surface Vickers hardness of the oxidized Ti67 specimens reached its maximum at the outermost layer and increased progressively with an increasing oxidation temperature. Notably, the peak surface Vickers hardness of the Ti67 $OX_{1173K/21.6ks}$ specimen was approximately 80% greater than that of the as-received Ti67 material. Additionally, the tensile strength of the OX-treated Ti67 specimens also increased by approximately 10% for the Ti67 $OX_{1173K/21.6ks}$ condition, as compared to the as-received Ti67 material. Conversely, the elongation of the OX-treated Ti67 specimens decreased with an increasing OX temperature and holding time, which was primarily driven by brittle fracture within the grown oxide surface film and the underlying oxygen-enriched layer.




Fig 1. Vickers hardness profiles of the as-received Ti67 specimen and the Ti67 specimens oxidized at various temperatures for 21.6 ks

Conclusion

The Ti67 $OX_{1173K/21.6ks}$ specimen, which developed an oxide film thickness of approximately 4.0 μm, exhibited a maximum surface Vickers hardness 80％ greater than that of the as-received Ti67 specimen. Furthermore, the tensile strength of Ti67 $OX_{1173K/21.6ks}$ was approximately 10% higher than that of the as-received Ti67 specimen. Conversely, the elongation decreased considerably owing to the initiation of brittle fracture within both the oxide surface film and the underlying oxygen-enriched layer.

References

[1]Takahashi T. et al. J. Japan Inst. Light Metal, *Vol. 66, No. 6* 2016; 306-311.
[2]Akahori T. et al. J. Japan Inst. Metal, *Vol.75, No. 8* 2011; 452-459.

D3 – P036

Post-processing of additively manufactured Ti6Al4V scaffolds: Balancing surface homogenization, porosity and mechanical strength

Orłowska A., Kajzer W.
Dept. of Biomaterials and Medical Device Engineering, Fac. of Biomedical Engineering, Silesian University of Technology, Zabrze, Poland

Introduction

Additive manufacturing technologies enable the production of implants with enhanced functionality by replacing solid material with porous scaffolds that better match the mechanical properties of bone and provide space for tissue ingrowth, promoting improved implant integration. The increasing use of such implants creates a need for modification methods tailored to their unique characteristics. While open-pore structures support osseointegration, they also complicate surface modification, particularly within internal scaffold regions. Moreover, powder-based additive manufacturing produces highly developed surface morphologies due to partially melted powder particles attached to scaffold struts, necessitating specialized post-processing procedures to standardize surface characteristics[1,2].

Aim

The aim of this study is to present chemical etching protocols enabling the homogenization of surface morphology and the production of scaffold struts with very low roughness.

Materials and Methods

The investigations were conducted on highly porous scaffolds produced from Ti6Al4V using DMLS technology. The scaffold architecture was based on a diamond lattice structure with a pore size: 600 µm and a total porosity >50%. After fabrication, the scaffolds were cleaned of loose powder and subjected to vacuum annealing at 900 °C. The etching process was carried out in solutions based on HF and HNO_3 using continuous and multi-stage sequential etching. The modified scaffolds were evaluated in terms of surface morphology (SEM, optical profilometry), surface wettability (sessile drop method), and real porosity (helium pycnometry). Additionally, the mechanical properties of the scaffolds were assessed in a static compression test and FEM analysis.

Results

Replacing continuous etching with a sequential etching process while maintaining the same solutions resulted in the formation of smooth scaffold surfaces as well as a significant increase in pore size and real porosity. The experimentally determined mechanical parameters differed significantly from those predicted by FEM analysis. Chemical etching resulted in a substantial decrease in the measured mechanical strength of the scaffolds.

Conclusion

The complex geometry and highly developed surface morphology of additively manufactured porous implants necessitate the use of specialized post-processing procedures. Appropriate surface modification can reduce morphological heterogeneity associated with partially fused powder particles, thereby improving surface quality and potentially enhancing osseointegration and long-term implant performance.

References

[1]Wang P. et al. J. of Central South University. *28.4* 2021; 1068-1077.
[2]Ouyang P. et al. Materials & Design. *183* 2019; 108151.

D3 – P037

Additive manufacturing of corrosion-resistant Mg-Zn-Ca bulk metallic glass

Cavaliere G. P. [1], Eirefors J.[2], Hulsart Billström G. [2], Bryant M.[3], D'Elia F.[1], Persson C. [1]
[1]Division of Biomedical Engineering, Dept. of Materials Science and Engineering, Uppsala University, Sweden; [2]Dept. of Medical Cell Biology, Uppsala University, Sweden; [3]School of Engineering, University of Birmingham, UK

Introduction

Magnesium-based bulk metallic glasses (BMGs) are promising candidates for biodegradable implants because they combine the favourable mechanical properties of metallic glasses with the biocompatibility and mechanical compatibility of magnesium alloys. Compared with conventional crystalline Mg alloys, BMGs can exhibit improved corrosion resistance, which is critical for maintaining the mechanical integrity of load-bearing implants during degradation. However, their fabrication is challenging because glass formation requires very high cooling rates, and conventional processing routes are generally restricted to simple geometries. This study investigates the fabrication of $Mg_{65}Zn_{30}Ca_5$ BMG by laser powder bed fusion (PBF-LB) and evaluates the relationships between processing conditions, microstructure, corrosion behaviour, and cytocompatibility.

Materials and Methods

Gas-atomized $Mg_{65}Zn_{30}Ca_5$ powder was processed using an Aconity MIDI PBF-LB system. Laser energy input was systematically varied, and a rescanning strategy was applied to promote amorphous phase retention. The manufactured samples were characterized in terms of relative density, phase composition by X-ray diffraction, and microstructure by electron microscopy. Corrosion behaviour was assessed electrochemically in simulated body fluid. Cytocompatibility was evaluated using MC3T3-E1 preosteoblast cells.

Results

The results revealed a trade-off between densification and amorphous phase retention governed by laser energy input. High energy densities achieved near-full densification (~98%) but resulted in substantial crystallinity (~52%), while lower energy densities resulted in a mostly amorphous structures (>90%) at the cost of increased porosity (> 4%). Microstructural analysis revealed a layered structure characteristic of the PBF-LB process, with largely amorphous melt pool cores and localized crystallisation. Electrochemical testing demonstrated that higher amorphous content directly translated into improved corrosion resistance, with amorphous-rich samples exhibiting corrosion rates of approximately 0.36 mm/y compared to ~0.55 mm/y in more crystalline counterparts. Cytocompatibility assays confirmed acceptable cell viability (>70%) across the majority of conditions, with a trend toward improved biological response in samples with higher amorphous fractions, likely reflecting the more uniform and slower degradation behaviour associated with the glassy phase.

Conclusion

These findings demonstrate that PBF-LB is a viable and promising route for manufacturing Mg–Zn–Ca BMGs, and establish a clear link between energy input, microstructure, and functional performance. By tailoring processing parameters to balance density and amorphous content, it becomes possible to design degradation behaviour in additively manufactured Mg-based implants, opening a path toward geometrically complex, patient-specific biodegradable devices with controlled corrosion kinetics.

Acknowledgements

This work was supported by the EU Horizon 2020 Marie Skłodowska-Curie programme (Grant No. 956004), VINNOVA through the AM4Life Competence Centre (Grants 2019-00029 and 2024-03847), and the Swedish Research Council (Grant 2021-04708).

D3 – P038

Single-step green synthesis of rosmarinic acid-functionalized silver nanoparticles

Sciabica M.C.[1], Carfì Pavia F.[2], Brucato V.M.B.[2], Ghersi G.[1]
[1]Dept. of Biological, Chemical and Pharmaceutical Sciences and Technologies (STEBICEF), University of Palermo; [2]Dept. of Engineering, University of Palermo, Italy

Introduction

Silver nanoparticles (AgNPs) are promising biomedical nanomaterials for their antibacterial, antifungal, antiviral properties. Although chemical and physical synthesis methods remain the gold standard, they require toxic reagents with adverse effects on human and environmental safety. Eco-friendly approaches based on plant extracts have therefore gained interest, as they enable the synthesis of multifunctional AgNPs enriched with bioactive phytochemicals[1]. Rosmarinic acid (RA), a natural polyphenol commonly found in *Lamiaceae* plant species, is known for its anti-inflammatory and antioxidant properties: RA contributes to maintaining the cellular redox balance, protecting cells from ROS-mediated damage[2].

Aim

This study aims to synthesize AgNPs through a green synthesis method using pure RA as both reducing and stabilizing agent. This approach combines the antibacterial activity of AgNPs with the properties of RA, potentially enhancing nanoparticles efficacy while reducing oxidative stress–related side effects of silver-based nanomaterials.

Materials and Methods

A chemical reduction method was employed. Specifically, a 2 mM aqueous solution of silver nitrate ($AgNO_3$) was combined with a 2.22 mM aqueous solution of RA at pH 8, maintaining a volume ratio of RA:$AgNO_3$ of 1:2.6. The reaction mixtures were stirred for 30 minutes at 350 rpm using a double-stirring system with constant temperature control at 70 °C. The colloidal suspensions were purified and characterized by UV–Vis spectroscopy, Raman spectroscopy, dynamic light scattering (DLS) to evaluate their physicochemical properties. Cytotoxicity and antibacterial tests were performed to validate their biological efficacy.

Results

UV-Vis spectroscopy confirmed the AgNPs formation, characterized by the typical band at 400–500 nm. Raman spectroscopy confirmed the presence of oxidized polyphenolic structures derived from RA and their interaction with the AgNPs surface, likely enhanced by the SERS effect. DLS analysis indicated low polydispersity and a negative zeta potential for the synthesized AgNPs, suggesting good colloidal stability (Figure 1). Finally, biological assays demonstrated their non-cytotoxicity and antibacterial efficiency.


Conclusion

This single-step green synthesis approach enabled the successful synthesis of functionalized and stable AgNPs for biomedical applications. The biocompatibility and antibacterial properties confirmed their potential as a sustainable nature-derived therapeutic system.

References

[1]Sharma N.K., Vishwakarma J., Rai S., Alomar T.S., AlMasoud N., Bhattarai A. Green Route Synthesis and Characterization Techniques of Silver Nanoparticles and Their Biological Adeptness. *ACS Omega* 2022; 7(31); 27004–27020.
[2]Saba N., Taj M., Malik A.R., Ali R., Naved A., Dharmendra K.Y., Md I.H., Abdullah M.A. Biomedical features and therapeutic potential of rosmarinic acid. *Arch. Pharm. Res*. 2022; 45; 205–228.

Figure 1


Experimental synthesis scheme
AgNO3
RA
30 min
70 °C
RA - AgNPs
Raman spectroscopy
Size Distribution by Intensity
Intensity (Percent)
Size (d.nm)
UV-Vis of RA-AgNPs

D3 – P039
Mg-based TPMS scaffolds for cast bone implants

Dmitruk A.[1], Naplocha K.[1], Díaz Lantada A.[2,3], De Blas De Miguel A.[2]
[1]Dept. of Lightweight Elements Engineering, Foundry and Automation, Faculty of Mechanical Engineering, Wrocław University of Science and Technology, Poland; [2]Mechanical Engineering Dept., Universidad Politécnica de Madrid, Spain, [3]IMDEA Materials Institute, Getafe, Spain

Introduction
Magnesium can compete with materials conventionally utilized for bone implants (e.g. Ti or Co-Cr alloys) because it offers mechanical properties more closely mimicking the ones of human bones. Additionally it is bioresorbable and can be replaced in time with bone tissue during osteoregeneration processes, however, it's gradual biodegradation should be controlled to adjust its rate to the healing period

Aim
Create spatial bioresorbable Mg-based scaffolds for bone implants on a basis of TPMS lattices 3D-printed with SLA technology.

Materials and Methods
A collection of TPMS lattices (gyroid, schwarz, walled diamond, body centered cubic, face centered cubic and octet) with and without external solid walls was designed and optimized with differing geometry features (e.g. wall thicknesses, cell sizes, porosity levels). Selected models were additively manufactured with SLA and on their basis the plaster moulds were further prepared for investment casting with a chosen Mg-alloy. Compressive behaviour of selected structures will be evaluated both numerically and experimentally, resulting with mapping of the chosen properties (e.g. Young's modulus vs porosity). Chosen cast parts will be subjected to microscopy analysis and both polymer patterns and castings will be also investigated in terms of the dimensional accuracy in relation to the design.

Results
Figure 1 a presents exemplary SLA 3D-printed patterns, while Figure 1 b shows the readily made cast pieces. Precision of the technology allows one to closely replicate even the smallest features of the model with great detail. Nevertheless, the external envelope restricts the access to the porous core and severely complicates the process of cleaning of the part from the gypsum remnants. Shrinkage resulting from polymer or metal solidification affects both stages of the process i.e. 3D-printing and casting.



Fig. 1. Fabricated TPMS structures (without external walls): a) SLA patterns, b) Mg alloy castings

Conclusion
Combined SLA and investment casting technologies allow for production of easily customized and complex scaffolds. Processing shrinkage needs to be taken into account for potential rescaling of the design to match the desired dimension in casting.

Acknowledgements
This work was supported by KMM-VIN Research Fellowship 2024 "Topological optimization of cast cellular scaffolds for bone implants". The Fellowship holder (Dmitruk A.) would like to sincerely thank the UPM Team for all the support and helpful consultancy. Authors acknowledge the support of Pedro Ortego García with additive manufacturing tasks.

D3 – P040

Development of a natural polymer-based bioink for 3D bioprinting of dermal constructs with canine amniotic mesenchymal stem cells

Noronha J.J.P.[1], Munhoz L.L.S.[2], Da Silva C.B.G.[1], Martins D.S.[2], Ambrósio C.E.[1]
[1]Laboratory of Stem Cell Culture and Gene Therapy - GDTI, University of São Paulo/FZEA, Pirassununga; [2]Laboratory of Immunohistochemistry and Experimental Physiology - FIFE, University of São Paulo/FZEA, Pirassununga, Brazil

Introduction

3D bioprinting of skin tissues requires bioinks with suitable physicochemical and biological properties to preserve cell viability and enable the fabrication of complex three-dimensional architectures. In this context, the development of natural polymer-based bioinks has emerged as a promising strategy for skin tissue engineering applications. The objective of this study was to develop and apply a natural polymer-based bioink for dermal bioprinting and to evaluate the viability, morphology, and adhesion of canine amniotic mesenchymal stem cells (cAMSCs) within the bioprinted constructs (Figure 1).

Materials and Methods

The formulation consisted of 3% sodium alginate, 1.22% porcine gelatin, 0.4% microcrystalline cellulose, and 0.66% xanthan gum, dissolved in α-MEM medium supplemented with L-ascorbic acid. The preparation was carried out under aseptic conditions with controlled temperature and stirring to ensure homogeneity and sterility. cAMSCs at passage 3 were incorporated into the bioink using type I collagen to promote uniform cell distribution. Bioprinting was performed by extrusion using the Genesis™ bioprinter, with a layer height of 0.35 mm, 70% infill density, and a rectilinear infill pattern. Constructs were printed in nine layers onto 6-well plates, with a total of 1×10^6 cells per well. Crosslinking was achieved using a 3% $CaCl_2$ solution for 7 minutes, followed by PBS washes to remove excess calcium ions.

Cell viability and metabolic activity were assessed by MTT assay at 21 days of culture, while Live/Dead staining was performed at 7, 14, and 21 days to evaluate cell survival within the constructs. Scanning electron microscopy (SEM) was performed after 21 days of culture to assess cell adhesion to the construct, as well as cellular morphology and material surface characteristics. Histological evaluation was conducted at 14 and 21 days of maturation using hematoxylin and eosin, Masson's trichrome, and Picrosirius Red (PSR) staining to analyze cellular distribution, extracellular matrix organization, and collagen deposition.

Results

MTT results demonstrated preserved metabolic activity after 21 days (figure 2- i), indicating sustained cellular functionality within the bioprinted constructs. Live/Dead analysis confirmed high cell viability across all evaluated time points (figure 2- ii). The SEM revealed effective cell adhesion to the construct, with well-spread cells and close interaction with the material surface (figure 2- iii). Histological analyses showed homogeneous cell distribution and progressive extracellular matrix remodeling (figure 2- iv), with increased collagen deposition over the maturation period (figure 2- v). The PSR staining further demonstrated organized collagen fibers, suggesting active matrix synthesis by the embedded cells (figure 2- vi).

Conclusion

Overall, the developed bioink and bioprinting strategy effectively supported cell viability, metabolic activity, and matrix organization, highlighting its potential for skin tissue engineering.

Figure 1

Development of a Natural Polymer-Based Bioink for 3D Bioprinting of Dermal Constructs with Canine Amniotic Mesenchymal Stem Cells






Figure 2


i)



Legend: Cell viability at 21 days of 2D culture bioprinted assessed by the MTT assay. The 2D group showed significantly higher absorbance compared to the positive control (CP), indicating greater metabolic activity. Data are expressed as mean ± standard error of the mean (n = 8). ***p < 0.001, Mann–Whitney test. Analysis performed using GraphPad Prism® v10.


ii)






Legend: Fluorescence-based cell viability of cAM-MSC cells in 2D culture at 7 (A–C), 14 (D–F), and 21 (G–I) days using the LIVE/DEAD® assay. Panels A, D, G: live cells stained with Calcein-AM (green, GFP filter); panels B, E, H: dead cells stained with Ethidium Homodimer-1 (red, Texas Red filter); panels C, F, I: merged images (MERGE). Images obtained by confocal microscopy, 10× objective. Scale bar: 100 µm. Graphic representing the number of live and dead cells in 2D cultures at 7, 14, and 21 days. The central line indicates the median; limits represent 1.5× IQR. Different letters (A, B, C) indicate statistically significant differences ($p < 0.05$, ANOVA followed by Tukey's test). Analysis performed using GraphPad Prism® v10.

iii)




Legend: Scanning electron microscopy (SEM) images of bioprinted constructs containing cells cultured in a 2D model. (A) Inner region of the construct, showing material morphology and the presence of cells adhered to the matrix. (B) Outer region of the construct, illustrating the material surface with adherent cells. The black boxes indicate representative areas where cells in contact with the biomaterial can be observed and do not correspond to magnified views between images. Scale bar: 100 µm.

iv)




Legend: Histological analysis of 2D bioprinted constructs with CTM-AMc after 14 days of culture, stained with Ferric Hematoxylin and Eosin (HE). (A) 40× objective showing porous hydrogel matrix and dispersed cells (black arrows); (B) 100× detail showing individualized cells with eosinophilic cytoplasm and visible nuclei (red arrows). (C-D) At 21 days, 40× and 100× objectives respectively showing sparse cells with preserved cytoplasm (black arrows), visible nuclei (red arrows). Scale bar: 50 µm (A, C) and 20 µm (B, D).


v)



Histological evaluation of 2D constructs stained with Masson's Trichrome (MT) for collagen deposition. (A) At 14 days, the blue-stained matrix (black arrow) and individualized cells (red arrows) are shown; (B) At 21 days, isolated cells (red arrows) are seen in a dense blue matrix (black arrow), indicating matrix integrity and possible extracellular secretion. Objective: 40×. Scale bar: 50 µm.

vi)





Legend: Representative polarized light microscopy images of 2D constructs stained with Picrosirius after 14 (A, B) and 21 days (C, D), showing predominantly type I collagen fibers (intense red). No birefringent fibers compatible with type III collagen (green) were observed. Images acquired under conventional (A, C) and reduced contrast (B, D) polarized light. Scale bar: 10 µm. Quantification shown as boxplot of collagen area (% µm²) for 14 and 21 days, expressed as median, interquartile range (Q1–Q3), and 1.5× IQR (n = 4). Distinct letters (A, B) indicate significant difference ($p = 0.0286$, Mann–Whitney test). Analysis performed with GraphPad Prism® v10.

D3 – P041

Unconventional approach for the synthesis of MOFs based on Vanadium for antidiabetic therapy

Pepi S.[1], Cimino V.[1], Passaponti S. [2], Cresti L.[2] , Ietta F. [2], Leone G.[1], Magnani A.[1]
[1]Dept. of Biotechnology, Chemistry and Pharmacy, University of Siena; [2]Dept. of Life Sciences, University of Siena, Italy

Introduction

Metal–organic frameworks (MOFs) are a promising class of hybrid materials from metal cluster and organic linker, that generate highly organized and crystalline structure. High surface area and high free volume porosity are two peculiar properties of this type of structures and thanks to that they can be even suitable to be used as drug delivery systems.

Aim

In this work a vanadium (V)-gallic acid (GA) based MOF was synthesized using a sonochemical approach, with the aim of optimizing their properties for therapeutical function, such as antidiabetic agent. A Full Factorial Experimental Design (table 1) was used to investigate the effect of four synthetic parameters on melting temperature (T_m), melting enthalpy (ΔH_m), average particle size, and particle size distribution in terms of polydispersity index (PDI).

Materials and Methods

Vanadium (IV) oxide sulfate hydrate ($VOSO_4 \bullet 3H_2O$) was used as the inorganic precursor, while gallic acid (GA) acted as organic crosslinker agent to modulate MOF porosity. Sonochemical synthesis was performed by varying the active pulsing time and pulsing amplitude. The influence of the selected factors was evaluated using a two-level full factorial design with duplicates runs. The resulting materials were characterized by Differential Scanning Calorimetry (DSC) and Dynamic Light Scattering (DLS).

Results

DLS analyses results show that all the frameworks possess the same behaviour and distribution: they're composed only by one size population with some differences in the particles size values. PDI is affected mostly by the GA concentration instead from the sonication amplitude. All samples' ζ-potential possess negative values. ζ-potential is affected and influenced in an important way from both the GA concentration and the interaction between this synthetic parameter, the VO_2^+ concentration and the sonication amplitude. DSC results show that T_m increases with higher GA concentration and greater sonication amplitude; while it decreases due to the interaction between vanadyl concentration, gallic acid concentration, and sonication amplitude. The melting enthalpy increases increasing GA concentration and the sonication amplitude decreases.

Conclusion

Component concentrations and factor interactions play a crucial role in determining the final properties of the MOFs. On the samples with best product properties were preliminary performed cytotoxicity analyses to assess the potential impact concentration of the MOFs and evaluate their suitable concentration for biomedical application. On those, an antioxidant activity in terms of EC50 were performed to evaluate the possibility of those product to reduce the oxidative species and enhance the therapeutic effect of the produced MOFs.

Table 1: Two factor Full Factorial Design for the Vanadium-based metal-organic framework synthesis

2^n FF runs[I]	**$VO2^+$ [mM]**	**GA [mM]**	**$t_{ActivePulse}$ [s]**	**Amplitude [%]**
1	12	5	1	20
2	12	5	1	90
3	12	5	59	20
4	12	5	59	90
5	12	20	1	20
6	12	20	1	90
7	12	20	59	20
8	12	20	59	90
9	20	5	1	20
10	20	5	1	90
11	20	5	59	20
12	20	5	59	90
13	20	20	1	20
14	20	20	1	90
15	20	20	59	20
16	20	20	59	90

[I]This is not the order of the performed runs; they were performed randomly ordered and in double.

D3 – P042
Polymer brush-based artificial organelles for gene delivery

Neri Cruz C.[1], Chang L.[1], Chit Ng S.[1], Zarbakhsh A.[2], Gautrot J.E.[1]
[1]School of Engineering and Materials Science, Queen Mary, University of London; [2]School of Physical and Chemical Sciences, Queen Mary, University of London, UK

Introduction
Despite significant progress and performance in the lab and clinic, RNA silencing remains mostly restricted to transient short term regulation of protein expression. Indeed, commercial gold standards such as Lipofectamine™ 3000 allow significant reduction in protein production for 1-3 days in the majority of targeted cells and proteins. However this is severely restricting the potential of siRNA for molecular biology studies and therapies. Upon internalization, RNA molecules are rapidly released by vectors, resulting in their transient impact on protein expression. Here, we report the engineering of artificial organelles that allow the controlled cytosolic release of RNA upon internalization and enable a long term impact on protein expression.




Figure 1. Competitive binding defines the cytoplasmic interactome associated with polycationic gene delivery vectors and regulates cytosolic RNA delivery.

Materials and Methods
We propose the use of polymer brush-based nanomaterials for the stable capture of RNA oligonucleotides and their protection and controlled cytosolic release. We investigate the growth of polymer brushes with precisely controlled nanostructures and characterized the resulting chemistry of interfaces and nanomaterials. Brush morphology, swelling and RNA complexation is investigated via a combination of ellipsometry, neutron reflectometry, surface plasmon resonance and fluorescence microscopy (1-5).

Results
The impact of competitive binding and interactions with macromolecules present extracellularly and within the cytosol is found to regulate the dissociation of RNA oligos from polymeric gene delivery systems (1). We use proteomics and confocal microscopy to characterize the interactome forming upon cytosolic entry and characterize the impact of polymer brush z-structuring on competitive binding. Finally, we investigate how such processes and their control through z-structuring enables the sustained release of oligonucleotides for siRNA-mediated knock down. We find high levels of knock down maintained over prolonged times, following a single transfection, with cell toxicities reduced to basal levels.

Conclusion
We demonstrate that the interactome associated with gene delivery nanomaterials may control not only their biodistribution and internalization, but also mediate disassembly and timely release of the genetic materials.

Acknowledgements
Funding from the ERC (ProLiCell, 772462) is gratefully acknowledged.

References
[1]Raynold et al. Nat. Commun. *12*; 2021; 6445.
[2]Qu et al. Biomacromolecules. *20(6)* 2019; 2218-2229.
[3]Gautrot et al. Advanced Materials Interfaces 2022; 9; (33).
[4]Neri-Cruz et al. J. Colloid Interface Sci. 2025; 684; 600-612.

D3 – P044

Highly-efficient protein encapsulation into thermoresponsive peptoid simple coacervate

Yasuda A.[1], Okuno Y.[2,3], Ryoki A.[4], Nishimura T.[5], and Iwasaki Y.[2,3]
[1]Kansai Univ., Grad. Sch. of Sci. Eng., Osaka; [2]Kansai Univ., Fac. Chem. Mater. Bioeng., Osaka; [3]Kansai Univ., ORDIST, Osaka; [4]Kyoto Univ., Grad. Sch. of Eng., Kyoto; [5]Shinshu Univ., Fac. of Textile Sci. & Tech., Nagano, Japan

Introduction

Encapsulating proteins into nanocompartment is fundamental technique to protect intrinsically unstable proteins with keeping their bioactivities; however, a low encapsulation efficiency remains the limitation. Previously, we found that the transition from coacervate-like structures to vesicles in thermoresponsive peptoids enhances protein encapsulation; thus, the thermoresponsive coacervate (simple coacervate) of peptoid was expected to be the key material to enclose proteins[1]. Although previous reports revealed that the random peptoid, poly(*N*-methylglycine-*r*-*N*-butylglycine), poly(NMG-*r*-NBG), exhibited thermoresponsiveness, a simple coacervate is generally unstable[2]. Herein we designed the gradient-sequenced poly(NMG-*grad*-NBG) to improve the colloidal stability, and investigated the encapsulation of various proteins into the resulting simple coacervate.

Materials and Methods

Poly(NMG-*grad*-NBG) was polymerized via one-shot ring-opening polymerization of NMG-*N*-carboxyanhydride (NMG-NCA) and NBG-NCA. UV-vis spectroscopy and variable-temperature nuclear magnetic resonance (VT-NMR) provided the thermoresponsiveness of the sample. The self-assembly was characterized by cryogenic transmittance electron microscopy (cryo-TEM), static light scattering (SLS), ultra-small-angle and small-angle X-ray scattering (USAXS, SAXS). The particle size of the self-assembly and its time-dependent change were measured by dynamic light scattering (DLS). Additionally, protein encapsulation efficiency in nanocompartment was evaluated by size-exclusion chromatography.

Results

Poly(NMG-*co*-NBG) was confirmed having gradient sequenced with a degree of polymerization of 200 and NMG content of 36%. The polymer exhibited LCST-type behavior in aqueous solution. Cryo-TEM, SAXS, USAXS and SLS analysis revealed the self-assembly was a uniform-density coacervate with a radius of 120 nm and a narrow size distribution. Furthermore, VT-NMR, DLS and VT-SAXS technique revealed that the coacervate was contracted upon hating and stabile above 30 ºC. The size was unchanged up to 24 h in time-coarse DLS, indicating high colloidal stability. Finally, the coacervate encapsulated model proteins with the efficiency up to 86%, depending on the glycan-contents in the proteins (**Figure**).




Figure (a) Schematic illustration of phase transition and protein encapsulation. **(b)** Protein encapsulation efficiency and glycan content of proteins.

Conclusion

Poly(NMG-*grad*-NBG) formed thermoresponsive simple coacervate with a thin membrane and encapsulated proteins with high efficiencies. The efficiencies consistent with glycan contents.

Acknowledgements

USAXS/SAXS were performed at BL19B2 of SPring-8 (2025A1966). This work was partly supported by JSPS KAKENHI (23H03750, 23K13803, 23KK0204), the Mukai Science and Technology Foundation, TOBE MAKI Foundation (25-JA-013), and Kansai University Research Branding Project (2024–2025).

References

[1]Okuno Y., Nishimura T., Iwasaki Y., Sasaki Y., Akiyoshi K., Substrate-selective nanofactories constructed from enzyme-loaded thermoresponsive peptoid-b-oligosaccharide vesicles. *Polymer Journal* 2025.
[2]Tao X., Du J., Wang Y., Ling J., Polypeptoids with tunable cloud point temperatures synthesized from N-substituted glycine N-thiocarboxyanhydrides. *Polym. Chem*. 2015; 6; 3164–3174.

D3 – P046

Nanoformulation of silver/DNA/Chitosan as potential combination therapy against cervical cancer

Pereira D.[1,2], Alves N.[2], Valente J.F.A.[2], Sousa A. [1,*]
[1]RISE-Health, Dept. of Medical Sciences, Faculty of Health Sciences, University of Beira Interior, Covilhã, Portugal; [2] CDRSP-PL-Centre for Rapid and Sustainable Product Development, Polytechnic of Leiria, Portugal

Introduction

Cervical cancer (CC) is the fourth leading cause of cancer-related death in women with human papillomavirus (HPV) being its primary origin. The most common types of HPV16/18 encode for E6/E7 oncoproteins, responsible for degrading/inactivating tumor suppressor proteins p53/pRB, resulting in the immortalization/transformation of infected cells. Gene therapy has shown great potential for disease treatment, involving gene transfer to correct/eliminate the function of proteins associated with disease development. Gene silencing can use microRNAs to degrade/inactivate transcripts of target proteins. Micro-RNA-375 (miR-375) demonstrated the ability to silence HPV E6/E7 oncoproteins, being considered a potential anticancer approach. Additionally, silver nanoparticles (Ag-NPs) known for their antiviral potential, and natural polymers like Chitosan (CH) with antimicrobial and mucoadhesive properties, can bring anticancer benefits.

Aim

Thus, the present study aimed the biosynthesis, isolation and purification of the innovative minicircle DNA (mcDNA) vector encoding pri-miR-375 gene to be incorporated into an Ag-NPs+CH nanosystem to be tested against CC-HPV-positive cell lines.

Materials and Methods

The Ag-NPs+DNA+CH nanoconjugates were formulated and adequately characterized by UV-visible spectra, zeta (ζ) potential and dynamic light scaterring (DLS). The anticancer effects of these materials were also evaluated *in vitro* in CC-HPV-positive cell lines as well as normal ones and compared with a control of Ag-NPs, Ag-NPs+CH; DNA+CH and a non-transfected control (NTC).

Results

The characterization results showed the nanoconjugates were successful obtained since UV–vis spectra measurements showed a shift of the silver peak when covered with DNA+CH and achieved yields of ~79% incorporated Ag-NPs and ~88% of incorporated DNA. A small size increase of Ag-NPs+DNA+CH was observed (from 131.8±4.6 nm to 198.9±3.8 nm, with the PDI kept between 0.233±0.013 and 0.216±0.019, respectively) after centrifugation, however it stayed bellow 200 nm allowing celular internalization. Zeta potential was also determined and demonstrated that after formulation and centrifugation shifted from negative to positive (-41.5±3.5 to 32.1±0.7) and since it's above 30 indicates the NPs are stable. Stability studies showed that after 6 h of transfection the NPs remain stable within the celular media. Furthermore, studies of NPs internalization, cell viability, migration as well as E6/E7 and p53/pRb transcript/protein levels evaluation are ongoing to assess the potential of this combined therapy against CC.

Conclusion

Overall, this work highlights the potential of the combination of Ag-NPs+CH with an mcDNA-pri-miR-375 vector towards gene therapy applications against CC-HPV-positive cell lines.

Acknowledgements

Fundação para a Ciência e Tecnologia: RISE-Health-UBI and CDRSP Funding (DOI: 10.54499/UIDB/00709/2020; DOI: 10.54499/UIDB/04044/2020) (DOI: 10.54499/UIDP/00709/2020; DOI: 10.54499/UIDP/04044/2020); Associate Laboratory ARISE LA/P/0112/2020; D. Pereira acknowledges FCT for her PhD fellowship (Ref. 2021.09331.BD) and Sousa Â. acknowledges FCT and the University of Beira Interior (DOI: 10.54499/CEECINST/00016/2021/CP2828/CT0003).

D3 – P047

pH-dependent molecular interactions on graphene oxide: From dye probes to doxorubicin delivery

Costinas C.[1,2], Cotet C.[2,3], Magyari K.[4], Szentes S.[2], Dénes K.S.[2], Kovács L.[2], Baia L.[1,2]
[1]Faculty of Physics, Babeș-Bolyai University; [2]Institute Institute for Research, Development and Innovation in Applied Natural Sciences, Babeș-Bolyai University; [3]Faculty of Chemistry and Engineering Chemistry, Babeș-Bolyai University; [4]Institute for Interdisciplinary Research in Bio-Nano-Sciences, Babeș-Bolyai University; [5]Faculty of Biology and Geology, Babeș-Bolyai University; [6]Faculty of Medical and Health Sciences, Babeș-Bolyai University, Cluj-Napoca, Romania

Introduction

Graphene Oxide (GO) is widely investigated as a nanomaterial for drug adsorption and delivery due to its high surface area and distribution of oxygen-containing functional groups. However, many studies report loading efficiencies without quantitatively addressing how the protonation state of these functional groups governs interactions with the molecular cargo. The relationship between surface acid-base chemistry and adsorption behavior is a first step for predicting loading and release under biological conditions. Here we investigate the surface chemistry of a highly oxidized, in-house produced GO and examine how its pH-dependent speciation influences interactions with dye probe molecules and an anticancer drug.

Materials and Methods

The acid-base properties of GO were characterized through potentiometric titration to determine the pKa values of the dominant surface functionalities and estimate their relative abundance across the pH range used in adsorption experiments. Material characterization was performed using UV-Vis, Raman, and FT-IR spectroscopy. To probe the adsorption mechanisms, two aromatic dyes were used as molecular probes: Methylene Blue (cationic) and Methyl Orange (anionic). Adsorption experiments were performed in buffered media at acidic and physiological pH, and were used to investigate the roles of electrostatic, hydrogen bonding and π-π stacking interactions in complex formation. Building on these mechanistic insights, loading and release experiments were conducted with Doxorubicin under physiological conditions.

Results

Potentiometric titration revealed multiple acidity domains consistent with the presence of carboxyl and phenolic surface groups, whose protonation states vary strongly between acidic and physiological pH. Dye adsorption experiments confirm this, indicating that electrostatic interactions significantly influence adsorption behavior while π-π interactions contribute to stabilization of the complexes. The dye probes provide a simplified framework for adsorption processes on GO. Based on this, doxorubicin loading was investigated in physiological buffer conditions. Release experiments demonstrated controlled, pH-dependent desorption behavior consistent with the surface speciation inferred from titration data. Preliminary biological evaluation of the GO-doxorubicin complex was performed using *Drosophila melanogaster* as an *in vivo* model to investigate toxicity and potential delivery effects.

Conclusion

The combination of potentiometric titration and probe-molecule adsorption experiments provided a mechanistic approach for linking the GO surface chemistry to a molecular loading and release behavior, indicating that pH-dependent surface speciation plays a central role in interactions with aromatic compounds and supports GO's potential as a tunable platform for drug delivery.

Acknowledgements

This work was supported by a grant of the Ministry of Research, Innovation and Digitization, CNCS - UEFISCDI, project number PN-IV-P1-PCE-2023-1377, within PNCDI IV.

D3 – P048

Nano-in-microparticles containing mucoadhesive nanoparticles for colon-targeted delivery of propionate

Carvalho S.G., De Souza M.R., Chorilli M.
Dept. of Drugs and Pharmaceutics, School of Pharmaceutical Sciences – São Paulo State University (UNESP), Araraquara, Brazil

Introduction

Inflammatory bowel diseases (IBD), including Crohn's disease and ulcerative colitis, are characterized by chronic inflammation of the gastrointestinal tract and are frequently associated with alterations in the intestinal microbiota. In this context, therapeutic strategies aimed at modulating the gut microbiome have gained increasing attention. Postbiotics, defined as bioactive compounds produced by the metabolic activity of microorganisms, have emerged as promising alternatives. Among them, short-chain fatty acids (SCFAs), such as propionate, exhibit important anti-inflammatory and immunomodulatory properties. However, their clinical application is limited due to low molecular weight, rapid absorption in the upper gastrointestinal tract, unfavorable pharmacokinetics, and poor palatability. Therefore, the development of delivery systems capable of protecting these compounds and promoting their targeted release in the colon represents a promising technological strategy.

Aim

This study aimed to develop and characterize a multifunctional nano-in-microparticles system for colon-targeted delivery of propionate.

Materials and Methods

Nanoparticles composed of propionate, hyaluronic acid, and chitosan were incorporated into polymeric microparticles to form a nano-in-microparticles platform. Microencapsulation was performed using retrograded starch and pectin matrices through the ionotropic gelation technique. The obtained systems were characterized in terms of particle size, span index, circularity, production yield, morphology, incorporation efficiency, swelling capacity, enzymatic degradation, in vitro release profile, and mucoadhesive properties.

Results

The developed nano-in-microparticles exhibited predominantly spherical morphology (circularity ≥ 0.900) and homogeneous particle size distribution, with span values ranging from 0.08 to 0.33. The microparticles showed mean diameters of approximately 900 µm and satisfactory production yields. Swelling capacity and enzymatic degradation were more pronounced under basic pH conditions, simulating the intestinal environment. Additionally, the system was able to modulate propionate release, particularly under acidic pH conditions, indicating protection of the compound during gastric transit.

Conclusion

The developed nano-in-microparticles platform represents a promising strategy for colon-specific delivery of propionate and may contribute to the development of novel therapeutic approaches for the treatment of inflammatory bowel diseases.

Acknowledgements

The authors acknowledge the financial support provided by the São Paulo Research Foundation (FAPESP) (Grant Nos. 2022/14075-1 and 2025/12801-5) and the National Institute of Science and Technology (INCT).

D3 – P049

From biological activity to delivery: Encapsulation of *p*-coumaric acid into PLGA nanoparticles for enhanced therapeutic potential

Bārzdiņa A.[1,2], Teterovska R.[1,2], Brangule A.[2,3], Bandere D.[1,2]
[1]Dept. of Applied Pharmacy, Riga Stradins University; [2]Baltic Biomaterials Centre of Excellence, Riga Technical University; [3]Dept. of Pharmacology and Pharmacotherapy, Riga Stradins University, Latvia

Introduction

p-Coumaric acid (CO) is a natural phenolic acid belonging to the hydroxycinnamic acid class. Due to favourable physicochemical properties and toxicological profile, CO has become a promising candidate for various pharmaceutical applications. To date, the antibacterial and antibiofilm effects of CO acid have been underexplored. In case of chronic infections like osteomyelitis or chronic wounds, the treatment would need to be prolonged. Therefore, encapsulation into biodegradable, sustained-release drug delivery systems (DDS), like PLGA nanoparticles, is necessary.

Aim

The aim of this study was to investigate the antibacterial and antibiofilm properties of CO against a panel of causative agents of chronic infections, encapsulate CO into PLGA nanoparticles, and evaluate the therapeutic applicability of the developed DDS.

Materials and Methods

The minimum inhibitory concentration (MIC) and minimum bactericidal concentration (MBC) were determined against strains of *S. aureus*, *S. epidermidis*, *B. subtilis*, *E. coli*, *P. aeruginosa*, *K. quasipneumoniae*, *K. pneumoniae*, and *P. mirabilis*. Biofilm prevention concentration (BPC) and biomass reduction percentage were determined. CO-loaded PLGA (Resomer RG 502 H, lactide:glycolide 50:50) nanoparticles were synthesized using the single emulsion method. Freeze-dried particles were characterized in terms of mean diameter, polydispersity index (PDI), zeta potential, encapsulation efficiency (EE%), drug loading, morphology (scanning electron microscopy (SEM)), drug release, FTIR spectra, and antibacterial activity.

Results

The MIC of CO ranged from 0.625 to 2.5 mg/mL, while the MBC/MIC ratio was from 1 to 4, indicating a bactericidal mechanism of action. Gram-positive strains were more susceptible to CO. BPC ranged from 0.625 to 5 mg/mL. CO was able to reduce the biofilm biomass from 40% (*E. coli*) to even 78% (*S. aureus*). Empty PLGA nanoparticles had a mean diameter of 190.7±0.6 nm, PDI of 0.07±0.05, and zeta potential of -15.7±3.3 mV. CO-loaded nanoparticles had a slightly larger size (200.9±3.9 nm) and PDI (0.11±0.01). Zeta potential was -9.3±0.6 mV. EE% was 55.6±5.0 %. The particles were monodispersed and of round shape. A sustained-release profile was detected. FTIR spectra confirmed the loading of CO.

Conclusion

CO-loaded PLGA nanoparticles were successfully synthesized. The antibacterial efficacy and nanoparticle properties show promise for therapeutic applications against chronic infections.

Acknowledgements

The research was executed under the project “Smart injectable nanoparticle-loaded hydrogel for synergic and targeted treatment of osteomyelitis (SinGel)”, project No lzp-2025/1-0108. The authors acknowledge the access to the infrastructure and expertise of the BBCE – Baltic Biomaterials Centre of Excellence (European Union’s Horizon 2020 research and innovation program under grant agreement No 857287).

D3 – P050

Multifunctional polymer nanoparticles for targeted liposarcoma therapy

Bae Y.R., Park J.Y., Lee K.Y.
Dept. of Bioengineering, Hanyang University, Seoul, Republic of Korea

Introduction

Liposarcoma is a malignant tumor arising from adipose tissue, with well-differentiated liposarcoma (WDLPS) being the most prevalent subtype. WDLPS exhibits limited responsiveness to conventional radiotherapy and chemotherapy, highlighting the need for more effective therapeutic strategies. In this study, we hypothesized that surface modification of poly(D,L-lactide-co-glycolide) (PLGA) nanoparticles with an adipocyte-targeting sequence (ATS) would enhance uptake in WDLPS cells, and that intracellular carbon dioxide (CO_2) gas generation from encapsulated calcium carbonate in the nanoparticles could induce membrane disruption. To test this, we evaluated cellular uptake and cytotoxic effects of CO_2-generating polymer nanoparticles functionalized with ATS peptides in vitro.

Materials and Methods

PLGA nanoparticles encapsulating calcium carbonate were prepared using the double emulsion method and subsequently conjugated with ATS peptide via carbodiimide chemistry. Physicochemical properties, including mean size and zeta potential, were determined using a zeta sizer. Successful peptide conjugation was confirmed by FT-IR and ^{1}H NMR spectroscopy. To evaluate therapeutic efficacy, the 93T449 cell line was utilized as a model for WDLPS. Prohibitin expression on the 93T449 cell surface was confirmed via immunofluorescence staining. Cellular uptake was observed by confocal microscopy. Cytotoxicity and the necrotic cell death mechanism were evaluated via 3-(4,5-dimethylthiazol-2-yl)-5-(3-carboxymethoxyphenyl)-2-(4-sulfophenyl)-2H-tetrazolium (MTS) and lactate dehydrogenase (LDH) assays, respectively.

Results

ATS-modified CO_2-generating nanoparticles were successfully prepared, with the formation of amide bonds between ATS peptide and nanoparticles confirmed by FT-IR and ^{1}H NMR spectroscopy. Surface modification with ATS peptide had minimal impact on the characteristics of the nanoparticles. However, a significant change in size distribution at acidic pH indicated effective CO_2 generation from the nanoparticles. ATS peptide modification significantly enhanced nanoparticle uptake by 93T449 cells, leading to increased intracellular CO_2 generation and a subsequent reduction in cell viability.

Conclusion

We developed multifunctional polymer nanoparticles for the targeted treatment of WDLPS. Modification with the ATS peptide improved the selective uptake of PLGA nanoparticles by WDLPS cells via prohibitin targeting. The subsequent intracellular release of CO_2 gas from the nanoparticles effectively induced necrotic cell death by disrupting the cellular membrane. These findings highlight the potential of ATS-modified gas-generating nanoparticles as a novel and effective therapeutic strategy for WDLPS that are resistant to conventional radiotherapy and chemotherapy.

Acknowledgements

This study was supported by the National Research Foundation of Korea (NRF) grant funded by the Korean Government (MSIT) [RS-2020-NR048193].

References

[1]Han Y.K., Jeong E.J., Seo Y., Lee I.Y., Choi S., Lee H., Kim C., Rhim T., Lee K.Y. Adipocytolytic Polymer Nanoparticles for Localized Fat Reduction. *ACS Nano* 2023; 17; 70-83.
[2]Choi S., Lee I. Y., Kim M.J., Lee S.K., Lee K.Y. Multi-Functional Polymer Nanoparticles with Enhanced Adipocyte Uptake and Adipocytolytic Efficacy. *Macromolecular Bioscience* 2023; 2300312.

D3 – P051

Precision therapeutic strategies for the treatment of colorectal and hepatocellular cancer

Borzacchiello A.[1], Barretta M.[1], Della Sala F.[1], Marino G.[1,2], di Gennaro M.[1], Longobardo G.[1], Ostuni A.[3], Amiranda S.[4], Pecchillo Cimmino T.[4], Gagliarde S.[4], Cerasuolo A.[4], Tornesello M.L.[4], Porto A.[4], Simonetti I.[4], Fusco R.[4], Granata V.[4]

[1]Institute of Polymers, Composites and Biomaterials, National Research Council (IPCB-CNR); [2]Dept. of Environmental, Biological and Pharmaceutical Sciences and Technologies (DiSTABiF), University of Campania "L. Vanvitelli", Caserta; [3]University of Basilicata, Dept. of Basic and Applied Sciences, Potenza; [4]Istituto Nazionale Tumori IRCCS Fondazione Pascale (IRCCS) Naples, Italy

Introduction

Targeted therapies are increasingly explored to address the poor specificity and significant side effects of conventional chemotherapy, especially in aggressive cancers like hepatocellular carcinoma (HCC) and colorectal cancer (CRC)[1]. The enzyme CD73 plays a central role in tumor progression, promoting drug resistance, angiogenesis, and metastasis, and is regulated by the ABCC6 transporter. Inhibiting ABCC6 reduces CD73 expression, thereby limiting cell migration, decreasing drug resistance, and enhancing anti-tumor immune responses[2]. Probenecid (PRO) acts as a pharmacological inhibitor of ABCC6, reproducing the effects of gene silencing and reducing cell motility. However, the application of PRO is heavily limited by its high hydrophobicity and its low stability in water[3]. Thus, advanced delivery systems such as polymeric nanoparticles are strictly required.

Aim

This study aims to develop poly(lactic-co-glycolic acid) (PLGA) nanoparticles (NPs) for the targeted delivery and controlled release of PRO in order to enhance its therapeutic efficacy against HCC and CRC cells.

Materials and Methods

NPs/PRO were fabricated by nanoprecipitation with solvent evaporation technique. Organic phase of PLGA/F68/F127 and PRO (5%) in acetone solution was forced through a Syringe-Pump. The solution was precipitated into an aqueous phase with poloxamer F127/F68 as surface-active agents. NPs morphology was investigated by TEM, while size and z-potential were evaluate by DLS, along with their colloidal stability over time. Drug encapsulation efficiency (DEE) and in vitro release profiles were quantified by HPLC. The *in vitro* biocompatibility (alarm blue assay) and the expression of *ABCC6 and CD73 genes (PCR*) was evaluated on HepG2 and Caco2 cell lines treated with both PRO and NPs/PRO for 48, 96, and 120 hours.

Results

DLS measurements showed well-defined peaks for both NPs and NPs/PRO with a size of 145.8 ± 0.8 nm and a zeta potential ranged from −35 ±1 mV to −39 ±0.2 mV. Overall, only slight variations in hydrodynamic diameter were observed under different storage conditions, indicating good stability over 10 days. PRO was encapsulated (DDE 70%) in PLGA NPs and released over 15 days. Viability assays showed the inherent biocompatibility of the NPs as a carrier. Treatment with NPs/PRO was more effective than PRO alone, causing a statistically significant reduction in ABCC6 expression levels in both HepG2 and Caco2 cell lines at 48, 96, and 120 hours of treatment, and in CD73 expression levels at 120 hours in the Caco2 cell line (Fig.1).




Fig.1 Analysis of the expression profile of ABCC6 and CD73 genes in Caco2 (A) and HepG2 (B) cell lines treated for 120 hours with probenecid (PRO) and probenecid-nanoparticles (NPs). The increase in CD73 expression levels in HepG2 cells is due to a change in the expression of the housekeeping gene ACTB.

Conclusion

Overall, NP/PRO were shown to modulate gene expression and signaling pathways associated with the ABCC6/CD73 system involved in HCC and CRC tumors.

Acknowledgements

The authors acknowledge the project “Precision therapeutic strategies for the treatment of colorectal and hepatocellular cancer” - PRESTO - CUP B63C23000090001. Funded by the European Union - Next Generation EU - PNRR M6C2 - Investment 2.1 Enhancement and strengthening of biomedical research in the National Health Service.

References

[1]Zafar A. et al. *Discover Oncology*; 2025; 16; 607.
[2]Ostuni A. et al. *Cells*; 2020; 9(6); 1410.
[3]Jeong Y. et al. *Pharmaceutics*; 2025; 17(11); 1454.

D3 – P052

DNA Origami artificial nano-cages: The next step in localized cell delivery

Gomes-Ribeiro B.F.[1], Swiderski B.[1], Naskalska A.[1], Robles M.[1], Stepien P.[2], Heddle J.[2]
[1]Malopolska Centre of Biotechnology, Jagiellonian University, Cracow, Poland; [2]Centre for Programmable Biological Matter, Durham University, UK

Introduction

DNA Origami is a powerful technology that allows the engineering of 3D nanostructures with near-atomic precision. While other nanostructures made of synthetic materials often lack controllability, this technology, which explores the self-assembly properties of the DNA molecule, allows bottom-up fabrication of well-defined DNA-based nanostructures.[1,2] One type of such structures are artificial nano-cages, which have been studied as carriers for localized transport of macromolecules to cells, including drugs, genetic materials or enzymes.[3] The advantage of producing these cages through the use of DNA is the ability to specific design and tailor the structure, providing it with desired properties for planned interactions, that may not be feasible on other nanostructures, and may help in controlling their biological response.[1,2]

Aim

To design, produce and functionalize DNA-Origami nanocages and study their interactions with several in-vitro models such as Human Umbilical Vein Endothelial Cells (HUVEC).

Materials and Methods

DNA-Origami based nano-cages (see Figure1) were produced from specifically designed single stranded DNA plasmids (Scaffold) and short DNA oligomers (Staples), and were assembled by a designed folding protocol (thermal annealing) in a thermocycler. A modular approach was used to conjugate the produced nanocages with an invasin protein, Fibronectin Binding Protein B (FbaB) from *Staphylococcus pyogenes*. Namely: an oligo complementary to nanocage scaffold was chemically conjugated to a maleimide moiety (maleimide-modified staples), which further interacts with cysteine present in the FbaB protein (Figure1). The obtained structures were characterized by gel electrophoresis, dynamic light scattering and transmission electron microscopy. Their biological interactions were tested against NIH 3T3 Fibroblasts and HUVEC cells.

Figure 1

Conclusion

This work demonstrated the possibility of designing and successfully assemble DNA nano-cages which can be attached with a protein cargo (Figure1) and successfully interact with cellular systems.

Acknowledgements

The research was supported by National Science Centre in Poland under the OPUS 22 (LAP) grant (2021/43/I/NZ1/02125).

References

[1]Knappe G.A., Wamhoff E.-C., Bathe M., Functionalizing DNA origami to investigate and interact with biological systems. *Nat Rev Mater* 2023; 8; 123-138.
[2]Hong F., Zhang, DNA Origami: Scaffolds for Creating Higher Order Structures. *Chem. Rev*. 2017; 117; 12584-12640.
[3]Lu F., Bai S., Shi Y., Dazhuang X., Chu C., Liu G., Artificial nanocage-based 3D framework platforms: From construction design to biomedical applications. *Chemical Engineering Journal* 2021; 426; 131891.

D3 – P053

Review of machine learning-driven optimization for ultrasound-triggered targeted liposomal drug delivery

Hannan H.[1], Alshraideh H.[2], Husseini G.[3]
[1]Dept. of Biosciences and Bioengineering, American University of Sharjah; [2]Dept. of Industrial Engineering, American University of Sharjah; [3]Dept. of Chemical Engineering, American University of Sharjah, U.A.E.

Introduction

Liposomes serve as established nanocarriers, yet their clinical success is often limited by challenges such as inconsistent targeting and suboptimal release kinetics. Ultrasound-triggered systems offer a promising non-invasive strategy for controlled drug release, but optimizing the complex interactions between acoustic parameters and liposomal formulations remains a significant hurdle. The integration of Artificial Intelligence (AI) and Machine Learning (ML) provides a robust platform for analyzing multidimensional datasets, recognizing patterns, and predicting release behaviors [1].

Aim

This review synthesizes current knowledge on AI-driven optimization to enhance the precision of ultrasound-responsive liposomal drug delivery systems.

Materials and Methods

An integrative review approach was utilized to comprehensively analyze literature at the intersection of liposomal delivery, ultrasound mechanisms, and AI methodologies. A structured literature search was conducted across databases, including PubMed, Scopus, Google Scholar, and IEEE Xplore, using Boolean operators and keywords such as "liposome," "ultrasound-triggered release," and "machine learning". Articles were screened based on their focus on optimizing formulations, predicting release kinetics, or enhancing delivery using computational techniques. Data extraction focused on AI methodologies, including supervised learning and predictive modeling, which were organized into thematic categories to evaluate methodologies and findings.

Results

The review finds that AI models, particularly Artificial Neural Networks (ANNs) and Random Forests (RFs), achieve high precision in predicting physicochemical properties such as particle size and encapsulation efficiency [1,2]. Ensemble learning techniques have demonstrated predictive accuracy up to 99.993% for drug release under varied ultrasound power densities [3]. Additionally, model predictive controllers (MPC) integrated with ANNs allow for real-time adaptive control of drug release rates by dynamically adjusting acoustic parameters [4]. However, hurdles remain, including data scarcity, the lack of standardized high-quality datasets, and limited interpretability of complex "black box" deep learning models.

Conclusion

The collaboration between AI and ultrasound-triggered liposomal systems represents a transformative advancement for precision medicine. While computational tools significantly accelerate formulation development and optimize acoustic parameters, addressing data scarcity and improving model transparency are critical for successful clinical translation. Future research should focus on establishing collaborative, standardized databases and validating AI models in complex in vivo environments to ensure reliable therapeutic outcomes.

References

[1]Das K.P., Nanoparticles and convergence of artificial intelligence for targeted drug delivery for cancer therapy: Current progress and challenges. *Frontiers in Medical Technology* 2023; vol. 4; 1067144.
[2]Izadiyan Z. et al. Advancements in Liposomal Nanomedicines: Innovative Formulations, Therapeutic Applications, and Future Directions in Precision Medicine. *International Journal of Nanomedicine* 2025; 1213–1262.
[3]Moussa H.G. et al. Use of model predictive control and artificial neural networks to optimize the ultrasonic release of a model drug from liposomes. *IEEE Transactions on* NanoBioscience 2027; vol. 16; (3); 149–156.
[4]Cardoso-Daodu I.M. et al. Artificial neural network for optimizing the formulation of curcumin-loaded liposomes from statistically designed experiments. *Progress in Biomaterials*; vol. 11; (1).

D3 – P054

Plasma-polymerized nanoparticle–hydrogel composites for targeted cancer drug delivery: A green, crosslinker-free fabrication strategy

Raghavendra Rao G., Akhavan B., Borzouyan Dastjerdi M., Masood A.
School of Engineering, University of Newcastle, Callaghan, Australia

Introduction

Conventional cancer therapies suffer from systemic toxicity, poor tumour selectivity, and multidrug resistance, contributing to over 90% of chemotherapy-related deaths.[1] Nanoparticle–hydrogel composites offer a promising solution, yet conventional fabrication involves toxic crosslinkers, multistep purification, and scalability barriers.[2] Plasma-polymerized nanoparticles (PPNs) synthesised solvent-free in a single step retain long-lived surface radicals enabling direct covalent bonding with hydrogel matrices without chemical crosslinkers.[3] This study is the first to integrate PPNs with gelatin methacryloyl (GelMA) hydrogel for targeted, controlled cancer drug delivery.

Materials and Methods

PPNs were synthesised in a custom-built inductively coupled plasma (4th state of matter) reactor using argon, nitrogen, and acetylene gas monomers at fixed pressure and Radio Frequency (RF) power. Plasma parameters were systematically varied to tune PPN size and surface chemistry. Another novel custom-built double-layer modular reactor was used to produce PPN and improve yield and reduce cross-batch contamination. PPNs were characterised by dynamic light scattering, electron microscopy (SEM/TEM), X-ray photoelectron spectroscopy (XPS), FTIR, UV–Vis spectroscopy, and water contact angle. GelMA hydrogel was synthesised via methacrylation, dialysis, and UV photo-crosslinking. PPNs were integrated into GelMA by linker-free incubation. Nanocomposite hydrogels were evaluated mechanically (tensile), structurally (SEM), and in the future biologically (MTT, apoptosis, ROS assays) against MCF-7 and MDA-MB-231 breast cancer cell lines.

Results


Higher monomer gas flow rates produced smaller PPNs consistent with nucleation-dominated kinetics.[4] XPS confirmed a predominantly carbonaceous surface (~80% C, ~10% N, ~5–10% O), with nitrogenated sites showing potential to serve as intrinsic drug conjugation anchors. A water contact angle of 145° validated the hydrocarbon-rich, superhydrophobic character of the PPN surface. UV–Vis Beer–Lambert linearity across serial dilutions enabled reproducible yield quantification. Collection geometry optimisation identified an optimal intermediate height within the reactor for maximum PPN collection. PPN–GelMA integration produced stable, homogeneous colloidal dispersions confirmed by SEM. The double-layer reactor reduced cross-batch contamination and improved batch-to-batch reproducibility.

Conclusion

This work establishes a solvent-free, scalable plasma-polymerization platform for fabricating PPN–GelMA nanocomposite hydrogels without chemical crosslinkers. The radical-rich PPN surface enables direct covalent integration with both GelMA and drugs, yielding composites with tunable mechanical properties and controlled drug release. By eliminating toxic reagents and simplifying fabrication, this platform overcomes key translational barriers, positioning PPN–hydrogel composites as a transformative strategy for a novel cancer drug delivery system.

References

[1]Bukowski K., Kciuk M., Kontek R. Mechanisms of multidrug resistance in cancer chemotherapy. *Int J Mol Sci* 2020; 21(9); 3233.
[2]Choi W., Kohane D.S. Hybrid nanoparticle–hydrogel systems for drug delivery depots and other biomedical applications. *ACS Nano* 2024; 18(34); 22780–22792.
[3]Haidar L.L., Baldry M., Fraser S.T., Boumelhem B.B., Gilmour A.D., Liu Z., Zheng Z., Bilek M.M.M., Akhavan B. Surface-active plasma-polymerized nanoparticles for multifunctional diagnostic, targeting, and therapeutic probes. *ACS Appl Nano Mater* 2022; 5(12); 17576–17591.
[4]Austria E.S., Akhavan B. Polymeric nanoparticle synthesis for biomedical applications: advancing from wet chemistry methods to dry plasma technologies. *Nanoscale* 2025; 17(21); 13020–13056.



Created using Biorender




Figure: Haidar, L. L. *et al.*, Small, 2024.

D3 – P055

Screening sono-activated nanoparticles anti-tumor performance in glioblastoma 3D models

Potthuri H.[1,2], Sosnik A.[1], Mano J.F.[2], Gaspar V.M.[2]*
[1]Laboratory of Pharmaceutical Nanomaterials Science, Faculty of Materials Science and Engineering, Technion-Israel Institute of Technology, Haifa, Israel; [2]CICECO-Aveiro Institute of Materials, Dept. of Chemistry, University of Aveiro, Portugal

Introduction

Glioblastoma multiforme (GBM) is one of the most aggressive and lethal primary brain malignancies, accounting for 14.5% of all central nervous system (CNS) tumors and 48.6% of malignant CNS tumors. Despite advances in treatment, including surgical resection, radiotherapy, and immunotherapy, prognosis remains poor, with a median survival of only 12–15 months. A major obstacle to effective GBM therapy is the blood–brain barrier (BBB), a specialized feature of the CNS microvasculature that severely restricts drug delivery to the brain.

Cancer cells often overexpress surface receptors that can be exploited for targeted drug delivery. One such receptor, low-density lipoprotein receptor-related protein-1 (LRP-1), is highly expressed in both the BBB and GBM while remaining at low levels in healthy brain tissue. Angiopep-2 (ANG-2), a 19-amino-acid peptide, can bind specifically to LRP-1 and facilitates transport across the BBB. This strategy has been validated by ANG1005, an ANG-2-based therapeutic that successfully delivers paclitaxel to brain tumors at therapeutically relevant concentrations.

However, drug efficacy in GBM remains limited by poor tumor accumulation and off target biodistribution, leading to systemic toxicity. Sonodynamic therapy (SDT) offers a promising alternative by using sonosensitizers activated by low-intensity ultrasound to generate reactive oxygen species that induce tumor cell death. Titanium dioxide (TiO_2) is a widely studied sonosensitizer, and our laboratory has developed hybrid amorphous TiO_2/PEO-PPO nanoparticles (NPs) with tunable sizes of 30–350 nm. To ensure stability and functionality in the bloodstream, these nanoparticles require suitable nanocarriers. Amphiphilic PEO-PPO-PEO block copolymers are particularly attractive due to their ability to self-assemble into polymeric micelles and be functionalized with targeting ligands, enabling enhanced tumor targeting and therapy.


Aim


This study aims to develop tumor-selective ceramic/polymeric hybrid NPs functionalized with a targeting peptide for efficient BBB penetration. Upon external ultrasound stimulation, the system is designed to selectively induce glioblastoma cell lysis, with therapeutic efficacy evaluated in both 2D and 3D GBM models.

Materials

Tetronic® 1107 (T1107, MW of 15 kg/mol, PEO weight content of 70%) were generously donated by BASF (Vandalia, IL, USA), TTIP (95% purity, Sigma-Aldrich, St. Louis, MO, USA), ANG-2 peptide (DG peptides Co., Ltd., Wuhan City, People's Republic of China).

Results





Conclusion.

ATR-FTIR and ^{1}H-NMR confirm successful polymer functionalization, with ~75% ANG-2 binding. DSC and TGA indicate thermal property changes, supporting amorphous nanoparticle formation. DLS, HR-SEM, and HR-TEM reveal uniform, spherical, negatively charged particles and surface modification, further supported by electrophoresis. In vitro assays show good biocompatibility and ultrasound-enhanced, ANG-2-mediated cytotoxicity in 2D and 3D glioblastoma models.

Acknowledgements
We gratefully acknowledge the Theratools (Ref. 101073404) for financial support of this research. We also extend our thanks to Material Science and Engineering-Technion, Israel for providing resources and facilities essential to this work. This work was developed within the scope of the project CICECO – Aveiro Institute of Materials, UID/50011/2025 & LA/P/0006/2020 (DOI 10.54499/LA/P/0006/2020), financed by national funds through the FCT/MCTES (PIDDAC).

D3 – P056

Deep eutectic nanogels (DENs) as a versatile platform for hydrophobic drug encapsulation

Khobotov-Bakishev A.[1], Martinez-Cartagena M.E.[1], Picchio M.L.[1,2], Beloqui A.[1,2]
[1]POLYMAT, Applied Chemistry Dept., Faculty of Chemistry, University of the Basque Country UPV/EHU, Donostia-San Sebastián; [2]IKERBASQUE, Basque Foundation for Science, Bilbao, Spain

Introduction

The clinical efficacy of many promising bioactive compounds is limited by poor aqueous solubility, severely restricting bioavailability and cellular uptake. Conventional solubilization strategies — including organic cosolvents, surfactants, and lipid-based carriers — are associated with systemic toxicity, colloidal instability, and limited control over drug release. Deep eutectic solvents (DES) have recently emerged as biocompatible, highly tunable media with a broad range of applications, owing to their unique physicochemical properties arising from strong intermolecular hydrogen bonding interactions. Beyond small molecules, certain DES formulations have demonstrated remarkable capacity to stabilize sensitive biomacromolecules, including proteins and DNA, suggesting their potential as protective environments for biological cargoes. Here we introduce Deep Eutectic Nanogels (DENs), a novel platform in which DES are encapsulated within crosslinked polymer networks, combining the versatility of DES with the structural tunability of nanogel architectures.

Materials and Methods

DENs were synthesized via microemulsion polymerization, in which a hydrogen bond donor–acceptor DES pair serves as part of the oleic phase of the emulsion, becoming encapsulated within the resulting crosslinked polymer network. To identify optimal formulations, a library of DES was screened, and menthol-based systems were selected for in-depth characterization due to the superior stability of the resulting nanoparticles. The composition of the microemulsion — including oil-to-water ratio, surfactant concentration, and DES content — was systematically varied to optimize nanogel formation and control particle size. The resulting DENs were characterized by DLS and cryo-TEM for size and morphological analysis, and by FTIR, NMR spectroscopy, and UV-vis spectroscopy to assess chemical composition and cargo incorporation. Encapsulation was evaluated across a range of hydrophobic compounds, with particular focus on the fluorescent probe Nile red and the anticancer drug paclitaxel.

Results

DENs with controlled sizes ranging from 30 to 120 nm and narrow size distributions were successfully obtained across the menthol-based DES formulations screened, as determined by DLS, with cryo-TEM confirming both size and spherical morphology. FTIR analysis provided evidence of DES incorporation within the polymer network, supported by NMR spectroscopy. Among the formulations evaluated, menthol:eucalyptol DENs exhibited particularly high encapsulation capacity, as demonstrated by the successful encapsulation of the hydrophobic fluorescent probe Nile red (Figure 1).




Figure 1. Encapsulation of Nile red within menthol:eucalyptol DENs. (a) Visual appearance before and (b) after microemulsion polymerization, showing solubilization of Nile red into a homogeneous pink suspension. (c) Cryo-TEM image of the resulting DENs from the same sample (scale bar: 200 nm).

Conclusion

DENs represent a novel and versatile platform for the encapsulation of hydrophobic compounds, combining the solubilization capacity of DES with the tunability of nanogel architectures. Future work will focus on engineering stimuli-responsive and functionalized shells to improve biocompatibility and enable targeted delivery. Ultimately,

this platform holds significant potential for extension towards the encapsulation of proteins and nucleic acids, paving the way for advanced therapeutic applications.

Acknowledgements
A.B. thanks the University of the Basque Country (GIU21/033); the Spanish Research Agency (PID2022-142128NB-I00 and CNS2023-145416 funded by MCIN/AEI/10.13039/501100011033/; and the “European Union NextGenerationEU/PRTR”; “María de Maeztu” Programme for Center of Excellence in R&D, grant CEX2023-001303-M funded by MICIU/AEI/10.13039/501100011033), and IKERBASQUE-Basque Foundation for Science. A.B. and M.L.P. thank the Ramón Areces Foundation for the financial support received through the “XXII Concurso Nacional para la adjudicación de Ayudas a la Investi-gación en Ciencias de la Vida y de la Materia” (CIVP22S18625).

D3 – P057

Review of machine learning-driven optimization for ultrasound-triggered targeted liposomal drug delivery

Yusuf B.[1], Dalibalta S.[2]
[1]Dept. of Biosciences and Bioengineering, American University of Sharjah, U.A.E; [2]Dept. of Biology, Chemistry and Environmental Sciences, American University of Sharjah, U.A.E

Introduction

Atherosclerosis, the pathophysiological basis of myocardial infarction, ischemic stroke, and peripheral arterial disease, continues to be a leading global health problem. Despite the effective systemic therapies including statins and antiplatelet drugs, current clinical treatment have been unable to directly modulate this highly complex and heterogeneous environment within atheroma plaques [1]. Recent progress in nanomedicine has opened new opportunities to overcome these limitations by engineering smart nanocarriers that bear site-directed responsive multi-functions. Such smart strategies can be specifically designed to respond dynamically to pathologic features such as oxidative stress, inflammation, acidic environment and lipid deposition, thereby providing enhanced targeting ability, bioavailability, and therapy efficacy [2].

Materials and Methods

This review provides a comprehensive overview of the advances in the development of smart engineered nanoparticles for treating atherosclerosis, including advancements in three main areas: targeted delivery strategy, multi-functionalized formulations, and translational progress. Targeting has developed from single-ligand to more complicated dual-targeting. For example, the LOX-1 receptor is an underexploited, but very attractive, target that is overexpressed on activated endothelial cells, macrophages and smooth muscle cells. Dual-functional nanoparticles bound to both LOX-1 and scavenger receptor (CD36 and/or VCAM-1) are more plaque-selective and taken up into cells more efficiently [3]. Additionally, stimuli-responsive carriers, such as ROS or pH responsive systems, can avoid the adverse effect by promoting drug release in an on demand approach by responding to certain local micro-environmental triggers.

Results

Multifunctional systems are also under development for both therapeutic and diagnostic applications in a single construct. The theranostic nanocarriers, such as IR780 micelles and quantum-dot-based platforms, give real-time information about the response during the treatment administration and deliver the anti-inflammatory, lipid-lowering, and antioxidant and agents. However, although promising data from ApoE^–/– mice, there is limited clinical translation [4]. Limitations include scale-up, immunogenicity, pharmacokinetics, and absence of more human relevant disease models. HDLMNPs such as CER-001, CSL112, liposomal statins, and SPION- based imaging agents are in Phase I–III trials, indicating the potential to translate these to clinical application [5].

Conclusion

In conclusion, the merger of 4D nanotechnology, systems biology, and AI guided strategy will reshape the field of cardiovascular nanomedicine. Smart nanoparticles will be used to predict, prevent, treat, and monitor atherosclerosis. They have the potential to transform the management of atherosclerosis from risk reduction to individualized therapy. Sustained cross-discipline collaboration will be critical in the translation of these advances into the clinic.

References

[1]Medrano-Bosch M., Simón-Codina B., Jiménez W., Edelman E.R., Melgar-Lesmes P. Monocyte-endothelial cell interactions in vascular and tissue remodeling. *Frontiers Media SA* 2023; doi: 10.3389/fimmu;1196033.
[2]Madaudo C., Coppola G., Parlati A.L.M., Corrado E. Discovering Inflammation in Atherosclerosis: Insights from Pathogenic Pathways to Clinical Practice. *Multidisciplinary Digital Publishing Institute (MDPI)* 2024; doi: 10.3390/ijms25116016.
[3]Hofmann A., Brunssen B., Morawietz H., Contribution of lectin-like oxidized low-density lipoprotein receptor-1 and LOX-1 modulating compounds to vascular diseases. Aug. 01, 2018. *Elsevier Inc*; doi: 10.1016/j.vph.2017.10.002.
[4]Huang J., Wang D., Huang L.H., Huang H. Roles of reconstituted high-density lipoprotein nanoparticles in cardiovascular disease: A new paradigm for drug discovery, Feb. 01, 2020. *MDPI AG*. doi: 10.3390/ijms21030739.
[5]Capodanno D., Mehran R., Gibson C.M., Angiolillo D.J. CSL112, a reconstituted, infusible, plasma-derived apolipoprotein A-I: safety and tolerability profiles and implications for management in patients with myocardial infarction, Dec. 02, 2018. *Taylor and Francis Ltd*. doi: 10.1080/13543784.2018.1543399.

D3 – P058

CRISPR-Cas9 applications in collagen biology: Advances in bone and tendon research, delivery strategies and therapeutic potential

Alhabash B.[1,2], Alnimri M. [1,2], Khader B.[2]
[1]Dept. of Biosciences and Bioengineering, American University of Sharjah; [2] Dept. of Chemical and Biological Engineering, American University of Sharjah, UAE

Introduction

Collagen-related musculoskeletal disorders, including osteogenesis imperfecta, Ehlers–Danlos syndrome, and collagen VI-related muscular dystrophies, arise from mutations affecting collagen synthesis, assembly, or extracellular matrix organization. CRISPR-Cas9 genome editing offers a promising strategy for correcting these pathogenic variants; however, its clinical translation is limited by the challenge of delivering CRISPR components efficiently and safely to dense connective tissues such as bone and tendon.

Aim

This review evaluates recent advances in CRISPR-Cas9 applications in collagen biology and compares viral, non-viral, and physical delivery systems, with particular emphasis on nanocarrier-based strategies for gene delivery.

Materials and Methods

A comprehensive literature review of recent literature was conducted focusing on CRISPR-Cas9-mediated correction of collagen-related mutations, extracellular matrix modulation, and comparing different delivery methods, including viral, non-viral, and physical delivery platforms and carriers, in bone and tendon research.

Results

Studies demonstrate that CRISPR-Cas9 can restore collagen production, improve extracellular matrix organization, and enhance osteogenic differentiation in preclinical models of collagen disorders. Among delivery platforms, adeno-associated viral vectors exhibit high transduction efficiency but are constrained by limited cargo capacity and immunological concerns. Non-viral nanocarriers, particularly lipid nanoparticles, polymeric nanoparticles, and inorganic nanoparticles, provide greater flexibility in delivering Cas9 mRNA, plasmid DNA, or ribonucleoprotein complexes while reducing the risk of genomic integration. Lipid nanoparticles have emerged as the most clinically advanced non-viral platform because of their biocompatibility, scalability, and capacity for repeated administration. Nevertheless, penetration into highly collagenous tissues remains a significant challenge. Emerging approaches involving surface modification, biodegradable ionizable lipids, and tissue targeting ligands are improving delivery efficiency and therapeutic specificity.

Conclusion

CRISPR-Cas9 represents a powerful tool for treating collagen-associated musculoskeletal disorders, but successful clinical translation depends on the development of efficient delivery systems. Nanocarrier-based platforms, particularly lipid nanoparticles, offer a promising balance between safety, scalability, and gene-editing efficacy and are likely to play a central role in future CRISPR-based therapies for bone and tendon diseases.

Acknowledgements

The authors acknowledge the Dept. of Bioengineering and Biosciences, American University of Sharjah, for supporting this work.

Table 1: Comparative overview of different gene delivery systems used in tissue engineering and regenerative medicine, highlighting their efficiency, safety profile, clinical translation potential, major advantages, and limitations, as well as their reported musculoskeletal applications.

Delivery System	Efficiency	Safety Profile	Clinical Translation Potential	Key Advantages	Key Limitations	Reported Musculoskeletal Application
Adenoviral Vectors	High Transient Expression and Transduction Efficiency	Moderate–Low	Low–Moderate	Broad Tropism; High Gene Transfer Efficiency; Large Cargo Capacity	Strong Immune Responses; Transient Expression; Repeated Dosing Difficulty	Tendon Healing Through BMP-12 and BMP-14 Gene Delivery; Enhanced collagen synthesis and tendon repair
Lentiviral Vectors	Very High; Stable Long-term Expression Through Genomic Integration	Moderate	Moderate	Long-term Expression; Infects Dividing and Non-Dividing Cells; Large Cargo Capacity	Risk Insertional Mutagenesis; Biosafety Concerns; Permanent Integration	Widely Used for Gene Editing, Stem Cell Engineering, and Musculoskeletal Research Models
AAV (Adeno-Associated Virus)	High In Vivo Delivery Efficiency	High	High	Low Immunogenicity; Tissue-Specific Serotypes; Long-Term Episomal Expression	Limited Cargo Capacity (~5 kb); Immune Response at High Dose	CRISPR-Mediated Correction of COL1A1/COL1A2 Mutation in Osteogenesis Imperfecta Models
Lipid Nanoparticles (LNPs)	Moderate–High (Variable in Dense Tissues)	Very high	High	Non-Integrating; Low Immunogenicity; Scalable Manufacturing; Suitable For mRNA AND RNP Delivery	Limited Penetration in Dense Tissues; Endosomal Escape Remains Challenging	Delivery Of Therapeutic Genes and Emerging CRISPR Cargo For Tendon and Bone Regeneration
Polymer-Based Nanoparticles	Moderate	Moderate	Low–Moderate	Tunable Size, Charge, and Degradation; Versatile Formulation	Potential Cytotoxicity; Variable Transfection Efficiency; Limited Clinical Validation	Experimental Gene-Editing and Regenerative Medicine Applications
Inorganic nanoparticles (gold, silica, magnetic)	Moderate-High	Moderate	Low-Moderate	High Cargo Loading; Tunable Physiochemical Properties; Stimulus-Responsive Delivery	Potential Long-Term Toxicity; Limited Biodegradability; Metal Accumulation Concerns	Experimental CRISPR Delivery and Mutation Correction Studies
Electroporation	High Localized Delivery	Moderate	Moderate	Efficient Delivery Of DNA, mRNA, and RNPs; Suitable for ex Vivo Editing	Cell Damage; Tissue Injury; Specialized Equipment Required	Bone Regeneration and Fracture Repair Models
Sonoporation	Moderate-High Localized Delivery	Moderate	Low-Moderate	Ultrasound-Guided Localized Delivery; Minimally Invasive	Variable Efficiency; Ultrasound Optimization Required	Tendon, Ligament, and Bone Repair Studies
Microinjection	Very High (Single Cell Level)	High	Low	Precise, Intracellular Delivery; Minimal Dependence on Carrier Systems	Abor-Intensive; Low Throughput; Poor Scalability	Embryo Editing and Proof-Of-Concept CRISPR Studies

D3 – P059

FAU-Type zeolite nanocarriers for stabilization of gadolinium-based MRI contrast agents

Qassab M.[1], Leveque M.[2], Amedlous A.[1], Valable S.[2]*, Mintova S.[1]*
[1]Catalysis and Spectrochemistry Laboratory (LCS), Caen; [2]CYCERON – UMS 3408, CNRS/ CEA/ Université de Caen Normandie, France

Introduction

Magnetic resonance imaging (MRI) is a widely used non-invasive diagnostic technique that often relies on contrast-enhanced MRI to improve sensitivity and resolution. Gadolinium-based compounds are among the most effective MRI contrast agents due to the strong paramagnetic properties of Gd^{3+}, which arise from its seven unpaired 4f electrons.[1] However, the toxicity of free Gd^{3+} ions and their potential interference with calcium-dependent biological processes remain major limitations for biomedical applications.

In this study, FAU-type zeolites are investigated as biocompatible nanoporous host materials for the confinement and stabilization of gadolinium ions. FAU zeolites were selected due to their high surface area, well-defined porous architecture, ion-exchange capacity, and recognized biocompatibility. These properties enable effective immobilization of Gd^{3+} ions within the zeolite framework while reducing their release into biological environments.

Results

The procedure used to incorporate gadolinium into FAU zeolites is illustrated in Figure 1 together with the main results obtained by characterization using XRD, DLS and Zeta potential measurements. Characterization analyses confirmed the successful incorporation of Gd^{3+} ions into the FAU zeolite framework while preserving the structural integrity of the zeolite nanocrystals. The zeolite nanocrystals enable effective confinement of the paramagnetic species within the inorganic matrix, thereby preserving gadolinium's functionality while enhancing structural stability and limiting potential ion leakage.




Figure 1. Schematic illustration of the synthesis and characterization of Gd^{3+}-loaded FAU zeolite nanocrystals (Gd-FAU).

Conclusion

The combination of gadolinium with the confinement capability of FAU zeolites represents a promising strategy for developing safer and more stable MRI contrast platforms for potential biomedical applications.

Acknowledgements

This work was supported by the Centre National de la Recherche Scientifique (CNRS), France.

References

[1]Runge V.M. Dechelation (Transmetalation): Consequences and Safety Concerns with the Linear Gadolinium-Based Contrast Agents, In View of Recent Health Care Rulings by the EMA (Europe), FDA (United States), and PMDA (Japan). *Investigative Radiology* 2018; 53; 571–578.
[2]Dang L.V., Nguyen T.T.M., Do D.V., Le S.T., Pham T.D., Le A.T.M. Study on the Synthesis of Chabazite Zeolites via Interzeolite Conversion of Faujasites. *Journal of Analytical Methods in Chemistry* 2021; 5554568–5554568.
[3]Zhu D., Wang L., Cui W., Tan J., Tian P., Liu Z., Regulation of the Si/Al Ratios and Al Distributions of Zeolites and Their Impact on Properties. *Chemical Science* 2023; 14; 1935–1959.

D3 – P061

Amphiphilic hyaluronic acid lipoate with intrinsic thixotropic behaviour as biostrucutral and soft tissue augmentation

di Gennaro M.[1], Della Sala F.[1], Barretta M.[1], Stucchi L.[2], Borzacchiello A.[1]
[1]Institute of Polymers, Composites and Biomaterials, National Research Council, Naples; [2]BMG Pharma spa, Milan, Italy

Introduction

Hyaluronic acid (HA) is the gold standard in aesthetic medicine for treating age-related defects, both in its linear form, for mesotherapy, and in its cross-linked form, as a dermal filler. Since traditional cross-linkers are a cause for concern due to their possible undesirable effects, research has focused on the preparation of materials based on HA containing natural molecules as an alternative.[1,2] In particular, mixtures of water with hydrophobically modified polysaccharides exhibited interesting hydrogel-like viscoelastic properties and thixotropy behaviour. Therefore, the modification of HA with hydrophobic groups appears as an intriguing strategy for the preparation of novel injectable systems. In previous studies, a stable and biocompatible amphiphilic compound with lipoate and formate groups (SHLF) was obtained.[3]

Aim

The aim of this work has been the synthesis of amphiphilic HA-LF and the characterization of HA-LF/water mixtures as potential devices in aesthetic medicine.

Materials and Methods

HA-LF was synthetized using a previously established protocol. The self-assembling of the amphiphilic HA-LF in water was investigated by UV-Vis measurements in presence of the dye Nile Red, and the molecular weight conservation after the reaction was assessed using Static Light Scattering. The viscoelastic properties, the thixotropy and the enzymatic degradation of the HA-LF/water mixtures were investigated by means of rheological analysis. The morphological and structural analysis on HA-LF/water mixtures were carried out by means of Small Angle X-Ray Scattering (SAXS) and Scanning Electron Microscopy (SEM). The interaction of HA-LF with water was assessed by Differential Scanning Calorimetry (DSC).

Results

HA-LF was obtained, and the synthesis has been assessed as not causing reductions in molecular weight. HA-LF obtained exhibited self-aggregation properties in water, and above a threshold concentration, the establishment of supramolecular structures with solid-like viscoelastic (Figure 1) properties was observed. The introduction of hydrophobic groups was observed to decrease the hydrophilicity of the polymer, and at the same time to reduce the chain flexibility. These structural chains have conferred to the systems marked shear thinning and thixotropic properties (Figure 2), making them suitable for the design of injectable devices. HA-LF degrades via hyaluronidase, whereas lipophilic shielding limits esterase activity. In vitro studies demonstrated the biocompatibility of HA-LF/water mixtures, with viability >70% over 3 days for all the systems.




Figure 1. Frequency Sweep of HA-LF/water mixtures at 0.1, 1 and 2% w/w.




Figure 2. Shear step test of HA-LF/water mixtures at 0.1, 0.5, 1, 1.5, 1.8 and 2% w/w.

Conclusion

HA-LF/water mixtures exhibited concentration-dependent properties that make them promising for application both in microinjections, as a viscous fluid, and in its solid-like form as a dermal filler.

References

[1]Wojtkiewicz M., Stachura A., Roszkowski B., Winiarska N., Kazimierska K., Stachura, K. Are We Overlooking Harms of BDDE-Cross-Linked Dermal Fillers? A Scoping Review. *Aesthetic plastic surgery* 2024; 48(23), 5147-5154.

[2]Murugesan M., Mathiyalagan R., Ramadhania Z.M., Nahar J., Luu C.H., Phan V.G., Thambi T. Tailoring hyaluronic acid hydrogels: Impact of cross-linker length and density on skin rejuvenation as injectable dermal fillers and their potential effects on the MAPK signaling pathway suppression. *Bioactive Materials* 2025; 49; 154-171.

[3]Picotti F., Fabbian M., Gianni R., Sechi A., Stucchi L., Bosco M. Hyaluronic acid lipoate: synthesis and physicochemical properties. *Carbohydrate polymers* 2013; 93(1); 273-278.

D3 – P062

Balancing cytocompatibility and antimicrobial performance in chemometrically optimized chitosan-stabilized sulfur nanoparticles

Nunes R.S.[1,2], Marzenta C.A.[1], Menarbazari A.A.[2], Sorribas A.R.[2,4], Cinel V.D.P.[1], Reis R.A.[1], Battistini G.C.[1], Silva R.A.G.[3], Seabra A.B.[1], Ginebra M.P.[2,4,5]

[1]Federal University of ABC, Santo André, Brazil; [2]Biomaterials, Biomechanics and Tissue Engineering Group, Dept. of Materials Science and Engineering, Universitat Politècnica de Catalunya - BarcelonaTech, Barcelona, Spain; [3]Federal University of São Paulo, São Paulo, Brazil; [4]Instituto de Salud Carlos III, Madrid, Spain; [5]Barcelona Institute of Science and Technology, Spain

Introduction

Infections associated with biomaterials are frequently caused by gram-positive bacteria and remain difficult to control due to rapid surface colonization. Sulfur nanoparticles exhibit antimicrobial activity, but their use is often constrained by colloidal instability and safety limits. Here, chitosan-stabilized sulfur nanoparticles optimized via multivariate design of experiments (DoE) are evaluated in human keratinocytes and against *Staphylococcus epidermidis*, enabling identification of a concentration window in which bactericidal activity is achieved while cytocompatibility is preserved.

Materials and Methods

Chitosan-stabilized sulfur nanoparticles (SNPs@CS, ≈100–260 nm) previously optimized by DoE were used. Cytocompatibility was assessed in human keratinocytes after 24 h exposure using AlamarBlue viability assay Antimicrobial activity was evaluated against *S. epidermidis*, a gram-positive model, by quantification of ATP and colony-forming units (CFU) over a concentration range of 12.5–400 µg/mL, allowing comparison between metabolic effects and bacterial viability.

Results

SNPs@CS exhibited a clear dose-dependent response against *S. epidermidis*. At low concentrations (25–50 µg/mL), ATP levels increased without a corresponding reduction in CFU, indicating metabolic overactivation consistent with bacterial stress. From 75 µg/mL onward, ATP levels decreased sharply, accompanied by a pronounced reduction in viable bacteria. Bactericidal activity, *i.e.* >99.9% reduction in CFU counts, was observed at concentrations ≥100 µg/mL. Cytocompatibility assays showed preserved keratinocyte viability up to approximately 200 µg/mL, defining a concentration window in which bactericidal activity against *S. epidermidis* is achieved while maintaining compatibility with host cells.




Figure 1. (A) Cell viability of HaCaT keratinocytes after 24 h exposure to SNPs@CS and Control SNPs. Negative control corresponds to untreated cells (100% viability), and positive control was 5% v/v DMSO; **(B)** Viability of *Staphylococcus epidermidis* after 2 h of exposure to SNPs@CS determined by CFU counting; **(C)** Bacterial ATP levels of *Staphylococcus epidermidis* after 2 h of exposure to SNPs@CS measured using the BacTiter-Glo™ microbial cell viability assay. Statistical significance was determined by one-way ANOVA followed by Dunnett's multiple comparisons test against the negative control. Bars with asterisks represent values significantly different from the negative control ($p < 0.05$).

Conclusion

DoE-driven optimization enabled the synthesis of SNPs@CS that combine antimicrobial activity against *S. epidermidis* with preserved cytocompatibility. Within the tested conditions, these results support their potential use as antimicrobial components in biomaterial-based strategies for infection control, warranting further evaluation in application-specific and long-term models, such as wound healing in skin.

Acknowledgements
The authors acknowledge the financial support from CAPES (Finance Code 001; Projects 88881.711920/2022-01 and 88887.123799/2025-00), CNPq (Grants 313117/2019-5 and 405908/2022-9), Human Resources Program of the National Agency of Petroleum, Natural Gas and Biofuels – PRH-ANP (Grant 2025/03449-6), and FAPESP (Grants 2022/14645-2, 2024/12112-2, 2024/04079-5, 2025/04749-3, 2025/26102-1, and 2023/16363-7). This study was supported in part by the INCT Nanotechnology for Sustainable Agriculture (INCT NanoAgro; MCTI–CNPq–CAPES, Grant No. 405924/2022–4). This work was funded by the European Research Council (ERC, BAMBBI, Grant No. 101055053). The research group is part of Maria de Maeztu Units of Excellence Programme CEX2023-001300-M/ funded by MCIN/AEI/10.13039/501100011033, Spanish Ministry of Science and Innovation.

D3 – P063

Structurally engineered carbonized polycatechin for targeting VEGF signaling and oxidative stress in corneal neovascularization

Huang Y.-F.[1,2,*], Lee W.-J.[2], Tsai H.-W.[1], Lin H.-C.[3,*]
[1]Institute of Analytical and Environmental Sciences, National Tsing Hua University; [2]Dept. of Biomedical Engineering and Environmental Sciences, National Tsing Hua University; [3]Dept. of Ophthalmology, National Taiwan University Hospital, Hsin-Chu Branch, Hsinchu, Taiwan

Introduction

Corneal neovascularization (CNV) is a condition where abnormal blood vessels grow into the cornea, potentially leading to opacification and blindness. This process is driven by the overexpression of vascular endothelial growth factor (VEGF) and its interaction with the VEGF receptor-2 (VEGFR-2), stimulating angiogenesis. The oxidative stress induced by reactive oxygen species accumulation further promotes the growth of new blood vessels, exacerbating the condition. Therefore, developing a multifaceted treatment capable of inhibiting the VEGF-VEGFR-2 interaction and mitigating oxidative stress is critical.

Aim


To develop a structurally engineered carbonized polycatechin (c-pCh) nanomedicine capable of simultaneously inhibiting VEGF-VEGFR-2 signaling and oxidative stress, and to evaluate its therapeutic potential for the treatment of CNV.

Materials and Methods

Catechin (Ch) was subjected to mild pyrolysis at 210 °C followed by alkaline polymerization to produce carbonized polycatechin (c-pCh-210). The material was characterized and evaluated for antioxidant activity using radical scavenging assays. Cellular uptake, VEGFR-2 binding, ROS scavenging, and VEGF inhibition were examined in Statens Seruminstitut rabbit cornea cells (SIRC) and human umbilical vein endothelial cells (HUVECs). Anti-angiogenic effects were assessed through proliferation, migration, and tube formation assays. Therapeutic efficacy was further evaluated in a rat suture-induced CNV model.

Results

c-pCh-210 retained strong antioxidative capacity and effectively reduced H_2O_2-induced intracellular ROS and VEGF expression. Compared with monomeric Ch and polycatechin (pCh), c-pCh-210 showed enhanced interaction with VEGF and VEGFR-2, resulting in stronger inhibition of endothelial cell proliferation, migration, and tube formation. In vivo, subconjunctival administration of c-pCh-210 significantly suppressed CNV progression, demonstrating superior efficacy compared with free Ch and comparable therapeutic outcomes to the clinically used anti-VEGF drug aflibercept.



Scheme 1. Schematic representation of (A) synthesis of carbonized-polycatechin (c-pCh) from catechin through pyrolysis at 210 °C followed by polymerization under alkaline conditions and (B) their application for the treatment of a suture-induced CNV rat model through the multifaceted anti-angiogenic actions.

Conclusion

The engineered c-pCh-210 nanomaterial provides a multifunctional therapeutic strategy that simultaneously targets oxidative stress and VEGF-mediated angiogenesis. These findings highlight the potential of carbonized phytochemical-derived nanomedicines for the treatment of CNV and other angiogenesis-related diseases.

Acknowledgements

This study was supported by the National Science and Technology Council, Taiwan, under contracts 111-2113-M-007-029 and 112-2113-M-007-022-MY3; by grants 110Q2505E, 111-F7MDHE1, 112-F7MCFE1, 113QF026E1, and 114QF018E1 from National Tsing Hua University; and by grants 110-HCH072, 111-HCH091, 112-HCH098, and 113-HCH111 from National Taiwan University Hospital, Hsin-Chu Branch, respectively.

D3 – P064
Study of photodetectors based on biomaterial-Si heterojunction

Kaddeche M.[1], Kaddeche Z.E.[2]
[1]Dept. of Electronics, Faculty of Science and Technology, Djilali Bounaama University of Khemis Miliana, Ain Defla, Algeria; [2]Faculty of E.A.S, Beyoğlu/İstanbul,Turkey

This study evaluates the modeling of a photodetector utilizing bio-functional Ag-containing biomaterials, featuring an Ag interface that incorporates a silk layer with integrated Ag nanowires as the top contact. A biocompatible and adaptable framework for electronic skin or tissue is provided by the photo-responsive biomaterial-Silicon semiconductor hetero-junction.

D3 – P065
PAAm/TOCNF-AgNPs bioactive platforms for antibacterial applications

Marinescu I.M.[1], Serafim A.[2], Olaret E.[2], Vasile B.S.[3], Mihailescu M.[4], Gradisteanu Pircalabioru G.[5], Syverud K.[6], Almeland S.K.[7], Mohamed-Ahmed S.[8], Mustafa K.[8], Stancu I.C.[1,9]
[1]APMG, Faculty of Chemical Engineering and Biotechnologies, NUSTPB, Bucharest, Romania; [2]APMG, CAMPUS Research Institute, NUSTPB, Bucharest, Romania; [3]National Research Center for Micro and Nanomaterials, Faculty of Chemical Engineering and Biotechnologies, NUSTPB, Bucharest, Romania; [4]Holographic Imaging and Processing Laboratory, Physics Dept., NUSTPB, Bucharest, Romania; [5]Faculty of Biology, University of Bucharest, Romania; [6]RISE PFI, Dept. of Chemical Engineering, Norwegian University of Science and Technology (NTNU), Trondheim, Norway; [7]Dept. of Plastic, Hand and Reconstructive Surgery, Norwegian National Burn Center, Haukeland University Hospital, Bergen, Norway; [8]Center of Translational Oral Research (TOR), Dept. of Clinical Dentistry, University of Bergen, Bergen, Norway; [9]Faculty of Medical Engineering, NUSTPB, Bucharest, Romania

Introduction
In the context of increasing antibacterial resistance, novel biomaterials are continuously developed to hinder the microorganisms' functions and prevent severe infections [1]. Silver nanoparticles' (AgNPs) efficiency against microorganisms is well-known, although long-term stability remains significantly challenging regarding greener synthesis approaches. TEMPO-oxidized cellulose (TOCNF) proved to be an excellent template for *in situ* formation of such nanoparticles for diverse applications (capping agents, food packaging layers, surface-enhanced Raman spectroscopy) [2,3].

Aim
The research aims to develop a double-crosslinked composite (PTA) where AgNPs are *in situ* generated on TOCNF, followed by incorporation in polyacrylamide network (PAAm), ensuring prolonged antibacterial effect of a flexible biocompatible polymeric template.

Materials and Methods
AgNPs were synthesized *in situ* using 1% TOCNF suspension, which was used to reduce and stabilize the nanoparticles (protocol adapted from [3]). The formation of the hybrid material (TOCNF_AgNPs) was confirmed by UV-VIS spectroscopy, transmission electron microscopy (TEM) and enhanced darkfield hyperspectral images (EDHI). Subsequently, the bioactive TOCNF_AgNPs was incorporated in acrylamide and N,N'-methylene-bis-acrylamide (MBA) at varying volumetric ratios of the constituents, further photocrosslinked using 10% Irgacure in ethanol solution. PTA hydrogels have been soaked in 2% calcium chloride ($CaCl_2$) for further physical crosslinking. Mechanical changes were evaluated by compression testing and rheological analysis. Surface properties and hydrophilicity were assessed using nanoindentation, contact angle measurements, and swelling degree determination. Finally, the *in vitro* antibacterial efficacy of the biomaterials was determined by evaluating the metabolic activity and viability of the *Staphylococcus aureus*.

Results
Investigations performed on the hybrid TOCNF_AgNPs revealed the successful synthesis of two distinct populations of AgNPs. The bimodal distribution suggests an initial nucleation phase developed with the silver nitrate addition, followed by accelerated growth triggered by NaOH. Mechanical characterization demonstrated that the Young modulus of the hydrogels is dependent on the TOCNF_AgNPs concentration, highlighting the plasticizer effect of the hybrid. Under applied stress, entrapped nanofibers align, enhancing the structural compliance and flexibility of the bulk network. Moreover, the swelling capacity and overall hydrophilicity are enhanced by TOCNF_AgNPs. Antibacterial assays revealed hindered metabolic activity and reduced bacterial viability in contact with PTA hydrogels.

Conclusion
The study demonstrates the versatility of the TOCNF in the structural architecture of composite hydrogel, enabling both the synthesis of AgNPs and the flexibility of the PAAm. With proven antibacterial efficiency and enhanced elasticity, the PTA hydrogels could be considered efficient platforms for antibacterial applications.

Acknowledgements
Authors acknowledge the project ERANET-M-3-Cellu4Heal, Advanced degradable nanocellulose-based matrix for stem cell differentiation and burn wound healing. Nanoindentation contact angle and DLS analyses were possible due to ERDF/COP 2014-2020, ID P_36_611, MySMIS 107066, INOVABIOMED.

References

The extended results are presented in "*AgNPs-cellulose nanofiber/polyacrylamide hydrogels as a robust antibacterial platform for soft tissue"*, currently under review for publication in the *Gels* journal (MDPI).

[1]Li J. et al. Methicillin-Resistant Staphylococcus aureus (MRSA): Resistance, Prevalence, and Coping Strategies, *Aug. 01, 2025, Multidisciplinary Digital Publishing Institute (MDPI)*. doi: 10.3390/antibiotics14080771.

[2]Liu S., Low Z.X., Xie Z., Wang H. TEMPO-Oxidized Cellulose Nanofibers: A Renewable Nanomaterial for Environmental and Energy Applications, *Jul. 01, 2021, John Wiley and Sons Inc*. doi: 10.1002/admt.202001180.

[3]Riva L. et al. Silver Nanoparticles Supported onto TEMPO-Oxidized Cellulose Nanofibers for Promoting Cd2+ Cation Adsorption*, ACS Appl. Nano Mater* 2024; vol. 7; no. 2; 2401–2413; doi: 10.1021/acsanm.3c06052.

D3 – P066

Crack-resistant nanopatterned titanium films for durable stainless-steel vascular stents

Recek N.[1], Junkar I.[1], Yelkarasi C.[2], Kazmanli K. [2], Kovač J.[1], Mozetič M.[1], Urgen M.[2]
[1]Dept. of Surface Engineering, Jozef Stefan Institute, Sl-1000 Ljubljana, Slovenia; [2]Dept. of Metallurgical and Materials Engineering, Istanbul Technical University, Turkey

Introduction

Cardiovascular stents often suffer from limited biocompatibility, leading to complications such as in-stent restenosis and thrombosis. Conventional solutions, including drug-eluting coatings, present long-term risks and mechanical instability[1]. This study proposes a novel surface modification strategy to create nanopatterned titanium films on stainless steel stents, aiming to enhance biocompatibility while maintaining mechanical integrity during deformation.

Materials and Methods

AISI 316 LVM stainless steel substrates were first coated with ~1 μm titanium using magnetron sputtering. The films were partially anodized to form nanoporous TiO_2, followed by ultrasonication to remove the porous oxide and produce a ~500 nm nanopatterned metallic titanium surface. Some samples underwent additional oxygen plasma treatment to modify surface chemistry. Surface morphology and structure were characterized by SEM and AFM, while XPS was used to analyze chemical composition. Mechanical stability was assessed via three-point bending tests. Biological performance was evaluated through in vitro studies using endothelial (HCAEC) and smooth muscle cells (HCASMC), as well as platelet adhesion tests for hemocompatibility.

Results

The nanopatterned titanium surfaces exhibited hemispherical nanostructures (~100 nm diameter) and maintained structural integrity under mechanical deformation, unlike brittle anodic oxide layers that cracked. Plasma treatment increased oxide thickness and removed fluorinated species, improving surface chemistry. Moreover, nanopatterned surfaces promoted endothelial cell proliferation while suppressing smooth muscle cell growth—an ideal combination for reducing restenosis risk. Plasma-treated samples further enhanced endothelial response and significantly reduced platelet adhesion, indicating improved hemocompatibility.

Conclusion

The developed nanopatterned titanium coating provides a mechanically stable, drug-free surface with selective biological responses, making it a promising candidate for next-generation vascular stents and related biomedical implants.




Figure 1: Surface morphology of nanoporous (aTiO2) and ultrasonicated (cTi) areas from SEM analysis. analysis. The sample was tilted at 30º.

Acknowledgements

Support or funding must be mentioned in a separate paragraph. This is an optional heading.

References

[1]Beshchasna N., Saqib M., Kraskiewicz H., Wasyluk, Ł., Kuzmin O., Duta O.C., Ficai D., Ghizdavet Z., Marin A., Ficai A. et al. Recent advances in manufacturing innovative stents. *Pharmaceutics* 2020; 12; 349.

D3 – P067

Industrial blown film extrusion of PLA/PBAT/LLDPE blends embedded with green silver nanoparticles for active packaging

Paosen S., Lethongkam L., Voravuthikunchai S.P.
Center of Antimicrobial Biomaterial Innovation-Southeast Asia, Division of Biological Science, Faculty of Science, Prince of Songkla University, Hat Yai, Thailand.

Introduction

The transition of active food packaging from laboratory prototypes to industrial-scale production remains a critical bottleneck for commercialization. While biopolymer blends and nanotechnology offer promising solutions for extending food shelf-life, demonstrating processability on commercial production lines and meeting rigorous food safety regulations are essential steps for market entry.

Aims

This study aims to bridge the gap between biomaterial innovation and industrial readiness (Technology Readiness Level 8) by scaling up the production of active packaging films embedded with green-synthesized silver nanoparticles (AgNPs) and comprehensively evaluating their antioxidant performance, migration safety, and structural stability.

Materials and Methods

Advanced polymer blends were developed using Polylactic Acid (PLA) and Polybutylene Adipate Terephthalate (PBAT), enhanced with Linear Low-Density Polyethylene (LLDPE). Green AgNPs were synthesized using *Eucalyptus camaldulensis* leaf extract as a sustainable reducing agent and incorporated into the polymer matrix. The films were manufactured using a commercial-scale blown film extrusion process operating at commercial speeds of 150–240 m/h. Antioxidant activity was evaluated under both dynamic and thermally accelerated conditions. Specific migration of silver ions into various food simulants was quantified via Inductively Coupled Plasma Optical Emission Spectrometry (ICP-OES) over a 5-day period, in compliance with Council Directive 82/711/EEC, EU Regulation No. 10/2011, and Thai Industrial Standard (TIS 1136-2559).

Results

All formulated films exhibited high and consistent antioxidant activity ranging from 83% to 93% across both dynamic and thermal stress environments. Notably, the biopolymer-based matrix (PLA/PBAT) demonstrated superior diffusion kinetics of active compounds compared to conventional plastics. Regarding consumer safety, ICP-OES analysis confirmed that the specific migration of silver into all tested food simulants ranged from 0.003 to 0.048 mg/L. This remains safely below the maximum Specific Migration Limit (SML) of 0.05 mg/L stipulated by EU No. 10/2011, even under aggressive acidic and fatty food simulant conditions. The optimized matrix structure successfully maintained stable and controlled release of silver throughout the 5-day testing period.

Conclusion

This study validates that green nanotextured packaging can be seamlessly integrated into existing industrial manufacturing lines without compromising material integrity or safety. By achieving TRL 8, this technology bridges the gap between laboratory-stage biomaterials and market readiness. Furthermore, this approach successfully aligns with the Bio-Circular-Green (BCG) economic model by utilizing botanical waste for nanoparticle synthesis, offering a highly sustainable, safe, and commercially viable solution for the global active food packaging sector.

Acknowledgements

This project is funded by National Research Council of Thailand (NRCT), Grant No. N82A680889.

D3 – P068

Thiol-responsive multi-layered nanocomposites for switching cell death pathway in cancer therapy

Seo H.[1], Kim H.[1], Lee J.[1], Kim T.[1], Park JH.[2], Um W.[1]
[1]Dept. of Biotechnology, College of Fisheries Science, Pukyong National University, Busan; [2]School of Chemical Engineering, Sungkyunkwan University, Suwon, Republic of Korea

Introduction

Glutathione (GSH) is a major component of cellular antioxidant defense and is overexpressed at 1–10 mM within tumor cells. Physiologically, GSH rapidly scavenges reactive oxygen species (ROS) and acts as a major resistance factor in ROS-based cancer therapies. Sonodynamic therapy (SDT), which activates sonosensitizers via ultrasound (US) to generate cytotoxic singlet oxygen ($^1O_2$), is significantly limited by this tumor antioxidant defense system. Herein, we designed a thiol-activatable multi-layered sonosensitizing nanocomplex (TMS-NC) that remains inactive in normal tissues but is activated in GSH-overexpressing tumor cells. We aimed to evaluate the ability of GSH depletion and US-induced oxidative damage to shift the cell death pathway from apoptosis to necrosis. We also assessed US-induced changes in oxidative stress signaling and the Annexin V/propidium iodide (PI)-based cell death pathway relative to controls.

Materials and Methods

(Preparation of TMS-NC) TMS-NC was prepared by covalently conjugating polyethyleneimine (PEI) onto titanium dioxide (TiO_2) nanoparticles using carboxyethane phosphonic acid (CEP) and an EDC/NHS coupling reaction. Manganese dioxide (MnO_2) was synthesized by the dropwise addition of a potassium permanganate ($KMnO_4$) solution, with PEI serving as a reducing agent. Carboxymethyl dextran (CMD) was subsequently conjugated onto the outer shell using an EDC/NHS reaction. (GSH reactivity evaluation) TMS-NC was incubated in buffers containing tumor-mimicking GSH concentrations (0–10 mM) for 30 min, and its absorbance and elemental distribution were analyzed by UV-Vis and TEM/EDS. (Annexin V/PI assay) The mode of cell death induced by TMS-NC was observed in SCC7 cells using confocal microscopy. Cells were incubated with TMS-NC for 24 h, subjected to US irradiation, and stained with an Annexin V-FITC/PI kit for analysis. (HMGB1 release assay) HMGB1 released into the medium was concentrated using an Amicon centrifugal filter and detected by western blotting.

Results

(Physicochemical characteristics of TMS-NC) TMS-NC exhibited a spherical shape with an average diameter of 208 nm and a zeta potential of −23.8 mV. TEM/EDS confirmed the coexistence of Ti, Mn, and C elements, validating the multi-layered structure. (Selective dissolution of MnO_2 layer in response to GSH) Absorbance of TMS-NC at 500–600 nm decreased in a GSH-dependent manner at 1–10 mM. After treatment with 10 mM GSH, the Mn content decreased below the detection limit. (Reprogramming of cell death) After US irradiation, control nanocomposite (CNC)-treated cells exhibited typical apoptotic features with Annexin V-positive fluorescence. In contrast, TMS-NC-treated cells showed predominant necrotic features with PI-positive fluorescence and cell swelling. (Immunogenic cell death confirmed by HMGB1 release) US irradiation significantly increased HMGB1 release in the TMS-NC-treated cells compared with the CNC-treated cells.

Conclusion

In this study, we demonstrated that TMS-NC shifts the cell death pathway from apoptosis to necrosis in SDT. Furthermore, HMGB1 release was observed exclusively in TMS-NC-treated cells following US irradiation, suggesting the potential to stimulate additional antitumor immune responses. Collectively, GSH-responsive nanocomposites represent a novel anticancer strategy to reprogram cancer cell death for enhanced SDT.

Acknowledgements

This research was a part of the project titled ‘Global bluefood leadership project (RS-2025-02373103)’, funded by the Ministry of Oceans and Fisheries, Korea.

D3 – P070

Probing water dynamics and water status in GelMA and dECMMA hydrogels

Chang C.[1,2], Dargaville B.L.[1,2], Momot K.I.[3], Hutmacher D.W.[1,2]
[1]Max Planck Queensland Centre for the Materials Science of Extracellular Matrices, Queensland University of Technology (QUT); [2]School of Mechanical, Medical and Process Engineering, Faculty of Engineering, Queensland University of Technology (QUT); [3]School of Chemistry and Physics, Queensland University of Technology (QUT), Australia

Introduction

The interplay between water molecules and the polymer network governs the structural integrity and biological functionality of hydrogels. This study investigates the colloidal behaviour and hydration characteristics for hydrogels of gelatin methacrylate (GelMA) and decellularised extracellular matrix methacrylate (dECMMA), two prevalent biomaterials in tissue engineering. By focusing on the distinction between freezable and non-freezable water fractions, we aim to elucidate how polymer–water interactions dictate colloid properties of hydrogels using NMR relaxometry (T_1, T_2, and T_{1rho}). These measurements provide a molecular-level view of water dynamics, revealing how the chemical composition of GelMA versus dECMMA influences the diffusion and "boundness" of the solvent. The constant of spin-relaxation in the rotating frame (T_{1rho}) further reveal the proton chemical exchange rate of water and biopolymers, giving insight into the accessibility of water to the chemical moieties of biopolymers and the strength of hydrogen bonds.

Materials and Methods

GelMA was purchased from Gelomics Pty Ltd; lung, cartilage, and bone dECMMA were synthesised in-house. Hydrogels were crosslinked with lithium phenyl 2,4,6-trimethylbenzoylphosphinate (LAP)/visible light at 405 nm. Differential scanning calorimetry (DSC) was employed to quantify water status within the hydrogel matrices. By measuring the enthalpy of fusion (ΔH), we determined the freezable water fraction—comprising both free and loosely bound water—and the non-freezable (tightly bound) water fraction, which remains unfrozen at sub-zero temperatures due to strong hydrogen bonding with the protein chains. To further refine our understanding of water mobility, dynamic NMR relaxometry measurements were conducted. By integrating relaxation data with the Bloembergen–Purcell–Pound (BPP) theory and the Stokes–Einstein–Debye (SED) relationship, we calculated the growth of the bound water ratio and rotational correlation times (τ_c) of water.

Results

Our findings indicate that the bound water fraction and microviscosity increase with the complexity of buffers as well as polymer concentration (Figure 1). GelMA hydrogels prepared with Dulbecco's Modified Eagle Medium (DMEM) showed the highest ratio of non-freezable water and lowest water relaxation constant (both T_1 and T_2), i.e. highest microviscosity of water and lowest water diffusion coefficient compared to pure water or phosphate-buffered saline (PBS). GelMA blended with hydrophilic polymer, hyaluronic acid methacrylate (HAMA), exhibited distinct hydration signatures compared to pristine GelMA hydrogel. dECMMA comprised with multiple components such as glycosaminoglycans (GAGs) in cartilage dECMMA or other protein, e.g. elastin and laminin in lung dECMMA also presented heterogeneous water behaviours with GelMA (Figure 2).

Conclusion

This study demonstrates that combining NMR relaxometry with DSC is a robust approach for probing water status and dynamics within ECM-based hydrogels. These insights facilitate a deeper understanding of how biopolymer composition influences the aqueous environment and the colloid properties of hydrogels.

Acknowledgements

Australian Research Council (DP230102934)
Max Planck Queensland Centre on the Materials Science for Extracellular Matrices (MPQC).




Figure 1 Graphical illustration of the solute effects on water status within GelMA hydrogels under H_2O, PBS, and DMEM




Figure 2 Graphical illustration of the studied dECMs and their hydrogel and water properties

D3 – P071

Assessment of collagen-based biomaterials for wound healing applications

Bileri M.I.[1], Kokkinidou D.[2], Georghiou D.[3], Wiedl D.[3], Chrysostomou M.[1], Kaliviotis E.[1], Spanoudes K.[4], Christodoulou N.[5], Pitsillides C.[2,3,5], Prokopi M.[2,3,5], Kapnisis K.[1]
[1]Dept. of Mechanical Engineering and Materials Science and Engineering, Cyprus University of Technology, Limassol; [2]RSL Revolutionary Labs Ltd, Limassol; [3]Promed Bioscience Ltd, Limassol; [4]Vet Ex Machina Ltd, Nicosia; [5]Theramir Ltd, Limassol, Cyprus

Introduction

Regenerative medicine is increasingly focusing on the development of bioengineered materials that interact dynamically with the wound microenvironment to enhance the healing process. Among these emerging technologies, collagen-based biomaterials have gained widespread attention due to their inherent biocompatibility, biodegradability, and structural similarity to the extracellular matrix [1-2].

Aim

This study aims to evaluate how formulation, composition, and structural complexity affect the physicochemical and microstructural properties of atelocollagen materials and hydrogels, to identify the best candidates for biomedical use for wound healing.

Materials and Methods

Atelocollagen formulations with different compositions (referred to herein as A, D, X3, and Combo) and concentrations were evaluated using various methods, including measurements of viscosity, osmolality, swelling, dissolution, contact angle, and scanning electron microscopy (SEM) to analyze fibrillar morphology. Hydrogel formulations (referred to herein as T40, T41, and T43) based on the Combo atelocollagen were also tested. Additionally, a preliminary *in vivo* study using the T41 hydrogel was conducted to help establish a protocol for future large-scale animal studies.

Results

The results indicate that variations in atelocollagen composition significantly influence the sample microstructure and physicochemical properties (Figure 1). Among the samples evaluated, Combo (a blend of D and X3 atelocollagens) showed the most balanced properties, offering good hydration control and mechanical stability, whereas formulation A exhibited weak consistency and high dissolvability. Hydrogel T41 demonstrated better performance in terms of swelling stability, suggesting superior moisture retention and compatibility with physiological conditions. These characteristics are essential for supporting wound healing. Preliminary *in vivo* studies in animal models demonstrated faster and more pronounced wound healing compared to untreated controls, confirming their potential for skin regeneration applications.




Figure 1: Physicochemical (a-e) and microstructural (f-h) characterization of atelocollagen samples.

Conclusion

The composition of atelocollagen significantly influences its physicochemical and biological performance. The most optimized formulations demonstrated balanced mechanical properties, appropriate moisture retention, and enhanced wound-healing effects. These findings support their further investigation and development for skin regeneration applications.

Acknowledgements
This work was co-funded by the European Regional Development Fund and the Republic of Cyprus through the Research and Innovation Foundation (Project: ENTERPRISES/0223/Sub-Call1/0212).

References
[1]Mahajan N., Soker S., Murphy S.V. Regenerative Medicine Approaches for Skin Wound Healing: from Allografts to Engineered Skin Substitutes. *Curr Transpl Rep 11* 2024; 207–221 https://doi.org/10.1007/s40472-024-00453-5.
[2]Zheng M. et al. A Review of Recent Progress on Collagen-Based Biomaterials. *Adv Healthc Mater* 2023; 12(16); doi: 10.1002/ADHM.202202042.

D3 – P072

Effect of different anions on agarose gelation: A comparison of two agarose types

Rossi A., Sacco P., Donati I.
Dept. of Life Sciences, University of Trieste, Italy

Introduction

Agarose undergoes thermoreversible gelation when hydrogen-bond-controlled junctions form between biopolymer chains, leading to aggregation. Hydrogen bonding between water molecules and polymer chains can modulate chain–chain and helix–helix interactions, thus affecting both gelation kinetics and the final structure of the network. The availability of water molecules able to interact with the polymer can be influenced by both polymer chemistry and the ionic environment. Agarose with different degrees of methylation exhibits different hydrophilicity, which may alter polymer–water interactions. In addition, anions belonging to the Hofmeister series differ in their ability to interact with water molecules and can compete with the polymer for hydrogen bonding. Consequently, they may sequester water from the polymer chains and modify the gelation process. Building on previous observations on agarose–water interactions[1], this work investigates how some anions influence the gelation kinetics of different agarose systems.

Materials and Methods

Gelation kinetics were investigated using two agarose types with different methylation degree: electrophoresis (EP) agarose and agarose from *Gelidium*. Agarose solutions were heated and salts containing different anions were added at 80 °C prior to rheological measurements. Kosmotropic anions (CO_3^{2-}, SO_4^{2-}, $H_2PO_4^-$, Cl^-) and the chaotropic anion (I^-) from the Hofmeister series were investigated. Gelation kinetics were monitored using rheological temperature ramps, to determine the gelation temperature and the evolution of the viscoelastic properties during cooling.

Results

Analysis of the temperature ramps revealed a clear trend in gelation temperature across the Hofmeister series. Kosmotropic anions induced gelation at higher temperatures than the chaotropic anion. This suggests that ions with stronger water-structuring ability promote earlier network formation. Differences were also observed between the two agarose types. Under identical ionic conditions, EP agarose showed gelation temperatures approximately 3.5 °C higher than *Gelidium* agarose. Moreover, earlier gelation was associated with the formation of stiffer gels at the end of the temperature ramp, whereas later gelation resulted in softer networks**.**

Conclusion

The results demonstrate that the ionic environment can effectively modulate the gelation kinetics of agarose hydrogels. These preliminary results provide further insight into the mechanisms governing agarose gelation and suggest that both ionic environment and polymer structure can be exploited to tune hydrogel formation. Further experiments are planned to deepen the understanding of the molecular mechanisms underlying these observations.

References

[1] Mio L., Piazza F., Abrami M., Conti M., Lopez F., Fratini E., Grassi M., Brun F., Donati I., Sacco P. Effect of anions, concentration and mechanical stimulation on the gelation of agarose. *International Journal of Biological Macromolecules* 2026; 340; 150233.

D3 – P073

Solvent ratio optimization of electrospun zein scaffolds for cultured meat

Krugly E.[1], Murthy B.[1], Gasiulyte E.[1], Pauliukaityte I.[1,2] and Ciuzas D[1]
[1]Faculty of Chemical Technology, Kaunas University of Technology; [2]Food Institute, Kaunas University of Technology, Lithuania

Introduction

Cultured meat production requires fibrous scaffolds that can guide cell organization and provide a three-dimensional growth environment. Zein, a maize-derived protein, is a candidate biomaterial for fibrous scaffold fabrication. This study examined the effect of ethanol:water ratio on the electrospinning performance and morphology of zein-based formulations for cultured meat applications.

Materials and Methods

Electrospinning solutions contained 25% (w/v) zein, 0.3% (w/v) poly(ethylene oxide) (PEO), 0.5% (w/v) NaCl, 7% (w/w) glycerol and 10% (w/w) glucose. Ethanol:water ratios of 60/40, 70/30, 80/20 and 90/10 were evaluated. All samples were processed at 24.5 °C and 55% relative humidity using 14 kV, 6 mL/h, a 10 cm needle-to-collector distance and an 18 G needle. Process stability, sample uniformity, bead formation, fibre morphology and fibre diameter were assessed.

Results

Solvent ratio markedly influenced jet stability and scaffold quality. The 60/40 formulation showed pulsing, non-uniform deposition and beads, producing ribbon-like fibres with a mean diameter of 13.9 ± 4 µm. The 70/30 formulation gave stable electrospinning, uniform mats and bead-free ribbon-like fibres, with a mean diameter of 10.1 ± 3 µm. The 80/20 formulation also spun stably and yielded the smallest diameter (7.4 ± 2 µm), but merged fibres and cracks were observed. In contrast, the 90/10 formulation led to electrospraying rather than consistent fibre formation, with non-uniform deposition, beads and merged structures/cracks; the measured diameter was 11.6 ± 4 µm.




Fig. 1. SEM Images of samples produced using solution ratios A - 60/40, B – 70/30, C – 80/20, D – 90/10.

Conclusion

Among the tested formulations, ethanol:water 70/30 provided the best overall compromise between electrospinning stability, sample uniformity and defect-free fibre formation. Although the 80/20 ratio reduced fibre diameter, the presence of merged fibres and cracks limits its suitability. These findings define a practical solvent window for further optimization of zein-based fibrous scaffolds and support future mechanical and cell-response studies for cultured meat.

Acknowledgements

This study was funded by the Research Council of Lithuania “Edible fibrous polymer scaffolds for meat cultivation” (Grant No. S-MIP-25-61).

D3 – P074

Effect of photoinitiator ratio on microneedle hydrogels produced from alginate methacrylate via DLP 3D printer

Ilgar M.
Dept. of Chemistry, Istanbul University-Cerrahpasa, Turkey

Introduction

Photo-crosslinkable hydrogels have gained interest in biomedical applications due to their tunable properties and compatibility with 3D printing. Alginate, a biopolymer used as a hydrogel by ionic cross-linking, has limitations in in situ applications and mechanical properties. Enhanced hydrogels can be developed by functionalizing alginate with methacrylic groups, thereby enabling in situ cross-linking under UV light[1].

Aim

This study aimed to produce alginate methacrylate (ALMA) microneedle hydrogels using digital light processing (DLP) 3D printing and optimize their mechanical and physical properties by varying the concentration of lithium phenyl-2, 4, 6-trimethylbenzoylphosphinate (LAP) as the photoinitiator.

Materials and Methods

ALMA was synthesized by reacting alginate with methacrylic anhydride[2]. The chemical structure of ALMA was characterized using Fourier transform infrared spectroscopy (FTIR) and proton nuclear magnetic resonance (^{1}H-NMR) analyses. ALMA microneedle hydrogels were fabricated at three different concentrations (5%, 10%, and 15%) of LAP using DLP. Scanning electron microscopy (SEM) was used to examine the pore structure of the hydrogels. Compression mechanical testing and in vitro swelling studies were performed to investigate the effect of LAP ratio.

Results

FTIR and ^{1}H NMR analyses confirmed alginate methacrylation, and the DS% was determined from the ^{1}H NMR spectra. The LAP ratio influences the crosslinking density, thereby affecting the mechanical strength and swelling ratio of ALMA hydrogels. SEM images showed ALMA hydrogels' porous microstructure became smaller with increased LAP ratio. Smaller pores indicate a polymer network with a high cross-linking density. Under normal conditions, a low swelling rate occurs owing to restricted chain expansion within the tight network. However, increasing the LAP ratio resulted in a slight increase in the swelling ratio. Excessive swelling in a small-pore structure suggests that water is absorbed directly by the polymer matrix rather than through the pore spaces[3]. Regarding mechanical properties, an increase in compressive stress was observed with a higher LAP ratio. Consequently, it was concluded that an increase in cross-linking density enhances mechanical properties.

Conclusion

The results demonstrate that ALMA hydrogels can be effectively photo-crosslinked using a LAP, and that LAP ratio critically affects hydrogel properties. DLP-based printing facilitated the successful fabrication of well-defined microneedle structures with high resolution, demonstrating the suitability of ALMA hydrogels for potential biomedical applications.

Acknowledgements

This study was supported by Scientific and Technological Research Council of Türkiye (TÜBİTAK) under Grant Number: 224M659.

References

[1]Wang X., Hao T., Qu J., Wang C., Chen H. Synthesis of thermal polymerizable alginate-GMA hydrogel for cell encapsulation. *Journal of Nanomaterials* 2015; (1); 970619.
[2]Gao Y., Jin X. Dual crosslinked methacrylated alginate hydrogel micron fibers and tissue constructs for cell biology. *Marine drugs* 2019; 17(10); 557.
[3]Mignon A., Zimmer J., Gutierrez Cisneros C., Kühnert M., Derveaux E., Daikos O., Schulze A. Electron-Beam-Initiated Crosslinking of Methacrylated Alginate and Diacrylated Poly (ethylene glycol) Hydrogels. *Polymers* 2023; 15(24); 4685.

D3 – P075

Investigation of DLP 3D printing performance of sargassum vulgare derivative methacrylated sodium alginate microneedle hydrogels

Emekdar E.[1], Carkcı E.D. [1], Ilgar Ş. [1], Cesur S. [2], Gunduz O.[2], Ilgar M.[3]
[1]Dept. of Bioengineering, Yıldız Technical University, İstanbul, Turkey; [2]Dept. of Metallurgical and Materials Engineering, Marmara University, İstanbul, Turkey; [3]Dept. of Chemistry, İstanbul University-Cerrahpasa, Türkiye

Introduction

Natural polysaccharides hold a significant place in tissue engineering and advanced biomaterial applications, particularly due to their biocompatibility, biodegradability, and modifiable structures. Sodium alginate (SA), obtained from brown algae, stands out with its ionic gel-forming capacity, and its photopolymerizability through chemical modifications makes it suitable for use in three-dimensional (3D) bioprinting technologies[1].

Aim

This study aimed to obtain alginate from Sargassum vulgare (brown algae) using a classical extraction method, functionalize it by methacrylation, and structure it in hydrogel form using digital light processing (DLP).

Materials and Methods

SA was extracted from *Sargassum vulgare* using a classical method involving formaldehyde pretreatment, acidic extraction, and alkaline dissolution. The resulting SA was purified by precipitation with ethanol and dried[2]. Subsequently, SA was functionalized with methacrylic anhydride to make it photopolymerizable[3]. Methacrylated SA (SA/MA) solutions were printed as microneedle structures using a DLP-based 3D printer and a computer-aided design (CAD) model, in the presence of lithium phenyl-2,4,6-trimethylbenzoylphosphinate (LAP). The chemical, physical, and morphological properties of the samples were investigated using a rheometer, Fourier transform infrared spectroscopy (FTIR), proton nuclear magnetic resonance (^{1}H-NMR) spectroscopy, scanning electron microscopy (SEM), differential scanning calorimetry (DSC), and a compression testing machine. In addition, the in vitro swelling and degradation behavior of SA/MA hydrogels were evaluated.

Results

Rheological analyses showed that SA exhibited pseudoplastic flow behavior, with structural strength and flow properties varying with concentration; however, all systems shared the same flow mechanism. FTIR and ^{1}H-NMR results confirmed the successful synthesis of SA and SA/MA. SEM analyses revealed the surface characteristics of SA and revealed that the morphologies of SA/MA hydrogels exhibit a porous microstructure ideal for potential biomedical applications. Mechanical compression tests revealed the desired mechanical strength of the photo-polymerized hydrogels (SA/MA-H). DSC analyses revealed changes in the thermal properties after modification, and in vitro swelling and degradation tests showed that SA/MA-H exhibited controlled water uptake and time-dependent degradation behavior.

Conclusion

This study demonstrates that SA derived from *Sargassum vulgare* can be extracted under optimal parameters, functionalized by methacrylation, and transformed into a bioink suitable for DLP-based 3D bioprinting. The morphological, mechanical, and physicochemical properties of the resulting hydrogels show promising potential for tissue engineering and biomedical applications. This approach represents an important strategy for integrating naturally derived biopolymers with advanced manufacturing technologies.

Acknowledgements

This study was supported by Scientific and Technological Research Council of Türkiye (TÜBİTAK) under Grant Number: 224M659.

References

[1]Aghajani M., Garshasbi H.R., Naghib S.M., Mozafari M.R. 3D printing of hydrogel polysaccharides for biomedical applications: a review. *Biomedicines* 2025; 13(3); 731.
[2]Hambali E., Wibawa Sakti S.C., Fahmi M.Z., Wahyudianto F.E., Nuryono Yessi P., Pratama B.S. Effect of extraction time and Na_2CO_3 concentration on the characteristics of alginate extracted from *Sargassum* sp. *IOP Conference Series: Earth and Environmental Science* 2018; 209(1); 012033.
[3]Hasany M., Talebian S., Sadat S., Ranjbar N., Mehrali M., Wallace G.G., Mehrali M. Synthesis, properties, and biomedical applications of alginate methacrylate (ALMA)-based hydrogels: Current advances and challenges. *Applied Materials Today* 2021; 24; 101150.

D3 – P076

Optimization and characterization of sodium alginate and metacrylated sodium alginate synthesis from brown algae

Carkci E.D. [1], Emekdar E.[1], Okudan E.Ş.[2], Gunduz O.[3], Ilgar M.[4]
[1]Dept. of Bioengineering, Yıldız Technical University, İstanbul; [2]Dept. of Marine Biology, Akdeniz University, Antalya; [3]Dept. of Metallurgical and Materials Engineering, Marmara University, İstanbul; [4]Dept. of Chemistry, İstanbul University-Cerrahpasa, Turkey

Introduction

Sodium alginate (SA), obtained from brown algae, is a naturally occurring polysaccharide widely used in biomedical applications due to its biocompatibility and gel-forming capacity. However, extraction conditions and chemical modification steps directly affect the structural and functional properties of the resulting SA [1].

Aim

This study aimed to obtain SA from *Sargassum vulgare* using different sodium carbonate (Na_2CO_3) concentrations, characterize the obtained alginates, and chemically modify them with methacrylate to tailor their physicochemical properties for advanced applications.

Materials and Methods

SA was extracted from *Sargassum vulgare* (brown algae) using different Na_2CO_3 concentrations (2%, 2.5%, and 3% w/v)[2]. The obtained SA samples at the three different Na_2CO_3 concentrations were subsequently modified with methacrylic anhydride (SA/MA)[3]. Morphological properties were analyzed using scanning electron microscopy (SEM), while viscosity behaviors were evaluated using an Ubbelohde viscometer. The molecular weight of the SA samples was determined using the Mark-Hauwink equation. The M/G ratio of the SA samples and the degree of saturation (DS%) of the SA/MA samples were determined using nuclear magnetic resonance (^{1}H-NMR) analysis. Fourier transform infrared spectroscopy (FTIR) and differential scanning calorimetry (DSC) were used to identify structural changes and thermal behavior before and after methacrylation.

Results

The results demonstrated that the Na_2CO_3 concentration significantly influenced the SA yield and structural characteristics. The extraction yield increased with increasing Na_2CO_3 concentration. FTIR confirmed the characteristic functional groups of SA and indicated the successful incorporation of methacrylate groups. SEM images revealed notable differences in the surface morphology depending on the extraction conditions. Viscosity measurements indicated that the Na_2CO_3 concentration affected polymer chain interactions and molecular organization, leading to variations in molecular weight, and H-NMR results confirmed the M/G ratio related to the viscosity results. Higher Na_2CO_3 concentrations resulted in increased intermolecular interactions and altered gel stiffness. DSC analysis showed that changes in the Na_2CO_3 concentration modified chain regularity and intermolecular interactions, leading to differences in the thermal transition temperatures and overall thermal stability. ^{1}H-NMR results confirmed that DS% was successfully optimized depending on Na_2CO_3 concentration.

Conclusion

This study demonstrates that the Na_2CO_3 concentration is a critical parameter in the production of SA from *Sargassum vulgare* and plays a decisive role in both extraction yield and chemical modification efficiency. SA with optimized methacrylation levels has potential applications in the field of biomedicine, particularly in photopolymerizable hydrogel systems.

Acknowledgements

This study was supported by Scientific and Technological Research Council of Türkiye (TÜBİTAK) under Grant Number: 224M659.

References

[1]Saji S., Hebden A., Goswami P., Du C. A brief review on the development of alginate extraction process and its sustainability. Sustainability 2022; 14(9); 5181.
[2]Hambali E., Wibawa Sakti S.C., Fahmi M.Z., Wahyudianto F.E., Nuryono Yessi P., Pratama B.S. Effect of extraction time and Na_2CO_3 concentration on the characteristics of alginate extracted from *Sargassum* sp. *IOP Conference Series: Earth and Environmental Science* 2018; 209(1); 012033.
[3]Hasany M., Talebian S., Sadat S., Ranjbar N., Mehrali M., Wallace G.G., Mehrali M. Synthesis, properties, and biomedical applications of alginate methacrylate (ALMA)-based hydrogels: Current advances and challenges. *Applied Materials Today* 2021; 24; 101150.

D3 – P077

Design and characterization of collagen–hyaluronic acid scaffolds enriched with ferulic acid

Kaczmarek-Szczepańska B.[1,2], Fałkowska K.[1], Dulok K.[1], Shinde A.[1], Obieziurska-Fabisiak M.[3], Zasada L.[1]
[1]Laboratory For Functional Polymeric Materials, Faculty of Chemistry, Nicolaus Copernicus University in Toruń; [2]Institute Of Advanced Studies, Nicolaus Copernicus University in Toruń;
[3]Dept. of Organic Chemistry, Faculty of Chemistry, Nicolaus Copernicus University in Toruń, Poland

Introduction

Collagen and hyaluronic acid are widely used natural polymers in tissue engineering due to their excellent biocompatibility, biodegradability, and structural similarity to the extracellular matrix[1]. However, their limited mechanical stability and susceptibility to rapid degradation remain key challenges. The incorporation of bioactive compounds, such as ferulic acid offers a promising strategy to enhance scaffold functionality. Ferulic acid exhibits antioxidant, anti-inflammatory, and potential crosslinking properties, which may improve both the physicochemical and biological performance of biomaterials[2].

Aim

The aim of this study was to design and characterize collagen or hyaluronic acid-based scaffolds enriched with ferulic acid and to evaluate their structural, mechanical, thermal, and antioxidant properties for potential biomedical applications.

Materials and Methods

Biopolymers were dissolved in 0.1M acetic acid separately. Collagen or hyaluronic acid-based scaffolds were fabricated using a freeze-drying method, followed by incorporation of ferulic acid to collagen or hyaluronic acid solution. The physicochemical properties of the scaffolds were analyzed using scanning electron microscopy (SEM) to assess morphology and porosity. Fourier-transform infrared spectroscopy (FTIR) was used to investigate interactions between components. Mechanical properties were evaluated through compression testing, and thermal stability was assessed using thermogravimetric analysis (TGA). The antioxidant activity of the scaffolds was determined using radical scavenging assays using DPPH method.

Results

The obtained scaffolds exhibited a highly porous and interconnected structure, suitable for cell infiltration and nutrient transport. FTIR analysis confirmed interactions between collagen, hyaluronic acid, and ferulic acid, suggesting partial crosslinking. Incorporation of ferulic acid resulted in improved mechanical strength and enhanced thermal stability compared to control scaffolds (without ferulic acid addition). Moreover, the modified scaffolds demonstrated significant antioxidant activity, increasing with higher ferulic acid content.

Conclusion

The developed collagen/hyaluronic acid scaffolds enriched with ferulic acid show enhanced physicochemical and functional properties, including improved stability and antioxidant activity. These multifunctional biomaterials demonstrate strong potential for applications in tissue engineering and wound healing, particularly where oxidative stress plays a critical role. Further biological evaluation is required to confirm their in vitro and in vivo performance.

Acknowledgements

The authors would like to thank the National Science Center (Grant no: UMO-2024/55/D/NZ7/01705) for providing financial support to this project.

References

[1]Xu Q., Torres J.E., Hakim M., Babiak P.M., Pal P., Battistoni C.M., Nguyen M., Panitch A., Solorio L., Liu J.C. Collagen- and Hyaluronic Acid-based Hydrogels and Their Biomedical Applications. *Materials Science and Engineering R: Reports* 2021; 146; 100641.
[2]Babbar R., Dhiman S., Grover R., Kaur A., Arora S. A Comprehensive Review on Therapeutic Applications of Ferulic Acid and its Novel Analogues: A Brief Literature. *Mini-Reviews in Medicinal Chemistry* 2021; 21; 1578–1593.

D3 – P078

Exploring collagen and alginate from fish skin and seaweed as sustainable blue materials for equine wound dressings

Franchi, J.M.[1], Rousseaux C.[1], Minsart M.[2], Dubruel P.[2], Declercq A.[1]
[1]Laboratory of Aquaculture & Artemia Reference Center (ARC), Dept. of Animal Sciences and Aquatic Ecology, Gent University; [2]Polymer Chemistry and Biomaterials Group (PBM), Dept. of Organic and Macromolecular Chemistry, Gent University, Belgium

Introduction

Fish skin from rainbow trout (*Oncorhynchus mykiss*) is an underutilized processing by-product rich in type I collagen with promising biomedical applications. Similarly, the invasive macroalga *Sargassum muticum* contributes to ecological disruption in the Belgian North Sea and is treated as marine waste, although it contains alginate suitable for hydrogel production. Both biopolymers can be applied in the development of novel wound dressings. Acquiring these molecules from discarded resources would increase their value and contribute to a more sustainable circular economy. Exuberant granulation tissue (EGT) is a chronic equine wound condition characterized by excessive granulation proliferation that prevents wound closure. Current treatment strategies focus on the use of bioactive wound dressings for their management.

Aim

To extract collagen and alginate from rainbow trout skin and *S. muticum* respectively and to develop collagen-alginate hydrogel blends as potential wound dressings for the management of equine EGT, while simultaneously valorizing aquatic waste resources.

Materials and Methods

Collagen and alginate were extracted using in-house developed protocols, and extraction yields were calculated. Structural characterization of both biopolymers was performed by Fourier Transform Infrared (FT-IR) spectroscopy, while collagen was further assessed using circular dichroism to confirm triple-helix integrity. Collagen-alginate blends with varying biopolymer proportions were prepared via ionic crosslinking and further characterized by FT-IR spectroscopy. Mechanical properties and swelling ratios were determined to evaluate hydrogel performance. Alginate was modified with methacrylic anhydride to permit covalent cross-linking and successful modification was verified through FT-IR spectroscopy. Covalent network formation was assessed using photo-rheology. A sterilization method for the blends was developed and assessed by monitoring bacterial growth on tryptic soy agar (TSA) plates. Biocompatibility and angiogenic effects of the extracts and blends were investigated via the chorioallantoic membrane (CAM) assay.

Results

Collagen and alginate were successfully extracted with yields of 12.8% (wet weight) and 13.9% (dry weight), respectively. FT-IR spectra displayed characteristic functional groups for both biopolymers, and blend spectra presented combined signals. Circular dichroism confirmed preservation of the collagen triple helix. The collagen-alginate (20:80) blend exhibited the best mechanical properties with a Young's modulus of 0.121MPa, total elongation of 28.47% and maximum stress at break of 0.017MPa. The swelling ratio of the blends tended to increase with alginate content. FT-IR confirmed successful alginate methacrylation. Sterilization was effective with no bacterial growth observed after 48h. The CAM assays indicated toxicity in alginate extracts while collagen was biocompatible; angiogenesis results remained inconclusive.

Conclusion

The extraction protocols are deemed successful and replicable, though improved purification is required to ensure biopolymer safety. Structural integrity was maintained throughout extraction. Collagen-alginate blends were successfully developed, and *S. muticum* alginate can be methacrylated to enable covalent cross-linking. Sterilization of the materials was effective. Future research will focus on improving biopolymer extraction, exploring modified blend variations and further characterizing bioactive properties.

Acknowledgements

This work was supported by the Research Foundation Flanders (FWO) through an SB PhD fellowship awarded to Franchi J.M. for the project "Exploring Collagen and Alginate from Fish Skin and Seaweed as Potential Blue Materials for Wound Dressings" (No. 1S51825N).

D3 – P079

Bacterial clycosaminoglycan-like polymers discovered by genome mining: A new frontier in biocompatible drug delivery materials

Halimi B.E., Barroug A., El Fatimy R.
Faculty of Medical Sciences, UM6P Hospitals, Mohammed VI Polytechnic University, Benguerir, Morocco

Introduction

Genome mining, the systematic exploration of genomic data to discover novel biomolecules, has emerged as a transformative approach for identifying bacterial producers of glycosaminoglycan (GAG)-like biopolymers. These biopolymers, including hyaluronic acid and heparosan, have significant biomedical applications, particularly in tissue engineering and drug delivery.

Materials and Methods

Using genome mining, we identified bacterial GAG-like biopolymers and confirmed their production through laboratory characterization. Some bacteria show substantial potential as a producer of GAG-like biopolymers. These biomaterials, structurally analogous to natural extracellular matrix components, are particularly suited for medical applications such as drug delivery systems. Members of some genus possess metabolic pathways that can be harnessed to synthesize polysaccharides with desirable properties, including biocompatibility, biodegradability, and hydrogel-forming capabilities.

Results

We have identified key biosynthetic pathways in Bacterial strains, enabling the optimization of GAG-like polymer production. These biomaterials demonstrate promise as carriers for controlled drug release, enhancing therapeutic efficacy while minimizing side effects. Furthermore, the inherent adaptability of bacteria species to diverse environmental conditions highlights their value in scalable biotechnological applications.

Conclusion

In summary, some bacterial genus represents an untapped resource in biomaterials research, with significant potential to advance drug delivery systems and other biomedical technologies.

Acknowledgements

The authors acknowledge the financial support provided by Mohammed VI Polytechnic University (UM6P) for the execution of this research.

D3 – P080
Colorimetric analysis of thermally modified Cedrela sp. wood

Polido N.G.F.D., Rodrigues L.G.M., Pratti M.E.M., Alves N.S.T., Rocha H.F., Alves J.C.
Dept. of Forest and Wood Sciences, Federal University of Espírito Santo, Jerônimo Monteiro, Brazil

Introduction

Thermal modification improves wood properties through heat treatment, promoting significant changes in chemical composition and appearance. Color is one of the most noticeable characteristics altered, serving as an indicator of chemical transformations in wood components, particularly lignin and extractives. *Cedrela sp.* is a valuable hardwood with commercial and ecological importance in Brazil, yet its colorimetric behavior under thermal modification remains underexplored. This study aimed to evaluate the colorimetric parameters of *Cedrela sp.* wood subjected to thermal modification at different temperatures.

Materials and Methods

Wood samples of *Cedrela sp.* were subjected to thermal modification at 180°C and 240°C, alongside an untreated control. Colorimetric measurements were performed using the SCE method, recording the L* (lightness) parameter. Data were analyzed by ANOVA followed by Tukey's test at 95% probability, and cluster analysis was applied to classify color groups.

Results

Figure 1 presents the lightness values (L*) of *Cedrela* sp. wood at the evaluated temperatures. A significant effect of temperature on L* was observed, with differences between treatments ($p < 0.05$). In the control, the wood presented L* = 62.73^{a}, confirming the light surface and natural pink tone (Group 04), characteristic of its chemical composition rich in phenolic extractives. At 180°C, lightness reduced approximately 15.7%, with L* = 52.87^{b}, indicating onset of thermal degradation of lignin and extractives, with chromophore formation responsible for surface darkening, classified as Reddish-brown (Group 25). At 240°C, lightness reached L* = 34.50^{c}, a total reduction of 44.97% compared to the control, evidencing severe darkening from intense lignin degradation and chromophoric structure formation, classified as Purplish-brown (Group 08).



Fig. 1. Color change of *Cedrela* wood after thermal treatment. Increasing temperature (180 °C and 240 °C) results in darker wood, as indicated by the decrease in L* values. Different letters (a, b, c) indicate significant differences between treatments ($p < 0.05$).

Conclusion

Thermal modification promoted progressive and significant lightness reduction in *Cedrela sp.* wood, confirming L* as the most sensitive colorimetric parameter, with transition from light pinkish tones in the control to dark brownish colorations at 240°C.

Acknowledgements

To the Espírito Santo Research and Innovation Support Foundation (FAPES) for the granting of the scholarship.

D3 – P081

Boosting yeast antagonism: Wickerhamomyces anomalus encapsulated in chitosan-coated alginate beads

Fernandes M.P.[1], Noronha H.[2], Silva C.[3,4], Rocha D.[4], Gerós H.[2], Matins V.[2], Silva F.S.[1,3], Rodrigues F.[5], Francesko A.[5], Fernandes M.M.[1,3]
[1]Center for Micro-Electro Mechanical Systems (CMEMS), University of Minho, Campus Azurém, Guimarães; [2]Centre of Molecular and Environmental Biology, Dept. of Biology, University of Minho, Campus de Gualtar, Braga; [3]LABBELS-Associate Laboratory in Biotechnology and Bioengineering and Microelectromechanical Systems, University of Minho, Braga; [4]Centre of Biological Engineering, University of Minho, Campus Gualtar, Braga; [5]RypLabs Portugal, Unipessoal Lda, Famalicão, Portugal

Introduction

The increasing restrictions on chemical fungicides and the need for sustainable agricultural practices have intensified the search for environmentally friendly biocontrol strategies. Antagonistic microorganisms, particularly yeasts, represent promising alternatives; however, their practical application is often limited by low environmental stability and reduced viability[1,2]. Encapsulation within natural polymeric biomaterials offers a sustainable approach to enhance microbial performance.

Materials and Methods

The antagonistic activity of *W. anomalus* was assessed in vitro using dual culture and double-plate chamber assays to evaluate contact-dependent and volatile-mediated mechanisms. Yeast cells were encapsulated in calcium alginate beads and chitosan-coated alginate beads via ionotropic gelation[3]. The resulting particles were physicochemically characterized (morphology, size, FTIR), and encapsulation efficiency was determined by CFU counting. Cell viability was evaluated using fluorescein diacetate staining. The antifungal activity of free and encapsulated yeast, as well as empty polymeric matrices, was assessed under hydrated and dried conditions through dual culture assays.

Results

W. anomalus exhibited a strong multimechanistic antagonistic profile against *B. cinerea*, achieving partial inhibition in dual culture assays and up to 100% inhibition under pre-colonization conditions, while volatile compounds contributed to ~47.5% inhibition. Encapsulation efficiency was approximately 100%, confirming effective cell entrapment within alginate matrices[4]. Chitosan coating increased particle size and structural stability through polyelectrolyte complex formation without compromising cell viability. Fluorescence microscopy confirmed preserved metabolic activity of encapsulated cells. Antifungal performance was strongly dependent on hydration state: hydrated chitosan-coated beads exhibited consistent inhibitory effects, while dried particles showed no detectable activity. Chitosan matrices displayed intrinsic antifungal properties, which were enhanced by the presence of encapsulated yeast, resulting in a complementary inhibitory effect.

Conclusion

This study demonstrates that alginate and chitosan-based systems, as natural and sustainable polymeric biomaterials, are effective carriers for *W. anomalus*, ensuring high encapsulation efficiency, preserved viability, and sustained antifungal activity under hydrated conditions. The synergistic interaction between chitosan's intrinsic antimicrobial properties and yeast antagonism highlights the potential of these bio-based materials as environmentally friendly and circular solutions for biological control of plant pathogens.

Acknowledgements

This work was financed by EU Project VINNY (101130039). The authors thank FCT - Fundação para a Ciência e Tecnologia for its financial support in the framework of the Strategic Funding: UID/04436/2025 (doi.org/10.54499/UID/04436/2025|) and for the Project Physiplant (https://doi.org/10.54499/2023.18539.ICDT). Fernandes M.P. would like to acknowledge the FCT for its individual grant (2025.05782.BDANA).

References

[1]Freimoser F.M., Rueda-Mejia M.P., Tilocca B., Migheli Q. Biocontrol yeasts: mechanisms and applications. *World Journal of Microbiology and Biotechnology* 2019; 35; 154–166.
[2]Kowalska J., Tyburski J., Matysiak K., Jakubowska M. Biocontrol agents in sustainable agriculture. *Agriculture* 2022; 12; 1–15.
[3]Balla A., Silini A., Cherif-Silini H. et al. Encapsulation techniques of plant growth-promoting microorganisms. *Applied Sciences* 2022; 12; 9020–9035.
[4]Santos S.S., Machado R. Chitosan-coated alginate beads for yeast encapsulation. *Journal of the Science of Food and Agriculture* 2021; 101; 1–10.

D3 – P082

Injectability evaluation of hyaluronan-based hydrogels functionalized with boronic acid

Korsulainen B.[1], Parihar V.S.[1], Kroon M.[1], Priimagi A.[2], Kellomäki M.[1]
[1]Faculty of Medicine and Health Technology, Tampere University; [2]Faculty of Engineering and Natural Sciences, Tampere University, Finland

Introduction

Injectability is a key property of precursors and hydrogels determining their potential applications, such as minimally invasive material implantation or organ-on-chip models. Injectability can be modulated, *e.g.*, by tailoring intermolecular interactions occurring in the material. Injectability is often examined manually resulting in poor repeatability or limited comparability. However, effects of chemical interactions, such as boronate ester formation, on the material injectability have received less attention, despite their impact on material behavior and injectability. Therefore, hyaluronan (HA) combined with phenylboronic acid is a fascinating approach for injectable materials.

Materials and Methods

Hyaluronic acid was functionalized with methacrylate (MA) and/or 3-aminophenylboronic acid (APBA) to form HAMA, HA–APBA and HAMA–APBA with degree of substitution being 30 % for MA, 17 % for APBA in HA–APBA, and 8 % for APBA in HAMA–APBA. Rheology was utilized to study shear-thinning properties of the polymer precursor, and mechanical strength of hydrogels. A mechanical tester was employed to evaluate the injectability of the precursors through small nozzles. All measurements were conducted in neutral pH 7 and mildly basic pH 8.

Results and Conclusions

Figure 1 illustrates how pH-responsiveness affects the shear-thinning behavior of three material compositions. Notably, HA–APBA:HAMA 1:1 blend at pH 8 showed remarkably increased viscosity and shear-thinning behavior in comparison to neutral pH 7. This reflects the enhanced formation of weak dynamic interactions, primarily boronate ester formation. Methacrylate is known to inhibit shear-thinning, which can be seen in unchanged behavior of HAMA under studied pH's and shear stresses. HAMA–APBA have double the MA and only half of the APBA content compared to the blend, which explains its moderate behavior between these three studied compositions.

Figure 2 shows the impact of weak interactions on injectability. Increased interactions at mildly basic pH 8 result in smoother, continuous flow for HAMA–APBA and the blend, whereas flow behavior of HAMA, with no interactive moieties in the polymer chain, is independent of pH. Required injection force at pH 7 varied between 5 and 7.5 N for all materials. Instead, pH 8 increased the injection force for HAMA–APBA up to 20.5 N for the highest injection speed measured, whereas for the blend the increase was minimal. This difference highlights how shear-thinning affect the injection force. Non-shear-thinning material directly increases the force due to increased interactions, while shear-thinning character of material compensates the change in interactions with the dynamic nature of increased weak interactions.

Acknowledgements

We acknowledge the financial support of the Finnish Ministry of Education and Culture through the PREIN/I-DEEP doctoral pilot (VN/3137/2024-OKM-4) and The Centre of Excellence in Body-on-Chip Research (CoEBoC) by the Research Council of Finland (decision no. 336663). A.P. acknowledges the European Research Council (Consolidator Grant project MULTIMODAL, no. 101045223) and the Research Council of Finland (Center of Excellence LIBER, no. 346107; Flagship Programme PREIN, no. 320165) for financial support.




Figure 1 Summary of rheological results. A and B represent flow sweeps, and C and D frequency sweeps for HAMA (grey), HAMA–APBA (pink), and HA–APBA:HAMA 1:1 blend (orange) at pH 7 and 8, respectively. In C and D, filled symbols represent storage moduli, G' and open symbols loss moduli, G''.




Figure 2 A visual illustration of the injectability tests. a) HAMA, b) HAMA–APBA, and c) HA–APBA:HAMA 1:1 blend at neutral and mildly basic pH with 300 and 500 mm/s injection speeds. Black circles highlight the difference in flow behavior between neutral and mildly basic pH.

D3 – P083

CD44-targeted nitric oxide–releasing hyaluronic acid for antifibrotic reprogramming in dermal fibrosis

Abdo A., Pandit A.
CÚRAM, Research Ireland Centre for Medical Devices, University of Galway, Ireland

Introduction

Dermal fibrosis is sustained by transforming growth factor beta (TGF-β)-driven myofibroblast differentiation, excessive collagen deposition, and a pathologic matrix metalloproteinases (MMPs)/tissue inhibitors of MMPs (TIMP) remodeling balance.[1,2] Nitric oxide (NO) can counter-regulate profibrotic programs via NO–soluble guanylate cyclase (sGC)–cyclic guanosine monophosphate (cGMP)/ cGMP-dependent protein kinase G (PKG) interference with TGF-β/Smad signaling,[3] but translation is limited by short half-life and off-target exposure. Our aim was to engineer NO-releasing hyaluronic acid (HA-SNO) designed to localize NO to $CD44^+$ fibrotic skin targeting a controlled inhibition of TGF-β mediated activation of dermal fibroblasts.

Materials and Methods

Sodium HA (10 or 700 kDa) was functionalized with cysteine ethyl ester (EDC/NHS, pH 6) and nitrosated ($NaNO_2$/HCl, 5 °C) to form S-nitrosothiol HA (HA-SNO). Degree of substitution was quantified by ^{1}H NMR and confirmed by FTIR confirmation. NO release in PBS (37 °C) was quantified by NO-specific detection (electrochemical/chemiluminescence) and by Griess assay following irradiation at 365 nm. Human dermal fibroblasts were activated with TGF-β1 and treated with soluble NO donors (DETA-NO; SNP) to benchmark cytocompatibility (metabolic assay) and antifibrotic signaling (alpha smooth muscle actin immunoblot). In addition, the influence of HA-SNO on TGF-β1- activated fibroblasts was evaluated by collagen I quantification, MMP/TIMP expression, and migration/wound closure, with CD44-dependence assessed by receptor blockade.

Results

^{1}H NMR confirmed HA-cysteine substitution of 24% (10 kDa) and 60% (700 kDa); after nitrosation, HA-SNO substitution was 24% (10 kDa) and 41% (700 kDa) **(Fig. 1A,B)**. HA-SNO displayed tunable, light-responsive NO release; 700 kDa HA-SNO showed a higher early NO signal than 10 kDa (electrode output ~0.39 vs ~0.31 V after 5 min at 365 nm) **(Fig. 1C)**. In fibroblasts, DETA-NO remained cytocompatible up to 500 µM (≥80% metabolic activity at 72 h), whereas SNP was cytotoxic at ≥200 µM (≤35% at 24 h). In TGF-β1–activated fibroblasts, concurrent NO exposure signficantly reduced α-SMA expression versus TGF-β1 alone, with different levels according to the concentration of the NO-donor and period of irradiation.

Conclusion

NO-releasing HA provides a modular biomaterial that couples HA-mediated targeting with controllable NO delivery to suppress TGF-β-driven dermal fibrotic activation. Ongoing studies will quantify sustained NO flux under physiological conditions and confirm downstream effects on collagen deposition and MMP/TIMP remodeling in advanced dermal fibrosis models (ex vivo and in vivo).

Acknowledgements

Supported by Research Ireland (13/RC/2073_P2) and the Irish Research Council (GOIPD/2023/1640).

References

[1]Alsharabasy A., Pandit A. Protocol for in vitro skin fibrosis model to screen the biological effects of antifibrotic compounds. *STAR Protoc;* 2021; *2*; 100387.
[2]Wang Y., Jiao L., Qiang C., Chen C., Shen Z., Ding F., Lv L., Zhu T., Lu Y., Cui X. The role of matrix metalloproteinase 9 in fibrosis diseases and its molecular mechanisms. *Biomed. Pharmacother* 2024; *171*; 116116.
[3]Gong K., Xing D., Li P., Hilgers R.H., Hage F.G., Oparil S., Chen Y. CGMP inhibits TGF-β signaling by sequestering Smad3 with cytosolic B2-tubulin in pulmonary artery smooth muscle cells. *Mol. Endocrinol.* 2011; *25* (10); 1794–1803.




Figure 1. (A) ^{1}H NMR spectra of 10 kDa HA, HA–cysteine ethyl ester conjugate, and the corresponding S-nitrosylated conjugate. **(B)** ^{1}H NMR spectra of 700 kDa HA, HA–cysteine ethyl ester conjugate, and the corresponding S-nitrosylated conjugate. **(C)** Amperometric detection of NO release from S-nitrosylated HA (10 kDa, left; 700 kDa, right) before and after UV irradiation (365 nm) for 5, 15, and 30 min. Data represent the mean of five independent measurements per condition.

D3 – P084

Resorbable polycarbonate-based NIPUs (non-isocyanate polyurethanes) as platform technology for innovative medical textile implants

Flock H.[1], Wienen D.[1], Herfurth C.[2], Bohrisch J.[2], Gries T.[1]
[1]Institut fuer Textiltechnik (ITA), RWTH Aachen University; [2]Fraunhofer-Institut fuer Angewandte Polymerforschung (IAP), Potsdam, Germany

Introduction

Elastic filaments are relevant for textile implants to safeguard the surrounding tissue from injury. Thermoplastic polyurethanes (TPUs) show great promise for this purpose; however, their synthesis relies on diisocyanates that are hazardous to health and therefore subject to usage restrictions. Moreover, the high reactivity of isocyanates can lead to variability in product quality. Isocyanate-free polyurethanes (NIPUs) represent an innovative material option for medical applications, but are not yet commercially available or have been extensively studied for these applications.

Materials and Methods

The research focuses on the investigation of NIPUs for medical applications. This involves screening of synthesis conditions and evaluating polymer properties. Biocompatibility regarding cytotoxicity is also examined. Selected NIPUs with suitable molecular weights undergo initial microextrusion trials and promising NIPUs are further processed into textile monofilaments using advanced melt spinning technology. The filaments are mechanically analysed (e.g., fineness, tensile tests) and morphologically assessed (e.g., reflected light, scanning electron microscopy). For NIPU monofilaments, a minimum fineness-related tensile strength of ≥10 cN/tex (diameter ≤250 µm) was set for warp-knitting of mesh-prototypes. Additionally, filaments undergo final in vitro degradation studies (pH 7.4, 37 °C, 60 days) and are evaluated through morphological and mechanical analyses, also screening the degradation products.

Results

Suitable components were chosen, used for the synthesis of initial polyether-, polyester- and polycarbonate-based NIPUs. Non-resorbable polyether-NIPUs and resorbable polycarbonate-NIPUs reached suitable molecular weights, whereas polyester-NIPUs presented very low molecular weights and were not further investigated. While monofilaments from polyether-NIPUs examined did not yet meet the requirements (<10 cN/tex), initially produced monofilaments from resorbable polycarbonate-NIPUs met the mechanical requirements (d ~250 µm, 12.17±0.4 cN/tex, draw ratio 5.6). Consequently, the focus has shifted to the further investigation of resorbable polycarbonate-based NIPUs and additional studies are ongoing (as of March 2026).

Conclusion

Polycarbonate-based NIPUs enable the production of resorbable fibres as a promising platform technology for innovative medical textiles and implants. Further research will focus on further improvement of produced fibre properties, investigating degradation behaviour and products as well as textile processing into mesh-prototypes.

Acknowledgements

We thank the German Federal Ministry for Economic Affairs and Energy for funding (01IF23028 N1).

D3 – P085

A versatile air-assisted spraying platform for high-throughput fabrication of structurally robust microgels

de Lapeyrière M., Viola M., Maniura K., Rottmar M.
Biointerfaces laboratory, Empa, Swiss Federal Laboratories for Materials Science and Technology, St. Gallen, Switzerland

Introduction

Microgels are highly modular building blocks with tunable size, morphology and polymer composition that can also be readily functionalized or used to encapsulate therapeutic agents, cells etc.... Achieving high-throughput fabrication of spherical microgels is an ongoing challenge. Air-assisted spraying (AAS) is a method that can be employed to generate a large quantity of spherical microgels by spraying a rapidly gelling polymer into a gelling bath. For this method to be used with gelatin-based polymers, alginate was incorporated as a sacrificial polymer to enable instant ionotropic gelation upon contact with a $CaCl_2$ bath. It was observed that the polymer diffused out of the newly formed microgels, into the gelling bath, without immediate cross-linking of the gelatin-based with UV radiation.

Materials and Methods

Blended polymer microgels are fabricated by ASS a solution of alginate, photoinitiator (either Irgacure 2959 or lithium phenyl-2,4,6-trimethylbenzoylphosphinate) and gelatin-based polymer (methacrylic acid gelatin (GelMA), allyl modified gelatin (GelAGE) and cold fish gelatin (cfGel)) into a CaCl2 bath to achieve rapid gelation of alginate. The gelatin-based polymer is cross-linked through UV exposure. Alginate is subsequently removed upon immersion in 1M NaCl for 24h.

Results




Fig. 1: Brightfield and CLSM images of GelMA-Rhodamine (red) and alginate microgels with and without direct UV exposure while spraying, before and after alginate removal.

ASS allows for fabrication of spherical microgels with uniform size distribution of 20 to 79 µm. Direct UV exposure during spraying was found to be necessary to avoid diffusion of the polymer out of the alginate network and maintain microgel stability after alginate removal. Indeed, it was found that the microgel concentration drops after alginate removal, without direct UV exposure (Fig. 2). This ASS with direct UV exposure technique allows for rapid fabrication of mono-polymer microgels.




Fig. 2: Microgel concentration after alginate removal normalized to concentration right after fabrication. In gray, indication of the drop in concentration after alginate removal.

Conclusion

ASS combined with in situ UV crosslinking demonstrates strong potential as a universal technique for rapid microgel fabrication. Next steps will focus on assembling these microgels into macroporous granular scaffolds.

D3 – P086

Reversible photocrosslinking polymers: New materials with tunable refractive indices for reconfigurable intraocular lenses

Malette N.[1], Fortier A.[1], Estrada A.[1], Singh H.[1], Zeng M.[1], Saravanamuttu K.[1], Sheardown H.[2], Vargas-Baca I.[1]
[1]Chemistry and Chemical Biology, McMaster University; [2]Chemical Engineering, McMaster University, Hamilton, Canada

Introduction

Cataract formation is one of the most common age-related eye conditions in the world, with the most prevalent treatment involving the replacement of the cloudy lens with an intraocular lens (IOL). IOL implantation is among the most successful procedures involving a biomaterial, however, many risks still exist, namely the need for multiple surgeries due to changes in vision over time.

Aim

The current work is focused on the development of a photoresponsive IOL that can be reconfigured (rIOL) following implantation. The ability to adjust the lens power non-invasively via benign near infrared light would allow for better outcomes, enhancing quality of life for those affected.

Materials and Methods

Chromophore-functionalized acrylates, methacrylates, and acrylamides were reacted with methyl methacrylate (MMA) via reversible addition fragmentation chain transfer polymerization to produce MMA-anthracene and MMA-coumarin copolymers with photoresponsive pendant groups. Copolymer samples prepared in dichloromethane (DCM) were irradiated with 365 nm UV light and their absorbance spectra were obtained at various time points using UV-visible spectroscopy. *In vitro* tests were performed on a spontaneously immortalized fetal human lens epithelial cell line (FHL124). Cells were treated with Minimum Essential Medium Alpha conditioned with PMMA and MMA-coumarin materials at a concentration of 7.5 or 10 mg/mL for 24 hours. Live/Dead and MTT assays were carried out following the treatment period.

Results

Number average molecular weight (M_n) and polydispersity index (PDI) values of 13.1 kDa and 1.35, respectively, were determined via gel permeation chromatography for a synthesized copolymer of MMA and 4-(anthracene-9-yl)butyl acrylate. Similarly, a copolymer of MMA and *N*-(7-(diethylamino)-2-oxo-2*H*-chromen-3-yl)acrylamide was synthesized with a M_n of 12.3 kDa and a PDI 1.38. A reduction in characteristic absorbance peaks was observed for both copolymers following irradiation with UV light. Absorbance decreased by ~60% for the MMA-anthracene and MMA-coumarin copolymers after 45 and 15 minutes, respectively, suggesting the crosslinking of pendant chromophore groups. *In vitro* test results for additional MMA-coumarin copolymers revealed that materials prepared in acetone with a MMA:chromophore ratio of 90:10 showed 57-80% cell viability after 24 hours, while materials prepared in DCM with a MMA:chromophore ratio of 75:25 showed 61-85% cell viability after 24 hours.

Conclusion

Materials containing photoresponsive pendant groups have been synthesized and can undergo photoinduced crosslinking in solution. *In vitro* test results display broad % cell viability ranges, with some materials performing better than others.

Acknowledgements

We thank McMaster University and the Natural Sciences and Engineering Research Council of Canada for funding.

D3 – P087

Ultra-high-molecular weight PEG bottlebrush polymers up to 22 × 10^6 Da via rapid RAFT polymerization and chromatography-free fractionation

Chen M.[1,2], Bulatova J. [1,2], Sizovs A.[1,2]
[1]Laboratory of Pharmaceutical Pharmacology, Latvian Institute of Organic Synthesis, Riga; [2]Baltic Biomaterials Centre of Excellence, Headquarters at Riga Technical University, Latvia

Introduction

Polyethylene glycol (PEG) bottlebrush polymers consist of densely grafted PEG side chains tethered to a polymer backbone, forming hydrated brush architectures with well-established protein-repellent, lubricating, and biointerfacial properties. Access to the ultra-high molecular weight (UHMW, >10^6 Da) regime is expected to enhance these characteristics through brush-mediated interfacial effects. However, steric congestion inherent to grafting-through polymerization restricts chain propagation and limits access to UHMW architectures. Reversible addition-fragmentation chain-transfer (RAFT) polymerization offers metal-free, functional group-tolerant conditions and broad monomer compatibility, yet reports of UHMW PEG bottlebrush polymers prepared by RAFT remain scarce. Furthermore, inherent broad polydispersity in HMW and UHMW bottlebrush systems complicates precise tuning of the desired properties and limits their reproducibility, making effective post-synthetic fractionation essential.

Materials and Methods

PEG bottlebrush polymers were polymerized via RAFT grafting-through using an optimized initiator/chain-transfer agent (CTA) system across a broad range of monomer-to-CTA feed ratios. Reactions were conducted on gram scale and reached completion within 1.5-2.5h. The resulting polymers were characterized by ^{1}H NMR spectroscopy and size-exclusion chromatography coupled with static light scattering (SEC-SLS). A chromatography-free fractionation strategy exploiting selective gelation in a binary solvent system was developed. Cloud-point mapping was performed using narrowly dispersed PEG bottlebrush polymer standards to construct a Flory–Huggins guided precipitation boundary equation.

Results and Discussion

Rapid RAFT polymerization at the highest [M]:[CTA] = 10000 yielded PEG bottlebrush polymers with M_n > 9 × 10^6 Da and M_w > 14 × 10^6 Da, representing a notable benchmark for controlled radical polymerization. Strong correlations between NMR-derived and SEC-SLS molecular weights confirmed effective RAFT control across the investigated feed ratio range. Selective gelation fractionation applied to three parent batches (M_n = 1.1, 5.3, and 9.5 × 10^6 Da) reduced dispersity from PDI 1.3-1.7 to 1.1-1.2 with mass recoveries of 66–88%. Fractionation of the M_n = 9.5 × 10^6 Da parent batch yielded fractions with narrower distributions and the 'heaviest' fraction with M_n = 22.1 × 10^6 Da. Guided by Flory–Huggins solution theory, cloud-point mapping yielded an empirical equation describing the precipitation boundary: $W_{GS} = 0.340 + 0.0141 \ln(S) + 0.0148 \ln(M_n)$, where W_{GS} is the good solvent weight fraction at cloud point, S is the polymer weight fraction, and M_n is in units of 10^6 Da.

Conclusion

This work establishes a scalable platform combining rapid RAFT polymerization with chromatography-free selective-gelation fractionation for the precision preparation of narrowly dispersed UHMW PEG bottlebrush polymers, reaching molecular weights up to 22 × 10^6 Da. These results substantially extend the accessible molecular-weight range in this system and provide a robust platform for systematically exploring structure-property relationships of well-defined PEG brush architectures in biomedical and material applications.

D3 – P088

Reversible photoactive coumarin-based networks with tunable properties for extrusion 3D printing and adhesive uses

Vandeputte H.[1], Parys A.[1], Houck H.[2], Van Vlierberghe S.[1]
[1]Polymer Chemistry and Biomaterials Group (PBM), Center of Macromolecular Chemistry (CMaC), Dept. of Organic and Macromolecular Chemistry, Ghent University, Belgium; [2]Photochemistry for Materials team, Dept. of Chemistry, University of Warwick, Coventry, UK

Introduction

Coumarin plays an important role in photo-reversible chemistry due to its ability to form and break stable covalent bonds, via a reversible [2+2] cyclization reaction, upon irradiation with 365 nm ultraviolet (UV) or 254 nm light, respectively. In addition to being reversible, the coumarin dimerization and cleavage can be carried out without solvents, initiators, or catalysts, offering a more sustainable, biocompatible, and low-cost way to create and recycle polymeric networks.

Materials and Methods

In this study, a multi-arm poly(ethylene glycol) (PEG) backbone was functionalized with a coumarin derivative using an isophorone diisocyanate (IPDI) linker, creating a coumarin-endcapped urethane-based PEG (CUP). The kinetic behavior of the reversible [2+2] cyclization reaction was investigated via UV-Vis measurements on spin-coated material. The material properties were determined using rheology, thermo-gravimetric analysis (TGA), differential scanning calorimetry (DSC), swelling tests, and contact angle measurements. The cytotoxicity of the crosslinked material was assessed using MTS and live/dead assays using Human Foreskin Fibroblasts, and its printability was examined via rheology. Finally, the material was used for 3D-printing applications using extrusion printing and as a photo-adhesive.

Results

The kinetics can be described by a two-phase exponential decay curve, with a “fast” and a “slow” reaction phase. A maximum dimer conversion of 94.2% was achieved (365 nm; 25 mW/cm^2), followed by a recovery of 72.5% of the monomer after irradiation at 100-290 nm (10 mW/cm^2) (Figure 1, A). This study also investigates the role of benzophenone as a photosensitizer and identifies its effect during the early stages of dimerization. Rheology shows an optimal gel point of 214 seconds using 25 mol% benzophenone. TGA indicates a high thermal stability above 250°C, and DSC shows a double melting peak accompanied by a lower melting enthalpy (ΔH_m = 10.43 J/g). The swelling test indicates limited swelling of 73 ± 5% in PBS (37 °C) due to its hydrophobic nature, which is supported by a static contact angle of 81.9 ± 1.8°. The biocompatibility assessments indicate a highly biocompatible material according to ISO 10993 (cell viability >70%). Finally, processing was performed via extrusion-based 3D printing, resulting in prints with a resolution of 400 µm (Figure 1, B and C) and as a photo-adhesive, yielding strong (E' = 205 ± 15 kPa; σ_{max} = 552 ± 34 kPa), on-demand, cleavable materials.

Acknowledgements

Funded by Ghent University Special Research Fund-BOF (grant number 01G02722) and by the European Union (DAEDALUS project, GA n. 101178568).




Figure 4: A) Plot showing % monomer left as a function of 365 nm irradiation time (min) of the dimerization reaction without (•) and with benzophenone (▲). B) Extrusion printed honeycomb structure with a filling degree of 25%. C) Extrusion printed wave pattern with a filling degree of 42%.

D3 – P089
Characterisation of hybrid implants made from titanium and magnesium

Haramus V., Limberg W., Willumeit-Römer R.
Helmholtz Zentrum Hereon, Geesthacht, Germany

The presence of degradable and permanent parts within an implant offers the opportunity to develop novel therapies and improved implant functionality. The stable titanium (Ti) and biodegradable magnesium (Mg) are attractive choices for such hybrid material. Ti is a well-known implant material due to its high strength and biocompatibility, while Mg has mechanical properties similar to bone, degrades in the body, and stimulates several biological functions, for example, bone formation. Thus, the aim of this study is to get information on the interaction between these strongly different metals during implant application.

Hydrogen evolution experiments showed rapid degradation of Mg by direct contact of Mg and Ti [1]. We have applied plasma electrolyte oxidation coating to moderate this rapid Mg degradation [2]. The mechanical tests, chemical composition determination, electron microscopy, X-ray diffraction, neutron and X-ray diffraction imaging were applied for the characterisation of the hybrid Ti-Mg implant system. Hydrogen released due to Mg degradation ingresses into the Ti part and could lead to embrittlement if not properly controlled. The distribution of hydrogen in the Ti part has been visualized on macroscopic and microscopic length scales [3, 4]. The results of the presented investigations will be used for further development of hybrid Mg-Ti implants, facilitating the simultaneous application of completely different properties.

References:

[1]Garamus V.M., Limberg W., Serdechnova M., Mei D., Lamaka S.V., Ebel T., Willumeit-Römer R. Metals 2021; 11; 527.
[2]Fazel M., Garamus V.M., Serdechnova M., Wilde F., Wieland F., Nidadavolu E.P.S., Wu T., Ebel T., Blawert C., Willumeit-Römer R., Zheludkevich M.L. Journal of Magnesium and Alloys 2024; 12; 3142-3158.
[3]Kumar R., Solis Dias C., Trtik P., Limberg W., Wieland D.C.F, Moosmann J.P., Serdechnova M., Blawert C., Ebel T., Willumeit-Römer R., Garamus V.M. RSC Advances 2025; 15; 4472-4480.
[4]Garamus V.M., Wieland D.C.F., Moosmann J., Beckmann F., Lottermoser L., Serdechnova M., Blawert C., Fazel M., Nidadavolu E.P.S., Limberg W., Ebel T., Willumeit-Römer R., Zeller-Plumhoff B. Journal of Composites Science 2025; 9; 396; 1-15.

D3 – P090

Electrospun wheat gluten fibrous scaffolds for meat analog cultivation applications

Gasiulyte E.[1], Pauliukaityte I.[1,2], Krugly E.[1], Ciuzas D.[1]
[1]Faculty of Chemical Technology, Kaunas University of Technology; [2]Food Institute, Kaunas university of Technology, Lithuania

Introduction

The increasing global demand for meat raises significant environmental, ethical, and food safety concerns, driving growing interest in cultivated meat technologies[1]. However, the development of structured *in vitro* meat analogues requires biomaterials capable of mimicking the native fibrous architecture of skeletal muscle. An ideal three-dimensional (3D) scaffold should replicate key structural features of the extracellular matrix (ECM) while complying with sustainability and food safety principles associated with cultivated meat systems. Plant-derived proteins are considered promising raw materials for such scaffolds. Nevertheless, due to their complex molecular structure, not all plant proteins are readily processable by electrospinning[2]. Wheat gluten, a plant-based viscoelastic protein composed of gliadin and glutenin fractions, exhibits network-forming ability and molecular entanglement that are favourable for fiber formation[3]. In addition, wheat gluten-based materials have demonstrated good biocompatibility and mechanical performance compared to other plant proteins, highlighting their potential as structural protein matrices[4].

Materials and Methods

Microfibrous wheat gluten scaffolds intended for muscle tissue cultivation were fabricated via solution electrospinning. Solutions for electrospinning were prepared by dissolving wheat gluten powder in different ratios of acidified water and ethanol or acetic acid and ethanol (Table 1). To achieve suitable electrical and rheological properties and ensure stable fiber formation, glucose (10%), glycerol (7%), and poly(ethylene oxide) (0.3%) were incorporated into the formulations. Prior to electrospinning, solution electrical conductivity, viscosity, and surface tension were measured (Table 1). The morphology of the resulting wheat gluten fibrous scaffolds was characterized using SEM.

Results

The results demonstrated that solvent composition significantly influenced solution conductivity, rheological behaviour, and electrospinning stability (Table 1 and Fig. 1). Depending on the solvent system, fiber formation ranged from droplet formation and beaded fibers to continuous microfibers. SEM analysis confirmed the formation of microfibrous scaffolds with average fiber diameters ranging from 1.66 ± 0.28 µm to 3.64 ± 0.61 µm, depending on solution composition. The results indicate a clear relationship between solvent ratio, solution properties, and microfiber morphology.

Conclusion

The study demonstrates that edible wheat gluten-based microfibrous scaffolds can be successfully fabricated via electrospinning using food-compatible solvent systems. Control of solvent composition enables regulation of solution behaviour during electrospinning and directly affects microfiber morphology and diameter. These results prove that food-grade electrospinning systems can be used as structural protein scaffolds for meat cultivation applications.

Acknowledgements

This study was supported by Research Council of Lithuania “Edible Fibrous Polymer Scaffolds For Meat Cultivation" (Grant No. S-MIP-25-61).

References

[1]Coderoni S., Casolani N., Chiodo E., Laudicina G., Perito M.A. Perspectives on cultured and traditional meat: An analysis of Italian consumers. *Journal of International Food & Agribusiness Marketing* 2025; 37(5); 888-907.
[2]Zdraveva E., Srcek V.G., Kraljic K., Skevin D., Slivac I., Obranovic M. Agro-Industrial Plant Proteins in Electrospun Materials for Biomedical Application. *Polymers* 2023; 15(12); 2684.
[3]Delcour J.A., Joye I.J., Pareyt B., Lagrain B. Wheat Gluten Functionality as a Quality Determinant in Cereal-Based Food Products. *Annual Review of Food Science and Technology* 2012; 3; 469-92.
[4]Wang L., Li G., Li X., Zhang Y., Liu G., Xie M., Zheng Z., Wang X., Chen Y., Kaplan D.L. Emerging Materials in Cultivated Meat: Engineering Sustainable Food Solutions – A Review. *Advanced Functional Materials* 2025; 35; 2413316.

Table 1. Effect of solvent composition (water/ethanol and acetic acid (AA)/ethanol) on the properties of wheat gluten electrospinning solutions and resulting microfiber morphology.

Sample code	Solvent ratio			Solution electrical conductivity, mS/cm	Solution viscosity, mPa s	Solution surface tension, mN/m	Spinnability	Mean fiber diameter, μm
	AA	H_2O	EtOH					
S1	0.5 ml *	1	9	145 ± 0.2	52 ± 2.2	22 ± 0.1	No fibers formation	–
S2	0.5 ml *	3	7	531 ± 0.1	1584 ± 22.8	34 ± 0.2	Continuous fibers	2.9 ± 0.3
S3	0.5 ml *	5	5	691 ± 0.2	40 ± 0.8	40 ± 0.6	Ribbon-like fibers	3.6 ± 0.6
S4	1	-	9	132 ± 0.1	84 ± 28.1	22 ± 0.0	No fibers formation	–
S5	3	-	7	218 ± 0.2	359 ± 53.9	26 ± 0.1	Beaded fibers	1.7 ± 0.3
S6	5	-	5	216 ± 0.1	1352 ± 28.1	36 ± 0.2	Continuous fibers	2.0 ± 0.2

* – due to acidification of the solution.




Fig. 1. SEM image of electrospun wheat gluten scaffold produced from sample S2.

D3 – P091

Influence of fabrication parameters on the structural stability of chitosan–hydroxyapatite scaffolds for bone regeneration

Zeideryte J., Vernickaite E., Tomkute-Luksiene D.
Research and development Dept. TRATE, UAB, Kaunas, Lithuania

Introduction

Bone defects in oral and maxillofacial surgery remain a major challenge, particularly in alveolar ridge preservation, periodontal regeneration, and implant site development. Chitosan–hydroxyapatite composite scaffolds have gained increasing attention as potential alternatives to conventional grafting materials due to their biocompatibility, biodegradability, and osteoconductive properties. However, scaffold fabrication parameters critically influence structural stability under physiological conditions, which is essential for maintaining space and supporting early bone formation [1, 2].

Aim

To optimize fabrication parameters of chitosan–hydroxyapatite scaffolds and assess their effect on structural stability under physiological conditions.

Materials and Methods

Chitosan solutions were prepared in dilute acidic media using acetic acid or an ascorbic acid–based solvent system, followed by controlled neutralization prior to hydroxyapatite incorporation. The resulting mixtures were freeze-dried to obtain porous scaffolds and subsequently crosslinked to enhance structural stability.
The obtained materials were characterized using scanning electron microscopy-energy dispersive X-ray spectroscopy, Fourier-transform infrared spectroscopy, and simultaneous thermal analysis.

Results

Preliminary observations suggest that neutralization prior to lyophilization ensures more uniform acid removal, compared with scaffold immersion, contributing to improved structural stability during incubation. Scaffolds fabricated using ascorbic acid exhibited discoloration and reduced stability at 37°C, while samples prepared in acetic acid demonstrated greater resistance to structural collapse in phosphate-buffered saline. Microscopic evaluation revealed the formation of a porous scaffold architecture characteristic of freeze-dried polymer matrices. Elemental analysis confirmed the presence of calcium and phosphorus within the composite structure, indicating successful incorporation of hydroxyapatite. Spectroscopic analysis suggested the preservation of characteristic functional groups associated with both chitosan and hydroxyapatite, supporting the formation of a composite material.

Conclusion

The present study highlights the critical role of formulation and processing parameters in determining the structural performance of chitosan–hydroxyapatite composite scaffolds. Future research will focus on investigating their biological activity and biodegradation behavior in order to further evaluate their suitability for regenerative applications.

Acknowledgements

Research is partially financed by the European Regional Development Fund (Project No. 02-048-K-0011).

References

[1]Alavi S.E., Alavi Z., Gholami M. et al. Biocomposite-based strategies for dental bone regeneration. *International Journal of Biological Macromolecules* 2023; 248; 125876–125876.
[2]Piszko P.J., Piszko A., Kiryk S. et al. Bone regeneration capabilities of scaffolds containing chitosan and nanometric hydroxyapatite: A systematic review based on in vivo examinations. *Biomimetics* 2024; 9; 503–503.

D3 – P092

Design and characterization of alginate/hydroxyapatite composites for bone scaffold application

Vernickaitė E.[1], Zeiderytė J.[1], Tomkutė-Lukšienė D.[1]
[1]Research and development Dept., TRATE, UAB, Kaunas, Lithuania

Introduction

Alginate is widely investigated in bone and dental tissue engineering due to its biocompatibility and controllable biodegradability. However, its high hydrophilicity, excessive swelling, and poor mechanical stability limit its use as a scaffold material. Combining alginate with hydroxyapatite (HA) improves mechanical and biological performance, while ion substitution in HA (Sr, Mg, Ag, Zn) can further enhance osteogenic and antibacterial properties[1].

Aim

This study aimed to optimize alginate/hydroxyapatite (ALG/HA) scaffold composition for bone tissue engineering.

Materials and Methods

ALG/HA scaffolds were prepared by dissolving sodium alginate in water, incorporating Sr-, Mg-, Ag-, and Zn-doped HA powders, and homogenizing the mixture before freeze-drying to obtain porous scaffolds. Morphology and elemental distribution were analyzed by scanning electron microscopy / energy dispersive spectroscopy technique, Fourier-transform infrared spectroscopy was used to study the functional groups of the scaffold. Degradability, porosity, and thermal stability were also evaluated.

Results

Alginate scaffolds were prepared using 1–4 wt% alginate solutions. The 1 wt% solution exhibited low viscosity, resulting in poor HA dispersion due to particle sedimentation and producing lamellar scaffolds with very low mechanical integrity. Increasing the alginate concentration to 3 wt% improved solution viscosity and scaffold stability, yielding a well-defined porous spongy architecture after freeze-drying. In contrast, 4 wt% alginate caused excessive viscosity, complicating processing and producing mechanically fragile lamellar structures. Therefore, 3 wt% alginate was selected for ALG/HA scaffolds containing up to 30 wt% Sr-, Mg-, Ag-, or Zn-doped HA. Surface area increased with HA-based material content; however, additions above 20 wt% reduced mechanical stability. Non-crosslinked scaffolds rapidly dissolved in PBS, whereas ionic crosslinking with $CaCl_2$ significantly enhanced scaffold stability through the formation of Ca^{2+}-mediated alginate networks. Scaffolds containing 3 wt% alginate and 10 wt% HA-based powder showed optimal durability and processability, whereas Zn-doped HA accelerated degradation compared with other doped materials.

Conclusion

Scaffolds composed of 3% ALG and 10% ion-doped HA demonstrate potential for bone tissue engineering, as their porous architecture and homogeneous HA distribution enhance structural stability and may promote cell proliferation and mineralization.

Acknowledgments

This work was supported by the European Regional Development Fund (Project No. 02-048-K-0011).

References

[1]Gupta S., Selvam S.P., Ramadoss R., Sundar S. Alginate-hydroxyapatite scaffolds: A comprehensive characterization study. Engineering: A Review. *Journal of Oral Biology and Craniofacial Research* 2025; 15(3); 555-562.

D3 – P093
Effective decellularisation of human bladder biomaterial

Desai A.[1], Varley C.[3], Roe J.[1, 2], Berry H.E.[1, 2], Southgate J.[3], Jennings L.M.[1]
[1]Institute of Medical and Biological Engineering, School of Mechanical Engineering, University of Leeds, UK:; [2]School of Biomedical Science, Faculty of Biological Sciences, University of Leeds, UK; [3]Jack Birch Unit for Molecular Carcinogenesis, Dept. of Biology, University of York, UK

Introduction
Neuropathic bladder often results in a small, stiff bladder that risks incontinence and kidney damage. Surgical augmentation with bowel can improve capacity but carries long-term complications[1]. A decellularised human bladder patch offers a promising augmentation material. Stretch-assisted decellularisation has been shown to be effective for the porcine bladder[2], but translation to human bladder tissue requires human-specific biomechanical data to redesign a human-specific stretch system for effective decellurisation.

Aim
To characterise the biomechanical properties of human bladder tissue and use these values to develop a stretching system to support decellularisation of human bladder biomaterial.

Materials and Methods
Uniaxial tensile failure strains were determined in longitudinal and circumferential directions for four human and six porcine bladder specimens. Scaling factors were calculated by comparing porcine and human failure strains, and these were used to adjust the porcine biaxial strain[2] targets to human specific values. These strain targets informed the design of the stretching system, and human bladders were subsequently halved and processed individually using the new system and the established decellularisation process.

Results
The resulting biaxial strain scaling factors were 1.24 longitudinally and 0.86 circumferentially. These values informed the design of 3D-printed stretching frames made from autoclavable polyamide, engineered to apply controlled biaxial strain and generate expanded matrices proportional to the original tissue size. The system was applied to human bladder halves in combination to our established decellularisation protocol. Its effectiveness was confirmed by the absence of cells, demonstrated by histology and quantitative DNA analysis.

Conclusion
A stretching system for effective decellurisation of human bladder tissue has been developed and applied using the derived strain ratios.

Acknowledgements
This work is supported by Kidney Research UK. We thank the donors and their families for providing the bladder tissue used in this study.

References
[1]Wezel F., Southgate J., Thomas D.F.M. Regenerative medicine in urology. *BJU International* 2011; 108; 1046–1065.
[2]Ward A., Morgante D., Fisher J., Ingham E., Southgate J. Translation of mechanical strain to a scalable biomanufacturing process for acellular matrix production from full-thickness porcine bladders*. Biomedical Materials* 2021; 16; 065023.

D3 – P094
MXene-based biomaterials for cardiac tissue regeneration

Diedkova K.[1,2], Truhins M.[2], Husak Y.[3], Baginskiy I.[1,4], Iatsunskyi I.[5], Zahorodna V.[4], Gogotsi O.[4,6], Pogorielov M.[1,2,6]
[1]University of Latvia, Riga, Latvia; [2]Biomedical Research Centre, Sumy State University, Ukraine; [3]Faculty of Chemistry, Silesian University of Technology, Gliwice, Poland; [4]Materials Research Centre, Kyiv, Ukraine; [5] NanoBioMedical Centre, Adam Mickiewicz University, Poznan, Poland; [6]NanoCarbonTech, Poznan, Poland

Introduction
The growing burden of cardiovascular diseases has stimulated intensive research into advanced biomaterials and tissue engineering approaches for myocardial regeneration[1]. In tissue engineering, the most promising biomaterial for the regeneration of conductive tissue is a three-dimensional electrospun scaffold due to their ability to mimic the fibrous architecture of the extracellular matrix and support cell attachment and organization. However, conventional polymeric scaffolds are typically electrically insulating and lack bioactive functionality. Since electrical conductivity is a fundamental property of cardiac tissue and essential for synchronized signal propagation, incorporating conductive nanomaterials into biomaterial scaffolds represents a promising strategy for tissue engineering. In particular, MXenes, a rapidly emerging family of two-dimensional transition metal carbides and nitrides, offer exceptional electrical conductivity and surface functionality, enabling the recreation of the native electrical microenvironment of the myocardium[2].

Aim
Therefore, this study aimed to develop a multifunctional electrospun 3D scaffold based on Polydioxanone (PDO) and Elastin, modified with Ta_4C_3 MXene, followed by an investigation of its structural and chemical properties and an evaluation of biological properties.

Materials and Methods
PDO/Elastin membranes were produced using the conventional electrospinning method, both with and without the addition of MXenes. The study evaluated the impact of architectural features and electroactive modification on cardiomyocyte viability, cytoskeletal organization, functional maturation, and the immune response to the biomaterial.

Results & Conclusions
Highly porous PDO/Elastin membranes with fiber diameters up to 1 μm and pore areas ranging from ≤0.3 to 1.5 μm² were fabricated and subsequently coated with MXenes. MXene incorporation significantly enhanced the mechanical stability and electrical conductivity of the scaffolds. Biological evaluation demonstrated that the PDO/Elastin-MXene composites are cytocompatible, support cardiomyocyte proliferation, and provide a large active surface for cell interaction, while improved conductivity facilitates intercellular communication. Overall, this conductive PDO/Elastin-MXene scaffold represents a promising strategy for the development of next-generation scaffolds for cardiac tissue regeneration.

Acknowledgements
This research was funded by Horizon Europe MSCA-2021-SE-01 project ESCULAPE (#101131147), Era.Net Anti-MicroMXene project and the "Latvian Post-doctoral" research project (No 1.1.1.9/LZP/1/24/142). The Ministry of Education and Science of Ukraine provided financial support research grants No 0126U000875.

References
[1]Gil-Cabrerizo P., Scacchetti I., Garbayo E., Blanco-Prieto M.J., Cardiac tissue engineering for myocardial infarction treatment, *Eur. J.Pharm. Sci*. 2023; 185; 106439.
[2]Alagarsamy K.N., Saleth L.R., Sekaran S. et al. MXenes as emerging materials to repair electroactive tissues and organs. *Bioact Mater* 2025; 48; 583-608.

D3 – P096
Multi-dimensional scaffold design for bone tissue engineering

Luzi G., Casadidio C., Censi R.
School of Pharmacy, University of Camerino, Italy

Introduction

Multidimensional bioprinting is an innovative technology that allows to design dynamic multi-material scaffolds based on “smart” stimuli-responsive materials to surpass the static nature of 3D bioprinted constructs. In our current design, time-varying characteristics are given by the thermo- and pH-sensitive shape-morphing polymer networks (PLGA, Col1) combined with biodynamic additives (nHAp, β-TCP, FGF-2) together with cellular co-cultures (pre-osteoblasts and endothelial cells). Additionally, we developed a novel triphasic design of chondrogenic, osteogenic, and angiogenic areas for improved biomimicking, ensuring a crosstalk between the phases while zonally regulate cells phenotype via the pre, in-action and post bioprinting biochemical, mechanical and physical stimuli exposure (Fig 1).

Aim

The first goal of our study is to efficiently treat osteosarcoma tumor and bone critical size defects, by controlling the lesion micro-environment. Secondly, we aim to create a reproducible, transversal and modular platform for molecules *in-situ* delivery.

Materials and Methods

The bioprinted scaffold functionality is characterized through an *in-silico* preliminary analysis (finite element analysis), a subsequent in-vitro assays (microscopy, markers, histology, gene analysis) and a final *in-vivo* ectopic insertion study in mouse models (Fig 2).

Results

Scaffold design was inspired by exploring existing physiology, architecture and biomimetic engineering literature. We came up with an osteon-like design, using the geometries which best resist and transmit stresses, while being easily bio printable and manageable for in-vitro maturation and analysis.
Subsequently, we gathered rheological data to select the best bioink for our applications, which ended up being PLGA 85:15 mixed with DMSO. This bioink can undergo physiological bone stresses (both in magnitude and frequency), show proper shape retention, while retain enough fluidity to be easily extruded.

Conclusion

This work provides a novel strategy for the preparation of dynamic multi-phasic scaffolds treating bone defects and tumors. Its modular design ensures application flexibility, better biomimicking and proper mechanical characteristics, allowing a broader tissue engineering application while unlocking new possibilities for drug, protein or gene delivery. Future work should focus on optimizing the bioink characteristics to increase *in-vivo* performance while trying different combinations of composite materials.



Figure 1. Triphasic scaffold CAD design




Figure 2. PLGA bioink initial characterization

D3 – P097

Electrospun aligned PLA/silk fibroin nanocomposite scaffolds for tendon tissue engineering

Alhamoudi F.[1], Akhtar H.[2], Khalid H.[2], Khan A.F.[2]
[1]Dept. of Allied Dental Health Science, College of Applied Medical Sciences, King Khalid University, Abha, Kingdom of Saudi Arabia; [2]Interdisciplinary Research Centre in Biomedical Materials, COMSATS University Islamabad, Lahore campus, Pakistan

Introduction

Tendon injuries are painful, slow to heal, and frequently associated with incomplete functional recovery. Conventional surgical repair often results in scar formation, inferior tissue organisation, and an increased risk of re-injury. Tissue engineering offers a promising alternative through biomimetic scaffolds that reproduce key structural and functional features of native tendons. In this study, electrospun poly(lactic acid) (PLA)-based composite nanofibrous scaffolds incorporating cerium oxide-based doped nanoparticles and silk fibroin were developed in random and aligned fibre configurations to mimic the anisotropic architecture of tendon tissue.

Materials and Methods

Scaffolds were fabricated by electrospinning to control fibre morphology and orientation. Random and aligned nanofibrous constructs were produced and characterised using Fourier-transform infrared spectroscopy (FTIR), scanning electron microscopy (SEM), and X-ray diffraction (XRD). SEM was further used to assess fibre diameter, morphology, and alignment. Physicochemical properties relevant to scaffold performance were evaluated, including wettability, swelling, porosity, and density. In vitro degradation was assessed to examine scaffold stability over time. Antibacterial activity was also investigated. Mechanical behaviour under dry and wet conditions, including performance after degradation, was evaluated to determine the suitability of the scaffolds for tendon repair applications.

Results

The results confirmed successful fabrication of the composite scaffolds and incorporation of the intended components. FTIR identified the expected chemical groups, while SEM demonstrated a continuous nanofibrous morphology with distinct random and aligned architectures. The aligned scaffolds more closely reproduced the organised fibre arrangement of the native tendon. The scaffolds exhibited favourable wettability, porosity, density, and swelling behaviour, indicating a microenvironment supportive of tissue regeneration. In vitro degradation exhibited a stability profile consistent with tendon-healing requirements. Antibacterial activity was observed, suggesting an additional protective benefit against infection. Overall, the aligned and composite scaffold design showed structural and functional features desirable for tendon tissue engineering.

Conclusion

These electrospun PLA-based composite scaffolds demonstrated promising physicochemical and functional properties for tendon regeneration. In particular, fibre alignment improved the biomimetic design by better reproducing native tendon architecture. The developed scaffold system, therefore, represents a promising platform for soft tissue repair and tendon tissue engineering.

Acknowledgements

The authors extend their appreciation to the Deanship of Research and Graduate Studies at King Khalid University for funding this work through Large Research Project under grant number RGP.1/99/46.

References

[1]Habib S. et al. RSC advances. 2026; 16(11); 9358-70.
[2]Shafiq et al. RSC advances. 2025; 15(22); 17649-64.
[3]Akhtar H. et al. Heliyon. 2024 Apr 15; 10(7).

D3 – P098

Source dependent structure–function relationships in freeze-dried porous collagen scaffolds for bone tissue engineering

Sahebalzamani M.A.[1,2], Molon G.[1], Redmond J.[1,2], Insley G.[4], Dunne N.[1-3], Levingstone T.[1,2]

[1]Centre for Medical Engineering Research, School of Mechanical and Manufacturing Engineering, Dublin City University (DCU), Ireland; [2]Biodesign Europe, DCU, Dublin, Ireland; [3]School of Pharmacy, Queen's University Belfast, UK; [4] PBC Biomed, Accelerating Medical Innovation, Limerick, Ireland

Introduction

Bone tissue engineering aims to develop biomaterial scaffolds that can effectively support cell attachment, proliferation and tissue regeneration while simultaneously providing adequate mechanical integrity and controlled degradation. Collagen is widely used in scaffold fabrication due to its biocompatibility, biodegradability and structural similarity to the native extracellular matrix. However, variations in collagen source and concentration can significantly influence scaffold microstructure and functional performance. Differences between marine- and bovine-derived collagen may result in distinct variations in scaffold microstructure, porosity, mechanical strength, and degradation behaviour.

Aim

This study aims to assess how collagen source and concentration influence functional performance, morphology, structural integrity, and stability under physiological conditions to optimise collagen-based scaffolds for bone tissue engineering.

Materials and Methods

The collagen slurries were prepared at concentrations of 0.5%, 1.0%, and 1.5% (w/v) using marine- and bovine-derived collagen. Scaffolds were fabricated via freeze-drying, followed by dehydrothermal crosslinking to enhance structural stability. The resulting scaffolds were characterised using scanning electron microscopy to evaluate pore morphology and microstructural architecture. Porosity was quantified using standard analytical gravimetric methods. Mechanical properties were assessed under uniaxial compression loading in both dry and hydrated conditions. Swelling behaviour was evaluated to determine fluid uptake capacity, while *in vitro* degradation studies were conducted in phosphate-buffered saline to assess scaffold stability over time. Rheological properties of the precursor collagen slurries were analysed via viscosity measurements using rotational viscometer.

Results

All scaffolds exhibited very high porosity (~98–99%) regardless of source. Porosity decreased with increasing collagen concentration for both marine and bovine scaffolds, reflecting increased solid content and thicker pore walls. Young's modulus increased with collagen concentration for both sources. Marine scaffolds showed 11.6–59.0 kPa (dry) and 11.3–45.0 kPa (hydrated), while bovine scaffolds ranged from 10.6–64.5 kPa (dry) and 5.3–24.0 kPa (hydrated) (Fig. 1). Marine-derived scaffolds demonstrated higher swelling capacity and slower degradation rates compared to bovine counterparts, suggesting variations in molecular structure. Marine scaffolds showed concentration-dependent, slower degradation (up to ~50% at 3 days for 0.5%, rapid loss for 1%, and minimal loss for 1.5%). In contrast, bovine scaffolds degraded rapidly, with ~96–100% mass loss within 6 hours across all concentrations. (Fig. 2).




Figure 1: Compressive Young's Modulus (kPa) of marine and bovine collagen scaffolds under dry and hydrated conditions at different collagen concentrations. Data are presented as mean values. Statistical significance is indicated by ns (not significant), **** ($p < 0.0001$).




Figure 2: Percentage mass loss (%) of marine and bovine collagen scaffolds at different concentrations after 6 hours of incubation in PBS. Data are presented as mean ± standard deviation. Statistical significance is indicated by ** ($p < 0.01$),
**** ($p < 0.0001$).

Conclusion

Collagen concentration and source are key determinants of freeze-dried collagen scaffolds' microstructure, mechanical performance, and degradation behaviour. By tuning these parameters, scaffold properties can be tailored to specific bone tissue engineering needs. Notably, marine collagen shows comparable performance to bovine collagen, with added advantages in sustainability and reduced risk of disease transmission.

D3 – P099

Fabrication of long decellularised muscle scaffolds for tissue engineering applications

Cordelle M.Z.[1], Biasi G[1], Snelling S.J.B[1], Mouthuy P.-A.[2]
[1]Nuffield Dept. of Orthopaedics, Rheumatology, and Musculoskeletal Sciences, University of Oxford; [2]Dept. of Materials, University of Oxford, UK

Introduction

Skeletal muscle tissue engineering (SMTE) is a rapidly evolving field with applications spanning regenerative medicine, disease modelling, drug screening, and biohybrid robotics. Effective SMTE requires scaffolds that reproduce the anisotropic architecture and mechanical properties of native muscle while supporting macroscale tissue formation. Decellularised tissues are strong candidates, yet existing approaches face key limitations. Whole-muscle decellularisation requires complex perfusion systems and often fails to fully clear the tissue core. In contrast, minced-tissue processing destructs native architecture and necessitates technically demanding reconstruction. Consequently, producing long continuous scaffolds needed to model or restore physiologically relevant muscle units remains challenging.

Aim

This work presents an intermediate strategy enabling the fabrication of long, aligned scaffolds from native muscle bundles.

Materials and Methods

Long (>10cm) skeletal muscle bundles were dissected to preserve native fibre alignment and decellularised using freeze–thaw cycles followed by a mild detergent protocol (0.5% SDS, 24h). Decellularisation efficiency, extracellular matrix (ECM) composition, microarchitecture and mechanical properties were assessed. Scaffold biocompatibility was evaluated through *in-vitro* culture of both C2C12 myoblasts and adult human skeletal muscle cells, assessing cell viability, proliferation, and preliminary assessment of myogenic differentiation.

Results

This method (Fig1.A) achieved removal of cellular material while preserving ECM structure (Fig1.B) and mechanical properties compatible with SMTE applications. The resulting scaffolds supported myogenic cell adhesion, proliferation, and differentiation of both murine and human cells (Fig1.C), demonstrating suitability for *in-vitro* muscle tissue culture.

Conclusion

This approach enables routine fabrication of centimetre-scale, structurally faithful scaffolds that support myogenic culture and mechanical conditioning. As a next step, these constructs will be seeded and matured under progressively more physiologically relevant actuation regimes, from static culture to human-scale bioreactor and robotic systems, to investigate how complex mechanical stimulation influences in-vitro muscle development.

Acknowledgements

This work has been completed with the financial support of the United Kingdom's Medical Research Council (MRC DTP iCASE 2023 Award), the United Kingdom's Engineering and Physical Sciences Research Council (EP/S003509/1) and the UKRI-BBSRC Interdisciplinary Bioscience Doctoral Training Partnership (BB/T008784/1). This project has also been supported by the National Institute for Health and Care Research, the Oxford Biomedical Research Centre and the EPA Cephalosporin Graduate Scholarship.




Fig. 1: (A) Workflow of scaffold preparation. (B) SEM, µCT, and H&E characterisation of decellularised scaffold. (C) Phalloidin (green) and DAPI (blue) staining of C2C12 cells after 5 days of differentiation on scaffolds. Bottom image shows a higher magnification view of the region of interest (scale bars = 200µm).

D3 – P100
In silico design of Mg-based biodegradable scaffolds for the repair of critical-size defects

Nguyen S.[1], Barzegari M.[2], Geris L.[1,3]
[1]Biomechanics Section, Dept. of Mechanical Engineering, KU Leuven, Belgium; [2]Electrochemical Materials and Systems, Dept. of Chemical Engineering and Chemistry, TU Eindhoven, The Netherlands; [3]Biomechanics Research Unit, GIGA In Silico Medicine, University of Liège, Belgium

Introduction
Critical-size bone defects arising from trauma, disease, or surgery remain difficult to treat because the intrinsic regenerative capacity of bone is limited. Biodegradable porous scaffolds have emerged as a promising alternative to grafting strategies for bridging such defects, yet the mechanisms governing bone regeneration within scaffolds are still not fully understood. Most large-animal studies rely on endpoint analyses, providing little insight into the dynamic interplay between bone formation and material degradation. In silico modeling could help provide longitudinal data of these coupled processes, supporting the design and development of more effective regenerative therapies. Here we developed a multi-factorial in silico model to study the balance between the kinetics of porous scaffold degradation and the rate of bone formation.

Materials and Methods
A set of partial differential equations (PDEs) was established describing the chemistry of corrosion of a magnesium scaffold, as well as bone ingrowth through the spatiotemporal concentration of bone cells. The model implicitly tracks the degradation and bone formation fronts in a phase-field framework, including curvature-based effects. The PDEs are solved numerically using the finite element method and implemented in FreeFEM. The interface between the scaffold and bone is refined over time through a mesh adaptation procedure, allowing accurate tracking of the moving interfaces. The model outputs are the concentration of bone cells and magnesium ions, the geometry of the degrading scaffold, and the density of new bone over time. The model will be informed by unpublished large animal data at various time points.

Results
The model is applied to a gyroid scaffold, investigating various differences in speed between the bone formation and implant degradation. Fig. 1 shows the results of the simulation where both processes occur at comparable speed, showing scaffold degradation while new bone is forming at the scaffold surface and filling the pores.

Conclusion
This work introduces an in silico model that quantitatively captures the spatiotemporal evolution of scaffold degradation and bone ingrowth, addressing the current lack of in vivo longitudinal data. Once validated, the model is intended to serve as a design tool to optimize scaffold geometry and support the development of treatments to repair critical-size bone defects.

Acknowledgements
The research was financially supported by the PRosPERoS-II project, funded by the Interreg VA Flanders - the Netherlands program, CCI grant no. 2021TC16RFCB041.




Fig. 1: Bone ingrowth (yellow) into pores (blue) of a degrading (grey) gyroid scaffold. Orange regions are the initial scaffold geometry.

D3 – P101

Post-fabrication silver ion incorporation into electrospun polypeptide membranes: Structural stability and biological response

Hu Z.-W., Ma T.-L.
School of Dental Technology, College of Oral Medicine, Taipei Medical University, Taiwan

Introduction

Electrospun polypeptide scaffolds have attracted considerable interest in biomaterials research due to their extracellular matrix-like architecture and tunable chemical functionality. However, the absence of intrinsic antimicrobial properties may limit their performance in microbially challenging environments. The aim of this study was to evaluate whether post-fabrication silver ion incorporation could introduce antibacterial functionality into electrospun synthetic polypeptide membranes while preserving structural stability and cytocompatibility.

Materials and Methods

A glutamate-derived synthetic polypeptide was processed into aligned fibrous membranes via electrospinning. Silver ions were introduced through controlled immersion in aqueous silver nitrate solutions at low concentrations, enabling ionic adsorption onto reactive domains within the scaffold. Morphology and elemental distribution were analyzed using scanning electron microscopy and energy-dispersive X-ray spectroscopy. Chemical stability was examined by Fourier-transform infrared spectroscopy. Silver release behavior was quantified using inductively coupled plasma mass spectrometry. Antibacterial performance and cytocompatibility were evaluated using representative bacterial strains and osteoblast-like cells.

Results

Electrospun membranes exhibited uniform and aligned fibrous morphology across all tested silver concentrations, with no observable structural collapse or fiber fusion following ionic incorporation (Figure 1A–C). Elemental mapping confirmed homogeneous silver distribution without detectable aggregation. Sustained silver ion release was observed within the tested concentration range. Silver-modified membranes demonstrated significantly reduced bacterial viability at both 1 h and 3 h in a concentration-dependent manner (Figure 2A–B). In vitro assays indicated maintained cell viability and osteogenic marker expression, suggesting that low-dose silver incorporation did not compromise cytocompatibility.

Conclusion

Post-fabrication silver ion incorporation provides a straightforward strategy to introduce antibacterial functionality into electrospun synthetic polypeptide membranes while maintaining structural and biological properties. These findings support the potential of ion-modified electrospun scaffolds for multifunctional biomaterial applications.

Acknowledgements

This research was supported by the National Science and Technology Council, Taiwan (NSTC114-2222-E-038-001-MY3), and Taipei Medical University (TMU113-AE1-B17).




Figure 1. Scanning electron microscopy images of electrospun polypeptide membranes with increasing silver concentrations: (A) 0.005 wt%, (B) 0.010 wt%, and (C) 0.015 wt%. Uniform aligned fibrous morphology was preserved across all concentrations. Scale bar = 100 μm.




Figure 2. Liquid antibacterial activity of silver-modified membranes against *E. coli* and *S. mutans* at (A) 1 h and (B) 3 h. Silver incorporation significantly reduced bacterial colony-forming units in a concentration-dependent manner.

D3 – P102

Design and mechanical evaluation of electrospun bilayer grafts for aortic replacement

Ragusa S.[1,2,3], Grasl C.[1,4], Stoiber M.[1,4], Licciardi M.[3], Zingales M.[5], Moscato F.[1,4,6]
[1]Center for Medical Physics and Biomedical Engineering, Medical University of Vienna, Austria; [2]Advanced Medical Engineering Devices s.r.l. (AMED), Palermo, Italy; [3]Dipt. di Scienze e Tecnologie Biologiche, Chimiche e Farmaceutiche (STEBICEF), University of Palermo, Italy; [4]Ludwig Boltzmann Institute for Cardiovascular Research, Vienna, Austria; [5]Dept. of Engineering, University of Palermo, Italy; [6]Austrian Cluster for Tissue Regeneration, Vienna, Austria

Introduction

The development of vascular grafts remains a major clinical challenge due to the complexity of mimicking the nonlinear mechanical behavior of native vessels. Arterial behavior is governed by a layered structure where the interaction of elastin and collagen modulates the tissue response under varying blood pressures. This study introduces an electrospun bilayer aortic graft, combining a biostable thermoplastic polyurethane (PU) and hemocompatible biodegradable poly(butylene succinate) (PBS) at the inner layer to engineer.
Aim The main goal is to develop a bilayer aortic graft that achieves native-like compliance, integrating the mechanical properties of PU–PBS systems and to ensure long-term stability in terms of creeping under physiological cyclic loading.

Materials and Methods

Bilayer vascular graft with a diameter of 25 mm and an overall wall thickness between 200 and 300 µm were produced. The graft had an architecture that integrates an inner PU (Tecoflex EG60D)–PBS blend (50:50 w/w) layer with an outer pure PU layer. Each layer accounted for 50% of the total graft thickness. Fiber morphology was characterized using scanning electron microscopy (SEM) and mechanical performance was investigated. Quasi-static uniaxial tensile tests were performed to determine the stress-strain behavior, while dynamic cyclic tensile tests were conducted to evaluate compliance and creep stability under physiological conditions (37°C, wet state). The cyclic load intervals were specifically adjusted to replicate the mechanical stress ranges corresponding to physiological systolic and diastolic pressures.

Results

Mechanical tests demonstrate that the bilayer architecture significantly improves compliance compared to pure PBS and PU–PBS blend scaffolds. While pure PBS exhibits insufficient compliance (1.7%/ 100 mmHg), the bilayer configuration maintains a physiological profile (8%/100 mmHg) even after 1800 cyclic loading cycles, showing superior performance compared to the blend alone (3.5%/100 mmHg). This result indicates that the bilayered composition successfully integrates the structural contribution of the PU outer layer with the mechanical response of the inner layer. Structural durability tests showed up to 35% diameter creep, which can be improved by adjusting scaffold thickness and the blend-to-PU ratio.

Conclusion

The bilayer architecture presented here overcomes key limitations of single-layer scaffolds, enabling a physiological compliance profile that conventional materials fail to replicate. These findings demonstrate the potential to balance mechanical performance with long-term structural integrity. Ongoing work aims to further enhance scaffold stability by optimizing layer thickness and polymer composition to minimize diameter creep.

D3 – P103

PLLA blends for melt-electrowritten piezoelectric scaffolds in neural tissue regeneration

Panfilo A.[1], Zapater J.[1], Schönlein R.[1,2], Mendes C.[3], Lanceros S.[2,3,4], Larrañaga A.[1], Ugartemendia M. J.[1]
[1]Group of Science and Engineering of Polymeric Biomaterials (ZIBIO Group), Dept. of Mining, Metallurgy Engineering and Materials Science, POLYMAT, Bilbao School of Engineering, University of the Basque Country (UPV/EHU), Spain; [2]CF-UM-UP − Physics Centre of Minho and Porto Universities and LaPMET − Laboratory of Physics for Materials and Emergent Technologies, University of Minho, Braga, Portugal; [3]BCMaterials, Basque Center for Materials, Applications and Nanostructures, UPV/EHU Science Park, Spain; [4]IKERBASQUE, Basque Foundation for Science, Bilbao, Spain

Introduction

Our work aims to develop biodegradable piezoelectric scaffolds based on poly(L-lactide) (PLLA) as flexible platforms for the repair of nervous system injuries, a major unresolved clinical and societal challenge. Single-step fabrication directly from the polymer melt would greatly facilitate the scalable production and clinical translation of PLLA-based piezoelectric scaffolds. However, achieving the high molecular chain orientation required for piezoelectricity, together with the rapid relaxation of polymer chains during processing, remains a key limitation that must be addressed. To address these challenges, the project combines two strategies: PLLA-based immiscible blends with droplets-in-matrix morphology and melt electrowriting (MEW) for scaffold fabrication. This morphology promotes *in situ* nanofibrillation under shear–elongational flow, enhancing PLLA chain orientation, crystallinity, and consequently its piezoelectric response.

Materials and Methods

Immiscible polymer blends were developed by incorporating biodegradable poly(L-lactide-co-ε-caprolactone) (PLCL, 40 wt%) into a PLLA matrix. Prior to scaffold fabrication, piezoelectricity was verified using drawn films (draw ratio=4), and the shear piezoelectric coefficient was measured with a Berlincourt d_{33}-meter equipped with a custom d_{13} adapter. Cytocompatibility was evaluated *in vitro* using neuronal cell lines. Rheological characterization (SAOS) was performed to determine the relaxation time spectrum and optimize MEW processing parameters. Scaffolds (4x4 cm, 10-20 layers, crosshatch geometry) were fabricated and structurally characterized by polarized light optical microscopy (PLOM) and atomic force microscopy (AFM). Piezoelectric morphology was analyzed through chain and crystal orientation (Herman orientation function) using polarized Raman spectroscopy and wide- and small-angle X-ray scattering (WAXD/SAXS), while the local piezoelectric response was measured by piezo-force microscopy (PFM).

Results

Preliminary characterization confirmed that the blends exhibited piezoelectric behavior and cytocompatibility (Figures 1 and 2). The incorporation of PLCL improved the thermal stability of the polymer melt, facilitating scaffold processing by MEW and increasing relaxation times. After optimizing MEW parameters, scaffolds with acceptable morphological stability were successfully fabricated. These scaffolds are anticipated to generate electromechanical cues that may promote neural cell responses.

Conclusion

This work is expected to demonstrate the potential PLLA-based flexible blends for the fabrication of piezoelectric scaffolds using scalable melt-based technologies. The findings may support the development of implantable electroactive biomaterials for neural tissue regeneration.

Acknowledgements

This work was supported by the Basque Government (Dept. of Education, GIC21/131 IT1766-22), the Spanish Ministry of Science and Innovation (PID2022-139821OB-I00, co-funded by ERDF), the María de Maeztu Excellence Unit (CEX2023-001303-M), and the University of the Basque Country (EHU-N24/62). A. Panfilo acknowledges a predoctoral fellowship from the Basque Government.




Figure 1. Piezoelectric response of PLLA and PLLA/PLCL 60:40 blend as-made, drawn at DR4 and drawn and annealed at 80 ºC .




Figure 2. Cytocompatibility of PLLA:PCL 60:40 blend non-activated and activated by ultrasounds (US) evaluated by WST-1 assay.

D3 – P104

Biomedical applications of multifunctional polydopamine nanotubes

Battaglini M.[1], Marino A.[1], Curiale T.[1], Carmignani A.[1], Bernardeschi M.[1], Emanet M.[1], Ceccarelli M.C.[1,2], Catalano F.[3], Drago F.[4], Marras S.[5], Pugliese G.[4], Torre B.[6], Ciofani G.[1]

[1]Istituto Italiano di Tecnologia, Smart Bio-Interfaces, Pontedera; [2]Scuola Superiore Sant'Anna, The Biorobotics Institute, Pontedera; [3]Istituto Italiano di Tecnologia, Electron Microscopy Facility, Genova; [4]Istituto Italiano di Tecnologia, Nanochemistry, Genova; [5]Istituto Italiano di Tecnologia, Materials Characterization Facility, Genova; [6]Istituto Nazionale di Ricerca Metrologica INRiM, Advanced Materials and Life Science Division, Torino, Italy

Introduction

Polydopamine (PDA) nanostructures are emerging as a highly versatile class of organic nanomaterials derived from the spontaneous oxidative self-polymerization of dopamine. Their unique combination of biocompatibility, biodegradability, broad chemical reactivity, antioxidant behaviour, and excellent photothermal conversion efficiency has driven widespread research interest in biomedical and materials science applications. While spherical PDA nanoparticles (PDNPs) are well-established and extensively characterized, achieving alternative anisotropic morphologies has remained a significant challenge due to the complex polymerization kinetics of dopamine. Among these, tubular PDA nanostructures (PDA-NTs) represent an almost unexplored architecture. To date, only scattered preliminary observations of PDA nanotubes have been reported, and their functional behaviour within biological systems remains largely unknown. In this study, we present the first comprehensive investigation of PDA-NTs, encompassing their synthesis, detailed physicochemical characterization, and functional biological activity. Beyond confirming expected PDA properties—such as antioxidant and photothermal effects—we discovered that PDA-NTs also exhibit previously unreported piezoelectric capabilities, positioning them as a novel class of organic, multifunctional nanomaterials. These findings broaden the fundamental understanding of PDA-based materials and open new pathways for biomedical innovation.

Materials and Methods

PDA-NTs were synthesized by coating ZnO nanowires with polydopamine and subsequently removing the inorganic template to obtain hollow nanotubes. Their morphology, composition, and structural features were characterized using electron microscopy, spectroscopic analyses, thermal analysis, and colloidal measurements. Piezoelectric behaviour was quantified by atomic-piezo force microscopy (AFM–PFM). Photothermal properties were evaluated under near-infrared (NIR) irradiation using thermal imaging. Biocompatibility, cellular uptake, and intracellular localization were assessed in U87 glioblastoma cells using viability assays, confocal microscopy, and scanning electron microscopy (SEM). Antioxidant effects were analyzed by flow cytometry of cytosolic and mitochondrial reactive oxygen species (ROS) and by cell death following oxidative stress. Intracellular Ca^{2+} dynamics during NIR or ultrasound stimulation were recorded to assess photothermal and piezoelectric activity. Dopamine release was quantified by High Performance Liquid Chromatography (HPLC) under passive and ultrasound-triggered conditions, and the bioactivity of released dopamine was tested in human neural stem cells.

Results

PDA-NTs displayed an average length of 1088 ± 583 nm, an outer diameter of 140 ± 40 nm (representative image of PDA-NTs shown in Figure 1). PDA-NTs exhibited strong piezoelectricity (d_{33} = 15.0 ± 0.7 pC/N), efficient NIR photothermal conversion properties (ΔT = 7.4–17.1°C across tested concentrations), and antioxidant activity comparable to PDNPs. They were internalized by U87 cells without cytotoxicity up to 100 µg/ml. NIR + PDA-NTs induced a ~50% increase in intracellular Ca^{2+}, while ultrasound + PDA-NTs triggered transient Ca^{2+} spikes, confirming piezoelectric activation. Dopamine release reached 96.3 ± 2.6 µg/ml at 72 h under ultrasound and induced Ca^{2+} responses in human neural stem cells (hNSCs).

Conclusion

PDA-NTs constitute a multifunctional organic nanoplatform integrating piezoelectricity, photothermal conversion, antioxidant activity, and dopamine release. Their ability to remotely modulate cellular activity highlights strong potential for applications in neurostimulation, oncology, and advanced biointerfaces.




Figure 1. TEM representative image of PDA-NTs

D3 – P105

Homotypic targeting of cell membrane-decorated lipid magnetic nanovectors in patient-derived glioblastoma models

Lefevre M.C.[1], Carmignani A.[1], Koutsoumpou, X.[1], Emanet, M.[1], Beola, L.[1], Moscato, S.[2], Ciofani, G.[1]
[1]Smart Bio-Interfaces, Istituto Italiano di Tecnologia, Pontedera; [2]Dept. of Clinical and Experimental Medicine, University of Pisa, Italy

Introduction

Glioblastoma (GBM) remains incurable, largely due to limited drug penetration across the blood-brain barrier (BBB) and rapid tumor recurrence. Lipid magnetic nanovectors (LMNVs) are attractive candidates for improved delivery and magnetic hyperthermia under alternating magnetic fields (AMF). Coating nanovectors with cancer cell membranes may further enable homotypic targeting through tumor-tumor recognition mediated by membrane proteins. Here, we evaluate patient-specific uptake and selectivity of cancer cell membrane-decorated LMNVs (CD-LMNVs) in complementary microfluidic and *ex ovo* chorioallantoic membrane (CAM) models of patient-derived GBM.

Materials and Methods

Primary GBM cells from two grade IV patients (GBM-P1, GBM-P2) were combined with immortalized human brain microvascular endothelial cells (IM-HBMEC) and immortalized human astrocytes (IM-HA) in a perfused microfluidic co-culture system. CD-LMNVs were produced by decorating LMNVs with cell membranes isolated from GBM-P1; non-decorated LMNVs served as a control. Uptake was quantified by flow cytometry after 4 h perfusion. In parallel, patient-derived GBM spheroids were grafted onto the CAM of shell-less Japanese quail (*Coturnix japonica*) embryos to generate vascularized tumors. LMNVs or CD-LMNVs were injected intravascularly, and tumor uptake and patient selectivity were assessed by flow cytometry. For preliminary therapeutic evaluation, CD-LMNVs were injected *in situ* and exposed to AMF, followed by flow cytometry, histology, and immunostaining.

Results

In the microfluidic model, CD-LMNVs showed significantly higher internalization in GBM cells from the membrane-donor patient (GBM-P1) than in GBM-P2, IM-HA, or IM-HBMEC, supporting homotypic targeting (Figure 1.a-b). In parallel, GBM spheroids were grafted in the CAM, forming vascularized tumors within 24h (Figure 1.c). Following intravascular administration, CD-LMNVs accumulated and were internalized more efficiently within vascularized tumors than non-decorated LMNVs (30.6 ± 6.7% vs. 15.3 ± 4.8%), showing that membrane coating enhanced tumor uptake (Figure 1.d). When GBM-P1 and GBM-P2 spheroids were grafted in the same embryo, uptake remained markedly higher in the homotypic configuration than in the heterotypic one (42.7 ± 9.9% vs 2.6 ± 0.8%) (Figure 1.e). Finally, the therapeutic effect of magnetic hyperthermia is currently evaluated by flow cytometry (apoptosis/necrosis), histology (hematoxylin and eosin), and immunostaining (heat shock protein, Ki-67).

Conclusion

Combining a BBB-relevant microfluidic platform with a vascularized patient-derived GBM CAM model enables comparative, patient-specific evaluation of targeted nanovectors. CD-LMNVs demonstrated consistent homotypic targeting across both models, motivating ongoing assessment of therapeutic response to support translation toward personalized magnetic hyperthermia/nanotherapy screening.

Acknowledgements

The research leading to these results has received funding from AIRC under IG 2020 – ID 24454.




Figure 1: Homotypic targeting of cell membrane-decorated lipid magnetic nanovectors in microfluidic and vascularized patient-derived glioblastoma models. (a-b) Schematic of the microfluidic system (a) and flow cytometry analysis of CD-LMNVs uptake across 4 cell types (b). (c-e) Schematic of the ex ovo CAM model (c), comparative analyses of CD-LMNVs and LMNVs uptake in GBM-P1 grafted spheroids (d), and selective uptake of CD-LMNVs in spheroids derived from two different patients (e). Data are presented as mean ± SEM (∗, $p < 0.05$; ∗∗, $p < 0.005$; ∗∗∗, $p < 0.0005$; $n \geq 3$).

D3 – P106

3D printing of thermally responsive shape memory scaffolds for bone regeneration

Victor Z.[1,2], Ferrari G.[2], Brancart J.[3], Schaubroeck D.[4], Dmitriev R.[2], Arslan A.[1]
[1]BIO INX BV, Ghent; [2]Tissue Engineering and Biomaterials Group, Faculty of Medical and Health Sciences, Ghent University; [3]Lab of Physical Chemistry and Polymer Science (FYSC), Sustainable Materials Engineering Research Group (SUME), Vrije Universiteit Brussel; [4]Centre for Microsystems Technology (CMST), imec and Ghent University, Belgium

Introduction

Shape memory polymers (SMP) are a class of smart materials capable of undergoing controlled shape transformations in response to external stimuli, which makes them particularly attractive for regenerative medicine applications such as minimally invasive and patient-specific implants. In this study, we employ a thermally responsive shape memory polycaprolactone (PCL)-based resin for the fabrication of bone tissue engineering scaffolds using digital light projection (DLP) 3D printing.

Materials and Methods

SMP resins (DEGRES INX© X100, BIO INX) were 3D printed into disk-shaped samples following the manufacturer's protocol. Shape memory behavior was analyzed using dynamic mechanical thermal analysis (DMTA). To enhance biological functionality, the disks were coated with collagen or collagen/hydroxyapatite (HAp). Surface hydrophilicity was evaluated through static contact angle measurements, while the morphology of the HAp coating was examined using Scanning Electron Microscopy (SEM). Human dental pulp stem cells (hDPSCs) were cultured on the scaffolds and evaluated via live/dead assay (Calcein-AM and Propidium Iodide staining), RUNX2 and COL1A1 immunostaining, Alizarin Red staining, Alkaline phosphatase (ALP) and ATP assays up to 21 days in culture.

Results

To demonstrate shape memory behavior, a DLP-printed wave-like structure was deformed into a temporary shape at 50 °C, fixed in its temporary shape by cooling in a freezer, and subsequently self-recovered their original shape upon reheating to 37 °C (Figure 1). Cyclic thermomechanical analysis using DMTA verified the shape memory performance of the SMP scaffolds under tensile loading. The shape fixity ranged from 94–96%, while the shape recovery reached 89% in the first cycle and 100% in subsequent cycles. SEM imaging confirmed homogeneous deposition of hydroxyapatite on the scaffold surfaces, with aggregate diameters in the range of 3–5 µm. Surface modification with HAp and collagen markedly enhanced hydrophilicity, as evidenced by decreased static contact angles. *In vitro* studies demonstrated good hDPSC adhesion on the SMP scaffolds. Furthermore, Alizarin Red staining and immunostaining indicated enhanced osteogenic differentiation in scaffolds coated with collagen and collagen/HAp.

Conclusion

The results of this study demonstrate that DLP-fabricated PCL-based SMP scaffolds exhibit robust and reliable shape memory behaviour, while also supporting cell growth and osteogenic differentiation following a straightforward surface functionalization process. These findings underscore the potential of these scaffolds as promising candidates for bone tissue engineering applications, particularly in scenarios requiring minimally invasive implantation and enhanced bioactivity.

Acknowledgements

This project is supported by the Interreg Crossroads Vlaanderen-Nederland Programme (InCart3D).




Figure 1 Photographs of a wave structure printed using SMPs demonstrating the shape memory behavior.

D3 – P107

Ultrasound-responsive polymeric nanobubbles for acoustical cell bursting and enhanced anticancer immunotherapy

Park J.Y.[1], You D.G.[1]
[1]Dept. of Chemical Engineering and Biotechnology, Tech University of Korea, Siheung, Republic of Korea

Introduction

Current cancer immunotherapy often relies on T cell recruitment, yet existing strategies face limitations. Interleukin-33 (IL-33) is a crucial damage-associated molecular pattern (DAMP) required for activating eosinophils and recruiting cytotoxic T cells. However, it is chromatin-bound and lacks an efficient extracellular release mechanism. Overcoming this barrier requires innovative biomaterial strategies to physically disrupt cellular compartments. We aimed to design ultrasound-responsive polymeric nanobubbles capable of inducing acoustical bursting of cancer cells, thereby facilitating the intact release of DAMPs to promote eosinophil-mediated anticancer immunity.

Materials and Methods

Amphiphilic carboxymethyl dextran and cholanic acid conjugates were synthesized via standard coupling chemistry to create hydrophobic internal pockets within the resulting nanoparticles. Perfluorohexane, a highly ultrasound-sensitive gas precursor, was encapsulated into these polymeric structures using sonication to fabricate the nanobubbles. Physicochemical properties, including size and morphology, were characterized using dynamic light scattering and transmission electron microscopy. In vitro acoustical bursting efficacy upon exposure to focused ultrasound was evaluated in colon cancer cells. The extracellular release of nuclear proteins was confirmed via Western blotting. In vivo therapeutic efficacy and immune cell infiltration were assessed in tumor-bearing mouse models, testing the biomaterial alone and in combination with a dipeptidyl peptidase-4 (DPP4) inhibitor.

Results

The formulated polymeric nanobubbles exhibited a stable spherical structure averaging 225.8 nanometers in diameter. Transmission electron microscopy confirmed the successful encapsulation of perfluorohexane within the hydrophobic core of the polymeric shell (Figure 1). Upon exposure to focused ultrasound, the internalized nanobubbles generated potent cavitation forces that physically ruptured both the plasma and nuclear membranes of targeted cancer cells. This mechanically induced bursting, which operates independently of biological programmed cell death pathways, enabled highly efficient extracellular release of intact nuclear contents, including IL-33. In vivo systemic administration of the nanobubbles combined with ultrasound significantly increased the infiltration of activated eosinophils, natural killer cells, and cytotoxic T cells within the tumor microenvironment (Figure 2). When co-administered with a DPP4 inhibitor, this biomaterial strategy demonstrated superior suppression of primary tumor growth and lung metastasis compared to conventional immune checkpoint inhibitors.

Conclusion

We successfully developed ultrasound-responsive polymeric nanobubbles as a novel biomaterial platform for precise, mechanically triggered cancer cell bursting. By physically disrupting cellular and nuclear membranes via acoustic cavitation, this system enables the efficient release of intact nuclear DAMPs, overcoming the inherent limitations of biological cell death pathways. Ultimately, this mechanically actuated biomaterial strategy facilitates robust eosinophil-mediated anti-tumor immunity, providing a practical approach for advancing cancer treatments.

Figure




Figure1. Schematic illustration of the formulation of ultrasound-responsive polymeric nanobubbles and their morphological characterization via transmission electron microscopy (TEM).




Figure2. In vivo immunohistochemical analysis demonstrating enhanced infiltration of activated eosinophils (Siglec F) and cytotoxic T/natural killer cells (CD3/CD49b) in the tumor microenvironment following treatment with nanobubbles and ultrasound.

D3 – P108

Electroresponsive GelMA-rGO microneedle patch for biphasic dual-drug delivery in psoriasis

Torkay Çay G.[1,2], Üstündağ C.B.[1], Bal Öztürk A.[2,3,4]

[1]Dept. of Bioengineering, Yildiz Technical University; [2]Stem Cell and Tissue Engineering Research and Application Center (ISUKOK), Istinye University; [3]Dept. of Analytical Chemistry, Faculty of Pharmacy, Istinye University; [4]Dept. of Stem Cell and Tissue Engineering, Institute of Graduate Education, Istinye University, Istanbul, Turkey

Introduction

Psoriasis is a chronic inflammatory skin disease that often requires long-term therapy, yet current topical and systemic treatments remain limited by poor skin penetration, off-target exposure, and insufficient control over release kinetics.[1] Here, an electroresponsive hydrogel microneedle patch is proposed to enable localized and sequential modulation of inflammation and angiogenesis in psoriatic lesions.

Materials and Methods

Layered microneedle platforms were fabricated in polydimethylsiloxane (PDMS) micromolds using light-crosslinkable gelatin methacryloyl (GelMA) formulations containing reduced graphene oxide (rGO). By adjusting the layered formulations, quercetin was loaded into the fast-release phase and bevacizumab into the delayed-release phase, achieving a two-phase delivery. Formulations with varying rGO contents, GelMA concentrations, and crosslinking conditions were optimized for microneedle accuracy, mechanical integrity, swelling, and degradation behavior. The generated microneedles were characterized by scanning electron microscopy (SEM) and electrochemical impedance spectroscopy (EIS). Drug release was evaluated in the presence and absence of electrical stimulation. Cytocompatibility was assessed on human dermal fibroblast and keratinocyte cells. Angiogenic response was evaluated by chorioallantoic membrane (CAM) assay, and porcine skin was used for permeability performance.

Results

A fabrication process for layered GelMA-rGO microneedles was established, and mechanically stable microneedle platforms carrying different drugs in separate layers were developed. The system was designed to provide rapid release of quercetin in the early inflammatory phase and delayed release of bevacizumab during the subsequent angiogenic remodeling process. The effects of rGO content and crosslinking density on conductivity, penetration capacity, and stimulus-assisted release profile were investigated.

Conclusion

This work presents a localized combination-therapy platform that integrates an electroconductive microneedle device with sequential dual-drug delivery for psoriasis management. The proposed system may offer a minimally invasive alternative to repeated topical or systemic administration and may be adaptable to other chronic inflammatory skin disorders.

Acknowledgements

This work was prepared within the scope of the TUSEB A3 Doctoral Students Project Support Program, Project No 47233. Gülşah TORKAY ÇAY is supported by TUBITAK 2211-E 2023/2.

References

[1]Moawad F., Ruel Y., Pouliot R., Brambilla D. Microneedle Technology in Psoriasis Management: Mechanistic Insights, Technological Innovation, Clinical Progress, and Challenges. *Advanced healthcare materials* 2025; e04294.

D3 – P109

Vanillin-functionalized carboxymethyl cellulose/PAM semi-IPN hydrogels for strain-sensitive sensors

Pauliuc C.G., Trandaș A.N., Bîru E.I., Iovu H.
Advanced Polymer Materials Group, National University of Science and Technology Politehnica of Bucharest, Romania

Introduction

Wearable sensors and next-generation flexible bioelectronics have advanced due to the rapid development of stimuli-responsive or smart materials. Among these materials, the inherent biocompatibility of hydrogels, adjustable viscoelasticity, and tissue-like softness make them the perfect interface between gadgets and the human body. Because strain-sensitive hydrogels can consistently convert mechanical deformations into measurable data, they have become essential elements for ongoing physiological monitoring and human motion tracking ranging from tiny facial expressions and pulse monitoring to macroscopic joint articulation. However, it is still very difficult to create hydrogels with high stretchability, high strain sensitivity, self-healing properties, and long-term electrical stability under cyclical body movements. We created a semi-interpenetrating polymer network (semi-IPN) hydrogel to close this gap using the structural synergy between a flexible synthetic network of polyacrylamide (PAM) and a stiff biopolymer (carboxymethyl cellulose (CMC)).

Materials and methods

Using a coupling method, vanillin (VA) was first added to CMC while carefully maintaining the free aldehyde groups unmodified to facilitate the development of dynamic Schiff base interactions in the network. FTIR and NMR spectroscopy were used to demonstrate this successful functionalization. Then, using a KPS/$FeSO_4$ redox system to begin the polymerization of acrylamide in the presence of the CMC-VA, the semi-IPN hydrogel was created.

Tube inversion tests and rheological analysis were used to assess the gelation kinetics, and frequency sweeps were carried out to assess the viscoelastic properties of the resulting networks. Tensile strength and elongation at break were measured by mechanical testing in order to assess structural integrity during deformation. Additionally, by connecting an LCR meter to a universal testing machine, the electro-mechanical sensing properties were evaluated. This allowed for the real-time monitoring of relative resistance changes $\Delta R/R_0$ under different dynamic strain profiles.

Results

The effective grafting of vanillin onto the CMC backbone and the development of stable semi-IPN architecture were validated by structural characterization. According to mechanical testing, the hydrogels have highly adjustable viscoelastic characteristics that combine strong tensile strength and stretchability to withstand considerable deformation without breaking down. Electromechanical testing proved the hydrogel's remarkable sensing abilities. Under different strain profiles controllable, the material showed a very sensitive and repeatable shift in relative resistance ($\Delta R/R_0$). The precise, real-time tracking of certain human joint motions, such as finger, elbow, and knee flexion, effectively shown practical applicability.

Conclusions

In conclusion, a highly promising tissue-mimicking material for flexible bioelectronics is produced by the synergistic integration of the vanillin-modified CMC within the PAM network. This platform provides the mechanical resilience and electromechanical sensitivity needed for real-time human motion monitoring.

D3 – P110

Smart nanoformulations for biopesticide's encapsulation in sustainable viticulture

Fernandes M.M.[1,2,3]

[1]Center for Micro-Electro Mechanical Systems, University of Minho, Guimarães, Portugal; [2]LABBELS-Associate Laboratory in Biotechnology and Bioengineering and Microelectromechanical Systems, University of Minho, Braga, Portugal; [3]Mads Clausen Institute, NanoSYD, University of Southern Denmark, Sønderborg, Denmark

Introduction

The increasing demand for sustainable agricultural practices requires alternatives to conventional chemical pesticides, which are associated with environmental pollution and resistance development. The development of innovative nanoformulations for biopesticides, aiming to enhance their stability, efficacy, and controlled delivery, is the focus of the European project VINNY. By integrating bioactive compounds derived from natural and circular sources into advanced nano-enabled systems, VINNY contributes to reducing agrochemical inputs while improving crop protection and productivity.

Materials and Methods

Bioactive compounds, including plant-derived volatiles, phenolic extracts, and bio-oil obtained from the condensation of biochar pyrolysis processes, have been encapsulated into nanoformulations using ultrasonic sonochemistry techniques and biodegradable biopolymers such as poly(3-hydroxybutyrate-co-3-hydroxyvalerate) (PHBV). These systems are designed to improve stability, protect active compounds from degradation, and enable controlled release. The nanoformulations are characterized in terms of physicochemical properties, encapsulation efficiency, and release kinetics. Their biological performance is evaluated through antimicrobial and antifungal assays, as well as plant protection studies under controlled and field conditions.

Results

The developed nanoformulations demonstrate enhanced stability and controlled release of bioactive compounds, leading to improved efficacy compared to non-encapsulated counterparts. Significant antimicrobial and antifungal activity has been observed, alongside positive effects on plant protection and health. These systems also show reduced environmental impact due to their biodegradability and the lower dosages required.

Conclusion

The VINNY project provides a novel platform for the development of sustainable biopesticides through nanoformulation strategies. By improving delivery efficiency and reducing environmental footprint, these systems represent a promising alternative to conventional agrochemicals, supporting the transition towards more sustainable and resilient agricultural systems.

Acknowledgements

This work was supported by European commission for VINNY project (ID:101130039).

D3 – P111

Short electrospun magnetic PCL fibres for minimally invasive anisotropic filling of bone defects

Honrado N.[1], Glushchenko V.[1,2], and Nguyen L.[1]
[1]Division of Biomaterials and Tissue Engineering, Eastman Dental Institute, University College London; [2]Division of Surgery and Interventional Science, University College London, UK

Introduction: The treatment of large bone defects, such as those created by osteosarcoma growth and wide surgical resection, remains a major clinical challenge, with gold-standard approaches like autologous or allogeneic bone grafts being limited by donor site morbidity, risk of immune rejection, and donor scarcity. Electrospun nanofibers are versatile biomaterials which have been widely explored in tissue regeneration and controlled drug delivery due to their high surface area-to-volume ratio and tuneable, ECM-like architecture. When aligned, they can recapitulate the anisotropic architecture of bone tissue and provide directional mechanical and topographical cues to enhance osteogenic differentiation. While these membranes are typically surgically implanted, incorporating discrete electrospun fibres as reinforcing fillers within injectable gels may allow for minimally invasive delivery while maintaining anisotropic reinforcement. Iron oxide nanoparticles (IONPs) can impart these discrete nanofibers with magnetic-responsive alignment, while simultaneously promoting osteogenic differentiation and enhanced bone repair.

Aim

Our aim is to develop a fabrication route for magnetically responsive short electrospun polycaprolactone (PCL) fibres intended as anisotropic reinforcing elements for injectable bone-repair hydrogels, with potential future combinatorial applications in IONP-based mild magnetic hyperthermia.

Materials and Methods

Magnetic PCL nanofibers (mPCL) are prepared by loading electrospinning solutions at varying IONP concentrations (%w/w), then electrospinning onto a thin water-soluble PVA film cast on aluminium foil and wrapped around a rotating mandrel. Short mPCL (smPCL) of varying lengths are obtained by cryocutting mPCL/PVA bilayer rolls frozen in OCT, followed by subsequent purification. Physicochemical characterisation of samples is conducted with SEM, SEM-EDX, DSC, FTIR, TEM, and DMA. Samples' IONP content is assessed with UV-Vis, and their magnetic properties are investigated with VSM and brightfield imaging under an external magnetic field. MC3T3-E1 cells are cultured under varying IONP, mPCL and smPCL concentrations, and subjected to CCK-8, Live-Dead, and ALP activity assays.

Results

Electrospun PCL fibres were successfully converted into discrete short fibres by cryocutting with a PVA support layer (Fig. 1). This approach preserved fibre morphology and generated short fibres with dimensions suitable for dispersion within an injectable matrix. TEM demonstrated homogeneous incorporation of 5% w/w IONPs within the electrospun PCL fibres, supporting successful fabrication of magnetic composite fibres.

Conclusion

These findings establish a feasible method for producing magnetically responsive short PCL fibres for anisotropic reinforcement of injectable biomaterials. This platform may support minimally invasive filling of irregular bone defects and has future potential as a local adjuvant strategy for osteosarcoma-associated bone repair.




***Figure 1**. **(a-b)** Discrete short PCL nanofibers cryosectioned to a nominal length of (a) 20 µm and (b) 100 µm, exhibiting average fibre lengths of (a) 32.21 ± 15.97 µm and (b) 104.14 ± 32.69 µm, respectively (n=40). **(c)** TEM images of PCL nanofibers loaded with 5% w/w IONP. **(d-e)** SEM images of (d) aligned PCL nanofibers electrospun directly onto a rotating mandrel and (e) short PCL fibres (agglomerated under vacuum) after cryosectioning to a nominal length of 100 µm.*

D3 – P112

Creation of protamine-heparin polyelectrolyte complex-loaded thermo-responsive PHEMA-NIPMA hydrogel for cardiovascular stents coatings

Akkaya B.[1], Akkaya R.[2]
[1]Dept. Molecular Biology and Genetics, Cumhuriyet Univeristy; [2]Dept. Biophysics, Cumhuriyet Univeristy, Sivas, Turkey

Introduction

Cardiovascular stents generally have problems such as acute thrombosis and late restenosis due to poor blood compatibility and uncontrolled drug release [1]. Conventional heparin coatings exhibit limited stability and uncontrolled release [2]. The present study aims to overcome these drawbacks by developing a novel, smart and versatile copolymeric coating of poly(2-hydroxyethyl methacrylate-co-N-isopropylmethacrylamide) [PHEMA-NIPMA] functionalised with protamine-heparin polyelectrolyte complexes (PECs). The technology is based on pure ionic interactions rather than toxic crosslinkers like glutaraldehyde and offers a green chemistry approach for better hemocompatibility and temperature-triggered continuous therapeutic administration.

Materials and Methods

The thermo-responsive PHEMA-NIPMA copolymer was prepared by free radical polymerisation [2]. The natural electrostatic interaction between highly cationic protamine and highly anionic heparin was used to form self assembled PECs in order to avoid chemical-coupling toxicity (e.g. EDC/DCC or glutaraldehyde). The resulting nanocomplexes were physically entrapped into PHEMA-NIPMA hydrogel matrix. Surface morphology, chemical structure FTIR and lower critical solution temperature (LCST) were well characterised. In vitro release kinetics of heparin were investigated at room temperature and physiological temperature (37^{o}C).

Results

FTIR and DSC analyses evidenced the function of PHEMA-NIPMA structure. At 37 ^{o}C the NIPMA segments collapsed to a hydrophobic state which effectively reduced the initial burst effect and limited uncontrolled diffusion. This smart mechanism provided a long and steady release of active heparin for a long duration, obtaining the necessary local antithrombotic concentration.




Figure 1. FTIR-ATR of P(HEMA-NIPMA)




Figure 2. DSC of P(HEMA-NIPMA)

Conclusion

The synergy of the components of the developed platform provides true multifunctionality. The hydrophilic PHEMA backbone then passively acts as an anti-fouling barrier that prevents the non-specific plasma protein adsorption. The collapsing NIPMA units actively regulate smart gating of the therapeutic cargo. In addition, the PECs that are part of the construct have two biological functions: heparin activates antithrombin III to prevent acute clot formation, and protamine inhibits hyperproliferation of vascular smooth muscle cells, thereby reducing restenosis [4]. Crucially, the crosslinker-free formulation does not cause cellular cytotoxicity, which makes the matrix very biocompatible and compliant with regulatory standards.

This work effectively illustrates a multifunctional, biocompatible, and stimuli-responsive stent coating. This platform has great potential for safer next-generation drug-eluting cardiovascular devices by balancing green engineering with smart polymers.

Acknowledgements

This study is funded by TÜBİTAK 1001 124Z389.

References

[1]Wen Y., Li Y., Yang R., Chen Y., Shen Y., Liu Y., Liu X., Zhang B., Li H. Biofunctional coatings and drug-coated stents for restenosis therapy. *Mater Today Bio* 2024 Sep 19; 29; 101259.

[2]Zhang X., Wang M., Liu L., Yu H., Liu Y., Duan X., Wang L., Shi H., Luan S. Hydrophobic-modified heparin coatings with adaptively anti-thrombotic and anti-bacterial functions for interventional cardiovascularcatheters. *Chemical Engineering Journal* 2025; Volume 514; 163278.

[3] Akkaya R., Ulusoy U. Preparation and Characterization of Poly(acrylamide/maleic acid)-based hydrogels Composites Hacettepe J. *Biol. & Chem.* 2011; 39 (4); 359–370.

[4]Ishihara M., Kishimoto S., Takikawa M., Hattori H., Nakamura S., Shimizu M. Biomedical Application of Low Molecular Weight Heparin/Protamine Nano/Micro Particles as Cell- and Growth Factor-Carriers and Coating Matrix. *Int. J. Mol. Sci.* 2015; 16; 11785-11803.

D3 – P113

Development of a gingiva-adhesive injectable hydrogel loaded with biosynthesized silver nanoparticles for periodontal applications

Lethongkam S.[1], Paosen S.[1], Voravuthikunchai SP.[2]
[1]Center of Antimicrobial Biomaterial Innovation-Southeast Asia, Faculty of Science, Prince of Songkla University; [2]Division of Biological Science, Faculty of Science, Prince of Songkla University, Thailand

Introduction

Periodontal disease is an inflammatory condition affecting the tooth-supporting tissues and remains a major global oral health concern. It is mainly caused by pathogenic microorganisms within dental biofilms, such as *Enterococcus faecalis*, *Streptococcus mutans*, and *Candida albicans*. These pathogens trigger inflammatory responses in gingival tissues, leading to periodontal ligament destruction and eventual tooth loss if untreated. Conventional treatments often rely on antimicrobial agents such as chlorhexidine, sodium hypochlorite, hydrogen peroxide, and ethanol-based mouth rinses. However, prolonged use of these agents may cause adverse effects, including mucosal irritation and tooth staining.

Aim

To develop an injectable, gingiva-adhesive hydrogel incorporating biosynthesized silver nanoparticles (bio-AgNPs) as a novel approach for localized periodontal therapy.

Materials and Methods

Bio-AgNPs were synthesized using *Eucalyptus camaldulensis* leaf extract as reducing and stabilizing agents. Nanoparticle formation was confirmed by a characteristic UV–Vis surface plasmon resonance peak. The nanoparticles were incorporated into a poloxamer-based thermosensitive hydrogel. Antibacterial activity was evaluated using the zone of inhibition assay, while cytotoxicity and anti-inflammatory activity were assessed using the MTT and Griess assays, respectively.

Results

Successful formation of bio-AgNPs was indicated by a yellowish-brown color change and confirmed by a characteristic UV-Vis surface plasmon resonance peak at 436 nm. The nanoparticles were incorporated into a poloxamer-based thermosensitive hydrogel that remained flowable at room temperature and gelled at physiological temperature (37 °C), enabling localized retention within periodontal pockets. Collagen was added to support cell growth and tissue regeneration. Bio-AgNPs exhibited strong antimicrobial activity against oral pathogens, including *Porphyromonas gingivalis*, *C. albicans*, *S. mutans*, and *E. faecalis*, with MIC values ranging from 2-16 µg/mL and MBC/MFC values ranging from 8-64 µg/mL. The nanoparticles also demonstrated notable antioxidant activity in the DPPH assay, with an IC_{50} value of 0.559 ± 0.098%. The bio-AgNP-loaded hydrogel showed antimicrobial activity, with inhibition zones of 11.70 ± 0.42 mm against *S. mutans*. *In vitro* evaluation demonstrated good biocompatibility of the AgNP-loaded hydrogel toward RAW 264.7 macrophage cells in a concentration-dependent manner and significantly reduced nitric oxide production in lipopolysaccharide-stimulated cells.

Conclusion

The developed bio-AgNP-loaded gingiva-adhesive hydrogel showed promising potential for localized periodontal therapy by effectively controlling oral infections and reducing inflammation, supporting its application in periodontal disease treatment.

Acknowledgements

This work was supported by National Science, Research and Innovation Fund (NSRF) and Prince of Songkla University (Grant No. SCI6901307S).

D3 – P114

Cold atmospheric pressure plasma for surface functionalization to develop antibiofouling copolymer coating

Le Dauphin E., Durand H., Marcoux P.
Université Grenoble Alpes, CEA-Leti, France

Introduction

Bacterial resistance to antibiotics, also called antibioresistance, is increasing and "could cause 10 billion deaths each year by 2050" according to the World Health Organization[1]. Phagotherapy, which involves bacteriophages, is an alternative to antibiotics. These bacterial viruses are extremely specific to their bacterial hosts and, once infected, bacteria are lysed and release hundreds of new virions. Because of the high specificity of the host-phage interaction, a large phage library is needed. However, some studies[2,3] have recently highlighted difficulties associated with bacteriophage storage, notably due to vials material composition. Phage's suspension stability may be impacted, leading to the decrease of infectious titer by several decades over time which requires time-consuming measurements of infectious titer just before use. The aim of the study is to develop antibiofouling thin films that prevent bacteriophages, and other amphiphilic biomolecules such as proteins, from being adsorbed on the inner-walls of glass vials.

Materials and Methods

In order to develop this kind of coating, an atmospheric pressure plasma assisted deposition equipment is used to coat silicon substrate by plasma polymers. This technic enables to get rid of solvent, heat and vacuum use, compared to dip-coating or chemical vapor deposition techniques. PEG-like and zwitterionic compounds are generally cited as having a good antibiofouling potential[4]. Plasma copolymer ppEGDMA-co-DMAEMA (Ethylene glycol dimethacrylate -co- (dimethylamino)ethyl methacrylate) has been deposited from a mix of EGDMA and DMAEMA monomers. This plasma copolymer zwitterion has been formed by Propanesultone vaporization. It has been studied to determine if its antibiofouling ability against proteins and bacteriophages is strengthened by zwitterionic effect.

Results

In addition to thickness and wettability measurements, FTIR and XPS analysis support the coatings characterization to confirm the zwitterion formation. The Quartz Cristal Microbalance with Dissipation monitoring (QCM-D) is used to determine the adsorption kinetics of bacteriophages on functionalized substrates. Investigation of the coatings antibiofouling effect with the amphiphilic protein BSA (Bovin Serum Albumin) has been explored.

Conclusion

PEG-like and zwitterionic coatings have been studied in that way and appear to be promising candidates to overcome bacteriophages adsorption and reach the antibiofouling objective.

References

[1]No Time to Wait: Securing the Future from Drug-Resistant Infections. 2019.
[2]Richter Ł., Księżarczyk K., Paszkowska K. Adsorption of bacteriophages on polypropylene labware affects the reproducibility of phage research. *Scientific Reports* 2021; 11; 7387.
[3]O'Connell L., Roupioz Y., Marcoux P.R. Container material dictates stability of bacteriophage suspensions. *Journal of Applief Microbiology* 2022; 133 (2); 529-543.
[4]Yang R., Gleason K.K. Ultrathin Antifouling Coatings with Stable Surface Zwitterionic Functionality by Initiated Chemical Vapor Deposition (iCVD) *Langmuir* 2012; 28; 12266–12274.

D3 – P115

In vivo evaluation of the osteoconductivity of titanium surfaces coated with biodegradable magnesium alloy

Miyake R.[1,2], Shimabukuro M.[2], Shimogishi M.[1], Shibasaki M.[1], Terauchi M.[1], Kawashita M.[2], Marukawa E.[1]
[1]Regenerative and Reconstructive Dental Medicine, Graduate School of Medical and Dental Sciences, Institute of Science Tokyo; [2]Laboratory for Biomaterials and Bioengineering, Institute of Integrated Research, Institute of Science Tokyo, Japan

Introduction

In dental implants, rapid osseointegration is essential for shortening healing period. Although titanium (Ti) exhibits excellent mechanical properties and biocompatibility, untreated Ti surfaces do not actively promote osteoconductivity. To impart biological functions to Ti surfaces, we focused on magnesium (Mg) and calcium (Ca), which are biodegradable metalls. Mg and Ca dissolve in physiological environments, releasing ions that are beneficial for osteogenesis. In addition, dissolution reactions of these metals generate hydroxide ions, which lead to a local alkaline environment favorable for osteogenesis[1]. In this study, Mg–Ca alloy was coated onto Ti implant surfaces by magnetron sputtering (MS), and the osteoconductivity of the resulting surface was evaluated in vivo.

Materials and Methods

Tapered Ti implants (f1.5 mm x 9 mm) without coating (NT) and Mg–30Ca-coated implants (MC30) prepared by MS were used as samples. Surface morphology and roughness were characterized using scanning electron microscopy and laser microscopy. The samples were implanted into the proximal tibia of 11-week-old Sprague-Dawley rats. At 28 days after implantation, the tibiae were extracted. Sections were prepared and stained with Villanueva-Goldner method. Histological analyses were performed to quantify bone-to-implant contact and bone volume around the Ti implants. In addition, pull-out tests were conducted to evaluate implant fixation strength.

Results

Surface characterization revealed that Mg and Ca uniformly covered the Ti surface in MC30. Histological evaluation at 28 days revealed that mineralized bone volume around MC30 was significantly higher than that of NT (Figure 1). Furthermore, pull-out tests demonstrated significantly greater maximum pull-out force for MC30 compared with NT. These results indicate that the increased bone formation around MC30 enhanced implant fixation.

Conclusion

The Mg–Ca coating enhanced osteoconductivity of Ti surface, possibly through ion release during coating dissolution in vivo. Thick mineralized bone formation around the Ti surface resulted in improved implant fixation. Our findings provide fundamental insights into the surface design of Ti implant to improve osseointegration.

Acknowledgements

This study was supported by Cooperative Research Project of Research Center for Biomedical Engineering, METI R&D Support Program for Growth-oriented Technology SMEs (grant number JPJ005698).

References

[1]Miyake R., Shimabukuro M., Terauchi M., Marukawa E., Kawashita M. Osteogenic Effects of ion released from biodegradable metallic magnesium and calcium coating. *Advanced Biology* 2025; 9(12); e00401.

Figure 1. Villanueva-Goldner stained sections 28 days after implantation of (a,c) NT, (b,d) MC30. (a,b) Overviews and (c,d) magnified views of regions indicated by black squares in panels (a,b), respectively. “Ti” and “MB” in panels indicate the titanium implant and mineralized bone, respectively.

D3 – P116

The Au-coated stainless steel plates as effective platforms in LDI-MS analysis

Skowronski L.[1], Robotnik K.[2], Brzozowska W.[1], Rerek T.[1], Trykowski G.[3], Pomastowski P.[2]
[1]Division of Surface Science, Faculty of Chemical Technology and Engineering, Bydgoszcz University of Science and Technology; [2]Centre for Modern Interdisciplinary Technologies, Nicolaus Copernicus University, Torun; [3]Dept. of Materials Chemistry, Adsorption and Catalysis, Faculty of Chemistry, Nicolaus Copernicus University, Torun, Poland

Introduction

Matrix-assisted laser desorption/ionization mass spectrometry (MALDI-MS) is a key technique in modern analytical chemistry, enabling the detection of many compounds such as proteins, peptides, metabolites, pharmaceuticals, and environmental pollutants[1]. However, its application to low-molecular-weight analytes ($m/z < 500$) is limited due to matrix background signals.
In recent years, alternative approaches have been explored, including nanostructure-assisted laser desorption/ionization (NALDI), where nanostructures such as AuNPs or AgNPs serve as ionization-supporting substrates[2].

Aim

The aim of this study was to develop and evaluate reproducible gold nanostructure-based substrates prepared by thermal evaporation on stainless steel for improved detection of low-molecular-weight analytes using NALDI-MS.

Materials and Methods

The Au nanolayers of nominal thickness 2.5-20 nm were deposited on stainless steel (AISI316L) using the thermal evaporation method (2×10^{-5} mbar, 0.5 Å/s). The produced samples have been investigated using spectroscopic ellipsometry (SE), scanning electron microscopy (SEM), atomic force microscopy (AFM) and Fourier transform infrared spectroscopy (FTIR) techniques.
Powdered methionine and serine standards were dissolved in water. A 0.5 µL aliquot of each solution was placed on a gold-coated steel plate, dried, and analyzed using a mass spectrometer (Bruker ultrafleXtreme, SmartBeam II laser).

Results

All of the produced Au layers exhibit nanogranular structure. Their optical resistivity decreases with the increase in the thickness of the film. The Au(5nm) and Au(10nm) samples produced the most complex spectra, suggesting that their surfaces offer the most favorable conditions for gold-assisted desorption/ionization. The primary adducts detected for all of the plates include $[M+H]^+$, $[M+Na]^+$, $[M+K]^+$ and $[M+Au]^+$ (where M is methionine or serine). Moreover, methionine fragmentation ions have been detected.

Conclusion

This study presents an alternative approach for preparing NALDI substrates using a thermal evaporation technique, to form gold nanolayers on stainless steel. The method enables precise control over film thickness, nanoparticle size and distribution. The resulting gold films are clean, uniform, and stable, making them suitable for the detection of low-mass analytes in NALDI-MS.

References

[1]Sekuła J., Nizioł J., Rode W., Ruman T. Gold nanoparticle-enhanced target (AuNPET) as universal solution for laser desorption/ionization mass spectrometry analysis and imaging of low molecular weight compounds. *Analytica Chimica Acta* 2015; 875m; 61-72.
[2]Iakab S.-A., Baquer G., Lafuente M., Pilar Pina M., Ramírez J.L., Ràfols P., Correig-Blanchar X., García-Altares M. SALDI-MS and SERS Multimodal Imaging: One Nanostructured Substrate to Rule Them Both. *Analytical Chemistry* 2022; 94 (6); 2785-2793.

D3 – P117
Variation of oxidation time by micro-arc in Ti-30Nb-5Mo alloy incorporating Cu ions

C.C.G., G.C.R.
UNESP - Univ. Estadual Paulista, Laboratório de Anelasticidade e Biomateriais, Bauru, Brazil

Introduction
Titanium alloys, especially β-type alloys, have been extensively studied for biomedical applications. However, more recently, there has been a need to better explore the surface functionalization of these materials to further improve their properties for use in medical devices. Among the surface modification techniques that can be used on titanium and its alloys is Micro-Arc Oxidation (MAO, also known as PEO). This technique allows the production of porous ceramic coatings on the metal surface, thereby modifying its characteristics by altering the oxidation parameters.

Aim
Therefore, this study aimed to oxidize the surface of the β-metastable Ti-30Nb-5Mo alloy by incorporating Cu into its surface. Part of this study was to investigate how varying the oxidation time altered the characteristics of the coatings produced.

Materials and Methods
The coatings were produced in an electrolytic solution containing calcium acetate, magnesium acetate, and copper chloride. A potential of 300 V was applied between the 10x0x1 mm^3 sample and a platinum foil, and the current was limited to 2.5 A. Oxidation times were 3, 5, and 10 minutes. The morphology and topography, chemical composition, wettability, and roughness of the coatings were analyzed.

Results
The morphology (Figure 1) of the coating pores was visibly altered by the oxidation time. The main difference is evident in the sample oxidized for 10 min, where oxide plates are observed on the surface, and the pores are visibly smaller.




Figure 1 – SEM images of the coatings

The coating thickness increased from approximately 26 µm to 55 µm, while the contact angle decreased, reaching less than 40° in the 10-minute-oxidized sample. With longer oxidation times, the coatings became rougher.

Conclusion
Variation in micro-arc oxidation time can significantly alter the properties of the resulting coatings, making it an important factor to consider when using this surface modification technique.

D3 – P118

Development of a novel antibiofilm coating based on catechol - 2 aminoimidazole conjugates

Maiti B.[1], Mhaskar H.[2], Srivastava M.G.[3], Braem A.[3], Steenackers H.[2], Van der Eycken E.V.[1], Coppola G.A. [1,2]
[1]Dept. of Chemistry, KU Leuven; [2]Centre of Microbial and Plant Genetics, KU Leuven; [3]Dept. of Materials Engineering, KU Leuven, Belgium

Introduction

Implant failure is often due to the formation of a bacterial biofilm on the implant's surface. There is a high demand for antibacterial coatings to prevent biofilm formation on implants. Recently, our lab has developed an anti-biofilm coating for titanium implants based on 2-aminoimidazole (2-AI). The coating procedure was multi-step and substrate-specific. Direct modification of catechol strategy has emerged as a powerful strategy for tailoring material properties and enabling diverse applications. We have developed catechol-bearing 2-aminoimidazole molecules (Cat-2-AI) for coating applications in a single step.

Aim

To develop coating for implant to combat orthopedic device related infection (ODRI).

Materials and Methods

The synthesis of conjugate molecules was optimized to accommodate different linking functionalities using various linker moieties. Coating formation conditions were optimized by varying the solvent system and oxidant proportion during polymerization. Thin films were deposited on glass substrates via dip coating (figure 1). Film thickness was measured by ellipsometry. Surface morphology and elemental composition were characterized using SEM–EDX. Biofilm inhibition was evaluated using a Calgary Biofilm Device assay.

Results

A linker between catechol and 2-aminoimidazole plays a crucial role in coating formation. Oxidative polymerization of catechol moiety using sodium periodate enables film deposition on glass surfaces, producing coatings with a thickness about 500–700 nm. EDX elemental analysis confirms the presence of 2-aminoimidazole within the coating. The coated glass slides demonstrate significant inhibition of adherence and biofilm formation by *E. coli* strains.




Figure 1 : Glass slides A: Blanck, B: coated with Cat-2-AI conjugates, and C: SEM image of coating

Conclusion

We present a novel catechol - 2-aminoimidazole coating as a fast and versatile alternative to multi step protocols. The coating can be applied on different surfaces, such as plastics, glass and metals. This will allow for a smooth implementation in orthopedics as well as other implantable devices.

Acknowledgements

This publication was funded by the European Union through the Horizon Europe Framework Program (HORIZON) under grant number 101057992.

D3 – P119

Species-dependent biofunctionalization of Ti6Al4V surfaces using microalgae-derived biomolecules

Hart M[1], Gutierrez Púa L.[3], Saez A[2], Paredes Mendez V.[3]
[1]Dept. of Mechanical Engineering, Universidad del Norte, Barranquilla; [2]School of Applied Sciences and Engineering, Universidad de EAFIT, Medellín; [3]Biomedical Engineering Dept., Universidad Simón Bolívar, Barranquilla, Colombia

Introduction

Surface biofunctionalization is a key strategy to enhance the biological performance of titanium-based biomaterials used in orthopedic and dental implants. Recently, natural biomolecules have gained attention as sustainable alternatives for developing bioactive coatings. Microalgae represent a particularly attractive source of proteins, polysaccharides, lipids, and bioactive compounds with potential biomedical functionality. However, the influence of microalgal species on the physicochemical characteristics of biofunctionalized metallic surfaces remains largely unexplored. To date, the biofunctionalization of metallic biomaterials using microalgae-derived biomolecules has been scarcely reported.

Aim

The aim of this study is to compare the biofunctionalization of Ti6Al4V surfaces using biomolecules derived from two microalgae species, Spirulina platensis and Scenedesmus, in order to identify species-dependent differences in the resulting surface chemistry and morphology.

Materials and Methods

Ti6Al4V substrates were activated using piranha solution to increase surface reactivity and subsequently functionalized with (3-aminopropyl)triethoxysilane (APTES). Biomolecules derived from Spirulina platensis and Scenedesmus were immobilized onto the surface as biomass and protein extracts at concentrations of 1–5 g/L and immersion times of 3 h and 14 h. The resulting surfaces were characterized by Fourier-transform infrared spectroscopy (FTIR), X-ray photoelectron spectroscopy (XPS), scanning electron microscopy (SEM), and energy-dispersive X-ray spectroscopy (EDS) to evaluate chemical composition and surface morphology (Figure 1).

Results

Surface characterization confirmed the successful immobilization of microalgae-derived biomolecules on Ti6Al4V. FTIR and XPS analyses revealed the incorporation of carbon-, oxygen-, and nitrogen-containing functional groups associated with proteins and polysaccharides. SEM observations revealed pronounced species-dependent differences in coating morphology. Coatings derived from *Spirulina platensis* produced heterogeneous aggregated structures consistent with the filamentous nature of this cyanobacterium, while *Scenedesmus*-derived coatings generated more homogeneous granular deposits. EDS analysis further confirmed the incorporation of bioorganic elements (C, O and N) associated with microalgal biomolecules The elemental composition and surface morphology were strongly influenced by both microalgal species and biomolecule type, indicating distinct biofunctionalization mechanisms for each system.

Conclusion

Both microalgae successfully generated biomolecular coatings on Ti6Al4V surfaces, confirming that microalgae-derived biomolecules can act as effective biofunctionalization agents for metallic biomaterials. The comparative analysis revealed a clear species-dependent biofunctionalization behavior, with *Spirulina platensis* producing heterogeneous aggregated structures and *Scenedesmus* generating more homogeneous granular coatings. These differences demonstrate that microalgal species selection significantly influences the resulting surface chemistry and morphology. Overall, this study highlights the potential of microalgae-derived biomolecules as sustainable platforms for tailoring bioactive coatings on titanium-based implants.




Figure 1. Schematic representation of Ti6Al4V surface biofunctionalization using microalgae-derived biomolecules.

D3 – P120

Impact of surface morphology on bacterial adhesion to polyethylene composites containing hybrid organo-inorganic clay mineral fillers

Klecandová L.[1,2], Antonowicz-Hubsh M.[3], Wilk K.[3], Alicja Kazek-KĘsik[4], Simha Martynková G.[1,2], Basiaga M. [3]
[1]Faculty of Materials Science and Technology, VSB—Technical University of Ostrava, Czech Republic; [2]Nanotechnology Centre, CEET, VŠB-Technical University of Ostrava, Czech Republic; [3]Silesian University of Technology, Faculty of Biomedical Engineering, Zabrze, Poland; [4]Dept. of Inorganic Chemistry, Analytical Chemistry and Electrochemistry, Silesian University of Technology, Gliwice, Poland

Introduction

Bacterial adhesion to polymeric surfaces is a critical concern in medical, water treatment, and packaging applications. Polyethylene (PE), while durable, is susceptible to microbial colonization due to its hydrophobic nature (1). Incorporating clay mineral fillers, such as montmorillonite or vermiculite, offers a promising strategy to modify surface properties and modulate bacterial interactions (2). Recent research highlights that the efficacy of these composites depends significantly on their surface morphology. The integration of hybrid organo-inorganic clay minerals alters the physical landscape, introducing specific topographical features and changes in surface roughness (3). Understanding this synergy between chemistry and morphology is essential for developing advanced materials with tailored antimicrobial properties (4).

Materials and Methods

Vermiculite (Brazil) and montmorillonite (Ivančice) were organically modified with chlorhexidine diacetate (1.0× CEC) and calcium-deficient hydroxyapatite (CDH) via wet precipitation. PE composites (Bralen VA 20-60) with 3 wt.% filler were compounded at 160 °C (HAAKE MiniLab 3) and pressed into 3 cm discs. Surface morphology and wettability were analyzed using optical profilometry (Sensofar S Neox) and contact angle measurements (Biolin Scientific). Bacterial adhesion assays used *Staphylococcus aureus* (4 h, 37 °C), with colonization visualized via SEM (Tescan VEGA).

Results

Pure PE (CA 80°) became more hydrophobic with unmodified clay (94.6°–97.5°). Organo-modification lowered the CA (86.4°–88°), while CDH-hybridization resulted in 90°–101°. Profilometry revealed that fillers, especially the organo-inorganic types, significantly reduced surface roughness compared to pure PE (Fig.1). Bacterial assays showed extensive colonization on pure PE and unmodified composites (Fig.2.). In contrast, organo-modified samples exhibited nearly zero bacterial adhesion, while the CDH-hybrid composite showed a significant reduction in attachment compared to the control.




Figure 1. Surface morphology of PE/VCA




Figure 2. PE-VCA surface with bacteria

Disscusion

The incorporation of clay fillers fundamentally redefines the PE surface environment. While unmodified clays increase hydrophobicity, organic and CDH modifications restore a more hydrophilic character. Crucially, the hybrid fillers smoothed the surface morphology, reducing available "shelter" sites for microbial anchoring. This decreased roughness, combined with the antimicrobial effect of chlorhexidine, synergistically inhibits *S. aureus* colonization.

Conclusion

In conclusion, hybrid organo-inorganic clay fillers represent a potent strategy for tailoring PE surfaces. The organo-modification drastically reduces bacterial adhesion, while the addition of CDH imparts bioactivity, making these composites ideal for advanced biomedical applications.

Acknowledgements

This paper was created as part of the project No. CZ.02.01.01/00/22_008/0004631. Materials and technologies for sustainable development within the Jan Amos Komensky Operational Program financed by the EU and project REFRESH – project number CZ.10.03.01/00/22_003/0000048 via the Operational Programme Just Transition.

References

[1]Al-Habaibeh A., Watkins M., Shah S., Wray D. Advanced Polymer Materials for Antimicrobial Applications. *Polymers* 2021; 13; 2361-2385.

[2]Jafari H., Danesh J., Garmabi H. Surface Modification of Polyethylene with Clay Nanoparticles: A Review of Recent Advances. *Journal of Materials Science* 2023; 58; 1120-1145.

[3]Pazourková L., Martynková G.S., Plachá D. Preparation and Characterization of Organo-Modified Clay Minerals for Polymer Applications. *Applied Clay Science* 2020; 188; 105509-105518.

[4]Klecandová L., Pazourková L., Martynková G.S. Antibacterial activity of clay mineral composites modified with organic agents and hydroxyapatite. *Materials Today Communications* 2022; 31; 103254-103265.

D3 – P121

Synergistic surface modification of hydroxyapatite with phytic acid and methacrylate for dental fillers

Buchwald Z.[1], Domke A.[1], Jakubowski M.[1,2], Buchwald T.[3], Sandomierski M.[1]
[1]Institute of Chemical Technology and Engineering, Poznan University of Technology; [2]Institute of Mechanical Technology, Poznan University of Technology; [3]Institute of Material Research and Quantum Engineering, Poznan University of Technology, Poland

Introduction

Hydroxyapatite, a calcium phosphate, constitutes the main inorganic component of the hard tissues of teeth and bones[1]. It has long attracted interest as a potential filler for resin-based dental composites. However, previous studies have indicated that experimental composites containing hydroxyapatite exhibit limited mechanical strength and, due to its hydrophilic nature, relatively low stability in aqueous environments[2]. One of the proposed strategies is the chemical modification of this potential filler. Since the primary components of the organic matrix in light-curable dental composites are methacrylate-based resins, it appears reasonable to modify the filler surface with a compound that also contains methacrylate functional groups.
Phytic acid, like hydroxyapatite, contains phosphate groups; however, it belongs to the class of organic compounds[3]. Our recent studies demonstrated that calcium and fluorinated derivatives of phytic acid represent a promising alternative to fillers used in resin-based dental composites, primarily due to their remineralization potential, defined as the ability to release calcium and fluoride ions[4]. However, when used as the sole filler in the composite, they proved suboptimal, owing to the relatively low flexural strength of the resulting composite and considerable water sorption during incubation[4].

Aim

The aim of this study was to modify hydroxyapatite using a methacrylate compound and phytic acid, to evaluate the use of these modified fillers in resin-based composites, and to assess the effect of the modifications on the physicochemical properties of the resulting composites.

Materials and Methods

Three different modification approaches were performed: using methacrylate alone, using phytic acid alone, and using both compounds in a single procedure. The effectiveness of the modifications was confirmed using spectroscopic and microscopic techniques, as well as thermogravimetry. Subsequently, the modified fillers were incorporated into light-curable resin-based composites, and their basic physicochemical properties were evaluated.

Results and Conclusions

The results demonstrated a synergistic effect of modification using both phytic acid and methacrylate, which yielded improved properties in the resulting composites compared to those containing hydroxyapatite modified with either modifier alone.

Acknowledgements

This work was produced with financial support from the National Science Centre, Poland (Sonata grant no. 2021/43/D/ST5/00888).

References

[1]Dorozhkin S.V. Bioceramics of calcium orthophosphates. *Biomaterials* 2010; 31; 1465-1485.
[2]Braga R.R. Calcium phosphates as ion-releasing fillers in restorative resin-based materials. *Dental Materials* 2019; 35; 3-14.
[3]Wang R., Guo S. Phytic acid and its interactions: contributions to protein functionality, food processing, and safety. *Comprehensive Reviews in Food Science and Food Safety* 2021; 20; 2081-2105.
[4]Buchwald Z., Domke A., Jakubowski M., Ratajczak M., Buchwald T., Özcan M., Voelkel A., Sandomierski M. Effect of calcium and calcium-fluoride phytate as active fillers in dental resin-based composites on chemical and physical properties. *Dental Materials* 2025; 41; 593-606.

D3 – P122
Electro-grafted organic interfaces for enhanced biointegration of implants

Maryam S.[1,2], Smołka S.[1,2], Patel T[1,2], Bogusz M.[1,2], Krukiewicz K.[1,3]
[1]Dept. of Physical Chemistry and Technology of Polymers, Silesian University of Technology; [2]Joint Doctoral School, Silesian University of Technology; [3]Centre for Organic and Nanohybrid Electronics, Silesian University of Technology, Gliwice, Poland

The development of biomaterials that promote biointegration is a key challenge in advancing tissue engineering strategies. Central to this objective is the precise control of surface chemistry at the biomaterial-cell interface, which governs cellular attachment, proliferation, and overall bio integration. When compared with other biomedical materials, metallic implants offer significant advantages, including high mechanical strength, durability, and resistance to damage. However, they remain susceptible to implant-associated infections due to bacterial colonization and biofilm formation. Although many antibacterial coatings have been explored to address this issue yet, such strategies may compromise biocompatibility and limit long-term clinical performance.

This study aims to develop bioactive, multifunctional coatings for metallic implants through the electrochemical deposition of diazonium, sulfonium and iodonium salts, as well as their mixtures. The proposed approach focuses on surface modification of commonly used biomedical metals, including platinum, stainless steel 316L, titanium, and Ti-6Al-4V, aiming to produce uniform coatings through a cost-effective electrodeposition process[1]. On the example of platinum, it has been shown that the presence of an organic layer results in 4.5-fold increase in the wettability of the surface and 1.5-fold increase in roughness, leading to the 84% decrease in bacterial adhesion without affecting surface's biocompatibility[2].
Although being ultrathin, fabricated organic interfaces are biocompatible, exhibit antimicrobial properties, as well as can prevent surface corrosion. Overall, this multifunctional coating strategy offers a promising approach to improving the safety, durability, and clinical performance of metallic implants.

Acknowledgements
The Authors would like to thank the National Centre for Research and Development for financial support *(LIDER15/0024/2024).*

References
[1]Skorupa M., Patel T., Krukiewicz K. Diazonium chemistry as a robust approach for the biofunctionalization of titanium surface. *Recent Advances in Computational Oncology and Personalized Medicine* 2022; 265.
[2]Skorupa M., Skonieczna M., Shyntum D.Y., Abdullah, Turczyn R., Asplund M., Krukiewicz K., Electrografted mixed organic monolayers as antibacterial coatings for implantable biomedical devices, *Electrochim. Acta 492* 2024; 144354.

D3 – P123

PEO–polymer–bioglass hybrid coatings for bioactivity and tribocorrosion improvement of Ti-6Al-4V

Soares P.[1], Laurindo C.A.H.[1], Madruga L.Y.[2], Popat K.[2]
[1]Dept. Mechanical Engineering, Pontifical Catholic University of Parana, Curitiba, Brazil; [2]Dept. Bioengineering, George Mason University, Fairfax, USA

Introduction

Metallic implants play a crucial role in various medical applications. Achieving rapid bone regeneration, preventing corrosion and wear, controlling metal ion release, and preventing infections are key objectives in implant development. However, osseointegration and implant durability can be affected by several factors.

Aim

This study focuses on the development of multifunctional coatings for metallic implants, particularly titanium alloys, to provide wear and corrosion protection, and bioactivity properties.

Materials and Methods

Oxidation of titanium alloy (Ti6Al4V) was performed using the plasma electrolytic oxidation (PEO) technique. Subsequently, a bioabsorbable polymer (PCL) film containing bioglass particles (BGs) was deposited on the oxidized surfaces. The coatings were characterized using scanning electron microscopy, energy-dispersive spectroscopy, X-ray diffraction, and contact angle measurements. Tribocorrosion tests were conducted in artificial saliva, and in vitro assessments of bioactivity were made.

Results

The PEO technique successfully produced oxide layers on titanium alloy, providing a suitable surface for subsequent polymer film deposition. The presence of BG particles enhanced the bioactivity of the coatings. Tribocorrosion tests revealed improved wear and corrosion resistance and reduced friction coefficients for the hybrid coatings compared to uncoated surfaces.

Conclusion

This study successfully developed multifunctional hybrid coatings for metallic implants, combining the PEO technique with bioabsorbable polymer films containing bioglass. The coatings exhibited enhanced tribocorrosion resistance, and bioactivity properties. These findings pave the way for the development of implant coatings with improved clinical performance, addressing the challenges associated with metallic implants.

Acknowledgements

This work was funded by CNPq and CAPES/PROEX.

D3 – P124

Antibacterial surface modifications of metallic implants using a polydopamine interlayer and the antimicrobial peptide HHC-36

Armatys P.[1], Burkiewicz Z.[2], Stodolak-Zych E.[1]
[1]AGH University of Krakow, Faculty of Materials Science and Ceramics; [2]AGH University of Krakow, Faculty of Electrical Engineering, Automatics, Computer Science and Biomedical Engineering, Poland

Introduction

The growing problem of antibiotic resistance is one of the most serious threats to public health, creating an urgent need to develop alternative strategies for preventing infections. Naturally derived materials, such as antimicrobial peptides (AMPs) have been intensely researched worldwide for this purpose – biomimetic molecules capable of effectively combating a broad spectrum of pathogens while reducing the risk of resistance. This paper presents the surface modification of titanium implants with the antimicrobial peptide HHC-36 to obtain antibacterial properties while maintaining the material's biocompatibility.

Materials and Methods

The polydopamine interlayer (PDA-I) was deposited on Grade 2 titanium plates in a two-step process involving initial etching and oxidation of the surface in 36% HCl and 30% H2O2, followed by a 24-hour incubation in a 2mg/ml dopamine solution. The modified and unmodified surfaces were incubated in a 2mg/ml HHC-36 antimicrobial peptide solution to immobilize the peptide on the surface. The efficiency immobilization and the effect of the PDA-I were determined using UV-Vis spectroscopy and QCM-D. Physicochemical properties were determined by measuring contact angle and surface free energy (SFE), as well as by SEM imaging and EDS analysis Microbiological properties were determined by assessing antimicrobial activity and biocompatibility testing on cell lines (RAW 243.7).

Results

The application of a polydopamine layer preserves the nanostructuring obtained during the oxidation process, while PDA-I significantly contributes to the increase in the number of AMPs attached to the material surface. The use of a PDA coating and AMP immobilization significantly affects the surface properties – the PDA-I causes an increase in the SFE (~35 mN/m to ~50 mN/m) with a simultaneous decrease in the polar component. AMP immobilization causes an increase in surface hydrophilicity (contact angle decreasing from ~85° to ~65°) and a significant increase in the polar component of the SFE. Bacterial studies demonstrated excellent antimicrobial properties of the HHC-36 peptide, reaching ~99% bacterial reduction for *Escherichia coli* and *Staphylococcus aureus*. For surfaces modified with the HHC-36 peptide, the reduction rate ranged from 30% to 60%. PDA-I increased the bacterial reduction, particularly for *Staphylococcus aureus*. Cellular studies demonstrated no cytotoxicity of the modified coatings

Conclusion

Modification of titanium substrates with AMPs offers an interesting alternative to antibiotic therapy, providing biocidal properties while maintaining biocompatibility. The PDA-I promotes increased protein attachment, enhances biocidal properties and extends the duration of the biocidal properties due to protein immobilization. Further research is needed to optimize the amount of protein attached to the surface for optimal biological properties.

D3 – P125

Long-term degradation behavior of ciprofloxacin-loaded PEO/P(L/G/TMC) hybrid coatings on WE43 magnesium alloy

Rynkus B.[1], Sowa M.[2], Wilk K.[1], Orłowska A.[1], Nowińska K.[3], Jaworska J.[4], Szewczenko J.[1]
[1]Dept. of Biomaterials and Medical Device Engineering, Silesian University of Technology, Zabrze; [2]Dept. of Inorganic Chemistry, Analytical Chemistry and Electrochemistry, Silesian University of Technology, Gliwice; [3]Dept. of Applied Geology, Silesian University of Technology, Gliwice; [4]Centre of Polymer and Carbon Materials, Polish Academy of Sciences, Zabrze, Poland

Introduction

Biodegradable magnesium alloys are promising materials for temporary orthopedic implants due to their favorable mechanical properties and gradual degradation under physiological conditions[1]. However, rapid degradation, localized corrosion and implant-associated infections may compromise implant stability before tissue healing[2]. Therefore, multifunctional surface modifications combining degradation control with local antibacterial functionality are of great importance.
This study aimed to evaluate the long-term degradation behavior and surface stability of ciprofloxacin-loaded hybrid coatings on WE43 magnesium alloy. Particular attention was paid to the effect of a calcium-phosphate PEO layer and an additional P(L/G/TMC) polymer coating containing ciprofloxacin on surface morphology and ion release during immersion for up to 9 weeks.

Materials and Methods

Three types of samples were investigated: unmodified WE43 magnesium alloy, WE43 coated with a calcium-phosphate plasma electrolytic oxidation layer, and WE43 modified with a hybrid coating composed of a PEO layer and a ciprofloxacin-loaded P(L/G/TMC) polymer layer. Initial surface morphology and chemical composition were characterized by SEM/EDS, while FT-IR spectroscopy confirmed the presence and distribution of the polymer-based drug-loaded layer. The samples were immersed in physiological medium for 3, 6 and 9 weeks. After each period, surface morphology was examined by SEM, and degradation was further evaluated by ion release into the medium.

Results

Initial SEM observations showed that PEO treatment produced a developed porous oxide layer, whereas deposition of the P(L/G/TMC)+CIP coating partially filled the pores, resulting in a less porous and more homogeneous surface. EDS confirmed the chemical changes induced by surface modification: the PEO layer was enriched in phosphorus and calcium, while the hybrid-coated surface was dominated by carbon and fluorine. FT-IR revealed bands assigned to the polymer coating and ciprofloxacin, confirming successful formation and uniform distribution of the hybrid layers. After immersion, unmodified WE43 exhibited the most pronounced degradation, with progressive accumulation of degradation products. The PEO layer reduced surface degradation, however, prolonged immersion led to coating deterioration, crack formation and local substrate exposure. In contrast, hybrid-coated samples showed no major morphological changes throughout immersion. Ion release analysis confirmed the highest release of alloying element ions from unmodified WE43, while PEO reduced ion release and the additional polymer layer further limited this process.

Conclusion

The ciprofloxacin-loaded PEO/P(L/G/TMC) hybrid coating improved the long-term surface stability of WE43 magnesium alloy and provided the most effective reduction in ion release. This coating system may be a promising strategy for biodegradable orthopedic implants requiring controlled degradation and local antibacterial functionality.

References

[1]Singh J., Hashmi A.W., Ahmad S., Tian Y. Critical review on biodegradable and biocompatibility magnesium alloys: Progress and prospects in bio-implant applications. *Inorganic Chemistry Communications* 2024; 169; 113111.
[2]Kumar S., Katyal P., Chaudhary R.N., Singh V. Assessment of factors influencing bio-corrosion of magnesium based alloy implants: A review. *Materials Today: Proceedings* 2022; 56; 2680-2689.

D3 – P126

Engineering bioactive PEEK surfaces via peptide grafting for enhanced tissue integration and antibacterial performance

Sczesny N.F.[1,4], Chevallier P.[1], Rodziewicz-Motowidło S.[2], Vuillaume P.[3], Marcoux P.L.[3] Houde V.[4], Mantovani, D.[1]

[1]Laboratory for Biomaterials and Bioengineering, Canada Research Chair Tier I, Dept. of Mineral Metallurgical and Materials Engineering and University Hospital Center de Quebec Research Center, Division Regenerative Medicine, Laval University, Canada; [2]Dept. of Biomedical Chemistry, Faculty of Chemistry, University of Gdańsk, Poland; [3]COALIA, Thetford Mines, Canada; [4]Groupe de Recherche en Écologie Buccale (GREB), Faculty of Dental Medicine, Laval University, Quebec, Canada

Introduction

Dental implants are widely used to restore oral function and improve patients' quality of life; however, implant failure remains a major clinical challenge. This is partly attributed to the mechanical mismatch between titanium, the current gold standard in dental implantology, and bone, which may lead to stress shielding and long-term complications[1]. Polyetheretherketone (PEEK) has emerged as a promising alternative due to its bone-like mechanical properties, biocompatibility, and chemical stability. However, its intrinsic bio inertness and lack of antibacterial properties limit effective tissue integration and increase susceptibility to peri-implant infections[2]. This study aimed to develop a robust surface biofunctionalization strategy for PEEK through peptide grafting to simultaneously promote tissue integration and inhibit bacterial colonization.

Materials and Methods

A three-step surface modification protocol was developed: (1) surface roughening to achieve specific surface roughness for enhancing cell adhesion, (2) plasma-assisted amination to introduce reactive amine functional groups, and (3) covalent grafting of selected bioactive peptides via a linking arm immobilization. Candidate peptides were previously screened based on their cell proliferation and antibacterial potential. Surface characterization was performed using X-ray Photoelectron Spectroscopy (XPS), Fourier Transform Infrared spectroscopy (FTIR), Water Contact Angle (WCA), profilometry, and Scanning Electron Microscopy (SEM). Biological performance was evaluated in the presence of cells, bacteria and blood. Cellular responses were assessed through adhesion and proliferation assays, while antibacterial activity was investigated through Minimum Inhibitory Concentration (MIC) and direct antibacterial testing. Hemocompatibility was also conducted through hemolysis and clotting time to confirm the non-toxicity of modified surfaces and biomolecules.

Results

The developed protocol enabled tunable surface roughness and successful incorporation of amino functional groups through plasma treatment. At this step, modified surfaces showed improved wettability, favorable for cell interaction. Then, chemical analyses confirmed the efficiency of the grafting of specific peptides selected according to their antibacterial activity against *Streptococcus salivarius* and significantly enhanced Human Gingival Fibroblasts (HGFs) cell proliferation as shown in Figure 1. Additionally, the surface modification strategy showed high reproducibility, highlighting its potential for scalable implant manufacturing.

Conclusion

This study presents a chemically stable and reproducible platform for peptide functionalization on PEEK. The proposed approach enables the development of multifunctional dental implants with improved biological performance, combining enhanced tissue integration with reduced bacterial adhesion. These findings support the potential of biofunctionalized PEEK as a next-generation material for dental implant applications.

Acknowledgements

This work was partially funded by FRQ-Strategia, NSERC-Alliance, Prima-Quebec.

References

[1]Klinge B. *et. al*. Dental Implant Quality Register-A possible tool to further improve implant treatment and outcome. *Clin Oral Implants Res* 2018; 18; 145-151.

[2]Pidhatika B. *et. al.* Surface Modifications of High-Performance Polymer Polyetheretherketone (PEEK) to Improve Its Biological Performance in Dentistry. *Polymers* 2022; 14(24); 5526.




Figure 1. (A) Antibacterial performance of different peptides against *S. salivarius*, a primary colonizer associated with peri-implantitis, expressed as bacterial survival. The red line indicates the contamination threshold; all values below this line represent effective bacterial inhibition. (B) Effect of peptides on the proliferation of Human Gingival Fibroblasts (HGFs), a key cell type in gingival tissue. Asterisks (*) denote statistically significant differences compared to the control group, represented by the red line.

D3 – P127

Plasma-assisted Zn functionalization of a-C:H coatings on PDMS: Effect of matrix structure on mechanical stability

Yáñez-Hernández L.A.[1], Chevallier P.[1], Houssiau L.[2], Wiggers H.[3], Sarkissian A.[4], Mantovani D.[1]
[1]Laboratory for Biomaterials and Bioengineering, (CRC-Tier I), Dept Min-Met-Materials Eng., & Regenerative Medicine, CHU de Quebec, Laval University, Canada; [2]Namur Institute of Structured Matter (NISM), University of Namur, Belgium; [3]Laboratory for Biomaterials and Bioengineering (LBB-BPK), Associação de Ensino, Pesquisa e Extensão, BIOPARK, Toledo, Brazil; [4]Plasmionique Inc., Varennes, Canada

Introduction

Polydimethylsiloxane (PDMS) is widely used in biomedical devices such as catheters due to its flexibility, chemical stability, and biocompatibility. However, its low surface energy and high deformability hinder coating adhesion and limit surface functionalization. Hydrogenated amorphous carbon (a-C:H) coatings have emerged as promising candidates to modify PDMS surfaces; nevertheless, achieving mechanically compatible and stable coatings on soft substrates remains challenging. In addition, integrating bioactive elements such as zinc (Zn) within such coatings requires controlled deposition strategies. This study aimed to develop adherent a-C:H coatings on PDMS and evaluate plasma-assisted Zn functionalization with a focus on the relationship between carbon matrix structure, surface properties, and mechanical behavior.

Materials and Methods

Medical-grade PDMS substrates were processed in a custom tubular PECVD reactor. Oxygen plasma activation was followed by deposition of polymer-like carbon (PLC) and hydrogenated polymer-like carbon (PLCH) coatings. Zn functionalization was achieved via direct vapor-phase delivery of heated zinc acetylacetonate (130 °C) during the final stage of deposition. Coating thickness was determined by AFM step-height measurements. Surface morphology and roughness were evaluated by AFM, wettability by water contact angle (WCA), and elemental incorporation by SEM-EDX. Mechanical behavior was assessed through stress-relaxation tests up to 50% strain, followed by optical microscopy and AFM analysis of deformed surfaces. Stability was evaluated after 24 h of immersion in aqueous media. The potential antibacterial activity of Zn-functionalized coatings will be evaluated using direct and indirect contact assays based on CFU log reduction.

Results

Coating thickness ranged from 488.12 ± 54.29 nm to 109.67 ± 30.63 nm, with Zn incorporation leading to a reduction in film thickness, indicating a modification of the film growth mechanism. Moreover, Zn incorporation significantly reduced nanoscale roughness for both matrices, from 18 ± 4 nm to 4.6 ± 0.8 nm for PLC and from 5.5 ± 2.9 nm to 1.9 ± 0.2 nm for PLCH. Wettability exhibited matrix-dependent behavior: WCA decreased from 94.4 ± 1.3° to 89.0 ± 0.7° for PLC, while increasing from 88.6 ± 0.6° to 92.9 ± 1.3° for PLCH, suggesting differences in surface chemistry after functionalization. Under mechanical deformation, PLC-based coatings exhibited brittle cracking, whereas PLCH-based coatings developed periodic buckling patterns. AFM analysis of deformed Zn-PLCH coatings revealed wrinkle structures with a wavelength of 7.9 ± 0.7 µm and an amplitude of 254 ± 57 nm, indicating strain accommodation through out-of-plane deformation of the thin film on a compliant substrate. All coatings remained adherent after 24 h immersion, demonstrating short-term interfacial stability. Antibacterial evaluation is currently in progress.

Conclusion

This study confirms that matrix structure governs both surface properties and mechanical response of a-C:H coatings on PDMS. PLCH coatings exhibit superior mechanical compatibility through buckling rather than fracture, while Zn functionalization modifies surface roughness and wettability in a matrix-dependent manner. These results highlight the importance of coupling surface functionalization with mechanical design to develop stable coating platforms for soft biomedical devices.

Acknowledgements

This work was partially supported by the Natural Science and Engineering Research Council of Canada (Discovery and Alliance funds), the Quebec Ministry of Economy and Innovation (PRIMA funds), and the Research Center of the CHU de Quebec. D.M. is the Holder of a Canada Research Chair Tier I awarded to the Laboratory for Biomaterials and Bioengineering (2012 – 2026).

D3 – P128

Sustainable sericin–hyaluronic acid conjugate hydrogels via green Michael addition for regenerative applications

Salahtia S., Ma Q., Casadidio C., Censi R.
School of Pharmacy, University of Camerino, ChIP Chemistry Interdisciplinary Project Research Centre, Camerino, Italy

Introduction

Hydrogels are widely used as extracellular matrix (ECM)-mimicking biomaterials due to their high water content, three-dimensional structure, and ability to support cell adhesion and proliferation. Sericin, a water-soluble silk protein representing 20–30% of silk mass, exhibits antioxidant, anti-inflammatory, and cell-supportive properties but is largely discarded during silk degumming, generating significant industrial waste. In line with circular economy strategies, this study valorizes sericin extracted from discarded cocoons and raw silk floss (2023–2024 batches) and converts it into functional hydrogels using green chemistry. By introducing vinyl sulfone (VS) groups onto sericin and thiol groups onto hyaluronic acid (HA), we engineered a tunable Michael-addition crosslinked platform for regenerative medicine and drug delivery.

Materials and Methods

Sericin was extracted from seven batches of cocoons and silk floss (0.02 M Na_2CO_3, 100 °C, 1 h), followed by dialysis (MWCO 12–14 kDa) and lyophilization. Molecular weight and structural integrity were assessed by GPC, FTIR, DSC, and SEM. Thiolated HA (HASH) was synthesized via carbodiimide coupling with DTP and subsequent DTT reduction. Vinyl sulfonated sericin (SerVS) was prepared using two strategies: ester bond formation in DMSO (DS% 3–30%) and ether bond formation in aqueous NaOH via divinyl sulfone click chemistry (DS% 2–27%). Polymers functionalizations were verified by ^{1}H-NMR and sulfur quantification. Hydrogels were formed by mixing SerVS and HASH (15% w/w, -SH:-VS = 1:1). Gelation time was determined by vial inversion. Rheology (37 °C, 0.1–100 rad/s) evaluated viscoelastic properties. Crosslinking was analyzed by FTIR and Raman spectroscopy. Cytocompatibility was assessed in mesenchymal stem cells (MSCs) exposed to Ser-HA nanogels (50–200 µg, 48 h).

Results

Raw silk floss showed the highest extraction yield (26.0–26.6%), compared to white (17.5–18.5%) and yellow cocoons (18.8%), while FITR confirmed preserved protein backbone structure. Controlled VS functionalization was achieved in both systems, with sulfur content increasing linearly with DS% (Fiigure 1). Ester and ether linkages provide tunable degradation behavior. Gelation depended strongly on DS% where the optimized formulation (SerVS_3% + HASH_70%) gelled within 2 h. Rheology showed G′>G″ across frequencies, and increasing polymer concentration (6.6% to 9.9% w/w) enhanced storage modulus (10^3–10^5 Pa), indicating improved mechanical robustness. Raman confirmed Michael addition crosslinking without disulfide formation. Furhtermore, cytocompatibility studies demonstrated high MSC viability across all formulations where gels containing 5% SerVS significantly enhanced cell proliferation (*$p<0.05$) (Figure 2). The hydrophilic nature of HA contributed to a favorable microenvironment, supporting cell survival and confirming the suitability of the Ser-HA platform for regenerative and drug delivery applications.

Conclusion

This work presents a sustainable, tunable sericin–HA hydrogel platform derived from silk waste. Controlled functionalization enables precise modulation of gelation, mechanics, and degradation, while maintaining excellent cytocompatibility. The system shows strong potential for regenerative medicine, injectable scaffolds, and advanced drug delivery, integrating circular economy principles with high-performance biomaterial design.

Acknowledgements

This work was partially supported by the National Recovery and Resilience Plan (NRRP), Mission 4, Component 2, Investment 1.1, Call for tender No. 104 published on 2 February 2022 by the Italian Ministry of University and Research (MUR), funded by the European Union-NextGenerationEU-TANDEM—Tackling neurodegeneration with by-product-based-nanohydrogels for the nose-to-brain-delivery of natural bioactive compounds 2013 2025. PROJECT ID: 20222W7P7S-CUP: J53D23007270006. Grant Assignment Decree No. 1064 adopted on 18 July 2023 by the Italian Ministry of Ministry of University and Research (MUR).

D3 – P129

Cold plasma-assisted green electrospinning of gelatin/PVA scaffolds for sustainable biomaterials

Roldan E.
Dept. of Engineering, Manchester Metropolitan University, UK

Introduction

Electrospun gelatin scaffolds are widely investigated for tissue engineering, wound healing and regenerative medicine due to their biocompatibility and bioactivity. However, conventional processing frequently relies on hazardous organic solvents to stabilise jet formation, raising sustainability and safety concerns.

Aim

This study investigates whether cold atmospheric plasma (CAP) pre-treatment of aqueous systems can expand the electrospinnability window of fully water-based gelatin and gelatin/polyvinyl alcohol (PVA) solutions, enabling greener scaffold fabrication for biomaterials applications.

Materials and Methods

Gelatin (10% and 12% w/w) and PVA (12% w/w) solutions were prepared exclusively in distilled water and blended at PVA:gelatin mass ratios of 1:0, 2:1, 1:1, 1:2 and 0:1. Distilled water was pre-treated with CAP for 0, 2, 4 or 6 minutes prior to polymer dissolution, generating 40 formulations. Electrospinning was performed under optimised conditions (30 kV, 0.02 mL/min, 10 cm tip-to-collector distance, 30 °C, 45% RH).
Solution properties (pH, conductivity, surface tension and viscosity) were characterised before and after processing. Resulting scaffolds were evaluated morphologically (SEM), topographically (white-light interferometry), chemically (ATR-FTIR) and in terms of wettability. Multivariate statistical analyses were conducted to assess relationships between solution parameters and scaffold outcomes.

Results

CAP exposure exerted a composition-dependent influence on electrospinnability. Short treatments (2 min) destabilised PVA-rich solutions, causing bead formation and poor fibre continuity. In contrast, intermediate exposure (4 min) consistently produced uniform nanofibrous networks (≈200–350 nm diameter) with reduced bead defects across blends, effectively widening the operational window for aqueous electrospinning. Prolonged treatment (6 min) increased surface texturing and occasional fibre fusion, particularly in lower-viscosity formulations.
FTIR analysis confirmed progressive surface oxidation with CAP, evidenced by enhanced O–H/N–H stretching (~3300 cm^{-1}), attenuation of aliphatic C–H bands and the emergence of carbonyl functionalities (~1700–1730 cm^{-1}). These changes indicate increased surface polarity and functional group availability without compromising overall fibre integrity at optimal exposure times.

Conclusion

Cold plasma pre-treatment enables solvent-free, water-based electrospinning of gelatin/PVA scaffolds with controlled morphology and enhanced surface functionality. An intermediate CAP dose (~4 min) emerges as optimal, balancing electrospinability, structural integrity and surface activation. This strategy provides a scalable, green manufacturing route for bioactive electrospun scaffolds, supporting sustainable biomaterials development for regenerative medicine applications.

D3 – P130

Mechanical performance of cellulose nanofibril threads produced with different additions of carbon sources

Pires T.F.M.[1], Lima F.R.[1], Moulin J.C.[1], Araújo F.G.S.[1], Oliveira M.P.[1],Oliveira H.F.B.L.[2], Oliveira T.R.[1], Da Cruz J.T.S.[1], Oliveira M.P.[1]

[1]Dept. of Forest and Wood Sciences, Federal University of Espírito Santo, Jerônimo Monteiro; [2]Dept. of Chemical Engineering, Federal University of Espírito Santo, Alegre, Brazil

Introduction

Cellulose nanofibrils (CNF) exhibit high strength, low weight, stiffness, and biodegradability. The production of CNF threads is an innovative high-performance alternative whose properties can be enhanced through different treatments. Carbon sources can improve these properties due to their favorable characteristics, such as electrical conductivity and mechanical and thermal resistance. Thus, this study aimed to produce CNF threads incorporated with different carbon sources in order to improve their mechanical strength.

Materials and Methods

The threads were produced using CNF from bleached short-fiber pulp (4.5% w/w), sodium alginate (2% w/w), calcium chloride at a concentration of 1 mol L^{-1}, and hydroxypropyl methylcellulose (HPMC) (1% w/w). The carbon sources used were lignin and lignin-derived carbonaceous material at 3% of the CNF weight. The threads were produced by the wet-spinning method with the solvent in a continuous flow of calcium chloride. After fabrication, the threads were washed and oven-dried at 60 °C for 4 hours. The tensile test on the threads was performed according to ASTM D2256-21/2021. The thread diameter used to calculate the cross-sectional area was obtained with the aid of a confocal microscope.

Results

The tensile strength of the threads did not vary statistically among the different incorporated carbon sources (Figure 1a). Regarding tensile strain, there was a significant variation ranging from 2.64 to 24.32 mm/mm, depending on the treatment (Figure 1b). The thread containing lignin presented the highest value (24.32 mm/mm), indicating greater flexibility and elongation of the thread before rupture.




Fig. 1. Bleached CNF threads with the addition of different carbon sources. Tensile strength (A); tensile strain (B). Different letters indicate significant differences (Tukey, $p \leq 0.05$).

The addition of lignin generated a more compact structure with fewer pores (Figure 2C), contributing to improved tensile strain performance.




Fig. 2. Bleached CNF threads with the addition of different carbon sources. B: without carbon addition (A); CA: lignin-derived carbonaceous material (B); LI: lignin (C) at 500× magnification.

Conclusion
The addition of carbon sources did not increase tensile strength; however, lignin contributed to the deformation of the threads, making them more flexible.

Acknowledgements
To the Espírito Santo Research and Innovation Support Foundation and the Coordination for the Improvement of Higher Education Personnel for the granting of the scholarship.

D3 – P131

Effect of acetone treatment on the physicochemical properties of chicken feather fibers for sustainable composite applications

Oliveira H.F.B.L.[1], Oliveira T.R.[2], Araújo F.G.S.[2], Pires T.F.M.[2], Da Cruz J.T.S.[2], Oliveira M.P.[2]
[1]Dept. of Chemical Engineering, Federal University of Espírito Santo, Alegre; [2]Dept. of Forest and Wood Sciences, Federal University of Espírito Santo, Jerônimo Monteiro, Brazil

Introduction

The increasing generation of agroindustrial residues has intensified interest in the development of sustainable materials. Among these residues, chicken feathers are produced in large quantities by the poultry industry and represent an underutilized protein-rich biomass mainly composed of β-keratin. Feather fibers exhibit low density, hierarchical morphology, and good thermal and mechanical stability, making them promising reinforcements for polymer-based composites. Surface treatments have been investigated to improve the physicochemical properties of natural fibers and enhance their compatibility with polymer matrices. However, studies evaluating the influence of solvent treatments on the structural properties of chicken feather fibers (CFF) remain limited.

Materials and Methods

CFF were washed and dried. Part of the material was used untreated, while the remaining fibers were immersed in acetone for 1, 12 and 24h, then rinsed with running water and dried. The fibers were characterized to evaluate physicochemical changes induced by the treatment. Real density (RD) was determined by gas pycnometry, chemical functional groups were analyzed by Fourier transform infrared spectroscopy (FTIR), and thermal stability was evaluated by thermogravimetric analysis (TGA/DTG).

Results

The RD showed values of 0.3044 g·cm^{-3} for the 0h and 0.3255 g·cm^{-3} for the 24h samples. The increase may be associated with modifications promoted by the treatment, such as the removal of volatile constituents.

FTIR (Figure 1) confirmed that acetone-treated fibers showed an increased intensity of the broad band at 3200–3400 cm^{-1} (N–H stretching). A reduction in the bands at 2920 and 2850 cm^{-1} (C–H stretching), indicates partial removal of surface lipids. The preservation of the amide bands suggests that the keratin structure remained stable.

TGA/DTG (Figure 2) showed a typical degradation behavior of keratin-based materials. The first stage (30–150°C) was associated with the loss of moisture and volatile compounds. The second (250–380°C) corresponded to keratin decomposition, with a maximum degradation peak around 310–330°C. Above 380°C, carbonization occurred. Treated fibers exhibited a thermal profile similar to the untreated sample, indicating preservation of the keratin structure.




Figure 1. FTIR spectra of untreated and acetone-treated chicken feather fibers.




Figure 2. TGA and DTG curves of untreated and acetone-treated chicken feather fibers.

Conclusion

Acetone treatment promoted moderate physicochemical modifications in chicken feather fibers, mainly associated with the removal of surface lipids and volatile constituents, as well as a slight increase in fiber density. However, the characteristic structure and thermal stability of keratin were preserved. These results indicate that solvent treatment can modify the surface composition of feather fibers while maintaining their structural integrity, supporting their potential use as reinforcement in sustainable composite materials.

Acknowledgements

Brazilian Federal Agency for Support and Evaluation of Graduate Education (CAPES); Espírito Santo Research and Innovation Support Foundation (FAPES).

D3 – P132

Evaluation of maximum stress and modulus of elasticity in epoxy composites reinforced with bamboo particles

Oliveira T.R.[1], Araújo F.G.S.[1], Oliveira H.F.B.L.[2], da Cruz J.T.S.[1], Pires T.F.M.[1], de Carvalho F.A.N.[3], Amorim G.A.[3], Dias Júnior A.F.[1], Oliveira M.P.[1]

[1]Dept. of Forest Sciences, Federal University of Espírito Santo, Jerônimo Monteiro; [2]Dept. of Chemical Engineering, Federal University of Espírito Santo, Alegre; [3]Dept. of Forest Resources, Luiz de Queiroz College of Agriculture (ESALQ/USP), Piracicaba, Brazil

Introduction

Bamboo is a woody plant widely recognized for its sustainability, rapid growth, high carbon sequestration capacity, and favorable mechanical properties, presenting strong potential for several industrial applications. In recent years, an increasing substitution of plastics and wood by bamboo-based products has been observed, particularly in composite materials. However, expanding its technological use requires a deeper understanding of bamboo processing methods. In this context, the present study evaluated the use of *Dendrocalamus giganteus* culm residues as reinforcement in epoxy resin composites, investigating the effect of different particle proportions on the maximum stress and modulus of elasticity of the composites.

Materials and Methods

Residues from culms of *Dendrocalamus giganteus* were collected in the municipality of Jerônimo Monteiro, Espírito Santo, Brazil, and ground to obtain particles ranging from 0.25 to 0.43 mm, which were subsequently oven-dried at 105 °C for 24 h. The composites were produced using epoxy resin 2004 and hardener 3154 (2:1 w/w), incorporating bamboo particle contents of 20% and 40%. After an initial curing period of 24 h in silicone molds and a post-curing period of seven days, seven specimens were produced for each treatment. Flexural tests were conducted according to ASTM D790, and the data were analyzed by ANOVA followed by Tukey's test (5%) using the R software.

Results

The flexural test results indicated differences among the evaluated systems (Figure 1). Pure epoxy resin (RE) presented an average maximum stress of 37.36 MPa and an average flexural modulus of 0.91 GPa, with standard deviations of 4.08 MPa and 0.23 GPa, respectively. For the composites containing 20% bamboo (B20) particles, average values of 38.74 MPa for maximum stress and 1.44 GPa for flexural modulus were observed, with standard deviations of 2.08 MPa and 0.24 GPa. Composites produced with 40% bamboo (B40) particles showed an average maximum stress of 33.91 MPa and a flexural modulus of 1.18 GPa, with standard deviations of 2.59 MPa and 0.11 GPa. Overall, the values indicate variations in the mechanical parameters as a function of the proportion of particles incorporated into the polymeric system.




Figure 1. Flexural stress and flexural modulus of the composites produced with different proportions of bamboo fibers.

Conclusion

The incorporation of bamboo particles influenced the mechanical behavior of the composites, with the 20% fraction showing the highest flexural modulus and maximum stress values comparable to those of the pure resin.

Acknowledgements

The authors thank the Espírito Santo Research and Innovation Support Foundation (FAPES) for granting the research scholarship.

D3 – P133

Biosynthesis of iron nanoparticles through Bacillus subtilis cell-free extract for biomedical applications

Della-Flora I.K.[1,2], Cardoso M.M.[3], Machado-de-Ávila R.A.[3], Hotza D.[1], Andrade C.J.[1], Boccaccini A.R.[2]
[1]Dept. of Chemical Engineering & Food Engineering, Federal University of Santa Catarina, Florianópolis, Brazil; [2]Institute of Biomaterials, Dept. of Materials Science and Engineering, Friedrich-Alexander-University Erlangen-Nuremberg, Erlangen, Germany; [3]Postgraduate Program in Health Science, University of Extremo Sul Catarinense, Criciúma, Brazil

Introduction

Iron nanoparticles (FeNPs) are widely studied due to their unique physicochemical properties and potential applications in antimicrobial and drug delivery [1,2]. However, their performance is inherently related to the synthesis method. In this sense, chemical routes are efficient; however, they usually use toxic reagents, whereas biosynthesis uses natural extracts, such as microbial, a more sustainable and biocompatible alternative [2].

Aim

Therefore, this study aimed to synthesize FeNPs using biological and chemical methods and compare their physicochemical and biological properties.

Material and Methods

A cell-free extract (CFE) from *Bacillus subtilis* biomass was used for biosynthesis by mixing with iron (1:1) at pH 7 and 150 rpm for 24 h. Chemically synthesized FeNP (Chem-FeNP) was produced by coprecipitation with lauric acid as a capping agent. FeNPs were characterized by FTIR and TEM. Biological properties were evaluated through cytotoxicity (NIH3T3 cells), fluorescence microscopy, and antibacterial activity against *Escherichia coli* and *Staphylococcus aureus* at 1, 0.1, and 0.01 mg L^{-1} of FeNP.

Results

TEM analysis showed that Chem-FeNPs (10.75 ± 3.86 nm) were smaller than Bio-FeNPs (18.87 ± 9.03 nm) (Figure 1 a). FTIR (Figure 1 b) confirmed Fe–O bonds in FeNPs and revealed organic functional groups in Bio-FeNP, indicating proteins, lipids, and polysaccharides acting as capping agents.

Biological assays demonstrated that Bio-FeNPs exhibited no cytotoxicity, maintaining cell viability above 70% across all concentrations (Figure 2a). In contrast, Chem-FeNPs showed dose-dependent cytotoxicity, reducing viability below 70% at higher concentrations. Fluorescence imaging corroborated these findings (Figure 2 b). Antibacterial activity appears dose-dependent. Both FeNPs exhibited moderate activity against *E. coli* and stronger activity against *S. aureus* (Figure 2c).

Conclusion

The larger size of Bio-FeNPs is correlated to biomolecular capping layers, which can enhance stability and functionality. It is worth noting that Bio-FeNPs combined moderate antibacterial activity with no significant cytotoxicity. On the other hand, Chem-FeNPs showed stronger antibacterial activity and higher cytotoxicity. Therefore, biological synthesis improves cell compatibility while maintaining antibacterial performance.

Acknowledgements

The authors acknowledge the Conselho Nacional de Desenvolvimento Científico e Tecnológico (141108/2024-0) and the Fundação de Amparo à Pesquisa e Inovação do Estado de Santa Catarina for their financial support.

References

[1]Unalan I., Occhipinti I., Miola M., Vernè E., Boccaccini A.R. Development of Super-Paramagnetic Iron Oxide Nanoparticle-Coated Melt Electrowritten Scaffolds for Biomedical Applications. *Macromol Biosci* 2024; 24.
[2]Della-Flora I.K., de Andrade C.J. Biosynthesis of metallic nanoparticles by bacterial cell-free extract. *Nanoscale*. *Royal Society of Chemistry* 2023; 13886–908.

Figure 1. Transmission electron microscopy (TEM) images alongside corresponding histograms of nanoparticle size distributions (a) and Fourier Transform Infrared (FTIR) spectroscopy (b) of Bio-FeNPs in comparison with the Chem-Fens.





Figure 2. Cell viability of NIH3T3 fibroblast-like cells after 1 day of exposure to different concentrations (1, 0.1, and 0.01 mg L^{-1}) of FeNPs (a). Fluorescence microscopy images of cells after 7 days at the highest concentration (1 mg L^{-1}) of FeNP (b), stained with DAPI (cell nuclei, blue) and rhodamine–phalloidin (F-actin, red). Antibacterial activity of FeNPs against *Escherichia coli* and *Staphylococcus aureus* (c) exposure to different concentrations (1, 0.1, and 0.01 mg L^{-1}). Data were analyzed using ANOVA and Tukey's test ($p < 0.05$).



D3 – P134

Influence of chemical treatments on the density and surface morphology of sisal fibers for application in polymeric composites

da Cruz J.T.S.[1], Araújo F.G.S.[1], Oliveira T.R.[1], Oliveira H.F.B.L.[2], Pires T.F.M.[1], da Silva K.C.A.[3], Carmona I.N.[1], Dias Júnior A.F.[1], Oliveira M.P.[1]

[1]Dept. of Forest Sciences, Federal University of Espírito Santo, Jerônimo Monteiro; [2]Dept. of Chemical Engineering, Federal University of Espírito Santo, Alegre; [3]Dept. of Forest Resources, Luiz de Queiroz College of Agriculture (ESALQ), University of São Paulo, Piracicaba, Brazil

Introduction

In recent years, increasing environmental awareness has driven the development of sustainable materials capable of replacing conventional synthetic polymers. Among these, polymer composites reinforced with lignocellulosic fibers have gained prominence due to their low cost, renewability, and biodegradability. However, the hydrophilic nature of these fibers may lead to poor interfacial adhesion with the polymeric matrix, which can compromise the mechanical performance of the composite. Therefore, chemical treatments have been applied to modify the fiber surface and enhance the fiber–matrix interaction. In this context, the present study evaluated the influence of different chemical treatments on the density and surface characteristics of sisal fibers (*Agave sisalana*).

Materials and Methods

Natural sisal fibers were obtained in Jerônimo Monteiro, Espírito Santo, Brazil. After washing under running water, the fibers were oven-dried (103 °C for 7 days) and subjected to five conditions: untreated (*in natura*, control), 5% NaOH, 15% NaOH, 5% HNO_3, and acetylation. After the treatments, the fibers were washed until reaching a pH close to 7 and then oven-dried at 100 °C for 24 h. The relative density was determined by pycnometry in triplicate. The surface morphology of the fibers was evaluated using scanning electron microscopy (SEM).

Results

The density values obtained were 0.88 g cm^{-3} (IN NAT), 1.17 g cm^{-3} (NaOH-5), 0.85 g cm^{-3} (NaOH-15), 1.05 g cm^{-3} (HNO_3-5), and 1.04 g cm^{-3} (acetylation). The NaOH-5 treatment showed the highest mean density value, whereas NaOH-15 resulted in a reduction compared with the *in natura* material.

Scanning electron microscopy images revealed modifications in the surface morphology of the fibers after the treatments (Figure 1). Fibers treated with NaOH-15 exhibited a thinner and more disordered structure, whereas NaOH-5 showed a cleaner surface with fewer deformations. In the acetylation treatment, removal of the outer fiber layer and exposure of internal fibrillar structures were observed, increasing the surface area and favoring mechanical interaction at the fiber–matrix interface, in addition to reducing the hydrophilicity of the material.




Figure 1. Scanning electron microscopy images of IN NAT fibers (A), NaOH-5 (B), NaOH-15 (C), HNO_3-5 (D), and ACT (E).

Conclusion

The results demonstrated that chemical treatments influence both the density and the surface morphology of sisal fibers, promoting modifications at the fiber–matrix interface and highlighting their potential to improve the mechanical performance of composites.

Acknowledgements


To the Espírito Santo Research and Innovation Support Foundation (FAPES) and the Coordination for the Improvement of Higher Education Personnel (CAPES) for the granting of scholarship support.

D3 – P135

Integration of cellulose nanofibers in the formulation of PLA/HAp filaments: An alternative to their application as ECM

Estrella Estrella-Guisado G.[1], Luque J.M.[1], Ferrández A.[2,3], Gallego L.[4], Ferrari B.[2,3], González Z.[1,3]
[1]BioPrEn Group (RNM-940), Chemical Engineering Dept., Instituto Químico para la Energía y el Medioambiente (IQUEMA), Faculty of Science, Universidad de Córdoba; [2]Instituto de Cerámica y Vidrio, CSIC, Campus de Cantoblanco, Madrid; [3]Unidad Asociada CSIC-UCO, Fabricación aditiva de materiales compuestos basados en celulosa funcionalizada, obtenida de residuos de biomasa; [4]COLFEED4Print S.L, Madrid, Spain

The need for advanced biomimetic biomaterials is critical in tissue engineering due to the rising demand for bone grafts and the limitations of conventional methods. In this context, the combination of bio-based nanocellulose matrix and hydroxyapatite (HAp) has garnered significant interest because of the complementary advantages these materials offer [1]. Nanoellulose provides mechanical strength, flexibility, and biodegradability, while HAp contributes its bioactivity, biocompatibility, and osteoinductivity [2]. This study proposes a dual role of cellulose nanofibers (CNF) as a mechanical nano-reinforcement within the solid matrix and as a biomimetic supporter within a hydrogel phase for bone tissue engineering.
CNF were obtained through an integral biorefinery process of agro-industrial by-products, aligning the fabrication with circular economy principles and sustainability goals. To produce advanced filaments ensuring optimal integration, a colloidal route was developed to incorporate the CNF and HAp into a PLA matrix.



This formulation does not compromise the fused filament fabrication (FFF) process, instead, it significantly enhances the microstructural properties by creating a tailored porosity that increases the specific surface area. The 3D-printed scaffolds structural integrity and functional behavior were assessed. Degradation assays revealed that the presence of CNF facilitates a sustained and enhanced release of calcium ions, a critical factor for triggering osteogenic signaling pathways. Additionally, CNF exhibited a buffering capacity that mitigates the autocatalytic acidification typical of PLA degradation, thereby maintaining a physiological pH environment that optimized the conditions for bone ingrowth. Biological validation through cell viability studies confirmed their potential as safe and bioactive grafts. The synergy between HAp and the waste-derived CNF provides a sustainable, high-performance alternative for bone tissue engineering.

Acknowledgements
This research is supported by Ministerio de Ciencia, Innovación y Universidades (MCIN/AEI/10.13039/501100011033) from Spain through CPP2023- 010820 project.

References
[1]Deng J., Song Q., Liu S., Pei W., Wang P., Zheng L. et al. Advanced applications of cellulose-based composites in fighting bone diseases. *Compos Part B Eng.* 2022; 245; 110221 https://doi.org/10.1016/j.compositesb.2022.110221.
[2]Berrahou S., Latifi S., Saoiabi S. *et al.* Hydroxyapatite–cellulose composites: properties, fabrication methods, and applications. *J Mater Sci: Mater Med* 2026; 37; 27. https://doi.org/10.1007/s10856-025-06993-1

D3 – P136

Influence of chemical treatments on the mechanical performance of sisal fiber reinforced epoxy composites

Araújo F.G.S.[1], Oliveira H.F.B.L.[2], Oliveira T.R.[1], Pires T.F.M.[1], Da Cruz J.T.S.[1], Oliveira M.P.[1]
[1]Dept. of Forest and Wood Sciences, Federal University of Espírito Santo, Jerônimo Monteiro, Brazil; [2]Dept. of Chemical Engineering, Federal University of Espírito Santo, Alegre, Brazil

Introduction

The increasing demand for sustainable materials has encouraged the development of polymer composites reinforced with lignocellulosic fibers. Natural fibers are attractive due to their low cost, renewability, biodegradability and good mechanical properties. However, their hydrophilic nature can result in weak interfacial adhesion with polymer matrices, reducing composite performance. Chemical surface treatments are therefore applied to improve fiber–matrix interaction. This study aimed to compare the effects of different chemical treatments applied to sisal fibers on the tensile properties of epoxy composites.

Materials and Methods

Sisal fibers (*Agave sisalana*) were obtained from a supplier located in Espírito Santo, Brazil. The fibers were initially washed in running water to remove impurities and then oven-dried before the application of chemical treatments. Five experimental conditions were evaluated: untreated fibers (IN NAT), alkaline treatments with sodium hydroxide at 5% (NaOH-5) and 15% (NaOH-15), nitric acid treatment at 5% (HNO3-5), and acetylation (ACT). After each treatment, the fibers were thoroughly washed until reaching neutral pH and subsequently dried. Epoxy composites were produced using epoxy resin (2004) and hardener (3154) in a 2:1 ratio. Fibers were aligned within silicone molds and incorporated at a fiber volume fraction of 20%. Tensile tests of the composites were performed according to ASTM D638 using a universal testing machine EMIC, with a crosshead speed of 1 mm/min. The elastic modulus was calculated from the stress–strain curves.

Results

The tensile properties of the composites varied according to the chemical treatments applied to the fibers. Composites reinforced with untreated fibers presented tensile strength of approximately 48.99 MPa. The NaOH-5 treatment showed the highest tensile strength, followed by NaOH-15 and acetylation. In contrast, composites reinforced with nitric acid treated fibers presented the lowest tensile strength. Regarding stiffness, the elastic modulus ranged from approximately 1.26 to 1.76 GPa depending on the treatment. The NaOH-15 treatment resulted in the highest modulus, indicating improved fiber–matrix interaction compared with the other treatments.




Fig. 1. Tensile strength and young's modulus of sisal fiber reinforced epoxy composites under different chemical treatments. Different letters indicate significant differences (Tukey, $p \leq 0.05$).

Conclusion

Chemical treatments significantly influenced the mechanical performance of sisal fiber reinforced epoxy composites. Alkaline treatments improved tensile strength and stiffness, indicating enhanced fiber–matrix interaction, while nitric acid treatment reduced composite performance.

Acknowledgements

To the Espírito Santo Research and Innovation Support Foundation and the Coordination for the Improvement of Higher Education Personnel for the granting of scholarship support.

D3 – P137

Grape byproduct-based active packaging for UV protection of walnuts

Cinegaglia J.F.C.S[1,2], Dos Santos L.B[1,3], Oliveira C.D[1], Azeredo H.M.C.[3]
[1]Embrapa Instrumentação, São Carlos-São Paulo; [2]Federal University of São Carlos; [3]São Paulo State University (UNESP), Brazil

Introduction

Agro-industrial byproducts have emerged as promising sources of functional compounds for the development of sustainable active packaging. Grape residues are particularly attractive due to their high content of anthocyanins and other phenolic compounds, which provide antioxidant activity and UV-blocking capacity. The use of these compounds in packaging systems may help protect lipid-rich foods from photooxidation.

Aim

This study aimed to develop active packaging based on grape byproducts and to evaluate its UV-blocking capacity and effectiveness in reducing lipid photooxidation in walnuts.

Materials and Methods

Active films were produced by continuous casting from acid-pretreated grape processing byproducts combined with polysaccharides, especially pectin and carboxymethylcellulose. Briefly, the grape byproducts were dispersed in 0.1 M citric acid and hydrolyzed for approximately 16 h at 40 °C, with 30% glycerol added as plasticizer. The resulting film-forming dispersion was then homogenized, deposited onto a moving polyester substrate, and dried to obtain continuous films.

The UV-blocking capacity of the films was evaluated before and after UV exposure. Walnuts were exposed to UV radiation for 7 days under three conditions: direct exposure (control), polyethylene packaging, and packaging with the developed active films. Oil samples were collected at day 0 and day 7, and lipid oxidation was analyzed by ^{1}H NMR through the loss of signal intensity.

Results

The films showed high UV-blocking efficiency before exposure, with values above 96% in the UVA, UVB, and UVC regions. After UV exposure, UVA blocking decreased, while UVB and UVC protection remained high. This effect was accompanied by a visible color change, quantified by the total color difference ($\Delta E \approx 7 \pm 2$), indicating a significant alteration in the films' optical properties. This variation is associated with structural transformations of anthocyanins, particularly their conversion into chalcone forms.

Lipid oxidation analysis showed that control samples exhibited signal intensity losses of 51-63%, while polyethylene-packaged samples exhibited losses of 45-62%. In contrast, walnuts packaged in the active films showed lower losses, ranging from 33 to 44%, indicating reduced lipid degradation.



Figure 1. Representative films developed from grape byproducts used for walnut packaging.

Conclusion

Grape byproduct-based active packaging produced by continuous casting demonstrated effective UV-blocking properties and significantly reduced lipid photooxidation in walnuts. These results highlight its potential as a sustainable alternative for protecting lipid-rich foods, contributing to both food preservation and the valorization of agro-industrial residues.

Acknowledgements

The authors acknowledge FAPESP (process nº 2025/00653-1) for financial support.

D3 – P138

Development of polymeric biomaterials from banana pseudostem for sustainable packaging applications

Oliveira C. D.[1], Dos Santos L.B.[1,2], Cinegaglia J.F.C.S.[1,3], Azeredo H.M.C.[1]
[1]Brazilian Agricultural Research Corporation (Embrapa Instrumentation), São Carlos, Brazil; [2]Dept. of Food and Nutrition, São Paulo State University "Júlio de Mesquita Filho" (UNESP), Araraquara, Brazil; [3]Dept. of Chemistry, Federal University of São Carlos (UFSCar), Brazil

Introduction

Agro-industrial by-products have gained attention as sustainable alternatives for waste valorization and the production of value-added materials. The banana pseudostem, typically discarded after harvest, shows high potential due to its high fiber content and can be explored as a raw material for technological applications. In this context, the production of flour from this residue emerges as a promising strategy, contributing to environmental impact reduction and the circular economy. The incorporation of this flour into polymeric matrices, such as pectin, enables the production of biodegradable films with potential use in packaging. Thus, this study aimed to develop pectin-based films incorporating banana pseudostem flour, promoting the valorization of this agro-industrial residue.

Materials and Methods

Banana pseudostem flour was subjected to hydrothermal treatment by dispersion in water under agitation, followed by autoclave processing (121 °C/30 min at 1.2 kgf cm^{-2}) and cooling in an ice bath. Subsequently, glycerol (30%) and pectin (20%) were added (both concentrations based on dry flour mass). The mixture was homogenized, degassed under vacuum, and cast onto glass plates using a casting bar to obtain an initial thickness of 2 mm. The films were dried in an oven with air circulation at 50 °C for 20 h.

Results

The main properties of the films are presented in Table 1. The mechanical properties were comparable to those of similar materials reported in the literature, such as banana peel and carboxymethyl cellulose (CMC)-based films (Silva et al., 2024)[1]. The water vapor permeability also showed similar values. The contact angle (52°) indicates a hydrophilic surface (WCA < 90°), suggesting a high affinity for water, likely due to the presence of hydrophilic groups such as hydroxyls from pectin and banana pseudostem flour.

Table 1. Properties of banana pseudostem film.

Properties	Means*
σ (MPa)	2.66±0.57
ε (%)	2.46±0.42
E (MPa)	106.82±20.91
WVP (g.mm.kPa^{-1}.h^{-1}.m^{-2})	6.84±0.68
WCA (°)	52.32±1.32

*Means ± standard deviations (for at least 5 measurements of mechanical properties and at least 3 measurements for the other properties). σ: tensile strength; ε: elongation at break; *E*: elastic modulus; WVP: water vapor permeability; WCA: water contact angle (air-exposed surface of the films).

Conclusion

The results demonstrate that banana pseudostem flour is a promising material for the development of biodegradable packaging, contributing to the valorization of agro-industrial waste. The obtained materials exhibited suitable properties, highlighting their potential as sustainable polymeric biomaterials.

Acknowledgements

The authors acknowledge FAPESP (process nº 2024/18058-0) for financial support.

References

[1]Silva R.D., Pacheco T.F., de Santi A.D., Manarelli F., Bozzo B.R., Brienzo M. et al. From bulk banana peels to active materials: Slipping into bioplastic films with high UV-blocking and antioxidant properties. *Journal of Cleaner Production* 2024; 438; 1-16.

D3 – P139

Valorization of sago biomass into high-value activated carbon electrodes for electrochemical applications

Munir M.A.[1], Ibrahim S.[2], Inayatullah A.[3,4]
[1]Faculty of Resource Science and Technology, Universiti Malaysia Sarawak, Kota Samarahan, Malaysia; [2]Malaysian Nuclear Agency, Kajang, Bangi, Malaysia; [3]Food Engineering Technology Study Program, Dept. of Agricultural Technology Engineering and Business, Sriwijaya State Polytechnic, Palembang, Indonesia; [4]Dept. of Agricultural Economics, Faculty of Bioscience Engineering, Ghent University, Belgium

Introduction

The increasing demand for sustainable, low-cost electrode materials has driven interest in biomass-derived activated carbon for electrochemical applications. Sago bark, an abundant agricultural by-product, represents an underutilized carbon precursor with potential for value-added conversion. However, its feasibility as an electrode material remains limited by insufficient understanding of its physicochemical and electrochemical properties compared to commercial activated carbon. This study aims to valorize sago biomass into activated carbon and critically evaluate its suitability as an electrode material by comparing its structural, surface, and electrochemical characteristics with commercial activated carbon. Additionally, the study investigates the effect of material form (powder vs. slurry) on performance and applicability in electrode fabrication.

Materials and Methods

Activated carbon was synthesized from sago bark and prepared in two forms: powder and slurry. Commercial activated carbon, also in powder and slurry forms, was used as a benchmark. Surface area and porosity were analyzed using BET analysis. Functional groups were identified via FTIR spectroscopy, while morphology and elemental composition (C, O, Si, K) were examined using SEM-EDX. The powder form of sago activated carbon was further converted into slurry to fabricate a printable electrode. Electrochemical performance was assessed using cyclic voltammetry to evaluate conductivity and charge storage behavior.

Results

BET analysis showed that sago-derived activated carbon exhibited a lower surface area (15.44 m^2/g) compared to commercial activated carbon (363.94 m^2/g). However, the slurry form of sago activated carbon demonstrated an increased surface area (70.12 m^2/g), indicating improved dispersion and pore accessibility, though still below commercial slurry (247.31 m^2/g). FTIR spectra revealed key functional groups, with characteristic peaks at 3856.38, 2928.54, 2159.27, 1566.32, and 1372.46 cm^{-1} for powder, and shifts to 3362.88, 2889.97, 1566.88, 1371.44, and 874.51 cm^{-1} in slurry form, suggesting surface chemical modifications. SEM-EDX analysis confirmed a porous morphology with predominant carbon content and the presence of oxygen, silicon, and potassium. Electrochemical testing via cyclic voltammetry demonstrated that the fabricated electrodes possess measurable conductivity and promising electrochemical response.

Conclusion

This study demonstrates that sago biomass can be successfully converted into activated carbon with potential for electrochemical electrode applications. Although its surface area and electrochemical performance are currently inferior to commercial counterparts, the material exhibits promising characteristics, particularly in slurry form. The findings highlight the need for further optimization to enhance performance, positioning sago-derived activated carbon as a sustainable and viable alternative for future energy storage technologies.

D3 – P140

Waste-derived eggshell-reinforced chitosan–pectin scaffold: In situ 3D bioprinting for bone regeneration

Güneş A.[1,2], Torkay G.[3], Bal Özturk A.[2,3,4]
[1]Dept. of Clinical Sciences, Faculty of Dentistry, Istinye University; [2]Dept. of Stem Cell and Tissue Engineering, Institute of Graduate Education, Istinye University; [3]Stem Cell and Tissue Engineering Research and Application Center (ISUKOK), Istinye University; [4]Dept. of Analytical Chemistry, Faculty of Pharmacy, Istinye University, Istanbul, Turkey

Introduction

Worldwide, large amounts of agricultural and industrial waste are generated annually. Transforming waste into functional biomaterials offers a sustainable future. Waste-valorized biomaterials, representing valuable sources, have gained interest in bone tissue engineering[1]. In this study, an *in situ* 3D-bioprintable bone scaffold was developed from waste-derived chitosan, pectin, and eggshell particles (ESP).

Materials and Methods

Chitosan was synthesized by deacetylation of chitin extracted from the silkworm *(Bombyx mori)*. Pectin isolated from lemon peels was chemically modified using methacrylic anhydride to synthesize pectin methacrylate (PecMA). ESP were prepared by grinding waste hen eggshells. Structural characterization of chitosan and PecMA were confirmed using FTIR and ^{1}H-NMR. ESP were characterized by FTIR, XRD, size distribution, and zeta potential. Scaffolds were prepared with GelMA, chitosan, PecMA, and varying ESP concentrations (0, 1, 2, 4, and 8 mg/mL). Scaffolds, including lithium phenyl-2,4,6-trimethylbenzoylphosphinate (LAP) as photoinitiator, were printed using a handheld bioprinter (AdBioPen, AdBioInk Biosystem Technology Inc., Türkiye.) and photocrosslinked under the light source (405 nm, 250-346 mW/cm^2) of the device. Swelling, degradation, mechanical properties, and printability of scaffolds were evaluated. Mineralization potential was investigated by SEM-EDX analysis after incubation of the scaffolds in simulated body fluid (SBF), and Alizarin Red was performed to indicate calcium deposition. *In vitro* biocompatibility of the scaffolds was evaluated using osteoblasts by MTT, PrestoBlue, and Live/Dead assays, while DAPI/actin staining was used to assess cell attachment and morphology.

Results

FTIR and ^{1}H-NMR analyses confirmed successful extraction and modification of chitosan and PecMA. Structure of ESP was verified by FTIR and XRD. ESP showed 1492 nm and −18.0 ± 7.16 mV, size and a zeta potential, respectively. Scaffolds showed rapid swelling behavior during 2-8 h, a plateau in 24-36 h, and rapid mass loss in the first 14 days. Incorporation of ESP improved the mechanical stability of the scaffolds up to 2 mg/mL. Printability analysis revealed Pr values between 1.01 and 1.09, indicating good printability and high shape fidelity. SEM-EDX analysis showed calcium and phosphorus deposition on the scaffold, indicating enhanced mineralization potential, and was further supported by Alizarin Red. *In vitro* studies demonstrated high cell viability (>80%) in most groups, with a slight decrease (~70–75%) in the scaffold containing 8 mg/mL ESP, alongside good cell adhesion and well-spread osteoblast morphology.

Conclusion

This study highlights potential of *in situ* printed, waste-derived bone scaffolds and underscores the effective integration of waste-derived biopolymers into bioprinting strategies, offering a sustainable and promising approach for bone tissue engineering.

References

[1]Putra N.E., Zhou J., Zadpoor A.A. Sustainable Sources of Raw Materials for Additive Manufacturing of Bone-Substituting Biomaterials. *In Advanced Healthcare Materials* 2024; Vol. 13, Number 1; https://doi.org/10.1002/adhm.202301837.

D3 – P141

Integration of water-soluble BODIPY derivatives into itaconic acid-functionalized hydrogel scaffolds for enhanced 3D cell imaging

Parihar V.S.[1], Sekaran B.[2], Rantamäki S.[2], Ruoko T.P.[2], Kellomaki M.[1]
[1]Faculty of Medicine and Health Technology, Tampere University, Finland; [2]Chemistry and Advanced Materials, Tampere University, Finland

Introduction

The development of sustainable soft materials is increasingly important in modern tissue engineering. Itaconic acid has emerged as a sustainable alternative to methacrylic acid for the development of photocrosslinkable biopolymers. Photocrosslinkable hydrogels are promising bioinks due to their printability and ability to support cell growth. However, imaging cells within thick 3D scaffolds remains a significant challenge. To address this, we synthesized novel water-soluble BODIPY derivatives and integrated them into itaconic acid–functionalized hydrogels as fluorescent imaging agents. We hypothesize that incorporating these dyes into 3D hydrogel scaffolds will enable improved imaging and more accurate visualization of cells within the 3D constructs.

Materials and Methods

Gelatin was conjugated with itaconic acid using an EDC coupling reaction, as shown in Figure 1A, to obtain Gel-IA (~30% functionalization, confirmed by ^{1}H-NMR and UV–vis). Hydrogels were prepared by dissolving GGMA (1.5% w/v) with 0.5% Irgacure (w/v). Optimal crosslinking was determined via photorheology. Rheological properties, including shear-thinning behavior and viscoelasticity, were subsequently assessed. Intermediates 2 and 3 were synthesized as illustrated in Figure 1B, followed by the synthesis of methoxy-hydroxy BODIPY (Figure 2A) and the water-soluble BODIPY derivative (1) (Figure 2B).

Results

The gelatin was successfully functionalized with itaconic acid, and the hydrogels were optimized through photocrosslinking. A novel water-soluble BODIPY derivative (Compound 1) was successfully synthesized by functionalizing the BODIPY core with a hydrophilic linker terminating in a carboxylic acid group, as shown in Figure 2. The introduction of the polyethylene glycol (PEG)-based linker significantly improved the aqueous solubility of the dye while maintaining strong fluorescence properties. The synthesized dye was successfully integrated into itaconic acid–functionalized gelatin hydrogels during photocrosslinking, resulting in uniformly fluorescent hydrogel scaffolds.




Figure 1: (A) Synthesis of itaconic acid-functionalized gelatin (Gel-IA). (B) Synthesis of intermediates 2 and 3 leading to BODIPY intermediate 7.




Figure 2: (A): (A) Synthesis of the methylhydroxy BODIPY derivative (7). (B) Synthesis of the water-soluble BODIPY derivative (1).

Conclusion

In this work, we developed itaconic acid–functionalized gelatin hydrogels as photocrosslinkable sustainable soft materials for 3D-tissue engineering. The water-soluble BODIPY dyes were successfully synthesised and integrated for imaging of cells inside 3D-hydrogel scaffolds.

Acknowledgements

The authors thank SUSBIO PROFI7 (seed funding programme) for financial support.

D3 – P142

Single use plastics: Its current uses, negative impacts, alternative products and government policies

Sinha A.D.K.[1], Shah A.[2], Mahato M.[2]
[1]Dept. of Physics, School of Applied Sciences, K. K. University, Berauti; [2]Dept. of Basic and Social Sciences, School of Technology, North-Eastern Hill University, Shillong, India

Introduction

Single-use plastics (SUPs) have blarge uses due to their low cost, lightweight nature, durability, and widespread applicability in packaging, healthcare, and consumer products (Ref 1, 2). However, their non-biodegradable nature and persistence in the environment for hundreds to thousands of years have resulted in severe ecological and health challenges, including microplastic pollution, soil and water contamination (Ref 3, 4). Despite increasing awareness and regulatory efforts, the dependence on SUPs still high. The major practical challenge in biodegradable plastics lies due to lack of large-scale avaialability of raw materials, higher cost, and comparatively lower efficiency. This issue is further exacerbated by inadequate infrastructure, particularly the lack of processing units required to convert natural raw materials into commercially viable products. In addition, behavioral resistance, market dynamics, and policy-related complexities ("plastic politics") continue to hinder large-scale adoption of alternative materials.

Aim

This study aims to highlight the infrastructural gaps, research limitations, technological challenges, demographic differences, and policy trade-offs associated with replacing SUPs. It emphasizes the coexistence of both practical and research gaps that contribute to the underutilization of sustainable alternatives. Factors such as geographical diversity, population density variations, and the conflict between strict bans and improved waste management systems play a crucial role in shaping the effectiveness of policies.

Materials and Methods

The methodology is based on a qualitative review of existing literature, focusing on environmental impact, economic feasibility, scalability, and material performance. Sustainable materials such as coir, jute, and other biofibers are proposed as viable alternatives due to their biodegradability and renewability. However, their widespread adoption requires advancements in processing technologies, improved supply chains, and cost-effective production methods.

Results




Fig.1: SUPs review aspects

Conclusion

In conclusion, transitioning from SUPs to sustainable alternatives requires an integrated approach involving technological innovation, development of processing infrastructure, stakeholder participation, and strong governmental policy support. Addressing both practical and research gaps is essential to reduce plastic dependency.

Acknowledgments

Authors thank their respective Institutes for basic resources.

References

[1]Singh N., Ogunseitan O.A., Wong M.H., Tang Y., Sustainable materials alternative to petrochemical plastics pollution: A review analysis. *Sustainable Horizons* 2022; 2; 100016.
[2]Chamas A., Moon H., Zheng J., Qiu Y., Tabassum T., Jang J.H., Abu-Omar M., Scott S.L., Suh S., Degradation Rates of Plastics in the Environment, *ACS Sustainable Chemistry and Engineering* 2020; 9; 3494-3511.
[3]Geyer R., Jambeck J.R., Law K.L. Production, Use and Fate of All Plastics Ever Made. *Sci. Adv.* 2017; 3(7); e1700782.
[4]Sangkham S., Islam M.A., Adhikari S., Kumar R., Sharma P., Sakunkoo P., Bhattacharya P., Tiwari A., Evidence of microplastics in groundwater: A growing risk for human health. *Groundwater for Sustainable Development* 2023; 23; 100981.

D3 – P143

From vineyard residues to high-value products: Advances in bioactive extraction and nanoformulations development

Roque C.S.[1,2,3], Fernandes M.M.[2,3], Silva C.[1,3]
[1]CEB - Center of Biological Engineering, University of Minho, Braga; [2]CMEMS - Center for Microelectromechanical Systems, University of Minho, Guimarães; [3]LABBELS - Associate Laboratory, Braga/Guimarães, Portugal

Introduction

The wine industry is a major economic sector in the European Union, whilst simultaneously generating large volumes of agro-industrial waste. In this context, the implementation of circular economy strategies is essential for the recovery of this waste. At the same time, the control of fungal and bacterial diseases remains a significant challenge, with conventional pesticides associated with negative impacts on the environment, soil and human health. As a sustainable alternative, the extraction of phenolic compounds from grape harvest waste using natural deep eutectic solvents emerges as a promising approach. These extracts can subsequently be incorporated into biodegradable agrotextiles, contributing to crop protection and more sustainable agricultural practices.

Aim

The aim of this study is to extract, characterise and valorise bioactive compounds from grape waste using deep eutectic solvents, aiming to encapsulate them into nanoformulations.

Materials and Methods

The different grape fractions were extracted using natural deep eutectic solvents (NADES) and conventional solvents (aqueous and hydroethanolic) under controlled time and temperature conditions. The extracts obtained were characterised in terms of their total phenolic compound, flavonoid and tannin content, as well as their antioxidant activity. The most promising extracts were evaluated for their antimicrobial activity against bacterial strains (*Escherichia coli* and *Staphylococcus aureus*) and fungal strains (*Botrytis cinerea* and *Penicillium expansum*).

Results

Overall, the most promising parts of the vine, in terms of the balance between phenolic compound content and antioxidant activity, were the stems, leaves and grapes. Extraction using NADES yielded results equivalent to or better than those obtained with conventional solvents, in terms of total phenolic content. In the antibacterial assays, the extracts showed greater efficacy against *S. aureus*, with reductions of up to 5 log units. In *E. coli*, some extracts showed no inhibitory effect, and where an effect was observed, the reduction was smaller. With regard to fungi, the extracts showed higher inhibition percentages against *Penicillium spp.*, when compared with the positive controls, being more effective than against *B. cinerea*, suggesting a selective potential for certain pathogens.

Conclusion

This study demonstrates the potential of NADES for the valorisation of grape by-products, enabling the production of extracts rich in bioactive compounds with high antioxidant and antimicrobial activity. The most promising extracts will be encapsulated in nanoformulations based on piezoelectric biopolymers, with a view to developing functional and biodegradable agrotextiles that contribute to more sustainable agricultural practices and the implementation of a circular economy.

Acknowledgements

This work was supported by *Fundação para a Ciência e a Tecnologia* (FCT) through a PhD fellowship (ref. 2024.03422.BDANA) and by VINNY - Advanced nano encapsulation of bio-based pesticides and fertilisers for a circular and sustainable viticulture project (doi:10.3030/101130039).

D3 – P144

From urban waste to biomedical materials: Processing eggshell-derived calcium carbonate into calcium acetate

Silva J.K. de O.[1], Simões A.Z.[2], Alves A.P. R.[2]
[1]School of Engineering, Sao Paulo State University (UNESP), Ilha Solteira; [2]School of Engineering and Sciences, Sao Paulo State University (UNESP), Guaratingueta, Brazil

Introduction

Eggshell waste, composed primarily of calcium carbonate and valuable organic compounds, remains an underutilized resource [1-2]. Global production of eggshell waste exceeds 8 million tons annually, with the majority disposed of in landfills [3]. This study develops and compares three methods for converting calcium carbonate from eggshell waste into calcium acetate, utilizing commercial vinegar (4–5% acetic acid) as a sustainable and accessible acid source for hydroxyapatite synthesis.

Materials and Methods

The eggshell and calcium acetate samples produced via the three routes evaluated were characterized using X-ray fluorescence, scanning electron microscopy (SEM), energy-dispersive X-ray spectroscopy (EDS), X-ray diffraction (XRD), and Fourier-transform infrared spectroscopy (FTIR).

Results

The results showed that eggshells contain approximately 95.39% calcium, indicating their potential as an efficient source of this mineral. Among the methods evaluated, the process using a spherical condenser under reflux at 90 °C demonstrated superior performance, achieving shorter reaction times and maintaining membrane byproduct yields comparable to alternative approaches. This method differs from conventional routes by eliminating the need for high-purity reagents, reducing processing time, and using only food-grade acetic acid, which increases both sustainability and cost-effectiveness.

Conclusion

Chemical and morphological analyses confirmed the quality of the calcium acetate produced. These findings indicate that eggshell waste can be efficiently converted into calcium acetate using a straightforward process. This approach reduces landfill disposal and supports circular economy strategies, with potential applications in the production of calcium-based biomaterials.

Acknowledgements

The authors express their gratitude to the Guaratingueta School of Engineering and Sciences – UNESP (São Paulo State University) and the Ilha Solteira School of Engineering – UNESP (São Paulo State University) for their institutional support and infrastructure. We also thank the participating laboratories for their technical assistance during the execution of this work, and the São Paulo Research Foundation (FAPESP) for funding through research grants Nº. 2024/04829-4 and Nº. 2022/14790-2 (NWO).

References

[1]Pagonis N., Flegkas D., Itziou A., Kountouras K., Stimoniaris A., Samaras P., Karayannis V. Upcycling of eggshell waste into calcium phosphates for use in sustainable biomedical engineering applications. *Eng* 2024; 5; 3540–3550.
[2]Torres Gouveia M.E., Milhans C., Gezek M., Camci-Unal G. Eggshell-based unconventional biomaterials for medical applications. *Adv. NanoBiomed Res.* 2025; *5*; 2400120.
[3]FAO. Gateway to Poultry Production and Products; FAO: Rome, Italy, 2025.

D3 – P145

Influence of chemical treatments on the tensile properties of sisal fibers for sustainable composite applications

Oliveira M.P.[1], Araújo F.G.S.[1], Oliveira H.F.B.L.[2], Oliveira T.R.[1], Pires T.F.M.[1], Da Cruz J.T.S.[1], Moulin J.C.[1]
[1]Dept. of Forest and Wood Sciences, Federal University of Espírito Santo, Jerônimo Monteiro; [2]Dept. of Chemical Engineering, Federal University of Espírito Santo, Alegre, Brazil

Introduction

The growing demand for sustainable and circular materials has promoted the use of lignocellulosic fibers as reinforcement in polymer composites due to their renewability, low cost and biodegradability. Nevertheless, their performance is strongly governed by surface characteristics and structural integrity, which can be tailored through chemical treatments. In this context, this study evaluates the influence of different chemical treatments on the tensile behavior of sisal fibers (*Agave sisalana*).

Materials and Methods

Sisal fibers were washed, dried and subjected to five conditions, including untreated fibers (IN NAT), alkaline treatments with sodium hydroxide at 5% (NaOH-5) and 15% (NaOH-15), nitric acid treatment at 5% (HNO3-5), and acetylation (ACT). After treatment, the fibers were washed until reaching neutral pH and subsequently dried. Tensile properties were obtained from stress–strain curves using a universal testing machine (Oswaldo Filizola, model AM2KN). Ten fibers were tested for each treatment according to ASTM D2256, using a crosshead speed of 1 mm/min and a gauge length of 50 mm. The elastic modulus was determined from the linear region of the stress–strain curve.

Results

Tensile strength ranged from 62.72 to 417.80 MPa depending on the treatment, as shown in Figure 1. No significant difference was observed between IN NAT and NaOH-5, which exhibited the highest values around 416–418 MPa. In contrast, NaOH-15 led to a marked reduction in strength, indicating structural damage to the fibers, while intermediate values were observed for HNO3-5 and ACT.




Fig. 1. Tensile strength and elastic modulus of sisal fibers under different chemical treatments. Different letters indicate significant differences (Kruskal–Wallis, $p \leq 0.05$).

A similar trend was observed for the elastic modulus. IN NAT fibers showed the highest stiffness at 4.03 GPa, followed by ACT and HNO3-5, whereas NaOH-15 resulted in the lowest modulus of 0.47 GPa, confirming severe degradation of fiber integrity. The reduced performance at higher NaOH concentration is attributed to excessive removal of lignin and hemicelluloses, while the decrease observed for acetylated fibers may be associated with excessive chemical modification compromising structural integrity.

Conclusion

Chemical treatments significantly affect the tensile properties of sisal fibers. Mild alkaline treatment with NaOH at 5% preserved mechanical performance, while higher concentration led to severe degradation. These findings support the use of chemically treated sisal fibers as sustainable biomaterials for composite applications.

Acknowledgements

To the Espírito Santo Research and Innovation Support Foundation and the Coordination for the Improvement of Higher Education Personnel for the granting of scholarship support.

D3 – P146

Influence of thermal modification on density reduction and mass loss in Pinus sp. wood

Rocha H.F., Polido N.G.F.D., Pratti M.E.M., Alves N.S.T., Alves J.C.
Dept. of Forest and Wood Sciences, Federal University of Espírito Santo, Jerônimo Monteiro, Brazil

Introduction

Thermal modification of wood is a widely used technique to improve properties such as dimensional stability and biological durability. However, this process promotes changes in the chemical composition of wood, especially through the degradation of hemicelluloses, resulting in mass loss. Since density is directly dependent on the relationship between mass and volume, such changes significantly affect this property. In this context, this study aimed to evaluate the effect of thermal modification at 180 °C on the density of *Pinus sp*. wood, with emphasis on the mass loss associated with the treatment.

Materials and Methods

Samples of *Pinus sp*. wood were prepared as specimens with dimensions of 5 × 5 × 1 cm. The samples were divided into two groups: an untreated control group and a thermally modified group at 180 °C, with five replicates each. Wood density was determined by densitometry. The Student's t-test for independent samples was applied using SigmaPlot software, adopting a significance level of 5% ($p < 0.05$).

Results

The control group showed a mean density of 748.40 kg/m³, while the thermally modified group presented a mean of 659.30 kg/m³, resulting in a reduction of 89.10 kg/m³. As shown in Table 1, the modified wood also exhibited greater variability, as indicated by the higher standard deviation values.

Table 1. Descriptive statistics and Student's t-test results for wood density of *Pinus sp*. (kg/m³)

Group Name	N	Missing	Mean	Std Dev	SEM
Control	5	0	748.402 kg/m³	16.966	7.588
Temperature 180°	5	0	659.302 kg/m³	33.218	14.856
Difference between averages	89.10 kg/m³				
Statistics t	5.341				
Degrees of freedom (df)	8				
P-value (t-test)	< 0.001				
Confidence interval (95%)	50,63 – 127,57				

Note: Significant difference between groups ($p < 0.001$).

Statistical analysis revealed a highly significant difference between groups ($t = 5.341$; $df = 8$; $p < 0.001$), with a 95% confidence interval ranging from 50.63 to 127.57 kg/m³. The reduction in density is directly associated with mass loss during thermal treatment, mainly due to hemicellulose degradation and volatilization of compounds.

Conclusion

Thermal modification at 180 °C significantly reduces the density of *Pinus sp.* wood due to mass loss caused by thermal degradation of cell wall components. The statistical significance confirms the treatment effect, highlighting the need to consider these changes in technological applications, particularly regarding mechanical performance and material behavior.

Acknowledgements

To the Espírito Santo Research and Innovation Support Foundation (FAPES) for the granting of the scholarship.

D3 – P147

Development of bioactive edible biomaterial enriched with maqui (*Aristotelia chilensis*) extract obtained by block cryoconcentration

Orellana-Palma P.[1], Vásquez-Senador M.[2], Petzold G.[2], Pérez-Bermúdez I.[3]
[1]Escuela de Nutrición y Dietética, Centro Integrativo de Biología y Química Aplicada (CIBQA), Universidad Bernardo O'Higgins, Santiago; [2]Dept. de Ingeniería en Alimentos, Universidad del Bío-Bío, Chillán, Chile; [3]Centro de Estudios en Alimentos Procesados (CEAP), Talca, Chile

Edible biomaterials have gained increasing attention due to their potential applications in food industry. However, their functionality often depends on the incorporation of bioactive ingredients capable of providing additional health-promoting properties[1]. Thus, fruit-derived extracts rich in phenolic compounds represent promising candidates for the development of novel functional biomaterials[2], where block cryoconcentration (BCC) offers an effective approach to obtain concentrates with enhanced bioactive content while preserving thermolabile compounds[3].

Specifically, the current study aimed to design a biomaterial derived from edible polymers to test their potential for use as an edible carrier of cryoconcentrated maqui.

For centrifugal BCC (CBCC), maqui juice (45 mL) was frozen at -20°C. Thus, the concentrate fraction was separated from the ice fraction by centrifugation (15°C/20 min/4600 rpm). Additionally, a Box–Behnken design (BBD), with a response surface methodology (RSM), was applied to optimize the amounts of gelatin (Gel), agar agar (AA) and κ-carrageenan (κ-C), with gel strength as dependent variable, and later, the cryoconcentrated maqui extract from CBCC was incorporated along with the optimal amounts of edible polymers to elaborate a cryoconcentrated-loaded edible biomaterial, analyzing, physicochemical parameters, total bioactive compounds content, antioxidant activity, and structural (textural and rheological) properties, where juice-loaded edible biomaterial was the control sample.

From the optimization process, the best combination to form the optimal biomaterial system was 8.0 g of Gel, 0.25 g of AA and 0.25 g of k-C, since it presented the highest gel strength value (450 g), while the juice presented 3.5% (w/w), 8.7 (°Brix), 12.2 mg gallic acid equivalents (GAE)/mL, 13.7 mg catequin equivalents (CE)/mL, 31.2 µmol trolox equivalents (TE)/mL (DPPH) and 122.2 µmol TE/mL (ORAC). The optimized hydrogel enriched with cryoconcentrated maqui showed higher results in solutes (9.0% w/w and 10.4 °Brix), total color difference (56.4 units) (Figure 1), total polyphenol (570 mg GAE/mL) and flavonoid (155 mg CE/mL) contents, antioxidant activity (713.9 and 617.2 µmol TE/mL, for DPPH and ORAC assays, respectively), textural profile (hardness, gumminess, chewiness) and apparent viscosity (at low shear rate) than juice-loaded edible biomaterial, where the G′ and G″ values indicate an appropriate solid- and gel-like structure (Figure 2). Therefore, CBCC process has the potential to preserve many bioactive compounds, facilitating the production of concentrated fractions with high biological value, and in turn, this research proposes a simple method, with low cost, to fabricate cryoconcentrated maqui solution-loaded biomaterial matrix can be a novel solution for medicinal, pharmaceutical, and food applications.



Figure 1. Color of cryoconcentrated-loaded edible biomaterial.




Figure 2. Variation of rheological parameters of biomaterial samples: (a) apparent viscosity; (b) frequency sweep behavior.

Acknowledgements

This research was funded by FONDECYT REGULAR 2025 (Folio 1252203) through the financial support of ANID-Chile (Agencia Nacional de Investigación y Desarrollo de Chile).

References

[1]Al Mahmud M.Z., Mobarak M.H., Hossain N. Emerging trends in biomaterials for sustainable food packaging: A comprehensive review. *Heliyon*; 2024; 10(1); e24122.


[2]Veiga M., Costa E.M., Silva S., Pintado M. Impact of plant extracts upon human health: A review. *Critical Reviews in Food Science and Nutrition* 2020; 60(5); 873-886.

[3]Tobar-Bolaños G., Casas-Forero N., Orellana-Palma P., Petzold G. Blueberry juice: Bioactive compounds, health impact, and concentration technologies-A review. *Journal of Food Science* 2021; 86(12); 5062-5077.

D3 – P148

Development of dual-chemically activated bamboo-biochar from waste bamboo for sustainable CO_2 capture and carbon reduction

Watmanee S., and Rodsuta C.
Dept. of Chemical Engineering, Faculty of Engineering, Kasetsart University, Bangkok, Thailand



Scheme 1. Overall expected outcomes

Introduction

Transforming biomass waste into functional carbon-capturing materials offers a promising strategy for both waste valorization and carbon reduction. In this work, waste bamboo is utilized as a sustainable precursor for high-performance activated bamboo-biochar for CO_2 capture. Owing to its rapid growth, hollow fibrous structure, and low mineral content, bamboo can facilitate porous carbon formation during carbonization. However, bamboo waste is typically converted into low-value charcoal for fuel, odor adsorption, or soil amendment, limiting its long-term contribution to carbon management. Therefore, this study aims to upgrade bamboo waste into a value-added porous carbon adsorbent through an energy-efficient dual-chemical activation strategy, as illustrated in Scheme 1.

Materials and Methods

Activated bamboo-biochar will be synthesized using KOH and a combined KOH/H_2O_2 treatment, followed by pyrolysis at different temperatures (500-700 °C). The dual-activation approach is designed to create a synergistic effect: KOH promotes pore formation and surface area development, while H_2O_2 enhances surface oxidation and oxygen-containing functional groups that can strengthen CO_2–surface interactions. The resulting activated bamboo-biochar will be systematically evaluated using SEM-EDX, XRD, Raman spectroscopy, BET surface area analysis, XPS, FT-IR, and TGA, together with CO_2 adsorption performance testing. These analyses will clarify the relationship between activation strategy, pore structure, surface chemistry, thermal stability, and CO_2 capture capacity.

Results

Chemical activation markedly enhanced the textural properties of bamboo-biochar. The BET surface area increased from 141.12 m²/g for pristine biochar to 165.99, 440.70, and 649.36 m²/g at 500, 600, and 700 °C, respectively. At 700 °C exhibited the highest surface area with a dominant micropore area of 546.77 m²/g, confirming the formation of a highly microporous structure favourable for CO_2 adsorption. Notably, dual KOH/H_2O_2 activation achieved significant pore development at lower temperature, with 500 °C reaching a BET surface area of 592.46 m²/g and micropore area of 540.94 m²/g. FTIR analysis further indicated surface chemical modification after activation, which may enhance CO_2–surface interactions.

Conclusion

Chemical activation using KOH and KOH/H_2O_2 effectively transformed waste bamboo into microporous activated biochar with high surface area and tunable surface functionality. These properties highlight its strong potential as a CO_2 adsorbent. This work offers a sustainable pathway for upcycling bamboo waste into value-added carbon-capturing materials, supporting circular economy and net-zero carbon goals.

D3 – P149

One-pot conversion of agro-industrial residue to self-reinforced, functional biocomposite films

Lueangwattnapong K.[1], Banditvong C.[2], Pitakworapak N.[2], Lerdlattaporn R.[2], Songkasiri W.[2], Saengchan K.[3]
[1]Dept. of Chemical Engineering, Faculty of Engineering, Kasetsart University; [2]The Joint Graduate School of Energy and Environment (JGSEE), King Mongkut's University of Technology Thonburi; [3]National Center for Genetic Engineering and Biotechnology, Bangkok, Thailand

Introduction

Cassava starch processing generates large volumes of fibrous pulp by-product, which retains substantial residual starch alongside cellulose-rich fibre. Conventional valorisation routes separately extract starch and cellulose, or nanocellulose, before recombining them into composite films. This approach is energy- and chemical-intensive, and isolated nanocellulose tends to converge towards similar physicochemical properties regardless of feedstock origin, limiting the added value of using an agro-industrial residue specifically.

Aim

This study proposes a minimal-processing, one-pot alternative: mechanically grinding whole, unfractionated cassava pulp to different intensities, then directly gelatinising the resulting suspension so that the pulp's intrinsic starch forms a film matrix while its cellulose fraction, at the grinding-determined size, acts as reinforcement. Zinc oxide (ZnO) nanoparticles are incorporated to confer antimicrobial and UV-blocking function, with the hypothesis that the cellulose fraction's size governs ZnO dispersion within the matrix.

Materials and Methods

Cassava pulp obtained from a starch-processing facility in Thailand was oven-dried and mechanically ground to three intensities (coarse, intermediate, fine) using a laboratory ball mill; resulting particle size distributions were determined by laser diffraction. Pulp-water suspensions were heated across 50 – 110°C, in 10°C increments, to identify the optimal gelatinisation temperature for whole-pulp film formation. At the optimised temperature, suspensions from each grinding fraction were combined with glycerol plasticiser, with and without ZnO nanoparticles (synthesised by precipitation and incorporated at 1-5 wt%), and cast into films. Films and precursor fractions are being characterised by FTIR, XRD (crystallinity index), SEM-EDX (morphology and zinc distribution), tensile testing, UV-Vis transmittance, and antimicrobial zone-of-inhibition assays against *Escherichia coli* and *Staphylococcus aureus*.

Results


Screening across 50 – 110°C identified 90°C as the optimal temperature for gelatinising whole cassava pulp into a homogeneous film-forming suspension, with markedly reduced starch solubilisation below 80°C and increasing degradation above 100°C. This temperature has been adopted for all subsequent one-pot formulations.

Conclusion

This minimal-processing, one-pot strategy offers a circular-economy route to convert an underutilised agro-industrial residue directly into a self-reinforced, antimicrobial, UV-protective biomaterial, without separate extraction, purification, or recombination steps. Determining how a single, scalable processing parameter, grinding intensity, governs reinforcement, ZnO dispersion, and resulting function will inform low-cost valorisation strategies for cassava pulp and analogous starchy lignocellulosic residues.

Acknowledgements

The authors would like to acknowledge the National Science and Technology Development Agency (NSTDA), Thailand, for financial support through the Fundamental Fund (FF) 2569, and the Excellent Center for Waste Utilization and Management (ECoWaste) for providing laboratory equipment and technical assistance during the experiment.



D3 – P150

Bioinspired multifunctional GelMA scaffolds fabricated via multiphoton lithography for bone tissue regeneration

Charitaki M.[1,2], Kabouraki E.[2], Ranella A.[1], Farsari M.[1]
[1]Institute of Electronic Structure and Laser Foundation for Research and Technology-Hellas (FORTH/IESL), Heraklion; [2]Dept. of Materials Science and Engineering, University of Crete, Heraklion, Greece

Introduction

Bone tissue regeneration requires scaffolds capable of replicating both the hierarchical architecture and the biochemical environment of native bone. Hydrogels based on gelatin methacryloyl (GelMA) are widely used due to their cytocompatibility and tunable properties; however, their mechanical strength and bioactivity are often limited. Advanced microfabrication techniques such as multiphoton lithography (MPL) enable the creation of highly precise three-dimensional architectures that can better mimic the structural complexity of bone while maintaining the advantages of hydrogel-based biomaterials.

Aim

The aim of this study is to develop multifunctional GelMA-based scaffolds fabricated via MPL and enhanced through hydroxyapatite mineralization and metal ion incorporation to create bioactive constructs capable of supporting bone tissue regeneration while providing antimicrobial and antifouling functionality.

Materials and Methods

GelMA-based photoresists containing curcumin as a biocompatible photoinitiator were processed via two-photon polymerization to fabricate architected scaffolds, including lattice and triply periodic minimal surface (TPMS) structures. Following fabrication, scaffolds were subjected to an *in situ* mineralization process for the formation of hydroxyapatite (HAp) crystals within the hydrogel matrix. Magnesium and zinc ions were incorporated to further enhance bioactivity. Structural and chemical characterization was performed using scanning electron microscopy (SEM), energy dispersive spectroscopy (EDS), Fourier transform infrared spectroscopy (FTIR), and X-ray diffraction (XRD). Cytocompatibility and cell–scaffold interactions were evaluated using mesenchymal stem cells (MSCs). Antimicrobial and antifouling properties were assessed against *Escherichia coli* and *Staphylococcus aureus*.

Results

MPL enabled the fabrication of highly defined three-dimensional scaffolds with controlled porosity and complex geometries. Mineralization produced hydroxyapatite crystals distributed across scaffold surfaces, with Ca/P ratios approaching the theoretical value. Cell studies demonstrated high viability (>95%), with MSCs showing attachment, spreading, and migration throughout the scaffold network. Additionally, curcumin-containing scaffolds exhibited reduced bacterial adhesion and significant antimicrobial activity under light activation.




Figure 5: *Representative multiphoton-fabricated GelMA–curcumin scaffolds and their biological performance: SEM images of printed architectures and mineralized structures, cell viability assay, antibacterial activity against E. coli and S. aureus, and high-resolution imaging of hydroxyapatite crystal formation on scaffold surfaces.*

Conclusion

The combination of high-resolution MPL fabrication with bioinspired mineralization produced multifunctional GelMA-based scaffolds with improved bioactivity and antimicrobial functionality. These findings highlight the potential of architected hydrogel scaffolds as advanced platforms for bone tissue engineering.

D3 – P151

Cytotoxicity and intradermal reactivity tests of the MPP100 photosensitizer using a non-toxic solubilizing buffer

Jung I.L [1,2]
[1]Korea Atomic Energy Research Institute; [2]University of Science and Technology, Daejeon, Republic of Korea

Introduction

Photodynamic therapy (PDT) combines a photosensitizer with light of a specific wavelength and is a minimally invasive modality that can complement or improve existing therapies[1]. However, many key photosensitizers used in PDT are poorly water-soluble and therefore require solubilization in toxic solvents, limiting their practical use in clinical settings. Accordingly, developing a non-toxic solubilizing solvent for hydrophobic photosensitizers and establishing its clinical applicability has become an important strategy.

Aim

MPP100 (3-[(3,5-dimethyl-1H-pyrazole-4-yl)methyl]-3-devinylpyropheophorbide-a methyl ester) is a hydrophobic photosensitizer that is commonly solubilized using toxic solvents such as DMSO or THF, which can cause solvent-driven cytotoxicity and hinder commercialization[2]. Recently, we developed a non-toxic solubilizing buffer (JIL buffer) and evaluated the cytotoxicity and intradermal reactivity of MPP100 formulated in JIL buffer to assess whether it mitigates solvent-related biocompatibility risks.

Materials and Methods

MPP100 was solubilized in JIL buffer to 500 μg/mL. A laboratory-scale cytotoxicity assessment was conducted at Korea Atomic Energy Research Institute (KAERI), and accredited cytotoxicity and rabbit intradermal reactivity tests were performed at Korea Conformity Laboratories (KCL). Cytotoxicity was evaluated using an extract test with L-929 mouse fibroblasts and Minimum Essential Medium (MEM) as the extraction vehicle. No light irradiation was applied.

Results

DMSO showed marked cytotoxicity, whereas JIL buffer showed no cytotoxicity (Figure 1). In the KCL qualitative cytotoxicity grading, the test extract (MPP100 in JIL buffer) was Grade 1; the negative control (polyethylene film) and vehicle (MEM) were Grade 0; and the positive control (0.1% ZDEC polyurethane film extract) was Grade 4. In the rabbit intradermal reactivity test, the overall score was 0.2, with no abnormal clinical signs, mortality, or test-article-related body weight changes (Table 1).

Conclusion

MPP100 formulated in JIL buffer met acceptance criteria for both cytotoxicity and intradermal reactivity tests.

Acknowledgements

This work was supported by the Commercialization Promotion Agency for R&D Outcomes (COMPA) grant funded by the Korea government (Ministry of Science and ICT) (Project No. RS-2025-02309076).

References

[1]Agostinis P., Berg K., Cengel K.A. et al. Photodynamic therapy of cancer: an update. *CA Cancer J Clin* 2011; 61(4); 250–281.
[2]Yook K.D., Kim J.W., Song Y.K. In vitro study on the effects of photodynamic inactivation using methyl pheophorbide a, PhotoMed, PhotoCure, and 660 nm diode laser on Candida albicans. *Photodiagn. Photodynam. Therapy* 2018; 38; 102871-102875.

Figure 1




Table 1. Test Reports

Qualitative analysis results (48h exposure group)

Exposure time	Test substance			Control substances								
				Blank			Negative			Positive		
	A	B	C	A	B	C	A	B	C	A	B	C
(48 ± 2) h	1	1	1	0	0	0	0	0	0	4	4	4

Skin Reaction Scoring Table (Appendix)

Erythema and Eschar Formation	Score
No erythema	0
Very slight erythema (barely perceptible)	1
Well-defined erythema	2
Moderate erythema	3
Very severe erythema and eschar formation	4
Edema Formation	**Score**
No edema	0
Very slight edema (barely perceptible)	1
Slight edema (edges of area well-defined by definite raising)	2
Moderate edema (raised ~1 mm)	3
Severe edema (raised >1 mm and extending beyond area of exposure)	4

SCORE

0.2

D3 – P153

Development of novel bone cement for osteoporosis treatment using poly(glutamic acid) composite materials

Hsu Y.-I.[1], Mae H.[2], Ukon Y.[2]
[1]Dept. of Applied Chemistry, The University of Osaka; [2]Dept. of Orthopedics, The University of Osaka Hospital, Japan

Introduction

Osteoporosis greatly increases fracture risk, and bone cement is commonly used to reinforce weakened bone. Conventional bone cement is based on polymethyl methacrylate (PMMA), which consists of a liquid monomer (MMA) with initiators and inhibitors, and a powder phase containing PMMA and radiopaque additives. During surgery, the viscosity of the monomer is critical: if too low, leakage occurs; if too high, handling becomes difficult. Thus, controlling viscosity is essential. Polyglutamic acid (PGA), a biodegradable and highly hydrophilic polymer produced by Bacillus subtilis, is widely used for its thickening and moisture-retaining properties. However, directly incorporating PGA into PMMA bone cement is challenging due to poor compatibility and difficulty achieving uniform mixing with MMA and the powder polymer.

Aim

To address the compatibility issues of PGA and create a new additive for tuning the viscosity and toughness of PMMA bone cement, we synthesized PGA-g-PMMA by grafting MMA onto PGA using a radical initiator. We then evaluated its solubility in MMA and examined how the graft copolymer affected the viscosity and mechanical properties of the resulting bone cement.

Materials and Methods

To synthesize PGA-g-PMMA, PGA was first modified with a radical initiator, 2,2'-azobis[2-(2-imidazolin-2-yl)propane] (AIP), then the AIP-modified PGA was reacted with MMA to obtain PGA-g-PMMA. Three types of PGA-g-PMMA with different MMA repeating unit lengths (m = 700, 800, 1300) were synthesized by varying the MMA feed ratio. Structural analysis using ^{1}H-NMR and FTIR confirmed the successful synthesis of PGA-AIP and PGA-g-PMMA. The grafting ratio of AIP to PGA was estimated at 1.7%. PGA-g-PMMA was found to dissolve uniformly in MMA at concentrations up to 3 wt%; higher concentrations led to aggregation of PGA segments. Thus, the optimal dissolution concentration was determined to be 3 wt%.

Results

Mechanical testing showed that PGA-g-PMMA enhanced the bending strength of bone cement as the grafted MMA chain length increased. PGA-g-PMMA1300 exhibited the highest strength, although with reduced bending elongation, and its toughness—calculated from the bending curve area—was twice that of PGA-g-PMMA700. Viscosity measurements revealed time-dependent thickening in all PGA-g-PMMA1300/MMA mixtures, with higher concentrations producing stronger increases. Compression testing further demonstrated that PGA-g-PMMA achieved the highest maximum load (1332 N), outperforming PMMA (991 N) and bone (581 N) (Fig.1). Fracture simulation also showed that PGA-g-PMMA produced the lowest yield-risk distribution and maintained low-risk regions even under greater displacement. Overall, these results indicate that adjusting the grafted MMA chain length enables fine-tuning of the mechanical performance of PMMA bone cement.




Fig. 1. Compression curves of bone, PMMA, and PGA-g-PMMA under compressive loading.

Conclusion


PGA-g-PMMA synthesized via AIP-initiated graft polymerization exhibits excellent solubility in MMA monomers and enables control over the viscosity and mechanical strength of PMMA bone cement. In particular, PGA-g-PMMA1300 offers a favorable balance of high toughness, adequate viscosity, and impact resistance comparable to conventional PMMA cement. This approach provides a promising pathway for the development of next-generation bone cement with improved handling and performance.

D3 – P154
Detoxifying substances from body using calcium phosphate particles

Bikharudin A.[1], Okada M.[2], Otaka A.[1], Matsumoto T.[1]
[1]Dept. Biomaterials, Okayama Univ., [2]Dept. Dental Biomaterials, Tohoku Univ., Sendai, Japan

Introduction
Mercury, found in large quantities in seafood, and cadmium, found in grains, can cause neurological, kidney, and bone disorders. Inorganic apatite, the main component of bone, has a high affinity for metal ions, including cadmium. Furthermore, inorganic apatite dissolves in acid during bone remodeling and reprecipitates in a neutral environment. The pH-responsive nature of inorganic apatite may be useful for the removal of heavy metal ions in the gastrointestinal tract.

Aim
This study aimed to evaluate the effectiveness of inorganic apatite materials as heavy metal capture materials. To confirm this, both *in vitro* and *in vivo* studies were conducted.



Materials and Methods
Inorganic apatite was synthesized using a wet method at 37°C. The resulting apatite was characterized by XRD, FTIR, and specific surface area measurements. For *in vitro* evaluation, apatite powder was added to a pH 3 solution containing $CdCl_2$, then transferred to a pH 7 solution, and the amount of Cd recovered was confirmed (gastrointestinal (GI) tract model). For *in vivo* evaluation, ICR mice (6-week-old, male) were given a $CdCl_2$-containing beverage and a diet containing inorganic apatite (0-10 wt%). After a 4-week experiment, liver, kidney, and bone tissues were stained, Cd deposition was evaluated, and fecal Cd excretion was quantified.

Results

In vitro GI tract model experiments demonstrated that inorganic apatite captures Cd through dissolution and reprecipitation. *In vivo* experiments, Cd in drinking water was deposited in tissues such as the liver and kidneys in the apatite-free group. Conversely, feeding apatite significantly reduced blood Cd concentrations and tissue Cd deposition. Almost all the supplied Cd was excreted in the feces in the group fed a diet containing 10% HAp.



Conclusion

Inorganic apatite powder was shown to function as an effective detoxifier for the excretion of heavy metals from the body. This powdered apatite may be useful as a novel detoxifying material.

Acknowledgements

This work was supported partly by the Japan Society for the Promotion of Science KAKENHI (grant numbers: JP21H03123, JP22H03274, and JP23H00235) and by the Japan Science and Technology Agency CREST (grant number: JPMJCR22L5).

D3 – P155

Evaluation of proinflammatory responses to post-processed decellularized ECMs using IL-1β-HiBiT–expressing THP-1 cells

Kimura T.[1], Suzuki M.[1,2], Kishida A.[1], Ohtsuki S.[3], Tanabe T.[4], Nakamura N.[5], Yamamoto M.[6]
[1]Dept. Biomed. Eng., Toyo University, Saitama; [2]Dept. Polymer. Chem., Kyoto University; [3]Fac. Life Sci., Kumamoto University; [4]Coll. Design Eng., Shibaura Institute of Technology, Tokyo; [5]Coll. Sys. Eng., Shibaura Institute of Technology, Saitama; [6]Dept. Mater. Processing, Tohoku University, Sendai, Japan

Introduction

Decellularized extracellular matrix (dECM) scaffolds are promising biocompatible materials due to their preserved ECM components and low immunogenicity, offering advantages over synthetic scaffolds. However, post-processing treatments such as heat and freeze-drying can alter ECM structure and influence macrophage-mediated immune responses. In this study, porcine pericardium and aorta were decellularized using a high hydrostatic pressure–based method, followed by additional treatments to evaluate their effects on ECM structure and immunological responses. Proinflammatory activity was assessed using IL-1β-HiBiT–tagged THP-1 cells.

Materials and Methods

Porcine pericardium and aorta were decellularized using the high hydrostatic pressure (HHP) method[1)]. The resulting dECMs were subsequently subjected to either heat treatment (90 °C for 1 hour) or freeze-drying. The histological structures of the treated dECMs were evaluated using hematoxylin–eosin (HE) and collagen hybridizing peptide (CHP) staining. To assess macrophage responses to the treated dECMs, IL-1β-HiBiT–tagged THP-1 cells were generated, in which the luminescent peptide (HiBiT) gene was inserted downstream of the IL-1β[2)]. Luminescence intensity was measured after seeding the cells onto the treated dECMs.




Figure 1. HE and CHP staining of the treated

Results

Histological staining (HE, CHP) and SEM showed that heat treatment induced collagen denaturation and loss of native structure, whereas freeze-drying caused expansion of interfibrillar spaces and fiber aggregation, indicating distinct ECM alterations(Fig.1). THP-1 cells adhered to all dECMs, but adhesion was reduced in heat-treated tissues, likely due to denaturation of collagen motifs involved in macrophage receptor binding. All dECMs exhibited lower IL-1β responses than the LPS control, confirming low immunogenicity. The pericardium induced higher IL-1β expression than the aorta, suggesting that tissue origin had a greater influence than processing. Freeze-dried pericardium and aortic media showed slightly elevated responses. These findings indicate that ECM composition, rather than structural changes, primarily governs immune activation. Proteomic analysis further revealed treatment-dependent differences in ECM composition.

Conclusion

Post-processing altered dECM structure and composition. Heat treatment induced collagen denaturation and reduced macrophage adhesion, whereas freeze-drying preserved ECM ligands. All dECMs exhibited low IL-1β luminescence, indicating minimal inflammation. Macrophage responses were more strongly influenced by tissue origin than processing method. Overall, ECM composition, rather than structural integrity, plays a central role in immunomodulatory biocompatibility.

Acknowledgements

This study was partly supported by JST CREST, Japan and JSPS KAKENHI Japan.

References

[1]Suzuki M., Kimura T. et al. Application of decellularized tissue for soft-hard interregional regeneration. *Front. Bioeng. Biotechnol.* 2025*;* 13; 1394714.
[2]Kimura T., Maeda H. et al. Evaluation of Proinflammatory Response to Polymeric Materials Using a Macrophage Cell Line Genetically Tagged with a Luminescent Peptide. *Advanced Biomedical Engineering* 2024; 13; 43-51.

D3 – P156

Antibacterial studies of the surface-modified medical-grade titanium with novel catechol compounds with quaternary ammonium at different carbon chain lengths

Liu, Z.H.[1], Fan N.C.[2,3], Cheng C.H.[2,4], Lin J.C.[1,5]
[1]Dept of Chemical Engineering, National Cheng Kung University, Tainan; [2]Division of Nephrology, Dept of Pediatrics, Chang Gung Memorial Hospital, Taoyuan; [3]Graduate Institute of Clinical Medical Sciences, Chang Gung University, Taoyuan; [4]Dept of Pediatrics, College of Medicine, Chang Gung University, Taoyuan; [5]School of Dentistry, Institute of Oral Medicine, College of Medicine, National Cheng Kung University, Tainan, Taiwan

Introduction

Bacterial adhesion, proliferation, and biofilm formation on device surfaces are the primary drivers of medical device-associated infections. The emergence of antibiotic- or biocide-resistant strains has been a concern when antibiotics or biocides are used as controlled-release agents. Henceforth, creating a bactericidal surface, such as the surface functionalized with cationic quaternary ammonium groups, could obviate this issue. Nevertheless, multiple reaction steps and the use of harsh solvents/acids would be needed to render the surface bearing cationic functionalities. A mussel-inspired surface modification technique that utilizes catechol-based derivatives has received significant attention lately due to the mussel's ability to bind to a wide variety of organic and inorganic substrates. This approach could reduce the number of surface processing steps and replace them with water or ethanol-based solvents.

Aim

A simple immersion coating process was used to modify the titanium surface with novel mussel-inspired, lab-synthesized catechol-terminated compounds bearing cationic quaternary ammonium groups with different carbon chain lengths, DAQA-C8, DAQA-C4, and DAQA-C1. The surface properties and antimicrobial characteristics of these modified surfaces were investigated.

Material and Methods

A novel synthesis scheme for these catechol-containing cationic compounds is shown (Figure 1). Various surface modification processes were used for the titanium substrates (Figure 2). Antimicrobial characteristics against *E. coli* and *S. aureus* were evaluated.

Results

The titanium substrate modified with DAQA-C1 using a two-step modification process exhibited the highest antibacterial activity against *E. coli* (90% reduction) and *S. aureus* (60% reduction).

Conclusion

The antibacterial properties of titanium were optimized through a well-balanced combination of processing conditions and cationic catechol-containing compounds with appropriate carbon chain lengths.




Figure 1: The synthesis scheme




Figure 2: Surface modification process.

Acknowledgements

Financial support from the National Science and Technology Council, Taiwan, NSTC 112-2221-E-006-027-MY3, 111-2314-B-006-120-MY3; and from the Chang Gung Memorial Hospital CMRPG 3M0382, 3P0041, and 3P0042 is acknowledged.

D3 – P157

Phage-loaded metal ion-containing biomaterials as a multimodal antibacterial strategy

Stipniece L.[1,2], Eglite D.[3,4], Yu H.-C.[1], Maurins S.[3], Racenis K.[3,5], Kroica J.[3]
[1]Institute of Biomaterials and Bioengineering, Faculty of Natural Sciences and Technology, Riga Technical University; [2]Baltic Biomaterials Centre of Excellence, Headquarters at Riga Technical University; [3]Dept. of Biology and Microbiology, Riga Stradins University; [4]Joint Laboratory, Pauls Stradins Clinical University Hospital, Riga; [5]Centre of Nephrology, Pauls Stradins Clinical University Hospital, Riga, Latvia

Introduction

Antimicrobial resistance is a global health challenge that has renewed interest in phage-based therapies. Phages selectively infect and lyse bacterial hosts while self-amplifying at infection sites. However, their standalone clinical application is limited by a narrow host range, immune clearance, and the development of resistance. Hybrid antibacterial strategies combining phages with complementary antimicrobials are increasingly explored to overcome these limitations. Among emerging approaches, material-enabled systems integrating phages with antibacterial metal ions are gaining attention as a bridge between biological specificity and biomaterials-driven functionality. Accordingly, the aim was to examine recent advances and perspectives in multimodal phage therapies, with a focus on ion-enabled biomaterials.

Materials and Methods

The literature on phage combinations with antimicrobial polymers, inorganic materials, biological agents, and physicochemical adjuvants was reviewed, with emphasis on systems incorporating antibacterial metal ions. To contextualize these concepts, preliminary proof-of-concept experiments were conducted. Initial studies evaluated direct interactions between phages and antibacterial metal ions. Subsequently, ion-containing biomaterials were explored, including calcium phosphate (CaP) nanoparticles doped with Zn^{2+} or Cu^{2+} and alginate beads ionically crosslinked with Ca^{2+} (control), Zn^{2+}, or Cu^{2+}. Study groups included ion-only and phage-loaded systems. Material morphology, metal ion loading, and chemical interactions were analyzed, and phage stability after immobilization or encapsulation was evaluated alongside antibacterial performance.

Results and Conclusions

The literature indicates that hybrid phage systems enhance antibacterial efficacy by improving biofilm penetration, destabilizing bacterial membranes, and suppressing the emergence of resistance. Our findings suggest that phage-metal ion combinations enhance antibacterial activity at intermediate ion concentrations, indicating additive effects. In contrast, higher ion levels were dominated by metal ion toxicity, potentially limiting phage contribution. Building on these observations, ion-containing biomaterials were evaluated as delivery platforms. Ion-doped CaP nanoparticles exhibited measurable antibacterial activity, confirming the intrinsic antimicrobial contribution of incorporated ions. Similarly, alginate beads crosslinked with Zn^{2+} or Cu^{2+} showed ion-dependent antibacterial effects compared with Ca^{2+} controls, highlighting the dual structural and functional roles of the ions. Overall, these results emphasize the importance of controlling ion exposure to preserve phage activity. Advancing such hybrid systems may enable next-generation precision antimicrobials for infection-resistant biomaterials and localized therapies.

Acknowledgements

This work was supported by the activity 1.1.1.9 "Post-doctoral Research" of the Specific Objective 1.1.1 "Strengthening research and innovative capacities and introduction of advanced technologies in the common R&D system" of the European Union's Cohesion Policy Programme for 2021-2027, research application No 1.1.1.9/LZP/1/24/056 "Antibacterial Biomaterials through Synergy of Metallic Ions-Substituted Calcium Phosphates and Bacteriophages". The authors acknowledge access to the infrastructure and expertise of the BBCE - Baltic Biomaterials Centre of Excellence (European Union's Horizon 2020 research and innovation programme under the grant agreement No. 857287).

D3 – P158

Engineering bioactive cotton textiles functionalized with plant agri-food by-product extracts: Linking biological performance to bioactive compounds release kinetics

Fernandes A.[1], Negut I.[2], Costa A.F.[3], Melo A.[1], Afonso T.[1], Silva C.[3], Pintado M.[1], Tavaria F.[1], Oliveira C.[1,4]

[1]Universidade Católica Portuguesa, CBQF - Centro de Biotecnologia e Química, Porto, Portugal; [2]National Institute for Lasers, Plasma and Radiation Physics, Măgurele, Romania; [3]Technological Centre of the Textile and Clothing Industries (CITEVE), Vila Nova de Famalicão, Portugal; [4]RISE-Health Research Unit – Associate Laboratory, Porto, Portugal

Introduction

Conventional bioactive textiles for dermatological applications commonly rely on synthetic or metal-based agents, which may raise concerns regarding skin compatibility and environmental sustainability. In contrast, plant-derived bioactive compounds recovered from agri-food by-products offer a sustainable and skin-friendly alternative for textile functionalization. Acorn shells (AS), an abundant agri-food residue, are particularly rich in phenolic compounds with reported antimicrobial, antioxidant, and anti-inflammatory activities[1]. Despite this promising bioactive profile, their integration into textile materials and the relationship between bioactive compound release and biological performance remain unexplored.

Here, cotton textiles were engineered using AS-derived extracts through different functionalization strategies. The biological performance of the functionalized textiles was systematically evaluated and correlated with the release kinetics of the bioactive compounds, aiming to provide insights into the design of sustainable bioactive textiles for dermatological applications.

Materials and Methods

AS extracts were incorporated into cotton fabrics using exhaustion, padding, and laser-assisted techniques. Cotton substrates were first pre-treated with cationic agents - chitosan (CH), potassium alum (AL), or a commercial synthetic cationic agent (CAT)[2] - to enhance the adhesion of bioactive compounds. Functionalization with AS extracts was performed via exhaustion or padding, while Ag nanoparticles containing AS extracts were incorporated using a laser-based approach.

Biological performance was evaluated through antimicrobial assays against *Staphylococcus aureus*, *Staphylococcus epidermidis*, and *Escherichia coli*[2]. Antioxidant activity was determined using the DPPH assay. Anti-inflammatory activity was assessed in LPS-stimulated macrophages after 24 h exposure to functionalized cotton by quantifying TNF-α, IL-1β, and IL-6 using ELISA. Biocompatibility was evaluated in keratinocyte monolayers using indirect and semi-direct exposure methods after 8 and 24 h.

The release of bioactive compounds from the functionalized cotton fabrics was evaluated under simulated physiological conditions by incubating the fabrics in artificial sweat at 37 °C for 24 h. The initial phenolic load of the textiles (0h) was determined by extraction using a MeOH:H_2O (80:20) mixture, followed by quantification of total phenolic compounds using the Folin–Ciocalteu assay. The phenolic compounds released into the sweat solution after 24h were quantified using the same method (24h), while antioxidant activity (0 and 24h) was assessed using the ABTS radical scavenging assay.

Results

Most AS-treated cotton samples exhibited enhanced antimicrobial activity compared with untreated cotton, with the most pronounced effects observed against Gram-positive bacteria, particularly when the exhaustion method was applied. The antioxidant capacity was significantly increased, with the exhaustion technique again yielding the strongest effects. Anti-inflammatory activity was also evident, as treated textiles promoted a significant reduction in pro-inflammatory cytokine production in macrophages. All AS-functionalized samples demonstrated excellent biocompatibility in both short-term (8 h) and long-term (24 h) indirect and semi-direct exposure assays, maintaining keratinocyte viability above 70%. Correlation with release kinetics analyses indicated that the sustained release of bioactive compounds from the functionalized textiles, accounting for approximately 20–58% of the initial loading after 24 h, likely contributed to the observed biological activities.

Conclusion

AS-derived extracts represent a promising sustainable strategy for engineering bioactive cotton textiles with antimicrobial, antioxidant, and anti-inflammatory properties while maintaining good skin biocompatibility. Linking biological performance to the release kinetics of bioactive compounds provides key insights for the rational design of functional textiles. These findings support the valorization of agri-food by-products and advance the development of next-generation bioactive textiles for biomedical and skin-contact applications.

Acknowledgements

This work was supported by National Funds from Fundação para a Ciência e a Tecnologia (FCT) through the DETEX project (https://doi.org/10.54499/2023.12365.PEX).

References

[1]Oliveira C., Melo A., Ribeiro T., Pintado M., Tavaria F. Targeting human skin health: Bioactive evaluation of acorn shell and red grape pomace extracts against pathogens and skin cell. *Fitoterapia* 2025; 186.

[2]Oliveira C., Costa A., Mendanha D., Macedo T., Moreira J., Oliveira J.A., Bernardes B.G., Silva C.J., Tavaria. Eucalyptus-Enhanced Cotton: Pretreatment and Bioactive Coating Strategies for the Development of Sustainable Textiles with Antimicrobial and Antioxidant Activities for Skin Applications. *ACS Applied Materials & Interfaces* 2025; 17, 35009−35022.

D3 – P159

Polyphenol-based multifunctional coatings with bioactive ions for antibiotic delivery from implant surfaces

Sandomierski M., Reczkowski J., Domke A., Jakubowski M.
Institute of Chemical Technology and Engineering, Poznan University of Technology, Poland

Introduction

Titanium implants are widely used in dentistry and other implant-related procedures because of their favorable mechanical properties, corrosion resistance, and biocompatibility. Likewise, polymeric artificial ligaments are increasingly employed in reconstructive surgery, especially in physically active patients. Despite these advantages, both types of implants may be affected by bacterial adhesion and biofilm formation, which can lead to peri-implant infections and treatment failure. Local delivery of antibiotics from implant surfaces may offer an effective alternative to systemic therapy by improving drug availability at the implantation site while reducing systemic side effects.

Aim

The aim of this study was to develop multifunctional polyphenolic coatings enriched with bioactive ions for titanium and polyester-based implant materials and to evaluate their potential as carriers for controlled ciprofloxacin release.

Materials and Methods

Titanium implants and polyester artificial ligament materials were modified with polyphenol-based coatings coordinated with bioactive metal ions. After surface functionalization, the samples were immersed in a ciprofloxacin solution to enable antibiotic loading. The morphology and chemical composition of the obtained coatings were characterized using scanning electron microscopy with energy-dispersive spectroscopy (SEM/EDS), X-ray photoelectron spectroscopy (XPS), and Fourier transform infrared spectroscopy (FT-IR). These analyses were used to verify the successful formation of the coatings and the incorporation of the drug.

Results

The obtained results confirmed the formation of polyphenolic ion-coordinated coatings on both titanium and polymeric substrates. The modified surfaces exhibited the ability to adsorb ciprofloxacin and subsequently release it in a sustained manner. In addition, biocompatibility studies indicated that the developed coatings maintained favorable biological properties, supporting their potential use in biomedical applications.

Conclusion

Polyphenolic coatings coordinated with bioactive ions represent a promising strategy for implant surface functionalization. Their ability to act as reservoirs for localized and controlled antibiotic delivery, combined with good biocompatibility, makes them attractive candidates for reducing the risk of implant-associated infections in dental and ligament reconstruction applications.

Acknowledgements

This work was produced with financial support from the National Science Centre, Poland (grant no. 2023/51/D/ST5/00144).

D3 – P160

Silver silicate as an antimicrobial additive for dental resin-based composites

Doimo A.L.C.[1,2], Damnjanovic A.[2], Sousa K.S.J.[3,4], Colombari Neto J.[5], Romero-Gavilán F.[4], Doñate-Buendia C.[2], Mínguez-Vega G.[2], Longo E.[1], Assis M.[4]

[1]Center for the Development of Functional Materials (CDMF), Federal University of São Carlos (UFSCar), Brazil; [2]GROC·UJI, Institute of New Imaging Technologies (INIT), Jaume I University (UJI), Castelló de la Plana, Spain; [3]Dept. of Biosciences, Federal University of São Paulo (UNIFESP), Santos, Brazil; [4]Dept. of Industrial Systems and Design Engineering, University of Castellón, Castellón de la Plana, Spain; [5]Dept. of Inorganic and Organic Chemistry, Jaume I University (UJI), Castellón de la Plana, Spain

Introduction

Microbial adhesion on denture bases can lead to inflammation of the palatal mucosa, a condition known as denture stomatitis, which may affect a significant proportion of patients.[1] In this context, silver nanoparticles have been widely investigated as a strategy to combat microorganisms. Among these materials, silver silicate stands out due to its antimicrobial activity against Gram-positive bacteria, Gram-negative bacteria, and fungi.[2]

Aim

The aim of this study was to develop a dental resin-based composite containing silver silicate to obtain a material with enhanced antimicrobial properties.

Materials and Methods

Silver silicate was synthesized via aqueous co-precipitation followed by microwave-assisted hydrothermal treatment at 160 °C for 64 min. The nanoparticles were incorporated into dental resin at concentrations ranging from 0.05 to 0.50 wt%. The mixtures were dispersed by magnetic stirring for 10 min and ultrasonication for 20 min; this cycle was repeated three times to ensure homogeneous distribution. The composites were processed by stereolithography (SLA) 3D printing to obtain cylindrical specimens (10 mm diameter × 2 mm thickness), tensile samples (ISO 527-1BA), and puncture resistance samples (ISO 868).

Results

SEM images revealed that increasing silver silicate concentrations led to loss of polymer structural organization (Fig 1). Contact angle measurements and puncture resistance tests indicated that the incorporation of silver silicate did not significantly affect the resin. Cell viability (Fig. 2) and proliferation assays using human gingival fibroblasts showed that increasing silver content resulted in a reduction in both parameters. Antimicrobial tests demonstrated that the incorporation of silver silicate produced a contact-killing effect against Staphylococcus aureus and Escherichia coli. Overall, these results suggest that silver silicate is a promising antimicrobial additive for dental resin-based materials.

Conclusion

The presence of silver silicate provided a contact-killing bactericidal effect while maintaining physicochemical and mechanical properties of the resin. Although higher silver concentrations slightly affected cell viability, most compositions showed cell proliferation over time. The developed dental resin composites demonstrated promising potential for applications requiring materials with enhanced antimicrobial activity.

Acknowledgements

Fundação de Amparo à Pesquisa do Estado de São Paulo – FAPESP (2023/10462-3, 2025/01424-6 and 2013/07296-2).

References

[1]A Teixeira A.B.V. et al. Adhesion of biofilm, surface characteristics, and mechanical properties of antimicrobial denture base resin. *The Journal of Advanced Prosthodontics* 2023; 15; 80-92.

[2]Doimo A.L.C. et al. Microwave-assisted synthesis of silver silicate: Linking structural and electronic properties to biological performance. *Surfaces and Interfaces* 2025; 107831.




Figure 1. SEM images of the samples **A)** DR; **B)** DR0.05SS; **C)** DR0.10SS; **D)** DR0.25SS, and **E)** DR0.50SS.




Figure 2. Cell viability of Human gingival fibroblasts after 24 h exposure to the samples, evaluated by MTS assay.

D3 – P161

Development of MXene-based coatings on polydopamine-modified titanium implants using alternating current electrophoretic deposition

Aktan M.K.[1], Zayed N.[2], Naenen V.[1], Windey R.[1], Braem A.[1], Vleugels J.[1]
[1]Dept of Materials Engineering, KU Leuven; [2]Dept. of Oral Health Sciences, KU Leuven, Belgium

Introduction

Titanium (Ti) implants are widely used in dental applications; however, their susceptibility to biofilm formation remains a major challenge. Surface functionalization strategies, such as polydopamine (PDA) coatings, can enhance adhesion of bioactive materials. Recently, MXenes have emerged as promising two-dimensional materials with antimicrobial properties. Their integration onto implant surfaces via controlled deposition techniques may offer improved biofilm resistance while maintaining biocompatibility.

Aim

This study aimed to develop MXene-based coatings on PDA-functionalized titanium surfaces using alternating current electrophoretic deposition (AC-EPD) and to evaluate their physicochemical properties, adhesion behavior, antimicrobial performance, and cytocompatibility (Figure 1).

Materials and Methods

MXene suspensions were first characterized in terms of zeta potential, pH, and temperature dependence. Titanium substrates were functionalized with PDA prior to MXene deposition via AC-EPD. Surface morphology and roughness were analyzed using scanning electron microscopy (SEM) and confocal microscopy. Surface charge properties were evaluated via zeta potential measurements as a function of pH, while wettability and surface energy were assessed using contact angle measurements with polar and dispersive liquids. Mechanical stability was examined via scratch testing at varying loads (0.1–0.5 N) and repetition cycles. Antimicrobial performance was evaluated using both 2-species and 14-species biofilm models, and cytocompatibility was assessed using human oral keratinocytes.

Results

MXene suspensions exhibited a zeta potential of −30.5 mV at pH 7.5, with an isoelectric point around pH 3.1 and minimal temperature dependence. PDA functionalization significantly enhanced MXene deposition, as confirmed by SEM and confocal analysis. Surface roughness increased from Sa ≈ 1.1 nm (bare Ti) to ≈ 5 nm for PDA-MXene coatings, with Sz increasing from ~13 nm to ~50 nm. PDA-MXene surfaces showed the lowest isoelectric point and highest basic surface character. Scratch tests indicated partial removal and redistribution of MXene flakes under repeated mechanical stress. Biofilm quantification revealed a significant reduction on PDA-MXene surfaces compared to bare Ti, while no major ecological shifts were observed in the 14-species model. SEM confirmed reduced bacterial adhesion on coated surfaces. Cytocompatibility tests demonstrated that MXene coatings were non-toxic, with cells exhibiting normal morphology and filopodia formation.

Conclusion

MXene coatings deposited on PDA-functionalized titanium via AC-EPD demonstrate enhanced surface properties, effective antimicrobial activity, and good cytocompatibility, highlighting their potential for improving dental implant performance.




Figure 1. Schematic illustration of AC-EPD MXene coatings on titanium implants.

D3 – P162

Low modulus and antibacterial SLM-printed Ti-Nb-based alloys for dental and orthopedic applications

Roquette M.[1], Aparicio C. [1,2], Gil J.[1]
[1]Bioinspired Oral Biomaterials and Interfaces, Dept. Ciencia e Ingeniería de Materiales, EEBE, Universitat Politècnica de Catalunya; [2]Catalan Institution for Research and Advanced Studies (ICREA), Barcelona, Spain

Introduction

Titanium and its alloys are widely used in orthopedic and dental implants due to their excellent corrosion resistance, mechanical strength, and biocompatibility. However, conventional materials such as commercially pure titanium exhibit elastic moduli significantly higher than that of cortical bone, which may lead to stress shielding and compromised long-term implant performance. β-type Ti-Nb alloys have attracted increasing attention as alternative biomaterials due to their reduced elastic modulus and favorable biological response. This work investigates microstructural and mechanical properties of Ti-45Nb and Ti-35Nb-4Ag alloys printed by selective laser melting (SLM) and cell in vitro biological responses of these alloys as candidates for dental and orthopedic applications. The incorporation of Ag is expected to convey antibacterial activity while maintaining biocompatibility and mechanical integrity.

Materials and Methods

Both alloys were fabricated by SLM using six parameter sets that varied (1) laser power, (2) scanning speed, and (3) hatch spacing to identify optimal processing conditions. Microstructural analysis was performed using scanning electron microscopy (SEM), while crystallographic phases were assessed by X-ray diffraction (XRD). Surface chemistry was analyzed by X-ray photoelectron spectroscopy (XPS). Mechanical properties were evaluated by nanoindentation and uniaxial compression testing. Biological performance was evaluated using Saos-2 osteoblast-like cells to assess biocompatibility and osteoblastic differentiation, while antimicrobial performance was tested against biofilms of relevant pathogens, such as *Staphylococcus aureus* and *Porphyromonas gingivalis*.

Results

Optimized processing parameters yielded highly dense parts with minimal porosity. The Ti-45Nb alloy exhibited a density of 5.42 ± 0.02 g/cm³, while Ti-35Nb-4Ag showed a density of 4.78 ± 0.12 g/cm³. Microstructural characterization revealed homogeneous structures in both alloys, and XRD confirmed the predominance of the β-titanium phase. XPS analysis indicated the presence of a stable oxide layer, and confirmed the incorporation of silver in Ti-35Nb-4Ag samples.

Nanoindentation results demonstrated reduced elastic modulus values compared to commercially pure titanium (≈110 GPa). Ti-45Nb exhibited an elastic modulus of 82.8 ± 2.8 GPa and a hardness of 3.46 ± 0.19 GPa. Preliminary mechanical characterization of Ti-35Nb-4Ag suggests similar trends, although further testing is ongoing to confirm these results. Initial biological assessments demonstrated good cell adhesion and viability on both alloys, with preliminary evidence of antibacterial activity in the Ag-containing alloy.

Conclusion

SLM-printed Ti-45Nb and Ti-35Nb-4Ag alloys exhibit appropriate densification, β-phase stability, and surface chemistry suitable for biomedical applications. The reduced elastic modulus and stable surface chemistry suggest strong potential for bone or dental applications to minimize bone resorption. Ongoing work will further investigate chemical stability with corrosion behavior and ion release kinetics tests and antimicrobial effectiveness to validate their potential performance in dental and orthopedic implant scenarios. These results highlight additive manufacturing as a viable approach for tailoring functional titanium alloys with improved mechanical compatibility and biological performance for next-generation implantable devices.

Acknowledgements

This work is part of the project PID2022-137496OB-100, funded by MCIN/AEI/10.13039/501100011033 and by the European Social Fund Plus (ESF+).

D3 – P163

Simvastatin-loaded poly(ε-caprolactone) nanoparticles for perspective application in bone regeneration

Pezzuto M.F., Bezze A., Mattu C.
Dept. of Mechanical and Aerospace Engineering, Politecnico di Torino, Italy

Introduction

Statins have been investigated in recent years for their potential in bone regeneration. Among them, simvastatin has attracted particular interest because of its reported osteogenic effects [1]. However, systemic administration may result in low drug concentrations at the target site and potential side effects. Local delivery systems based on biodegradable polymer nanoparticles (NPs), alone or in combination with hydrogels or scaffolds, are therefore being studied to control the release kinetics. Poly(ε-caprolactone) (PCL) is widely used for this purpose by virtue of its biocompatibility, biodegradability, and ease of processing into nano- and microstructures.

Aim

This work aimed at preparing and characterizing simvastatin-loaded PCL NPs obtained via the nanoprecipitation method. The main physicochemical properties and drug encapsulation/release performances were investigated.

Materials and Methods

PCL nanoparticles were prepared by nanoprecipitation. PCL and simvastatin were dissolved in acetone and added dropwise to an aqueous phase under moderate stirring. The resulting NPs suspension was purified by centrifugation, and the process yield was calculated after freeze drying. Particle size distribution and colloidal stability were analysed by dynamic light scattering (DLS) over 36 days. Encapsulation efficiency and drug release profile were determined by UV–vis spectroscopy. Differential scanning calorimetry (DSC) was used to investigate the physical state of simvastatin within the particles. Nanoparticle morphology was examined by transmission electron microscopy (TEM). Blank PCL nanoparticles were also prepared for comparison.

Results

The nanoprecipitation process produced PCL nanoparticles with a mean hydrodynamic diameter of approximately 220 nm and a polydispersity index of 0.1. The particles remained stable in aqueous suspension for up to 36 days. The process yield was approximately 75%, while simvastatin encapsulation efficiency reached 15%. DSC analysis did not show a clear melting peak for simvastatin, suggesting that the drug may be dispersed within the polymeric matrix in an amorphous state. TEM images (Fig. 1) confirmed the formation of spherical nanoparticles with relatively uniform morphology. These results indicate that nanoprecipitation provides a reproducible approach for obtaining stable PCL nanoparticle suspensions.

Conclusions

The nanoprecipitation method allowed the preparation of simvastatin-loaded PCL nanoparticles with an appropriate size, good stability in aqueous suspension, high drug encapsulation, and controlled release. These NPs can potentially be applied for local delivery of simvastatin to support bone regeneration and tissue repair.

Acknowledgements

This work is carried out with the support of EU-funded HYDROHEAL project (101178398, HORIZON Innovation Actions programme).

References

[1]Jin H., Ji Y., Cui Y., Xu L., Liu H., Wang J. Simvastatin-Incorporated Drug Delivery Systems for Bone Regeneration, *ACS Biomaterials Science & Engineering* 2021; 7(6); 2177-2191.




Fig. 1 TEM images of the blank (a) and Simvastatin-loaded (b) PCL nanoparticles.

D3 – P164
Electrophoretic deposition of chitosan on APTES-functionalized PLA plates

Rosa L.G.S.[1], Segat B.[1], Becker D.[1], Boccaccini A.R.[2]
[1]Laboratory of Plasmas, Films and Surfaces, Santa Catarina State University, Joinville, Brazil; [2]Dept. of Biomaterials, Friedrich-Alexander Universität, Erlangen, Germany

Introduction
One of the main drawbacks of EPD is electric field dampening when working with insulating substrates such as polymeric scaffolds. To enable particle deposition on insulators, strategies such as substrate surface modification, reactor configuration adjustments, and the use of higher voltages are commonly applied to compensate for the reduced local electric field. In this work, these three strategies were employed to deposit chitosan, a biopolymer known for its biocompatibility, hydrophilicity, and adhesion, onto poly-lactic acid (PLA) surfaces. PLA was functionalized with APTES through a two-step process: oxygen inductively coupled plasma treatment followed by immersion in an ethanolic APTES solution. Chitosan was then deposited using higher voltages than typically reported, employing a cylindrical electrode configuration.

Materials and Methods
For PLA plasma surface treatment, samples were positioned in an inductively-coupled plasma reactor – a borosilicate glass chamber with 30.0 mm diameter and 400.0 mm length, with a copper coil of 30 rounds positioned in the middle of the glass chamber. The pressure was maintained at 400 mTorr, and an RF power source (45 W net power) was applied for 10.0 min. After the oxygen plasma treatment, the samples were immersed in a 10% v/v APTES/ethanol solution for 30.0 min, kept under magnetic stirring. For EPD, the samples were positioned at the centre of the cylindrical electrode and clamped to the biased electrode. 50, 75, and 100 V were chosen as applied voltage, and the suspension was prepared using chitosan with 79% v/v ethanol, 20% v/v deionized water, and 1% v/v acetic acid as solvents. Deposition time was kept at 5 min, and electrode radial distance was set to 20 mm. Samples were left to dry at room temperature for at least 12 h.

Results
Table 1 shows the atomic concentrations obtained for pure PLA and APTES-treated PLA. It is possible to conclude that APTES was inserted in the surface due to the sharp rise in Si and N concentrations. Figure 2 shows the SEM micrographs for pure and APTES-treated PLA after chitosan deposition. No chitosan is seen in lower voltages for pure PLA, whereas in APTES-treated PLA all the chosen voltages show chitosan deposition.

Conclusion
Based on XPS, APTES was successfully inserted on PLA surface using inductively-coupled plasma pre-treatment. The APTES insertion is beneficial for chitosan deposition, since every EPD condition yielded a coating, although not homogeneous in every applied voltage.

Acknowledgements
CAPES (code 001), CNPq 404401/2023-6, 306823/2021-7 and 404320/2024-4.

Figure 1 – SEM micrographs for Pristine PLA and APTES-treated PLA after EPD.




Table 1 – atomic concentrations detected via XPS.

Sample	Element	Atomic concentration (at.%)
PLA Pristine	Si	1.5
	S	0.2
	C	63.8
	O	34.6
APTES-treated PLA	Si	13.0 ± 0.7
	C	48.4 ± 1.0
	O	26.2 ± 1.1
	N	12.2 ± 1.2

D3 – P165

A 3D bioprinted bicompartmental breast cancer model for antimetastatic drug screening

Zorba I.[1], Platania V.[1], Chatzinikolaidou M.[1,2]
[1]Dept. Materials Science and Engineering; [2]Foundation for Research and Technology Hellas (FORTH), Heraklion, Greece

Introduction

Breast cancer is a heterogenous disease varying in aggressiveness and prognosis, and one of the most common malignancies worldwide. As the disease progresses, tumors exhibit distinct mechanical and morphological characteristics that correlate to their aggressiveness. 2D cell culture models are commonly used to study drug responses on breast cancer cells, but with results that do not reflect preclinical and clinical outcomes. 3D bioprinting enables complex in vitro drug testing mimicking the 3D microenvironment of cancerous tissue, and the interactions of the cells with their environment.

Aim

We aim to develop a 3D bioprinted, biomimetic, bicompartmental model that replicates the biochemical and mechanical properties of the breast cancer microenvironment, resembling the stiffness and the collagen content of the native tumour tissues, able to monitor the migration of 4T1 breast cancer cells in the presence and absence of a migration inhibiting drug.

Materials and Methods

The bicompartmental model comprised two bioink formulations of different concentrations of gelatin and alginate. Each ink was evaluated for its printability, degradation, mechanical and biological properties. The first bioink mimics the denser, stiffer cancerous tissue with 6 w/v% gelatin (Gel), 2 w/v% alginate (Alg) and encapsulated 4T1 cells, and the second bioink recapitulates the physiological tissue with 3 w/v% Gel, 1 w/v% Alg and fibroblasts.

Results

The breast cancer-mimicking bioink was stable for 21 days. The bioinks showed adequate printability over 60%, stability, and Young modulus values of 84 kPa and 45 kPa, which are relevant to breast cancer tumours and the surrounding healthy tissue, respectively. The migration assays demonstrate the potential of the bioprinted, bicompartmental model to study the metastatic capacity of the highly aggressive 4T1 breast cancer cells, mimicking the clinical progression of human triple-negative breast cancer, and develop new antimetastatic drugs. The drug used in this study is the ROCK (Rho-associated protein kinase) inhibitor GSK269962A. A significant inhibition of the 4T1 cell migration was observed in the presence of the ROCK inhibitor added for 2 and 24 h to the culture, compared to the control, with the antimigrational effect being higher after 2 h of induction. The proliferative capacity of the 4T1 cells was significantly reduced in the presence of the inhibitor. These observations have been validated by means of time lapse microscopy and in 3D bioprinted constructs with GFP-positive 4T1 cells.

Conclusion

This study provides a 3D bioprinted bicompartmental model to investigate the proliferative and migratory behaviour of 4T1 cells.

D3 – P166

A universal visible-light-responsive sacrificial polysaccharide platform for biofabrication

Jafari H., Malekmohammadinouri A.S., Shavandi A.
3BIO-BioMatter, École Polytechnique de Bruxelles, Université Libre de Bruxelles, Belgium

Introduction

Sacrificial biomaterials are widely used to fabricate complex biological architectures; however, existing systems are often material-specific and rely on temperature-triggered removal mechanisms, limiting versatility and temporal control. Here, we introduce a universal polysaccharide-based sacrificial platform capable of programmable dissociation under mild visible-light conditions while simultaneously functioning as printable hydrogels and embedded printing support baths.

Materials and Methods

A library of oxidized polysaccharides was combined with carboxymethyl chitosan to form dynamically crosslinked hydrogels, which were subsequently converted into jammed microgel support baths through mechanical fragmentation (Fig. 1A). Material behaviour was evaluated through rheological characterization (Fig. 1C), self-printing and embedded printing experiments (Fig. 1D–F), and visible-light-triggered dissociation studies.

Results

The platform successfully generated printable bulk hydrogels and microgel support baths exhibiting shear-thinning and rapid recovery behaviour (Fig. 1A-C). By tuning the photosensitizer concentration, material lifetime could be programmed from rapid visible-light-triggered dissociation within seconds to prolonged stability over several hours or days in the absence of irradiation. Self-supporting lattice structures were readily fabricated and subsequently removed on demand through visible-light exposure, demonstrating complete construct dissociation within approximately one minute (Fig. 1D). The microgel support bath further enabled embedded printing and stabilization of complex structures, followed by selective matrix removal and recovery of the printed construct (Fig. 1E). Importantly, the platform supported fabrication of diverse freeform geometries, including hollow, helical and branched architectures, highlighting its versatility for sacrificial biofabrication applications (Fig. 1F).

Conclusion

This work establishes a universal visible-light-responsive sacrificial biomaterial platform combining programmable dissociation, embedded printing capability, and broad polysaccharide compatibility. The ability to tune material lifetime from seconds to days while enabling fabrication, support, and recovery of complex structures provides a versatile strategy for next generation biofabrication and tissue engineering applications.




Figure 1. Universal visible-light-responsive sacrificial polysaccharide platform demonstrating hydrogel formation and microgel generation (A), macroscopic image of hydrogel before and after light exposure (B), rheological behavior of the sacrificial material (C), self-printing and on-demand removal (D), embedded printing and construct recovery (E), and fabrication of complex freeform architectures (F).

D3 – P167

Sequential integrated breast-vesse-bone model for breast cancer bone metastasis

Gungor E.O.[1], Son C.D.[1], Buyuksungur S.[2]
[1]Dept. Biology, Middle East Technical University (METU); [2]METU BIOMATEN, Center of Excellence in Biomaterials and Tissue Engineering, Ankara, Turkey

Introduction

Breast cancer is one of the most common cancer types in women, and most deaths are related to metastasis. Bone is the most common metastatic site in 70% of cases. Tissue engineered 3D matrices provide physiologically relevant platforms to mimic the intratumoral and extracellular interactions. This study presents a physiologically relevant, triphasic 3D breast cancer bone metastasis model, which was built by sequentially integrating mature bone (hFOB in GelMA/HAp) and vessel (HUVEC: ADSC in GelMA) matrices before adding MDA-MB-231/MCF10A coculture spheroid (in GelMA), to capture intratumoral interactions and tumor microenvironment, while enabling the monitoring of the transendothelial migration toward bone.

Materials and Methods

Hydrogels with varying GelMA concentrations (5-15%, w/v) were prepared for breast and vascular matrices, while GelMA/HAp hydrogels with different HAp concentrations (5-15%, w/w) were used for bone matrix. Optimal compositions were chosen based on mechanical tests. After the bone matrix was first established using hFOB cells and matured for 7 days, the vascular matrix composed of ADSC and HUVEC cells was added. After an additional 7 days, breast cancer matrix containing MDA-MB-231:MCF10A spheroids was incorporated to have the triphasic model. Metastatic behavior was monitored by labeling MDA-MB-231, HUVEC, and hFOB cells with CellTrackers and imaging with CLSM.

Results

For the breast cancer matrix, 15% GelMA (5.9±0.6 kPa), for the vascular matrix, 10% GelMA (3.2±0.6 kPa), and for the bone matrix, 15% GelMA containing 15% HAp (15G15H, 8.6±1.1 kPa) were chosen. To establish the bone matrix, hFOB cells were encapsulated in 15G15H hydrogels. After 7 days of bone matrix incubation, vascular matrix was added adjacent to the bone matrix. Cell infiltration was observed in the interface of the bone vessel compartment (Figure 1). Finally, MDA-MB-231:MCF10A coculture spheroids were encapsulated in 15% GelMA to establish the triphasic model. It was observed that cancer cells metastasized to bone matrix in the presence of vascular matrix (Figure 2A), whereas bone matrix alone didn't trigger metastasis (Figure 2B).

Conclusion

The sequential integration of the bone, vascular, and breast cancer phases enabled the assessment of metastatic behavior under physiologically relevant tissue conditions. *In vitro* results indicated that the vascular compartment is a key mediator of tumor migration. Overall, the model has potential as a physiologically relevant platform to study transendothelial migration of breast cancer cells toward bone tissue.

Acknowledgements

This study was supported by the Presidency of Strategy and Budget (Project No: 08.11.KB.2016K121520), METU BIOMATEN, TUBİTAK through BIDEB 2210/A MSc/MA scholarship.




Figure 1. Immunofluorescence staining of vessel (HUVECs and ADSCs in 10G hydrogels)-bone (hFOB in 15G15H hydrogels) after 7 days for vessel matrix, and 14 days for bone matrix. Red: OPN, AlexaFluor 647 conjugate, Green: CD31 AlexaFluor 488 conjugate, Blue: nucleus, DAPI (n=3) (Magnification: 10X, Scale bar: 50µm).




Figure 2. Confocal micrograph of the triphasic model containing A) Br-Ca, Vessel,and Bone and B) Br-Ca, cell free GelMA hydrogel, and bone on days 1, 4, and 7. Red: MDA-MB-231 cells labeled CellTracker™ Deep Red, Green: HUVECs labeled CellTracker™ Green, Blue: hFOB labeled CellTracker™ Blue. Magnification: 5X (0.5X digital zoom was applied to increase the field of view), scale bar: 500 µm.

D3 – P168
Photocrosslinkable chitosan-based hydrogels for bone regeneration

Traldi C.[1,2], Peletto M.[1,2], Tonda-Turo C.[1,2]
[1]Dept. of Mechanical and Aerospace Engineering, Politecnico di Torino; [2]POLITO BIOMedLAB, Politecnico di Torino, Italy

Introduction
The effective healing of severe bone defects remains an unmet clinical need. Biocompatible hydrogels have emerged as versatile systems to obtain implantable bioactive scaffolds which can support tissue growth and regeneration. Among naturally derived polymers, chitosan has shown great potential for the formulation of biological matrices, due to its native biocompatibility and biodegradability. However, chitosan-based hydrogels exhibit low mechanical properties under physiological conditions, limiting their *in vivo* applications. Therefore, the optimization of crosslinking strategies is essential to increase the processability of this material and ensure structural stability for tissue engineering. In this study, thermoresponsive and photocrosslinkable chitosan-based hydrogels were investigated. The primary objective was to formulate extrudable systems, capable of fast *in situ* gelation for minimally invasive application directly in the bone defect site.

Materials and Methods
Thermo-induced physical crosslinking was obtained by neutralizing chitosan solution with β-glycerophosphate, which enabled sol-gel transition in physiological conditions. Chitosan/β-glycerophosphate ratio was optimized to modulate the gelation kinetics and the viscoelastic properties of the hydrogel formulations. To achieve light-induced crosslinking, methacrylated chitosan was synthetized as photosensitive polymer via reaction with methacrylic anhydride. The formulated hydrogels were characterized in terms of rheological behaviour, extrudability, mechanical properties and biocompatibility.

Results
The gelation kinetics of the hydrogels were investigated through rheological analysis. Amplitude sweep tests showed an increase in the storage modulus of chitosan/β-glycerophosphate hydrogels, consistent with the sol-gel transition at 37°C. In addition, real-time photorheology demonstrated the fast crosslinking of methacrylated chitosan after visible light irradiation. Frequency sweep tests confirmed the prevalence of elastic response and the stability of the crosslinked networks. Injectability and printability tests proved hydrogel extrudability and shape fidelity. Lastly, the feasibility of the proposed hydrogels as matrices for cell growth was assessed via indirect and direct assays with human cells.

Conclusion
The results demonstrate the potential of the here presented hydrogel formulations for tissue engineering applications. The choice of chitosan as base polymer was proved effective as its easy chemical modification enables for a fine-tuning of its properties to meet specific application requirements. Given their biocompatibility, chitosan-based systems are suitable for future *in vivo* applications. The possibility of using hydrogel-based implants fitting the lesion site represent an innovative therapeutic strategy, then further studies will focus on incorporating bioactive cues into the hydrogel network to accelerate bone healing and confer antibacterial properties.

Acknowledgements
This work is carried out with the support of EU-funded HYDROHEAL project (101178398, HORIZON Innovation Actions programme).

D3 – P169

3D-printed bio-based methacrylated pectin patches for personalized skin therapy and regeneration

Tivano F.[1], Zoso A.[1], Scano A.[2], Chiappone A.[2], Casti F. [2], Ennas G. [2], Carmagnola I.[1], Chiono V.[1]
[1]Dept. of Mechanical and Aerospace Engineering, Politecnico di Torino; [2]Dept. of Chemical and Geological Sciences, Università di Cagliari, Italy

Introduction

Chronic wounds and inflammatory skin disorders represent a major unmet clinical need and are often associated with excessive production of reactive oxygen species. Hydrogel dressings represent promising platforms for localized therapeutic delivery, yet many current systems lack sustainability and adaptability to patient-specific wound geometries. In this context, combining bio-based materials with additive manufacturing may enable the development of customizable and environmentally responsible wound therapies. Methacrylated pectin (PECMA), a chemically modified polysaccharide derived from agricultural by-products, represents an attractive printable biomaterial. Moreover, PECMA matrices can serve as drug delivery platforms, where antioxidant plant-derived bioactives are loaded into a mesoporous silica matrix to obtain novel hybrid nanocomposites enabling a controlled release, and supporting multifunctional and sustainable wound healing strategies.

Aim

This study aimed to develop a bio-based PECMA hydrogel system for extrusion-based 3D bioprinting of personalized wound patches capable of delivering antioxidant plant-derived therapeutics through a mesoporous silica matrix.

Materials and Methods

Pectin was chemically modified through methacrylation to enable photo-crosslinking and compatibility with extrusion bioprinting. Hydrogels were fabricated through a dual crosslinking strategy combining UV-induced polymerization and calcium-mediated ionic crosslinking. Rheological analyses, mechanical testing, swelling and degradation studies were performed to evaluate hydrogel properties and printability. Then, antioxidant *Rosa canina*/silica (R/SiO_2 NC) and *Harpagophytum procumbens*/silica nanocomposites (H/SiO_2 NC) were prepared by an eco-friendly ball-milling technique in collaboration with the University of Cagliari and incorporated into PECMA inks. The physico-chemical properties of the composite hydrogels were evaluated after nanocomposites (NCs) incorporation. *In vitro* cytocompatibility was assessed using human fibroblasts (HFF-1) and keratinocytes (HaCaT).

Results

PECMA was successfully synthetized with a degree of methacrylation of 65%. PECMA hydrogels exhibited rapid UV-induced crosslinking (~40 s) and suitable shear-thinning behavior for extrusion-based printing. The dual crosslinking strategy significantly enhanced hydrogel stiffness, increasing the storage modulus from 42 Pa to 795 Pa while maintaining structural stability. The incorporation of NCs further reinforced the hydrogel network, increasing the storage modulus up to 2600 Pa without compromising print fidelity (Figure 1). *In vitro* assays using HFF-1 and HaCaT cells confirmed excellent cytocompatibility with R/SiO_2 NC (100 mg/mL) and H/SiO_2 NC (30 mg/mL)-loaded PECMA hydrogels.

Conclusion

Overall, NCs-loaded PECMA hydrogels enabled the fabrication of customizable bio-based wound patches with tunable mechanical properties, good printability, and high cytocompatibility. This platform represents a promising strategy for personalized treatment of oxidative stress–driven chronic wounds while promoting sustainable biomaterial design.

Acknowledgements

FT acknowledges support from Research and Innovation NOP 2014-2020 for Doctoral Research programmes (Action IV.5) and INJECTHEAL Project, funded by the European Union, through the Horizon Europe research and innovation programme under the Grant Agreement no. 101177924. Views and opinions expressed are however those of the author(s) only and do not necessarily reflect those of the European Union or European Health and Digital Executive Agency (HADEA). Neither the European Union nor the granting authority can be held responsible for them.




Figure 1. Confocal images showing square pores of double crosslinked PECMA (left) and NCs-loaded PECMA (right) hydrogels.

D3 – P170

Photoactivated polyurethane hydrogels for biofabrication: Tunable thermo-responsive bioinks with enhanced printability and stability

Boffito M.[1], Calzone S.[1], Naing M.W.[2], Ciardelli G.[1]
[1]DIMEAS Politecnico di Torino, Italy; [2]A*STAR - Agency for Science, Technology and Research, Singapore

Introduction

Photoactivated biomaterials are emerging as key enablers in biofabrication, allowing spatiotemporal control over scaffold formation and properties. Among injectable systems, thermo-responsive hydrogels such as Poloxamer 407 (P407) are attractive due to their processability; however, their poor mechanical stability and rapid dissolution limit their application in 3D bioprinting. This work aims to develop photo-crosslinkable, thermo-responsive hydrogels with improved structural integrity and tunable properties for advanced biofabrication.

Materials and Methods

Amphiphilic polyurethane (PUR)-based copolymers were synthesized by chain extension of P407 using aliphatic diisocyanates and amino acid-derived diols (NHP407). To introduce photo-responsiveness, acrylate functionalities were incorporated through two strategies: (i) blending with poly(ethylene glycol) diacrylate (PEGDA), and (ii) end-capping an isocyanate-terminated P407-based prepolymer with hydroxyethyl methyl acrylate or Pentaerythritol triacrylate, respectively (HHP407, PHP407). (Fig.1)
Three classes of hydrogels were developed: PUR/PEGDA blends, intrinsically acrylated PURs, and hybrid systems combining both approaches. Materials were characterized for thermo-gelation, photo-crosslinking behavior, rheological properties, and stability in aqueous environments.
Selected formulations were processed as bioinks using a modified extrusion-based bioprinter. Printing parameters and UV/Vis-induced crosslinking conditions were optimized to achieve high printing fidelity and cell-compatible processing**.**

Results

PUR-modified hydrogels exhibited enhanced gelation kinetics, mechanical strength, and stability compared to native P407 systems. However, thermo-responsive behaviour alone was insufficient to ensure filament stability during printing.

The introduction of photoactivated crosslinking enabled rapid post-deposition stabilization, significantly improving shape fidelity and resistance to dissolution. In particular, PUR/PEGDA and HHP407/PEGDA formulations showed optimal rheological properties for extrusion and efficient light-induced network formation. These systems enabled the fabrication of multilayered, grid-like constructs with high resolution and long-term stability, while maintaining cell viability for up to one month (Fig.2). The dual thermo- and photo-responsive nature of the bioinks allowed independent tuning of printability and post-printing mechanical reinforcement.

Conclusion

This study demonstrates that integrating photoactivation into thermo-responsive polyurethane hydrogels is a powerful strategy to overcome key limitations in biofabrication. Light-triggered crosslinking provides precise temporal control over scaffold stabilization, enabling the transition from printable soft inks to mechanically robust constructs.

The developed platform offers a high degree of tunability in rheological behavior, crosslinking density, and structural stability, making it adaptable to diverse biofabrication requirements. By decoupling extrusion properties from final scaffold mechanics, these materials address a critical bottleneck in the design of bioinks. Overall, this work highlights the potential of photoactivated polyurethane hydrogels as next-generation bioinks for high-resolution, cell-laden constructs, advancing the development of clinically relevant biofabrication strategies based on light-controlled materials.




Fig.1 Representations of the different tested strategies and expected thermos- and photo-sensitive behavior: (A) upon irradiation, the acrylate water soluble polymer forms a mesh entrapping PUR micelles; (B) upon irradiation, the acrylate PUR forms crosslinked micelles; (C) two different degrees of crosslinking are involved.




Fig.2 Fluorescence microscope images of the cellularized 3D printed scaffolds.

D3 – P171
Photoactivated click chemistry for 3D models

Laurano R., Boffito M., Ciardelli G.
Dept. of Mechanical and Aerospace Engineering, Politecnico di Torino, Italy

Introduction
Resembling the mechanical features of native tissues is a key aspect in the design of *in vitro* tissue models. In this regard, the engineering of light-responsive hydrogels can bring high potential to finely tune construct mechanical properties through the control over the crosslinking density and photoactivated chemistry. Vis-light thiol-ene photo-click chemistry represents a powerful tool, ensuring high spatiotemporal control and biorthogonal network formation.

Aim
This work aimed at engineering two polyurethane-based thiol-ene bioinks and investigating the influence of the –ene moieties on the photo-crosslinking mechanism and hydrogel mechanical properties.

Materials and Methods
An amphiphilic poly(ether urethane) (PEU) was synthesized through a two-step procedure and subjected to an acidic treatment to expose secondary amino groups. Carbodiimide-mediated chemistry was exploited to functionalize PEU polymeric chains with thioglycolic acid, 2-carboxyethyl acrylate and 5-norbornene-2-carboxylic acid to finally expose thiol (S-PEU), acrylate (A-PEU) and norbornene (NB-PEU) moieties, respectively. PEUs were characterized through Size Exclusion Chromatography (SEC), Infrared (IR) and Nuclear Magnetic Resonance (NMR) spectroscopies, and colorimetric assays. Thiol-ene hydrogels were photo-irradiated at 525 nm (80k Lux, 30s) in the presence of Eosin Y and Triethanolamine (TEOA) and their mechanical properties were studied through rheology. Hydrogel processability as bioinks was studied by extruding differently-shaped structures, while cytocompatibility was assessed according to the ISO10993-5.

Results
SEC, IR and Orange assay first assessed the successful synthesis of a high molecular weight PEU ($\overline{Mn}$ 22kDa) bearing 4.5×10E20±1.8×10E19 amines/$g_{polymer}$. Then, the Ellman test and NMR spectroscopy confirmed the carbodiimide-mediated functionalization, giving approx. 10E19 thiol and acrylate groups/$g_{polymer}$ and 10E17 norbornene moieties/$g_{polymer}$. Furthermore, NMR spectra showed the almost complete consumption of photo-sensitive moieties upon irradiation with green light. Compared to not-irradiated samples, photo-irradiated bioinks exhibited a significantly higher elastic behavior (i.e., storage/loss moduli crossover frequency at 30 °C ω=8 rad/s *vs*. 4 rad/s for S-PEU/A-PEU and 3 rad/s *vs.* 1.4 rad/s for S-PEU/NB-PEU) and improved hydrogel resistance to applied strain (i.e., critical deformation ε=18.6% *vs*. 11.6% for S-PEU/A-PEU and 11.6% *vs.* 7.2% for S-PEU/NB-PEU). Furthermore, TEOA addition resulted in improved mechanical properties only for S-PEU/A-PEU, thus demonstrating the ene-dependent photo-crosslinking mechanism. Hydrogel capability to keep the shape over time was proved through the fabrication of 3D structures. Lastly, hydrogels were found to be cytocompatible (cell viability > 98%) according to the ISO 10993-5.

Conclusion
The selection of the -ene moiety allowed a fine tuning of the photoactivated mechanism, paving the way for the fabrication of tissue models differing for mechanical features (e.g., young *vs.* aged).

D3 – P172

Development of an animal model of hypoxia on porcine skin mimicking diabetic chronic wound treatment

Svobodova L.[1], Filova E.[1], Knitlova J.[1], Litvinec A.[1,2], Juhas S.[3], Juhasova J.[3], Jencova V.[4], Havlickova K.[4], Hauzerova S.[4], Riedel T.[5], Riedelova Z.[5], Bacakova L.[1]

[1]Dept of Biomaterials and Tissue Engineering, Institute of Physiology of the Czech Academy of Sciences, Prague; [2]Dept. of Tissue Engineering, Institute of Experimental Medicine of the Czech Academy of Sciences, Prague; [3]Institute of Animal Physiology and Genetics of the Czech Academy of Sciences, Libechov; [4]Dept. of Chemistry, Faculty of Science, Humanities and Education, Technical University of Liberec; [5]Dept. of Chemistry and Physics of Surfaces and Biointerfaces, Institute of Macromolecular Chemistry of the Czech Academy of Sciences, Prague, Czech Republic

Introduction

Diabetic non-healing wounds constitute a huge clinical problem in contemporary healthcare. The unique pathophysiological characteristics of chronic diabetic wounds require the development of appropriate preclinical models for evaluating novel therapeutic interventions. This study aimed to establish and validate a clinically relevant chronic hypoxic diabetic wound model in a porcine system.

Materials and Methods

Hypoxic conditions mimicking the diabetic wound microenvironment were established in porcine skin via full-thickness dermal-fascial separation using a silicone membrane barrier, while normoxic controls underwent identical procedures without membrane insertion. Wounds were covered by PCL nanofiber membranes, membranes made of PCL coated with fibrin and VEGF, or no specific treatment was applied, and a standard wound dressing was applied on top. The study optimized wound dimensions and assessed healing kinetics over 21 days. Evaluation included macroscopic wound closure measurements and histological analysis of excised specimens using Masson's trichrome staining to quantify collagen deposition, neovascularisation, and newly established keratinocyte layer. Immunohistochemical staining for HIF-1α confirmed hypoxic conditions.

Results

The preliminary histological results confirmed delayed wound closure and intense HIF-1 staining in hypoxic wounds. Vascularisation was the best developed in hypoxic and normoxic wounds coated with PCL-fibrin-VEGF nanofibers, supported and in normoxic wounds treated with PCL. The highest collagen fiber formation was in the hypoxic group treated with PCL-fibrin-VEGF nanofibers.

Conclusion

Hypoxia, one of the common pathological conditions in diabetic patients, was established in a porcine model. PCL and PCL-Fb-VEGF treatments had a positive influence on the healing of hypoxic and control wounds.

Acknowledgements

This project was supported by project No. CZ.02.01.01/00/22_008/0004562 of the Ministry of Education, Youth and Sports of the Czech Republic, co-funded by the European Union. Further support was provided by the *Praemium Academiae* grant (No. AP 2202) of the Czech Academy of Sciences and the research plan of the Institute of Animal Physiology and Genetics (RVO:67985904).

D3 – P173
Engineering perfused vasculature in gelatin-based 3D tissue constructs

Gaglio C.G. [1,2], Napione L.[1], Frascella F.[1], Moroni L.[2], Pirri C.F.[1,3]
[1]DISAT, PolitoBIOMed Lab, PoliTO, Turin, Italy; [2]CTR Dept., MERLN Institute, FHML, Maastricht University, The Netherlands; [3]CSFT, IIT, Turin, Italy

Introduction
Three-dimensional (3D) in-vitro models better recapitulate in-vivo conditions than traditional 2D cultures. However, reproducing functional vasculature remains a critical challenge, as it regulates nutrient and oxygen delivery, waste removal, and the establishment of a physiologically relevant endothelial barrier.

Aim
This study aims to develop a PDMS millifluidic platform integrating a perfusable vascular compartment within gelatin-derived tissue constructs, enabling their integration into diseased models to study angiogenesis, tumor-vasculature interactions, and drug-response.

Materials and Methods
Gelatin-based materials including Gelatin Methacryloyl (GelMA), GelMA-Polyvinyl alcohol (PVA) aqueous two-phase emulsions (ATPE), and unmodified gelatin hydrogels were evaluated for human umbilical vein endothelial cells (HUVECs) compatibility, both as cell-laden matrices and substrates for endothelial monolayer formation. Cell metabolic activity, viability and monolayer stability were assessed using MTT assays, Live/Dead staining, and VE-Cadherin immunostaining. A PDMS chip was fabricated via master molding. To fabricate patent channels extrusion-based bioprinting, light-based techniques, and sacrificial templating were evaluated. A parallel auxiliary channel was incorporated to host 3D structures including spheroids or organoids at a controlled distance from the vascular compartment. To enhance endothelial stability, two approaches were investigated: exposure to pathophysiologically relevant shear stress and co-culture with human mesenchymal stem cells (hMSCs), using CD31 and Vimentin for cell identification.

Results
All formulations supported HUVECs adhesion and viability. Live/Dead staining confirmed high cell viability, while VE-cadherin immunostaining demonstrated the formation of a continuous endothelial monolayer on selected hydrogel surfaces. Sacrificial templating yielded smooth and patent channels (~700 µm diameter) that and supported endothelialization and stable perfusion. Under flow, HUVECs remained attached to the channel walls and showed an elongated morphology. Co-culture with hMSCs further enhanced monolayer stability in static conditions and promoted mural cell-like differentiation, confirmed by immunostaining.

Conclusion
This work establishes dynamic culture conditions in gelatin-derived vascular models. Ongoing barrier function characterization and integration of diseased compartments will further validate the platform as a versatile tool for vascularized 3D tissue models enabling disease modeling and drug screening.

Acknowledgements
This publication is part of the project PNRR-NGEU which has received funding from the MUR – DM 118/2023. Project PNC 0000001 D3 4 Health, - CUP B83C22006120001, National plan for complementary investments to the PNRR, funded by European Union – NextGenerationEU".

D3 – P174

Dynamic organ-on-chip 3D breast cancer models for investigating metabolic interventions in chemotherapy

Giannoccaro A.[1,3], Palamà E. [2], Scaglione S. [2], Mattu C.[1], Ciardelli G. [1]
[1]DIMEAS, Politecnico di Torino; [2]React4life s.p.a, Genoa; [3]Me.Pre.C.C, Università di Palermo, Italy

Introduction

Triple-negative breast cancer (TNBC) remains one of the most challenging breast cancer subtypes due to its aggressive behavior and the lack of targeted therapies. Increasing evidence links tumor progression and therapy resistance to altered glucose metabolism, generating growing interest in dietary interventions such as glucose restriction or fasting-mimicking approaches as adjuvant strategies to conventional chemotherapy. However, the limited predictive capability of traditional in vitro and in vivo models still hampers the translational evaluation of these combined therapeutic strategies.

Aim

This study aims to develop a novel 3D in vitro TNBC model integrated into an organ-on-chip platform to evaluate the impact of glucose restriction on breast cancer cells viability and chemotherapy efficacy.

Materials and Methods

In this study, an advanced dynamic 3D in vitro TNBC model was developed by embedding MDA-MB-231 cells within tunable alginate-based hydrogels and integrating the constructs into an organ-on-chip platform (MIVO®), enabling physiologically relevant diffusion of nutrients, metabolites, and chemotherapeutic agents. The breast cancer model was used (i) to reproduce the clinically observed impact of glucose intake on tumor cell viability by simulating normal glucose uptake (25 mM glucose), glucose restriction (5 mM glucose), and fasting (0 mM glucose) conditions. In addition, (ii) the cross-interaction between fasting and chemotherapy was investigated by combining Cisplatin (10 µM) treatment with different fasting regimens. Distinct fasting windows applied before and/or during chemotherapy were explored to better mimic clinically adopted protocols. Parallel experiments were performed under static and dynamic culture conditions, and the results were compared with conventional 2D cultures. An in vitro healthy tissue control based on human dermal fibroblasts (HDFs) was included to evaluate potential off-target effects.

Results

Cell viability, proliferation, and morphology were assessed through live/dead assays, Alamar Blue, and immunofluorescence analysis of proliferation (Ki67) and hypoxia (HIF-1α). Glucose deprivation induced a significant reduction in tumor cell viability and proliferation, particularly under dynamic 3D culture conditions, whereas healthy fibroblasts showed minimal sensitivity. Notably, dynamic perfusion significantly improved cisplatin penetration into the 3D tumor constructs, resulting in increased tumor cell death compared with static cultures, in closer agreement with clinical observations. The combination of fasting-mimicking conditions and chemotherapy further reduced tumor viability, although residual proliferative and hypoxic markers suggested complex tumor adaptation mechanisms that warrant further investigation.

Conclusion

Overall, this organ-on-chip–based dynamic 3D TNBC model represents a robust and predictive platform for investigating tumor metabolic dependencies, evaluating combinatorial therapeutic strategies, and improving the translational relevance of preclinical cancer research.

D3 – P175

Fused deposition modelling of custom poly(ester-urethane)s: A printability study

Sartori S., Grivet Brancot A., Ciardelli G., Boffito M.
Dept. of Mechanical and Aerospace Engineering, Politecnico di Torino, Italy

Introduction

The demand for physiologically relevant *in vitro* models has driven interest in organ-on-chip technologies, where 3D printing offers design flexibility and scalable fabrication. Fused Deposition Modelling (FDM) is widely accessible; however, commonly used materials such as PLA lack the mechanical compliance required to mimic soft tissues. Poly(ester-urethane)s (PUs) represent a promising alternative, although their processability remains challenging. This study investigates PUs to assess their suitability for FDM-based fabrication.

Materials and Methods

We synthesised different PU from poly(ε-caprolactone) diol, 2000Da, 1,6-diisocyanatohexane and different chain extender (1,4-butanediol; 1,8-octanediol; 1,12-dodecanediol). The PUs were synthesized according to a previously developed protocol[1]. The PU were characterized by Size-Exclusion Chromatography (SEC), Thermogravimetric Analysis, Differential Scanning Calorimetry and rheology. The polymers where microfabricated by using Dr. INVIVO 4D6 (Rokit Healthcare); printing temperature and pressure of about 120°C and 170 kPa were used. Square scaffolds were fabricated with two infill structures (45°/135° grid with 20 or 25 infill percentages), named inf_20 and inf_25, respectively. The morphology was observed by an optical microscope (DFC3000 G, Leica Microsystems). Scaffold Compression in the longitudinal direction were assessed using an Instron 3365 tester (Norwood).

Results

The PUs exhibited Mn in the range of 29.000 - 30.000 Da, with narrow polydispersity (1.3–1.5). All materials showed elastomeric behavior (up to ~740% strain at break) and Young's moduli ranging from 170 to 540 MPa. Thermal analysis highlighted dependence of phase crystallinity on the chain extender: BHC2000 showed the lowest crystallinity, while DHC2000 the highest one. PUs exhibited thermal stability, ensuring compatibility with melt extrusion. Rheology highlighted the highest crossover temperatures for DHC2000, at 120 °C. Frequency sweep tests performed at a temperature 10 °C above the T_{CO}, showed only BHC2000 and OHC2000 reached fully molten states. No degradation was observed during processing, as assed by SEC analysis. BHC2000 scaffolds showed uniform, smooth filaments (fig. 1) whereas DHC2000 and OHC2000 exhibited irregular morphologies due to higher crystallinity. BHC2000 scaffolds demonstrated compressive moduli in the range 7.4–12.3 MPa.




Fig.1 Optical microscopy images of BHC2000 inf_20 scaffolds

Conclusion

Different PUs were synthesized and successfully processed, with BHC2000 demonstrating superior printability and structural regularity due to its lower crystallinity. The resulting scaffolds showed high potential for soft tissue engineering applications.

References

[1]Sartori S., Boffito M., Serafini P., Caporale A., Silvestri A., Bernardi E., Sassi M.P., Boccafoschi F., Ciardelli G., Synthesis and structure-property relationship of polyester-urethanes and their evaluation for the regeneration of contractile tissues. *React. Funct. Polym* 2013; 73; 1366–1376.

D3 – P176

Self-healing injectable hydrogels for the treatment of myocardial infarction using nanoparticles in a microfluidic device

Paoletti C.[1], Tivano F.[1], Nicoletti L.[1,2], Stola G.P.[1,2], Ballerini M.[3], Damonte G.[4], Coletto M.[1], Zoso A.[1], Marcello E.[1], Bollini S.[4,5], Occhetta P.[3], Rasponi M.[3], Chiono V.[1,2,6]

[1]Dept. of Mechanical and Aerospace Engineering (DIMEAS), Politecnico di Torino; [2]POLIRNA Srl, Torino; [3]Dept. of Electronics, Information and Bioengineering, Politecnico di Milano; [4]Dept. of Experimental Medicine (DIMES), Università di Genova; [5]IRCCS Azienda Ospedaliera Metropolitana (IRCCS AOM), Genova; [6]Interuniversity Center for the Promotion of 3Rs Principles in Teaching and Research (Centro3R), Italy

Introduction

Myocardial infarction (MI) remains a leading cause of morbidity and mortality worldwide, emphasizing the need for innovative strategies to enhance cardiac repair. Injectable hydrogels have attracted significant interest in this field, as they can provide structural support to damaged tissue while enabling the localized and controlled release of therapeutic agents. Among emerging approaches, the non-viral direct reprogramming of cardiac fibroblasts (CFs) into induced cardiomyocytes (iCMs) using a combination of four microRNAs (miRcombo) has shown considerable potential. In this context, we recently developed polymer-lipid hybrid nanoparticles (NPs) featuring a lipoplex core for efficient miRNA encapsulation and a stabilizing polymeric shell. These nanoparticles were further functionalized via click chemistry with a CF-specific antibody (F-NPs), allowing targeted delivery. To further enhance nanoparticle delivery, this study investigates the development of self-healing injectable hydrogels based on alginate dialdehyde (ADA) and carbohydrazide-modified gelatin (Gel-CDH). The system is designed to support the co-delivery of F-NPs and human amniotic fluid stem cell-derived extracellular vesicles (hAFSC-EVs), combining direct reprogramming with paracrine regenerative cues. The proposed approach was validated using a five-channel microfluidic Heart-on-Chip (HoC) platform incorporating human cardiac fibroblasts, engineered to recapitulate tissue-hydrogel interactions and enable localized, sustained release, ultimately promoting cardiac tissue regeneration.

Materials and Methods

ADA was synthesized via sodium alginate oxidation using sodium metaperiodate and characterized by ATR-FTIR and 13C MAS NMR analyses. Gel-CDH was produced via carbodiimide chemistry and its degree of functionalization was assessed using the 2,4,6-Trinitrobenzene Sulfonic Acid (TNBS) assay. ADA-Gel-CDH hydrogels were prepared by varying the polymer weight ratios (%w/w) (from 70:30 to 30:70, ADA:Gel-CDH) while maintaining constant the final polymer concentration (%w/v) and were characterized through rheological and in vitro stability tests. Extracellular vesicles (hAFSC-EVs) were isolated from human amniotic fluid stem cell. F-NPs, with miRcombo, negative microRNA control (negmiR) or siRNA-Cy5, were formulated based on a patented composition and functionalized on their surface using a CF-specific antibody via click-chemistry reaction. Adult human cardiac fibroblasts (AHCFs) were plated in the second and fourth channels of HoC platform in a fibrin-based matrix. The next day, ADA-Gel-CDH hydrogel loaded with F-NPs was injected in the central third channel adjacent to cells. Culture was continued up to 14 days.

Results

ADA-Gel-CDH hydrogel was developed, showing good biocompatibility, stability and the ability to provide controlled release of both hAFSC-EVs and miRNA-loaded F-NPs. The hydrogel enabled sustained delivery, with about 60% of hAFSC-EVs released within 48 hours and complete miRNA release delayed up to about 14 days when nanoparticles were embedded in the matrix. Within this HoC platform, the hydrogel successfully delivered nanoparticles to embedded cells and preliminary in vitro validation showed that EVs and F-NPs/miRcombo reduced fibrosis-associated ECM markers.

Conclusion

Co-delivery of hAFS-EVs and F-NPs is still under investigation to enhance reprogramming efficiency. Overall, this platform represents a promising biomimetic strategy for localized, sustained delivery of combinatorial therapeutics, with potential to improve cardiac regeneration after myocardial infarction.

Acknowledgements

The authors would like to thank the ERC under EU H2020 research and innovation program (BIORECAR; 772168); DESIRE project (CUP E53D23003950006)– funded by European Union – Next Generation EU within the PRIN 2022 program (D.D. 104 - 02/02/2022 Ministero dell'Università e della Ricerca); RECOVERY project (CUP E53D23017470001)– funded by European Union – Next Generation EU within the PRIN 2022 PNRR program (D.D.1409-14/09/2022 Ministero dell'Università e della Ricerca) and INJECTHEAL project funded by the European Union, through the Horizon Europe research and innovation programme (Grant Agreement no. 101177924).

D3 – P177

One-step fabrication of organ-on-chip platforms to screen hydrogel therapeutics

Monteiro M.V.[1,2], Pequeno C.[1,2], Machado A.B.[1,2], Mano J.F.[1,2], Gaspar V.M.[1,2]
[1]CellularisBiomodels, Pci Creative Science Park Aveiro Region, Ílhavo; [2]Dept. of Chemistry, CICECO - Aveiro Institute of Materials, University of Aveiro, Campus Universitário de Santiago, Portugal

Introduction

Organ-on-chip systems have emerged as advanced *in vitro* platforms capable of recapitulating key physiological features of human tissues, including dynamic flow conditions and tissue-material interactions. However, their widespread implementation is still constrained by fabrication workflows that commonly rely on micromolding techniques, which are time-consuming, labor-intensive, and limited in scalability. In parallel, there is an increasing need for robust platforms to screen biomaterial-based therapeutics, particularly hydrogels and nanoparticle systems, under physiologically relevant conditions. In this context, additive manufacturing technologies, such as stereolithography (SLA), offer a promising alternative for the rapid and reproducible fabrication of microfluidic devices.

Aim

This work aims to develop a transparent, SLA-fabricated microfluidic platform for the dynamic screening of hydrogel therapeutics and nanoparticle-based systems, enabling the evaluation of biomaterial adhesion, penetration and performance in tissue-like environments.

Materials and Methods

Microfluidic chips were designed using SolidWorks and fabricated using an ELEGOO Saturn 16K SLA printer and Liqcreate Bio-Med Clear resin, enabling high-resolution features and optical transparency. The fabrication workflow was optimized to reduce production time while ensuring structural fidelity and reproducibility. The resulting chips were engineered to support the incorporation of tissue-mimetic constructs (up to 6 mm) within the microfluidic well. Dynamic flow conditions were established to simulate physiologically relevant environments, with flow rates systematically evaluated in the range of 1-30 µL/min. The platform was used to assess the interaction between biomaterials, ranging from nanoparticle formulations to hydrogel systems, and biological substrates, with particular emphasis on hydrogel adhesion under flow.

Results

SLA fabrication enabled rapid prototyping of microfluidic chips with high geometrical accuracy and reproducibility, significantly reducing fabrication time compared to conventional micromolding approaches (Figure 1). The use of a transparent biocompatible resin allowed real-time visualization of biomaterial behavior within the chip. The platform successfully supported the integration of tissue-like constructs and the establishment of controlled dynamic flow conditions.




Figure 1. (A) Computer-aided design (CAD) of the microfluidic chip featuring a single central cell culture well. (B) Representative image of the SLA-printed chip under fluid flow, using a blue food dye to demonstrate channel integrity and absence of leakage. (C) Adapted chip design incorporating five independent wells, each one with a dedicated inlet and outlet, enabling parallel analysis of multiple tissue models within the same platform. (D) Fluorescence image of 3D tissue models. Red Channel: Phalloidin filaments, Blue channel: nucleus.

Conclusion

This study demonstrates that SLA-based fabrication is a robust and scalable strategy to produce organ-on-chip platforms. The developed system provides a versatile tool for the dynamic screening of biomaterials, bridging the gap between static *in vitro* assays and physiologically relevant testing conditions. This approach has strong potential to accelerate the development and optimization of hydrogel therapeutics and nanoparticle-based delivery systems.

Acknowledgements

This work is supported by the Horizon Europe EIC Pathfinder Open project NatProLub (Grant Agreement No. 101130633).

D3 – P178

Immunocompatibility of self-assembling peptide hydrogels as biomaterial platforms for vaccine delivery

Djumaev A.I.[1], Shivkumar M.[1], Mansour O.T.[1], Tashmukhamedova S.h.S.[2], Cordeiro A.S.[3], Elsawy M.A.[4]
[1]Leicester Institute for Pharmaceutical Innovation, Leicester School of Pharmacy, De Montfort University, UK; [2]Faculty of Biology, National University of Uzbekistan, Tashkent, Uzbekistan; [3]Strathclyde Institute of Pharmacy and Biomedical Sciences University of Strathclyde, Glasgow, UK; [4]Division of Pharmacy and Optometry, School of Health Sciences, University of Manchester, UK

Introduction

Self-assembling peptide hydrogels are increasingly explored as biomaterials for drug and vaccine delivery due to their tunable nanostructure, injectability, and inherent biocompatibility[1,2]. In subunit vaccine systems, biomaterial carriers are expected to stabilise protein antigens while maintaining favourable interactions with immune cells. Therefore, evaluating the immunocompatibility of peptide hydrogels is an important step in their development as biomaterial platforms for vaccine delivery. In this study, our ultra-short β-sheet forming peptide hydrogels were investigated as potential matrices for the incorporation of protein-based subunit antigens, with emphasis on their physicochemical properties and preliminary immunocompatibility[3,4].

Materials and Methods

Our previously reported short self-assembling peptide UICP8 was investigated as a hydrogel vehicle for SARS-CoV-2 Spike protein subunit vaccine[3]. Peptide solutions (5–50 mg/mL) were prepared in HPLC-grade water, and pH was adjusted to 7.2–7.4 using 0.5 M NaOH to induce self-assembly. Samples were stored overnight at 4 °C to allow hydrogel formation. Gelation behaviour and critical gel concentration (CGC) were assessed using the inverted vial test. Peptide secondary structure was analysed by ATR-FTIR spectroscopy, while rheological measurements were performed to evaluate thixotropic behaviour and structural recovery. Preliminary immunocompatibility was assessed using a 24-hour in vitro cytotoxicity assay on THP-1 human monocytic cells.

Results

Peptide formulations demonstrated concentration-dependent hydrogel formation, with the inverted vial test indicating a critical gel concentration (CGC) of approximately 20 mg/mL, as samples below this concentration did not form self-supporting gels. ATR-FTIR analysis revealed β-sheet secondary structure characteristic of self-assembled peptide nanofiber networks, with β-sheet-associated peaks becoming more pronounced at concentrations ≥20 mg/mL. Rheological analysis demonstrated pronounced thixotropic behaviour, with structural recovery of at least 80% following shear stress. Preliminary cytotoxicity studies indicated favourable THP-1 cell viability after 24-hour exposure to peptide hydrogel formulations.




Figure 1. Characterisation and preliminary biological evaluation of UICP8 self-assembling peptide hydrogels. **(a)** Inverted vial test showing concentration-dependent gel formation of UICP8 peptide solutions (5–50 mg/mL, pH 7.2–7.4). **(b)** ATR-FTIR spectra of peptide hydrogels at different concentrations confirming β-sheet secondary structure associated with peptide self-assembly.

Conclusion

These findings demonstrate favourable physicochemical properties and baseline immunocompatibility of the investigated peptide hydrogel, supporting its potential as a biomaterial platform for subunit vaccine delivery. Ongoing studies aim to further evaluate immune cell responses to peptide hydrogel–antigen formulations.

Acknowledgements

This work was supported by the DMU Research Student Scholarship from the De Montfort University Doctoral College.

References

[1]Cordeiro A.S., Patil-Sen Y., Shivkumar M., Patel R., Khedr A., Elsawy M.A. Nanovaccine delivery approaches and advanced delivery systems for the prevention of viral infections: from development to clinical application. *Pharmaceutics* 2021; *13*(12); 2091.

[2]Abdullah T., Bhatt K., Eggermont L.J., O'Hare N., Memic A., Bencherif S.A. Supramolecular self-assembled peptide-based vaccines: current state and future perspectives. *Frontiers in Chemistry* 2020; 8; 598160.

[3]Soliman M.A., Khedr A., Sahota T., Armitage R., Allan R., Laird K., Allcock N., Ghuloum F.I., Amer M.H., Alazragi R., Edwards-Gayle C.J. Unraveling the Atomistic Mechanism of Electrostatic Lateral Association of Peptide β-Sheet Structures and Its Role in Nanofiber Growth and Hydrogelation. *Small* 2025; *21*(6); 2408213.

[4]Khedr A., Soliman M.A., Corrigan A., Sahota T., Armitage R., Allcock N., Jegadeesan J.T., Amer M.H., Alazragi R., Ahmad Z., Wychowaniec J.K. Charge Directed Selective Co-Assembly of Ionic Complementary Peptide Binary Mixtures. *Small* 2026; e13140.

D3 – P179

Particle swelling impacts the biophysical properties of hyaluronic acid-based microporous annealed particle hydrogels

Konecna M.[1], McGrath M.[1], O'Brien F.J.[1], Browne S.[1,2,3]
[1]Tissue Engineering Research Group, Dept. of Anatomy and Regenerative Medicine, Royal College of Surgeons in Ireland, Dublin, Ireland; [2]CÚRAM, Centre for Research in Medical Devices, University of Galway, Ireland; [3]Trinity Centre for Biomedical Engineering (TCBE), Trinity College Dublin, Ireland

Introduction

According to the World Health Organisation 64 million people in Europe are affected by diabetes, many of whom suffer from chronic wounds with impaired wound healing and insufficient vascularization playing a key role. Biomaterials derived from native biopolymers offer a promising therapeutic option. Hyaluronic acid (HyA)-based hydrogels stand out owing to biocompatibility, biodegradability and ease of modification. However, bulk hydrogels lack sufficient porosity to support cell infiltration and vascularisation. To introduce porosity, we propose hydrogels composed of microporous annealed particles (MAP) formed from particles of fragmented hydrogels. This study aims to develop a highly porous HyA-based MAP hydrogel and assess the impact of particle swelling on hydrogel properties, and ultimately cell infiltration and behaviour.

Materials and Methods

HyA was modified with acrylate groups (AcHyA) and the degree of acrylation verified using H^1 NMR. Bulk AcHyA hydrogels were formed using a PEG-dithiol crosslinker and fragmented mechanically using needles in descending order of size from 18G to 27G controlling the swelling of the particles during the fragmentation from highly to low swelled. These particles were UV-crosslinked to form MAP hydrogels with lithium phenyl-2,4,6-trimethylbenzoylphosphinate (LAP) as photo-initiator. Biophysical characterization of MAP hydrogels includes degradation and compressive modulus. To assess cell infiltration and proliferation, endothelial cells were encapsulated inside MAP hydrogels and the nuclei and actin cytoskeleton stained.

Results

NMR confirmed successful acrylation of HyA (~31%) which facilitated formation of stable HyA-based hydrogels. HyA hydrogel particles were successfully fabricated *via* mechanical fragmentation, with average size of 250 μm (Figure 1A). Crosslinking of these particles formed MAP hydrogels with similar mechanical properties. Measurement of Young's modulus shows MAP hydrogels were significantly softer compared to bulk hydrogels regardless of particle swelling (Figure 1B). However, enzymatic degradation revealed that controlling the swelling of particles during fragmentation affects degradation time, with least-swelled groups degrading significantly slower (Figure 1C). There was no observable difference in cell spreading and proliferation (Figure 2) in MAP hydrogels compared to bulk hydrogels.

Conclusion

Porosity was introduced to an AcHyA hydrogel system using a MAP approach which was used to form stable and porous hydrogels suitable for cellular infiltration. Increasing swelling of particles during hydrogel fragmentation impacted the stability and accelerated enzymatic degradation of porous hydrogels. While minimal cell spreading was observed, porous HyA-based hydrogels will be functionalised with ECM moieties and other pro-angiogenic stimuli to support cell spreading and ultimately vascularisation.

Acknowledgments

This project is funded by the Health Research Board (ILP-POR-2024-023)




Figure 1. Biophysical characterization of MAP hydrogels made from 500 kDa AcHyA 3% and PEG-dithiol. A) Fragmented hydrogel particles visualised with TRITC-dextran (particles are represented by dark regions). Scale bar = 200 µm. **B)** Hyaluronidase-mediated degradation of HyA MAP hydrogels. **C)** Young's modulus of HyA MAP hydrogels. * indicates $p<0.05$. n=3




Figure 2. Endothelial cells encapsulated in Bulk and MAP hydrogels made from 500 kDa AcHyA 3% crosslinked with LAP (MAP hydrogels) or PEG-dithiol (Bulk hydrogel) cultured for 7 days. A) Bulk AcHyA hydrogel control. **B)** 1.5xPBS MAP hydrogel. **C)** Mixed 1.5x and 3xPBS MAP hydrogel. **D)** 3xPBS MAP hydrogel. Scale bar = 50 µm.

D3 – P180
From particles to immune niches: Engineering regeneration

Segura T.[1,2]
[1]Duke University, Dept. of Biomedical Engineering, Durham, USA

Particulate biomaterials offer a powerful framework for engineering biological function by assembling discrete building blocks into complex microenvironments. In this talk, I will present how particle-based design enables control over both tissue regeneration and immune modulation.
We developed microporous annealed particle (MAP) scaffolds that assemble into injectable, tissue-integrating networks. By incorporating immunogenic cues, these materials form localized immune niches that recruit and activate antigen-specific B cells directly within injured tissue, reprogramming inflammation and promoting regenerative healing.
In parallel, we developed computational tools to quantify how particle packing governs pore architecture, revealing how particle properties define void space, connectivity, and accessibility.
Together, these studies illustrate how particulate building blocks can be used to program immune responses and guide endogenous regeneration through control of material architecture.

Acknowledgements
I like to thank my lab for their hard work and creative science. I also like to thank the USA National Institutes of Health for funding. Part of the work presented in this keynote presentation is a collaboration with Joel Collier and lead by a co-mentored student Pablo Cordero.

D3 – P181

Coating of wound dressings with the biomimetic biomaterial PhenoDrive-U: Physicochemical and biocompatibility properties

Shirin S., Nadia T., Dipak S., Susan S., Matteo S.
Centre for Regenerative Medicine and Devices, School of Applied Sciences, University of Brighton, UK

Introduction

Wound dressings are the primary treatment modality for wound healing. They are provided either as tulle-based devices to protect the wound from mechanical insults or as hydrocolloids in those cases where wounds present excessive volumes of exudates. In many cases, they are used in combination whereby the tulle-based devices are applied as primary dressings and the hydrocolloids are added as secondary to control exudate volumes. Despite the availability of many formulations. The present study aims to enhance the physicochemical and biocompatibility properties of two distinct primary wound dressings: Atrauman (tulle-based synthetic polymer coated by triglycerides to make it non-adhesive to wound material), N-A (tulle-/cellulose-based) and Kaltostat (alginate hydrocolloid) by the application of a biomimetic biomaterial Phenodrive-U (PD-U), a poly-L-Lysine biomaterial presenting betaine at high density, as a coating.

Materials and Methods

PD-U freeze-dried powder (1mg) was dissolved in 10 ml of 75%/25% v/v ethanol/water. Sterile Atrauman, N-A, and Kaltostat were cut into 1 cm × 1 cm samples and transferred to the 24-well plate. PD-U solution (200 µl) was added to each well and cast coating was obtained by evaporation of the solution overnight, at room temperature in a sterile laminar flow cabinet. Control and coated samples were analysed by scanning electron microscopy (SEM), swelling, water content evaporation, and body mass degradation over 48 hours. The effect of the coating on the non-adherent U937 monocyte cell line was assessed over 48 hours by evaluating the cells' ability to differentiate into adherent macrophages through morphological analysis as well as their polarization into either M1 (iNOS+) or M2 (CD206+) macrophages by immunostaining.

Results and Discussion

SEM demonstrated the deposition of the PD-U coating on the fibres of all dressings and throughout their cross section (Figure 1). However, in the case of Atrauman, the coating was not uniform due to the removal of the triglyceride layer by the ethanol/water solution in which PD-U was dissolved. The swelling rate of the PD-U-coated dressing did not exhibit any significant difference compared to the control, but the water-loss tests showed that Kaltostat water loss was significantly reduced ($p < 0.05$). Furthermore, the PD-U coating significantly decreased ($p < 0.001$) both the adhesion of inflammatory cells and their polarization into M1 and M2 phenotypes .

Conclusion

Coating N-A with PD-U can reduce inflammation; however, it does not affect the dressing's physicochemical properties. The most optimal dressing to enhance physicochemical and biocompatibility properties is Kaltostat coated with PD-U.

Acknowledgements

The work was supported by the UKRI Engineering and Physical Sciences Research Council, contract n. EP/WO23164/1.




Figure 1: SEM pictures from 3 different tips of wound dressings (Atrauman, N-A and Kaltostat) coated with PD-U and Non-coated

D3 – P182

Nanostructured bacterial cellulose membranes as carriers for antibiotic-loaded chitosan nanoparticles in wound infection control

Livrinska Trpeska L.[1], Petrushevska M.[1], Geskovski N.[1], Simonoska Crcarevska M.[1], Djurdjic B.[2], Vuksanovich V.[2], Jančič U.[3], Gorgieva S.[3]
[1]Institute of Pharmaceutical Technology and Center of Pharmaceutical Nanotechnology, Faculty of Pharmacy, Ss. Cyril & Methodius University in Skopje, North Macedonia; [2]Center for Medical Microbiology, Institute of Public Health, Podgorica, Montenegro; [3]Faculty of Mechanical Engineering, University of Maribor, Slovenia

Introduction

Bacterial nanocellulose (BNC) has emerged as a highly attractive biomaterial for advanced wound care due to its exceptional purity, high water retention, mechanical robustness and biocompatibility[1,2]. Its 3D nanofibrillar network enables incorporation of functional additives such as antimicrobial agents, nanoparticles and bioactive molecules. These properties make BNC particularly suitable as a platform for localized drug delivery systems aimed at preventing wound infections while maintaining a moist healing environment.

Aim

To overcome the limitations of systemic antibiotic administration, such as toxicity and poor localization, we develop a bioactive dressing utilizing BNC impregnated with gentamicin-loaded chitosan nanoparticles.

Materials and Methods

Chitosan nanoparticles containing the aminoglycoside antibiotic gentamicin were produced using ionic crosslinking with sodium tripolyphosphate. Process parameters were optimized to obtain stable nanoscale particles with narrow size distribution. The nanoparticle suspensions were subsequently introduced into hydrated BNC membranes to create a composite. Structural and physicochemical characterization was performed using Fourier transform infrared spectroscopy, X-ray diffraction and scanning electron microscopy. Biological performance was evaluated through antibacterial testing against *Klebsiella pneumoniae* and cytocompatibility assays with fibroblast BJ cells.

Results

The optimized nanoparticle formulation produced nanoscale particles with good colloidal stability. SEM observations demonstrated that the BNC retained its interconnected nanofibrillar architecture after incorporation of the nanoparticles. The particles were distributed throughout the cellulose network without visible aggregation, indicating successful loading of the active system within the membrane. The composite dressing exhibited clear antibacterial activity against the tested pathogen while maintaining acceptable cell viability and adhesion in fibroblast cultures[3].




Figure 1. SEM micrographs of fibroblast BJ cells attachment and morphology on BNC, nanocellulose impregnated with varying concentrations of gentamicin sulfate solution (BNC-GS-Sol), nanocellulose impregnated with empty nanoparticles (BNC-NP) and with gentamicin-loaded nanoparticles (BNC-GNP) at three different concentrations (ranging from 5 to 15 µg/disk) and magnification of (**A**) 1000× (scale bar = 20 µm), (**B**) 5000× (scale bar = 2 µm) and (**C**) 25,000× (scale bar = 1 µm)

Conclusion

The developed BNC disks impregnated with gentamicin-loaded chitosan nanoparticles showed suitable physicochemical properties, strong antibacterial activity against *Klebsiella pneumoniae*, and good biocompatibility, highlighting their promise as multifunctional wound dressings. Importantly, nanoparticle

incorporation did not compromise the structural integrity of the bacterial nanocellulose matrix, preserving its favorable properties for cell attachment and proliferation. Although the results demonstrate strong potential for localized treatment of surgical-site infections and improved wound healing, further studies—including broader antimicrobial testing and in vivo validation—are required to confirm safety, efficacy, and clinical applicability.

Acknowledgements
The financial support of EU through NABIHEAL project (n°101092269), Slovenian Research and Innovation Agency, ARIS (P-0118 and N2-0388).

References
[1]Jančič U. et al. Bacterial nanocellulose loaded with bromelain and nisin as a promising bioactive material for wound debridement. *International Journal of Biological Macromolecules* 2024; 266; 1-20.
[2]Jančič U., et.al. Bioactive bacterial nanocellulose membranes for non-surgical debridement and infection prevention in burn wound healing. *Carbohydrate Polymer Technologies and Applications* 2025; 10; 1-20.
[3]Livrinska Trpeska L et.al. Bacterial Nanocellulose Wound Dressings with Gentamicin-Loaded Chitosan Nanoparticles for Surgical Site Infection Management. *Polymers* 2026; 18; 510.

D3 – P183

The Safe-and-Sustainable-by-Design approach for alternative metal-free wound dressings in NABIHEAL

Garcia D., Falk A., Scheper J.K.
BioNanoNet Forschungsgesellschaft mbH (BNN), Graz, Austria

Introduction

Chronic wounds are characterized by persistence for more than six weeks despite active intervention and a lack of significant progression towards healing. These problematic wounds affect up to 2% of the population in industrialized countries, with increasing prevalence due to aging demographics. Chronic wounds not only significantly impact patients' quality of life but also place a considerable burden on healthcare systems, accounting for up to 4% of the total healthcare budget in Europe. A major clinical concern associated with non-healing wounds is the high risk of microbial infection. Current standard-of-care treatments rely heavily on silver-based antimicrobial agents; however, these approaches often show heterogeneous clinical outcomes and raise concerns regarding cost, environmental impact, and long-term sustainability.

Materials and Methods

To address these limitations, the NABIHEAL project aims to develop alternative metal-free biomaterials for advanced wound dressings with enhanced antimicrobial activity and improved wound healing properties. The project integrates a Safe-and-Sustainable-by-Design (SSbD) approach to ensure that newly developed nano-based multicomponent materials minimize risks to human health and the environment. The assessment follows the SSbD framework published update from 2025 by the Joint Research Centre of the European Commission (JRC-EC). Within this framework, BNN contributes expertise in advanced materials and biomedical applications. A structured and tiered evaluation process has been implemented, including questionnaires and on-site visits to production sites, to collect relevant information and assess the current status of the materials development during the project.

Results

Initial evaluations provided a comprehensive overview of the materials and production processes currently under development within the NABIHEAL project. The collected data enabled preliminary safety and sustainability assessments and highlighted areas requiring further optimization. Following each evaluation round, risk assessments are performed and targeted recommendations are provided to project partners to support improvements in safety, environmental performance, and regulatory readiness. This iterative process allows continuous monitoring of the development stages while guiding the innovation process toward safer and more sustainable material design.

Conclusion

The implementation of a Safe-and-Sustainable-by-Design strategy within the NABIHEAL project supports the development of innovative metal-free wound dressings while addressing potential safety and environmental concerns early in the research and development process. This proactive and iterative approach not only strengthens the sustainability and safety profile of the developed materials but also contributes to reducing the healthcare burden associated with chronic wounds.

Acknowledgements

This project has received funding from the European Union's Horizon Europe research and innovation programme under grant agreement n°101092269.

D3 – P184

Optical coherence tomography characterization of bacterial cellulose films

Gutiérrez J.A.[1,2], Ekselenski S.[4], Gorgieva S.[4], Conde O.M.[1,2,3]
[1]Photonics Eng. Group, University of Cantabria, Santander, Spain; [2]CIBER-BBN, Madrid, Spain; [3]IDIVAL, Santander, Spain; [4]Faculty of Mechanical Engineering, University of Maribor, Slovenia

Introduction

Bacterial cellulose (BC) is a nanofibrillar biomaterial produced by specific types of bacteria at the air-culture medium interface, in a form of highly hydrated three-dimensional network [1]. Its purity, biocompatibility, and mechanical strength make it attractive for biomedical applications. Optical Coherence Tomography (OCT) [2] enables high-resolution, label-free, non-destructive imaging, allowing visualization of BC internal structure estimating its optical properties [3].

Aim

The aim of this work is to evaluate the feasibility of using OCT to characterize BC membranes and to assess their internal structure and optical properties, such as the attenuation coefficient.

Materials and Methods

Up to 5 BC-based membranes with different composition/processing background have been produced for this feasibility study: (1) membrane from modified-molasses medium; membrane casted from BC dispersion in (2) Milly-Q water and (3) carboxymethyl cellulose (CMC); and membrane casted from BC molasses dispersion in (4) Milly-Q water and (5) CMC. OCT measurements (TEL221PS, Thorlabs, USA) were performed at 1300 nm (5.5/13 µm axial/lateral resolution). OCT images reveal the internal structure of the membranes. The attenuation coefficient was calculated [3] from the depth-resolved OCT signal by calibrating the backscattered intensity with a reference scattering phantom.

Results

The morphology of BC membranes can be manipulated by different post-processing routes, such as dispersion casting. Addition of non-BC components further affect the morphology and the overall physicochemical and mechanical behaviour of the material. BC morphology is usually analyzed by electron microscopy, which requires preparation steps that can alter the sample's native state. Figure 1 demonstrate the potential of OCT as a non-destructive tool for characterizing BC biomaterials (a-b). Depth sections of BC samples (c) show different morphological BC behaviour and their associated attenuation maps (d) correlate with the dispersive and scattering properties of each biomaterial.

Conclusion

The results demonstrate the potential of OCT as a non-destructive tool for characterizing BC biomaterials, enabling visualization of internal structures and providing quantitative information on optical attenuation related to cellulose nanofiber organization, which may support quality assessment and optimization of BC-based materials.

Acknowledgements

EU project NABIHEAL (GA No. 101092269), PID2022-137269OB-C22 (PERFORMANCE, MICIU/AEI/10.13039/ 501100011033, FEDER, UE), EU project FABULOSE (GA No. 101214009), ARIS (N2-0388, P2-0118).




Figure 1: OCT structural images of BC samples: (a) BC samples; (b) white-light imaging of BC samples regions; (c) depth sections of BC samples; (d) end face attenuation coefficient maps of BC samples.

References

[1]Gorgieva S. Bacterial cellulose as a versatile platform for research and development of biomedical materials. *Processes* 2020; 8; 1-26.
[2]Maestro D., Palanca A., Soto H. et al. CTPR390 prevents structural and functional remodeling in engineered cardiac connective tissues by inhibiting fibrosis. *iScience* 2025; 28; 113013.
[3]Mieites V., Ghosh S., Gutiérrez-Gutiérrez J.A., Fanarraga M.L., Conde O.M. Melanoma fixation for OCT imaging: How long is too long? *Proceedings of SPIE* 2025; 13351; 133510F.

D3 – P185
L-phenylalanine based biocatalytic material for rapid wound healing applications

Singh A., Mukherjee S.
School of Biomedical Engineering, IIT-BHU, Varanasi, Uttar Pradesh, India




Figure.1 Oxygen generation due to catalysis of H_2O_2 relieving hypoxia thereby promoting faster wound healing
Wound healing is a complicated response to tissue injury that involves multiple cell types, cytokines, growth factors, and the vascular system. The healing process progresses through four phases: haemostasis, inflammation, proliferation, and remodelling. Under normal conditions, these steps occur in a controlled way, ensuring quick tissue repair and restoration of skin integrity. However, certain conditions, such as diabetes, significantly delay this process. Chronic diabetic wounds can last for several weeks to months due to ongoing low oxygen levels, excessive reactive oxygen species (ROS), poor blood flow, and long-lasting inflammation. These factors slow down tissue regeneration and increase the risk of infection and tissue death. This makes finding effective treatments for diabetic wounds a major challenge. However, chronic wounds often develop hypoxic condition because of poor blood circulation. Therefore, materials that can generate oxygen *in situ* can greatly improve healing.

In this study, we created a new L-phenylalanine-based material containing manganese (Mn-F) designed to generate therapeutic levels of oxygen (O_2) in the wound area. It takes advantage of manganese's ability to catalyse hydrogen peroxide (H_2O_2) found in inflamed tissues to produce oxygen. This process increases oxygen levels in the tissue. Additionally, also helps reduce oxidative stress at the wound site.




Figure.2 Release of O_2 and amelioration of ROS in wounded tissue to accelerate wound healing
We conducted in vitro tests to evaluate the antioxidant and ROS-scavenging abilities of Mn-F. The findings showed that it considerably lowered levels of intracellular reactive oxygen species, proving its strong antioxidant properties. The conversion of hydrogen peroxide into oxygen helped maintain a balance of reactive and non-reactive substances in the cells. This double action of reducing ROS and generating oxygen creates an environment that supports cell growth and tissue repair.

We also tested its effectiveness in vivo using normal and chronic diabetic wound models in Wistar rats. In the normal wound model, the catalytic material led to quick wound closure in just 7 days, showing faster tissue regeneration than untreated controls. More importantly, in the chronic diabetic wound model the material significantly enhancing healing, achieving closure within 11 days. These results suggest that this oxygen-generating system effectively relieves the oxygen deficiency common in diabetic wounds.

Overall, this study highlights the potential of Mn-F for improving wound healing. By combining catalytic efficiency with antioxidant effects, this system offers functional and mechanistic benefits. Notably, the biomaterial showed much higher and longer-lasting antioxidant capacity compared to common treatments. This therapeutic approach decreases oxidative stress and also promotes blood vessel growth, cell growth, and tissue repair. As a result, this catalytic material appears to be a promising material for better wound care and may provide a superior method for treating chronic diabetic wounds and other conditions related to low oxygen levels.

D3 – P186

Lysozyme amyloid nanofibril-reinforced carrageenan–CMC bioinks for high-fidelity 3D bioprinting of living wound healing patches

Teixeira M.C.[1], Carvalho J.P.F.[1], Lameirinhas N.S.[1], Luís J.[2], Oliveira H.[3], Oliveira J.M.[2], Silvestre A.J.D.[1], Vilela C.[1], Freire C.S.R.[1]

[1]CICECO - Aveiro Institute of Materials, Dept. of Chemistry, University of Aveiro; [2]CICECO – Aveiro Institute of Materials, EMaRT Group, University of Aveiro, Oliveira de Azeméis; [3]Dept. of Biology & CESAM, University of Aveiro, Portugal

Introduction

Severe skin injuries remain a major clinical challenge due to infection risk, delayed healing and impaired tissue regeneration. Recent advances in extrusion-based 3D bioprinting allow the fabrication of personalized, cell-laden constructs that mimic the architecture of native tissues. Natural polymer hydrogels are promising bioink matrices due to their biocompatibility and ability to support cellular activity; however, many still lack optimal printability and mechanical stability for high-fidelity bioprinting. Here, lysozyme amyloid nanofibrils (LNFs) are explored as multifunctional nano-reinforcing agents to simultaneously enhance bioink printability, mechanical performance and biological functionality.

Aim

This study aimed to develop a multifunctional polysaccharide-based hydrogel bioink reinforced with LNFs for high-fidelity extrusion 3D bioprinting of keratinocyte-laden living wound healing patches (Figure 1).

Materials and Methods

Hydrogel bioinks were prepared from a carrageenan–carboxymethyl cellulose (Crg–CMC) matrix reinforced with LNFs (5, 10 and 15 wt.% relative to the polymer content). Rheological behavior, printability, mechanical properties, porosity, degradation and cytocompatibility were evaluated. The optimal formulation was loaded with human keratinocytes (HaCaT, 3×10^6 cells mL^{-1}) and dexpanthenol (Dex, 5 wt.%) as a therapeutic agent. Cell-laden constructs were fabricated using extrusion-based 3D bioprinting and cultured for up to 21 days. Cell viability was assessed using LIVE/DEAD assays and fluorescence microscopy.

Results

The incorporation of LNFs significantly improved the rheological performance of the Crg–CMC bioinks, reducing gelation temperature to ~31 °C and enabling extrusion printing under physiological conditions. LNFs enhanced printing fidelity, yielding constructs with high shape accuracy and printability values close to 0.9. The resulting hydrogels exhibited suitable porosity and mechanical strength (~360–500 kPa), within the physiological range of native skin tissue. The optimized Crg–CMC–LNFs (10%) bioink supported long-term keratinocyte survival, with cell viability exceeding 91% after 21 days. The presence of Dex did not compromise cell viability while providing additional therapeutic potential.

Conclusion

The developed Crg–CMC–LNFs nanocomposite bioink exhibited excellent rheological, mechanical and biological performance for extrusion-based 3D bioprinting. LNFs significantly enhanced printability and structural stability while maintaining high keratinocyte viability. These findings demonstrated the potential of LNF-reinforced polysaccharide bioinks as a promising platform for the fabrication of living wound healing patches and next-generation skin tissue engineering constructs.

Acknowledgements

This work was developed within the scope of the projects CICECO – Aveiro Institute of Materials, UID/50011/2025 (DOI 10.54499/UID/50011/2025) & LA/P/0006/2020 (DOI 10.54499/LA/P/0006/2020), and CESAM (UID/50006 & LA/P/0094/2020 (doi.org/10.54499/LA/P/0094/2020)), financed by national funds through the FCT/MCTES (PIDDAC), and financially supported by the project I&D “NANOBIOINKS-Engineering bio-based nanofibers for the development of high-performance nanostructured bioinks for 3-D bioprinting, CENTRO-01-0145-FEDER-031289” funded by the Operational Program of the Center Region, in its FEDER/FNR component, and by national funds (OE), through FCT/MCTES

D3 – P187
Antibiotic-loaded bioactive glass systems for enhanced wound healing

Soriente A.[1], Zuppardi F.[1], Bigham A.[1], Mariano A.[1], Liguori F.[1], Martino S.[1], Ambrosio L.[1], Logoyda L.[2], Raucci M.G.[1]
[1]Institute of Polymers, Composites and Biomaterials, National Research Council of Italy (IPCB-CNR), Naples, Italy; [2]I. Horbachevsky Ternopil National Medical University, Ternopil, Ukraine

Introduction
Mesoporous bioactive glasses (MBGs) are promising platforms for wound healing due to their high surface area, tunable porosity, and ability to promote tissue regeneration. Their mesoporous structure enables efficient loading and controlled release of antibiotics, addressing infections in acute and chronic wounds. In addition, MBGs can modulate cellular responses and support tissue repair. In this context, antibiotic-loaded MBG systems were developed to evaluate drug delivery performance and their effects on fibroblast viability and inflammatory response.

Materials and Methods
Mesoporous bioactive glass (MBG) was synthesized via evaporation-induced self-assembly (EISA) using Pluronic F127 as a template, followed by the addition of TEOS, TEP, and $Ca(NO_3)_2 \cdot 4H_2O$. The resulting sol was cast, dried at 40 °C, and calcined at 700 °C for 5 h. MBG was subsequently loaded with levofloxacin (LEVO) or minocycline (MNC) by incubation in organic or aqueous solutions for 24 h, followed by filtration, washing, and drying. Drug loading and release were analyzed by HPLC, and release kinetics were evaluated using Higuchi and Korsmeyer–Peppas models. In vitro biological response was assessed on human dermal fibroblasts by evaluating cell viability, proliferation, and inflammatory modulation.

Results
TEM analysis revealed that MBG particles form agglomerated clusters while maintaining a well-defined mesoporous structure. Low-angle XRD showed a sharp peak indicative of an ordered mesoporous architecture with cubic symmetry, while wide-angle XRD confirmed the amorphous nature of the glass.
Drug release studies demonstrated distinct behaviors for the loaded systems. BG-LEV exhibited the highest release (77.1%, loading 13.7%), with an initial burst (~20% within the first hours) followed by a plateau phase, attributed to surface-adsorbed drug release kinetic. In contrast, BG-MIN samples showed a slower and sustained release, extending up to 22 days.
Biological evaluation on human dermal fibroblasts demonstrated concentration- and time-dependent effects. At low concentrations (≤50 μg/mL), both unloaded and loaded MBG maintained cell viability and normal morphology, while higher concentrations led to reduced viability. Moreover, MBG significantly decreased nitric oxide production under both basal and inflammatory conditions, indicating anti-inflammatory potential. These findings identify a therapeutic window combining cytocompatibility and controlled drug delivery.

Conclusions
MBG systems exhibit a well-defined mesoporous structure that enables efficient antibiotic loading and tunable release profiles. Levofloxacin-loaded MBG provides rapid release, while minocycline ensures sustained delivery. Additionally, MBG demonstrates cytocompatibility and immunomodulatory effects, supporting its potential as a multifunctional platform for wound healing applications.

Acknowledgements
This study was sponsored by the NATO Science for Peace and Security Programme under grant id. SPS.MYPG6031 - Wearable smart patches for multimodal wound healing – DRESWOUTRE. CUP: B63C23001400005.

D3 – P188

A novel hyaluronic acid–based matrix containing sulphated GAGs and collagen as an active ingredient for wound healing

Gálvez-Martín P.[1], Marchal J.A.[2], Martínez-Puig D.[1], Velasco J.[1]
[1]R&D Human Health, Bioibérica S.A.U., Barcelona, Spain; [2]Dept. of Human Anatomy and Embryology, Faculty of Medicine, University of Granada, Spain

Introduction

Wound healing is a complex biological process requiring coordinated cellular proliferation, migration, extracellular matrix (ECM) synthesis, angiogenesis, and tissue remodeling. Disruption of these events can result in delayed healing or chronic wounds, highlighting the need for biomaterials that actively support tissue regeneration. Hyaluronic acid (HA), sulphated glycosaminoglycans (GAGs) such as chondroitin sulfate (CS) and dermatan sulfate (DS), and collagen are key ECM components regulating cell signaling, matrix organization, and vascular development. Their biocompatibility, biodegradability, and biological activity make them attractive for advanced wound care. This study evaluated in vitro the regenerative, wound healing, and angiogenic properties of a HA matrix ingredient containing sulphated GAGs (CS/DS) and collagen of natural origin.

Materials and Methods

Human dermal fibroblasts (HDF) from neonatal foreskin and human umbilical vein endothelial cells (HUVECs) were exposed to the HA matrix ingredient at 0.05, 0.2, and 1 mg/mL. HDF proliferation was measured after 24 and 48 hours using bromodeoxyuridine incorporation quantified by ELISA. Fibroblast migration was assessed at 24 hours with the Oris Cell Migration Assay using calcein labeling. GAG synthesis was analyzed after 48 hours by ELISA. Wound healing capacity was assessed in HDF using an in vitro scratch assay, measuring wound closure after 48 hours. Angiogenic activity was evaluated using HUVECs tube formation on Matrigel, followed by calcein-AM staining, fluorescence imaging, and ImageJ analysis after 24 hours.

Results

The HA matrix ingredient significantly increased HDF proliferation. At 1 mg/mL, proliferation increased 1.81-fold at 24 hours and 4.17-fold at 48 hours versus untreated controls. Fibroblast migration was significantly enhanced at all concentrations, reaching increases of approximately 63% compared to controls. ECM production was stimulated, evidenced by a 77% increase in GAG synthesis at 0.2 mg/mL. The scratch assay showed significant improvement in in vitro wound closure after 48 hours, with healed area increases ranging from approximately 22% to 37% across tested concentrations. Angiogenesis assays demonstrated enhanced endothelial network formation, including increased total network length and modulation of tube-related parameters, indicating pro-angiogenic activity.

Conclusion

This in vitro study demonstrates that a HA matrix ingredient containing sulphated GAGs (CS/DS) and collagen promotes key processes involved in skin regeneration. By enhancing fibroblast proliferation and migration, ECM synthesis, wound closure, and angiogenic responses, this matrix shows strong potential for use as a biomaterial or active ingredient to enhance wound healing and tissue repair. These findings support further development in translational wound care and biomaterial-based therapeutic strategies.

Acknowledgements

This study was supported by Bioiberica SAU, Barcelona, Spain.

References

[1]Pena O.A., Martin P. Cellular and molecular mechanisms of skin wound healing. *Nature Reviews Molecular Cell Biology* 2024; 25; 599-616.
[2]Antoszewska M., Sokolewicz E.M., Baranska-Rybak W. Wide use of hyaluronic acid in the process of wound healing: a rapid review. *Scientia Pharmaceutica* 2024; 92; 23-35.
[3]Pellacani G. et al. Sulfated hyaluronan in dermatology: what's new? Overview of evidence in specific dermatological diseases. *Pharmaceutics* 2025; 17; 1600-1620.
[4]Sen C.K., Friday A., Khanna S., Roy S. Collagen-based products in wound, skin, and health care. *Advances in Wound Care* 2025; 14; 1-18.

D3 – P189

Tuning magnetic nanoparticles for wound healing through ROS modulation

Flavián-Lázaro A.C.[1], Ben-Jeddou K.[1], García-Rubio I.[2], Grazú V. [1,3], Moros M.[1,3]
[1]Dept. de Bio-nano-medicina, Instituto de Nanociencia y Materiales de Aragón (INMA, CSIC-UNIZAR), Zaragoza; [2]Dept. de Física de la Materia Condensada, Instituto de Nanociencia y Materiales de Aragón (INMA, CSIC-UNIZAR), Zaragoza; [3]Centro de Investigación Biomédica en Red de Bioingeniería, Biomateriales y Nanomedicina. (CIBER-BBN), Madrid, Spain

Introduction

Magnetic nanoparticles (MNPs) have been widely used in biomedical applications due to their magnetic properties, biocompatibility and low toxicity. Beyond these, they can also act as nanozymes, exhibiting intrinsic oxidoreductase-like activity arising from Fe^{2+}/Fe^{3+} redox couples at their surface, enabling the catalytic decomposition of hydrogen peroxide (H_2O_2) into reactive oxygen species (ROS) through Fenton-like reactions. While MNPs have been traditionally used to induce high ROS levels for cancer therapy, moderate and controlled ROS production regulate key cellular processes such as proliferation and migration, and signalling pathways involved in wound healing. However, controlling ROS generation remains challenging due to their dual role in cytotoxicity and tissue repair. Strategies explored include tuning MNP size and shape, which determine catalytic surface area, and applying external stimuli such as magnetic hyperthermia, which enhances catalytic rates. However, the role of surface chemistry remains comparatively underexplored. Although the inorganic core governs redox activity, the organic coating can influence catalytic behaviour by modulating surface accessibility, diffusion, and interfacial redox processes.

Aim

To evaluate how different organic surface coatings modulate MNP-mediated ROS production and the resulting biological response in 2D keratinocyte wound healing assay.

Materials and Methods

MNPs were synthesized via thermal decomposition and transferred to aqueous media via different coatings: 3-aminopropyltriethoxysilane (APTES, positively charged), dimercaptosuccinic acid (DMSA) and poly(maleic anhydride-alt-1-octadecene) (PMAO), both negatively charged, PMAO-coated NPs were further functionalized with aminophenyl-β-D-glucopyranoside to promote cell-interaction. MNPs were characterized by TEM, DLS, and zeta potential. Catalytic ROS generation was assessed by electron paramagnetic resonance (EPR). Cellular uptake was assessed in HaCaT cells. Wound healing scratch assays were performed after MNPs internalization to evaluate effects on cell migration.

Results

All MNPs exhibited a similar core morphology (~19 ± 2 nm), consistent with the shared inorganic core. Physicochemical characterization confirmed coating-dependent differences in hydrodynamic size and surface charge, as expected for the different functionalization. ROS measurements revealed coating-dependent catalytic activity, highlighting the influence of surface chemistry on redox behavior. Differences in cellular internalization were also observed depending on the coating. Wound healing assays showed coating-dependent differences in wound closure, with PMAO- and APTES-coated nanoparticles showing faster migration rates.

Conclusion

Surface coating influences ROS generation and cellular behaviour in keratinocytes. These differences highlight the role of surface functionalization in modulating nanozyme activity and associated biological responses, providing a basis for nanotechnology-driven approaches in wound healing.

Acknowledgements

Severo Ochoa funds (CEX2023-001286-S, MICIU/AEI/10.13039/501100011033). PCI2023-143448 funded by MICIU/AEI/10.13039/501100011033 and cofunded by the European Union.

D3 – P190

Harnessing the therapeutic effects of natural zeolite to engineer personalized chronic skin wound treatments

Laurano R.[1], Wiech H.[2], Ciardelli G.[1]
[1]Dept. of Mechanical and Aerospace Engineering, Politecnico di Torino, Italy; [2]AURANICUM holistic health UG, Hamburg, Germany

Introduction

Chronic skin wounds (CSWs) are lesions failing to heal within a physiological time frame due to persistent inflammation and infections, which management still remains a substantial clinical challenge. The pursuit of innovative and more effective therapeutic approaches has become a critical area of research. Natural zeolites extracted from volcanic and sedimentary rocks have emerged as a promising alternative to conventional therapeutics owing to their excellent ion-exchange and scavenging capabilities, crucial features for anti-inflammatory and anti-microbial treatments. Additionally, zeolites are known to promote tissue healing by guiding cell behavior.

Aim

Among different types of zeolites, clinoptilolite was investigated as a green material due to its abundancy, easy accessibility and promising therapeutic potential in treating CSWs and functionalized through environmental-friendly reactions to further enhance its anti-inflammatory features.

Materials and Methods

The clinoptilolite powder (referred to as MANC) was kindly supplied by Froximun AG company (Germany) and surface functionalized with heparin through a two-step reaction: (i) silanization with 3-aminopropyltrihetoxysilane (APTES) for amine exposure and, (ii) water-based carbodiimide-mediated heparin grafting. Dynamic Light Scattering (DLS), Infrared (IR) spectroscopy, Z-potential measurements and colorimetric assays were used to quantify grafted molecules. Cell viability and proliferation assays were conducted to study powder cytocompatibility in direct contact with murine fibroblasts, while the anti-inflammatory heparin scavenging action was quantified by measuring cytokines levels in the media over time. Lastly, a proof-of-concept of minimally invasive powder application was carried out.

Results

Compared to native MANC, powder silanization resulted in increased average hydrodynamic diameters and Z-potential values, confirming APTES grafting. The reaction time (i.e., 3h and 24 h) did not significantly alter the grafting yield. Conversely, adopted solvent strongly affected the number of exposed amines: anhydrous toluene increased the superficial charge from approx. -50mV to -21.35±1.44 mV, but Z-potential trend inversion to positive values (i.e., +19.68±0.80 mV) was obtained only when water was used. Such results were definitely confirmed by the colorimetric quantification of amino groups (i.e., $7\times10^{19}\pm2\times10^{18}$ *vs.* $1\times10^{20}\pm3\times10^{19}$ units/g_{powder}). However, the use of toluene gave a more stable functionalization coating in contact with fluids, further enhanced by MANC drying through thermal treatment. The successful water-based carbodiimide-mediated heparin grafting was confirmed by: IR spectra through the appearance of the peaks at 1635 and 1530 cm^{-1} (i.e., C=O and N-H vibrations); negative Z-potential values in accordance with the exposure of negative heparin molecules; increased particle average hydrodynamic diameter and, improved stability of the powder suspension over time. Moreover, colorimetrically quantified heparin gave approx. 100% functionalization yield. MANC-functionalized treated murine fibroblasts exhibited high cytocompatibility and improved cell proliferation compared to cells in contact with unmodified MANC. Moreover, heparin-grafted MANC effectively sequestered pro-inflammatory cytokines from the media, thus proving its anti-inflammatory potential. Lastly, powder encapsulation in a thermo-sensitive hydrogel was investigated in its perspective clinical application as therapeutic agent in the form of injectable system/cream to be mini-invasively applied in the wound bed.

Conclusion

Natural zeolites hold significant potential as alternative therapeutics owing to their inherent scavenging features, wide availability, ease of extraction, and the feasibility of functionalization through environmentally friendly chemical processes.

D3 – P191

A bioactive and immunomodulatory DNA tetrahedron-mineralized hydrogel for craniofacial bone regeneration

Yao L, Lin
State Key Laboratory of Oral Diseases, National Center for Stomatology, National Clinical Research Center for Oral Diseases, West China Hospital of Stomatology, Sichuan University, Chengdu, Sichuan, China

Introduction

The regeneration of craniofacial bone defects remains a significant clinical challenge in dentistry and oral surgery, as current graft substitutes often fail to orchestrate the sequential immune and osteogenic events essential for successful healing. While DNA-based hydrogels offer biomimetic potential, their clinical translation is constrained by rapid degradation and poorly defined immunomodulatory functions. This study aims to develop a mineralized DNA hydrogel platform that integrates early immunomodulation with sustained osteogenic support, providing a dual-functional strategy tailored for craniofacial bone repair.

Materials and Methods


A DNA hydrogel was constructed using tetrahedral framework nucleic acids (tFNAs) as cross-linking nodes. Biomimetic mineralization of nanoscale calcium phosphate (CaP) was introduced to enhance structural stability. In vitro, the capacity of the mineralized hydrogel (CaP-gel) to induce macrophage polarization toward the anti-inflammatory M2 phenotype was evaluated, along with its direct and indirect effects on osteoblast differentiation. In vivo, a rat critical-sized calvarial defect model—representative of craniofacial bone injury—was employed. Bone regeneration was assessed across early, mid-, and long-term stages using histology, immunohistochemistry/immunofluorescence, and micro-CT analysis.

Results

The CaP-gel demonstrated the ability to skew macrophage polarization toward the pro-regenerative M2 phenotype and establish an anti-inflammatory cytokine environment in vitro. This immunomodulatory effect, together with local calcium release, synergistically promoted osteogenic differentiation. In vivo, implantation of CaP-gel effectively modulated the early osteoimmune microenvironment in the calvarial defect, leading to significantly enhanced new bone formation and accelerated defect closure compared to controls..

Conclusion

A dual-functional mineralized DNA hydrogel was successfully developed that couples early immunomodulation with sustained osteogenic activity. By initiating a favorable osteoimmune response and subsequently supporting bone regeneration, this platform offers a promising and translatable strategy for advanced bone repair in dental and craniofacial applications.



D3 – P192

Investigation of variations in cellular response of primary human gingival fibroblast originating from different patients

Sun W.[1], Turkalj M.[1], Čokić S.M.[1], Pedano de Piero S.[1], Vanoirbeek J.[2], Hoet P.[2], Van Meerbeek B.[1], Van Landuyt K.L.[1]
[1]KU Leuven, Dept. of Oral Health Sciences, BIOMAT & UZ Leuven (University Hospitals Leuven), Dentistry; [2]KU Leuven, Environment and Health, Dept. of Public Health and Primary Care, Belgium

Introduction

Evaluating the biocompatibility of materials is crucial for ensuring the safety and well-being of patients by minimizing the risks of cytotoxic, immunogenic, or allergenic responses, while ensuring sustained material performance without eliciting adverse biological effects over time. Human gingival fibroblasts (HGFs) have been routinely used as in vitro model for screening dental materials for potential biotoxic effects. However, it remains unclear to what extent the heterogeneity of donors-derived samples influences the outcomes of biocompatibility assessments. This study aims to validate the reproducibility and accuracy of the use of primary HGFs obtained from different donors as a platform for biocompatibility assessment.

Materials and Methods

All experimental procedures, including the collection of gingival tissues, primary cell lines establishment, cell characterization, cell proliferation assay, cell doubling time, exposition procedure, XTT assay, LDH assay, and cell cycle analysis. The collection of human gingival tissue samples was approved by the Ethics Committee of the KU Leuven/UZ Leuven (S54254) and conformed to the Declaration of Helsinki. All quantitative data were presented as mean ± SD from at least 4 independent experiments. GraphPad Prism software (Version 10) was used for statistical analysis. Differences were considered statistically significant at $P < 0.05$.

Results

HGFs from junior donors displayed shorter cell doubling times than those from senior donors, as shown in Figure 1. Donor-derived HGFs exhibited compound-specific differences in EC50 values, reflecting inter-individual variation in cytotoxic response. Among the tested compounds, TEGDMA showed the lowest donor-to-donor variability, indicating a highly reproducible response across all ten donors. By contrast, HEMA, DOX, and DMSO induced substantial inter-individual variation in EC50 values, as shown in Figure 2.

Conclusion

In conclusion, donor-derived primary HGFs showed substantial inter-individual variability in proliferation and in response to the tested compounds. Although HGFs from junior donors tended to proliferate more rapidly, differences in monomer sensitivity were driven primarily by inter-individual variability rather than by a clear age-dependent effect. Our study provides important guidance for the future development of more comprehensive biocompatibility assessment of dental materials. These findings highlight the importance of accounting for donor-related variation in dental-material biocompatibility testing and provide guidance for the development of more comprehensive and clinically relevant in vitro assessment strategies.

Acknowledgements

We gratefully acknowledge the All of Us participants for their contributions, without whom this research would not have been possible.

References

[1]Williams D.F. Guidance on the assessment of biocompatibility of biomaterials: fundamentals and testing considerations. *J Dent Res*. 2019; 98(4); 371–381.
[2]Geurtsen W., Spahl W., Müller K. Cell death effects of resin-based dental material compounds and mercurials in human gingival fibroblasts. *Dent Mater* 1998; 14(4); 286–294.
[3]Kantarci A. Passaging of gingival fibroblasts from periodontally healthy and diseased sites upregulates osteogenesis-related genes. *J Periodontal Res* 2015; 50(2); 229–237.




Figure 1. Establishment and characterization of primary human gingival fibroblasts derived from donors of different ages. (A) Experimental workflow of primary HGFs isolation, cell line establishment, and expansion from gingival tissue explants obtained from junior and senior donors. (B) Representative phase-contrast images showing cellular outgrowth from gingival tissue explants between Day 4 and Day 8 after primary culture. Scale bar: 50 μm. (C) Representative images of Passage 0 cultures illustrating two distinct cell populations: fibroblast-like (left) and epithelial-like (right) cells migrating from the gingival tissue explants. Scale bar: 100 μm. (D) Representative phase-contrast images of Passage 3 HGFs exhibiting homogeneous spindle-shaped fibroblast morphology. Scale bar: 50 μm. (E) Immunofluorescence staining confirming the establishment and fibroblastic identity of primary HGFs, as indicated by positive vimentin expression. Nuclei were counterstained with DAPI. (F) Cell growth curves of HGFs derived from junior (18–25 years, n = 5) and senior (55–65 years, n = 5) donors. (G) Cell metabolic activity assessed at 12 h, 24 h, 48 h, 96 h, and 168 h using a metabolic assay. (H) Cell doubling time of HGFs derived from individual donors, demonstrating inter-donor variability. (I) Comparison of cell doubling times between junior and senior donor groups. (J) Representative flow cytometric profiles of cell cycle distribution of HGFs derived from different individual donors. (K) Quantitative analysis of cell cycle phase distribution of Passage 4 HGFs from individual donors. (L) Comparison of cell cycle phase distribution between junior and senior donor groups. Data are shown as mean ± SD (n = 6 per group, *P < 0.05, **P < 0.01, ***P < 0.001, ****P < 0.0001). The same letters represent no significant difference in percentage relative viability values.

Figure 2. Individual-based EC_{50} profiling of HGFs in response to dental materials and chemical agents. Mean concentrations of monomers, (with standard error of the mean) which reduced the gingival fibroblasts metabolism by 50% and caused release of 50% of LDH from cells. Monomers applied for 24 h (n=4). (A) Concentration ranges used for individual EC_{50} profiling of HEMA, TEGDMA, DOX, and DMSO in HGFs derived from different donors. (B–I) Comparison of individual EC_{50} values of HGFs derived from different donors following exposure to HEMA (B: XTT assay, F: LDH assay), TEGDMA (C: XTT assay, G: LDH assay), DOX (D: XTT assay, H: LDH assay), and DMSO (E: XTT assay, I: LDH assay). Data are shown as mean ± SD (n = 4 per group). Statistical significance was determined using one-way ANOVA followed by Tukey's post hoc test. $p < 0.05$ was considered statistically significant. The same letters represent no significant difference in percentage relative viability values.

D3 – P193

Designing dynamic and printable biomaterials with aldehyde-functionalized benzene-1,3,5-tricarboxamide supramolecular hydrogels

Pierrard A.[1], Sampon T.[1], Helsen A.[1], Duimel H.[2], Schauenburg D.[1], Baker M.[1]
[1]MERLN Institute for Technology-Inspired Regenerative Medicine, Maastricht University; [2]Microscope CORE lab, Maastricht University, The Netherlands

Introduction

Replicating the dynamic structure and functional complexity of native extracellular matrices (ECM) is essential for designing environments that adequately interact with living cells. Yet, current biomaterials still struggle to reproduce this hierarchical organization while maintaining sufficient mechanical robustness and adaptive behavior. To overcome this, a promising solution lies in the synthesis of supramolecular hydrogels, whose reversible (and thus dynamic) non-covalent interactions can more effectively mimic complex native structures, which rely on both covalent and supramolecular bonds. Benzene-1,3,5-tricarboxamide (BTA)-based supramolecular polymers are especially appealing as they self-assemble into fibers via H-bonding and hydrophobic interactions, forming dynamic hydrogels that resemble ECM structures.

Aim

In this work, we develop aldehyde-functionalized BTA hydrogels as a modular platform that combines both supramolecular self-assembly and post-assembly covalent network reinforcement.

Materials and Methods

Acetal-functionalized BTA-PEG telechelic macromonomers were first synthesized and subsequently deprotected to yield aldehyde-terminated arms. Hydrogel formation and supramolecular organization (self-assembly) were investigated by Nile Red fluorescence analysis, cryoTEM and complementary characterization methods. The viscoelastic properties of the resulting hydrogels were evaluated by rheology. In addition, the aldehyde groups provided reactive handles for further covalent or dynamic covalent crosslinking (using amine-based crosslinkers).

Results

The modified BTA macromonomers retained their ability to self-assemble into fibrous hydrogel networks. The introduction of aldehyde functionalities provided a chemically accessible route to reinforce the supramolecular matrix while preserving its dynamic character. Their characterization indicates that this strategy enables further tuning of gel stability, dynamicity and viscoelastic behavior while maintaining a highly hydrated, ECM-like architecture. These properties are expected to be valuable for optimizing injectability and printability in the bioprinting of these dynamic biomaterials.

Conclusion

Aldehyde-functionalized BTA hydrogels constitute a versatile supramolecular platform for the development of hybrid bioinks that combine reversible supramolecular interactions with covalent or dynamic covalent crosslinking. Such biomaterials may support advanced biofabrication and regenerative medicine by offering improved adaptability together with enhanced mechanical performance.

Acknowledgements

This work was supported by the European Union through a European Research Council (ERC) Consolidator Grant awarded to M. Baker under the Horizon Europe programme (Grant Agreement ID: 101088285).

D3 – P194

Supramolecular design of poly(urethane)-based polypseudorotaxane scaffolds for bone regeneration

Pochettino E.[1,2,3], Boffito M.[2], Pappalardo R.[1,2], Bronco S.[4], Cassino C.[5], Mortati L.[6], Ciardelli G.[1,2]
[1]Life Sciences Dept., University of Modena and Reggio Emilia; [2]Dept. of Mechanical and Aerospace Engineering, Politecnico di Torino; [3]Dept. of medical and surgical sciences, Università di Torino; [4]Institute for Chemical-Physical Processes, National Research Council (CNR-IPCF), Pisa; [5]Dept. of Science and Technological Innovation and Magnetic Resonance Platform (PRISMA-UPO), Università del Piemonte Orientale, Alessandria; [6]National Institute of Research in Metrology, INRIM, Turin, Italy

Introduction

Bone regeneration remains a major challenge in reconstructive medicine, particularly in the treatment of bone defects caused by trauma, disease, or surgical procedures. Tissue engineering strategies based on biomimetic scaffolds have gained increasing attention, as they provide structural support for cell adhesion, proliferation, and tissue growth. Among the materials explored, thermoplastic poly(urethanes) (PURs) are promising due to their tunable thermal and mechanical properties, and biocompatibility. Moreover, supramolecular approaches offer new opportunities to further tailor polymer properties through reversible host–guest interactions.

Aim

This work aims to design and characterize supramolecular scaffolds based on PUR/cyclodextrins (CDs) polypseudorotaxanes (PPRs) for bone tissue engineering applications.

Materials and Methods

A custom-made thermoplastic PUR based on poly(ε-caprolactone) (PCL), an aliphatic diisocyanate, and 1,4-butanediol was synthesized and characterized by infrared spectroscopy and size exclusion chromatography to confirm its chemical structure and molecular weight. Supramolecular PPR systems were obtained by combining PUR with CDs, generating formulations with PCL block coverage ranging from 0 to 12%. Complex formation was investigated by X-ray diffraction (XRD). Thermal and mechanical properties were evaluated by differential scanning calorimetry (DSC), thermogravimetric analysis (TGA), and atomic force microscopy (AFM). Finally, scaffolds were fabricated using a salt-leaching technique to assess material processability.

Results

The PUR was successfully synthesized, showing a number-average molecular weight of approximately 40 kDa and a polydispersity index of 1.4. The formation of PUR-based PPRs was confirmed by XRD and DSC, which revealed a peak at 20° associated with the channel-like structure of CDs and changes in melting and crystallization behavior compared to pristine PUR. Increasing CD coverage reduced PCL crystallinity due to the threading of CDs along the polymer chains, while supramolecular crystalline domains increased material stiffness, as evidenced by AFM. Porous scaffolds with a porosity of approximately 70% were obtained, and their morphology was evaluated by scanning electron microscopy.

Conclusion

These results demonstrate that supramolecular assembly between CDs and PCL-based PUR chains is an effective strategy to tune the structural and mechanical properties of thermoplastic scaffolds, enabling the fabrication of customizable materials for bone tissue engineering.

Acknowledgements

The research leading to these results has received funding from the European Union - NextGenerationEU through the Italian Ministry of University and Research under PNRR - M4C2-I1.3 Project PE_00000019 "HEAL ITALIA". The views and opinions expressed are those of the authors only and do not necessarily reflect those of the European Union or the European Commission. Neither the European Union nor the European Commission can be held responsible for them.

D3 – P195

Integrating supramolecular & covalent bonds to design spatiotemporal complexity in hydrogel biomaterials

Aliev A.E., Schauenburg D., Baker M.B.
Dept. of Instructive Biomaterials Engineering, Maastricht University, The Netherlands

Aim


One of the major challenges in tissue engineering is the ability to design synthetic materials that mimic the hierarchical and spatiotemporal complexity of the extracellular matrix. The project aims to address this challenge by integrating supramolecular interactions with stimuli-responsive covalent crosslinking to create tough, adaptive hydrogels capable of dynamic remodelling.

Materials and Methods

The project begins with the development of a versatile benzene-1,3,5-tricarboxamide (BTA) library. This approach opens access to diverse BTA architectures bearing reactive handles, which in my case would be alkynes, 4-aminophenylboronic acid pinacol ester and dopamine. Additionally, the potential of lipase-based acrylic resin catalysts to induce regioselectivity in amidation and azide-functionalized BTA synthesis will be investigated. The project aims to develop dynamic, tough hydrogels with controllable spatial and temporal behaviour, enabling advanced studies of cell–matrix interactions. This includes exploring structure–dynamics–property relationships governing cell adhesion in hydrogels. Ultimately, this work aims to enable covalent modification of synthetic hydrogels by living cells.

Results

In this work, BTA-based monomers were synthesized via amidation using propargylamine, hex-5-yn-1-amine, and 4-aminophenylboronic acid pinacol ester, introducing versatile reactive handles. These monomers provide a modular platform for further functionalization, including click chemistry and boronic ester interactions



Conclusion

With the successful synthesis of these monomers, the next step is to combine them with PEG to form hydrogels in which supramolecular assembly and crosslinking can be precisely tuned. This strategy enables post-synthetic modification and establishes a versatile platform for the development of adaptive hydrogels with potential applications in biomaterials and tissue engineering.

D3 – P196

Unraveling host-guest complexation in (photo-)crosslinkable gelatins for biofabrication purposes

Vermeersch E.[1], Lyskawa J.[2], Woisel P.[2], Van Vlierberghe S.[1]
[1]Polymer Chemistry and Biomaterials group (PBM), Centre of Macromolecular Chemistry (CMaC), Dept. of Organic and Macromolecular Chemistry, Ghent University, Belgium; [2]Univ. Lille, CNRS, INRAE, Centrale Lille, UMR 8207, UMET Unité Matériaux et Transformations, France

Introduction

A strong focus within the tissue engineering field is on the bioprinting of hydrogel-based scaffolds containing optimized biophysical cues and cell formulations. Stress relaxation is an example of such an important biophysical cue to target specific mesenchymal stem cell differentiation. Yet, conventional bioinks, including the ones based on the gold standard gelatin-methacryloyl (GelMA) and more recently developed thiolated gelatin/gelatin-norbornene (GelSH/GelNB), result in a permanently covalently crosslinked matrix with poor viscoelasticity. Hence, stress relaxation can be introduced by combining those photo-crosslinkable systems, allowing light-based bioprinting, with reversible bonds. A physical reversible bond that shows promise in gelatin-based systems is the host-guest complex, as gelatin not only allows the introduction of hosts and guests but also inherently contains guest moieties as functional groups of the amino-acids tyrosine and phenylalanine. However, a fundamental investigation of host-guest (beta-cyclodextrin-guest) complexation in combination with photo-crosslinkable functionalities (thiol-norbornene) is lacking to date.

Materials and Methods

In this project, gelatin was modified with photo-crosslinkable groups (thiol and norbornene), different potential guests (adamantane and tyramine), as well as with carboxymethyl beta-cyclodextrin as host, after which the degree of substitution was quantified using ^{1}H-NMR and UV-VIS spectroscopy. Next, the ability for the hosts to form a host-guest complex with the potential guests as well as with norbornene as side reaction was investigated using one dimension (1D), diffusion-ordered spectroscopy (DOSY) and rotational nuclear Overhauser effect spectroscopy (ROESY) ^{1}H-NMR. Finally, (photo-)rheology is currently being used to evaluate the effect of host-guest complexation on (photo-)crosslinking supporting further progress towards bioprinting.

Results

Thiolated gelatin (GelSH, DS 56%), gelatin-norbornene (GelNB, DS 95%), gelatin-adamantane (GelADA, DS 46%), gelatin-tyramine (GelTYR, DS 32%) and gelatin-cyclodextrin (GelCD, DS 71%) were successfully synthesized. The ^{1}H-NMR data prove that non-coupled beta-cyclodextrin has the ability to form host-guest complexes with GelADA and GelTYR, as well as with GelNB as side reaction. More specifically, the ROESY data show strong spatial correlation between the protons of norbornene and beta-cyclodextrin. This was no longer the case when competitive 1-admantane carboxylic acid was added, proving a stronger GelADA/beta-cyclodextrin complex with respect to the GelNB/beta-cyclodextrin complex. Finally, only limited complexation was detected between GelNB (as guest model) with carboxymethyl-beta-cyclodextrin or GelCD.

Conclusion

Complexation was detected between gelatin modified with different guests including norbornene and beta-cyclodextrin. However, complexation was only present to a minor extent with carboxymethyl-beta-cyclodextrin as host.

Acknowledgements

E.V. would like to acknowledge the financial support from FWO under the form of an FWO-SB PhD fellowship (1S89426N).

D3 – P197

Biomechanical performance of PCL cog threads for vaginal wall reinforcement: A ovine model study

Pinheiro F.[1,2], Silva A.T.[1,3], Sousa P.[2,4,5], Moreira A.[2,4,5], Sousa A.C.[2,4,5], Lopes B.[2,4,5], Rêma A.[2,4,5], Atayde L.[2,4,5], Mendonça C.[2,4,5], Amorim I.[6,7,8], Matos G.[6], Maurício A.C.[2,4,5], Alves N.[9], Fernandes A.A.[1,3], Alvites R.[2,4,5,10], Silva M.E.T.[1,3]

[1]Associated Laboratory of Energy, Transports and Aerospace (LAETA), INEGI, Porto; [2]Dept. of Veterinary Clinics, ICBAS, University of Porto, Portugal; [3]Faculty of Engineering, University of Porto; [4]Associated Laboratory for Green Chemistry (LAQV), REQUIMTE, Porto; [5]Associate Laboratory for Animal and Veterinary Science (AL4AnimalS), Lisbon; [6]Dept. of Molecular Pathology and Immunology, ICBAS, University of Porto; [7]Institute for Research and Innovation in Health (i3S), University of Porto; [8]Institute of Molecular Pathology and Immunology, University of Porto (IPATIMUP); [9]Centre for Rapid and Sustainable Product Development (CDRSP), IPL, Marinha Grande; [10]Instituto Universitário de Ciências da Saúde (IUCS), CESPU, Gandra PRD, Portugal

Introduction

Pelvic organ prolapse (POP) significantly affects women's quality of life. Complications from synthetic meshes have led to a search for biocompatible alternatives. This study evaluates biodegradable polycaprolactone (PCL) cog threads as a minimally invasive reinforcement for the vaginal canal in a translational sheep model 1-4.

Materials and Methods

Ten adult ewes were divided into a control group (n=5) and a reinforced group (n=5). In the reinforced group, two PCL cog threads were implanted longitudinally in the vaginal walls. After 180 days, the tissues were excised for ex vivo evaluation. Biomechanical performance was assessed via uniaxial tensile testing and ball-burst testing. Histopathological analysis evaluated tissue integration and inflammatory response.

Results

Uniaxial tensile testing showed a 48% increase in ultimate tensile strength in reinforced tissues compared to controls (29.89 ± 5.4 N vs. 20.17 ± 3.4 N; $p < 0.01$). Ball-burst resistance improved by 60%, with reinforced specimens withstanding 127.4 ± 14 N compared to 79.8 ± 16 N in controls ($p < 0.001$). Histology at 6 months revealed moderate chronic vaginitis and increased collagen deposition, indicating organized tissue remodeling without rejection.

Conclusion

PCL cog threads effectively integrate into the vaginal wall, providing significant mechanical reinforcement while promoting structured tissue remodeling. These findings suggest they are a promising, minimally invasive, and biodegradable alternative to permanent synthetic meshes for POP repair.

Acknowledgements

Funding provided by FCT, Portugal, under grants 2023.00640.BD, PTDC/EMD-EMD/2229/2020, and 2021.00077.CEECIND.

D3 – P198

Geometry-driven design of melt electrowriting PCL nerve guide conduits for peripheral nerve repair

Martins J.A.P.[1], Alvites R.[2,3], Maurício A. C.[3,4] Parente M.[1,5], Silva M.E.T.[1,5]
[1]Faculty of Engineering of the University of Porto; [2]ICETA, Porto, Portugal; [3]REQUIMTE, Porto; [4]Institudo de Ciências Biomédicas de Abel Salazar, Porto; [5]LAETA-INEGI, Porto, Portugal

Introduction

Peripheral nerve injuries (PNI), occurring frequently due to trauma, can lead to structural changes resulting in partial or complete loss of motor and sensory function. End-to-end sutures (EtE) or autografts are the standard treatments for PNIs, but nerve guide conduits (NGCs) are emerging promising alternatives, providing physical guidance and a supportive microenvironment for axonal growth. Polycaprolactone (PCL) is a biocompatible and biodegradable polymer with various applications in tissue engineering. Regarding NGCs, PCL offers sufficient structural stability while maintaining the flexibility required to support nerve regeneration. Its ability to be processed into aligned fibrous scaffolds provides a topographical surface that guides axon growth, thereby enhancing peripheral nerve regeneration. It is also a material frequently employed in melt electrowriting (MEW), a high-precision electrospinning technique that allows the fabrication of porous structures, with nanometer-scale dimensions. Beyond material selection, the geometry and internal microarchitecture of conduits play a critical role in influencing cellular behavior and regenerative outcomes. This study aims to develop PCL-based nerve guide conduits with controlled geometries using MEW and to evaluate their mechanical and structural performance.

Materials and Methods

PCL scaffolds were fabricated via MEW onto a flat collector, enabling precise deposition of microfibers with defined orientation, spacing, and layer organization. The resulting planar constructs were subsequently transformed into tubular conduits through a post-fabrication molding process. Fiber alignments, pore size and stacking patterns were varied in order to achieve different geometrical designs, and the mechanical properties were evaluated through tensile and compression assays, to assess suitability for nerve repair applications.

Results

MEW enabled the fabrication of highly organized and reproducible PCL microstructures with controlled fiber orientation and pore geometry. The conversion of flat scaffolds into tubular conduits was successfully achieved without compromising structural integrity or fiber organization. The mechanical tests demonstrated that scaffold architecture influenced NGCs' properties, with aligned fiber configurations enhancing flexibility and mechanical stability.

Conclusion

This study reveals the potential of combining MEW with post fabrication molding to produce nerve guide conduits with customized geometries. The ability to control microarchitecture and translate planar constructs into tubular forms provides a versatile platform for optimizing regenerative strategies. These finding highlight the importance of geometrical design in enhancing mechanical properties of MEW-NGCs for peripheral nerve repair.

Acknowledgements

The authors acknowledge the Foundation for Science and Technology (FCT) for financial support to LAETA through project UID/50022/2025. This research was also supported by the FCT PhD grant 2025.00829.BD.

D3 – P199

Milk extracellular vesicles as nanomedicines and drug delivery systems in bone regeneration

Santos-Coquillat A., Iriarte-Urdiain E., des Rieux A.
Louvain Drug Research Institute, Advanced Drug Delivery and Biomaterials (ADDB), Université catholique de Louvain, UCLouvain, Brussels, Belgium

Introduction

Extracellular vesicles (EVs) are signaling particles without replicative capacity, released by cells into the biological fluids with the aim of controlling intercellular communication. They have a nanometric size and can carry and exchange proteins, lipids, miRNA, or DNA between diverse cell types. Milk extracellular vesicles (MEV) have been studied as immunomodulatory nanomedicines and drug delivery systems (DDS) with a natural origin. Their effects on bone cells and as DDS in biomaterials are still under study.

Aim

Understand the effects of milk EVs on osteoclastogenesis and osteoblastogenesis to use as nanomedicines within biomaterials in bone regeneration applications.

Materials and Methods

Goat MEVs preparations were obtained by sequential centrifugation, ultrafiltration, and size-exclusion chromatography and characterized by NTA and DLS. SCAP (Stem Cells from the Apical Papilla) and RAW 264.7 macrophages were used as in vitro models to assess the effects of MEVs on osteoblastogenesis and osteoclastogenesis.

SCAP cells were differentiated towards a bone phenotype with conditioned media containing ascorbic acid, dexamethasone, and β-glycerophosphate. MEVs were added together with this media at a dose of 250 particles/cell every 2-3 days for 14 days. After this time, RUNX2, ALP, and OCN gene expression was analysed by RT-qPCR.

For osteoclastogenesis, cells were treated with either one dose of low or high MEVs (250 or 2500 particles/cell, respectively), in the presence or absence of RANKL (50 ng/mL). After 6 days, TRAP and Cathepsin K were analysed by RT-qPCR. In order to impede the differentiation, mRNA coding for IL4 was encapsulated in MEV (MEV-IL4) using Exo-Fect reagent and purified following the manufacturer's instructions. IL4 secretion from macrophages was analysed by ELISA, and TRAP and Cathepsin K expression were analysed by RT-qPCR after 6 days.

Results

The incorporation of MEVs into the differentiation media increased statistically significantly the expression of RUNX2, ALP, and OCN, indicating a synergistic effect on the differentiation process. The addition of MEVs neither increased nor reduced the osteoclastogenesis process, with neither of the two doses used. On the other hand, when the IL4 mRNA was encapsulated and dosed to the cells, the high dose of 2500 particles/cell reduced the osteoclastogenesis process.

Conclusion

MEVs are able to improve the bone formation in SCAP cells with a sustained dosing strategy. MEV-IL4 can reduce osteoclastogenesis, whereas MEVs alone do not affect the process. To sum up, MEVs are interesting candidates as nanomedicines to be associated with biomaterials for a controlled release in bone regeneration applications.

D3 – P200

Strain based structural optimization of bioresorbable biomimetic polymer-ceramic composite cages for spinal fusion

Fragas Gouveia A.[1], Kok J.[1], Villette C.[2], Ito K.[1], Van Rietbergen B.[1], Dias Castilho M.[1]
[1]Biomedical Engineering Dept., TU Eindhoven, The Netherlands; [2]School of Engineering and Materials Science, Queen Mary University of London, UK

Introduction

Spinal fusion surgery is a widely used treatment for low back pain, one of the leading causes of disability worldwide. However, it typically relies on non-resorbable materials (typically metals and polymers), which sometimes fail to stimulate bone ingrowth, increasing risks of delayed fusion and related complications. Here we hypothesize that fusion rates can be improved by creating a biomechanical environment that favours bone growth, while the use of fully bioresorbable materials may reduce late-stage stress-shielding and enable complete and stable fusion. Our aim was therefore to design, structurally optimize, and manufacture an interbody cage composed of a novel hydroxyapatite (HA)–poly(DL-lactide) (PDLA) composite[1], with tailored mechanical and resorption characteristics to maximize early bone ingrowth through mechanical stimulation.

Materials and Methods

A spinal fusion cage was designed with a repeating body-centered cubic lattice unit cell and material properties of a biomimetic HA/PDLA composite[1], comparable to those of cortical bone. The design was iteratively adjusted using a strain optimization method based on finite element (FE) simulations[2]. In each iteration, patient-specific loading was simulated using a FE model of the spine from a cohort of patients eligible for spine fusion, and the strut strains were calculated. The cross-sectional area of each beam was then adjusted until convergence to a target strain value of 2250με, within the bone apposition range according to the Mechanostat hypothesis[3].

Results

The converged strut design produced a total cage porosity of 85% while ensuring mechanical integrity under spinal loading. Preferential directionally of strut thickening was evident, and aligned with the expected trajectory of load transfer. During the optimization, undeformed beams were removed and remaining elements converged to either the target strain or the extremes of the acceptable diameter range (Figure). When subjected to the applied loads, 87% of the final structure is in the bone apposition range.

Conclusion


The results indicate that a considerable increase in struts in the target strain is possible, while keeping adequate overall cage stiffness and strength. Compared to earlier topology optimization studies, the use of a strut adaptation approach simplifies the optimization workflow and applicability, as initial cage shape, unit cell size, geometry, and acceptable strut thickness can be adjusted to ensure manufacturability and prevent material failure. It also enables easy implementation of resorption to simulate later fusion stages.

Acknowledgements

The authors acknowledge funding from the Dutch Research Council (NWO) and the São Paulo Research Foundation (FAPESP) through the BioFusion project (482.22.404).

References

[1]Zhang Y. et al. Biomimetic Mechanically Strong One Dimensional Hydroxyapatite/Poly(D,L-lactide) Composite Inducing Formation of Anisotropic Collagen Matrix. *ACS Nano* 2021; 15; 17480-17498.
[2]Phillips A. et al. Femoral bone mesoscale structural architecture prediction using musculoskeletal and finite element modelling. *International Biomechanics* 2015; 2:1; 43-61.
[3]Frost H. Bone's mechanostat: A 2003 update. *The Anatomical Record* 2003; 275A:2; 1081-1101.



D3 – P201

Biofabrication of biomimetic skeletal muscle fascicles via rotary wet spinning and an aqueous two-phase porous interface

Celikkin N.[1,2], Volpi M.[3], Maulliari F.[1], Promovych Y.[1], Vandenbosch M.[2], Costantini M.[1]
[1]Institute of Physical Chemistry, Polish Academy of Sciences, Warsaw; [2]M4i, Maastricht University, The Netherlands; [3]Materials Science and Engineering, Warsaw University of Technology, Poland

Introduction

Skeletal muscle exhibits a highly organized anisotropic architecture in which aligned myofibers are bundled into fascicles and embedded within a connective tissue matrix. This hierarchical organization is essential for uniaxial contraction, mechanical stability, and functional performance in vivo. Reproducing these structural and cellular features in vitro remains a major challenge in skeletal muscle engineering.

Materials and Methods

An engineered skeletal muscle (eSM) platform was developed to generate biomimetic fascicles using rotary wet spinning (RoWS). Fibers were fabricated with a fibrin-based bioink in the core and a stable aqueous two-phase system (ATPS)-based hydrogel ink in the shell. The shell formulation was designed to entrap thermoresponsive hydrogel droplets within a rapidly crosslinkable alginate matrix during fiber formation. Upon incubation, the thermoresponsive droplets dissolved, generating a porous shell network. To establish a physiologically relevant cellular organization, myoblasts were embedded within the fibrin core, while fibroblasts were seeded onto the porous outer shell. This configuration was designed to mimic native muscle architecture, in which myofibers are surrounded by a fibroblast-regulated extracellular matrix. Immunofluorescence and proteomic analyses were used to assess myogenic differentiation, extracellular matrix deposition, and overall fascicle maturation.

Results

The developed platform enabled the formation of highly anisotropic skeletal muscle fascicles with a porous outer shell and a cell-laden myogenic core. The ATPS-based porous interface supported sacrificial droplet removal during incubation, creating a shell architecture expected to enhance nutrient diffusion and metabolic waste exchange while promoting biochemical communication between the external environment and the encapsulated myogenic compartment. The biomimetic distribution of myoblasts recapitulates key aspects of native muscle tissue organization. Immunofluorescence and proteomic analyses supported fascicle maturation by identifying myogenic markers together with extracellular matrix-associated proteins, indicating both myogenic differentiation and matrix remodeling. These findings suggest that the combination of ATPS-enabled porosity contributes to structural and biochemical features relevant for engineered muscle development.

Conclusion

This study presents a robust, tunable strategy for engineering highly anisotropic in vitro skeletal muscle fascicles with improved architectural fidelity and greater biological complexity. By integrating ATPS-enabled porosity with a biomimetic co-culture design, the platform supports fascicle maturation and provides a promising model for applications in biorobotics, cultured meat, disease modeling, drug screening, and regenerative medicine.

Acknowledgements

The results are based on research funded by the National Science Centre, Poland, under the SONATINA 2023/48/C/ST5/00230 project. We acknowledge the Laboratory of Imaging Tissue Structure and Function, at the Nencki Institute, the Leader of the Polish Euro-BioImaging Node “Advanced Light Microscopy NodePoland” supported by the Minister of Education and Science based on contract No 2022/WK/05, for their assistance.

D3 – P202

Multilevel nanosafety screening in freshwater planarians combining organismal endpoints and DNA primary damage assessment

Bernardeschi M.[1], Battaglini M.[1], Carmignani A.[1], Lefevre M.[1], Fragouli D.[2], Ferrari G.[2], Athanassiou A.[2], Armirotti A.[3], Di Fonzo A.[3], Ciofani G.[1]

[1]Smart Bio-Interfaces, Italian Institute of Technology, Pontedera; [2]Smart Materials, Italian Institute of Technology, Genoa; [3]Analytical Chemistry Facility, Italian Institute of Technology, Genoa, Italy

Introduction

Engineered nanomaterials (ENMs) and micro/nanoplastics are increasingly found in aquatic environments, but rapid whole-organism assays able to capture both toxicity and early DNA damage are still limited. The freshwater planarian *Schmidtea mediterranea* is a useful *in vivo* model because its regenerative stem-cell compartment enables sensitive toxicological readouts.

Materials and Methods

Within the iCARE project and the IIT Flagships for Sustainability programme, we developed a multilevel screening workflow based on 7-day exposure, survival, regeneration and DNA diffusion assay. Planarians were exposed to reference ENMs (SiO_2, graphene oxide and AgPure silver nanoparticles), project nanomaterials, polydopamine-based structures, ZnO nanowires and polylactic acid (PLA) microplastics. PLA was tested both in water and by oral administration.

Results

GO and SiO_2 showed full survival up to 50 µg/mL, whereas AgPure displayed marked toxicity above 0.05 µg/mL. DNA diffusion analysis detected increased primary damage at high SiO_2 doses and ranked selected project materials as AVN-1 > COG >= GNP-1. Graphene- and polydopamine-based nanostructures also produced distinct effects on cell proliferation, while PDNPs showed preliminary protective activity under oxidative stress. PLA microplastics did not affect survival or regeneration; oral administration provided the most controlled and reliable exposure.

Conclusion

S. mediterranea provides a rapid, low-cost and ethically favourable platform integrating organismal and mechanistic endpoints for early nanosafety assessment. This workflow supports safer-by-design selection of nanomaterials and offers a practical approach to evaluate emerging plastic alternatives under relevant exposure conditions.

D3 – P203

Influence of fibre substrates on iPSC differentiation to cardiomyocytes in 3D gels

Tung W.T.[1], Kaliannagounder Krishnamoorthi V.[1], Steedman O.F.[1], Melo P.[1], Gill J.[2], Ferreira A.M.[1], Armstrong L.[3], Dalgarno K.[1]

[1]School of Engineering, Newcastle University; [2]School of Pharmacy and Translational and Clinical Research Institute, Faculty of Medical Sciences, Newcastle University; [3]Biosciences Institute, International Centre for Life, Faculty of Medical Sciences, Newcastle University, UK

Introduction

There is a growing demand for physiologically relevant cardiac tissue models to advance the study of cardiac disease mechanisms, evaluate regenerative therapies, and improve cardiotoxicity screening for emerging drugs. Our group employs Reactive Jet Impingement (ReJI) bioprinting, which leverages the rapid crosslinking characteristics of a collagen-alginate-fibrin (CAF) hydrogel to fabricate three-dimensional constructs for in vitro cardiac modeling. The aim of this work is to optimise in situ differentiation of human induced pluripotent stem cells (iPSCs) into cardiomyocytes, co-cultured with human cardiac fibroblasts (HCFs), within ReJI-printed CAF hydrogels using a commercially available cardiomyocyte differentiation kit. To explore the integration of structural reinforcement with differentiation, we introduce an electrospun PCL fibre substrate for CAF gel deposition, creating a hydrogel-fibre composite. Ultimately, this approach will support the development of a future perfusable cardiac tissue model by enabling ReJI deposition of CAF-encapsulated cells onto electrospun PCL scaffold.

Materials and Methods

iPSCs, cultured with and without HCFs, were first differentiated on 2D CAF hydrogels casted in 48 well plates, by crosslinking collagen-alginate-fibrinogen precursor solution with thrombin and calcium chloride, with 2D Geltrex serving as a control substrate. ReJI bioprinting was then employed to encapsulate iPSCs, with and without HCFs, into individual 3D CAF gel constructs (~100 uL each, 5 million cells/ml) and induced cardiomyocyte differentiation. Subsequently, we ReJI-printed a layer of CAF gel encapsulated iPSC-HCF co-cultures onto electrospun PCL substrates to assess compatibility of the hydrogel-fibre composite for supporting in situ differentiation and to examine potential fibre-mediated cellular orientation. Analyses included calcium flux imaging, immunocytochemistry, PCR and flow cytometry.

Results

Preliminary findings demonstrated successful formation of contracting iPSC-derived cardiomyocytes (iCMs) on 2D Geltrex, 2D CAF, and within 3D CAF gels. The inclusion of HCFs appeared to promote early cardiac lineage specification, as evidenced by the detection of GATA4 expression in iPSCs prior to induction with differentiation medium. Calcium flux imaging confirmed the presence of coordinated electrical activity and synchronous calcium transients within the self-organised cardiomyocyte clusters. For the CAF gel-fibre composite, the fibres provide a multi-scale network of attachment points within the hydrogel. These results indicate that the CAF hydrogel environment is compatible with iPSC cardiac differentiation and supports functional cardiomyocyte development, laying a strong foundation for advancing toward a 3D perfusable in vitro cardiac tissue model.

D3 – P204

Electrospun scaffolds functionalized with a hydrogen sulfide donor stimulate angiogenesis

Yao T.[1,2], van Nunen T.[1], Rivero R.[1], Powell C.[3], Carrazzone R.[3], Kessels L.[4], Wieringa P.A.[1], Hafeez S.[1], Wolfs T.G.A.M.[4], Moroni L.[1], Matson J.B.[3], Baker M.B.[1]

[1]Dept. of Complex Tissue Regeneration, MERLN Institute for Technology-Inspired Regenerative Medicine, Maastricht University, The Netherlands; [2]School of Chemical Engineering, Northwest University, Xi'an, China; [3]Chemistry Dept., Macromolecules Innovation Institute, Virginia Tech, Blacksburg, USA; [4]Dept. of Pediatrics, Maastricht University, The Netherlands

Introduction

Vascularization remains a major bottleneck in tissue engineering, where insufficient blood vessel formation limits construct survival and integration. Hydrogen sulfide (H_2S) is an endogenous gasotransmitter with pro-angiogenic potential, but its controlled and sustained delivery from biomaterials remains challenging.

Aim

We aimed to develop a fully synthetic fibrous scaffold that integrates structural extracellular matrix mimicry with localized H_2S delivery, and to determine whether covalent incorporation of an H_2S donor can enhance angiogenic responses in vitro and in ovo.

Materials and Methods

Electrospun polycaprolactone (PCL) scaffolds were fabricated by blending high-molecular-weight PCL with 1, 5, or 10 wt% azide-functionalized PCL. Scaffolds were post-functionalized by click chemistry with an alkyne-bearing N-thiocarboxyanhydride (NTA), an H_2S donor that releases carbonyl sulfide followed by H_2S formation in aqueous conditions. Scaffold morphology, functionalization, and H_2S release were characterized by SEM, fluorescence labeling, FTIR, and methylene blue assay. Human umbilical vein endothelial cells (HUVECs) were cultured on the scaffolds and evaluated for viability, proliferation, and endothelial phenotype. Angiogenic performance was further assessed using the chick chorioallantoic membrane (CAM) assay.

Results

NTA was successfully conjugated to electrospun fibers without altering scaffold morphology. H_2S release increased with NTA loading, reaching approximately 4.1, 7.0, and 12 nmol/mg scaffold for the 1, 5, and 10% functionalized groups, respectively. All scaffolds were cytocompatible. Compared with controls, the 5 and 10% NTA-functionalized scaffolds increased HUVEC metabolic activity and proliferation, promoted more confluent endothelial layers, and enhanced VE-cadherin-positive cell-cell junction formation. In the CAM assay, the 10% NTA-functionalized scaffold significantly increased vessel area by about 15% relative to the nonfunctionalized control, demonstrating enhanced angiogenesis in ovo.

Conclusion

Covalent integration of an H_2S donor into electrospun PCL scaffolds provides a simple and modular strategy to combine fibrous architecture with gasotransmitter delivery. These H_2S-releasing scaffolds enhanced endothelial cell behavior and promoted angiogenesis without growth factors, highlighting their promise as therapeutic biomaterials for vascularized tissue regeneration.

Acknowledgements

This work was supported by the Dutch Province of Limburg, the China Scholarship Council (grant 201508610081), the InSciTe funding agency through the EyeSciTe consortium, and the US National Institutes of Health (R01GM123508).

D3 – P205

Droplet microfluidic generation of pancreatic cancer mini spheroids using HPAF-II cells

Abbasi Aval N., Joensson N.H.
Protein Science, School of Engineering Sciences in Chemistry, Biotechnology and Health, KTH Royal Institute of Technology, Stockholm, Sweden

Introduction

Three-dimensional (3D) tumor spheroids have emerged as physiologically relevant models for studying tumor biology, cell–cell interactions, and drug responses compared with conventional two-dimensional cell cultures. However, commonly used spheroid formation methods such as hanging-drop or low-adhesion plates often produce spheroids with heterogeneous size and limited reproducibility[1]. Droplet microfluidics offers a promising approach for generating uniform microenvironments that can support controlled cell aggregation and high-throughput spheroid formation[2].

Aim

The aim of this study was to develop a droplet-based microfluidic platform for controlled generation of pancreatic cancer minispheroids using the human pancreatic adenocarcinoma cell line HPAF-II. Because the platform requires only ~50 cells per droplet, it may enable minispheroid generation from limited or rare samples, including primary patient-derived cells.

Materials and Methods

We utilized a microfluidic chip (Fluidic 163, 140 µm nozzle, PC material, ChipShop) with a negative pressure setup[2]. The oil phase (Bio-Rad premixed droplet oil) and aqueous HPAF-II cell suspension were maintained at atmospheric pressure, while outlet pressure was controlled via a pump. The droplets were collected and incubated under standard cell culture conditions to promote cell aggregation and mini spheroid formation. Microscopy imaging was used to monitor droplet stability, cell distribution, and mini spheroid development over time.

Results

The droplet microfluidic system enabled reproducible generation of monodisperse droplets and controlled encapsulation of cancer cells. Within 48–72 hours of incubation, cells aggregated inside droplets and formed compact multicellular mini spheroids. The confined microenvironment promoted cell–cell interactions and supported consistent mini spheroid morphology. The size distribution of the generated droplets and spheroid formation on day 3 is shown in Figure 1.




Figure 1. Size distribution of 50 droplets and HPAF-II mini spheroid formation in the droplets after 72 hours.

Conclusion

This study demonstrates that droplet microfluidics can be used as a simple and scalable platform for the controlled generation of pancreatic tumor mini spheroids. The approach enables precise control over cell loading and microenvironmental confinement, which can improve reproducibility compared with conventional spheroid culture techniques. The platform may provide a useful tool for future studies involving tumor microenvironment modeling, tumor–stroma interactions, and high-throughput drug screening applications.

References

[1]Pampaloni F., Reynaud E.G., Stelzer E.H.K. The third dimension bridges the gap between cell culture and live tissue. *Nature Reviews Molecular Cell Biology* 2007; 8; 839–845.
[2]Trossbach M., Åkerlund E., Langer K., Seashore-Ludlow B., Joensson H.N. High-throughput cell spheroid production and assembly analysis by microfluidics and deep learning, *SLAS Technology* 2023; 28; 423-432.

D3 – P206

Synergistic effects of extrinsic photobiomodulation and biofunctional micropatterns on promotion of mesenchymal stem cell differentiation

Tsai G.-Y.[1], Chen S.-Y.[2], Wang M.-J.[1]
[1]Dept. of Chemical Engineering, National Taiwan University of Science and Technology; [2]Institute of Atomic and Molecular Sciences, Academia Sinica, Taipei, Taiwan

The chemical and physical niches of biomaterials can synergistically control the cell behavior including cell attachment, migration, proliferation, and differentiation. Among different strategies, the specific control of the shape of the micro-patterns of substrate was reported to direct mesenchymal stem cells (MSCs) differentiation effectively. In addition, photobiomodulation can regulate the cell growth as well as to promote MSCs differentiation by exposing cells under light that MSCs containing photosensitizer would differentiate to adipogenic cells after light irradiation. This study proposes to use collagen microislands with different shape, aspect ratios, areas, and symmetries by photolithography method to guide the differentiation of Wharton Jelly mesenchymal stem cells (WJ-MSCs).

The preliminary results showed that the adipogenic and osteogenic differentiation of WJ-MSCs can be found on rectangular and stellate microislands, correspondingly. Moreover, the stellate microislands rendered the highest percentage for osteogenic differentiation, whereas the square microislands promoted the highest adipogenic differentiation. In summaries, this research work applied an unbiased method to dictate the WJ-MSC differentiation by topography of microislands and photobiomodulation which possess great potential for the applications in tissue engineering and regenerative medicine.

Acknowledgements
Financial supports from the National Science and Technology Council of Taiwan are acknowledged.

D3 – P207

Immune cell extracellular vesicle-crosslinked hydrogel microparticles for post-stroke brain immunomodulation and repair

Xin S.
College of Biomedical Engineering & Instrument Science, Zhejiang University, Hangzhou, China

Introduction

Stroke induces a complex inflammatory response that shapes tissue remodeling and neurological recovery. Our previous studies using injectable hydrogel microparticles in a mouse photothrombotic stroke model showed that promoting the infiltration of reparative immune cells into the infarct cavity was associated with reduced glial scarring, enhanced vascular and neural remodeling, and improved functional recovery. These findings suggest that peripheral immune processes may actively participate in brain repair after injury. However, how peripheral reparative immune signals are initiated, recruited, and sustained within the post-stroke brain remains poorly understood. Here, we developed immune cell extracellular vesicle (EV)-crosslinked hydrogel microparticles as an injectable immunomodulatory material to investigate and regulate peripheral immune-cell-mediated brain repair after stroke.

Materials and Methods

Hydrogel microparticles were fabricated and functionalized to enable crosslinking through EVs derived from peripheral immune cells with reparative phenotypes. They are injected into the infarct using a mouse photothrombotic stroke model. Post-stroke immune responses were evaluated by immunofluorescence staining, flow cytometry, and transcriptomic analysis, with emphasis on peripheral immune cell infiltration, vascular remodeling, neural repair, and scar formation.

Results

Hydrogel microparticles were successfully crosslinked using EVs derived from neutrophils, regulatory T cells, macrophages, and human mesenchymal stem cells. After implantation into the post-stroke infarct cavity, these EV-crosslinked microparticles exhibited rapid in vivo degradation, with most implanted materials nearly cleared by 16 days after implantation. Despite their similar degradation behavior, different immune EV formulations produced distinct regenerative outcomes. Among the tested groups, only macrophage EV-crosslinked microparticles significantly promoted vascular repair within the infarct region, as shown by enhanced vascular reconstruction and improved organization of the lesion microenvironment (Fig. 1). In contrast, neutrophil EV- and Treg EV-crosslinked microparticles did not induce comparable vascular regeneration. These results suggest that macrophage-derived EVs provide direct pro-vascular reparative signals in the post-stroke brain, supporting a specific role of macrophage-mediated immune regulation in infarct remodeling and vascular repair.




Fig. 1 Macrophage EV-crosslinked microparticles promote vascular repair in the post-stroke infarct.

Conclusion

This study establishes immune cell EV-crosslinked hydrogel microparticles as a bioactive material platform for probing and regulating peripheral reparative immune responses after stroke. By linking peripheral immune signaling with local brain repair, this strategy provides new insight into post-stroke immunomodulation for brain regeneration.

D3 – P208
Natural nanobiomaterials for medicine and drug delivery

Rysová M.[1], Tománková H.[1,2], Morávková K.[1,3], Prokopcová.[1,3], Ševců A.[1]
[1]Institute for Nanomaterial, Advanced Technologies and Innovation, Technical University of Liberec; [2]Faculty of Natural Sciences, Humanities, and Education, Technical University of Liberec; [3]Faculty of Mechatronics, Computer Science, and Interdisciplinary Studies, Technical University of Liberec, Czech Republic

Introduction
Natural biomaterials utilize natural substances - most commonly in the form of natural biopolymers - to create a wide range of structures for medical applications and biotechnology. Their bioactivity, biodegradability, and cellular response are determined not only by their material composition and structure, but also by the method and degree of cross-linking, further functionalization, and other factors. Biomaterials can also be obtained by synthesis from low-molecular-weight precursors. Such materials often aim to mimic properties or structures that occur naturally but are difficult to isolate.

This work presents nanobiomaterials based on polysaccharide chitosan, protein silk fibroin, and inorganic silicon dioxide as important examples of biopolymers with high potential for applications in regenerative medicine and drug delivery. To enhance their natural bioactivity, all materials were treated with antibiotic gentamicin.

Materials and Methods
Chitosan was obtained from a commercial source; silk fibroin was isolated from silkworm cocoons; and SiOx macromolecules were synthesized from the low-molecular-weight precursor TEOS using the sol-gel method. All biopolymers were processed by electrospinning into nanofiber layers with basis weights of 10 and 30 g/m². The cross-linked nanofibers were evaluated for morphological properties, bioactivity, antioxidant and antibacterial efficacy, and biodegradability. Antibacterial properties were enhanced by incorporation of antibiotic gentamicin.

Results
Chitosan nanofibers exhibit a number of unique properties that can be utilized, for example, in regenerative medicine, wound healing, and drug delivery. Chitosan nanofibres were confirmed to be biocompatible to human dermal fibroblast, antioxidant, and antimicrobial against gram-positive S. gallinarum in their untreated form. Silk fibroin, obtained from the cocoons of the silkworm, is an easily cross-linkable protein with potential in tissue engineering and regenerative medicine. Cross-linked silk fibroin nanofibres were confirmed to be stable in moist environment while supporting cellular adhesion and proliferation. Silica, as an interesting bioactive inorganic material, showed biodegradability tunable by cross-linking degree combined with surface available for further functionalization. All gentamicin-treated materials showed remarkable antimicrobial activity against gram-positive and gram-negative bacteria with drug release kinetics affected by the type of the biopolymer matrix.

Conclusion
Processing of selected biopolymers into nanomaterials lead to increased specific surface area, enhanced bioactivity, and altered bioavailability of their bioactive degradation products and incorporated active substance. These biological effects were further enhanced by biopolymer type and crosslinking degree, which also allowed modification degradation kinetics and altered release profiles of active substance from the nanobiomaterial matrix.

Acknowledgements
This research was supported by OABI TUL 8330/117 fund and project CZ.02.1.01/0.0/0.0/16_019/0000843.

D3 – P209
Viruses and bacteria inhibition using low temperature plasma

Vig K., Zafaryab M.
Dept. of Biological Sciences, Alabama State University, USA


Introduction
The fourth fundamental type of matter, plasma, is a fascinating medium composed of electrons and charged species that can be found throughout the observable cosmos. Thermal plasma and low temperature plasma (LTP) are two types of artificial plasma that can be created using precise laboratory techniques. LTP is gaining usage for biomedical and therapeutic applications. The aim of the current study was to investigate LTP effect on the inhibition of respiratory syncytial virus (RSV) and bacteria (*S. aureus* and *E. coli*).

Materials and Methods
For virus inhibition study, HEp2 cells infected with RSV were treated with LTP for 2 and 5 minutes. After 72 hours of incubation immunofluorescence assay was done using FTIC labeled secondary antibody and western blot was performed using HRP labeled secondary antibody against F protein. For both assays, RSV Inhibitor -VP-14637 was used as a positive control. Further, viral load was detected using RT-PCR followed by qPCR. Similarly, for antibacterial study, cells were treated with LTP (2-8 min) and zone of inhibition, colony count assay and live/dead assay were performed.

Result
RSV immunofluorescence assay demonstrated that F-protein expression was decreased in RSV treated with LTP. Similarly, western blot showed decreased expression of F-protein in LTP treated RSV which was similar to positive control (VP-14637) (Fig.1). Likewise, qPCR on RSV F gene expression indicated 13 fold decrese in viral load with 5 min LTP treatment. *S. aureus* and *E.coli* treated with LTP showed Zone of Inhibition (ZOI) of 27 and 23 mm compared to 24 and 21 mm with Gentamicin respectively. Similarly, it was found that bacterial colony count decreased as exposure time of LTP increases (Fig. 2).

Conclusion
Our results indicate that LTP inhibited RSV and the studies bacteria S. aureus and E.Coli.

Acknowledgment
This work is supported by the NSF EPSCoR RII-Track-1 cooperative Agreement OIA-2128653.






Fig 2: Colony Count of bacteria after LTP treatment

D3 – P210

Terminally functionalized urethane oligomers containing quaternary ammonium groups for antimicrobial coatings

Hurck B.J.[1], Arts J.J.[1,2], Dias A.A.[3]
[1]Laboratory for Experimental Orthopedics, Dept. of Orthopaedic Surgery, Care and Public Health Research Institute (CAPHRI), Maastricht University Medical Centre; [2]Dept. Biomedical Engineering, Eindhoven University of Technology; [3]DSM-Firmenich, Geleen, The Netherlands

Introduction

Quaternary ammonium compounds (QACs) are well-established cationic antimicrobials that exert their bactericidal effect through contact-mediated disruption of bacterial membranes. Electrostatic interactions between the positively charged QACs and the negatively charged bacterial cell wall result in both bacterial adsorption as well as membrane disruption and subsequent bacterial cell death. These QA groups can be incorporated in polymers at various positions, either as terminal, pendant groups, or in the backbone of the polymer. In contrast to QACs in the pendant positions, the antimicrobial performance of polymers featuring QACs incorporated into the polymer at the terminal positions has been underexplored. In this study, QACs were incorporated in the terminal positions of a urethane oligomer, and its structure was varied to improve adhesion to metal, antibacterial properties, and biocompatibility.

Materials and Methods

The polymers were synthesized, characterized, and applied to titanium by dip-coating. Adhesion of a 10 wt% solution of the UOSME oligomers in Isopropanol was tested with Bromophenol Blue staining and a tape test. The antimicrobial effectiveness was tested with an *in-vitro* 24h proliferation assay, and the cytotoxicity was tested with a WST- and LDH-assay (ISO 10993-5). The chemical structure, modification, and application as coatings on titanium, along with their *in-vitro* antimicrobial and cytotoxicity properties, are presented here

Results

The structure of the UOSME oligomers was modulated by varying the length of the QAC alkyl group. Both structures were coated and, by the application of an appropriate primer layer, exhibited strong physical adhesion to a titanium substrate, as demonstrated by standardized tape adhesion testing. The coatings demonstrate very promising antibacterial properties of up to 6-log for an alkyl length of C16 (Figure 1) in 24h, but unfortunately, insufficient biocompatibility properties for both variations (Figure 2).

Conclusion

Incorporation of QACs in the terminal functional groups of a urethane-oligomer matrix enables the synthesis of a metal coating demonstrating promising antimicrobial properties. Several strategies are currently being investigated to reduce the cytotoxicity of the oligomer and improve biocompatibility prior to *in-vivo* testing.

Acknowledgements

This publication is part of the DARTBAC project (with project number NWA.1292.19.354) of the research program NWA-ORC, which is (partly) financed by the Dutch Research Council (NWO).




Figure 1: Preliminary antimicrobial results of 24h proliferation assay.




Figure 2: Preliminary cytoxicity results of a LDH-/WST assay (ISO 10993-5).

D3 – P211

Mesoporous silica nanoparticles reinforced electrospun methacrylated alginate fibers for modulated drug release

Srivastava M.G.[1], Cisneros C.G.[1], Zayed N.[2], Deknudt M.[1], Teughels W.[2], Braem A.[1], Mignon A.[1]
[1]Dept. of Materials Engineering, KU Leuven; [2]Dept. of Oral Health Sciences, KU Leuven, Belgium

Introduction

Biomedical drug delivery systems often face limitations such as local toxicity, suboptimal dosing and drug resistance due to poor control over drug concentration at target sites. Mesoporous silica nanoparticles (MSNs) have emerged as promising drug carriers owing to their exceptionally high surface area, tunable pore size and large pore volume, which enable high drug loading and controlled release. Their physicochemical properties can be precisely tailored during synthesis, while surface functionalization allows further adaptation for advanced delivery strategies. However, MSNs used alone may exhibit burst release caused by drug desorption from the particle surface. Incorporating MSNs into electrospun polymeric matrices offers an effective strategy to overcome this limitation.

Aim

In this study, MSNs were incorporated into electrospun methacrylated alginate fibers to enhance mechanical stability and modulate drug release.

Materials and Methods

MSNs were synthesized via a modified Stöber process and incorporated into methacrylated alginate fibers through electrospinning. The resulting fibers were subsequently UV-crosslinked and post-loaded with chlorhexidine (CHX) as a model antiseptic drug. The materials were comprehensively characterized to evaluate their structural, mechanical and functional properties. Fiber morphology and MSN loading was analyzed using scanning electron microscopy (SEM), while mechanical performance was assessed through compressive and tensile testing. Drug loading capacity and release behavior were investigated using thermogravimetric analysis (TGA), nitrogen physisorption, Fourier transform infrared spectroscopy (FTIR) and ultraviolet–visible (UV–Vis) spectroscopy. In addition, the antibacterial efficacy of the system was evaluated using a multispecies oral biofilm model and cytocompatibility was assessed to determine its suitability for biomedical use.

Results

Incorporation of MSNs into methacrylated alginate fibers significantly improved mechanical properties, increasing the compressive modulus by ~30% and nearly doubling the tensile modulus. Thermogravimetric analysis (TGA) confirmed increasing CHX loading from 6% to 40% with rising initial CHX concentrations (0.2–5 wt%). A corresponding increase in CHX release over 7 days was observed. Brunauer–Emmett–Teller (BET) analysis showed a ~62% reduction in surface area (from 847 to 319 $m^2 g^{-1}$) after CHX loading, confirming pore occupation. FTIR and TGA further verified CHX incorporation in both alginate and MSN–alginate fibers. CHX release from pure alginate increased with loading concentration, whereas interestingly, MSN-containing fibers exhibited an inverse trend, likely due to electrostatic interactions between positively charged CHX and negatively charged alginate and MSNs. Biofilm studies (qPCR and SEM) demonstrated effective inhibition for CHX-loaded systems. Cytocompatibility tests indicated no toxicity for CHX-free systems and highest compatibility at the lowest CHX loading, highlighting the balance between antimicrobial efficacy and cellular viability.

Conclusion

Methacrylated alginate electrospun hydrogels, reinforced with mesoporous silica nanoparticles (MSNs), were developed for controlled chlorhexidine release. MSN incorporation improved mechanical strength and modulated swelling and drug release via electrostatic interactions. The system showed dose-dependent antimicrobial activity, prolonged biofilm inhibition and good biocompatibility, highlighting its potential for tunable localized antimicrobial drug delivery.

D3 – P212

Antimicrobial ZnO(Al) layer deposition on ceramics, metals, glasses, polymers and textiles surfaces by laser treatment to prevent infections: Results from the ANTIRESI project

Hocquet S.
CRIBC, Mons, Belgium

Introduction

Infections remain a major challenge in orthopaedic and biomedical devices, but also in a large panel of domains (transport, animal farming, nursing homes, public facilities, agri-food, etc.) often leading to severe complications and revision surgeries.

Aim

The ANTIRESI project aims to develop innovative antimicrobial materials and surface treatments capable of preventing bacterial colonisation while maintaining the mechanical and functional properties required for biomedical applications.

Materials and Methods

Within this framework, the CRIBC research group focuses on the development of antimicrobial ceramic coatings and biomaterials for implant-related applications. One approach involves the deposition of aluminium-doped zinc oxide (ZnO:Al) coatings on metallic and ceramic substrates. These coatings are designed to combine antimicrobial activity with mechanical robustness and long-term stability. The coatings were produced using advanced deposition techniques and evaluated for their mechanical behaviour and stability under simulated service conditions. Preliminary results demonstrate good adhesion and mechanical resistance, including during impact and friction tests, highlighting their potential for durable antimicrobial surface treatments.

Results

Preliminary results demonstrate good adhesion and mechanical resistance, including during impact and friction tests, highlighting their potential for durable antimicrobial surface treatments. Biological validation of the developed materials is carried out using in vitro antimicrobial assays and experimental infection models targeting pathogens commonly involved in orthopaedic infections, such as *Staphylococcus aureus* and *Cutibacterium acnes*.

Conclusion

The results obtained so far highlight the potential of combining surface engineering, ceramic biomaterials and hybrid systems to design next-generation antimicrobial biomaterials. These developments contribute to the prevention of implant-associated infections and support the development of safer biomedical devices.

Acknowledgements

ANTIRESI (www.ANTIRESI-interreg.eu) is a project within the framework of INTERREG VI FWVL program (Accueil | Interreg) and ERDF funded, n°0100016. The consortium is composed of 8 partners (CRIBC, CER Groupe, SYMBIOSE-UMONS, CENTEXBEL, EURAMATERIALS, CRITT-MI, ITHEMM-URCA, BIOS-URCA and CERMATHS-UPHF) and one associated partner (MECATECH).

D3 – P213

Decellularized peripheral nerve allografts for nerve repair: findings from a rat model

Carriel V.[1,2]
[1]Dept. of Histology & Tissue Engineering Group, Faculty of Medicine, University of Granada; [2]Instituto de Investigación Biosanitaria, Ibs.GRANADA, Spain

Introduction

A substantial unmet clinical need persists for patients with critical nerve defects, especially when autografting is not an option. In this setting, tissue engineering provides a promising strategy to generate tissue-like models for diverse biomedical applications, including peripheral nerve repair[1]. Accordingly, this study aimed to design, develop, and preclinically characterize novel decellularized peripheral nerve allografts (DPNAs) for peripheral nerve repair.

Materials and Methods

This study evaluated protocols for generating DPNAs, assessing decellularization efficiency and *ex vivo* structural and biological properties compared to conventional DPNAs. These were used to repair 10- and 15-mm sciatic nerve defects in rats, with functional, neurophysiological, and histological outcomes assessed after 12–14 weeks.

Results

Ex vivo analyses confirmed effective decellularization, preservation of extracellular matrix and structural integrity in most DPNAs, particularly with novel chemo-enzymatic protocols. *In vivo*, these constructs supported muscle reinnervation, sensory recovery, and nerve regeneration in 10- and 15-mm defects. However, none outperformed autologous nerve grafts [2,3].

Conclusion

Overall, DPNAs generated using optimized chemo-enzymatic protocols demonstrate good structural preservation and support functional nerve regeneration across 10- and 15-mm defects, although recovery remains slower and slightly inferior to that achieved with autologous nerve grafts.

Acknowledgements

This study was supported by “Instituto de Salud Carlos III (ISCIII)” through the project No PI23/00337 and co-funded by the European Union and by the “Fundación Mutua Madrileña”, Grant No FMM-AP23014-2025).

References

[1]Carriel V. et al. Combination of fibrin-agarose hydrogels and adipose-derived mesenchymal stem cells for peripheral nerve regeneration. *J Neural Eng* 2023; Apr 10; 2; 026022.
[2]García-García O.D. et al. Comprehensive ex vivo and in vivo preclinical evaluation of novel chemo enzymatic decellularized peripheral nerve allografts. *Front Bioeng Biotechnol* 2023; Mar 30; 11; 1162684.
[3]Chato-Astrain J. et al. Detergent-based decellularized peripheral nerve allografts: An in vivo preclinical study in the rat sciatic nerve injury model. *J Tissue Eng Regen Med*. 2020; Jun 14; 6; 789-806.

D3 – P214
Innovative biomaterials in peripheral nerve repair

Raimondo S.[1], Fregnan F.[1], Muratori L.[1], Paravizzini G.[1], Orsini S.[2], Matino F.[2], di Leo N.[2], Persano l.[2], Tonazzini I.[2]
[1]Dept. of Clinical and Biological Sciences and Cavalieri Ottolenghi Neuroscience Institute, University of Turin, Orbassano; [2]Istituto Nanoscienze-Consiglio Nazionale delle Ricerche (CNR-NANO) @NEST- Scuola Normale Superiore, Pisa, Italy

Introduction
The repair and regeneration of peripheral nerve injuries represent a major research field where clinical application of innovative therapies in regenerative medicine should be sought. The more used surgical technique of repair is a primary end-to-end repair, while in nerve gap injuries, when tension precludes a primary repair, a nerve autograft is usually used to provide a scaffold for the regenerating nerve. The possibility of repairing nerve defects by bridging the gap by means of non-nervous scaffolds has been widely studied, both experimentally and in clinical practice. In this context, several studies about the employment of biomaterials for nerve repair were published.

Aim
The aim of this study was to evaluate *in vitro* and *in vivo* the efficacy of nano-structured piezoelectric polymeric membranes in poly(vinylidene fluoride) (PVDF), with different topographies, for the improvement of peripheral nerve regeneration.

Materials and Methods
In vitro analyses were performed using rat primary Schwann cells and dissociated dorsal root ganglia neurons cultured on PVDF nanofibers, with either random or aligned architecture. Morphological analysis and evaluation of cell alignment with respect to the orientation of the nanofibers and neurites elongation were performed. The quantification of β-NGF production was performed by ELISA assay, to evaluate the piezoelectric effect of the membranes on cells. Moreover, *in vivo* experiments were performed to test the regenerative capability of PVDF membranes with aligned architecture on cavernous nerve lesion in adult male rats.

Results
In vitro analysis using primary glial and neuronal cell models demonstrated the biocompatibility and the biomimeticity of the tested membranes. Moreover, the experiments demonstrated that cell behaviour (i.e. alignment, polarization) is influenced by the topography of the devices. Finally, *in vivo* analysis demonstrated that PVDF scaffolds support peripheral nerve regeneration in a preclinical model of cavernous nerve injury.

Conclusion
These results demonstrate that the piezoelectric and topographical properties of scaffolds can actively promote the response of neuronal and glial cells and support regenerative processes.

Acknowledgements
This research was funded by Italian Ministry of Research and University: PRIN Bando 2022, Project Development of nano/micro-engineered devices for applications in peripheral nervous system pathological models (ENGInerve).

D3 – P215

Generation and characterization of improved biogenic conduits for neural engineering applications

García-García O.D.[1,2], Escalante-Quirós S.[1], Llinares-Monllor C.[1], Semmler-Aranguiz I.[1,2], Etayo-Escanilla M.[1,2], Campos F.[1,2], Chato-Astrain J.[1,2], Carriel V.[1,2]
[1]Dept. of Histology & Tissue Engineering Group, University of Granada; [2]Instituto de Investigación Biosanitaria ibs.GRANADA, Spain

Introduction

Nerve autografts are the standard for repairing nerve injuries but face limits in availability and donor site complications. While biogenic conduits offer a promising alternative, they lack mechanical strength and can trigger immune responses. This study addresses these flaws by using decellularization and genipin cross-linking to create a stronger, non-immunogenic, and ready-to-use scaffold.

Materials and Methods

Biogenic conduits were generated by implanting silicone tubes subcutaneously into the dorsum of Wistar rats for [1]chemo-enzymatic decellularization protocol and chemically cross-linked with either 0.1% or 0.25% genipin. The resulting scaffolds were then characterized through comprehensive histological, structural, and biochemical evaluations. Additionally, their biomechanical properties were determined via tensile testing, and biological safety was validated using ex vivo cell biocompatibility and macrophage polarization (M1/M2) assays.

Results

Histological analysis confirmed that decellularization completely removed nuclear debris while preserving the structural integrity and collagen architecture of the extracellular matrix (ECM). Conduits matured for 8 weeks showed significantly better preservation of key ECM components. Furthermore, genipin (GP) cross-linking successfully enhanced the mechanical strength (break load and Young's modulus) of the scaffolds, providing the stability needed to withstand physiological forces. Crucially, these modifications maintained excellent cell biocompatibility and a favorable immunological profile, without altering macrophage polarization[1].

Conclusion

Combining a 2-month maturation period, decellularization, and genipin cross-linking yields a mechanically robust, biocompatible, and ready-to-use scaffold that serves as a promising alternative to traditional nerve grafts. However, future in vivo repair studies are required to fully evaluate its functional nerve regeneration potential.

Acknowledgements

This study was supported by "Instituto de Salud Carlos III (ISCIII)" through the project No PI23/00337 and co-funded by the European Union and by the "Fundación Mutua Madrileña", Grant No FMM-AP23014-2025).

References

[1]García-García Ó.D., Escalante-Quirós S., Llinares-Monllor C., Ávila-Fernández P., Sánchez-Porras D., Etayo-Escanilla M., Campos F., Chato-Astrain J., Carriel V. Novel genipin-crosslinked acellular biogenic conduits for tissue engineering applications. *Biomed Pharmacother* 2025; Jun; 187; 118064.

D3 – P216

Investigating the coefficient of friction of cartilage-on-PEEK OPTIMA™

Seth T.[1], Cowie R.M.[1], Briscoe A.[2], Jennings L.M.[1]
[1]Institute of Medical and Biological Engineering, School of Mechanical Engineering, University of Leeds; [2]Invibio Ltd, Thornton-Cleveleys, UK

Introduction

Cobalt chrome (CoCr) is the current gold standard material for the femoral component of total knee replacements however, potential issues with metal ion release into the patients' bloodstream have led to alternative materials being sought. PEEK-OPTIMA™ (a trademark of Invibio Ltd.) is a high-performance medical grade polymer being investigated as an alternative to metal. When the knee is replaced, the patella can be replaced or retained with an approximate 50:50 split between the two approaches. The friction of patella cartilage articulating against a PEEK femoral component in a patella retention application has not been comprehensively studied.
Aim: The aim of this study was to investigate the coefficient of friction (CoF) of cartilage-on-PEEK using a simple geometry pin-on-plate configuration and compare to conventional materials (cartilage-on-CoCr) and the native joint (cartilage-on-cartilage).

Materials and Methods

Studies were conducted as cartilage-on-PEEK and PEEK-on-cartilage to understand the influence of different configurations on friction (Table 1). Bovine cartilage samples were dissected from the patella (pins) or the femur (plates); highly polished CoCr and PEEK samples were of similar initial surface roughness. Uniaxial motion at 0.5Hz and 1 MPa contact pressure was used approximating the conditions in the natural patella-femoral joint. 25% newborn calf serum with Ringer's solution was used as a lubricant for the 3-hour studies. CoF was measured using a piezoelectric sensor and the mean ± 95% confidence limits calculated at 180 minutes for each experimental group. Statistical analysis was conducted using one-way ANOVA and a post hoc Tukey's test ($p<0.05$).

Results

For the negative control (cartilage-on-cartilage) and when the material of interest (PEEK or CoCr) was the pin, the CoF was low (<0.02, Table 1) demonstrating the ability of the cartilage to maintain fluid pressurisation and a low CoF when artificial materials articulate against it with a small contact area. However, when cartilage pins were articulated against PEEK or CoCr plates, there was an order of magnitude increase in the CoF, likely due to the constant loading of the cartilage pin preventing the cartilage from rehydrating and hence the load being supported by the solid phase of the cartilage rather than the fluid. The friction of cartilage-on-CoCr was significantly higher than cartilage-on-PEEK ($p<0.05$).

Conclusion

The behaviour of PEEK and CoCr when articulated against cartilage in simple geometry was similar, but with a significantly lower CoF of cartilage-on-PEEK compared to cartilage-on-CoCr showing promise for natural patella retention in an all-polymer knee replacement.

Acknowledgements

This research was funded through an EPSRC Prosperity Partnership (Grant reference: EP/Y528924/1).

Table 1: The coefficient of friction of different material configurations at 180 minutes with 95% confidence limits.

Experimental group	N	Pin	Plate	Coefficient of friction at 180 minutes with 95% CL
1: Negative control	6	Bovine patella cartilage	Bovine femur cartilage	0.019 ± 0.003
2: Conventional materials	6	Bovine patella cartilage	Cobalt chrome	0.284 ± 0.063
3: Materials of interest	6	Bovine patella cartilage	PEEK OPTIMA™	0.234 ± 0.017
4: Conventional materials	6	Cobalt chrome (100 mm radius of curvature)	Bovine femur cartilage	0.016 ± 0.006
5: Materials of interest	6	PEEK OPTIMA™ (100 mm radius of curvature)	Bovine femur cartilage	0.014 ± 0.001

D3 – P217

Challenges of melt electrowriting of electroactive polylactide scaffolds for bone regeneration

Schönlein R.[1,2,3], Larrañaga X.[1], Panfilo A.[1], Lanceros-Méndez S.[2,3,4], Ugartemendia M.J.[1]
[1]Group of Science and Engineering of Polymeric Biomaterials (ZIBIO Group), Dept. of Mining, Metallurgy, Engineering and Materials Science, POLYMAT, Bilbao School of Engineering, University of the Basque Country (UPV/EHU), Spain; [2]BCMaterials, Basque Center for Materials, Applications and Nanostructures, UPV/EHU Science Park, Leioa, Spain; [3]CF-UM-UP − Physics Centre of Minho and Porto Universities and LaPMET − Laboratory of Physics for Materials and Emergent Technologies, University of Minho, Braga, Portugal; [4]IKERBASQUE, Basque Foundation for Science, Bilbao, Spain

Introduction

Piezoelectric biodegradable polymers offer a unique route to mimic bone's electromechanical environment by converting mechanical loads into bioelectrical stimuli. Poly(L-lactide) (PLLA) is particularly promising, being biodegradable, biocompatible, FDA-approved and intrinsically piezoelectric when molecular chains are oriented.[1,2] However, conventional electrospinning produces random 2D mats, and achieving oriented 3D electroactive architectures remains challenging.[3] Melt electrowriting (MEW) enables strong melt elongation during processing, making it a promising technique to directly induce piezoelectric chain orientation in PLLA from the melt, but processing electroactive PLLA is challenging due to its fast chain relaxation time and narrow thermal stability window.[4]

Materials and Methods

This study focuses on identifying suitable material grades and processing windows to enable molecular chain orientation in PLLA during MEW. Printing temperature, voltage, and collector speed were systematically optimized to minimize thermal degradation and to maximize the electroactive phase. As shown in Figure 1, the robustness of the MEW process was increased, indicated by improved quality of the 2nd and 3rd scaffolds after process optimization. The resulting scaffolds were characterized by SEM, XRD, Raman, PLOM and DSC to correlate fiber morphology, crystallinity, and chain orientation. Piezoelectric response was assessed under cyclic mechanical loading, measuring the voltage output.

Results

Controlled MEW processing within a defined stability window enabled improved process robustness in fiber deposition and enhanced chain orientation despite significant molecular weight loss. Decreased nozzle temperature and increased collector speed led to greater molecular chain orientation. Post-annealing increased the crystallinity, thus the piezoelectric properties. Relating to the chain orientation and crystallinity, the PLLA scaffolds exhibited a correlated piezoelectric coefficient of ~6 pC/N.

Conclusion

Optimizing MEW parameters for PLLA successfully balanced thermal stability and molecular chain orientation, leading to electroactive scaffolds. The defined processing window and material selection provide a foundation for manufacturing PLLA-based piezoelectric 3D scaffolds for bone regeneration.

Acknowledgements

Basque Government (consolidated research groups GIC IT1766-22 and IT1503-22); Spanish Gov. MICINN (PID2019-106236GB-I00/AEI/10.13039/501100011033); Project BIOIMP_ACE_MAS_6_E Interreg

References

[1]Das R. et al. Osteo-Inductive Effect of Piezoelectric Stimulation from the Poly(l-Lactic Acid) Scaffolds. *PLoS One* 2024; 19 (2); e0299579.
[2]Schönlein R. et al. Piezoelectric Polylactic Acid-Based Biomaterials: Fundamentals, Challenges and Opportunities in Medical Device Design. *Biomaterials* 2026; 324; 123522.
[3]Das R. et al. Biodegradable Nanofiber Bone-Tissue Scaffold as Remotely-Controlled and Self-Powering Electrical Stimulator. *Nano Energy* 2020; 76; 105028.
[4]Schönlein R. et al, Flow--Induced Crystallization of Piezoelectric Poly(L-Lactide) Fibers by a One--Step Melt--Spinning Process. *Mater. Des.* 2023; 112525.




Figure 6. Influence of increasing residence time of polymer melt in syringe MEW device on scaffold quality and process robustness before and after material and process optimization.

D3 – P218

Electrospun silk-PVDF core-shell fibres for tunable piezoelectricity and guided cell alignment

Kulkarni G.[1], Navarro Pons M.[1], Lefaix L.[1], Bagur L.[1], Blanquer A.[2], Murillo G.[1]
[1]Institute of Microelectronics of Barcelona (IMB-CNM, CSIC), Barcelona; [2]Universitat Autònoma de Barcelona (UAB), Bellaterra, Spain

Introduction

Electrospun fibrous scaffolds integrating natural and synthetic polymers offer a promising strategy to combine biological functionality with electroactive properties. Silk fibroin (SF) provides excellent cytocompatibility, while poly(vinylidene fluoride) (PVDF) exhibits piezoelectric behavior. However, achieving well-defined core-shell architectures remain challenging due to solvent incompatibility, viscosity mismatch, and interfacial mixing during electrospinning. This study aims to optimize processing conditions for stable SF core-PVDF shell fibre fabrication and to evaluate their structural and electromechanical behavior.

Materials and Methods

SF (15 wt%) with polyethylene oxide (0.25 wt%) was prepared in formic acid, while PVDF (17 wt%) was dissolved in a 4:6 DMF: Acetone system. Electrospinning was performed using both single-phase and coaxial configurations. Key parameters, including flow rate, voltage, and needle configuration, were systematically optimized to promote stable Taylor cone formation and core confinement. Fibre morphology was assessed using SEM, while TEM was used to probe internal structure. FTIR and XRD were employed to evaluate chemical composition and crystallinity. Piezoelectric response was measured using a custom-built setup and interpreted alongside COMSOL simulations. Cytocompatibility was assessed using normal human dermal fibroblasts (NHDF) via viability assays and live-cell imaging.

Results

Stable fibre formation was achieved for SF, PVDF, and coaxial systems. Optimization revealed that lower core flow rates (0.05-0.08 mL/h), combined with moderate shell flow (0.3-0.5 mL/h), improved jet stability and promoted core confinement. SEM (Fig. 1a) of randomly oriented core-shell fibres showed uniform, bead-free fibres with diameters of 100-150 nm.

COMSOL simulations provided insight into the electromechanical response. Line profile analysis across the fibre diameter (Fig. 1b) revealed that the presence of the SF core alters stress and potential gradients within the PVDF shell, indicating modified mechanical-electrical coupling. Electric potential maps (Fig. 1c) showed comparable voltage magnitudes between PVDF and core-shell fibres; however, the core-shell architecture significantly altered the spatial distribution of the electric field.

FTIR and XRD analyses were dominated by PVDF signatures, suggesting shell enrichment at the fibre surface. All scaffolds, including SF, PVDF, and core-shell, supported cell viability (>90%). Aligned SF fibrous scaffolds demonstrated clear guidance of fibroblasts, with pronounced elongation along the fibre direction (Fig. 1d).

Conclusion

This study demonstrates that stable SF-PVDF core-shell fibres can be achieved through careful control of electrospinning parameters, particularly flow rate and viscosity balance. Rather than increasing voltage output, the core-shell architecture modulates stress transfer within the piezoelectric phase, enabling control over electromechanical behaviour. Combined with cytocompatibility and alignment-induced cell guidance, these scaffolds present a promising platform for bioelectromechanical tissue engineering.




Figure 1. (a) SEM image of randomly oriented electrospun core-shell fibres (scale bar: 500 nm). (b) COMSOL simulation showing stress distribution across a single fibre. (c) Electric potential profiles for SF, PVDF, and core–shell fibres, highlighting differences in electromechanical response. (d) SEM image of fibroblasts cultured on aligned SF fibres, demonstrating cell alignment and guidance along the fibre direction (scale bar: 50 µm).

D3 – P219

Designing novel biodegradable peptide hydrogel scaffolds for cultured meat production

Chauhan N.[1,3], Saiani A.[2,3], Miller A.F.[1,3]
[1]Dept. of Chemical Engineering, the University of Manchester; [2]Division of Pharmacy and Optometry, the University of Manchester; [3]Manchester Institute of Biotechnology, the University of Manchester, UK

Introduction

With the rising demand for sustainable protein sources, cultured meat has emerged as a promising alternative to conventional livestock production. However, despite advances in cell expansion and bioprocessing, generating structured, meat-like tissues remains a significant scientific and engineering challenge. A key limitation is the lack of edible, biocompatible, and mechanically tunable scaffolds capable of supporting large-scale cell expansion and organised tissue formation. Many current scaffold systems lack sufficient tunability, food compatibility, or scalability for cellular agriculture applications[1]. Self-assembling peptide hydrogels (SAPHs) provide a biodegradable and chemically defined scaffold platform with inherent biocompatibility, edibility, and adjustable mechanical properties, with significant potential as a scaffold for cultured meat[23].

Aim

Through this project, we aim to develop novel biodegradable SAPHs that enable microbead-assisted bovine and porcine muscle and fat cell expansion and support 3D bioprinting of structured cultured meat constructs.

Materials and Methods

Peptide hydrogels were prepared by dissolving peptide powder in HPLC-grade water, followed by vortex mixing and pH adjustment to ~7 using NaOH. Salt effects on hydrogel and microbead stability were evaluated using NaCl or $CaCl_2$ at concentrations ranging from 0.1 to 2 M. The peptide hydrogel-salt mixtures were incubated at 4°C for 24 hours to allow complete network formation. Microbeads were generated by using a syringe pump from the optimised hydrogel formulation. For cellular studies, murine C2C12 myoblasts were encapsulated within SAPH microbead-containing hydrogels using a 3D encapsulation approach and cultured at 37 °C, with cell viability assessed using live/dead assays. Mechanical, chemical, and structural characterisation were conducted to confirm peptide self-assembly and network morphology.

Results

Salt concentration significantly affected the stability of the hydrogel and microbeads. As cell culture media contain salts that could potentially stabilise peptide microbeads, salt-triggered gelation was first investigated. An optimised NaCl concentration of 0.5 M produced stable hydrogels and enabled uniform microbead formation without sedimentation or structural disruption. Using this formulation, stable SAPH microbeads were successfully obtained in cell culture media. Encapsulation of C2C12 myoblasts supported high cell viability and enhanced proliferation. Rheological analysis confirmed mechanically stable hydrogel networks suitable for 3D cell culture and biofabrication, while structural characterisation using FTIR, circular dichroism (CD), SAXS and TEM verified peptide self-assembly and nanostructure formation.

Conclusion

SAPHs microbeads provide a biodegradable and structurally stable scaffold platform for enhanced myoblast expansion. The microbead-assisted system promotes efficient cell proliferation, supporting scalable bioreactor expansion. Next, we plan to develop SAPH's bioink for printing structured meat.

References

[1]Chriki S., Hocquette J.F. The Myth of Cultured Meat: A Review. *Front Nutr* 2020; 7; 7.
[2]Fu K., Wu H., Su Z. Self-assembling peptide-based hydrogels: Fabrication, properties, and applications. *Biotechnol* 2021; Adv 49; 107752.
[3]Wang X., Wang M., Xu Y. et al. A 3D-printable gelatin/alginate/ε-poly-l-lysine hydrogel scaffold to enable porcine muscle stem cells expansion and differentiation for cultured meat development. *Int J Biol Macromol* 2024; 271; 131980.

D3 – P220

Designing peptide hydrogels as vehicles for targeted and localised in vivo therapeutic delivery

Mazhar S.[1,2], Elsawy M.[1], Finegan K.[1], Saiani A.[1,2]
[1]Faculty of Biology, Medicine and Health, School of Health Sciences, Dept. of Pharmacy and Optometry, the University of Manchester; [2]Manchester Institute of Biotechnology, University of Manchester, UK

Introduction

Breast cancer is the second leading cause of death in women. Triple-negative breast cancer (TNBC) has a unique molecular profile, is aggressive and has high relapse rates. TNBC is primarily treated with chemotherapy, commonly using doxorubicin (DOX); however, it is cardiotoxic and leads to severe side effects when delivered systemically through intravenous, leading to long-term health complications for patients. Self-assembling peptide hydrogels (SAPHs) offer a promising solution for the delivery of chemotherapy drugs, such as DOX, directly in-situ to solid tumours via injection, potentially reducing drugs' adverse systemic effects and improving their efficacy (1).

Aim

This project aims to design an injectable SAPH for the local and controlled delivery of DOX to treat solid tumours.

Materials and Methods

For this study, we selected two peptide designs with opposite charge: $K(FEFKK)_2K$ (pH 7, +2 charge) and $EE(FKFE)_2EE$ (pH 7, -3 charge). Peptide solutions were prepared at 20mg/ml and pH 3, and gelation was then triggered via NaOH addition by adjusting the samples' pH to 7. The SAPHs were loaded with 0.1mg/ml Doxorubicin (pH 7, +1 charge). The hydrogel's mechanical properties, with and without drug, were quantified using oscillatory rheology (1% strain, 1Hz). The cumulative release of DOX from the hydrogels into PBS was assessed via UV-Vis spectroscopy. Additionally, DOX release from hydrogels was tested in vitro on 4T1 (murine) and MDA-MB-231 (human) cells using their respective DOX IC50 concentrations over 72 hours. Cell viability was measured using CellTiter Glo.

Results

We observed a higher amount of DOX being released from $K(FEFKK)_2K$ (95 ± 8 %) compared to $EE(FKFE)_2EE$ (39 ± 3 %) after 96 hours, likely due to the repulsive electrostatic interactions between the positively charged DOX and the positively charged peptide fibres. We also showed that peptide charge influences the morphology of MDA-MB-231 and 4T1 cells when cultured in the presence of peptide fibrillar aggregates. $K(FEFKK)_2K$ induced morphological changes, including filopodia formation and cell polarisation, features associated with increased migratory rather than proliferative behaviour.

Conclusion

Overall, the findings highlight the potential of SAPHs as a tunable drug-delivery platform for the in-situ delivery of cancer therapeutics, while also emphasising the importance of drug-biomaterial interactions on cell behaviour. Future work will focus on investigating the in vivo delivery of DOX using the SAPHs developed in a small-animal TNBC solid-tumour model. We will investigate whether delivery of DOX using SAPHs decreases systemic side effects while still shrinking or eliminating the solid tumours.

Acknowledgements

Funding for this project is provided by the UKRI Medical Research Council (MRC) doctoral training partnership (DTP) – CASE studentship PhD programme

References

[1]Elsawy M.A., Wychowaniec J.K., Castillo Diaz L.A., Smith A.M., Miller A.F., Saiani A. Controlling Doxorubicin Release from a Peptide Hydrogel through Fine-Tuning of Drug–Peptide Fiber Interactions. *Biomacromolecules* [Internet]. 2022 Jun 13 [cited 2023 Aug 23];23(6):2624–34. Available from: https://www.sciencedirect.com/org/science/article/pii/S1525779722005797

D3 – P221

Multiscale and multiphysics characterization of hydrogels for tissue engineering applications: Bridging material properties and biological performance

Alamán Díez P.[1,2], García-Villagrasa L.[1,2], Calderon-Villalba A.[1,2], Villarroya F.[1], Horta L.[1], García-Gareta E.[1,2,3], García-Aznar J.M.[1,2]

[1]Multiscale in Mechanical & Biological Engineering Research Group, Aragon Institute of Engineering Research (I3A), School of Engineering & Architecture, University of Zaragoza, Spain; [2]Aragon Institute for Health Research (IIS Aragon), Miguel Servet University Hospital, Zaragoza, Spain; [3]Division of Biomaterials & Tissue Engineering, University College London Eastman Dental Institute, University College London, UK

Introduction

Biomimetic hydrogels derived from natural extracellular matrix (ECM) components are widely used in tissue engineering due to their ability to replicate key biochemical and structural features of native tissues. However, the performance of these materials as biological models strongly depends on the physicochemical properties, such as, rheological behavior, permeability, swelling ratio, microstructure, and degradation dynamics. A comprehensive characterization approach is therefore essential to establish architecture–property–function relationships that guide the rational design and application of hydrogel-based systems. In this work, we present a multiscale and multiphysics characterization framework applied to a range of natural hydrogels commonly used in tissue engineering models, ranging from collagen-based matrices, basement membrane extracts (BME), to different decellularized extracellular matrices.

Materials and Methods

Hydrogels were analyzed using an integrated set of mechanical, structural, physicochemical, and biological characterization techniques. Mechanical properties were evaluated through rheological analysis and permeability measurements to assess viscoelastic behavior and transport characteristics. Microstructural and ultrastructural features were investigated using scanning electron microscopy (SEM) and focused ion beam SEM (FIB-SEM) to quantify pore architecture and network organization. Complementary physicochemical analyses included swelling behavior, degradation studies, and spectroscopic characterization to evaluate matrix stability and composition. Biological performance was assessed through cytocompatibility assays and through evaluation of angiogenic responses using the *ex ovo* chick chorioallantoic membrane (CAM) model.

Results

The combined and integrated analyses revealed clear correlations between hydrogel microstructure, biomechanical properties, and biological performance. Variations in fiber organization and pore architecture significantly influenced hydrogel permeability and viscoelastic behavior, which in turn affected cellular compatibility and angiogenic responses. Hydrogels displaying interconnected porous networks and intermediate stiffness supported enhanced vascularization in the CAM model compared with denser or mechanically limited matrices. These results highlight the importance of integrating structural, biomechanical and biological analysis when selecting hydrogels for specific tissue engineering applications.

Conclusion

This methodology demonstrates the value of a multiscale and multiphysics characterization strategy to comprehensively evaluate biomimetic hydrogels used in tissue engineering. By linking material microarchitecture, mechanical behavior, and biological response, this framework provides relevant insights for the selection and optimization of hydrogel systems in advanced in vitro and in vivo-like models. Such approaches can contribute to improving the predictive capacity and translational relevance of hydrogel-based tissue engineering platforms.

Acknowledgements

This work is part of a project that has received funding from the European Research Council (proof of concept HYMATE grant agreement No 101248308).

D3 – P222

Laser-induced graphene biohybrid substrates for bioelectronics

Almeida H., Pinheiro T., Barata M., Monteiro G., Calmeiro T., Ureña C., Igreja R., Martins R., Fortunato E.
CENIMAT|i3N, Dept. of Materials Science, School of Science and Technology, NOVA University Lisbon and CEMOP/UNINOVA, Caparica, Portugal

Introduction

Cardiovascular and skeletal muscle disorders remain leading causes of mortality and morbidity worldwide, underscoring the urgent need for advanced regenerative medicine strategies. Although muscle tissue engineering has shown significant promise, the limited maturation of stem cell-derived cardiomyocytes and myogenic cells in vitro remains a major bottleneck. Conductive biomaterials have emerged as key regulators of electromechanical coupling and cellular phenotype; however, conventional graphene-based platforms often suffer from complex synthesis routes, limited sustainability, and cytotoxic concerns. Laser-induced graphene (LIG) offers a scalable, environmentally friendly alternative, enabling the fabrication of conductive and biomimetic substrates suitable for regenerative applications.

Materials and Methods

LIG was fabricated via direct laser writing using distinct biopolymer-based precursors, including parylene-C, collagen-derived gelatin, and agarose-lignin membranes. Laser processing parameters were optimized to generate anisotropic, sp^2-rich carbon architectures. Structural, chemical, and electrical properties were assessed using Raman spectroscopy, XPS, SEM, and sheet resistance measurements. The biological performance of the substrates was evaluated using pluripotent stem cells, embryoid bodies, induced pluripotent stem cell-derived cardiomyocytes, and C2C12 myoblasts. Cell viability, metabolic activity, morphology, protein expression, and contractile behavior were analyzed, including the impact of external electrical stimulation.

Results

All LIG-based substrates demonstrated excellent cytocompatibility, maintaining cell viability and metabolic activity throughout culture. Electrical characterization revealed conductivities comparable to native cardiac tissue, with thinner and more porous LIG layers exhibiting enhanced performance. Cardiomyocytes derived from embryoid bodies displayed spontaneous contractile activity and expressed cardiac-specific proteins, including α-actinin. Similarly, myoblasts cultured on conductive agarose-lignin LIG substrates showed improved survival, early alignment, and myogenic organization, particularly under electrical stimulation. Crosslinking and functionalization strategies enabled substrate stabilization while preserving bioelectrical functionality.

Conclusion

This work demonstrates that sustainable LIG-based biohybrid substrates effectively replicate key electrical and structural features of the native muscle extracellular matrix, promoting functional maturation in both cardiac and skeletal muscle models. These platforms represent a versatile and transformative class of biomaterials for regenerative medicine, with strong potential for disease modeling, drug screening, and future translational therapies.

Acknowledgements

The authors acknowledge the financial support of the Portuguese Recovery and Resilience Plan (PRR) through the projects Pacto Bioeconomia Azul (BlueBio; C644915664-00000026) and From Fossil to Forest (FF2F; PC644920945-00000036).

D3 – P223

Engineering bioinks for urethral tissue engineering through a tissue-informed approach

Shajahan A.B.[1], Alexandris S.[2], Pien N.[3], Jing R.[4], Martinier I.C.[5], Christiansen J.C.[1], Porsborg S.[1], Nielsen, T.T.[4], Larsen K.L.[4], Van Vlierberghe S.[3], de Graaf P.[5], Pennisi C.P.[1]
[1]Dept. of Health Science and Technology, Aalborg University, Denmark; [2]Dept. of Materials and Production, Aalborg University, Denmark; [3]Dept. of Organic and Macromolecular Chemistry, Ghent University, Belgium; [4]Dept. of Chemistry and Bioscience, Aalborg University, Denmark; [5]Dept. of Urology, Regenerative Medicine Center Utrecht, University Medical Center Utrecht, The Netherlands

Introduction

Urethral tissue engineering remains challenging due to the complex structural and mechanical properties of native tissue. Bioprinting presents a promising strategy for fabricating functional urethral constructs; however, current bioinks fail to replicate native tissue characteristics adequately. Here, we propose a tissue-informed bioink design strategy based on detailed biomechanical and histological characterisation of healthy urethral tissue to establish benchmarks for bioink development (Fig.1)




Fig.1 Overview of the tissue-informed bioink design strategy for urethral regeneration.

Materials and Methods

Healthy rabbit urethral tissues were analysed in cross-sectional and longitudinal orientations. Microscale mechanical properties were evaluated on 100 µm sections using nanoindentation to assess viscoelastic behaviour. Histological analyses (8 µm sections) included haematoxylin and eosin (morphology), fast green (collagen), and orcein (elastin). Bioinks were developed using dextran- and gelatine-based hydrogels with hybrid formulations generated by combining both systems. Gelation kinetics and viscoelastic properties were characterised by UV-assisted photorheology. Hydrogels with optimised photorheological and mechanical properties were subsequently evaluated for cytocompatibility using human dermal fibroblasts through elution and direct-contact assays, LDH cytotoxicity, proliferation, and live/dead staining.

Results

Native urethral tissue exhibited heterogeneous Young's moduli (~2.8–10 kPa), indicating spatial mechanical variability. Frequency sweep analysis confirmed a predominantly elastic response. Hydrogel properties were tunable through polymer concentration, molecular weight, and degree of substitution. Functionalised dextran combined with bifunctional gelatine yielded a mechanically stable and reproducible hybrid hydrogel (GelSH–DexNB). The hybrid hydrogels prepared at 5%, 7.5%, and 10% polymer concentrations exhibited shear-thinning behaviour suitable for extrusion-based bioprinting. Selected hydrogel candidates were further evaluated for cytocompatibility, demonstrating low cytotoxicity, sustained cell proliferation, and high cell viability, with optimal performance observed for 5% hybrid formulations. Based on these findings, optimised bioink candidates were advanced for in vivo evaluation in a rabbit model.

Conclusion

This study establishes a tissue-informed framework for designing hydrogel bioinks that recapitulate native urethral properties. The developed supramolecular systems exhibit tunable mechanical properties, printability, and cytocompatibility, supporting their potential for the fabrication of tubular scaffolds for preclinical urethral tissue engineering.

Acknowledgements

This work was funded by the European Union's Horizon Europe programme (STRONG-UR, grant agreement No. 101191695). The views expressed are those of the authors and do not necessarily reflect those of the European Union or HaDEA.

D3 – P224

Building vascularized tubular tissues: A biomaterial-centered approach to urethral reconstruction

Mykuliak A.[1], Evans Austin D.[2], Oommen P.,[3], Gebraad A.[1,4], Miettinen S.[1]
[1]Adult Stem Cell Group, Faculty of Medicine and Health Technology. Tampere University, Finland; [2]Bioengineering and Nanomedicine Group, Faculty of Medicine and Health Technology, Tampere University, Finland; [3]School of Pharmacy and Pharmaceutical Sciences, Cardiff University, UK; [4]Biomedical Spectroscopy Laboratory, Dept. of Technical Physics, University of Eastern Finland, Kuopio, Finland

Introduction

Current urethral tissue engineering strategies are limited by an overemphasis on epithelial coverage, while long-term clinical outcomes depend on successful regeneration of the underlying vascularized stroma. Insufficient vascular integration leads to hypoxia, fibrosis, and stricture formation, particularly in large defects. Therefore, functional urethral reconstruction requires coordinated regeneration of urothelial cells (hUCs), stromal components, and a perfusable vascular network. The aim of this study was to develop and evaluate a biomaterial platform capable of supporting microvascular network formation and providing a foundation for integrating urothelial and stromal cell compartments for urethral tissue engineering.

Materials and Methods

A blue light-crosslinked fibrin–hyaluronan composite hydrogel was engineered by incorporating gallic acid-functionalized hyaluronic acid (HAGA) into fibrin matrices at varying concentrations. Human umbilical vein endothelial cells (HUVECs) were co-cultured with human bone marrow-derived mesenchymal stromal cells (hBMSCs), selected for their strong pro-angiogenic capacity, to induce vascular network formation. Cell viability, proliferation, and hydrogel stability were assessed over three weeks. Quantitative analysis of vascularization included network area coverage, total vessel length, and basement membrane deposition. Functional vascularization was evaluated using microfluidic platforms to assess perfusability and flow responsiveness. Material formulations were compared to identify conditions that balance structural stability and angiogenic potential.

Results

All hydrogel formulations supported high cell viability and proliferation. Incorporation of HAGA significantly reduced hydrogel contraction and improved structural stability compared to fibrin alone. Hydrogels with intermediate HAGA concentrations supported significantly greater vascular network formation, as evidenced by increased vessel length and network coverage, whereas higher concentrations impaired angiogenesis. Co-culture with hBMSCs enabled robust and stable microvascular network formation, consistent with their pro-angiogenic role. Perfusable and interconnected vascular networks were successfully established in microfluidic systems, demonstrating functional lumen formation. The platform also supported extracellular matrix deposition, indicating its suitability for stromal tissue development.

Conclusion

This study demonstrates that tuning hydrogel composition enables the formation of stable, perfusable vascular networks while maintaining a microenvironment supportive of stromal function. The use of hBMSCs as a pro-angiogenic component further enhances vascularization potential. These features are essential for engineering vascularized tubular tissues for urethral reconstruction. Future work should integrate hUC and stromal compartments within this platform and leverage bioprinting for spatial organization of multilayered tubular structures. Microfluidic systems provide physiologically relevant in vitro models to study perfusion, remodeling, and epithelial–stromal interactions, offering valuable insights for optimizing scaffold design and cell integration strategies. Together, these approaches support the development of prevascularized, clinically translatable urethral grafts.

D3 – P225

Experimentally calibrated and validated finite element model for the biomechanical assessment of intraocular lenses

Bucca Puy R.[1,2], Boldrin J.[2], Pagnoulle C.[1], Geris L.[2]
[1]Research and Development, BVI Medical, Liège; [2]Biomechanics Research Unit, GIGA In Silico Medicine, University of Liège, Belgium

Introduction

The global prevalence of myopia and cataracts is increasing, resulting in a growing demand for intraocular lens (IOL) implantation. Several preclinical approaches are used to evaluate IOL performance, including ISO mechanical tests, artificial eye models, *ex vivo* implantation, and finite element method (FEM) simulations. However, these methods only partially reproduce the physiological biomechanical environment of the human eye. Moreover, IOL biomaterials are soft, highly compliant, and exhibit nonlinear mechanical behaviour, making accurate material characterization under hydrated conditions particularly challenging. This study aimed to develop and validate a finite element model of an IOL test bench using experimentally characterized material properties to predict IOL biomechanical behaviour.

Materials and Methods

The study comprised three stages. First, a literature-based *in vivo* analysis was conducted to identify the physiological constraints acting on implanted IOLs. Second, the ISO 11979-3 haptic radial compression test was reproduced *in vitro* to obtain reference measurements of reaction forces and axial displacements. Third, an *in silico* FEM model was developed in ANSYS Workbench and Mechanical to replicate the experimental setup and predict reaction forces, axial displacement, optic deformation, contact angle, and stress distribution. The experimentally calibrated hyperelastic constitutive model was obtained from stress-strain data acquired through uniaxial tensile tests on dogbone specimens under hydrated conditions (Lloyd UTM). The complete FEM model was subsequently validated by comparing its predictions with experimental results obtained from a FineVision HP IOL (BVI Medical) tested in a CellScale MicroSquisher according to ISO 11979-3.

Results

The calibrated constitutive model accurately reproduced the uniaxial tensile behaviour of the IOL material. Using these calibrated material properties, the FEM model predicted reaction force and axial displacement during radial compression with good agreement with the experimental measurements, demonstrating successful model validation.

Conclusion

This verified and validated FEM model demonstrates that reliable prediction of IOL biomechanical behaviour depends on accurate characterization of nonlinear hydrated biomaterials. The proposed framework supports future IOL design optimization and enables the incorporation of physiological parameters, such as capsular bag interactions and tissue compliance, for more realistic virtual preclinical assessment.

D3 – P226

Ex vivo permeation and skin deposition of mometasone furoate-loaded nanostructured lipid carriers for localised topical delivery in psoriasis

Adekola P., Conway B., Adebisi A.
Dept. of Pharmacy, University of Huddersfield, UK

Introduction

Mometasone furoate (MF) is a potent corticosteroid used topically in psoriasis, where the target lies within the epidermis and dermis. However, delivery is challenging because MF has poor aqueous solubility and has a molecular weight of 521 Da, above the ~500 Da threshold for efficient stratum corneum permeation[1]. Nanostructured lipid carriers (NLCs) may address this by solubilising MF in a lipid matrix, enhancing interaction with the skin lipid barrier and promoting localised deposition while limiting unnecessary systemic permeation[2]. This study evaluated ex vivo permeation and skin deposition of MF-NLCs across porcine skin compared with free MF suspension and marketed MF cream.

Aim

This study evaluated ex vivo permeation and skin deposition of MF-NLCs across porcine skin compared with free MF suspension and marketed MF cream.

Materials and Methods

Several MF-NLC formulations were generated from the design of experiments study, and four candidate formulations, coded F4–F7, were selected based on their physicochemical performance. These formulations were compared with free MF suspension and marketed MF cream using excised porcine skin mounted on Franz diffusion cells (area 3.142 cm^2; 20 mm orifice). The receptor contained 15 mL phosphate buffered saline 7.4 with 0.5% w/v Tween 80 at 37 °C under continuous stirring. Equivalent nominal MF dose was applied. Receptor samples collected over 24 h were replaced with fresh medium and quantified by validated HPLC. Cumulative permeation and skin deposition were expressed as percentages of applied dose, and steady state flux (Jss) was calculated from the linear region. Studies were performed in triplicate (n = 3).

Results

The marketed cream gave the highest 24 h cumulative permeation (17.28%), followed by suspension (6.82%), whereas the NLCs permeated far less (F4 2.31%, F5 2.83%, F6 3.13%, F7 1.86%). Flux followed the same trend, with cream and suspension (6.85 and 3.04 $\mu g \cdot cm^{-2} \cdot h^{-1}$) exceeding the NLCs (0.81–1.18 $\mu g \cdot cm^{-2} \cdot h^{-1}$). In contrast, skin deposition was markedly higher for the NLCs (F4 73.77 ± 0.13%, F5 64.05 ± 0.06%, F6 51.58 ± 0.13%, F7 67.80 ± 0.11%) than cream (10.11 ± 0.06%) or suspension (6.55 ± 0.04%), representing up to an ~11 fold increase in cutaneous retention. The deposition to permeation ratio favoured F7 (36.4) and F4 (31.9) over cream (0.6) and suspension (1.0), indicating a skin retentive profile.

Conclusion

MF-loaded NLCs enhanced localised cutaneous deposition while limiting transdermal permeation compared with marketed cream and free drug suspension. This profile is more suitable for topical psoriasis therapy, where local retention is preferred over systemic movement. F4 and F7 emerged as lead formulations for further development.

References

[1]Jia W., Pang Y., Zhao C., Cai Y., Zhang Y., Liu C., Fang L. Low drug load, high retention mometasone furoate cream with Polyglyceryl - 3 oleate as a chemical enhancer: formulation development, in vivo and in vitro evaluation and molecular mechanisms. 2023 https://doi.org/10.21203/rs.3.rs-3390900/v1.

[2]Patil T.S., Gujarathi N.A., Aher A.A. et al. Recent advancements in topical anti-psoriatic nanostructured lipid carrier-based drug delivery. *Int J Mol Sci* 2023; 24; 2978.